


 Cite this: *RSC Adv.*, 2021, 11, 33661

DOI: 10.1039/d1ra90158c

[rsc.li/rsc-advances](https://rsc.li/rsc-advances)

## Correction: Comparative study of the extrinsic properties of poly(lactic acid)-based biocomposites filled with talc *versus* sustainable biocarbon

 Michael R. Snowdon,<sup>ab</sup> Feng Wu,<sup>b</sup> Amar K. Mohanty<sup>\*ab</sup> and Manjusri Misra<sup>\*ab</sup>

 Correction for 'Comparative study of the extrinsic properties of poly(lactic acid)-based biocomposites filled with talc *versus* sustainable biocarbon' by Michael R. Snowdon *et al.*, *RSC Adv.*, 2019, 9, 6752–6761, DOI: 10.1039/C9RA00034H.

The authors regret that the values given for oxygen and water vapor permeability in Table 1 were incorrect in the original article. The correct version of the table is shown here.

**Table 1** Oxygen and water vapor permeability of the PLA composites and their diffusion path length with tortuosity factors

| Sample                 | Oxygen permeability at 23 °C and 0% RH (cm <sup>3</sup> mm m <sup>-2</sup> day <sup>-1</sup> atm <sup>-1</sup> ) | Water vapor permeability at 38 °C and 100% RH (g mm m <sup>-2</sup> day <sup>-1</sup> ) | Total path of diffusing gas (μm) | Tortuosity factor |
|------------------------|--|---|----------------------------------|-------------------|
| PLA                    | 7.37 ± (0.39)  | 16.83 ± (0.69)  | 0.63                             | 1.00              |
| PLA/talc               | 5.66 ± (0.09)  | 12.50 ± (0.67)  | 0.78                             | 1.23              |
| PLA/BC                 | 8.50 ± (0.25)  | 19.58 ± (0.57)  | 0.64                             | 1.01              |
| PLA/BC <sub>24 h</sub> | 8.38 ± (0.17)  | 16.84 ± (0.27)  | 0.66                             | 1.04              |

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

<sup>a</sup>School of Engineering, Thornbrough Building, University of Guelph, 80 South Ring Rd E, Guelph, Ontario, N1G 1Y4, Canada. E-mail: mmisra@uoguelph.ca; mohanty@uoguelph.ca; snowdonm@uoguelph.ca

<sup>b</sup>Bioproducts Discovery & Development Centre (BDDC), Department of Plant Agriculture, Crop Science Building, University of Guelph, 117 Reynolds Walk, Guelph, Ontario, N1G 1Y4, Canada. E-mail: fengwu@uoguelph.ca

