Chemical Science

EDGE ARTICLE



Cite this: Chem. Sci., 2021, 12, 4825

All publication charges for this article have been paid for by the Royal Society of Chemistry

Received 15th December 2020 Accepted 15th February 2021 DOI: 10.1039/d0sc06843h

rsc.li/chemical-science

Introduction

Lithium silicate nanosheets with excellent capture capacity and kinetics with unprecedented stability for high-temperature CO₂ capture[†]

Rajesh Belgamwar,^a Ayan Maity,^a Tisita Das,^d Sudip Chakraborty,^b Chathakudath P. Vinod ^b^c and Vivek Polshettiwar ^b*^a

An excessive amount of CO₂ is the leading cause of climate change, and hence, its reduction in the Earth's atmosphere is critical to stop further degradation of the environment. Although a large body of work has been carried out for post-combustion low-temperature CO₂ capture, there are very few high temperature pre-combustion CO₂ capture processes. Lithium silicate (Li₄SiO₄), one of the best known high-temperature CO₂ capture sorbents, has two main challenges, moderate capture kinetics and poor sorbent stability. In this work, we have designed and synthesized lithium silicate nanosheets (LSNs), which showed high CO₂ capture capacity (35.3 wt% CO₂ capture using 60% CO₂ feed gas, close to the theoretical value) with ultra-fast kinetics and enhanced stability at 650 °C. Due to the nanosheet morphology of the LSNs, they provided a good external surface for CO₂ adsorption at every Li-site, yielding excellent CO₂ capture capacity. The nanosheet morphology of the LSNs allowed efficient CO₂ diffusion to ensure reaction with the entire sheet as well as providing extremely fast CO₂ capture kinetics $(0.22 \text{ g} \text{ g}^{-1} \text{ min}^{-1})$. Conventional lithium silicates are known to rapidly lose their capture capacity and kinetics within the first few cycles due to thick carbonate shell formation and also due to the sintering of sorbent particles; however, the LSNs were stable for at least 200 cycles without any loss in their capture capacity or kinetics. The LSNs neither formed a carbonate shell nor underwent sintering, allowing efficient adsorption-desorption cycling. We also proposed a new mechanism, a mixed-phase model, to explain the unique CO₂ capture behavior of the LSNs, using detailed (i) kinetics experiments for both adsorption and desorption steps, (ii) in situ diffuse reflectance infrared Fourier transform (DRIFT) spectroscopy measurements, (iii) depth-profiling X-ray photoelectron spectroscopy (XPS) of the sorbent after CO₂ capture and (iv) theoretical investigation through systematic electronic structure calculations within the framework of density functional theory (DFT) formalism.

Fossil fuels provide greater than 85% of the world's energy needs.¹ An excessive amount of CO_2 is the main cause of climate change. If the use of fossil fuel is to be continued in the coming years, the CO_2 emission needs to be dramatically reduced by developing sustainable sorbents to capture and separate CO_2 from various industrial processes. For CO_2 capture, in general, two protocols can be used, post-combustion and precombustion.^{2–4} Low-temperature sorbents (based on amines, silica, zeolites, carbon, and MOFs) are mainly used for postcombustion CO₂ capture from flue gas at low temperatures (25 to 75 °C), while high-temperature sorbents are specifically developed for pre-combustion capture between 500 and 700 °C.^{2–4} "Pre-combustion capture" is one of the most challenging but best ways to tackle climate change as CO₂ is captured during the process at high temperatures with ideally zero release into the environment.^{5–7} Pre-combustion capture, as CO₂ gets captured as soon as it is produced during the process without releasing it into the environment.^{5–7}

Although a large body of work has been carried out for postcombustion low-temperature CO_2 capture,² there are very few high temperature pre-combustion CO_2 capture processes. Lithium silicate (Li₄SiO₄) is one of the best high-temperature CO_2 capture sorbents due to its relatively high capture capacities as compared to other alkali metal-containing ceramics.⁵⁻⁷ Although lithium silicates display excellent CO_2 sorption



^aDepartment of Chemical Sciences, Tata Institute of Fundamental Research (TIFR), Mumbai, India. E-mail: vivekpol@tifr.res.in

^bMaterials Theory for Energy Scavenging (MATES) Lab, Department of Physics, Indian Institute of Technology, Simrol, Indore, India

^cCatalysis and Inorganic Chemistry Division, CSIR-National Chemical Laboratory (NCL), Pune, India

^dHarish-Chandra Research Institute, HBNI, Allahabad, Uttar Pradesh, India

[†] Electronic supplementary information (ESI) available: Detailed experimental, the effect of mole ratio, the effect of thermal treatment temperature and time, the effect of CO₂ flow, XPS data, and kinetic data. See DOI: 10.1039/d0sc06843h

Chemical Science

capabilities at high temperatures, they face two main limitations, slow capture kinetics and poor stability-recyclability of the sorbents.⁵⁻⁷ Formation of a lithium carbonate product layer limits CO₂ diffusion, thus limiting kinetic performance; second, sintering reduces the cycling stability necessary for practical application. Recently, nanowires of lithium silicates and lithium tungstate showed good kinetics of CO₂ capture.^{8,9} However, these nanowires were not stable against agglomeration/sintering during the high-temperature CO₂ adsorption– desorption process, with a loss of 50% of their capture performance (capacity and kinetics) in the first three cycles. Thus, there was a need for a sorbent that has the following properties: (i) high CO_2 capture at elevated temperatures (between 600 and 750 °C), (ii) faster rate of adsorption/desorption, and (iii) cycling stability for hundreds of CO_2 capture–release cycles.

In continuation of our work on CO_2 capture and conversion,¹⁰⁻¹³ here we report lithium silicate nanosheets (LSNs) as a high-temperature CO_2 sorbent. The LSNs showed a high CO_2



Fig. 1 (a and b) SEM images, (c) PXRD pattern, and (d) N_2 sorption isotherm of the LSNs; (e) CO_2 adsorption thermograms, (f) CO_2 capture kinetics in the first minute at 650 °C using 60% CO_2 for various cycles; (g) CO_2 capture by the LSNs (4-cycle activated) at various temperatures; (h) CO_2 capture capacity at 650 °C for feeds with various CO_2 concentrations.

capture capacity of 35.3 wt% CO₂ (96.18% efficiency, in comparison with the theoretical capacity of 36.7 wt%) and ultrafast kinetics (0.22 g g⁻¹ min⁻¹). Notably, the LSNs were stable even after 200 cycles without any loss in their capture capacity or kinetics.

Results and discussion

LSNs were synthesized using dendritic fibrous nanosilica (DFNS).12 The DFNS surface area is highly accessible by virtue of its fibrous nature instead of tubular pores like in MCM-41 and SBA-15.12 After several synthetic optimizations, in terms of lithium precursor, heating temperature and time (Tables S1 to S3[†]), the desired LSNs were prepared by thermal treatment of physically mixed DFNS and lithium nitrate with a Li : Si molar ratio of 4.66:1 at 650 °C for 6 h in air. Scanning electron microscopy (SEM) images indicated that the LSNs are made up of nanosheets randomly stacked on each other with overall sheet widths of a few microns (Fig. 1a and b). Powder X-ray diffraction (PXRD) of the LSNs showed the presence of Li₄SiO₄ as a major phase, with Li2SiO3 and Li2CO3 as minor phases (Fig. 1c). These impurities were due to the reaction of the LSNs with trace amounts of CO_2 present (~400 ppm) in the environment during LSN synthesis. Synthesis of the pure phase of Li_4SiO_4 was possible by using an inert atmosphere (Fig. S1⁺); however, since a small amount of minor phases did not affect the CO₂ performance of the LSNs, we chose sustainable synthesis conditions in an air environment. The N₂ sorption isotherm (Fig. 1d) displayed type IV characteristics with hysteresis and a low surface area of 8 m² g⁻¹.

The CO₂ capture performance of the LSNs was evaluated using thermogravimetric analysis (TGA). First, the CO₂ adsorption/desorption of the LSNs was studied at 650 °C using 60% CO₂ (balance nitrogen) with 25 mg of sorbent (Fig. 1e and f, and S2[†] for the effect of sorbent weight). Notably, we observed an increase in capture capacity from 0.277 to 0.353 g g^{-1} as well as initial kinetics from 0.06 to 0.22 g g^{-1} min⁻¹ up to the 4th cycle. The increase in capture capacity and kinetics up to the 4th cycle was due to systematic purification of the asprepared Li₄SiO₄, which had Li₂SiO₃, and Li₂CO₃ as minor phases. With every cycle of CO2 adsorption-desorption, these minor phases were converted to Li₄SiO₄ and at the 4th cycle, their concentrations were significantly reduced (Fig. 2a). The PXRD pattern indicated the reaction of Li₄SiO₄ with CO₂ to form Li₂SiO₃ and Li₂CO₃ during the adsorption step followed by the conversion of Li₂SiO₃ and Li₂CO₃ phases to Li₄SiO₄ during the CO_2 desorption step (eqn (1)). This process was reversible (Fig. 2a), which was the reason for the better cycling stability of the LSNs.

$$Li_4SiO_4 + CO_2 \rightleftharpoons Li_2SiO_3 + Li_2CO_3$$
(1)

The LSNs' CO_2 capture performance was then studied at different temperatures using a 4-cycle activated sample using 60% CO_2 with 25 mg of sorbent (Fig. 1g). The CO_2 sorption capacity first increased from 500 to 650 °C and then decreased

at 700 °C. At 500 °C, the diffusion process was kinetically controlled, and the diffusion barrier is the main reason for the low CO₂ sorption capacity. With the increase in temperature to 650 °C, the diffusion and chemisorption processes were accelerated and hence the CO₂ capture rate was much faster. However, at 700 °C, the desorption kinetics of CO₂ was faster than the adsorption kinetics, reducing the overall capture capacity and kinetics. Thus, 650 °C was found to be the optimized temperature in terms of CO₂ capture capacity. At this temperature, using these 4-cycle activated LSNs, the effect of CO₂ concentration was also studied, with 20, 30, 40, 50 and 60% CO₂, all of which (except 20% CO₂) showed good capture capacities and kinetics (Fig. 1h and S3⁺), indicating their usability in various pre-combustion processes where different amounts of CO₂ are generated. We then studied the effect of gas flow using 150, 100, and 50 mL min⁻¹ of 100% CO₂ (Fig. S4[†]). The LSNs showed good capture rates with all the flows, indicating their usability in various processes with different flows.

X-ray photoelectron spectroscopy (XPS) was performed to study the LSNs and how they change during CO₂ adsorptiondesorption steps (Fig. 2b). The XPS spectra contained two peaks for Li (1s) at binding energies (BEs) of \sim 54 eV and \sim 55.9 eV. The peak at ~ 54 eV was assigned to Li₄SiO₄ (major phase)¹⁴ as well as Li₂CO₃ (minor phase).¹⁵ Although their deconvolution was not possible due to their very close binding energy (BE), based on PXRD, this peak at \sim 54 eV was assigned mainly to Li₄SiO₄. The signal at \sim 55.9 eV was assigned to Li₂SiO₃.^{14,15} After CO₂ capture, in the adsorbed 4-cycle activated sample, the area under the peak of Li₂SiO₃ at ~55.9 eV increased due to the conversion of Li₄SiO₄ to Li₂SiO₃ and Li₂CO₃, as also observed in PXRD (Fig. 2a). The formation of Li₂CO₃ was observed with the signal at \sim 54 eV BE (overlapping with the Li₄SiO₄ signal), but clearly differentiable in PXRD. The Si (2p) spectra of the LSNs showed two Si signals, at BEs of \sim 101 eV for Li₄SiO₄ and \sim 102 eV for Li₂SiO₃ (Fig. 2a).^{14,15} After CO₂ adsorption, ideally, there should be only one Si site, as PXRD indicates the presence of Li₂SiO₃ and Li₂CO₃ only (Fig. 2a). However, we observed two signals, at \sim 102 and \sim 104 eV. This indicates that the signal at ~104 eV was for SiO₂.¹⁶

The LSNs' stability and cyclability were then studied and the results indicated that the LSNs could be used for at least 200 cycles without any loss in their capture capacity or kinetics (Fig. 3a). We compared the recyclability of the LSNs with that of the best lithium silicates reported in the literature (Fig. 3b and Table S4[†]). The LSNs were found to be stable and did not lose their capture capacity or kinetics during the adsorptiondesorption cycling. In general, conventional lithium silicates systematically lose their capture capacity with every cycle with a significant loss in the first few cycles (Fig. 3b);5-7,17-29 however, the LSNs were found to be stable even after 200 cycles. The LSNs were even better than one of the best recently reported sorbents, lithium silicate nanowires (NWs)⁸ (Fig. 3c). The NW sorbent lost more than 50% of its capture capacity, which fell from 0.35 to 0.15 g g^{-1} , in just four cycles, while the LSNs capture capacity (0.35 g s^{-1}) did not change even after 200 cycles. The kinetics of the NWs reduced to 0.1 g $m g^{-1}$ min $^{-1}$ in 4 cycles, while the LSNs kinetics remained at 0.22 g g^{-1}



Fig. 2 (a) PXRD pattern and (b) XPS spectra of lithium silicates after various CO₂ adsorption-desorption cycles.

 min^{-1} even after 200 cycles. Thus, we found that the LSNs outperform the NWs and other reported sorbents in terms of capture capacity and kinetics as well as cycling stability. Notably, the LSNs were even stable in the presence of a CO₂ feed containing water vapor (Fig. S5†).

For most of the reported Li_4SiO_4 , due to its dense morphology and large particle size (Table S4†), CO₂ capture took place mainly at the surface, while the interior surface cannot fully interact with CO₂, which limits the capture capacity of the conventional lithium silicate material. Also, as pore size



Fig. 3 (a) Stability and cyclability of the LSNs for 200 cycles of CO_2 adsorption–desorption, (b) comparison with various best-known lithium silicate sorbents, and (c) cycle-by-cycle comparison of the LSNs with lithium silicate nanowires (NWs)⁸ at 650 °C using 60% CO_2 .

has a critical impact on the CO_2 capture performance of Li_4SiO_4 ,⁵ due to the formation of Li_2SiO_3 and Li_2CO_3 , which have a higher molar volume than Li_4SiO_4 , the pores get blocked due to this volumetric expansion, causing further degradation in the sorbent's CO_2 capture performance (capacity, kinetics, and recyclability). Our synthesized sorbent LSNs, due to their thin sheets, provided a good external surface and allowed CO_2 diffusion to every Li-site without any hindrance. Although the LSNs aggregated after 4 cycles, these sheets did not undergo

sintering even after 200 cycles, possibly because they were covalently interlinked with each other between the sheets (Fig. S6 and S7†), and remained stable for 200 cycles. This was the reason for the excellent CO_2 sorption performance of this sorbent (with CO_2 capture capacity close to the theoretical value).

According to the double-shell model⁵ (Fig. 4, left), first Li_4SiO_4 reacts with CO_2 at the sorbent surface to generate an external shell made up of Li_2CO_3 . Once this shell is formed, the



Fig. 4 Proposed mixed-phase vs. double shell model for CO₂ adsorption-desorption.

diffusion of CO_2 and Li^+ through this external shell dictates the sorbent performance. The formation of thick carbonate shells was the main reason for the degradation of capture performance for the conventional lithium silicates.⁵ In the case of the LSNs, the sheet thickness is a few nanometers, and hence CO_2 and Li^+ can easily diffuse across the entire sheet, and CO_2 reacts with Li^+ without the formation of the external shell. The rate of the CO_2 capture is generally limited by the diffusion of CO_2 and Li^+ through the external shell; however, since no such shell was formed in the LSNs, they showed extremely fast CO_2 capture kinetics (0.22 g g⁻¹ min⁻¹). Based on these observations, we propose that the LSNs adsorb/desorb CO_2 *via* a mixed-phase model and not the double-shell model (Fig. 4).

To study this process and understand the effect on CO_2 chemisorption and Li^+ diffusion, isotherms at different temperatures were fitted to the double-exponential equation (eqn (2); Fig. S8⁺)

$$y = A \exp(-k_1 x) + B \exp(-k_2 x) + C$$
(2)

 Table 1
 Kinetic parameters obtained from the LSNs' adsorption

 isotherms at different temperatures

$T(^{\circ}C)$	$k_1 (s^{-1})$	$k_2 (s^{-1})$	R^2
500	0.003510	0.00093	0.99878
550	0.003783	0.00028	0.99943
600	0.006214	0.00048	0.99771
650	0.065421	0.00164	0.99068
700	0.001788	0.00015	0.99960

where *y* represents the CO₂ adsorbed in wt%, *x* is the time required to capture CO₂, and k_1 and k_2 are the exponential parameters for CO₂ chemisorption and lithium diffusion processes, respectively. *A* and *B* are constants, and *C* is the *y*-axis intercept.

Table 1 summarizes the kinetic parameters obtained after this fitting from the LSNs' CO₂ adsorption isotherms (Fig. S4[†]). At the optimized sorption temperature, 650 °C, k_1 was 0.065421 s^{-1} , far better than the reported values for conventional silicates,⁵⁻⁷ indicating extremely fast CO₂ chemisorption by interaction with Li-ions on the surface of the LSNs (Fig. 4). This confirms the role of nanosheet morphology, which allowed more external surface and less core, causing efficient CO₂ adsorption and indicating the mixed-phase model of CO2 capture. In conventional silicates, in the 2nd step, the Li-ion has to diffuse through carbonate shells (as per the double-shell model, Fig. 4), and this slows down the CO₂ capture kinetics (k_2) . In the case of LSNs, k_2 was 0.00164 s⁻¹, similar to reported values. However, in the case of LSNs, more than 90% of the total CO_2 capture happened in the first 3 minutes, indicating that k_1 (CO₂ chemisorption) is the rate-limiting step and not k_2 (Li⁺ diffusion). This again indicates that the LSNs' CO₂ capture follows the proposed mixed-phase model.

In order to gain more insight into the mixed-phase model, we compared the LSN sorbent (prepared from DFNS) with a conventional sorbent prepared from Stöber silica, named Stöber lithium silicate (SLS), which is known to follow the double-shell model of CO_2 adsorption-desorption. When we



Fig. 5 CO₂ capture by the LSNs and SLS at 650 °C using 60% CO₂: (a) CO₂ adsorption thermograms of the LSNs and SLS; (b) CO₂ capture kinetics in the first five minutes; (c) CO₂ desorption kinetics.

compared the CO₂ capture performance of the LSNs and SLS using feed with various CO₂ concentrations, in all cases, the LSNs showed far better CO₂ capture capacity and kinetics as compared to SLS (Fig. S9[†]). For further comparison, we chose a feed with a 60:40 ratio of $CO_2: N_2$ and observed that in 2 h, the LSNs capture 35.3 wt% CO₂ (22.04 wt% in the first minute) while SLS captures only 26.2 wt% (16.49 wt% in the first minute) (Fig. 5a). The LSNs showed faster kinetics of 5.8 wt% per minute, compared to the 3.1 wt% per minute for SLS (Fig. 5b), indicating faster Li diffusion throughout the LSNs, supporting the mixed-phase model. This model should also significantly affect desorption kinetics, as kinetics should be faster in the case of a mixed-phase model compared to the double-shell model, which is known for slow desorption due to the thick shell. The LSNs showed very fast desorption, 6.8 wt% per minute, while SLS desorbed 5.1 wt% per minute with respect to their total capture capacity. A similar trend was observed under all three flow conditions (Fig. S10[†]). This confirms the presence of a mixed-phase model in the LSNs but the double-shell model in SLS.

If the proposed mixed-phase model is correct, CO_2 chemisorption should be a rate-determining step and not lithium-ion diffusion. The extremely high value of k_1 and low value of k_2 (in Table 1) clearly indicate that chemisorption is a major path of CO_2 adsorption, while the lithium-ion diffusion path is insignificant. We then fitted the adsorption kinetics to a single exponential equation (eqn (S1)[†]) and found that k_1 was 0.00285 s⁻¹ for the LSNs and 0.00093 s⁻¹ for SLS (Fig. S11 and Table S5[†]). In addition to adsorption kinetics, desorption kinetics should also be accelerated by the mixed-phase model. We hence fitted the desorption (Fig. 5c) to the single exponential equation (Fig. S12[†]) and found that k_1 was 0.002027 s⁻¹ for the LSNs as compared to only 0.001652 s⁻¹ for SLS. This also confirms the presence of a mixed-phase model in the case of LSNs.

To gain mechanistic insights into the CO_2 capture process of CO_2 adsorption on the Li_4SiO_4 surface and the formation of Li_2CO_3 and Li_2SiO_3 , we carried out *in situ* diffuse reflectance infrared Fourier transform (DRIFT) spectroscopy measurements of the LSNs under similar CO_2 adsorption and desorption conditions. For the adsorption study, in a reactor chamber with a heater and gas flow controller, the LSNs were treated with CO_2 (60%) at 650 °C, while for the desorption study, the LSNs, after CO_2 treatment, were treated with N_2 at 650 °C and an IR spectrum was recorded at various time intervals. The band at 2342 cm⁻¹ was assigned to the linearly chemisorbed CO_2 molecule on the lithium silicate surface (Fig. S13a and b⁺),³⁰ while the band in the region of 3500 to 3900 cm⁻¹ was assigned to Si–OH¹⁰ of lithium silicates (Fig. S13c and d⁺).

The intensity of the band in the region of $650-750 \text{ cm}^{-1}$, assigned to the stretching vibration of Si–O–Si of the SiO₃ chain present in Li₂SiO₃ (ref. ³¹), increased with time (Fig. 6a) as the LSNs on exposure to CO₂ (adsorption step) converted to Li₂SiO₃



Fig. 6 In situ DRIFT study of CO_2 adsorption – desorption using the LSNs and SLS at 650 °C. FTIR spectra of LSN (a and b) adsorption and (c and d) desorption steps. Adsorption is by 60% CO_2 while desorption is by 100% N_2 .

and Li₂CO₃. When CO₂ was replaced by a N₂ flow (desorption step), the intensity of these bands decreased with time (Fig. 6b), indicating that Li₂SiO₃ and Li₂CO₃ converted back into Li₄SiO₄. The desorption took place in just 240 s (4 minutes), and such fast desorption indicates the mixed-phase model, as the double-shell model had very slow desorption kinetics. Along similar lines, the intensity of the band in the region of 1300–1600 cm⁻¹, assigned to the stretching vibration of C–O in the carbonate ion (CO_3^{-2-}) present in Li₂CO₃ (ref. ³²), increased with time (Fig. 6c) as the LSNs on exposure to CO₂ (adsorption step) converted to Li₂SiO₃ and Li₂CO₃. During the desorption (Fig. 6d), this signal intensity decreased with time. Since complete disappearance was not observed, the as-synthesized LSNs have the impurity of lithium carbonate.

To further study the proposed mixed-phase model of CO_2 adsorption-desorption, an XPS depth-profiling study of the LSNs was carried out by etching at various depths of the LSN sample after the CO_2 adsorption step (Fig. 7). If it is a conventional double-shell model, one should see lithium carbonate only at the surface (and not in the core) in XPS, while if it is the proposed mixed-phase model, lithium carbonate should be present at the surface as well as inside the core. The XPS depth profile of the LSN sample after CO_2 adsorption is shown in Fig. S14.† We calculated the area under the peak for Li 1s corresponding to Li₂SiO₃ and Li₂CO₃ (Fig. 7a) and observed that at all depths from 0 to 255 nm, there was a presence of both Li₂CO₃ and Li₂SiO₃, clearly confirming the mixed-phase model. This was further confirmed by comparing the area under the

peak for Si 2p and C 1s at various depths (Fig. 7b and c) and notably, Si 2p and C 1s also followed the same trend as Li 1s, confirming the presence of $\rm Li_2CO_3$ and $\rm Li_2SiO_3$ across the LSNs. This further supports the proposed mixed-phase model of $\rm CO_2$ adsorption and desorption by the LSNs.

In order to gain further insight into the adsorption/desorption kinetics of the LSN sorbent, a theoretical investigation was carried out through systematic electronic structure calculations within the framework of density functional theory (DFT) formalism. In our DFT modeling, we primarily highlighted the correlation between adsorption characteristics and the corresponding charge transfer mechanism for the sorbent and adsorbate along with the adsorbate induced work function change, which are immensely instrumental fundamental parameters for any surface investigation. We analyzed the electronic density of states (DOS) of the composite (CO₂ adsorbed on the LSNs) as well as the individual systems after and before the adsorption process to elucidate the salient features of the electronic structures, as depicted in Fig. 8. The middle panel of Fig. 8a illustrates the total DOS of Li₄SiO₄ before CO₂ adsorption, exhibiting a wide bandgap semiconducting nature. But as soon as CO2 gets adsorbed on top of the LSNs, finite states are found to emerge near the Fermi level $(E_{\rm F})$ due to the interaction between Li₄SiO₄ and the CO₂ molecule, as shown in the top panel of Fig. 8a. Interestingly, we observed that the density of states corresponding to an isolated CO_2 molecule (as depicted in the bottom panel of Fig. 8a) has been shifted substantially in the vicinity of $E_{\rm F}$ under the



Fig. 7 Area under the peak of (a) Li 1s for Li₂SiO₃ and Li₂CO₃, and (b) Si 2p and (c) C 1s of the LSN sample in the CO₂ adsorbed state, from XPS fitting (Fig. S13†) at different etching depths.



Fig. 8 (a) Density of states plot for CO₂ adsorbed on top of Li₄SiO₄. The top panel illustrates the total DOS of the composite systems after adsorption, while the middle and bottom panels represent the DOS of the isolated Li₄SiO₄ sorbent and CO₂ molecule before adsorption. (b) Charge density distribution between a Li₄SiO₄ nanosheet and CO₂ molecule. The accumulation and depletion of charge are denoted by yellow and blue color, respectively. The iso-surface value was set to 0.0003 e⁻ Å⁻³. (c) Work function and DFT total energies in the bulk form of reactants and products.

influence of the LSN surface, which is also manifested through the charge transfer mechanism representation in the subsequent section. It is worth mentioning that we observed the finite density of states appear near the Fermi region after adsorption in the composite system. This reveals the fact that the adsorbate in the form of CO₂ is tuning the bandgap of the surface, which is Li_4SiO_4 , which has also been reflected in the substantial charge transfer process. As we investigated the interaction of an incoming CO₂ with the Li_4SiO_4 surface, the noticeable change in the electronic structure through the appearance of finite states after adsorption signifies the fact that CO₂ is chemisorbed on the Li_4SiO_4 surface. The composite system represents the lefthand side of the reaction mechanism of CO₂ adsorption by Li_4SiO_4 before converting to the product form, while our

theoretical analysis focused on the surface adsorption, whereas in the experimental section, the CO_2 adsorption occurred within the nanosheets of Li_4SiO_4 .

The charge density distribution is illustrated in Fig. 8b, where it is observed that the charge is mainly accumulated around the Li–O bond region, indicating a valuable observation and validation of this work, as reflected in the covalent bond formation between the LSN surface and CO_2 . This particular theoretical finding has shed light not only on the CO_2 capture but also on the subsequent desorption possibility, as found in the experimental outcome. Bader charge analysis indicates that $0.85 \text{ e}^- \text{ Å}^{-3}$ (amount of charge) is transferred from a Li atom of LSNs to an O atom of CO_2 during the adsorption process. During the electron transfer process from the Li atom to the O

atom of CO_2 , covalent bond formation occurred, which eventually helps in the CO_2 adsorption/capture. This particular covalent bond formation also supports the adsorption/desorption process, as desorption would be favorable in the absence of a strong ionic bond between the surface and adsorbate. This is due to the higher electronegativity of oxygen atoms as compared to lithium and carbon, as both of them share their electrons with oxygen, which leads to charge depletion around the lithium and carbon atoms.

The work function values (Fig. 8c) for Li₂SiO₃ and Li₂CO₃ are higher as compared to those of both LSNs and LSN-CO₂ composite systems, suggesting that a larger amount of energy is required to extract an electron from Li₂SiO₃ and Li₂CO₃ surfaces as compared to the Li₄SiO₄ system. Therefore, we could infer the favorable capture of a CO₂ molecule by the LSNs, while the subsequent desorption of CO2 had been reflected in the previously discussed Bader charge analysis. This observation has also been verified theoretically from the reaction energy value of the reaction (Li₄SiO₄ + CO₂ \rightleftharpoons Li₂SiO₃ + Li₂CO₃), which has been calculated as -1.36 eV from DFT total energy calculations. Here, the negative reaction energy signifies the exothermic, spontaneous CO_2 capture process. Thus, we have theoretically validated the experimental observation of not only the CO₂ capture process but also the CO₂ desorption. The adsorption of CO₂ has also been confirmed from the elongated C-O bond being closer to the LSN surface as compared to that in the preadsorbed state, while the corresponding adsorption energy is found to be -1.54 eV.

The cycling stability of the sorbents is determined by the efficiency of CO₂ desorption, which is known to be difficult from an interior (core) portion of the double-shell model in conventional lithium silicates, causing a reduction in CO2 capture performances with every cycle for reported lithium silicates (Fig. 3b).⁵ In addition to the formation of thick carbonate shells, the sintering of sorbent particles was another reason for the fast decline in capture capacity and kinetics in conventional silicates.8,9 In the LSN sorbent, due to the absence of any carbonate shell, CO₂ desorption was very efficient (nearly 100%, Fig. 3a). This allowed efficient regeneration and reuse of the LSNs, and even after 200 cycles, they remained active, without even a minute loss of CO₂ capture capacity or kinetics. Also, although the sheets of LSNs have nano-dimensions, they are stacked and their overall particle size is in microns, making them sinterproof and stable. Thus, the LSN sorbent neither generated the carbonate shell nor underwent sintering. This made CO2 adsorption-desorption a completely reversible process and hence the LSNs were stable and recyclable even after 200 cycles.

Conclusions

In this work, we synthesized lithium silicate nanosheets by solid-state thermal treatment of DFNS and lithium nitrate. The LSNs showed CO_2 capture capacity close to the theoretical value, with a high rate of CO_2 adsorption. The nanosheet morphology of the LSNs provided a good external surface for efficient CO_2 interaction with every Li-site, yielding high CO_2 capture capacity (35.3 wt% CO_2 using 60% CO_2 feed gas). The

rate of CO₂ capture is generally limited by the diffusion of CO₂ and Li⁺ through the external carbonate shell, but since no such shell was formed in the LSNs, they showed extremely fast CO_2 capture kinetics (0.22 g g⁻¹ min⁻¹). Notably, the LSNs show dramatic stability (even after 200 cycles without any loss in their capture capacity or kinetics), as compared to reported sorbents, which are known to systematically lose their capture capacity significantly. The LSN sorbent neither formed a carbonate shell nor underwent sintering, causing efficient adsorption-desorption with no loss in capture performance. Thus, the LSNs have all three desirable properties (high capture capacity, fast kinetics and cycling stability for more than 200 cycles) of a CO₂ sorbent. Various kinetics and spectroscopic studies (XPD depth profiling and in situ DRIFT) were performed to prove the proposed mechanism of the mixedphase model, which explained the unique CO₂ capture behavior of lithium silicate nanosheets in terms of good capture kinetics and prolonged stability.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the Department of Atomic Energy (DAE), Government of India (under project no. R&D-TIFR-RTI4003). We acknowledge the use of the EM and XRD facilities of TIFR, Mumbai.

References

- 1 H. Yang, Z. Xu, M. Fan, R. Gupta, R. B. Slimane, A. E. Bland and I. Wright, Progress in carbon dioxide separation and capture: a review, *J. Environ. Sci.*, 2008, **20**, 14–27.
- 2 J. G. Vitillo, B. Smit and L. Gagliardi, Introduction: Carbon capture and separation, *Chem. Rev.*, 2017, **117**, 9521–9523.
- 3 V. O. Özçelik, K. Gong and C. E. White, Highly surface-active $Ca(OH)_2$ monolayer as a CO_2 capture material, *Nano Lett.*, 2018, **18**, 1786–1793.
- 4 M. Bui, *et al.*, Carbon capture and storage (CCS): the way forward, *Energy Environ. Sci.*, 2018, **11**, 1062–1176.
- 5 Y. Zhang, Y. Gao, H. Pfeiffer, B. Louis, L. Sun, D. O'Hare and Q. Wang, Recent advances in lithium containing ceramic based sorbents for high-temperature CO₂ capture, *J. Mater. Chem. A*, 2019, 7, 7962–8005.
- 6 Y. Hu, W. Liu, Y. Yang, M. Qu and H. Li, CO_2 capture by Li_4SiO_4 sorbents and their applications: current developments and new trends, *Chem. Eng. J.*, 2019, 359, 604–625.
- 7 M. Kato, S. Yoshikawa and K. Nakagawa, Carbon dioxide absorption by lithium orthosilicate in a wide range of temperature and carbon dioxide concentrations, *J. Mater. Sci. Lett.*, 2002, **21**, 485–487.
- 8 A. Nambo, J. He, T. Q. Nguyen, V. Atla, T. Druffel and M. Sunkara, Ultrafast carbon dioxide sorption kinetics

using lithium silicate nanowires, *Nano Lett.*, 2017, 17, 3327–3333.

- 9 M. Z. Akram, V. Atla, A. Nambo, B. P. Ajayi, J. B. Jasinski, J. He, J. R. Gong and M. Sunkara, Low-temperature and fast kinetics for CO_2 sorption using Li_6WO_6 nanowires, *Nano Lett.*, 2018, **18**, 4891–4899.
- 10 A. K. Mishra, R. Belgamwar, R. Jana, A. Datta and V. Polshettiwar, Defects in nanosilica catalytically convert CO₂ to methane without any metal and ligand, *Proc. Natl. Acad. Sci. U. S. A.*, 2020, 24, 6383–6390.
- 11 M. Dhiman, A. Maity, A. Das, R. Belgamwar, B. Chalke, Y. Lee, K. Sim, J.-W. Nam and V. Polshettiwar, Plasmonic colloidosomes of black gold for solar energy harvesting and hotspots directed catalysis for CO₂ to fuel conversion, *Chem. Sci.*, 2019, **10**, 6594–6603.
- 12 A. Maity, R. Belgamwar and V. Polshettiwar, Facile synthesis protocol to tune size, textural properties and fiber density of dendritic fibrous nanosilica (DFNS): Applications in catalysis and CO₂ capture, *Nat. Protoc.*, 2019, **14**, 2177–2204.
- 13 A. Maity, S. Chaudhari, J. J. Titman and V. Polshettiwar, Catalytic nanosponges of acidic aluminosilicates for plastic degradation and CO₂ to fuel conversion, *Nat. Commun.*, 2020, **11**, 3828.
- 14 P. V. Korake and A. G. Gaikwad, Capture of carbon dioxide over porous solid adsorbents lithium silicate, lithium aluminate and magnesium aluminate at pre-combustion temperatures, *Front. Chem. Sci. Eng.*, 2011, 5, 215–226.
- 15 J. F. Moulder, W. F. Stickle, P. E. Sobol and K. D. Bomben, *Handbook of X-ray photoelectron spectroscopy*, ed. J. Chastain, Perkin-Elmer Corporation Physical Electronics Division, 1992, pp. 34–35.
- 16 A. Kaur, P. Chahal and T. Hogan, Selective Fabrication of SiC/Si Diodes by Excimer Laser under Ambient Conditions, *IEEE Electron Device Lett.*, 2016, 37, 142–145.
- 17 H. Kim, H. D. Jang and M. Choi, Facile synthesis of macroporous Li₄SiO₄ with remarkably enhanced CO₂ adsorption kinetics, *Chem. Eng. J.*, 2015, **280**, 132–137.
- 18 M. T. Izquierdo, A. Turan, S. Garcia and M. M. Maroto-Valer, Optimization of Li_4SiO_4 synthesis conditions by a solid state method for maximum CO₂ capture at high temperature, *J. Mater. Chem. A*, 2018, **6**, 3249–3257.
- 19 P. V. Subha, B. N. Nair, P. Hareesh, A. P. Mohamed, T. Yamaguchi, K. G. K. Warrier and U. S. Hareesh, Enhanced CO_2 absorption kinetics in lithium silicate platelets synthesized by a sol-gel approach, *J. Mater. Chem. A*, 2014, **2**, 12792–12798.
- 20 P. V. Subha, B. N. Nair, A. P. Mohamed, G. M. Anilkumar,K. G. K. Warrier, T. Yamaguchi and U. S. Hareesh,Morphologically and compositionally tuned lithium

silicate nanorods as high-performance carbon dioxide sorbents, *J. Mater. Chem. A*, 2016, **4**, 16928–16935.

- 21 N. A. Zubbri, A. R. Mohamed and M. Mohammadi, Parametric study and effect of calcination and carbonation conditions on the CO_2 capture performance of lithium orthosilicate sorbent, *Chin. J. Chem. Eng.*, 2018, 26, 631–641.
- 22 K. Wang, X. Wang, P. Zhao and X. Guo, High-temperature capture of CO₂ on lithium based sorbents prepared by a water-based sol-gel technique, *Chem. Eng. Technol.*, 2014, 37, 1552–1558.
- 23 M. E. Bretado, V. Guzman Velderrain, D. Lardizabal Gutierrez, V. Collins-Martinez and A. L. Ortiz, A new synthesis route to Li_4SiO_4 as CO_2 catalytic/sorbent, *Catal. Today*, 2005, **4**, 863–867.
- 24 L. Ortiz, M. A. E. Bretado, V. G. Velderrain, M. M. Zaragoza, J. S. Gutierrez, D. L. Gutierrez and V. Collins-Martinez, Experimental and modeling kinetic study of the CO_2 absorption by Li₄SiO₄, *Int. J. Hydrogen Energy*, 2014, **39**, 16656–16666.
- 25 S. Shan, S. Li, Q. Jia, L. Jiang, Y. Wang and J. Peng, Impregnation precipitation preparation and kinetic analysis of Li₄SiO₄-based sorbents with fast CO₂ adsorption rate, *Ind. Eng. Chem. Res.*, 2013, **52**, 6941–6945.
- 26 X. Yang, W. Liu, J. Sun, Y. Hu, W. Wang, H. Chen, Y. Zhang, X. Li and M. Xu, Preparation of novel Li₄SiO₄ sorbents with superior performance at low CO₂ concentration, *ChemSusChem*, 2016, 9, 1607–1613.
- 27 Y. Hu, W. Liu, Y. Yang, X. Tong, Q. Chen and Z. Zhou, Synthesis of highly efficient, structurally improved Li_4SiO_4 sorbents for high-temperature CO_2 capture, *Ceram. Int.*, 2018, 44, 16668–16677.
- 28 G. J. Rao, R. Mazumder, S. Bhattacharyya and P. Chaudhuri, Synthesis, CO_2 absorption property and densification of Li_4SiO_4 powder by glycine-nitrate solution combustion method and its comparison with solid state method, *J. Alloys Compd.*, 2017, **725**, 461–471.
- 29 Y. Hu, W. Liu, Z. Zhou and Y. Yang, Preparation of Li_4SiO_4 sorbents for carbon dioxide capture *via* a spray-drying technique, *Energy Fuels*, 2018, **32**, 4521–4527.
- 30 J. A. Lercher, C. Colombier and H. Noller, Acid-base properties of alumina-magnesia mixed oxides. Part 4. Infrared study of adsorption of carbon dioxide, *J. Chem. Soc., Faraday Trans.* 1, 1984, 80, 949–959.
- 31 M. L. Grassoa, P. Arneodo Larochettea and F. C. Gennari, CO₂ capture properties of Li₄SiO₄ after aging in air at room temperature, *J. CO₂ Util.*, 2020, **38**, 232–240.
- 32 K. Coenen, F. Gallucci, B. Mezari, E. Hensen and M. V. Annaland, An *in situ* IR study on the adsorption of CO₂ and H₂O on hydrotalcites, *J. CO₂ Util.*, 2018, **24**, 228–239.