

Cite this: *Chem. Sci.*, 2021, 12, 4981

All publication charges for this article have been paid for by the Royal Society of Chemistry

Received 8th January 2021  
Accepted 19th February 2021

DOI: 10.1039/d1sc00127b

rsc.li/chemical-science

# Light-induced assembly and disassembly of polymers with Pd<sub>n</sub>L<sub>2n</sub>-type network junctions†

Ru-Jin Li, Cristian Pezzato, Cesare Berton and Kay Severin\*

Polymers containing Pd<sub>n</sub>L<sub>2n</sub> complexes as network junctions were obtained by reaction of poly(ethylene glycol)-linked N-donor ligands with Pd<sup>2+</sup>. The addition of a metastable state photoacid renders the networks light sensitive, and gel–sol transitions can be achieved by irradiation with light. The inverse process, a light-induced sol–gel transition, was realized by using a molecularly defined Pd complex as an acid-sensitive reservoir for Pd<sup>2+</sup>. Upon irradiation, Pd<sup>2+</sup> ions are released, allowing the formation of an acid-resistant polymer network. Both the gel–sol and the sol–gel transitions are reversed in the dark.

## Introduction

Polymer networks can be obtained by covalent interconnection of discrete metal–organic assemblies (macrocycles or cages) with organic linkers.<sup>1,2</sup> Two main synthetic strategies have been explored in this context: (a) the post-synthetic cross-linking of assemblies featuring reactive sites/groups in their periphery,<sup>3–7</sup> and (b) the utilization of polymer-linked ligands during the self-assembly process.<sup>8–11</sup> The incorporation of metal-based assemblies into polymer networks can lead to materials with interesting properties. For example, a hydrogel containing tetranuclear Fe cages was found to display sorption properties, which reflect the host–guest chemistry of the Fe cage.<sup>8</sup> Similarly, by cross-linking of porous Rh cages, it was possible to obtain materials with permanent porosity.<sup>3</sup> The utilization of cages as nodes in polymer networks is also interesting in terms of network topology, because cage junctions can act as highly connected nodes.<sup>11</sup> Another noteworthy feature of metal-based junctions is the fact that they can be altered or cleaved with appropriate stimuli.<sup>8–10</sup> Light is a particularly interesting stimulus, because it allows remote manipulation with high spatial and temporal control.<sup>12</sup> First studies about light-induced modifications of cage-containing polymer networks were recently published by Johnson and co-workers. They have shown that networks containing Cu<sub>24</sub>L<sub>24</sub>-type cages can be cleaved by photochemical reduction of the Cu(II) centers to Cu(I), resulting in a gel–sol transition.<sup>9</sup> The inverse process could be induced by re-oxidation with O<sub>2</sub>. Furthermore, they have reported a system, where irradiation allows converting macrocyclic Pd<sub>3</sub>L<sub>6</sub> junctions reversibly into Pd<sub>24</sub>L<sub>48</sub> cage junctions.<sup>10</sup> The light sensitivity was achieved by using polymeric


ligands containing photochromic dithienylethene groups. Below, we describe a new approach for rendering Pd-based polymer networks photosensitive. Importantly, our approach allows both the light-induced destruction of polymer networks and the light-induced formation of polymer networks without accumulation of ‘chemical waste’.<sup>13</sup>

## Results and discussion

The study described herein was inspired by our recent observation<sup>14</sup> that the assembly of certain metal–organic cages can be controlled with light if the merocyanine-based photoacid PAH<sup>15</sup> (Scheme 1) is added to the mixture.

Upon irradiation with blue light, PAH undergoes a ring-closure reaction, liberating a proton.<sup>16</sup> The increased acidity can lead to the disassembly of metal–organic cages if they contain acid-sensitive metal–ligand bonds. Importantly, cages containing more basic ligands display an increased susceptibility for an acid-induced cleavage.<sup>17</sup> In the dark, the process is reversed, and metal–ligand interactions are re-established.

In order to investigate if a photoacid can be used to control the assembly and disassembly of cage- and macrocycle-



Scheme 1 The photoacid PAH allows controlling the assembly of metal–organic cages.

Institut des Sciences et Ingénierie Chimiques, École Polytechnique Fédérale de Lausanne (EPFL), 1015 Lausanne, Switzerland. E-mail: kay.severin@epfl.ch


† Electronic supplementary information (ESI) available: Containing synthetic procedures and experimental details. See DOI: 10.1039/d1sc00127b



containing polymer networks, we have prepared the tetrapotic N-donor ligands **L1**–**L4** (Scheme 2). All ligands feature a poly(ethylene glycol) spacer with an average molecular weight of  $M_n = 4600$ . The design of these ligands was inspired by work of Johnson and co-workers, who have used structural analogues of **L2** and **L3** for the assembly of networks with  $\text{Pd}_2\text{L}_4$  and  $\text{Pd}_{12}\text{L}_{24}$  cage junctions.<sup>11b,c</sup> Ligand **L1** features additional alkynyl spacers, which renders the terminal 3-pyridyl group less basic than the pyridyl groups of **L2** and **L3**. Ligand **L4**, on the other hand, shows more basic imidazolyl donor groups (for details, see the ESI†).

The geometry of the terminal pyridyl groups of **L1** favors the formation of  $\text{Pd}_2\text{L}_4$ -type metal–organic cages.<sup>18</sup> Upon mixing of  $[\text{Pd}(\text{CH}_3\text{CN})_4](\text{BF}_4)_2$  (1 equiv.) with **L1** (1 equiv.) in acetonitrile, an opaque gel was immediately obtained. The mixture was then tempered at 70 °C for 4 h to ensure the formation of a polymer network (**P1**) with intact  $\text{Pd}_2\text{L}_4$  junctions. The gels **P2**–**P4** were prepared in an analogous fashion. Based on literature reports<sup>19–21</sup> and our own control experiments (see the ESI†), we expected the presence of  $\text{Pd}_2\text{L}_4$  links with some  $\text{Pd}_2\text{L}_3\text{X}_2$  defects<sup>22,23</sup> for **P2**,  $\text{Pd}_{12}\text{L}_{24}$  cage junctions for **P3**, and a mixture of macrocyclic  $\text{Pd}_3\text{L}_6$  and  $\text{Pd}_4\text{L}_8$  junctions for **P4**.

The polymers **P1**–**P4** were characterized by NMR spectroscopy, scanning electron microscopy (SEM), and rheology measurements (for details, see ESI†). Selected data are depicted in Fig. 1. The  $^1\text{H}$  magic angle spinning (MAS) NMR spectrum of **P1** shows six broad signals in the aromatic region, which are shifted downfield with respect to those of **L1** (Fig. 1a). It was possible to obtain a standard solution-based  $^1\text{H}$  NMR spectrum of **P1** when the reaction between **L1** and  $[\text{Pd}(\text{CH}_3\text{CN})_4](\text{BF}_4)_2$  was performed under dilute conditions. The resulting spectrum was similar to what was obtained for the gel by MAS NMR. The SEM image of dried **P1** shows a three-dimensional cross-linked structure (Fig. 1b). Rheology measurements were used to assess the mechanical properties of **P1**–**P4**. The storage modulus ( $G'$ ) increases in the order  $\text{P2} < \text{P1} < \text{P3} < \text{P4}$ . Two factors are expected to contribute to the observed differences:



Scheme 2 Polymers **P1**–**P4** with  $\text{Pd}_n\text{L}_{2n}$ -type network junctions are formed upon mixture of the N-donor ligands **L1**–**L4** with  $[\text{Pd}(\text{CH}_3\text{CN})_4](\text{BF}_4)_2$  in  $\text{CH}_3\text{CN}$ .




Fig. 1 (a) Aromatic region of the  $^1\text{H}$  NMR spectra (400 MHz,  $\text{CD}_3\text{CN}$ ) of **L1** (bottom), **P1** in dilute solution (middle), and  $^1\text{H}$  MAS NMR spectrum of gel **P1** (top); (b) SEM image of **P1**; (c) rheology data for **P1**–**P4**.

the cross-link density,<sup>10,11</sup> and the strength of the metal–ligand bond. The latter is related to the basicity of the ligands. An alternative measure for the donor strengths of a ligand is the Huynh Electronic Parameter (HEP).<sup>24</sup> We have determined the HEP parameter for close analogues of **L1**–**L4** (lacking the polymer linker), and the data confirmed that the relative donor capability of the ligands is in line with the ligand basicity (see the ESI†). The high  $G'$  value observed for **P4** is probably a reflection of the strong Pd–N bonds in the  $\text{Pd}_3\text{L}_6$  and  $\text{Pd}_4\text{L}_8$  assemblies. On the other hand, the donor strength of the ligand can be compensated by other factors (e.g. anion effects),<sup>23</sup> as evidenced by the higher  $G'$  value of **P1** when compared to what is found for **P2**.

The acid sensitivity of **P1**–**P4** was examined with trifluoroacetic acid (TFA). After addition of TFA (4 equiv. per N-donor group) and heating at 70 °C for 1 h, a gel–sol transition was observed for **P2**–**P4**, but not for **P1**. The higher acid resistance of **P1** is likely related to the low basicity of **L1**. Having established that acid-induced gel–sol transitions are possible, we subsequently performed test experiments with photoacid **PAH**. Unfortunately, **PAH** was not sufficiently soluble in  $\text{CH}_3\text{CN}$  to perform photoswitching experiments. Therefore, we have prepared the new photoacid **PAH'**( $\text{BF}_4$ ) featuring a neutral  $-(\text{CH}_2)_2\text{OH}$  side chain instead of the anionic  $-(\text{CH}_2)_3\text{SO}_3^-$  side chain of **PAH** (Fig. 2a). **PAH'**( $\text{BF}_4$ ) turned out to be soluble in  $\text{CH}_3\text{CN}$ .

An excess of **PAH'**( $\text{BF}_4$ ) was added to the respective gel ( $\geq 2$  equiv. per donor group), and the mixture was homogenized by agitation with a vortex mixer. When the samples were irradiated with blue light (456 nm) for 1 h, we observed a similar behavior as for TFA additions: all gels were transformed to solutions except **P1**. The gel–sol transition could be reversed by heating the solutions in the dark for 2 h. The cycle was repeated another 4 times without noticeable difference in behavior.






Fig. 2 (a) Structure of the photoacid  $\text{PAH}'(\text{BF}_4)$ , and (b) reversible gel-sol transition of the polymer networks **P2**–**P4**. Polymer **P1** contains acid-resistant network junctions, and is therefore not affected by light.

The results obtained with  $\text{PAH}'(\text{BF}_4)$  showed that it is possible to use a photoacid for the light-triggered disassembly of polymers with  $\text{Pd}_n\text{L}_{2n}$  network junctions. Next, we set out to explore a more challenging task: the acid-induced assembly of Pd-based networks. In view of the good acid resistance of **P1**, we hypothesized that it might be possible to achieve the assembly of **P1** from **L1** and  $\text{Pd}^{2+}$  under acidic conditions. The prerequisite would be a source of Pd, which would liberate  $\text{Pd}^{2+}$  only under acidic conditions.

Previously, we had shown that metalloligand **L5** (Fig. 3) forms hexanuclear Pd complexes of the formula  $[\text{Pd}_6(\text{L5})_{12}]^{12+}$ .<sup>25</sup> The two pyridyl groups of **L5** are highly basic, rendering the Pd assembly sensitive to acid.<sup>14</sup> Consequently,  $[\text{Pd}_6(\text{L5})_{12}]^{12+}$  represents a reservoir for  $\text{Pd}^{2+}$ , with metal ions being released under acidic conditions.

When a mixture of **L1** (1 equiv.), **L5** (2 equiv.) and  $[\text{Pd}(\text{CH}_3\text{CN})_4](\text{BF}_4)_2$  (1 equiv.) in  $\text{CD}_3\text{CN}$  was equilibrated at 70 °C for 3 h, a dark red solution was obtained. Inspection of this solution by NMR spectroscopy revealed the formation  $[\text{Pd}_6(\text{L5})_{12}]^{12+}$  along




Fig. 3 Light-induced assembly of the Pd-based polymer network **P1** is achieved by irradiation of a mixture of **L1**,  $[\text{Pd}_6(\text{L5})_{12}]^{12+}$ , and  $\text{PAH}'(\text{BF}_4)$ . The hexanuclear complex  $[\text{Pd}_6(\text{L5})_{12}]^{12+}$  acts as an acid-sensitive reservoir for  $\text{Pd}^{2+}$ , enabling the formation of **P1** under acidic conditions. The sol-gel transition can be reversed by heating the sample in the dark.

with 'free' polymer ligand **L1**. The preferential complexation of **L5** over **L1** can be explained by the higher donor strength of the former. When TFA (2 equiv. per total N-donor groups) was added, the mixture gradually converted to a gel when annealed at 70 °C for 2 h.

Next, we have performed a similar experiment using photoacid  $\text{PAH}'(\text{BF}_4)$  instead of TFA. After irradiation of the sample with blue light at 50 °C for 11 h, we observed the formation of a gel (Fig. 3). The network could be cleaved by keeping the sample in the dark at 70 °C for 7 h. A light induced sol-gel transition followed by a heat-induced gel-sol transition cycle could be repeated 4 times without noticeable difference.

## Conclusions

To conclude, we have demonstrated that the photoacid  $\text{PAH}'(\text{BF}_4)$  can be used for the light-controlled assembly and disassembly of Pd-based polymers networks. Light-induced gel-sol transitions were achieved by using acid-sensitive  $\text{Pd}_n\text{L}_{2n}$  network junctions. For realizing the inverse process, the light-induced formation of a metallogel, we have employed a hexanuclear Pd cage as an acid-sensitive reservoir for  $\text{Pd}^{2+}$ . The relative basicity of the polymeric N-donor ligand is a key parameter for both processes, because the ligand basicity controls the acid-sensitivity of the polymer network. Another important factor is the pH range, which can be accessed with the photoacid. The metastable state acidity of  $\text{PAH}'(\text{BF}_4)$  is suited to cleave Pd-N bonds. In principle, it should be possible to use photoacids for the light-controlled cleavage of other types of metal-ligand assemblies. However, it might be necessary to use – or develop – photoacids with different properties in order to achieve a reversible cleavage of the respective metal-ligand bond. Investigations in this direction are ongoing in our laboratory.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

The work was supported by the Swiss National Science Foundation (SNSF "Ambizione" PZ00P2\_180008), and by the École Polytechnique Fédérale de Lausanne (EPFL). We thank Dr Daniel Ortiz for measuring mass spectra and Dr Claudia Avalos for help with MAS NMR spectroscopy measurements.

## References

- (a) P. Sutar and T. K. Maji, *Dalton Trans.*, 2020, **49**, 7658–7672; (b) V. J. Pastore and T. R. Cook, *Chem. Mater.*, 2020, **32**, 3680–3700; (c) Y. Gu, J. Zhao and J. A. Johnson, *Angew. Chem., Int. Ed.*, 2020, **59**, 5022–5049; (d) K. C. Bentz and S. M. Cohen, *Angew. Chem., Int. Ed.*, 2018, **57**, 14992–15001.
- The interconnection of metal-based macrocycles and cages *via* non-covalent interactions has also been explored. For reviews, see: (a) B. Li, T. He, Y. Fan, X. Yuan, H. Qiu and



- S. Yin, *Chem. Commun.*, 2019, **55**, 8036–8059; (b) Y. Sun, C. Chen and P. J. Stang, *Acc. Chem. Res.*, 2019, **52**, 802–817; (c) L. J. Chen and H. B. Yang, *Acc. Chem. Res.*, 2018, **51**, 2699–2710; (d) S. Datta, M. L. Saha and P. J. Stang, *Acc. Chem. Res.*, 2018, **51**, 2047–2063.
- 3 (a) A. Legrand, G. A. Craig, M. Bonneau, S. Minami, K. Urayama and S. Furukawa, *Chem. Sci.*, 2019, **10**, 10833–10842; (b) A. Carné-Sánchez, G. A. Craig, P. Larpent, V. Guillermin, K. Urayama, D. MasPOCH and S. Furukawa, *Angew. Chem., Int. Ed.*, 2019, **58**, 6347–6350; (c) A. Carné-Sánchez, G. A. Craig, P. Larpent, T. Hirose, M. Higuchi, S. Kitagawa, K. Matsuda, K. Urayama and S. Furukawa, *Nat. Commun.*, 2018, **9**, 1–8.
- 4 G. Lal, M. Derakhshandeh, F. Akhtar, D. M. Spasyuk, J.-B. Lin, M. Trifkovic and G. K. H. Shimizu, *J. Am. Chem. Soc.*, 2019, **141**, 1045–1053.
- 5 J. Liu, W. Duan, J. Song, X. Guo, Z. Wang, X. Shi, J. Liang, J. Wang, P. Cheng, Y. Chen, M. J. Zawarotko and Z. Zhang, *J. Am. Chem. Soc.*, 2019, **141**, 12064–12070.
- 6 X.-Y. Xie, F. Wu, X. Liu, W.-Q. Tao, Y. Jiang, X.-Q. Liu and L.-B. Sun, *Chem. Commun.*, 2019, **55**, 6177–6180.
- 7 S.-Q. Deng, D.-M. Li, X.-J. Mo, Y.-L. Miao, S.-L. Cai, J. Fan, W.-G. Zhang and S.-R. Zheng, *ChemPlusChem*, 2020, DOI: 10.1002/cplu.202000570.
- 8 J. A. Foster, R. M. Parker, A. M. Belenguer, N. Kishi, S. Sutton, C. Abell and J. R. Nitschke, *J. Am. Chem. Soc.*, 2015, **137**, 9722–9729.
- 9 N. J. Oldenhuis, K. P. Qin, S. Wang, H. Z. Ye, E. A. Alt, A. P. Willard, T. Van Voorhis, S. L. Craig and J. A. Johnson, *Angew. Chem., Int. Ed.*, 2020, **59**, 2784–2792.
- 10 Y. Gu, E. A. Alt, H. Wang, X. Li, A. P. Willard and J. A. Johnson, *Nature*, 2018, **560**, 65–69.
- 11 (a) Y. Wang, Y. Gu, E. G. Keeler, J. V. Park, R. G. Griffin and J. A. Johnson, *Angew. Chem., Int. Ed.*, 2017, **56**, 188–192; (b) A. V. Zhukhovitskiy, M. Zhong, E. G. Keeler, V. K. Michaelis, J. E. P. Sun, M. J. A. Hore, D. J. Pochan, R. G. Griffin, A. P. Willard and J. A. Johnson, *Nat. Chem.*, 2016, **8**, 33–41; (c) A. V. Zhukhovitskiy, J. Zhao, M. Zhong, E. G. Keeler, E. A. Alt, P. Teichen, R. G. Griffin, M. J. A. Hore, A. P. Willard and J. A. Johnson, *Macromolecules*, 2016, **49**, 6896–6902.
- 12 (a) L. Li, J. M. Scheiger and P. A. Levkin, *Adv. Mater.*, 2019, **31**, 1807333; (b) Q. Zhang, D.-H. Qu and H. Tian, *Adv. Opt. Mater.*, 2019, **7**, 1–18; (c) E. R. Draper and D. J. Adams, *Chem. Commun.*, 2016, **52**, 8196–8206; (d) G. L. Fiore, S. J. Rowan and C. Weder, *Chem. Soc. Rev.*, 2013, **42**, 7278–7288.
- 13 M. Weißenfels, J. Gemena and R. Klajn, *Chem*, 2021, **7**, 23–27.
- 14 S. M. Jansze, G. Cecot and K. Severin, *Chem. Sci.*, 2018, **9**, 4253–4257.
- 15 (a) Y. Liao, *Acc. Chem. Res.*, 2017, **50**, 1956–1964; (b) Z. Shi, P. Peng, D. Strohecker and Y. Liao, *J. Am. Chem. Soc.*, 2011, **133**, 14699–14703.
- 16 For a detailed mechanistic investigation of this process, see: C. Berton, D. M. Busiello, S. Zamuner, E. Solari, R. Scopelliti, F. Fadaei-Tirani, K. Severin and C. Pezzato, *Chem. Sci.*, 2020, **11**, 8547–8468.
- 17 S. M. Jansze and K. Severin, *J. Am. Chem. Soc.*, 2019, **141**, 815–819.
- 18 D. P. August, G. S. Nichol and P. J. Lusby, *Angew. Chem. Int. Ed.*, 2016, **55**, 15022–15026.
- 19 Y. Wang, M. Zhong, J. V. Park, A. V. Zhukhovitskiy, W. Shi and J. A. Johnson, *J. Am. Chem. Soc.*, 2016, **138**, 10708–10715.
- 20 M. Tominaga, K. Suzuki, M. Kawano, T. Kusukawa, T. Ozeki, S. Sakamoto, K. Yamaguchi and M. Fujita, *Angew. Chem., Int. Ed.*, 2004, **43**, 5621–5625.
- 21 D. Samanta and P. S. Mukherjee, *Chem. Eur. J.*, 2014, **20**, 12483–12492.
- 22 B. Chen, J. J. Holstein, S. Horiuchi, W. G. Hiller and G. H. Clever, *J. Am. Chem. Soc.*, 2019, **141**, 8907–8913.
- 23 Apparently, the formation of Pd<sub>2</sub>L<sub>4</sub> links is compromised when using [Pd(CH<sub>3</sub>CN)<sub>4</sub>](BF<sub>4</sub>)<sub>2</sub> instead of Pd(NO<sub>3</sub>)<sub>2</sub> (see ref. 11b). For anion effects during the formation of Pd<sub>2</sub>L<sub>4</sub> complexes, see: T. Tateishi, S. Takahashi, A. Okazawa, V. Martí-Centelles, J. Wang, T. Kojima, P. J. Lusby, H. Sato and S. Hiraoka, *J. Am. Chem. Soc.*, 2019, **141**, 19669–19676.
- 24 Q. Teng and H. V. Huynh, *Dalton Trans.*, 2017, **46**, 614–627.
- 25 M. D. Wise, J. J. Holstein, P. Pattison, C. Besnard, E. Solari, R. Scopelliti, G. Bricogne and K. Severin, *Chem. Sci.*, 2015, **6**, 1004–1010.

