



Cite this: *Catal. Sci. Technol.*, 2022, 12, 3957

## Atomic-scale changes of silica-supported catalysts with nanocrystalline or amorphous gallia phases: implications of hydrogen pretreatment on their selectivity for propane dehydrogenation<sup>†</sup>

Pedro Castro-Fernández, <sup>a</sup> Alexander I. Serykh, <sup>b</sup> Alexander V. Yakimov, <sup>c</sup> Igor P. Prosvirin, <sup>d</sup> Andrey V. Bukhtiyarov, <sup>d</sup> Paula M. Abdala, <sup>\*a</sup> Christophe Copéret, <sup>c</sup> Alexey Fedorov <sup>\*a</sup> and Christoph R. Müller <sup>\*a</sup>

This work explores how H<sub>2</sub> pretreatment at 550 °C induces structural transformation of two gallia-based propane dehydrogenation (PDH) catalysts, *viz.* nanocrystalline  $\gamma$ - $\beta$ -Ga<sub>2</sub>O<sub>3</sub> and amorphous Ga<sub>2</sub>O<sub>3</sub> (GaO<sub>x</sub>) supported on silica ( $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> and Ga/SiO<sub>2</sub>, respectively) and how it affects their activity, propene selectivity and stability with time on stream (TOS). Ga/SiO<sub>2</sub>-H<sub>2</sub> shows poor activity and propene selectivity, no coking and no deactivation with TOS, similar to Ga/SiO<sub>2</sub>. In contrast, the high initial activity and propene selectivity of  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> decline with TOS but to a lesser extent than in calcined  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>. In addition,  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> cokes less than  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>. Ga K-edge X-ray absorption spectroscopy suggests an increased disorder of the nanocrystalline  $\gamma$ - $\beta$ -Ga<sub>2</sub>O<sub>3</sub> phases in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> and the emergence of additional tetrahedral Ga sites (Ga<sub>IV</sub>). Such Ga<sub>IV</sub> sites are strong Lewis acid sites (LAS) according to studies using adsorbed pyridine and CO probe molecules, *i.e.*, the abundance of strong LAS is higher in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> compared to  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> but lower than in Ga/SiO<sub>2</sub> and Ga/SiO<sub>2</sub>-H<sub>2</sub>. Dissociation of H<sub>2</sub> on the Ga-O linkages in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> yields high-frequency Ga-H bands that are observed in Ga/SiO<sub>2</sub> and Ga/SiO<sub>2</sub>-H<sub>2</sub> but not detected in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>. We attribute the increased amount of Ga<sub>IV</sub> sites in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> mostly to an increased disorder in  $\gamma$ - $\beta$ -Ga<sub>2</sub>O<sub>3</sub>. X-ray photoelectron spectroscopy detects the formation of Ga<sup>+</sup> and Ga<sup>0</sup> species in both Ga/SiO<sub>2</sub>-H<sub>2</sub> and  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub>. Therefore, it is likely that a minor amount of Ga<sub>IV</sub> sites also forms through the interaction of Ga<sup>+</sup> (such as Ga<sub>2</sub>O) and/or Ga<sup>0</sup> with silanol groups of SiO<sub>2</sub>.

Received 13th January 2022,  
Accepted 1st May 2022

DOI: 10.1039/d2cy00074a

rsc.li/catalysis

## Introduction

The industrial production of propene through propane dehydrogenation (PDH) relies mainly on PtSn/Al<sub>2</sub>O<sub>3</sub> or CrO<sub>x</sub>/Al<sub>2</sub>O<sub>3</sub> catalysts, yet the high cost of Pt and the environmental toxicity of Cr<sup>6+</sup> has motivated the search for alternative catalyst formulations.<sup>1–5</sup> Among the alternatives explored, Ga-based catalysts are considered promising. For instance, a Ga/H-ZSM-5 zeolite catalyst has been used for the Cyclar propane

aromatization process, in which the dehydrogenation of propane to propene proceeds on Ga-based active sites, followed by dehydrogenative aromatization of propene on the strong Brønsted acid sites of the zeolite.<sup>6,7</sup> Furthermore, the FCDh (fluidized catalytic dehydrogenation of propane) process, which uses a PtGa/Al<sub>2</sub>O<sub>3</sub> catalyst is currently at the initial phase of its industrial deployment.<sup>8</sup>

A reductive pretreatment of zeolitic Ga-based catalysts under H<sub>2</sub> at 450–650 °C is often used to increase the activity and selectivity of the Ga-based active sites for propane dehydrogenation.<sup>9</sup> It has been demonstrated that the dispersion of Ga in mechanically mixed Ga<sub>2</sub>O<sub>3</sub>/H-ZSM-5 catalysts increases under H<sub>2</sub> pretreatment conditions, explained by the formation of reduced Ga species that diffuse within the zeolitic channels and anchor onto acidic hydroxyl groups.<sup>10</sup> Various reduced zeolitic Ga species have been proposed to form after reductive pretreatment or under reaction conditions, and, presumably, also the reduced species are active in PDH.<sup>11–13</sup> H<sub>2</sub> pretreatment of Ga/H-ZSM-

<sup>a</sup> Department of Mechanical and Process Engineering, ETH Zürich, CH-8092, Zürich, Switzerland. E-mail: abdalap@ethz.ch, fedoroal@ethz.ch, muelchri@ethz.ch

<sup>b</sup> Zelinsky Institute of Organic Chemistry, RAS, Moscow, 119991, Russia

<sup>c</sup> Department of Chemistry and Applied Biosciences, ETH Zürich, CH-8093, Zürich, Switzerland

<sup>d</sup> Boreskov Institute of Catalysis, SB RAS, 630090 Novosibirsk, Russia

<sup>†</sup> Electronic supplementary information (ESI) available: Experimental procedures, XAS, FTIR, STEM-EDX, XPS, dPDF and <sup>15</sup>N DNP SENS experimental parameters. See DOI: <https://doi.org/10.1039/d2cy00074a>



5 and Ga/H-MFI zeolites, followed by *in situ* X-ray absorption near edge structure spectroscopy (XANES) experiments at the Ga K-edge showed a shift in the absorption edge to lower energies (~4.6 eV (ref. 14)) that has been related to the reduction of  $\text{Ga}^{3+}$  to  $\text{Ga}^+$ , which then may quickly reoxidize to form  $\text{GaO}^+$  or  $[\text{GaH}_2]^+$  species.<sup>11,14–16</sup> The conclusions from XANES experiments have been supported by X-ray photoelectron spectroscopy (XPS) studies of Ga zeolites that revealed Ga 3d features at lower binding energies relative to the  $\text{Ga}^{3+}$  peaks; such features have been ascribed to  $\text{Ga}^+$ ,  $\text{Ga}^{\delta+}$  and metallic Ga.<sup>17</sup>

That being said, the interaction of the gallia phase with silica, a typical non-microporous support, and the nature of the Ga sites formed in such supported materials under  $\text{H}_2$  treatment remains less explored. Treatment of a  $\text{Ga}_2\text{O}_3/\text{SiO}_2$  catalyst with  $\text{H}_2$  at 550 °C has been reported to lead to a partial reduction of  $\text{Ga}_2\text{O}_3$ , lower propene yields in PDH and higher yields to aromatics, the latter observation explained by an increase in the number of Brønsted acid sites.<sup>18</sup> Similar to the reduction of  $\text{Ga}^{3+}$  sites in zeolites, it has been shown that  $\text{H}_2$  pretreatment at 550 °C of a  $\text{Ga}_2\text{O}_3/\text{SiO}_2$  material gave XPS features consistent with  $\text{Ga}^+$  species.<sup>19</sup> In another report, Ga K-edge XANES and XPS analysis of a  $\text{Ga}_2\text{O}_3/\text{SiO}_2$  catalyst treated with  $\text{H}_2$  at 650 °C also suggested the presence of reduced Ga sites.<sup>20</sup> However, after  $\text{H}_2$  pretreatment, the latter catalyst showed a loss of PDH activity, suggested to be due to the formation of lower-coordinated  $\text{Ga}^{\delta+}$  species.<sup>20</sup> Additionally, the emergence of a low-energy XANES edge feature has been observed when comparing fresh and used (after 20 hours of time on stream, TOS) single site  $[(\equiv\text{SiO})_3\text{Ga}(\text{XOSi}\equiv)]$  (where X is H or  $\equiv\text{Si}$ ) PDH catalyst,<sup>21</sup> prepared by the surface organometallic chemistry approach.<sup>22</sup> The low energy edge feature in the XANES spectra may be associated with the reduction of Ga sites; however, recent evidence from reference molecular alkyl gallium compounds suggests that such feature may, at least in part, be associated with the formation of Ga alkyl surface species during the PDH reaction.<sup>23</sup> This evidence is in line with a further report that demonstrated that an edge feature at lower energies in the Ga K-edge XANES spectra could be due to changes in the coordination number and/or formation of gallium hydride and alkyl species.<sup>24</sup>

Studies of unsupported gallia catalysts have suggested that the high activity of  $\beta\text{-Ga}_2\text{O}_3$  in PDH (as compared to other gallia polymorphs) is due to the high relative fraction of weak Lewis acid sites (LAS) on the surface of  $\beta\text{-Ga}_2\text{O}_3$ .<sup>25</sup> It has been shown that oxygen vacancy ( $\text{V}_\text{o}$ ) surface sites in  $\beta\text{-Ga}_2\text{O}_3$  can be generated by  $\text{H}_2$  pretreatment.<sup>26</sup> Density functional theory studies on a dehydroxylated model surface of  $\beta\text{-Ga}_2\text{O}_3$  have ascribed weak LAS to tricoordinated  $\text{Ga}^{3+}$  sites, that is, Ga sites in tetrahedral surface termination positions that neighbor  $\text{V}_\text{o}$  surface sites.<sup>25</sup> The relevance of weak Ga-based LAS in unsupported nanoparticle catalysts for a high activity in PDH has also been supported by structure–performance relationship studies of mixed oxide  $(\text{Ga},\text{Al})_2\text{O}_3$  catalysts.<sup>27,28</sup>

In this work, we compare the structural changes of two gallia based, silica-supported catalysts upon  $\text{H}_2$  pretreatment,

with one material containing a nanocrystalline, and another one an amorphous gallia phase, denoted  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga}/\text{SiO}_2$ , respectively (with similar Ga loadings of 2–3 wt%). The calcined materials have been characterized by us in detail previously.<sup>25</sup>  $\text{Ga}/\text{SiO}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  display different reducibility under  $\text{H}_2$  treatment. More specifically,  $\text{Ga}/\text{SiO}_2$ , a PDH catalyst with a low activity and selectivity owing to the undesired cracking of propane on unselective Ga sites and, possibly, also on strong Brønsted acid sites (BAS, due to a small amount of gallosilicate sites in  $\text{Ga}/\text{SiO}_2$ ), shows no notable changes in its PDH performance after  $\text{H}_2$  treatment at 550 °C (2 h). In contrast,  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  displays, after the same reductive pretreatment, a higher stability with TOS both with regards to its activity and even more notably in its propene selectivity. The *in situ* X-ray absorption spectroscopy (XAS) study of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  at the Ga K-edge complemented by quasi *in situ* XPS suggests a higher reducibility of the nanocrystalline gallia phase in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  relative to the amorphous gallia phase in  $\text{Ga}/\text{SiO}_2$ . Upon  $\text{H}_2$  treatment we observe an increased disorder of the nanocrystalline gallia phase in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  that occurs in parallel with the reduction of  $\text{Ga}^{3+}$  sites to  $\text{Ga}^+$  and  $\text{Ga}^0$  species and the emergence of additional tetrahedral Ga sites ( $\text{Ga}_{\text{IV}}$ ). According to surface acidity studies using pyridine and CO probe molecules, the newly formed  $\text{Ga}_{\text{IV}}$  sites feature strong Lewis acidity, similarly to the acidity of the LAS in the amorphous gallia catalysts  $\text{Ga}/\text{SiO}_2$  and  $\text{Ga}/\text{SiO}_2\text{-H}_2$ , while avoiding the formation of strong BAS. In addition to the explanation given above, it is conceivable that  $\text{Ga}^+$  and/or  $\text{Ga}^0$  species interact with and anchor onto silanol groups of the silica support.

## Materials and methods

### Materials

The synthesis and structural characterization of the  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga}/\text{SiO}_2$  catalysts have been described by us previously.<sup>25</sup> In brief,  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga}/\text{SiO}_2$  were obtained by the incipient wetness impregnation of amorphous silica with a colloidal solution of  $\gamma\text{-Ga}_2\text{O}_3$  nanoparticles in toluene (particle diameter  $2.5 \pm 0.6$  nm) or an aqueous solution of  $\text{Ga}(\text{NO}_3)_3$ , respectively, followed by drying and calcination (600 °C, 2 h).  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\text{Ga}/\text{SiO}_2\text{-H}_2$  were obtained by pretreating  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga}/\text{SiO}_2$  in undiluted  $\text{H}_2$  at 550 °C for 2 h ( $10\text{ °C min}^{-1}$ ).

### Catalytic testing

Propane dehydrogenation tests were carried out in a benchtop Microactivity EFFI reactor (PID Eng&Tech). A mass of 50 mg of catalyst was mixed with 1.20 g of SiC (46 grit, Alfa-Aesar), and placed, between two plugs of quartz wool, onto a frit of a quartz fixed-bed reactor (diameter 13 mm). After reaching the reaction temperature (550 °C,  $10\text{ °C min}^{-1}$ ) under a flow of  $\text{N}_2$ , a mixture of 10%  $\text{C}_3\text{H}_8$  diluted in  $\text{N}_2$  was



introduced into the reactor (weight hourly space velocity, WHSV = 7.2 h<sup>-1</sup>). The composition of the outlet gasses was analyzed using a gas chromatograph (Clarus 480, PerkinElmer) with a flame ionization detector and a thermal conductivity detector. The first sampling of the gasses was made after 4 min of reaction, collecting data for every 20 minutes afterwards. For the H<sub>2</sub>-treated catalysts, before PDH reaction, the catalysts were heated up under H<sub>2</sub> to 550 °C (50 mL min<sup>-1</sup>), and held at this temperature for 2 hours. Subsequently, the catalyst bed was flushed with N<sub>2</sub> for 15 min before switching to a C<sub>3</sub>H<sub>8</sub>/N<sub>2</sub> mixture.

### Thermogravimetric analyses

For thermogravimetric analyses (TGA), *ca.* 15 mg of the catalyst were placed in a 70 µL alumina crucible and introduced into the instrument (DSC 1, Mettler-Toledo). The material was heated to 550 °C (10 °C min<sup>-1</sup>) under a N<sub>2</sub> flow of 75 mL min<sup>-1</sup> (of which 25 mL min<sup>-1</sup> correspond to the purge flow of the balance). After having reached the desired temperature and holding at this temperature for 10 min, 10% of propane (7.5 mL min<sup>-1</sup>) was introduced to the N<sub>2</sub> flow. Changes in the catalyst weight were monitored for 160 min.

### XAS and X-ray total scattering

X-ray absorption measurements were performed at the Swiss-Norwegian beamlines (SNBL, BM31) at the European Synchrotron Radiation Facility (ESRF).<sup>29</sup> Spectra were obtained at the Ga K-edge in transmission mode (continuous scanning), using a double-crystal Si(111) monochromator. For *ex situ* measurements, the materials were mixed with an optimal amount of cellulose and pressed into self-supporting pellets.<sup>30</sup> Pellets of H<sub>2</sub>-treated materials were prepared inside of a glovebox and kept in air-tight sealed bags for measurements.

*In situ* XAS experiments were carried out in a quartz capillary reactor (diameter 1 mm; wall thickness = 0.1 mm) whereby the catalyst was placed between two quartz wool plugs. H<sub>2</sub> was flowed (10 mL min<sup>-1</sup>) through the reactor while heating up from room temperature to 550 °C (10 °C min<sup>-1</sup>) using an air blower. During cooling down the reactor was flushed with He. A schematics of the XAS setup has been described in a previous publication.<sup>25</sup> Data processing was carried out using the DEMETER software suite.<sup>31</sup> Energy calibration was performed using a Zn-foil. Data processing was done using the Athena software.<sup>30</sup> FEFF paths and the amplitude reduction factor ( $S_0^2$ ) were generated by the Artemis software using a  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> structural model.<sup>31,32</sup>

X-ray total scattering data were collected at BM31 in a consecutive (combined) mode to the *in situ* XAS data. Data collection was performed before and after H<sub>2</sub> treatment at 50 °C, using a wavelength of  $\lambda = 0.25811$  Å (set by a double-crystal Si(111) monochromator), and a two-dimensional MAR detector (MAR345 image plate). The data collection time was 20 min. To obtain pair distribution functions (PDF, G(r)) from

the supported gallia phase, the scattering signal was subtracted from the scattering signal of the pure SiO<sub>2</sub> support.<sup>33</sup> PDFs were obtained using the PDFgetX3 software,<sup>34</sup> setting a  $Q_{\max} = 16$  Å<sup>-1</sup> and a  $R_{\text{poly}} = 1.6$ .

### Dynamic nuclear polarization surface enhanced nuclear resonance spectroscopy (DNP SENS)

Prior to NMR measurements,  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> and Ga/SiO<sub>2</sub>-H<sub>2</sub> were dehydroxylated at 550 °C at *ca.* 10<sup>-5</sup> mbar for 2 h (3 °C min<sup>-1</sup>). Subsequently, the materials were exposed for 20 min at room temperature to the saturated vapor pressure of <sup>15</sup>N labelled pyridine (Py), followed by evacuation at 150 °C at *ca.* 10<sup>-5</sup> mbar for 15 min. Before use, <sup>15</sup>N Py was dried by adding CaH<sub>2</sub> and stirring at 60 °C for 72 h. Afterwards, the solution was degassed by several freeze-pump-thaw cycles.<sup>22</sup> Materials with pre-adsorbed Py were impregnated in a glovebox (O<sub>2</sub> and H<sub>2</sub>O < 1 ppm) with a 16 mM TEKPol in 1,1,2,2-tetrachloroethane (TCE) solution.<sup>35,36</sup> The impregnated materials were introduced into a sapphire rotor (outer diameter 3.2 mm), and closed with a zirconia cap. The rotor was placed quickly in a cold NMR probe (100 K). <sup>15</sup>N DNP SENS spectra were acquired on a Bruker 600 MHz (14.1 T) instrument equipped with a 3.2 mm Bruker low-temperature double-resonance probe coupled to a 395 GHz gyrotron microwave source (output power = 6–10 W) to drive the DNP cross-effect. In all experiments a MAS rate of 8 kHz was used. DNP-enhanced <sup>15</sup>N NMR spectra were measured using a <sup>1</sup>H<sup>15</sup>N CPMAS pulse sequence with the contact time of 2 ms. As a reference for the static magnetic field, the <sup>13</sup>C higher-frequency peak of adamantane at 38.4 ppm was used. The DNP buildup time ( $\tau_{\text{DNP}}$ ) was measured by a <sup>1</sup>H saturation-recovery experiment with the microwaves turned on. A summary of the experimental DNP SENS parameters are given in Table S1.†

### XPS

X-ray photoelectron spectra were recorded on a SPECS photoelectron spectrometer using a hemispherical PHOIBOS 150 MCD 9 analyzer (AlK<sub>a</sub> radiation,  $h\nu = 1486.6$  eV, 150 W). The binding energy (BE) scale was pre-calibrated using the positions of the peaks of the Au 4f<sub>7/2</sub> (BE = 84.0 eV) and Cu2p<sub>3/2</sub> (BE = 932.67 eV) core levels. The Si 2p peak at 103.5 eV of the SiO<sub>2</sub> support was used as an internal standard. The survey spectra were recorded at a pass energy of 50 eV, and for the narrow spectral regions at 20 eV. To determine the chemical (charge) state of elements on the surface of the materials, the regions of Ga 3d and O 2s, Si 2p, Si 2s, C 1s, O 1s, Ga 2p<sub>3/2</sub> were measured. The atomic ratios of the elements on the catalyst surface were calculated from the integral photoelectron peak intensities which were corrected by theoretical sensitivity factors based on Scofield's photoionization cross sections.<sup>37</sup> The residual gas pressure during the measurements did not exceed  $8 \times 10^{-9}$  mbar. To carry out experiments using the high pressure cell (HPC) of



the SPECS photoelectron spectrometer, all materials were rubbed into a stainless steel mesh that was spot welded onto a standard holder. HPC allows to pretreat the specimen under different gases at pressures up to 1 bar and in the temperature range from 50 to 450 °C. The pretreatment was performed for 1 h at a hydrogen pressure of *ca.* 300 mbar either at 300 °C or 450 °C, followed by an outgassing to UHV conditions at the respective pretreatment temperature. The pretreated materials were transferred to the analyzer chamber without any contact with air. Additional XPS data (survey scans, C 1s, Si 2p, Ga 3d, O 2s and Ga LMM lines) are presented in Fig. S4 and S5.†

#### Fourier-transform infrared spectroscopy (FTIR)

Infrared spectra were recorded on a Nicolet Protege 360 spectrophotometer in transmittance mode (spectral resolution 4  $\text{cm}^{-1}$ ). Powdered materials were pressed into self-supporting wafers (15–20 mg  $\text{cm}^{-2}$ ) and placed into a vacuum infrared quartz cell equipped with  $\text{CaF}_2$  windows. The dissociative adsorption of hydrogen (*ca.* 1–2 min hydrogen exposure time) was studied at different temperatures (300, 450 and 540 °C) at an equilibrium hydrogen pressure of *ca.* 70 mbar on both calcined materials and on the materials treated in hydrogen. Calcined and  $\text{H}_2$ -treated materials before hydrogen adsorption were outgassed at 813 K for 2 h in a medium vacuum of *ca.*  $10^{-3}$  mbar. The hydrogen pretreatment of the self-supporting wafers was conducted in the IR cell under static conditions (three cycles of exposure of the specimen to *ca.* 130 mbar of  $\text{H}_2$  for 0.5 h with evacuation to *ca.*  $10^{-3}$  mbar in-between the  $\text{H}_2$  exposures). The IR spectra were measured at room temperature. Both calcined and  $\text{H}_2$ -treated materials were also characterized by the adsorption of CO. The adsorption of CO was conducted at room temperature and an equilibrium pressure of *ca.* 27 mbar.

#### Scanning transmission electron microscopy – energy dispersive X-ray spectroscopy (STEM-EDX)


Materials were dispersed on a copper grid and analyzed using a FEI Talos F200X instrument. The operation voltage was set to 200 kV in scanning transmission electron microscopic (STEM) mode. EDX was performed using an accelerating voltage of 40 keV.

Fig. 1, 2, S2 and S7,† and Table 1 present results for calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  catalysts. This data has been reported by us in ref. 25 and is reproduced here for comparison to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$ , with permission from the American Chemical Society (Copyright 2021).

## Results

### Catalytic performance and coking

$\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  are PDH catalysts that contain dispersed nanocrystalline gallia nanoparticles (NPs,  $\gamma/\beta$ -phase  $\text{Ga}_2\text{O}_3$ ) and a mostly XRD-amorphous gallia phase with a




**Fig. 1** Results of the PDH catalytic tests for calcined (black traces) and  $\text{H}_2$ -treated (blue traces)  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$ . (A) Ga-Normalized formation rate of propene, (B) selectivity to propene, and (C) Ga-normalized formation rates of cracking products (methane and ethene). Catalytic data for the calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  has been reported by us previously and is reproduced here for comparison.<sup>25</sup>

short range order (*ca.* 5 Å), respectively.<sup>25,38</sup> These two catalysts were treated in undiluted  $\text{H}_2$  at 550 °C for 2 h prior to their catalytic PDH tests at 550 °C for 104 min at a WHSV = 7.2  $\text{h}^{-1}$ . Note that the catalytic results for  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  have been reported by us previously,<sup>25</sup> and are plotted in Fig. 1 to allow a comparison with the  $\text{H}_2$ -treated materials. Fig. 1A displays propene formation rates normalized per ICP-determined Ga loading. Fig. 1B and C present the selectivity to propene and Ga-normalized formation rates of the cracking products (methane and ethene), respectively.

The initial activity and selectivity to propene (after 4 min TOS) of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  are 10.3 mol  $\text{C}_3\text{H}_6$  mol  $\text{Ga}^{-1}$   $\text{h}^{-1}$  and 72%, respectively, which are similar to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ . However, the decrease of the activity and selectivity of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  after 104 min TOS is lower than that in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (Fig. 1A). The higher propene selectivity of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  relative to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  correlates with the decreased rate of cracking to methane and ethene, *i.e.* *ca.* 4.2 mol  $(\text{CH}_4 + \text{C}_2\text{H}_4)$  mol  $\text{Ga}^{-1}$   $\text{h}^{-1}$  for  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and 3.2 mol  $(\text{CH}_4 + \text{C}_2\text{H}_4)$  mol  $\text{Ga}^{-1}$   $\text{h}^{-1}$  for  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  after 40 min TOS (Fig. 1C). In contrast, the rates of cracking and





**Fig. 2** *Ex situ* Ga K-edge XANES spectra of  $\text{Ga/SiO}_2$  (A) and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (B) before and after  $\text{H}_2$ -treatment (black and blue traces, respectively). EXAFS FT plots (non-phase corrected) before and after  $\text{H}_2$  treatment (black and blue traces, respectively) for  $\text{Ga/SiO}_2$  (C) and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (D). We note that the *ex situ* XANES and EXAFS data for calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  have been reported by us previously,<sup>25</sup> and are reproduced here for comparison. (E) Selected normalized traces of *in situ* Ga K-edge XANES during  $\text{H}_2$  treatment of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (50–550 °C). The inset shows changes of the white line and a derivative plot is presented in (Fig. S6†). (F) Comparison of the XANES spectra of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  before flowing  $\text{H}_2$  at 50 °C, after 90 min under  $\text{H}_2$  at 550 °C, and after cooling down under He.

**Table 1** Results of EXAFS fittings. Fittings of calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  have been reported previously and are provided here for comparison in square brackets.<sup>25</sup> Uncertainties determined by least-squares minimization are given in parenthesis. Fixed values are marked by an asterisk. See Table S2† for fittings that include Ga–Si paths

Material	Path	CN	Distance (Å)	$\sigma^2$ (Å <sup>2</sup> )	R-Factor
$\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$	Ga–O	5.4(1) [5.4(5)]	1.87(1) [1.89(1)]	0.011* [0.011*]	0.004
	Ga–Ga <sub>1</sub>	1.7(2) [2.0(1)]	2.98(1) [2.99(1)]	0.009* [0.009]	
	Ga–Ga <sub>2</sub>	2.3(3) [3.0(1)]	3.37(1) [3.38(1)]	0.009* [0.009]	
$\text{Ga/SiO}_2\text{-H}_2$	Ga–O	5.7(3) [5.7(9)]	1.85(1) [1.86(1)]	0.011* [0.011*]	0.016
	Ga–Ga <sub>1</sub>	1.0(1) [2.0(1)]	2.91(2) [2.97(1)]	0.011* [0.011]	

propene formation, and the selectivity to propene are similarly low for  $\text{Ga/SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2$ , although these catalysts show no deactivation with time on stream (Fig. 1A and B).

*In situ* thermogravimetric analyses (TGA) were carried out under PDH reaction conditions for the  $\text{H}_2$ -treated catalysts and compared to those of the calcined catalysts obtained in our previous work.<sup>25</sup> The amount of coke deposited (g coke g  $\text{Ga}^{-1}$ ) after 104 minutes TOS is *ca.* 25% lower for  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  relative to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (0.09 vs. 0.12 g coke g  $\text{Ga}^{-1}$ ).  $\text{Ga/SiO}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$  did not deposit any detectable amounts of coke.

### Ga K-edge XAS

The local environment and the oxidation state of Ga in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$  were evaluated using Ga K-edge XANES and compared to the reported results of

calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$ .<sup>25</sup> The  $\text{H}_2$ -treated catalysts were measured *ex situ* in air tight conditions. The white-line features at *ca.* 10 375 and 10 379 eV have been attributed to tetrahedral and octahedral,  $\text{Ga}_{\text{IV}}$  and  $\text{Ga}_{\text{VI}}$  sites, respectively.<sup>25,27,39</sup> Yet the interpretation of the XANES spectra, especially for the  $\text{H}_2$ -treated  $\text{Ga}_2\text{O}_3/\text{SiO}_2$  materials, is not straightforward since the position of the white line peaks is affected by the coordination number and symmetry of the Ga sites, as well as the oxidation state of Ga and the ligand type (–O– or –H).<sup>23,40,41</sup> A broad white-line in  $\text{Ga/SiO}_2$  was previously related to the non-crystalline nature of this material, *i.e.*, only a short range order with different type of sites (different coordination environment) is present in this material.<sup>25</sup> In the spectrum of  $\text{Ga/SiO}_2$ , the feature attributed to the  $\text{Ga}_{\text{IV}}$  site has a slightly higher intensity than that of the  $\text{Ga}_{\text{VI}}$  site (Fig. 2A). The intensity of the white-line peaks in  $\text{Ga/SiO}_2\text{-H}_2$  is lower compared to  $\text{Ga/SiO}_2$ , while the  $\text{Ga}_{\text{IV}}$  feature is slightly more intense than the  $\text{Ga}_{\text{VI}}$  feature,



suggesting a change in Ga coordination after  $H_2$  treatment (Fig. 2A). Likewise, the  $Ga_{IV}$  feature increases and the  $Ga_{VI}$  feature decreases in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  relative to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (Fig. 2B). The edge position (determined from the maximum in the derivative plot) is 10 374 eV for all studied materials. Thus, *ex situ* Ga K-edge XANES data does not indicate a reduction of  $\text{Ga}^{3+}$  sites in the  $H_2$  treated materials, yet it suggests a change in their local structure.

We further analyze the local structure around Ga in  $\text{Ga/SiO}_2\text{-H}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and compare it to that of the calcined catalysts using extended X-ray absorption fine structure (EXAFS). Similar to the calcined catalysts, the  $H_2$ -treated catalysts display two main peaks in the range of 1–3 Å (non-phase corrected EXAFS plots are presented in Fig. 2C and D) whereby the first peak corresponds to Ga–O and the second peak to Ga–Ga coordination spheres. Modelling of the EXAFS Fourier transformed (FT) data for  $\text{Ga/SiO}_2\text{-H}_2$  was carried out using a simplified model including one (average) Ga–O path and one Ga–Ga path, while fitting of the EXAFS FT data of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  relied on one Ga–O path and two Ga–Ga paths (Fig. S1,† Table 1). Note that the second coordination sphere may also contain contributions from a Ga–Si path, and including a Ga–Si path to the fitting of the EXAFS spectra of  $\text{Ga/SiO}_2\text{-H}_2$  decreases the *R*-factor (*i.e.* the fractional misfit) notably relative to the fitting that considers only Ga–Ga paths (*i.e.*, from 0.016 to 0.003, Fig. S10, Table S2†). This result is consistent with the presence of gallosilicate species in  $\text{Ga/SiO}_2\text{-H}_2$  that yield strong BAS (*vide infra*). In contrast, no abundant BAS are detected in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and, in line with this result, the inclusion of a Ga–Si path to fit the EXAFS spectrum of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  improves the *R*-factor only slightly, *i.e.* it decreases from 0.004 to 0.002. The  $\sigma^2$  values (*i.e.*, the mean square relative displacement of the nearest-neighbor atoms around Ga) were fixed to allow a comparison of the materials, *i.e.*, to avoid the high correlation between  $\sigma^2$  and coordination number (CN). Notice that an increase in the NPs disorder (due to defects or amorphization) can lead to both a decrease in CN and an increase in  $\sigma^2$  of the second coordination sphere. An alternative fitting using a fixed CN and a variable  $\sigma^2$  is discussed in the ESI† (Tables S3 and S4).

According to the fittings, the average Ga–O distance in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  is 1.87 Å, which is lower by 0.02 Å than in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (Table 1).<sup>25</sup> This decrease can be related to a higher relative fraction of  $Ga_{IV}$  sites in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  as indicated by the XANES data.<sup>39</sup> However, there is no detectable decrease in the coordination number of the first shell, possibly due to the large uncertainties in determining small variation in CN. However, a more notable change in CN occurs in the second coordination sphere, *i.e.*, the CNs of the Ga–Ga shell in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  are lower than in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (Fig. 2D and S1,† Table 1). This result can be explained by an increased disordering (such as the creation of defects and/or partial amorphization) of the gallia phase in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ . Indeed,  $\text{Ga/SiO}_2$  with mostly amorphous gallia shows even lower intensity of the Ga–Ga coordination

sphere and lower CN values (Table 1). A decrease in the CN of  $\text{Ga/SiO}_2$  upon  $H_2$  treatment ( $\text{Ga/SiO}_2\text{-H}_2$ ) may be due to a further dispersion of the gallia phase during the  $H_2$  pretreatment of  $\text{Ga/SiO}_2$  (*vide infra*).

Changes in the coordination environment of Ga during  $H_2$  treatment of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  were followed by *in situ* Ga K-edge XAS.  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  was heated in a quartz capillary reactor from 50 to 550 °C under an  $H_2$  flow (10 mL min<sup>-1</sup>, WHSV = 4.9 h<sup>-1</sup>) and held at 550 °C for 90 min (Fig. 2E and the derivative plot in Fig. S6†). A subtle feature at *ca.* 10 372 eV develops with increasing temperature, accompanied by a gradual decrease of the white-line intensity (Fig. 2E, inset). Fig. 2F presents XANES spectra of the initial  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  at 50 °C, after 90 min under  $H_2$  at 550 °C, and after the subsequent cooling down to room temperature under He flow (green, red and blue traces, respectively). The room temperature spectrum shows that the low-energy feature disappears after cooling down in He, with an increase in the white line intensity relative to that at 550 °C under  $H_2$ ; yet the final (after cooling down) white line intensity is slightly lower as compared to the calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ . Therefore, *in situ* and *ex situ* XANES are consistent in that the emergence of a low-energy edge feature (at *ca.* 10 372 eV) is observed under  $H_2$  flow at 550 °C but disappears under inert conditions at room temperature.

### PDF analysis


To complement the XAS analysis, we further evaluate the structural changes of  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  by the PDF analysis of X-ray total scattering data. The data collection was carried out *in situ* at 50 °C before and after the treatment of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  with  $H_2$  at 550 °C. Towards this end, difference PDF (dPDF) analysis was performed by subtracting the background signal of the  $\text{SiO}_2$  support from that of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ . The reciprocal space data after the subtraction of the  $\text{SiO}_2$  signal is shown in Fig. S8,† The signal to noise ratio allowed for a  $Q_{\max} = 16$  Å<sup>-1</sup>. The data reveals subtle differences in the intensity of the  $\gamma/\beta\text{-Ga}_2\text{O}_3$  peaks in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ . Turning to real space data, a comparison of the dPDF profiles evidences subtle changes in the local environment of Ga, as reflected by a broadening of the dPDF peaks of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  relative to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ , particularly within the range of *ca.* 1.5–6 Å (inset in Fig. S9†). This observation agrees with EXAFS results that suggested that  $H_2$  treatment leads to an increasingly disordered structure of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ .

### Quasi *in situ* XPS

To deepen our understanding of the reducibility of silica-supported, nanocrystalline and amorphous gallia, XPS spectra were acquired after: i) calcination, ii) pretreatment at 550 °C under a flow of  $H_2$  followed by the exposure of the activated material to air before the measurement, and iii) quasi *in situ* treatment under static  $H_2$  (300 mbar, 1 h) at 300 °C and 450 °C (performed at the HPC introduced in the XP



spectrometer). Calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  features a single peak at 1119.1 eV in the Ga 2p<sub>3/2</sub> region due to Ga<sup>3+</sup> sites. The low-energy shoulder at *ca.* 1117.2 eV appears in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  (*ca.* 12% of the total Ga intensity) even after exposure of the activated material to ambient air during the material transfer (Fig. 3A). Peaks at such low binding energies have been ascribed previously to the formation of either gallium hydrides, Ga<sup>2+</sup> or Ga<sup>+</sup> species.<sup>20</sup> *In situ* H<sub>2</sub> treatment at 300 °C increases the intensity of this peak to 22% of the total Ga intensity. After H<sub>2</sub> treatment of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  at 450 °C, an additional peak appears at 1115.7 eV, indicating the formation of Ga<sup>0</sup>.<sup>17,42</sup> At this stage, the fitted relative fractions of Ga<sup>0</sup>, Ga<sup>+</sup> and Ga<sup>3+</sup> are *ca.* 21, 37 and 42%, respectively. Calcined Ga/SiO<sub>2</sub> also features a single peak due to Ga<sup>3+</sup> at 1119.1 eV (Fig. 3B). Ga/SiO<sub>2</sub>-H<sub>2</sub> exposed to air during the material transfer shows signatures of reduced Ga sites whereby the fraction of Ga<sup>+</sup> is *ca.* 10%. Performing an *in situ* reduction of Ga/SiO<sub>2</sub> at 300 °C under static H<sub>2</sub> yields Ga<sup>+</sup> and Ga<sup>3+</sup> species with a distribution of 15 and 85%, whereas the *in situ* reduction of Ga/SiO<sub>2</sub> at 450 °C yields Ga<sup>0</sup>, Ga<sup>+</sup> and




**Fig. 3** Deconvoluted Ga 2p XPS spectra of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (A) and Ga/SiO<sub>2</sub> (B). XPS spectra were acquired on calcined materials (initial), after treating them in a reactor under a H<sub>2</sub> flow at 550 °C (H<sub>2</sub>-550 °C) followed by their exposure to air during material transfer, and reduced *in situ* at 300 °C or 450 °C in the pretreatment chamber of the XPS instrument (labelled H<sub>2</sub>-300 °C and H<sub>2</sub>-450 °C, respectively). Fitted blue, green and red traces correspond to XPS features due to Ga<sup>3+</sup>, Ga<sup>+</sup> and Ga<sup>0</sup> species, respectively.

Ga<sup>3+</sup> states with a distribution of 7, 23 and 70% (according to the fits). This comparison reveals that the reduction of Ga<sup>3+</sup> surface sites proceeds to a larger extend on  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  compared to Ga/SiO<sub>2</sub>-H<sub>2</sub>.

### Surface acidity studies by <sup>15</sup>N DNP SENS and FTIR

$\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and Ga/SiO<sub>2</sub>-H<sub>2</sub> catalysts were exposed to pyridine vapor at room temperature for 20 min, followed by outgassing at 150 °C for 15 min. The respective <sup>15</sup>N DNP SENS spectra are presented in Fig. 4A. In these spectra, strong BAS are identified by a peak at *ca.* 205 ppm due to protonated pyridine; furthermore, strong LAS appear at *ca.* 235 ppm, mild LAS at *ca.* 260 ppm, while weak LAS and weak BAS are evidenced with a peak at *ca.* 280 ppm.<sup>43,44</sup>  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  reveals two main peaks at *ca.* 237 ppm and 286 ppm. The peak due to strong LAS at 237 ppm was not detected by us previously in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  after evacuation at 100 °C.<sup>25</sup> The peak at 286 ppm, most likely contains contributions from Py adsorbed on weak LAS of the gallia phase and Py interacting with mild/weak BAS of the silica support.<sup>25</sup> Interestingly, Ga/SiO<sub>2</sub>-H<sub>2</sub> shows a similar <sup>15</sup>N DNP SENS spectrum compared to that of Ga/SiO<sub>2</sub> (outgassed at 100 °C),<sup>25</sup> and features a major peak due to Py on strong LAS at 236 ppm and a less intense peak due to Py on mild LAS at 260 ppm. In addition, a minor peak due to strong BAS at 206 ppm is present in Ga/SiO<sub>2</sub>-H<sub>2</sub> (Fig. 4A). The difference between the intensities of peaks at 283 ppm and 286 ppm in, respectively, Ga/SiO<sub>2</sub>-H<sub>2</sub> and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  is noteworthy and suggests a sizeable contribution of Py adsorbed on weak Ga-based LAS in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  compared to Ga/SiO<sub>2</sub>-H<sub>2</sub>.<sup>27</sup>



**Fig. 4** (A) <sup>15</sup>N DNP SENS spectra of <sup>15</sup>N-Py adsorbed on  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and Ga/SiO<sub>2</sub>-H<sub>2</sub>. <sup>15</sup>N-Py vapor was adsorbed at room temperature and desorbed under *ca.* 10<sup>-5</sup> mbar during 15 min at 150 °C. CO adsorption transmission FTIR results for calcined (B) and H<sub>2</sub>-treated materials (C). Catalysts were heated to 540 °C and outgassed overnight at *ca.* 10<sup>-5</sup> mbar. After cooling down to 50 °C, CO was introduced up to a pressure of *ca.* 27 mbar.



Complementary FTIR experiments were carried out to characterize the surface acidity of the studied catalysts. Py adsorption FTIR (Py-FTIR) results show the emergence of a band at *ca.* 1620 cm<sup>-1</sup> in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub>. As this band is absent in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>,<sup>25</sup> the appearance of this band in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> is consistent with the formation of strong LAS after H<sub>2</sub> pretreatment (Fig. S2†). The band at 1620 cm<sup>-1</sup> is present in Ga/SiO<sub>2</sub>,<sup>25</sup> and also in Ga/SiO<sub>2</sub>-H<sub>2</sub> (Fig. S2†). On the other hand, bands due to Py on weak/mild BAS located at *ca.* 1595 and 1589 cm<sup>-1</sup> are removed almost entirely in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> after outgassing at 100 °C, while these bands are detected in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> after evacuation at 200 °C.

Adsorption of CO on the four studied catalysts allows to compare the relative intensities of bands due to CO interacting with strong LAS (Fig. 4B and C). CO adsorbed on  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> and Ga/SiO<sub>2</sub> gives bands at *ca.* 2218 cm<sup>-1</sup> for both materials, although the intensity of adsorbed CO is notably stronger on Ga/SiO<sub>2</sub> relative to  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>. CO adsorbed on Ga/SiO<sub>2</sub>-H<sub>2</sub> gives a spectrum very similar to that of CO adsorbed on Ga/SiO<sub>2</sub>. In contrast, CO adsorbed on  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> gives a peak shifted slightly to higher wavenumbers, *i.e.* centered at 2221 cm<sup>-1</sup>, and with a notably higher intensity than in  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>, although the intensity is still lower than in Ga/SiO<sub>2</sub> or Ga/SiO<sub>2</sub>-H<sub>2</sub>.

### Hydrogen adsorption FTIR

The heterolytic splitting of H<sub>2</sub> on Ga-O linkages was used to identify and characterize surface sites capable to dissociate H<sub>2</sub> in the calcined and H<sub>2</sub>-treated materials. Dissociation of H<sub>2</sub> forms GaH and OH sites and the position of the GaH


bands scales with the bond strength and is indicative of the coordination geometry of Ga atoms, *i.e.*, it has been reported that Ga<sub>IV</sub>-H bands are found at *ca.* 2003 cm<sup>-1</sup> and Ga<sub>VI</sub>-H bands at *ca.* 1980 cm<sup>-1</sup> (for unsupported gallia).<sup>45</sup> Calcined and *in situ* H<sub>2</sub>-treated materials were evacuated at 540 °C for 2 h under *ca.* 10<sup>-4</sup> mbar. Subsequently, adsorption of H<sub>2</sub> of *ca.* 70 mbar was conducted at 300, 450 and 540 °C. Fig. 5A and B compare FTIR spectra after dissociation of H<sub>2</sub> focusing on the location of the Ga hydride bands of calcined  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> and Ga/SiO<sub>2</sub>, respectively. Fig. 5C and D show the spectra obtained after dissociation of H<sub>2</sub> on  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> and Ga/SiO<sub>2</sub>-H<sub>2</sub>, respectively. The dissociation of H<sub>2</sub> on  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> gives bands due to gallium hydrides at *ca.* 2037, 2012 and 1986 cm<sup>-1</sup> (Fig. 5A). In Ga/SiO<sub>2</sub>, narrower bands are found at higher frequencies at *ca.* 2073, 2058 and 2037 cm<sup>-1</sup> (Fig. 5B). The dissociation of H<sub>2</sub> at 300 °C on  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> produces bands at *ca.* 2073, 2058 and 2041 cm<sup>-1</sup> (Fig. 5C). These bands resemble closely the gallium hydride bands in Ga/SiO<sub>2</sub> (Fig. 5B). Dissociation of hydrogen on  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> at 450 and 540 °C yields an additional broad, lower frequency band at *ca.* 2021 cm<sup>-1</sup> (Fig. 5C). Except for a slight change of the relative intensities between the different bands, no notable shifts or appearance of new bands were detected on Ga/SiO<sub>2</sub>-H<sub>2</sub> at 300, 450 and 540 °C. When comparing Ga/SiO<sub>2</sub>-H<sub>2</sub> with Ga/SiO<sub>2</sub> at the three different temperatures, no substantial band shifts were detected between Ga/SiO<sub>2</sub>-H<sub>2</sub> and Ga/SiO<sub>2</sub>, although a shoulder at 2021 cm<sup>-1</sup> becomes notably more intense in Ga/SiO<sub>2</sub>-H<sub>2</sub> (at 450 and 540 °C) and the partial intensities of other bands change after H<sub>2</sub> treatment (Fig. 5D).

Lastly, STEM-EDX mappings were used to characterize the dispersion of Ga in the H<sub>2</sub>-treated catalysts and compare it to calcined catalysts. The images tentatively suggest a higher degree of dispersion of Ga in both H<sub>2</sub>-treated catalysts relative to the respective calcined catalysts (Fig. S3†).

### Discussion

In this work, we aimed to investigate the effect of H<sub>2</sub> pretreatment (550 °C, 2 h, undiluted H<sub>2</sub>) on the catalytic performance and structure of two silica-supported PDH catalysts, one is Ga/SiO<sub>2</sub> derived from gallium nitrate containing mostly an amorphous gallia phase, while the other one is a  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> catalyst, obtained by the incipient wetness impregnation of colloidal  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub> nanocrystals onto the SiO<sub>2</sub> support. After calcination,  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub> nanocrystals transform partially into  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>, yielding SiO<sub>2</sub>-supported, mixed-phase  $\gamma$ / $\beta$ -Ga<sub>2</sub>O<sub>3</sub> NPs. Calcined  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> and Ga/SiO<sub>2</sub> have been characterized in detail in our previous report.<sup>25</sup>

The Ga/SiO<sub>2</sub>-H<sub>2</sub> catalyst yields a low rate of propene formation (stable at around 3.5 mol C<sub>3</sub>H<sub>6</sub> mol Ga<sup>-1</sup> h<sup>-1</sup>), and its selectivity to propene is only *ca.* 50%. This catalyst does not deactivate with TOS and does not deposit any measurable amount of coke. Overall, the activity, selectivity and stability of Ga/SiO<sub>2</sub>-H<sub>2</sub> and Ga/SiO<sub>2</sub> are very similar (Fig. 1). In contrast, while the initial activity and selectivity of  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/



**Fig. 5 (A–D)** Transmission FTIR results of H<sub>2</sub> dissociation experiments. Panels show Ga-hydride bands for  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> (A); Ga/SiO<sub>2</sub> (B);  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>-H<sub>2</sub> (C); Ga/SiO<sub>2</sub>-H<sub>2</sub> (D). Materials in self-supported pellets were outgassed for 2 h under *ca.* 10<sup>-4</sup> mbar at 540 °C. Hydrogen adsorption was conducted at 300 °C, 450 °C and 540 °C at the equilibrium pressure of *ca.* 70 mbar of H<sub>2</sub>. The hydrogen exposure time at the given temperature was *ca.* 1–2 min, after which the specimen was cooled down to ambient temperature. H<sub>2</sub>-Treated materials were prepared *in situ* by heating  $\gamma$ -Ga<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub> and Ga/SiO<sub>2</sub> in *ca.* 130 mbar of H<sub>2</sub> at 550 °C for 2 h.



$\text{SiO}_2\text{-H}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  are similar (10.3 mol  $\text{C}_3\text{H}_6$  mol  $\text{Ga}^{-1}$   $\text{h}^{-1}$  and 72%, respectively), after 104 min TOS the activity and selectivity of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  are notably higher than that of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ . In addition,  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  deposits *ca.* 25% less coke as compared to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ . Therefore,  $\text{H}_2$  pretreatment attenuates the deactivation of calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  with TOS, primarily owing to a less pronounced decrease of the propene formation rate and the selectivity to propene with TOS, in combination with a lower degree of coking. In what follows, we rationalize the differences in the structure (bulk and surface) between  $\text{H}_2$ -treated and calcined  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  catalysts and relate this structural insight to the improved catalytic performance of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  discussed above.

*Ex situ* XAS (XANES and EXAFS analyses) experiments performed at the Ga K-edge in air-tight conditions suggest a change in the local coordination of Ga that is explained by a higher fraction of  $\text{Ga}_{\text{IV}}$  sites in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  than in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  as seen by a higher intensity of the white line feature at 10375 eV and a decrease in the average Ga–O distance in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ . Hydrogen treatment of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  leads to a strong decrease in the coordination number of the Ga–Ga sphere; to a lower extent, this is also observed for  $\text{Ga/SiO}_2$ . This result indicates that  $\text{H}_2$  treatment increases disorder of the supported  $\gamma/\beta\text{-Ga}_2\text{O}_3$  phase in the  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  catalyst. However, a loss in coherence length in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  is not revealed by dPDF analysis, yet this analysis also suggests an increased disorder, particularly in the short range structure (1.5–6 Å). Interestingly, a comparison of the dPDF data for the unsupported  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs before and after  $\text{H}_2$  treatment (500 °C) shows no detectable differences neither in the short range structure, nor in the medium-to-long range order.<sup>46</sup> STEM-EDX imaging suggests that the agglomeration of the gallia phase on the silica support in both reduced catalysts may be lower relative to the calcined catalysts (Fig. S3†).

In the *in situ* XANES experiments an additional (lower energy) edge feature is observed in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  under  $\text{H}_2$  flow above *ca.* 400 °C. The appearance of such a feature in the XANES spectra (*ca.* 10 370–10 373 eV) of reduced silica-supported gallia catalysts and Ga-containing zeolites during *in situ*  $\text{H}_2$  treatment has been ascribed previously either to the reduction of  $\text{Ga}^{3+}$  to  $\text{Ga}^+$ , or  $\text{Ga}^0$  species, or to a non-reductive change of the coordination environment of  $\text{Ga}^{3+}$  sites, including the formation of Ga-hydrides or Ga-alkyls.<sup>16,20,21,23,24</sup> Thus, the observed feature in the *in situ* XANES data of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  is consistent with a partial reduction of  $\gamma/\beta\text{-Ga}_2\text{O}_3$  in the  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  material and/or a change in the coordination environment of Ga. Interestingly, this feature disappears after the cooling down of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  under a He flow, in accordance with the lack of this specific low-energy edge feature in the *ex situ* XANES experiments, and may be due to i) the reoxidation of reduced Ga species by the protons of water or surface silanol groups or ii) surface relaxation leading to a loss of low-coordinated  $\text{Ga}_{\text{III}}$  sites formed at high temperature during  $\text{H}_2$  treatment.

Analysis of the Ga 2p XPS region confirms clearly the reduction of  $\text{Ga}^{3+}$  sites in both catalysts after exposing them in the pretreatment chamber to 300 mbar of  $\text{H}_2$  for 1 h at 300 and 450 °C. The reduction is evidenced by the appearance of two features at lower BE ascribed to  $\text{Ga}^+$  or  $\text{Ga}^0$  states. The reduction of  $\text{Ga}^{3+}$  sites proceeds, according to XPS data fits, to a larger extent in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  than in  $\text{Ga/SiO}_2\text{-H}_2$ . The reduction of  $\text{Ga}^{3+}$  sites is not detected in the Ga 3d region (Fig. S4 and S5†). This is explained by the lower penetration depth for the Ga 2p relative to the Ga 3d XPS region analysis (the inelastic mean free path,  $\lambda$ , is *ca.* 0.9 and 2.4 nm for the Ga 2p and Ga 3d electron energies, respectively), and therefore the formation of  $\text{Ga}^+$  or  $\text{Ga}^0$  states is mostly a surface phenomenon.  $\text{Ga}^+$  or  $\text{Ga}^0$  states have been observed previously by XPS of  $\text{H}_2$ -treated  $\text{Ga}_2\text{O}_3/\text{SiO}_2$  and the formation of metallic  $\text{Ga}^0$  was explained by the disproportionation of  $\text{Ga}^+$  into  $\text{Ga}^{3+}$  and  $\text{Ga}^0$ ; it has been suggested that the high vacuum conditions of the XPS measurement may destabilize  $\text{Ga}^+$  species and induce disproportionation.<sup>19</sup>

It is interesting to note that  $\text{Ga}^+$  sites formed during  $\text{H}_2$  pretreatment at 650 °C of a silica-supported amorphous gallia catalyst have been suggested to be inactive in PDH as the reaction rate declined by *ca.* 30% after the  $\text{H}_2$  pretreatment.<sup>20</sup> In addition, deactivation of the highly selective ( $\geq 93\%$ ) single-site  $[(\equiv\text{SiO})_3\text{Ga}-(\text{XOSi}\equiv)]$  PDH catalyst after 20 h of TOS at 550 °C has tentatively been linked to the reduction of  $\text{Ga}^{3+}$  surface sites to  $\text{Ga}^+$ , as seen by the appearance of a low-energy edge feature in the Ga K edge XANES spectrum.<sup>21</sup> In contrast to these results,  $\text{H}_2$  pretreatment attenuates the deactivation of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  with time on stream despite the formation of reduced Ga species. This may be explained by the low amount of reduced Ga species and/or their subsequent disproportionation into  $\text{Ga}^{3+}$  and  $\text{Ga}^0$ .

Comparison of the Ga–O sites that are capable of heterolytically dissociating  $\text{H}_2$  in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  and  $\text{Ga/SiO}_2$  reveals that three major GaH bands appear in  $\text{Ga/SiO}_2$  at higher wavenumbers (2073, 2058 and 2037  $\text{cm}^{-1}$ ) than in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  (2037, 2012 and 1986  $\text{cm}^{-1}$ ). This is consistent with stronger GaH bonds in  $\text{Ga/SiO}_2$  which, assuming these  $\text{Ga}^{3+}$ –O sites are also active in PDH, may be difficult to regenerate by  $\text{H}_2$  coupling, leading to a lower catalytic activity of  $\text{Ga/SiO}_2$ . Interestingly, higher frequency GaH bands that are similar to those in  $\text{Ga/SiO}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$  can be observed in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ , most clearly when using 300 °C for  $\text{H}_2$  dissociation. At higher dissociation temperatures of 450 °C or 540 °C, the main GaH bands in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  are similar to those detected in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  such as the broad lower frequency bands at *ca.* 2021  $\text{cm}^{-1}$ , although the bands at the higher wavenumbers, typical for  $\text{Ga/SiO}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$ , remain (Fig. 5). Comparison of the GaH bands obtained using silica-supported catalysts of this work with that of unsupported  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs after  $\text{H}_2$  pretreatment (500 °C) indicates that the more active catalysts feature lower-frequency GaH bands (corresponding to weak GaH bonds), and that the number of distinct GaH bands increases in




silica-supported catalysts, likely due to the appearance of interfacial sites (with the support).<sup>46</sup> Consequently, the Ga-weight normalized activity of silica-supported catalysts is higher with respect to the unsupported catalysts, *viz.* initial activity of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  is *ca.* 4.8 times higher relative to  $\gamma\text{-Ga}_2\text{O}_3$ , while the surface area of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  is only *ca.* 2 times higher.

$^{15}\text{N}$  DNP SENS experiments probe the surface acidity and reveal that the intensity of the peak at *ca.* 286 ppm (desorption temperature 150 °C), which likely has contributions from Py bonded to weak  $\text{Ga}^{3+}$  LAS and mild/weak BAS (silanols or  $\text{GaOH}$  sites, which do not protonate pyridine), is notably higher in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  relative to  $\text{Ga/SiO}_2\text{-H}_2$ . Py-FTIR experiments show that while Py bonded to mild/weak BAS (bands at *ca.* 1595 and 1589  $\text{cm}^{-1}$ ) is almost entirely removed from  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  at 100 °C pyridine desorption temperature ( $T_{\text{des}}$ ), the band at 1595  $\text{cm}^{-1}$  remains on  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  at  $T_{\text{des}} = 200$  °C (Fig. S2†). This may point at the consumption of some of the surface silanols by the reduced Ga species ( $\text{Ga}^+$  or  $\text{Ga}^0$ ) with the formation of  $\text{Ga}_{\text{IV}}$  sites (*vide infra*). Given that the Ga loadings in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$  are similar, it is likely that the fraction of weak LAS is higher in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  than in  $\text{Ga/SiO}_2\text{-H}_2$  and this contributes to the higher initial activity of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  compared to  $\text{Ga/SiO}_2\text{-H}_2$ . Both  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$  contain a peak due to Py on strong  $\text{Ga}^{3+}$  LAS at 236–237 ppm. FTIR experiments with CO probe molecule indicate a notably higher intensity of the CO- $\text{Ga}^{3+}$  adduct in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  compared to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ . An increased dispersion of the gallia phase in the  $\text{H}_2$ -treated material may contribute to this increase of intensity of bound CO. However, since a similar increase of dispersion is also observed in  $\text{Ga/SiO}_2\text{-H}_2$  but the intensity of adsorbed CO for this material increases only slightly relative to  $\text{Ga/SiO}_2$ , it is likely that the formation of additional strong LAS in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  is responsible for the increased intensity of bound CO in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and the blue shift of the CO band (from 2218 to 2221  $\text{cm}^{-1}$ ). The formation of strong LAS in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  is also consistent with Py-FTIR data which shows the emergence of a band at *ca.* 1620  $\text{cm}^{-1}$  in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ . This band is weak in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  but is notably stronger in  $\text{Ga/SiO}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$  (Fig. S2†). We cannot exclude that the formation of these strong LAS is related to the dispersion of Ga after interaction of reduced  $\text{Ga}^+$  or  $\text{Ga}^0$  species with surface silanols (Scheme 1). These reduced

species may disproportionate or get oxidized by  $\text{H}_2\text{O}$  forming tetrahedral  $\text{Ga}^{3+}$  sites. Consistent with this hypothesis is the fact that strong BAS are observed in  $\text{Ga/SiO}_2\text{-H}_2$  and previously also in  $\text{Ga/SiO}_2$ , *i.e.*, in materials where an amorphous gallia phase likely co-exists with a small amount of a gallosilicate phase that is responsible for the strong Brønsted acidity. However, we do not observe substantial amounts of strong BAS in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  (or  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ ).<sup>25</sup> The higher amounts of reduced Ga species in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$  relative to  $\text{Ga/SiO}_2$  may be due to the presence of gallosilicate species in  $\text{Ga/SiO}_2$ , which are not reduced in the conditions used in this work.

Overall, the attenuated deactivation of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  (due to the more stable selectivity to propene and reduced coking with TOS) correlates with an increased disorder of  $\gamma\beta\text{-Ga}_2\text{O}_3$  NPs in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ . dPDF analysis of *in situ* X-ray total scattering data suggests that the structural disorder of silica-supported  $\gamma\beta\text{-Ga}_2\text{O}_3$  NPs increases during  $\text{H}_2$  pretreatment and remains only in the local structure of  $\gamma\beta\text{-Ga}_2\text{O}_3$ . The surface reduction of  $\text{Ga}^{3+}$  sites is confirmed by the Ga 2p XPS spectra and, potentially, also by *in situ* XANES experiments (appearance of a low-energy edge feature).  $\text{H}_2$  pretreatment leads to the dissociation of hydrogen and the formation of several gallium hydride sites, some of which are similar in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$ ,  $\text{Ga/SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2$  but are not observed in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ . The additional formation of  $\text{Ga}_{\text{IV}}$  sites in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  (according to a comparison of the XANES and EXAFS data of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ ) is responsible for more abundant strong Lewis acidity in this material (according to FTIR experiments with CO and Py probe molecules). We propose that those  $\text{Ga}_{\text{IV}}$  sites are mostly due to disordered  $\gamma\beta\text{-Ga}_2\text{O}_3$  NPs, yet, there may be a contribution to the formed  $\text{Ga}_{\text{IV}}$ -based strong LAS from the interaction of reduced gallium species ( $\text{Ga}^+$  and/or  $\text{Ga}^0$ ) with silica (Scheme 1), as indicated by the shorter distances of the second coordination sphere of Ga sites after  $\text{H}_2$  pretreatment. An alternative mechanism for the formation of new  $\text{Ga}_{\text{IV}}$  sites is the disproportionation of  $\text{Ga}^+$  species (to  $\text{Ga}^{3+}$  and  $\text{Ga}^0$ ). However, while the interaction of  $\text{Ga}^+$  and/or  $\text{Ga}^0$  is expected to be comparable in both  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\text{Ga/SiO}_2\text{-H}_2$ , and the catalytic performance of  $\text{Ga/SiO}_2\text{-H}_2$  remains unchanged relative to  $\text{Ga/SiO}_2$  (in contrast to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ ), the newly formed  $\text{Ga}_{\text{IV}}$  sites in disordered  $\gamma\beta\text{-Ga}_2\text{O}_3$  NPs of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  are likely responsible for the attenuated decrease of the propene selectivity with TOS



**Scheme 1** Proposed mechanism for formation of new  $\text{Ga}_{\text{IV}}$  sites in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  through the reductive disordering of  $\gamma\beta\text{-Ga}_2\text{O}_3$  NPs and the subsequent interaction of  $\text{Ga}^+$  and/or  $\text{Ga}^0$  species with the surface silanols.



for this material. Further,  $^{15}\text{N}$  DNP SENS and Py-FTIR data indicate that weak LAS are more abundant in  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  than in  $\text{Ga/SiO}_2\text{-H}_2$ , and this correlates with the higher initial activity of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  and the presence of lower frequency GaH bands in this catalyst. Note that the cracking rate on  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  has decreased by *ca.* 25% relative to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ , and it remained unchanged (within the experimental error) for  $\text{Ga/SiO}_2\text{-H}_2$  relative to  $\text{Ga/SiO}_2$ . Thus, the attenuated loss of activity and propene selectivity with TOS for  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  (relative to  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ ) is probably due to the formation of less active but more stable  $\text{Ga}_{\text{IV}}$  sites (due to reduced coking) in the more disordered  $\gamma/\beta\text{-Ga}_2\text{O}_3$  and/or consumption of unselective Ga sites during the  $\text{H}_2$  treatment, while the higher initial activity and selectivity of silica-supported catalysts based on  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs relative to amorphous gallia is due to the presence of weak LAS in  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs.

## Conclusions

We reported that  $\text{H}_2$  pretreatment (550 °C, 2 h) of  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2$ , a PDH catalyst containing silica-supported nanocrystalline  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs, attenuates its deactivation with time on stream. At the same time,  $\text{H}_2$  pretreatment does not impact notably the catalytic performance of a  $\text{Ga/SiO}_2$  catalyst containing an amorphous gallia phase and a small amount of a gallosilicate phase, identified by its strong Brønsted acidity. We observe that on the silica support,  $\text{H}_2$  pretreatment induces a reductive disorder of nanocrystalline  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs. This reaction yields additional strong Lewis acid sites, but does not generate strong Brønsted acid sites (that is, it avoids forming a gallosilicate phase). These new sites in the  $\gamma\text{-Ga}_2\text{O}_3/\text{SiO}_2\text{-H}_2$  catalyst may form due to the disproportionation of  $\text{Ga}^+$  species (observed by XPS), the anchoring of  $\text{Ga}^+$  or  $\text{Ga}^0$  species onto silanol groups, and/or an  $\text{H}_2$ -induced local disordering of nanocrystalline  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs; the latter mechanism appears to contribute the most. Our results suggest that the active sites in the silica-supported gallia catalysts based on strong LAS (*i.e.*,  $\text{Ga}_{\text{IV}}$  sites formed after the  $\text{H}_2$  pretreatment) are less active but more stable with TOS than weak LAS of  $\gamma/\beta\text{-Ga}_2\text{O}_3$  NPs.

## Author contributions

P. C.-F. and A. F. designed the research project and planned the experimental work. P. C.-F. carried out the preparation of materials, characterization and testing of the catalysts, and data analysis. A. I. S. performed hydrogen adsorption FTIR experiments and supervised data interpretation. A. V. Y. carried out  $^{15}\text{N}$  DNP SENS experiments, processed the results and contributed to data analysis. I. P. P. and A. V. B. conducted XPS experiments, data processing and analysis. P. M. A. supervised XAS and dPDF experiments and contributed to the data analysis. The data were discussed among all co-authors. P. C.-F. and A. F. wrote the first version of the draft

that was edited by all authors. All authors have given approval to the final version of the manuscript.

## Conflicts of interest

The authors declare no conflicts of interest.

## Acknowledgements

Dr. Agnieszka Kierzkowska is thanked for STEM-EDX measurements and ICP analysis. Dr. Dragos Stoian (SNBL/ESRF) is acknowledged for his support during XAS measurements. The Swiss National Science Foundation is acknowledged for the partial funding of this work (grant IZSEZ0\_178677). P. M. A. acknowledges funding from the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (grant agreement No. 819573). A. V. Y. and C. C. gratefully acknowledge ETH+ Project SynthMatLab for the financial support. I. P. P. and A. V. B. thank the budget project of the Ministry of Science and Higher Education of the Russian Federation (AAAA-A21-121011390011-4) for support of the XPS measurements at the Boreskov Institute of Catalysis.

## Notes and references

- 1 J. J. H. B. Sattler, J. Ruiz-Martinez, E. Santillan-Jimenez and B. M. Weckhuysen, *Chem. Rev.*, 2014, **114**, 10613–10653.
- 2 Z. P. Hu, D. Yang, Z. Wang and Z. Y. Yuan, *Chin. J. Catal.*, 2019, **40**, 1233–1254.
- 3 S. Chen, X. Chang, G. Sun, T. Zhang, Y. Xu, Y. Wang, C. Pei and J. Gong, *Chem. Soc. Rev.*, 2021, **50**, 3315–3354.
- 4 C. Copéret, F. Allouche, K. W. Chan, M. P. Conley, M. F. Delley, A. Fedorov, I. B. Moroz, V. Mougel, M. Pucino, K. Searles, K. Yamamoto and P. A. Zhizhko, *Angew. Chem., Int. Ed.*, 2018, **57**, 6398–6440.
- 5 S. R. Docherty, L. Rochlitz, P. A. Payard and C. Copéret, *Chem. Soc. Rev.*, 2021, **50**, 5806–5822.
- 6 A. Bhan and W. N. Delgass, *Catal. Rev.: Sci. Eng.*, 2008, **50**, 19–151.
- 7 J. R. Mowry, D. C. Martindale and A. H. P. Hall, *Arabian J. Sci. Eng.*, 1985, **10**, 367–375.
- 8 M. Monai, M. Gambino, S. Wannakao and B. M. Weckhuysen, *Chem. Soc. Rev.*, 2021, **50**, 11503–11529.
- 9 R. Fricke, H. Kosslick, G. Lischke and M. Richter, *Chem. Rev.*, 2000, **100**, 2303–2405.
- 10 V. Kanazirev, G. L. Price and G. Tyuliev, *Zeolites*, 1992, **12**, 846–850.
- 11 M. W. Schreiber, C. P. Plaisance, M. Baumgärtl, K. Reuter, A. Jentys, R. Bermejo-Deval and J. A. Lercher, *J. Am. Chem. Soc.*, 2018, **140**, 4849–4859.
- 12 N. M. Phadke, E. Mansoor, M. Bondil, M. Head-Gordon and A. T. Bell, *J. Am. Chem. Soc.*, 2019, **141**, 1614–1627.
- 13 E. Mansoor, M. Head-Gordon and A. T. Bell, *ACS Catal.*, 2018, **8**, 6146–6162.



14 N. M. Phadke, J. Van Der Mynsbrugge, E. Mansoor, A. B. Getsoian, M. Head-Gordon and A. T. Bell, *ACS Catal.*, 2018, **8**, 6106–6126.

15 E. J. M. Hensen, M. García-Sánchez, N. Rane, P. C. M. M. Magusin, P. H. Liu, K. J. Chao and R. A. Van Santen, *Catal. Lett.*, 2005, **101**, 79–85.

16 G. D. Meitzner, E. Iglesia, J. E. Baumgartner and E. S. Huang, *J. Catal.*, 1993, **140**, 209–225.

17 A. I. Serykh and M. D. Amiridis, *Surf. Sci.*, 2009, **603**, 2037–2041.

18 I. Takahara, M. Saito, M. Inaba and K. Murata, *Catal. Lett.*, 2004, **96**, 29–32.

19 A. I. Serykh and M. D. Amiridis, *Surf. Sci.*, 2010, **604**, 1002–1005.

20 V. J. Cybulskis, S. U. Pradhan, J. J. Lovón-Quintana, A. S. Hock, B. Hu, G. Zhang, W. N. Delgass, F. H. Ribeiro and J. T. Miller, *Catal. Lett.*, 2017, **147**, 1252–1262.

21 K. Searles, G. G. Siddiqi, O. V. Safonova and C. Copéret, *Chem. Sci.*, 2017, **8**, 2661–2666.

22 C. Copéret, A. Comas-Vives, M. P. Conley, D. P. Estes, A. Fedorov, V. Mougel, H. Nagae, F. Núñez-Zarur and P. A. Zhizhko, *Chem. Rev.*, 2016, **116**, 323–421.

23 L. Rochlitz, K. Searles, D. F. Nater, S. R. Docherty, D. Gioffrè and C. Copéret, *Helv. Chim. Acta*, 2021, **104**, e2100078.

24 A. Getsoian, U. Das, J. Camacho-Bunquin, G. Zhang, J. R. Gallagher, B. Hu, S. Cheah, J. A. Schaidle, D. A. Ruddy, J. E. Hensley, T. R. Krause, L. A. Curtiss, J. T. Miller and A. S. Hock, *Catal. Sci. Technol.*, 2016, **6**, 6339–6353.

25 P. Castro-Fernández, D. Mance, C. Liu, I. B. Moroz, P. M. Abdala, E. A. Pidko, C. Copéret, A. Fedorov and C. R. Müller, *ACS Catal.*, 2021, **11**, 907–924.

26 W. Jochum, S. Penner, K. Föttinger, R. Kramer, G. Rupprechter and B. Klötzer, *J. Catal.*, 2008, **256**, 268–277.

27 P. Castro-Fernández, M. Kaushik, Z. Wang, D. Mance, E. Kountouri, E. Willinger, P. M. Abdala, C. Copéret, A. Lesage, A. Fedorov and C. R. Müller, *Chem. Sci.*, 2021, **12**, 15273–15283.

28 M. Chen, J. Xu, F. Z. Su, Y. M. Liu, Y. Cao, H. Y. He and K. N. Fan, *J. Catal.*, 2008, **256**, 293–300.

29 W. Van Beek, O. V. Safonova, G. Wiker and H. Emerich, *Phase Transitions*, 2011, **84**, 726–732.

30 C. S. S. R. Kumar, *X-ray and Neutron Techniques for Nanomaterials Characterization*, Springer Nature, Berlin, 2016.

31 B. Ravel and M. Newville, *J. Synchrotron Radiat.*, 2005, **12**, 537–541.

32 J. Åhman, G. Svensson and J. Albertsson, *Acta Crystallogr., Sect. C: Cryst. Struct. Commun.*, 1996, **52**, 1336–1338.

33 P. J. Chupas, K. W. Chapman and G. J. Halder, *J. Am. Chem. Soc.*, 2011, **133**, 8522–8524.

34 P. Juhás, T. Davis, C. L. Farrow and S. J. L. Billinge, *J. Appl. Crystallogr.*, 2013, **46**, 560–566.

35 A. Zagdoun, G. Casano, O. Ouari, M. Schwarzwälder, A. J. Rossini, F. Aussenac, M. Yulikov, G. Jeschke, C. Copéret, A. Lesage, P. Tordo and L. Emsley, *J. Am. Chem. Soc.*, 2013, **135**, 12790–12797.

36 A. Zagdoun, A. J. Rossini, D. Gajan, A. Bourdolle, O. Ouari, M. Rosay, W. E. Maas, P. Tordo, M. Lelli, L. Emsley, A. Lesage and C. Copéret, *Chem. Commun.*, 2012, **48**, 654–656.

37 J. H. Scofield, *J. Electron Spectrosc. Relat. Phenom.*, 1976, **8**, 129–137.

38 P. Castro-Fernández, M. V. Blanco, R. Verel, E. Willinger, A. Fedorov, P. M. Abdala and C. R. Müller, *J. Phys. Chem. C*, 2020, **124**, 20578–20588.

39 K. Nishi, K. Shimizu, M. Takamatsu, H. Yoshida, A. Satsuma, T. Tanaka, S. Yoshida and T. Hattori, *J. Phys. Chem. B*, 1998, **102**, 10190–10195.

40 K. Groden, F. D. Vila, L. Li, S. R. Bare, S. L. Scott and J.-S. McEwen, *J. Phys. Chem. C*, 2021, **125**, 27901–27908.

41 L. Yang, J. L. Bourque, J. A. McLeod, P. Shen, K. M. Baines and L. Liu, *Inorg. Chem.*, 2017, **56**, 2985–2991.

42 R. Carli and C. L. Bianchi, *Appl. Surf. Sci.*, 1994, **74**, 99–102.

43 I. B. Moroz, K. Larmier, W.-C. Liao and C. Copéret, *J. Phys. Chem. C*, 2018, **122**, 10871–10882.

44 W. R. Gunther, V. K. Michaelis, R. G. Griffin and Y. Roman-Leshkov, *J. Phys. Chem. C*, 2016, **120**, 28533–28544.

45 S. E. Collins, M. A. Baltanás and A. L. Bonivardi, *Langmuir*, 2005, **21**, 962–970.

46 P. Castro-Fernández, D. Mance, C. Liu, P. Abdala, E. Willinger, A. A. Rossinelli, A. I. Serykh, E. A. Pidko, C. Copéret, A. Fedorov and C. R. Müller, *J. Catal.*, 2022, **408**, 155–164.

