



Cite this: *Mater. Adv.*, 2022, 3, 6566

## *In situ* CsPbBr<sub>3</sub> architecture engineered in electrospun fibers and its ultrafast charge-transfer dynamics<sup>†</sup>

Kaliyamoorthy Justice Babu,<sup>a</sup> Gurpreet Kaur,<sup>a</sup> Ayushi Shukla,<sup>a</sup> Arshdeep Kaur,<sup>a</sup> Himanshu Bhatt,<sup>a</sup> Nandan Ghorai,<sup>a</sup> Goutam De<sup>a</sup> and Hirendra N. Ghosh<sup>a</sup> <sup>\*ab</sup>

All-inorganic lead halide perovskite nanocrystals (NCs) have witnessed a rapid progression in the field of optoelectronics as well as photovoltaic applications. However, their environmental instability, tedious synthesis protocols, and post treatments hinder their further development for energy-harvesting devices. However, the aforementioned obstacles can be easily tackled by engineering them with a piezoelectric polymer, *in situ* perovskite construction, and by encapsulation. To date, the fundamental photophysical study of piezoelectric polymers with perovskite materials is still in early phase, and deeper understanding could illustrate a road map for their further advancement in solar cells and photodetectors, which is the main focus of this study. Herein, we present a facile route for the synthesis of highly stable cesium lead bromide (CsPbBr<sub>3</sub>) inside poly(vinylidene fluoride)-co-hexafluoropropylene (PVDF-HFP) fibers using a single step *in situ* electrospinning technique. X-Ray diffraction analysis depicted the successful formation of the  $\beta$ -phase in PVDF-HFP along with CsPbBr<sub>3</sub> during the electrospinning process. High-resolution transmission electron microscopy (HR-TEM) images clearly evidenced the arrangement of CsPbBr<sub>3</sub> inside the fiber matrix. Moreover, the synthesized CsPbBr<sub>3</sub>@PVDF-HFP fibers exhibited narrow light emission, which supported the optical and structural analysis. To understand the charge-transfer process in the CsPbBr<sub>3</sub>@PVDF-HFP fibers, transient absorption (TA) spectroscopy was employed. Different pump excitations were employed to identify the carrier-relaxation mechanism in the type-I CsPbBr<sub>3</sub>@PVDF-HFP fiber architecture. TA spectroscopy studies clearly suggested the transfer of charge carriers from CsPbBr<sub>3</sub> to PVDF-HFP upon 300 nm pump excitation, which was a thermodynamically viable process. Our results provide a facile and effective strategy for the preparation of a stable perovskite architecture and an in depth study of the photophysical properties, which could provide significant assistance in the development of highly efficient perovskite-based solar cell and photodetector applications.

Received 4th May 2022,  
Accepted 5th July 2022

DOI: 10.1039/d2ma00503d

[rsc.li/materials-advances](http://rsc.li/materials-advances)

## Introduction

The rapid emergence of optoelectronic devices based on all-inorganic metal halides (CsPbX<sub>3</sub>, X = Cl, Br, I) perovskite materials have attracted tremendous interest owing to their

tunable photoluminescence (PL) across the whole visible spectrum (400–700 nm), high PL quantum yield (QY), narrow emission width, and fast carrier diffusion.<sup>1,3</sup> However, perovskite materials have some obstacles, including poor stability against water and polar solvents, as drawbacks that largely limit their practical applicability.<sup>4,5</sup> Thus number of methods have been explored to stabilize the perovskite nanomaterials encapsulated with other matrices, including silica, zirconia, and polymers for the applications of light-emitting diodes (LED), visible-light communication, and X-ray scintillators.<sup>6–9</sup> As a state-of-the-art technique, electrospinning is considered one of the most effective techniques to prepare nanocrystalline fibers.<sup>10</sup> Moreover, nanofibers can act as an effective support for the functional materials, including metal nanoparticles and quantum dots (QDs) nanocrystals. Polyvinyl pyrrolidone (PVP), poly(methyl methacrylate)

<sup>a</sup> Institute of Nano Science and Technology, SAS Nagar, Sector 81, Mohali Punjab – 140306, India. E-mail: [hnghosh@inst.ac.in](mailto:hnghosh@inst.ac.in), [hnghosh2004@gmail.com](mailto:hnghosh2004@gmail.com)

<sup>b</sup> Radiation and Photochemistry Division, Bhabha Atomic Research Centre, Mumbai – 400085, India

<sup>†</sup> Electronic supplementary information (ESI) available: Experimental details, instrumentation details, optical studies, EDS analysis, quantum yield measurement, low temperature TA spectra, kinetics and tables. See DOI: <https://doi.org/10.1039/d2ma00503d>

<sup>‡</sup> Present address: S. N. Bose National Centre for Basic Sciences, Salt Lake, Kolkata 700106, India.



(PMMA), and polystyrene (PS) polymers have been efficiently utilized for the synthesis of perovskite nanofibers and these are highly stable under ambient atmosphere. Moreover, these materials are not suitable for energy-harvesting purposes owing to the insulating nature of aforementioned polymers.<sup>11–13</sup> Polyvinylidene fluoride (PVDF) is one of the well-known piezoelectric polymers that have great potential for use in mechanical energy-harvesting techniques, sensors, and biomedical applications due to its lightweight, soft, and biocompatible nature.<sup>14,15</sup> Moreover, PVDF being a semicrystalline polymer resides in five crystalline phases in nature, *i.e.*,  $\alpha$ ,  $\beta$ ,  $\gamma$ ,  $\delta$ , and  $\varepsilon$ . Amid these phases, the  $\beta$  and  $\gamma$  phase are polar in nature and in the electroactive forms, particularly the  $\beta$  phase, which exhibits piezoelectric, pyroelectric, and ferroelectric properties.<sup>14–17</sup> Moreover, PVDF polymer is hydrophobic in nature and it can effectively prevent the degradation of  $\text{CsPbBr}_3$  from polar solvents, which would improve the stability. Wang *et al.* *in situ*-encapsulated  $\text{CsPbBr}_3$  spheres using an electrospray method with polyvinylidene fluoride for cell-imaging applications.<sup>18</sup> Further, unusual stability and temperature-dependent properties have been reported by Pan and co-workers.<sup>19</sup> Recently, piezoelectric nanogenerators have been widely reported with PVDF along with different types of perovskites. In addition to that, Sultana *et al.* demonstrated improvements in the photocurrent could be achieved with the use of a methylammonium lead iodide ( $\text{CH}_3\text{NH}_3\text{PbI}_3$ ) and  $\beta$ -phase poly(vinylidene fluoride) composite.<sup>20</sup> Improved acoustic nanogenerators comprising methylammonium lead bromide ( $\text{CH}_3\text{NH}_3\text{PbBr}_3$ ) and poly(vinylidene fluoride) (PVDF) nanofibers were reported by Mandal and co-workers using an electrospinning process.<sup>21</sup>

The improved photocurrent in the aforesaid materials could be due to the formation of a high degree of  $\beta$ -phase formation. The  $\beta$ -phase in the PVDF matrix is nucleated by perovskite QDs using surface electrostatic interaction to transform the  $\alpha$  phase into the  $\beta$ -phase. Fang *et al.* incorporated PVDF-HFP into  $\text{CH}_3\text{NH}_3\text{PbI}_3$  solution for solar-cell applications and found that PVDF-HFP could improve the carrier lifetimes and reduce the charge-transfer resistance, which could collectively enhance the solar-cell efficiency.<sup>22</sup> Moreover, upon the excitation of perovskite nanocrystals, excitons were created within the nanocrystals, which further improved the polarizability in the PVDF polymer, reducing the electron–hole recombination and increase the charge transfer.<sup>20–22</sup> These results clearly evidenced that these materials could prove to be an asset for optoelectronic applications.

In addition, Dong *et al.* synthesized  $\text{CsPbBr}_3$ /PVP fibers using a microfluidic electrostatic spinning method. However, the microfluidic electrostatic spinning technique could not meet the high-rate throughput of fibers owing to the strict standards on the precursor materials.<sup>23</sup> Further, Cheng's group developed *in situ* methylammonium lead halide ( $\text{MAPbX}_3$ , X = Cl, Br, and I) perovskite at a large scale inside polyacrylonitrile (PAN) nanofiber films based on a microfluidic blow spinning (MBS) technique.<sup>24</sup> This method influenced the unique advantages, including mild reaction conditions, straightforward operation, low cost, and scalability. However, even a small

variation in the polymer concentration, gas pressure, viscosity, and flow rate could lead to capillary instability, dripping, clogging, and fly formation, strictly affecting the continuous fiber formation.<sup>25</sup> Importantly, the electrospinning process can effectively circumvent the aforesaid demerits and support the development of the *in situ* architecture of  $\text{CsPbBr}_3$  along with the formation of the  $\beta$ -phase in PVDF-HFP fibers.

So far, only limited reports are available in the literature on this subject, which might be due to the lack of fundamental evidence present in the earlier reports. The limited knowledge regarding the photophysical aspects of these polymer-embedded perovskite seems to be a hindrance to the further development progress of these polymer–perovskite-based photovoltaics. In order to make progress, the profound physical properties of the perovskite-encapsulated PVDF matrix should be addressed, which could assist in effective device fabrication. The charge-carrier dynamics, including charge separation, carrier relaxation, and carrier transfer, and recombination processes occur within the sub-picosecond time scale and can be studied employing transient absorption (TA) spectroscopy, which should also motivate further improvements for practical device applications.<sup>26–28</sup> In the present study, we synthesized  $\text{CsPbBr}_3$  inside polymer fibers based on a one-step *in situ* electrospinning strategy. To the best of our knowledge, there has been no detailed study of the charge-carrier dynamics in confined media, especially perovskite nanoparticles embedded in piezoelectric PVDF-HFP fibers. Consequently, we investigated the charge-carrier dynamics of *in situ*-encapsulated  $\text{CsPbBr}_3$  in a PVDF-HFP polymer matrix using transient absorption spectroscopic studies to explore the possibilities for application in highly efficient solar cells and photodetectors.

## Results and discussion

A single solution containing PVDF-HFP,  $\text{CsBr}$ , and  $\text{PbBr}_2$  was dissolved in DMF (details in the ESI†) prior to the formation of electrospun fibers. During the electrospinning, the tip of the needle was dipped in to a solution containing PVDF-HFP,  $\text{Cs}^+$ ,  $\text{Pb}^{2+}$ , and  $\text{Br}^-$  ions, for drawing the solution into a cone-like structure, termed a Taylor cone, under a high electric field. Then the solution was stretched along the axis due to the charge accumulation followed by repulsion of the charges. The *in situ* growth of  $\text{CsPbBr}_3$  inside the fibers took place with simultaneous solvent evaporation and the fiber was collected on the drum collector (Fig. 1).

### *In situ* $\text{CsPbBr}_3$ architecture engineering in electrospun PVDF-HFP fibers

The *in situ* formation mechanism of  $\text{CsPbBr}_3$  along with the formation of the  $\beta$ -phase in PVDF-HFP during the electrospinning process are schematically represented in Fig. 1. Commonly, the bare PVDF-HFP exhibits the  $\alpha$ -phase owing to its random orientation of dipoles that leads to net average polarization, represented as a non-polar phase. Owing to its aforesaid characteristics, the  $\alpha$ -phase of PVDF-HFP fails to produce piezo- and pyroelectric properties.






Fig. 1 Schematic illustration for the *in situ* growth of  $\text{CsPbBr}_3$  in the PVDF-HFP polymers via a one-step electrospinning method.

On the other hand, the  $\beta$ -phase, in which the molecular dipoles are entirely aligned in one direction, generates spontaneous polarization, which makes the non-polar phase useful for a wide range of applications. However,  $\beta$ -phase formation needs the use of expensive and tedious techniques, including poling, mechanical stretching, and ball milling. Among these, electrospinning results in a partial phase transition to the polar  $\beta$ -phase. In order to enhance the polarizability number, fillers have been utilized that electrostatically interact with  $-\text{CF}_2$  or  $-\text{CH}_2$  units that can nucleate the polar phase, which promotes the superior piezo- and pyroelectric properties. Recently, perovskite materials have been efficiently used for optoelectronic as well as photovoltaic applications.<sup>20–22</sup> Owing to their ionic nature, perovskite materials easily degrade with moisture and polar solvents, which hinders their practical applications. To improve the stability as well as the feasibility of utilizing perovskites, such materials have been engineered with a piezoelectric polymer matrix. Here, the electrospinning technique was concurrently used for the formation of the polar  $\beta$ -phase along with the *in situ* formation of  $\text{CsPbBr}_3$ . *In situ*-formed  $\text{CsPbBr}_3$  acted as the filler for the polar phase formation along with the electrospinning. Moreover, we did not utilize any ligands for the formation of  $\text{CsPbBr}_3$  NCs, yet the *in situ*-synthesized  $\text{CsPbBr}_3$  NCs maintained better optical as well as structural stability compared to that prepared with traditional methods. The  $\text{CsPbBr}_3$  comprises three-dimensional (3D) corner-shared  $[\text{PbBr}_6]^{4-}$  octahedra and Cs cations that stabilize the structure. Moreover, the electronegative bromine atoms of the  $[\text{PbBr}_6]^{4-}$  octahedra provide the negative charge density that electrostatically interacts with the  $-\text{CH}_2$  dipoles (positively charged). The aforesaid interaction helps to nucleate the polar phases during the electrospinning process. In addition, the formation of the electroactive  $\beta$ -phase mainly arises due to the strong electrostatic interaction between the  $[\text{PbBr}_6]^{4-}$  and  $-\text{CH}_2$  dipoles (Fig. 1).<sup>20</sup> In addition, the *in situ*-synthesized  $\text{CsPbBr}_3$  NCs act as the filler to engineer the  $\beta$ -phase formation of PVDF-HFP fibers, which may help to enhance the photovoltaic properties and stability compared to that of traditional  $\text{CsPbBr}_3$  NCs. Finally, the

*in situ* formation of  $\text{CsPbBr}_3$  NCs with the  $\beta$ -phase PVDF-HFP fiber can be termed as a form of *in situ* architecture engineering.

### XRD patterns

XRD patterns were utilized to evaluate the crystallographic structure and phase purity of the  $\text{CsPbBr}_3$  NCs, electrospun PVDF-HFP fiber, and  $\text{CsPbBr}_3$ @PVDF-HFP fiber. The XRD pattern of  $\text{CsPbBr}_3$  NCs (for comparison), electrospun PVDF-HFP fiber, and  $\text{CsPbBr}_3$ @PVDF-HFP fiber are depicted in Fig. 2. The XRD peaks of  $\text{CsPbBr}_3$  NCs were well defined and belonged to the orthorhombic phase and were in good agreement with the standard JCPDS (PDF-01-0172-7929) values (Fig. 2a).<sup>19,28</sup> The bare electrospun PVDF-HFP fiber exhibited peaks at  $18.2^\circ$ ,  $20.4^\circ$ ,  $26.6^\circ$ , and  $36.6^\circ$ , corresponding to the diffractions of the  $(100)$ ,  $(020)$ ,  $(110)$ , and  $(021)$  planes of the  $\alpha$ ,  $\beta$  crystalline phases (Fig. 2b).<sup>29,30</sup> The  $\text{CsPbBr}_3$ @PVDF-HFP fiber retained the above-mentioned planes for PVDF-HFP along with additional diffraction planes. The noticed additional main peaks were at  $14.9^\circ$ ,  $15.1^\circ$ ,  $21.3^\circ$ ,  $21.5^\circ$ ,  $30.2^\circ$ ,  $30.5^\circ$ , and  $37.5^\circ$  (Fig. 2c) and corresponded to the  $(002)$ ,  $(110)$ ,  $(112)$ ,  $(200)$ ,  $(004)$ ,  $(220)$ , and  $(312)$  reflection planes of  $\text{CsPbBr}_3$ . The characteristic diffraction planes ensured the orthorhombic phase  $\text{CsPbBr}_3$  with the  $Pnma$  space group. Moreover, the diffraction peaks at  $19.2^\circ$  ( $002$ ) and  $20.8^\circ$  ( $110/200$ ) were ascribed to the presence of the  $\gamma$ - and  $\beta$ -phase, respectively.<sup>29,30</sup> These results clearly confirmed the *in situ* formation of  $\text{CsPbBr}_3$  along with the formation of the  $\beta$ -phase in PVDF-HFP during the electrospinning process (Fig. 2c). Importantly,  $\text{CsPbBr}_3$ @PVDF-HFP fiber did not contain any other phases, including  $\text{CsPb}_2\text{Br}_5$  and  $\text{Cs}_4\text{PbBr}_6$ , as evidenced from our XRD analysis.<sup>31</sup> Furthermore, the FT-IR spectrum of  $\text{CsPbBr}_3$ -PVDF-HFP fiber showed characteristic peaks at  $841$  and  $1278\text{ cm}^{-1}$  (Fig. S2a, ESI†), corresponding to the  $\beta$ -phase,<sup>21</sup> which supported the XRD observation.

### Microscopy studies of $\text{CsPbBr}_3$ @PVDF-HFP fiber

The SEM images of  $\text{CsPbBr}_3$ @PVDF-HFP fibers are shown in Fig. 3a and b. The electrospun mats were highly interconnected






Fig. 2 XRD patterns of (a)  $\text{CsPbBr}_3$  NCs, (b) electrospun PVDF-HFP fiber, and (c)  $\text{CsPbBr}_3$ @PVDF-HFP fiber, with the orthorhombic  $\text{CsPbBr}_3$  JCPDS values marked at the bottom.





**Fig. 3** (a and b) SEM images of  $\text{CsPbBr}_3$ @PVDF-HFP fiber, (c) optical microscopic and (d) fluorescence images of a single strand of  $\text{CsPbBr}_3$ @PVDF-HFP fiber (inset: corresponding photographic images of a  $\text{CsPbBr}_3$ @PVDF-HFP fiber mat deposited over aluminum foil).

with a randomly oriented fibrous morphology. The surface of the individual  $\text{CsPbBr}_3$ @PVDF-HFP fiber was highly uniform and smooth. In addition, no defects or cracks were noticed on the surface of the  $\text{CsPbBr}_3$ @PVDF-HFP fiber, indicating that the PVDF-HFP fiber did not become brittle after the *in situ*  $\text{CsPbBr}_3$  formation. The  $\text{CsPbBr}_3$ @PVDF-HFP fibers exhibited an average diameter of 600–800 nm and length of several millimeters (Fig. 3a and b). Next, energy-dispersive X-ray spectroscopy (EDS) was performed to establish the  $\text{CsPbBr}_3$  in the  $\text{CsPbBr}_3$ @PVDF-HFP fibers through elemental analysis by evaluating the Cs, Pb, and Br elements. The EDS pattern of  $\text{CsPbBr}_3$ @PVDF-HFP fiber showed it was composed of C, F, Cs, Pb, and Br. The ratio of 1:1:3 was maintained for Cs, Pb, and Br with the stoichiometry of  $\text{CsPbBr}_3$  after the electrospinning method (Fig. S2b, ESI†). The elemental distribution of the electrospun  $\text{CsPbBr}_3$ @PVDF-HFP fiber was determined through elemental mapping. The mapped red, blue, cyan, green, and pink colored regions corresponded to C, F, Cs, Pb, and Br elements, respectively, representing the homogeneous distribution of  $\text{CsPbBr}_3$  inside the electrospun PVDF-HFP fiber (Fig. S3, ESI†). An optical image of the  $\text{CsPbBr}_3$ @PVDF-HFP fiber showed smooth, transparent, and black particles. The corresponding fluorescent image displayed green light emission along the fibers, which clearly suggested the *in situ* formation of  $\text{CsPbBr}_3$  inside the PVDF-HFP fiber matrix (Fig. 3c and d). The internal morphology of the embedded  $\text{CsPbBr}_3$  over PVDF-HFP fibers was further evaluated *via* transmission electron microscopy (TEM) and the results are depicted in Fig. 4. The average diameter of the electrospun  $\text{CsPbBr}_3$ @PVDF-HFP fibers matched exactly with the SEM observation and it showed a fiber length of several nanometers (Fig. 4a and b). Owing to the higher thickness of the fibers, the particles were not properly visible, but in the walls of the fibers small particles of  $\text{CsPbBr}_3$  were visible. The interior structure of the  $\text{CsPbBr}_3$ @PVDF-HFP fibers was further explored *via* high-resolution TEM (Fig. 4c and d). From that, it could be seen that  $\text{CsPbBr}_3$  was homogeneously formed inside the



**Fig. 4** (a and b) TEM and (c and d) HR-TEM images of the  $\text{CsPbBr}_3$ @PVDF-HFP fiber.

PVDF-HFP fiber matrix. During the electrospinning process, *in situ*  $\text{CsPbBr}_3$  was formed and it was encapsulated by the PVDF-HFP fibers (Fig. 4c). The average crystallite size was calculated using the Scherrer formula from the most intense diffraction peak (220) of  $\text{CsPbBr}_3$  and was found to be around  $\sim 21.4$  nm (Fig. 4c). The HR-TEM images clearly revealed the (110) plane of orthorhombic  $\text{CsPbBr}_3$  with an interplanar spacing of 0.58 nm, confirming the formation of *in situ* orthorhombic  $\text{CsPbBr}_3$  (Fig. 4d).<sup>31</sup> The aforementioned results matched exactly with the XRD data. The pristine  $\text{CsPbBr}_3$  NCs displayed a cubic morphology with an average size of 12 nm and showed a typical *d* spacing (110 plane) of 0.58 nm, confirming the orthorhombic phase of  $\text{CsPbBr}_3$  (Fig. S1a and b, ESI†).

#### XPS analysis

XPS spectra of *in situ*-synthesized samples were obtained to evaluate the oxidation states and chemical compositions of the PVDF-HFP@ $\text{CsPbBr}_3$  fiber. The signals of C, F, Cs, Pb, and Br from the survey spectrum were constituent elements of the PVDF-HFP polymer and  $\text{CsPbBr}_3$  (Fig. 5a).<sup>29–32</sup> The PVDF-HFP polymer exhibited very strong peaks related to C and F, which were the constituents of the polymer backbone. The core C1s spectrum was fitted with six peaks with binding energies of 285.5, 286.6, 287.2, 291, 291.5, and 294.1 eV, corresponding to  $\text{CH}_2$ , C–H, C–F,  $\text{CF}_2$ – $\text{CH}_2$ ,  $\text{CF}_2$ – $\text{CF}_2$  and  $\text{CF}_3$ – $\text{CF}_2$  respectively and the binding energy at 688.5 eV was related to F1s (Fig. 5b and c).<sup>32</sup> Further,  $\text{Cs3d}_{5/2}$  and  $\text{Cs3d}_{3/2}$  appeared as two peaks centered at 724.8 and 738.9 eV, respectively (Fig. 5d). The spectrum of Pb 4f showed binding energies of 138.8 and 143.7 eV, corresponding to  $4f_{7/2}$  and  $4f_{5/2}$  (Fig. 5e). In addition, peaks for Br 3d<sub>5/2</sub> and Br 3d<sub>3/2</sub> were displayed at 68.7 and 69.7 eV, confirming the *in situ* formation of  $\text{CsPbBr}_3$  in the PVDF-HFP fiber matrix (Fig. 5f).<sup>33–35</sup>






Fig. 5 XPS spectra of PVDF-HFP@CsPbBr<sub>3</sub> fiber: (a) survey scan and high-resolution scans of (b) C1s, (c) F1s, (d) Cs3d, (e) Pb4f, and (f) Br3d.

### Optical studies

To further study the synthesized materials properties, optical absorption and steady-state photoluminescence (PL) spectroscopy were performed at room temperature. Fig. 6a and Fig. S1c (ESI<sup>†</sup>) show the optical properties of CsPbBr<sub>3</sub> NCs dispersed in toluene (for comparison) and CsPbBr<sub>3</sub>@PVDF-HFP fiber. The CsPbBr<sub>3</sub> NCs and *in situ*-synthesized CsPbBr<sub>3</sub>@PVDF-HFP fiber exhibited a clear first excitonic absorption peak at 506 nm, 514 nm, and sharp band edge PL peak ( $\lambda_{\text{ex}} = 420$  nm) at 516 nm, 524 nm, respectively. The full width at half-maximum (FWHM) was calculated to be 18 and 28 nm for CsPbBr<sub>3</sub> NCs and CsPbBr<sub>3</sub>@PVDF-HFP fiber, respectively. Further, a small Stokes shift appeared (10 nm) for both samples, implying that the PL emission of CsPbBr<sub>3</sub> originated from direct exciton recombination.<sup>2,3</sup> The PL quantum yield (PLQY) was calculated to be 30% and 70% for CsPbBr<sub>3</sub>@PVDF-HFP fiber and CsPbBr<sub>3</sub> NCs, respectively (Fig. S4 and Table S1, ESI<sup>†</sup>). The core-shell

CsPbBr<sub>3</sub>@PVDF-HFP fiber exhibited a type-I band alignment and the PLQY of CsPbBr<sub>3</sub>@PVDF-HFP fiber was decreased compared to that of CsPbBr<sub>3</sub> NCs, which might be due to some unavoidable agglomeration of the CsPbBr<sub>3</sub> or some interfacial trap states.<sup>13</sup> The excited state behaviors of the CsPbBr<sub>3</sub>@PVDF-HFP fiber and CsPbBr<sub>3</sub> NCs were evaluated using time resolved emission measurements. The PL emission decay at 524 and 516 nm was monitored for CsPbBr<sub>3</sub>@PVDF-HFP fiber and CsPbBr<sub>3</sub> NCs, respectively. Both the samples were excited with a 402 and 300 nm laser pulse and the corresponding PL decay was plotted (Fig. 6b and Fig. S1b, ESI<sup>†</sup>). Fig. S1b (ESI<sup>†</sup>) presents the PL decay trace of CsPbBr<sub>3</sub> NCs in toluene after exciting the sample at 300 and 402 nm and monitoring the emission at 516 nm. It can be clearly seen that the PL lifetimes for both excitations were very similar at ~8.2 and 6.8 ns. This observation clearly suggested that the PL lifetime of CsPbBr<sub>3</sub> NCs in toluene is independent of the excitation. However, the average PL decay




Fig. 6 (a) Optical absorption and PL spectra of CsPbBr<sub>3</sub>@PVDF-HFP fiber; the sample was excited at 420 nm, (b) time-correlated single photon counting (TCSPC) study of CsPbBr<sub>3</sub>@PVDF-HFP fiber after exciting the sample at 402 and 300 nm and monitoring the emission at 524 nm (laser pulse (IRF) green line), and (c) schematic representation of the charge-transfer mechanism under 402 (left panel) and 300 nm (right panel) excitation for the CsPbBr<sub>3</sub>@PVDF-HFP fiber.



lifetime for  $\text{CsPbBr}_3$ @PVDF-HFP fiber was found to be 5.4 and 3.2 ns for ( $\lambda_{\text{ex}}$ ) 402 and 300 nm, respectively (Fig. 6b). Here, with the PVDF-HFP fiber acting as the protecting shell for the *in situ* synthesized  $\text{CsPbBr}_3$  it also provided a large band offset, which led to this type I band alignment. In accordance with this band alignment, for 402 nm excitation, the incident photons were capable of exciting the charge carriers only within the band gap of  $\text{CsPbBr}_3$  but the photogenerated carriers did not have sufficient energy to cross over to PVDF-HFP due to the large band offset of the PVDF-HFP polymer compared to  $\text{CsPbBr}_3$ . However, this was not the situation with 300 nm excitation, where photoexcited carriers were generated in both the  $\text{CsPbBr}_3$  core and PVDF-HFP shell. The decrement in the PL decay for  $\text{CsPbBr}_3$ @PVDF-HFP fiber at 300 nm over that of 402 nm could thus be attributed to the thermodynamically viable delocalization of charge carriers (electron/hole) among the levels of  $\text{CsPbBr}_3$  and PVDF-HFP in the former case (Fig. 6c (right panel)) and the subsequent inevitable loss of some of the carriers in this process as a consequence of trapping at the interface of the  $\text{CsPbBr}_3$  and fiber. It was interesting to see that the PL lifetime of  $\text{CsPbBr}_3$  in the PVDF-HFP fiber was much lower compared to that of  $\text{CsPbBr}_3$  NCs in toluene. This might be due to the unavoidable trapping of charge carriers between the PVDF-HFP fiber and  $\text{CsPbBr}_3$  interface.<sup>13</sup> From the above studies, it was confirmed that the  $\text{CsPbBr}_3$ @PVDF-HFP fiber showed charge delocalization behavior at 300 nm excitation. However, as the PL lifetime setup in our laboratory has a nanosecond time resolution, it was difficult for us to monitor

the accurate charge-transfer dynamics, including the carrier relaxation and carrier-transfer dynamics of  $\text{CsPbBr}_3$ @PVDF-HFP fiber after photoexcitation. So, we employed the femtosecond transient absorption (TA) measurements to resolve the charge-transfer dynamics in the  $\text{CsPbBr}_3$ @PVDF-HFP fiber.

### Water stability study

To quantify their water stability, the synthesized electrospun  $\text{CsPbBr}_3$ @PVDF-HFP fibers were immersed in water and the corresponding PL and FWHM were recorded for a fresh sample and after the 10th day. During this period, we noticed there was no appreciable PL change or change in FWHM (Fig. S5, ESI<sup>†</sup>) in the  $\text{CsPbBr}_3$ @PVDF-HFP fibers. In addition, the electrospun  $\text{CsPbBr}_3$ @PVDF-HFP fibers retained 90% of PLQY after 10 days of storage. This result clearly showed the high stability of  $\text{CsPbBr}_3$  after the encapsulation with the PVDF-HFP fiber, where the PVDF-HFP provided good stability for  $\text{CsPbBr}_3$  under water due to its hydrophobic characteristics.<sup>19</sup>

### Ultrafast transient absorption studies

In the present investigation, ultrafast transient absorption (TA) spectroscopy was employed to follow the charge-carrier dynamics, including the carrier relaxation and carrier-transfer dynamics, after exciting both  $\text{CsPbBr}_3$  NCs and  $\text{CsPbBr}_3$ @PVDF-HFP fiber samples with 420 nm and 300 nm pump pulses (FWHM  $\sim$  120 fs) and monitoring the transients in the visible region.




Fig. 7 Time-dependent evolution of the transient absorption (TA) spectra of (a)  $\text{CsPbBr}_3$  NCs in toluene and (b)  $\text{CsPbBr}_3$ @PVDF-HFP fiber at the excitation wavelength of 420 nm, (c) corresponding comparison of the bleaching and (d) biexciton kinetics of  $\text{CsPbBr}_3$ @PVDF-HFP fibers after exciting the samples at 420 nm.



**420 nm pump excitation.** Fig. 7a and b depict the TA spectra at different time delays for  $\text{CsPbBr}_3$  NCs and  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber with the 420 nm pump pulse. Analogous features were observed in the  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber, including negative bleach and positive signals on either side of the bleach, corresponding to band edge exciton and photoinduced absorption, respectively.<sup>31,36–40</sup> The ground state bleach was observed in the 490–525 nm spectral region, peaking at 517 nm. At the early time scale (0.2–0.5 ps), a positive absorption band could be discerned at 532 nm. Moreover, another positive absorption band was observed at 470–490 nm with a peak maximum at 488 nm, which could be attributed to the excited state absorption (ESA). In the TA spectrum, a negative absorption peak at 517 nm was ascribed to the ground state bleach due to state filling of the electronic states upon excitonic transition. The positive absorption below the band gap lying toward the higher wavelength side at around 532 nm was associated with probe-induced biexcitons formed as a consequence of the band renormalization due to the Stark effect, which is due to the carriers-induced electric field reducing the bandgap. Interestingly, the aforementioned TA spectra closely resembled the TA spectra of the bulk  $\text{CsPbBr}_3$  reported by our group and others.<sup>31,37,40</sup>


The transient kinetic traces were monitored at different wavelengths to explore the carrier dynamics of the synthesized  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fibers, and the results are depicted in Fig. 7c and d. The bleach kinetics at 517 nm fitted with a biexponential growth and multiexponential recovery with the time constants of  $\tau_{g1}^1 = <150$  fs and  $\tau_{g2}^1 = 0.7$  ps and  $\tau_1 = 72$  ps,  $\tau_2 = 220$  ps and  $\tau_3 = >1$  ns, respectively. We observed a rise in the time of 0.7 ps for the bleaching of  $\text{CsPbBr}_3@\text{PVDF-HFP}$ , which was in accordance with the cooling of the charge carriers to the band edge. Further, the multiexponential recovery kinetics could be ascribed to the charge recombination of the photoexcited charge carriers of  $\text{CsPbBr}_3$ . Importantly, the growth and recovery kinetics exactly resembled those of  $\text{CsPbBr}_3$  NCs (Table S2, ESI†). Moreover, the probe induced biexciton signal was monitored at 532 nm. The formation time of the probe-induced biexciton signal could be fitted with a single exponential time component  $\tau_g^1 = <150$  fs and the biexciton decay was found to be 250 fs (Table S3, ESI†). At 420 nm pump excitation, the charge carriers are confined within  $\text{CsPbBr}_3$ , owing to the type-I band alignment. From the above results, it can be concluded that the  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fibers maintained the same charge-carrier dynamics as that of pristine  $\text{CsPbBr}_3$  NCs and did not undergo any charge (electron/hole)-transfer processes. This observation was the opposite to what we observed in our earlier report,<sup>31</sup> where we explored the ultrafast charge-delocalization dynamics of  $\text{CsPbBr}_3$  NCs encapsulated in a transparent polystyrene (PS) fiber matrix. The  $\text{CsPbBr}_3@\text{PS}$  displayed slower cooling compared to that of bare  $\text{CsPbBr}_3$  NCs, as delocalization of the carriers was possible even at 420 nm pump excitation.<sup>41,42</sup>

The  $\text{CsPbBr}_3$  exhibited conduction band (CB) and valence band (VB) positions (vs. vacuum) of –3.3 eV and –5.7 eV, respectively;<sup>43</sup> on the other hand, PVDF-HFP is a well-known piezoelectric polymer with the highest occupied molecular

orbital (HOMO) and lowest unoccupied molecular orbital (LUMO) as –6.13 eV and –2.45 eV, respectively.<sup>44,45</sup> Interestingly, the PVDF-HFP (shell) did not induce any strain over  $\text{CsPbBr}_3$  (core) owing to the soft nature of the polymer. Owing to the high band offset of PVDF-HFP polymer, the carrier transfer and delocalization of the carriers from the  $\text{CsPbBr}_3$  to PVDF-HFP states could not be held liable. Herein, as the excitation wavelength was lower, *i.e.*, 420 nm, it was not high enough to excite PVDF, which thus nullified the possibility of any kind of transfer process being involved. Also as previously observed by Mandal and co-workers, a high energy excitation enhances the transition probability of carriers.<sup>20</sup> Exciting with photons having a higher energy than the band gap leads to the generation of electron–hole pairs, which in turn increases the photoconductivity of a material. So, to gain further insights into these processes, we employed TA spectroscopy for  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fibers under 300 nm excitation, so that the carriers were excited in both  $\text{CsPbBr}_3$  and PVDF-HFP.<sup>20</sup>

**300 nm pump excitation.** With the same intent of gaining insights into the carrier cooling and charge-transfer dynamics of  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber, we carried out a TA study at 300 nm pump excitation. Fig. 8a and b depict the TA spectra of the photoexcited bare  $\text{CsPbBr}_3$  NCs and  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber at different time delays. In the TA spectra, bleaching, biexciton, and PIA were noticed at 517, 526, and 488 nm, respectively.<sup>36–40</sup> Due to the contribution of the high energy states under 300 nm pump excitation, the ground state 1S bleaching appeared to be broad compared to that of the 420 nm pump in both the samples.<sup>36</sup> Further, to understand the exciton dynamics of the synthesized samples, transient kinetics were monitored at the bleaching position. The bleach kinetics of the bare  $\text{CsPbBr}_3$  NCs at 514 nm could be fitted to a biexponential growth with time constants of  $\tau_{g1} = 150$  fs and  $\tau_{g2} = 1.2$  ps and a multiexponential recovery with time constants of  $\tau_1 = 5.8$  ps,  $\tau_2 = 52.7$  ps and  $\tau_3 = 300$  ps and  $\tau_4 = >1$  ns. Interestingly, the bleach kinetics of  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber at 517 nm could be fitted with a very fast single exponential pulse width limited growth (<150 fs) and multiexponential recovery with time constants of  $\tau_1 = 2.2$  ps,  $\tau_2 = 43.7$  ps,  $\tau_3 = 250$  ps and  $\tau_4 = >1$  ns (Table S4, ESI†). Interestingly, compared to that of bare  $\text{CsPbBr}_3$  NCs, the growth and recovery were faster in the case of the  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber (Fig. 8c). The following reason may account for the fast growth and recovery in the  $\text{CsPbBr}_3@\text{PVDF-HFP}$  fiber.<sup>20,21</sup> In the case of 300 nm (4.1 eV) excitation, the charge carriers are excited across the band gap for both  $\text{CsPbBr}_3$  (2.4 eV) and PVDF-HFP (3.84 eV). The immediate outcome is that the majority of the carriers instead of cooling toward the band edge of  $\text{CsPbBr}_3$  delocalize among  $\text{CsPbBr}_3$  and PVDF-HFP energy states and some of them are lost as an outcome of trapping at the interface. This was reflected in the faster growth as well as recovery seen for the  $\text{CsPbBr}_3@\text{PVDF-HFP}$  sample (inset: Fig. 8c). The kinetics for the bare  $\text{CsPbBr}_3$  NCs was fitted biexponentially, while for  $\text{CsPbBr}_3@\text{PVDF-HFP}$ , the growth fitted  $\text{CsPbBr}_3@\text{PVDF-HFP}$  alone, which indicated an underlying transfer mechanism took place. This was not the case under 420 nm excitation, where only the  $\text{CsPbBr}_3$  NCs were





**Fig. 8** Time-dependent evolution of the transient absorption (TA) spectra for: (a) control experiment using the  $\text{CsPbBr}_3$  NCs in toluene and (b)  $\text{CsPbBr}_3$ @PVDF-HFP fiber at the excitation wavelength of 300 nm. Comparison of (c) bleaching (inset: plausible mechanism of charge transfer from  $\text{CsPbBr}_3$  to PVDF-HFP states) and (d) biexciton kinetics of  $\text{CsPbBr}_3$ @PVDF-HFP fiber after exciting the samples at 300 nm and monitoring the kinetics were at the peak maxima.

photoexcited, since the excitation energy (2.95 eV) was insufficient to create photogenerated charge carriers across the single exponential case (IRF limited growth). This led to faster cooling in PVDF (whose band gap was much higher, 3.84 eV). So, the resultant kinetics for both the  $\text{CsPbBr}_3$  NCs and  $\text{CsPbBr}_3$ @PVDF-HFP samples were similar.

To further understand the charge-carrier mechanism of  $\text{CsPbBr}_3$ @PVDF-HFP, the biexciton dynamics were investigated. The probe-induced biexciton signal was monitored at 524 and 528 nm for  $\text{CsPbBr}_3$  NCs and  $\text{CsPbBr}_3$ @PVDF-HFP (Fig. 8d) respectively. The observed TA kinetics of biexciton growth and the recovery looked very different for  $\text{CsPbBr}_3$ @PVDF-HFP compared to those of  $\text{CsPbBr}_3$  NCs. Fig. 8d depicts the biexciton kinetics of  $\text{CsPbBr}_3$  NCs at 524 nm, which could be fitted with a growth time of 200 fs and decay time of 410 fs along with single exciton growth, followed by a multiexponential recovery (Table S5, ESI<sup>†</sup>). More importantly, with the same 300 nm pump, the biexciton growth kinetics for  $\text{CsPbBr}_3$ @PVDF-HFP could be fitted with a time constant of <150 fs along with a decay time constant of 250 fs. It was interesting to see that the biexciton growth and decay of  $\text{CsPbBr}_3$ @PVDF-HFP were much faster compared to those of  $\text{CsPbBr}_3$  NCs at 300 nm excitation. Upon photoexcitation, biexcitons generated in  $\text{CsPbBr}_3$ @PVDF-HFP fibers become dissociated due to delocalization of charge carriers within  $\text{CsPbBr}_3$  and PVDF-HFP energy states. The TA studies clearly indicated that far band edge excitation leads to

efficient charge transfer from  $\text{CsPbBr}_3$  to PVDF-HFP. Thus, upon far band gap pump excitation, the conductivity of the composite material concurrently increased, which was not the case with 420 nm pump excitation.

#### Low-temperature transient absorption study

It was noticed that there are only a limited number of reports available in literature on low-temperature TA studies of  $\text{CsPbBr}_3$  NCs. Consequently, there is no report available in the literature regarding the low-temperature transient study of *in situ*-formed  $\text{CsPbBr}_3$  inside PVDF-HFP electrospun fibers. Yet, it is important to understand the carrier dynamics of  $\text{CsPbBr}_3$ @PVDF-HFP fibers at cryogenic temperatures to develop highly efficient opto-electronic devices, which may be subjected to such low temperatures while under operational conditions. Here,  $\text{CsPbBr}_3$ @PVDF-HFP was excited with a 420 nm pump and the dynamics were monitored in a wide temperature range from 300 K down to 5 K (here, we present the TA data for 200 K down to 5 K and as the TA data at 300 K is already given in Fig. 7, so, we omitted the TA of 300 K in order to avoid repetition of the data). Fig. 9a,b and Fig. S4a (ESI<sup>†</sup>) depict the temperature-dependent TA spectra of  $\text{CsPbBr}_3$ @PVDF-HFP fiber deposited over glass (sample preparation is given in the ESI<sup>†</sup>) at a wide range of temperatures from 200 K down to 5 K excited ( $\lambda_{\text{ex}}$ ) at 420 nm. At the early time scale in all the spectral (5 K to 200 K) responses, we noticed three obvious spectral features, as also observed in the room temperature




Fig. 9 (a and b) TA spectra of  $\text{CsPbBr}_3$ @PVDF-HFP fiber with the temperature of 200 and 5 K under 420 nm pump excitation and (c and d) bleach and biexciton kinetics at different temperature for  $\text{CsPbBr}_3$ @PVDF-HFP fiber monitored at 514 and 530 nm probe wavelength respectively.

studies conducted for the dispersed samples, namely the ground-state photobleaching (GSB) peak at 514–518 nm in the position of the band edge and photoinduced absorptions (PIA) on either side. The PIA signal at the low energy side coming from the biexcitons completely vanished after 0.5 ps and the TA signal was completely dominated by the GSB at later time scales (200 K). Moreover, we found that the 1S excitonic position of the  $\text{CsPbBr}_3$ @PVDF-HFP fiber was continuously shifted toward lower energy upon decreasing the temperatures from 300 K to 5 K (514–518 nm), due to the decrement in the band gap.<sup>36,37,46–52</sup> It is clear that the  $\text{CsPbBr}_3$ @PVDF-HFP fiber synthesized by the *in situ* electrospinning method resulted in the formation of surface trap states stemming from Br vacancies.<sup>39</sup> From the TA studies through the vast ranges of temperature, it was clearly observed that the  $\text{CsPbBr}_3$ @PVDF-HFP fibers were prone to forming defects owing to their larger size. Further, we monitored the temperature-dependent carrier cooling kinetics near the spectral maxima and these are depicted in Fig. 9c. Interestingly, the carrier cooling of  $\text{CsPbBr}_3$ @PVDF-HFP fibers was much faster (0.21 ps) at 5 K compared to that of 0.62 ps at 200 K. The growth kinetics was faster in the case of 5 K and became slower upon increasing the temperature to 300 K (Table S6, ESI<sup>†</sup>). The faster cooling at 5 K was a consequence of the quicker relaxation of the charge carriers to the band edge because the lattice was completely frozen at 5 K, which leads to an absence of carrier-longitudinal (LO) phonon

coupling. Thus, at 5 K, the carrier relaxation is mediated by acoustic phonons and there is no possibility of polaron formation, which could otherwise interfere in the carrier-cooling process.<sup>38,51</sup> Fig. 9d and Fig. S4c show the biexciton kinetics monitored in the peak maxima over a wide range of temperatures (200–5 K). The  $\text{CsPbBr}_3$ @PVDF-HFP fiber exhibited  $\tau_1 = <100$  fs biexciton growth for all the temperatures at 420 nm excitation. However, biexciton decays were slower (320 fs) at 5 K compared to that of 240 fs at 200 K. Upon decreasing the temperature from 200 to 5 K, the kinetics was observed to become positive at long time scales at the position of both the bleaching and biexciton maxima, which might be due to the trapping of charge carriers in the  $\text{CsPbBr}_3$ @PVDF-HFP fiber, as the  $\text{CsPbBr}_3$ @PVDF-HFP fibers are more prone to defects (Table S7, ESI<sup>†</sup>). From the above observation, it can be concluded that  $\text{CsPbBr}_3$ @PVDF-HFP fibers can be effectively used for high-performance optoelectronic as well as photovoltaic applications.<sup>52</sup>

## Conclusions

In summary, we successfully synthesized  $\text{CsPbBr}_3$ @PVDF-HFP fibers using a facile one-step electrospinning method. The *in situ* synthesis of  $\text{CsPbBr}_3$  inside the PVDF-HFP fibers induced the electroactive  $\beta$ -phase, which efficiently avoided the cost-efficient,



time-consuming, and tedious methods commonly used for polar phase formation in PVDF-HFP. The structural and optical studies suggested that the crystallinity and strong light absorption properties were maintained even after  $\text{CsPbBr}_3$  formation inside the fiber matrix. TRPL studies witnessed efficient charge transfer from  $\text{CsPbBr}_3$  to PVDF-HFP at 300 nm over that of 402 nm excitation in the fiber matrix. Furthermore, the aforementioned claims were confirmed through femtosecond TA spectroscopy. The excitation-dependent transient absorption study evidently showed that upon far band edge excitation of both  $\text{CsPbBr}_3$  and PVDF-HFP, an efficient delocalization of the carriers takes place, which would lead to an increase in the photoconductivity; whereas, there was no possibility of such carrier transfer at low pump excitation energies. The TA studies verified the formation of stable  $\text{CsPbBr}_3$ @PVDF-HFP fibers through evidence of all its optical properties being similar to those of  $\text{CsPbBr}_3$  NCs, even at cryogenic temperatures. Importantly, the engineering of electroactive polymers with  $\text{CsPbBr}_3$  may efficiently be utilized for next-generation piezoelectric-based energy-harvesting applications. This comprehensive study provides a number of photophysical insights and would pave the way for the development of flexible and highly efficient solar cells and photodetector devices.

## Author contributions

The manuscript was written through contributions of all the authors. All authors have given approval to the final version of the manuscript.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

K. J. B. thank SERB-NPDF (PDF/2019/000549), India for his National Postdoctoral research fellowship. G. K., A. S., H. B., and N. G. thank INST, Mohali for their research fellowships. H. N. G. thank DST India for the project SERB/DST (CRG/2019/000938). A. K. thank Department of Science and Technology (DST) for Inspire Research fellowship (IF-180009) and H. N. G. is grateful to DST, Govt. of India, for JC Bose fellowship (JCB/2018/000047) and the DST project Sanction No. SERB/DST (CRG/2019/000938). The authors acknowledge Institute of Nano Science and Technology, Mohali for providing instrument facilities for supporting this research work.

## References

- 1 M. V. Kovalenko, L. Protesescu and M. I. Bodnarchuk, *Science*, 2017, **358**, 745–750.
- 2 L. Protesescu, S. Yakunin, M. I. Bodnarchuk, F. Krieg, R. Caputo, C. H. Hendon, R. X. Yang, A. Walsh and M. V. Kovalenko, *Nano Lett.*, 2015, **15**, 3692–3696.
- 3 Q. A. Akkerman, G. Raino, M. V. Kovalenko and L. Manna, *Nat. Mater.*, 2018, **17**, 394–405.
- 4 X. Li, D. Yu, F. Cao, Y. Gu, Y. Wei, Y. Wu, J. Song and H. Zeng, *Adv. Funct. Mater.*, 2016, **26**, 5903–5912.
- 5 T. A. Berhe, W. N. Su, C. H. Chen, C. J. Pan, J. H. Cheng, H. M. Chen, M. C. Tsai, L. Y. Chen, A. A. Dubale and B. J. Hwang, *Energy Environ. Sci.*, 2016, **9**, 323–356.
- 6 H. Guan, S. Zhao, H. Wang, D. Yan, M. Wang and Z. Zang, *Nano Energy*, 2020, **67**, 104279.
- 7 Q. Mo, C. Chen, W. Cai, S. Zhao, D. Yan and Z. Zang, *Laser Photonics Rev.*, 2021, **15**, 2100278.
- 8 X. Li, W. Cai, H. Guan, S. Zhao, S. Cao, C. Chen, M. Liu and Z. Zang, *Chem. Eng. J.*, 2021, **419**, 129551.
- 9 B. Wang, J. Peng, X. Yang, W. Cai, H. Xiao, S. Zhao, Q. Lin and Z. Zang, *Laser Photonics Rev.*, 2022, 2100736.
- 10 S. Peng, G. Jin, L. Li, K. Li, M. Srinivasan, S. Ramakrishna and J. Chen, *Chem. Soc. Rev.*, 2016, **45**, 1225–1241.
- 11 J. Hai, H. Li, Y. Zhao, F. Chen, Y. Peng and B. Wang, *Chem. Commun.*, 2017, **53**, 5400–5403.
- 12 Y. Wang, Y. Zhu, J. Huang, J. Cai, J. Zhu, X. Yang, J. Shen and C. Li, *Nanoscale Horiz.*, 2017, **2**, 225–232.
- 13 Y. Wang, Y. Zhu, J. Huang, J. Cai, J. Zhu, X. Yang and C. Li, *J. Phys. Chem. Lett.*, 2016, **7**, 4253–4258.
- 14 V. K. Thakur and R. K. Gupta, *Chem. Rev.*, 2016, **116**, 4260–4317.
- 15 J. Chang, M. Dommer, C. Chang and L. Lin, *Nano Energy*, 2012, **1**, 356–371.
- 16 A. Gebrekrstos, G. Madras and S. Bose, *Cryst. Growth Des.*, 2019, **19**, 5441–5456.
- 17 B. Mohammadi, A. A. Yousefi and S. M. Bellah, *Polym. Test.*, 2007, **26**, 42–50.
- 18 F. Wang, H. Wang, A. Ali, Y. Zhang, X. Cui and Y. Liu, *Inorg. Chem. Commun.*, 2019, **106**, 99–103.
- 19 P. Liang, P. Zhang, A. Pan, K. Yan, Y. Zhu, M. Yang and L. He, *ACS Appl. Mater. Interfaces*, 2019, **11**, 22786–22793.
- 20 A. Sultana, P. Sadhukhan, M. M. Alam, S. Das, T. R. Middya and D. Mandal, *ACS Appl. Mater. Interfaces*, 2018, **10**, 4121–4130.
- 21 A. Sultana, M. M. Alam, P. Sadhukhan, U. K. Ghorai, S. Das, T. R. Middya and D. Mandal, *Nano Energy*, 2018, **49**, 380–392.
- 22 S. Zhang, Y. Lu, B. Lin, Y. Zhu, K. Zhang, N. Y. Yuan, J. N. Ding and B. Fang, *Sol. Energy Mater. Sol. Cells*, 2017, **170**, 178–186.
- 23 T. Dong, J. Zhao, G. Li, F. C. Li, Q. Li and S. Chen, *ACS Appl. Mater. Interfaces*, 2021, **13**, 39748–39754.
- 24 R. Cheng, Z. B. Liang, L. Zhu, H. Li, Y. Zhang, C. F. Wang and S. Chen, *Angew. Chem., Int. Ed.*, 2022, e202204371.
- 25 G. C. Dadol, A. Kilic, L. D. Tijing, K. J. A. Lim, L. K. Cabatingan, N. P. B. Tan, E. Stojanovska and Y. Polat, *Mater. Today Commun.*, 2020, **25**, 101656.
- 26 S. Maiti, J. Dana and H. N. Ghosh, *Chem. – Eur. J.*, 2019, **25**, 692–702.
- 27 P. Singhal and H. N. Ghosh, *J. Phys. Chem. C*, 2018, **122**, 17586–17600.
- 28 R. Aepuru, S. Mondal, N. Ghorai, V. Kumar, H. S. Panda and H. N. Ghosh, *J. Phys. Chem. C*, 2018, **122**, 27273–27283.



29 S. Mondal, T. Paul, S. Maiti, B. K. Das and K. K. Chattopadhyay, *Nano Energy*, 2020, **74**, 104870.

30 N. Senthilkumar, K. J. Babu, G. G. Kumar, A. R. Kim and D. J. Yoo, *Ind. Eng. Chem. Res.*, 2014, **53**, 10347–10357.

31 K. J. Babu, G. Kaur, L. Biswal, G. De and H. N. Ghosh, *Chem. – Eur. J.*, 2021, **27**, 683–691.

32 D. Yuan, Z. Li, W. Thitsartarn, X. Fan, J. Sun, H. Li and C. He, *J. Mater. Chem. C*, 2015, **3**, 3708–3713.

33 Q.-F. Li, J.-T. Wang, B. Tian, S. Kong and T. Z. Wang, *Eur. J. Inorg. Chem.*, 2018, 4215–4220.

34 M. Ou, W. Tu, S. Yin, W. Xing, S. Wu, H. Wang, S. Wan, Q. Zhong and R. Xu, *Angew. Chem., Int. Ed.*, 2018, **57**, 13570–13574.

35 C. C. Ilie, F. Guzman, B. L. Swanson, I. R. Evans, P. S. Costa, J. D. Teeter, M. Shekhirev, N. Benker, S. Sikich, A. Enbabders, P. A. Dowben, A. Sinitskii and A. J. Yost, *J. Phys.: Condens. Matter*, 2018, **30**, 18LT02.

36 G. Kaur, K. J. Babu, N. Ghorai, T. Goswami, S. Maiti and H. N. Ghosh, *J. Phys. Chem. Lett.*, 2019, **10**, 5302–5311.

37 A. Shukla, G. Kaur, K. J. Babu, N. Ghorai, T. Goswami, A. Kaur and H. N. Ghosh, *J. Phys. Chem. Lett.*, 2020, **11**, 6344–6352.

38 G. Kaur, K. J. Babu and H. N. Ghosh, *J. Phys. Chem. Lett.*, 2020, **11**, 6206–6213.

39 K. J. Babu, G. Kaur, A. Shukla, A. Kaur, T. Goswami, N. Ghorai and H. N. Ghosh, *J. Phys. Chem. Lett.*, 2020, **12**, 302–309.

40 H. Chung, S. I. Jung, H. J. Kim, W. Cha, E. Sim, D. Kim, W.-K. Koh and J. Kim, *Angew. Chem., Int. Ed.*, 2017, **56**, 4160–4164.

41 S. L. Sewall, A. Franceschetti, R. R. Cooney, A. Zunger and P. Kambhampati, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2009, **80**, 81310.

42 A. M. Smith, A. M. Mohs and S. Nie, *Nat. Nanotechnol.*, 2009, **4**, 56–63.

43 S. Maiti, T. Debnath, P. Maity and H. N. Ghosh, *J. Phys. Chem. C*, 2015, **119**, 8410–8416.

44 P. Maity, J. Dana and H. N. Ghosh, *J. Phys. Chem. C*, 2016, **120**, 18348–18354.

45 K. A. Bogdanowicz, D. Augustowski, J. Dziedzic, P. Kwaśnicki, W. Malej and A. Iwan, *Materials*, 2020, **13**, 2721.

46 B. T. Diroll, H. Zhou and R. D. Schaller, *Adv. Funct. Mater.*, 2018, **28**, 1800945.

47 A. Dey, P. Rathod and D. Kabra, *Adv. Opt. Mater.*, 2018, **6**, 1800109.

48 B. T. Diroll, G. Nedelcu, M. V. Kovalenko and R. D. Schaller, *Adv. Funct. Mater.*, 2017, **27**, 1606750.

49 H. Ryu, H. R. Byun, K. M. McCall, D. Y. Park, T. J. Kim, S. Jeong, M. G. Kanatzidis and J. I. Jang, *J. Am. Chem. Soc.*, 2021, **143**, 2340–2347.

50 A. Dey, J. Ye, A. De, E. Debroye, S. K. Ha, E. Bladt, A. S. Kshirsagar, Z. Wang, J. Yin, Y. Wang and L. N. Quan, *et al.*, *ACS Nano*, 2021, **15**, 10775–10981.

51 K. Justice Babu, G. Kaur, A. Shukla, R. Saha, A. Kaur, M. S. Deva, D. K. Yadav and H. N. Ghosh, *ACS Photonics*, 2022, **9**, 969–978.

52 K. Maity, U. Pal, H. K. Mishra, P. Maji, P. Sadhukhan, Z. Mallick, S. Das, B. Mondal and D. Mandal, *Nano Energy*, 2022, **92**, 106743.

