


 Cite this: *RSC Adv.*, 2022, **12**, 7009

Photocatalysis and perovskite oxide-based materials: a remedy for a clean and sustainable future

Muneeb Irshad, ^{*a} Quar tul Ain, ^a Muhammad Zaman, ^a Muhammad Zeeshan Aslam, ^a Naila Kousar, ^a Muhammad Asim, ^a Muhammad Rafique, ^b Khurram Siraj, ^a Asif Nadeem Tabish, ^c Muhammad Usman, ^d Masood ul Hassan Farooq, ^e Mohammed Ali Assiri, ^f and Muhammad Imran ^f

The massive use of non-renewable energy resources by humankind to fulfill their energy demands is causing severe environmental issues. Photocatalysis is considered one of the potential solutions for a clean and sustainable future because of its cleanliness, inexhaustibility, efficiency, and cost-effectiveness. Significant efforts have been made to design highly proficient photocatalyst materials for various applications such as water pollutant degradation, water splitting, CO_2 reduction, and nitrogen fixation. Perovskite photocatalyst materials are gained special attention due to their exceptional properties because of their flexibility in chemical composition, structure, bandgap, oxidation states, and valence states. The current review is focused on perovskite materials and their applications in photocatalysis. Special attention has been given to the structural, stoichiometric, and compositional flexibility of perovskite photocatalyst materials. The photocatalytic activity of perovskite materials in different photocatalysis applications is also discussed. Various mechanisms involved in photocatalysis application from wastewater treatment to hydrogen production are also provided. The key objective of this review is to encapsulate the role of perovskite materials in photocatalysis along with their fundamental properties to provide valuable insight for addressing future environmental challenges.

Received 8th November 2021

Accepted 21st February 2022

DOI: 10.1039/d1ra08185c

rsc.li/rsc-advances

Introduction

Rapid industrialization and population growth resulted in increased energy resources utilization and release of harmful pollutants. The increased human activities are depleting the energy resources and polluting our ecosystem. The toxic gasses in the air are causing respiratory diseases, and the direct disposal of industrial and organic waste into the water reservoirs is causing water-borne diseases. Nearly 663 million people in the world have no access to clean water. The amount of CO_2 in the atmosphere is also increasing due to rapid industrialization. The increased concentration of CO_2 is causing global warming and is the leading cause of acid rain, which is

dangerous for all living things on the earth. The current decade 2021–2030, is the decade of ecosystem system restoration. Therefore, it is essential to pay attention to clean ways to tackle environmental issues. The new global challenge is the achievement of ecological sustainability. The research focus of this era is oriented toward the way to achieve the eco-friendly system.^{1–6}

The blissful gift of Mother Nature, the Sun is an ultimate renewable energy resource that irradiates 3.85 yotta joule (YJ) of energy yearly on the earth's surface. Sunlight is one of the best routes to deal with environmental issues owing to its cleanliness and abundant availability. Sunlight can be utilized as an energy medium by photovoltaic, photoelectrochemical catalysis, or photocatalysis in daily activities.^{7,8}

Photocatalysis is defined as the science of employing a catalyst that uses light to speed up the chemical reaction. In photocatalysis, the photocatalyst material is used, and the energy of the light acts as a source to generate electron–hole pair. The photogenerated electron–hole pair then initiates the redox reaction at the surface of the photocatalyst. This redox reaction can be utilized to degrade water pollutants and convert abundant earth elements (H_2O , CO_2 , and N_2) into fuel (pure H_2 , or organic fuel like CH_4 , CH_3OH , and NH_3). The conversion of water into the fuel (H_2) by using light and photocatalyst

^aDepartment of Physics, University of Engineering and Technology, Lahore, 54890, Pakistan. E-mail: muneebirshad@gmail.com; muneeb_irshad@uet.edu.pk

^bDepartment of Physics, University of Sahiwal, Sahiwal, Pakistan

^cDepartment of Chemical Engineering, University of Engineering and Technology, New Campus, Lahore, Pakistan

^dDepartment of Mechanical Engineering, University of Engineering and Technology, Lahore, 54890, Pakistan

^eDepartment of Basic Sciences, University of Engineering and Technology, New Campus, Lahore, Pakistan

^fDepartment of Chemistry, Faculty of Science, Research Center for Advanced Materials Science (RCAMS), King Khalid University, P. O. Box 9004, Abha 61413, Saudi Arabia



material is known as photocatalytic water splitting. The conversion of CO_2 into the hydrocarbons is known as CO_2 reduction, and conversion of nitrogen into NH_3 is called nitrogen fixation. All these application deals with the viable way to clean the environment. The main challenge while dealing with photocatalysis is the region of operation of the photocatalyst in the solar spectrum. Most photocatalysts operate under UV radiations, which is only 5% of the sunlight reaching earth. Therefore, suitable photocatalysts are required to respond to the extensive range of the solar spectrum.⁹⁻¹⁸

History of photocatalysis

The word catalysis was first used in 1836 by the Jöns Jakob Berzelius, derived from the Greek word “kata”, meaning down or loosen. Catalysis is the process of fastening or accelerating the reaction in the presence of the catalyst. The catalyst itself doesn't participate in the reaction but increases the reaction rate. The term photocatalysis first appeared in 1911, when Eibner studied the effect of light irradiation on transition metal oxide (ZnO) for the decolorization of Prussian blue. Photocatalysis term also appeared simultaneously in the title of the article investigating the degradation of the oxalic acid in the presence of the uranyl salts upon light irradiation. In 1921 Edward Charles Cyril Baly studied the production of formaldehyde using colloidal uranium salts and ferric hydroxides as a catalyst. Soon after, in 1924, the Baur and the Perret at the ETH of Zurich reported the effect of light irradiation on the ZnO suspension and observed that ZnO suspension enhanced reduction of Ag^+ salts to Ag^0 upon irradiation. The mobility for the TiO_2 as a photosensitizer for the dyes was first studied by Doodeve and Kitchener in 1938. This work reported that TiO_2 upon light irradiation decolorized the dyes, and TiO_2 remains unchanged during the process.¹⁹⁻²²

Many researchers from 1940 to 1972 investigated different parameters of the photocatalyst. Photocatalysis gained significant attention when electrochemical photolysis of the water was done by using titanium dioxide under UV irradiation. The oil crisis in 1973 also changed the social and economic status of the western world. The first time, the shortage of fossil fuels became a significant issue, which led to an unprecedented increase in the efforts for alternative energy resources, including photocatalysis. The application of photocatalysis is not limited to energy fuels but can also clean the environment. Much attention has been given to photocatalysis during the last two decades due to its wide range of applications.^{21,23}

Photocatalysis has its application in the pollutant degradation and production of fuel. Material can be an excellent photocatalyst if it is responsive to light, especially (UV or visible), biologically and chemically inert, has low cost, and exhibits adsorption and absorption capacity. Normally the metal oxide semiconductors are used in the application of the photocatalyst. Perovskite materials, due to their unique optical properties, also gained importance in the application of photocatalyst during the last decade.^{24,25}

Perovskite oxide based materials

Perovskite material was first discovered in 1839 in the Ural Mountains by the German scientist Gustave Rose. The mineral was named perovskite after Russian mineralogist Count Lev Aleksevich von Perovski.²⁶⁻²⁸ The first discovered perovskite material was CaTiO_3 .²⁹ The basic chemical formula of the single perovskite is ABX_3 , where A and B are cations while X is an anion. Normally, A is alkaline earth metals or lanthanides, B is the transition metal, and X is oxygen or any halide. The perovskite is known as perovskite oxide when the anion is oxygen and is known as perovskite halide when the anion is a halide. In single perovskite, the coordination number of A site is 6, the coordination number of B site is 12, and the coordination number of O anion is 6. In single perovskite, the perfect structure of the BO_6 octahedral connection results in the cubic lattice.³⁰⁻³³ The structure of single perovskite is shown in Fig. 1.

The tolerance factor can indicate the distortion and the crystallographic structure of the perovskite material. The tolerance factor of the single perovskites ions was defined by V. M Goldschmidt in 1926. The tolerance factor of the perovskite structure tells the stability of the perovskite structure and the compatibility of the ions in the crystal structure.³⁴⁻³⁹ The tolerance factor is a dimensionless quantity given by eqn (1).^{38,40}

$$t = \frac{r_A + r_X}{\sqrt{2}(r_B + r_X)} \quad (1)$$

In eqn (1), r_A and r_B are the ionic radii of the electropositive ions, while r_X is the radius of the oxygen or halide ions.⁴¹ The perovskite structure can be divided into octahedral hexagonal, tetragonal, and ideal cubic structures on the basis of the tolerance factor. When the tolerance factor is between 0.9 and 1, the structure is the ideal cubic structure with the length of the unit cell (a) as:⁴²

$$a = r_A + r_O = \sqrt{2}(r_B + r_X) \quad (2)$$

In non-ideal cases, the tolerance factor deviates from 1, which shows the mismatch in the A–O and B–O bond lengths. The corundum structure ($\alpha\text{-Al}_2\text{O}_3$) and its derivative are




Fig. 1 Perovskite structure.



considered when the tolerance factor is less than 0.75.⁴³ The stable bixbite polymorph (α -Mn₂O₃) is favored when the factor decreases. If the tolerance factor is greater than 1, the structure of perovskite is hexagonal close-packed (HCP), and [BO₆] octahedra share faces with the hexagonal *c*-axis.^{30,44}

The sum of the charges of cations and anion of the perovskite structure should equal one for perovskite material to be electrically neutral. Different cations having different ionic radii and valences can be doped in the structure of perovskite material by employing the method of partial substitution at A and B-site. Deficiency at A and B-site cations and excess or deficiency of oxygen anions can change the composition of ions and the non-stoichiometry phenomenon.^{45,46}

Double perovskite structures were used at a significant scale in the 1980s. The double perovskite exhibits structure that is twice the single perovskite. The coordination number of the A and B cation is the same as that of the single perovskite. Double perovskites are generally of two types depending upon the types of the cations A'A''B₂O₆ (double A-site) or A₂B'B''O₆ (double B-site).^{47,48} The double perovskite strain energy depends on the charge difference between the two types of B cations (B and B'). There are three ways to arrange the B-type cation based on the charge difference between B and B'. The arrangement is random if the charge difference is one ($\Delta Q = 1$).⁴⁹ The most common arrangement of the double perovskite is the rock-salt arrangement, also called elpasolite structure, in which the cations change in all three dimensions, and it dominates when the charge difference between the B and B' is greater than 2 ($\Delta Q > 2$). Due to the difference in the charge size of the B cation in the rock salt order, the crystal symmetries are less than their single perovskite structure. Another arrangement is the layered arrangement of the B and B', where the cations can change in only one dimension (Fig. 2).⁵⁰⁻⁵⁴

The perovskite structures are preferred due to their structural and compositional flexibility.

Structural flexibility

The ideal single perovskite structure is with the high symmetry of *Pm* $\bar{3}$ *m*. It comprises a highly flexible network built up from chains of corner-sharing [BO₆] octahedra with A cations occupying the resulting holes with cubic octahedral symmetry. The symmetry of the structure can be transformed into the tetragonal, hexagonal, octahedral, monoclinic, triclinic, and

rhombohedral structures by changing the size of cations or anions in the structure. Double perovskites generally have a double B site. Double perovskites are modified single perovskite; the high symmetry ideal single perovskite with the space group of *Pm* $\bar{3}$ *m* is reduced to *Fm* $\bar{3}$ *m* in double perovskite. The double perovskite structure with double B site has two elements in the corner linked and has alternatively arranged BO₆ and B'O₆ octahedra double A site.^{55,56}

The tolerance factor of both single and double perovskite changes by altering the size of cations or anions in the perovskite. The resulting lattice distortion affects the dielectric, electronic, magnetic, and optoelectronic properties. The lattice distortion also influences the movement and excitation of the photo-generated charge carrier under the influence of light.^{27,57-59} The sintering temperature also affects the structure of the perovskite material. The structure generally becomes ideal cubic at high temperatures, and as the temperature goes down, the octahedral rotation in the perovskite changes to lower symmetry.^{60,61}

Octahedral tilting also has an indispensable role in the structural flexibility of single and double perovskite structures. Octahedral tilting is the rotation along with the orthogonal symmetry of the BO₆; Glazier explained the octahedral tilting in 1972. Currently, there are twenty-three different perovskite structures available depending on the octahedral tilt.^{62,63}

The ferroelectric properties of the perovskite structure are also dependent on the octahedral tilting. Octahedral tilting breaks the centro-symmetry, which affects the ferroelectricity. The bandgap of the perovskite can also be changed by changing the octahedral tilting. Calculation of the electronic structure of the oxide perovskites on the tilted phase depicts that bandgap due to the different tilt can change up to the 0.2 eV and is even more significant in the case of halide perovskites.^{30,64,65}

The large distortion in the perovskite lattice can break the structure and result in low dimension perovskite formation (1D, 2D). The distortion in the crystal structure affects the BO₆ octahedral, breaks the B-O bond, and forms a 1D/2D perovskite derivative. In 1D wires with linear or zigzag configuration, the BO₆ octahedral network can be edge-sharing, face-sharing, or corner-sharing. While in the case of a 2D stacked-layer, the BO₆ octahedra are edge-sharing. Low dimension perovskites are helpful in the application of photocatalysis due to their high surface to bulk ratio.⁶⁵⁻⁶⁷




Fig. 2 Double perovskite structures.



Stoichiometric and compositional flexibility. The perovskite structure exhibits a high degree of stoichiometric and compositional flexibility. Theoretically, 346 different kinds of ABO_3 , 264 are experimentally investigated. The ABO_3 perovskite structure is divided into five groups depending upon the A and B site charges that are $\text{A}^{1+}\text{B}^{5+}\text{O}_3$, $\text{A}^{2+}\text{B}^{4+}\text{O}_3$, $\text{A}^{3+}\text{B}^{3+}\text{O}_3$, $\text{A}^{4+}\text{B}^{2+}\text{O}_3$, and $\text{A}^{5+}\text{B}^{1+}\text{O}_3$. Theoretically, there are 10^5 possible material double perovskite, out of which 10^3 double perovskites are experimentally investigated. For material to be double perovskite, the charge balance of all the charges present in the structure should be equal to 12. Double perovskite allows the elements with high valence shells to accommodate in structure, thus expanding the compositional flexibility.^{49,68}

Perovskites' compositional flexibility is often represented by their ease of alloying on A and B sites. Normally, the mixing element in semiconductors is isovalent, while in perovskite, the mixing element is non-isovalent. The simplicity of cation mixing in perovskite materials makes it easy to alter its chemical and physical characteristics. The double perovskite structure also shows interesting properties like half-metallicity, high-temperature ferromagnetism, and many magnetic interactions. The infrastructure of the complicated oxide unit cell depends upon the electronic configuration and the atoms located at the A and B-site. The B-site atoms are considered to be more critical than A-sited cations. The size of the A^{2+} cation is larger compared to the A^{3+} cation. As the A^{3+} cation has a smaller size, it limits the size of B-site cations. More than one thousand double perovskite materials are reported in the literature, all of which are prepared at ambient pressure. Some new materials were synthesized at high pressure. More than 720 compounds are reported as the divalent A-site compounds and 200 as trivalent A-site.^{30,69-71}

The structural network of BO_6 octahedra can be maintained in the presence of vacancies at A, B, and O sites because of the perovskite's excellent structural and compositional flexibility. Applications of the perovskite materials are broad due to these vacancies, and therefore, they carry applications in photocatalysis, photovoltaics, supercapacitors, batteries and fuel cells, *etc.*³⁰


Stability of perovskite oxide materials. The challenge to make use of perovskite photocatalyst materials come from two significant restraints: (1) chemical instability in polar solvents and (2) vulnerability of the surface to transform with chemical

species present in solution. Recent progress in this field improved these issues and illustrated different courses of actions to make use of perovskite materials in photocatalytic processes.⁷² There are two main stability issues; (1) intrinsic stability-stability issues, and (2) extrinsic stability-stability issues of perovskite. Intrinsic stability involves structural stability, electronic band structure, and thermodynamic phase stability. In contrast, extrinsic stability encompasses interaction with water molecules and pathways of degradation, thermochemical stability, light induced ion redistribution, light stability, photochemical degradation, and oxidation/photo-oxidation of charge-transporting layers and perovskites.⁷³

Perovskite material and photocatalysis. Perovskite materials, due to their structural, compositional, and stoichiometric flexibility, are considered promising materials for photocatalysis (Fig. 3). Perovskites-based photocatalysts operate in UV, IR, and visible regions. There are three different sites of alteration in perovskite material which makes tuning of the bandgap in perovskite material easy. In this review, the applications of the perovskite material in photocatalysis are discussed in detail.^{74,75}

General reaction mechanism of photocatalysis. The light interacts with the surface of the nano photocatalyst, which generates the electron (e^-) and hole (h^+) pair. The photo-generated electron-hole pair then initiates the redox reaction at the photocatalyst's surface. There are three steps involved in the mechanism of photocatalysis. The first one is photo-excitation, provided that the energy of the light source should be high enough to overcome the bandgap. The second step is trapping the electron-hole pairs to increase the recombination time. The recombination of photoinduced charges produces heat, which decreases the efficiency. The third and final step is the degradation of the pollutant by the reactive species produced due to a redox reaction or the production of the fuel.⁷⁶⁻⁷⁹ The general reaction mechanism for all the reactions is given by;

1st step: photoexcitation of photocatalyst



2nd step: trapping of electron and hole:





Fig. 3 Applications of perovskite materials.






The final step varies for each application of photocatalysis and governing equations:

For water splitting:



For CO_2 reduction:



For nitrogen fixation:



The photogenerated electron–hole pair can be used in various applications depending upon the redox potential for the applications, as depicted in Fig. 4.

The selection of the photocatalyst material for the particular application is crucial and an important step to achieve better results.⁸⁰ The semiconductor material is selected by balancing the band edge potential of the semiconductor material with the reaction potential. The main hurdles in photocatalysis are the less recombination time of the photoinduced electron–hole pair and absorption wavelength corresponding to the photocatalyst material. Most materials are UV activated, and in the solar spectrum, the UV region is only 5%; therefore, for enhanced photocatalytic activity, the material bandgap should be responsive to visible and NIR radiations along with the high recombination time of electron–hole pair.^{81,82}

In the perovskite structure, there are three sites of the alteration (A site, B site, and O site). The doping at these sites can enhance light absorbance in the visible and NIR regions by bandgap alteration. The recombination time can also be addressed by employing the different strategies that includes tuning of bandgap and repression of electron–hole recombination. To solve both light absorption and recombination time problems, a new innovative solution known as defect

engineering has been proposed.^{8,83–85} The strategies for tuning the bandgap are;

- (i) Bandgap engineering
- (ii) Repression of electron–hole pair recombination
- (iii) Defect engineering

The bandgap of the various perovskite materials is given in Table 1.

Bandgap engineering. Most perovskite materials respond to UV light due to their wide-bandgap. The conduction band of perovskite materials contains d-orbital, slightly above or equal to zero eV. The valence band has the 2p orbital, due to which energy of the valence band in perovskite material is generally greater than 3 eV. The perovskite bandgap provides enough redox potential to execute different photocatalytic reactions, like H_2 generation, CO_2 reduction, contaminants degradation, and nitrogen fixation. The donor and acceptor impurities in the perovskite crystal structure can adjust the bandgap. The donor and acceptor impurities in a perovskite can tune the material's bandgap. The doping at the cations or anions at different sites of perovskite structure enhances the photocatalytic activity by introducing the intra-band energy levels; the shallow and deep intraband energy levels trap the photogenerated electron–hole pair. Doping also reduces the bandgap of the perovskite material (Fig. 5).^{30,95}

In perovskite material, doping of the transition metals (d-electrons rich cations) led to the production of donor impurities in the perovskite structure. The high atomic energy of the transition metal ensures better electron mobility without changing conduction band minima of perovskite host material.⁹⁶

The doping at the different sites of the perovskite structure changes the absorption peak of the material, thus increasing the light absorption. Doping also tailors the material's bandgap and increases the efficiency of the photocatalyst material. Incorporating a new transition energy level in the perovskite structure improves the higher wavelength absorption without changing the intrinsic absorption properties of the material. Hybridization of orbital in perovskite structure and formation heteroatom due to the doing changes the absorption spectra of material. The hybridization decreases the bandgap and therefore increases the absorption of light. Thus, the doping changes the bandgap and increases the recombination time.^{83,97–99}

The bandgap of pure SrTiO_3 is 3.25 eV, and doping with noble metals like Ru, Rh, Au, etc., introduces the intra-band




Fig. 4 Redox potential required for the various photocatalytic applications.¹⁰

Table 1 Bandgap of some perovskite materials

Material	Bandgap (eV)	Ref.
SrTiO_3	3.20	86
NaTaO_3	4.0	87
CaTiO_3	3.62	88
BiFeO_3	2.40	89
LaFeO_3	2.00	90
NaNbO_3	3.48	91
LaCoO_3	2.1	92
Bi_2WO_6	2.70	93
$\text{La}_2\text{Ti}_2\text{O}_7$	3.28	94






Fig. 5 Effect of doping on the bandgap.

local states, making the doped SrTiO_3 a suitable photocatalyst.¹⁰⁰ The Ru doping introduces the intra-band energy state between conduction band (Ti 3d) and valence band (O 2p, Sr 4p). The ionic radius of Ru is greater than Sr and nearly equals Ti; therefore, the Ru substitutes Ti atom in SrTiO_3 . Ru doping at the B site of the SrTiO_3 introduces the local states and increases the photocatalytic performance. The doping of noble metals in SrTiO_3 makes it a Vis-IR responsive photocatalyst.⁸⁶

Similarly, doping the bismuth (Bi) or copper (Cu) at A site of SrTiO_3 introduces the intra-band energy level and reduces the bandgap. The change in the absorption shift was also reported due to the change in the bandgap with doping.¹⁰¹ It is reported that doping of the sulfur at the O site of the ABO_3 introduces the intraband energy level at 1.23 eV. Researchers also noted that doping the nitrogen at the O site of the perovskite material increases photocatalytic activity.^{102,103}

The amount and the quantity of the dopant should also be optimized to impede the recombination of the photogenerated charge carrier. Synthesis methods for preparing the perovskite material also affect the bandgap, recombination of charges, and migration properties of photocatalyst.^{104,105}

Repression of the photogenerated electron–hole pair recombination. The movement of photoinduced charge carriers at the photocatalyst's surface initiates the redox reaction at the surface of the photocatalyst. The recombination of charge carriers can occur either at the surface or in bulk. The recombination reduces efficiency, so it must be repressed.^{106–108}

The crucial step in photocatalysis is selecting the material, which depends upon the absorption coefficient of the photocatalyst material. The absorption coefficient of photocatalyst depends upon the bandgap and photon energy.^{109–111} The incident light generates the electron–hole pair below the catalyst surface, known as the absorption length. The development of the space charge region takes place at the phase of the solid–liquid interface, and if the absorption extent exists in the space charge region, the photoinduced electron–hole pair can be easily separated. However, in the case of the bulk material, the recombination rate will be high.^{112,113} After separating the photo-induced charges, the next step is the migration of the

charge carriers. The migration mainly depends on the material's symmetry and diffusion length. Diffusion length is the distance that photogenerated charges travel without recombining or scattering. Diffusion length is the governing factor for controlling the movement of the charges in the absence of the potential gradient. Separation of the photogenerated charges beyond the charge separation region is feasible with materials whose diffusion length is longer. The diffusion length is multiple of the lifetime of the charge carrier and diffusion constant, and it should be of high value to generate the maximum photogenerated charge carriers.^{114–116} The limiting factor for the range of charge space region is the particle size. The width of the charge space region should not surpass the particle's radius, and therefore the use of nano-size crystals improves the photocatalytic activity.^{108,117,118}

The perfection in the crystal structures affects the lifetime of the photogenerated charge carrier. The potential gradient also affects the photocatalytic activity because it efficiently separates the photo-induced charges through the support interfaces between the semiconductor–semiconductor, semiconductor–metal, and semiconductor–conductor surfaces, forming the heterojunctions. Therefore, it is necessary to introduce the potential gradient for attaining better efficiency of photocatalytic material. Furthermore, combining the two semiconductors with different bandgaps represses the electron–hole pair recombination. Co-catalyst can also enhance efficiency by introducing active sites and better charge transfer.^{79,119–126}

Charge transfer mechanism. Charge transfer mechanisms are of different types, depending on the photocatalyst system. The coupling of two photocatalyst semiconductor materials gives the heterojunction, further categorized into three types. The heterojunction type formed by the semiconductor materials depends on their bandgap.^{119,127} The three types of heterojunctions are type I, type II, and type III. The combination of the semiconductor materials forms the Z-scheme, p–n junction, and the Schottky junction based on the type of the semiconductor used (Fig. 6).^{121,128,129}

Type I, a heterojunction known as straddling gap heterojunction, involves one semiconductor photocatalyst (SP I) with




Fig. 6 Charge transfer mechanisms (a–f) in two coupled semiconductors.

a highly negative conduction band and highly positive valence band while the bands of the other photocatalyst semiconductor (SP II) lie within it. The drawback of type I heterojunction is that the charges accumulate on the semiconductor with a lower bandgap which is not favorable.^{127,130}

In type II, the conduction and valence band of the one semiconductor SPI lies above the conduction and valence band of the SPII. The charge separation of the photogenerated electron-hole pair is efficient in type II because of the electron's downward movement from the conduction band of SPII and an upward movement of the holes from SPI's valence band.^{131,132}

In type III heterojunction, the valence and conduction bands difference is more than type II. The photogenerated electrons of the SPI unite with the photogenerated hole of SPII. The SSPII electron and the SPI hole innate the redox reaction in the semiconductor photocatalyst.^{120,130}

The understanding of the Z-scheme is necessary to understand the heterojunction. In Z-scheme, two semiconductor photocatalyst materials are linked in a way that they form the letter Z. The electrons from the conduction band of the SPII trans into the valence band of the SPI. SPI acts as a reduction site, and SPII serves as an oxidation site. Due to the redox potential between the two semiconductors, the inbuilt electric field allows efficient charge separation. The direct Z-scheme involves the contact at the interface of two semiconductor materials. In contrast, the indirect Z-scheme involves mediators that allow the charge transfer between the two semiconductor materials. The mediator can be solid or liquid. The iron-based mediators are more commonly used.^{133–135}

The heterojunction can also be formed by combining the p and n-type of the semiconductor materials. A free-electron from n-type semi-conductor material migrates toward the p-type semiconductor material upon contact. The migration of free electrons results in the formation of oppositely charged interfaces. This migration also strengthens the inbuilt electric field at the contact of the p–n junction. The built-in electric field facilitates the migration of the photogenerated charge carrier after light irradiation, which increases the photocatalytic performance (Fig. 7).^{136,137} Examples of semiconductor–semiconductor photocatalyst are $\text{SnO}_2\text{-TiO}_2$, $\text{CdS}\text{-TiO}_2$, $\text{Bi}_2\text{O}_3\text{-Bi}_2\text{WO}_6$ and $\text{Bi}_2\text{WO}_6\text{-TiO}_2$, etc.¹³⁸

The increased charge separation of metal–semiconductor photocatalysts arises from the transfer of the electron across the interface of metal–semiconductor. Metal improves photocatalytic performance because it provides active sites and facilitates the separation and transfer of photoinduced charge carriers. When a metal (having a high work function) couples with semiconductor, the electrons flow from the semiconductor to the metal until their Fermi levels get aligned, resulting in upward bending of band edges in semiconductor and accompanied by the band bending; formation of Schottky barrier takes place at the metal–semiconductor interface (Fig. 8). The electron from the conduction band of the semiconductor material migrates to the co-catalyst and causes charge separation, and increases the photocatalytic activity.^{139–141} The prominent examples of metal–semiconductor photocatalysts are Au/TiO_2 , Au/ZnO , Ag/ZnO , Ag/TiO_2 , etc.¹⁴²






Fig. 7 Schematic energy band structure and electron–hole pair separation in the p–n heterojunction.¹²⁶

Defect engineering. Defect engineering is a suitable and easy way to enhance the photocatalytic efficiency of perovskite materials. Substituting the different materials can introduce defects in the perovskite materials in the perovskite structure. These defects act as a site to trap the charge carriers and thus enhance the separation of charge carriers and increase the photocatalytic efficiency. These defects can be a vacancy of an extra atom that results in the formation of the line or screw dislocation.^{143–145}

In perovskite materials, three different alteration sites allow the introduction of the defects or vacancies. The doping at the A and B site cations introduces the dislocation but does not allow structural changes. The structural changes can introduce vacancies at the A site or O site. The vacancy at the B site is challenging to introduce due to the BO_6 octahedra. Furthermore, it is thermodynamically unfavorable to introduce the vacancy at the B site due to the high charge value and the small B site cation size.^{146,147}

The vacancies at the A site can be induced by substituting the A-site cation with a cation of the high or low valence. The substituted single perovskite oxide formula is: $\text{A}_{1-x}\text{A}_x\text{BO}_3$ and the oxygen-deficient vacancy can be created by doping the sulphur or nitrites. The second approach is doping at the B site, in which the reduction of the B site produces oxygen vacancy. In recent years, many defect-rich perovskite materials with excellent photocatalytic activity have been reported. Fig. 9 represents different strategies for bandgap tuning of perovskite materials.^{30,148,149}

The potential of semiconductor photocatalyst mainly depends on the electron injection capacity of the material, which is controlled by the energies of valence (E_{VB}) and conduction bands (E_{CB}). Therefore, to investigate the possible applications of semiconductors, it is crucial to have an understanding of the E_{CB} and E_{VB} band edges. In a semiconductor, the

Fermi level (E_F) determines the electrochemical potential of electrons. At thermodynamic equilibrium, E_F tells the occupation of the energy levels, but thermodynamic equilibrium can be perturbed by external bias or irradiation due to injection or photogeneration of holes and electrons. Therefore, the quasi-Fermi levels define the non-equilibrium densities of electrons in conduction band and holes in valence band. Generally, the quasi-Fermi level for the majority carriers approximates the equilibrium E_F because of the negligible increase of density of majority carriers. However, the quasi-Fermi level can be shifted because of the small minority carriers at equilibrium.¹⁵⁰

When a semiconductor is in contact with another phase, the ionic interactions at the interface of the two phases cause an electrostatic adjustment in the material. To attain the equilibrium, especially at the semiconductor/electrolyte interface, the electrons flow from the phase of more negative E_F to the other, in which the semiconductor E_F matches the electrolyte $E_{F,\text{redox}}$. This forms a space charge layer (SCL) in the semiconductor phase, which is associated with the upward bending of the band edges in the n-type semiconductor (Fig. 10c) and downward band bending in the p-type semiconductor (Fig. 10d). The SCL contributes to an internal electric field in the semiconductor, where majority carriers are forced away from the interface of semiconductor/electrolyte. Such an SCL accounts for one of the three distinct double layers, in addition to the Helmholtz layer and Gouy–Chapman layer, which are commonly present at the interface of semiconductor/electrolyte.¹⁵⁰

Recyclability of perovskite photocatalyst. Reusability is crucial for a photocatalyst, reflecting its superiority in the photocatalysis domain. It is worth mentioning that commonly available or used photocatalysts are homogeneous photocatalysts that cannot be recycled in the developed methods. Moreover, their practical applications are limited because of complex synthesis approaches, the high cost of noble metals, conditions of air-free reaction, and modest activity. Therefore, it

is essential to develop an easily produced heterogeneous photocatalyst that also exhibits the property of easy catalyst separation along with recyclability. The researchers have recently started reporting heterogeneous perovskite photocatalyst in photocatalytic organic synthesis. The perovskites-catalyzed selective oxidation of benzyl alcohols to aldehydes under visible light irradiation has been reported by a group of researchers. Another group reported the photoredox CsPbBr_3 -catalyzed oxidative coupling of thiols to disulfides and cross-dehydrogenative coupling of dialkyl H-phosphonates with tertiary amines to α -phosphoryl tertiary amines. Yan and their fellows also reported the α -acylmethylation of aldehydes starting from aldehydes and α -bromo ketones catalyzed by CsPbBr_3 under light. The same group also used CsPbBr_3 photocatalyst for the formation of C–C bond *via* C–H activation, formation of C–N, and C–O *via* N-heterocyclization, and arylation. A group of researchers prepared a heterogeneous perovskite photocatalyst and used it at least five times without noticeable degradation in its activity.^{151,152}

Applications of photocatalysis

There are numerous photocatalysis applications, but during the last couple of decades, a lot of focus has been given to applications having environmental applications such as wastewater treatment, nitrogen fixation, CO_2 reduction, air purification, and water splitting. All of these applications except air purification have been discussed in the current article.

Degradation of water pollutants

Rapid industrial growth, mainly the textile industry, produces increased chemical wastes in the water. Industrial chemical wastes or pollutants are known as dyes. The dyes produced by the textile industry can impede plant growth, impair photosynthesis, and its accumulation in soil disturbs the food chain. The textile dyes in water also cause genetic problems and cancer. The dyes in water aggravate the regulatory functions of the different glands in humans and can also have adverse effects, like infertility and immune suppression in humans. The traditional ways to clean the dyes in water give rise to massive sludge because of adsorbent usage, which can further cause bacterial infections and skin problems. The photocatalytic degradation of the contaminants in the water is more reliable than the traditional methods. Recycling the adsorbents in conventional methods generally generates secondary pollutants, and recycling adsorbents also requires harsh conditions.^{153–156}

The use of the photocatalyst is an eco-friendly way to degrade these water pollutants. The photocatalytic techniques utilize the advanced oxidation process (AOP) for degradation. The interaction of the light with the photocatalyst generates electron–hole pair. Generally, oxygen is employed as an electron scavenger to increase the recombination time for enhanced photocatalytic activity. The redox reaction of the photogenerated electron–hole pair gives reactive species such as $(\text{OH}^*, \text{OH}^-, \text{H}^+)$, and these reactive species then attack the organic

pollutants and degrade them into low molecular weight products (environmentally friendly products) within no time.^{153,157,158}

The heterogeneous design and the self-cleaning surface of the catalyst make recyclability much easier. The reactions occur at the catalyst's surface, followed by the desorption of the materials; thus, this method is known as a sustainable solution to address the water contamination crisis.^{159,160}

The photocatalytic activity can not only be monitored by investigating the absorption spectra of the dye molecule but also involves the investigation of the mineralized products formed due to the cleavage of the chromophore. The mineralized products can be investigated by measuring the chemical oxygen demand (COD) and total organic carbon (TOC). The photocatalytic reaction for degradation of the contaminants occurs in an aqueous environment. The irradiation of the light on the aqueous system (consisting of photocatalyst + polluted water) generates photogenerated electron–hole pair in water. The oxygen or different impurities are added as an electron scavenger to increase the recombination time.^{25,104,161,162} The photogenerated electron–hole pair then migrates towards the surface of the photocatalyst and induces the reactive ions (such as OH^* , $\text{O}^{2-}*$, etc.). The redox potential of the created reactive ion species depends upon the bandgap of the photocatalyst. The reactive ion species then degrade the contaminant into the smaller fragments, which are then changed into green compounds. The degradation of the contaminants takes place at the surface of the catalyst. Initially, the dye gets adsorbed at the catalyst surface, and after the degradation product gets desorbed, the new pollutant is adsorbed, and this process continues until no contaminant is left. The overall reaction mechanism is shown in (Fig. 11).^{30,76,135,163,164}

Many perovskite materials are used as a photocatalyst, but titanium, bismuth, and ferrite-based single and double perovskite are widely reported due to their excellent photocatalytic properties.¹⁶⁵ The first reported perovskite material CaTiO_3 exhibited photocatalytic activity and degraded pollutants. The wide bandgap of CaTiO_3 (3.0–3.5 eV) responds only to the UV light and efficiently degrade the brilliant green (BG), methyl blue (MG), and rhodamine B (RhB).^{88,166} The synthesis route and the morphology of the CaTiO_3 structure change the bandgap and thus affect the photocatalytic performance for pollutant degradation. CaTiO_3 nanocuboid showed the excellent photodegradation of the RhB dye upon visible light irradiation. Zirconium (Zr) doping at the Ti site of CaTiO_3 generates oxygen vacancies, producing defects and increasing photocatalytic activity by changing the lattice structure.^{167,168} The reported photocatalytic activity of the Zr doped CaTiO_3 is thirteen times greater than the un-doped CaTiO_3 . Fe-doped CaTiO_3 efficiently degraded the methyl blue using the visible light source.¹⁶⁶ The doping of the Fe in the CaTiO_3 increased the absorption ability of CaTiO_3 . The photocatalytic activity also depends upon the calcination temperature and the irradiation time of the light. Fe-doped CaTiO_3 showed 100% photodegradation of the methyl blue at optimum condition (temperature, irradiation time, and light source).¹⁶⁹ BaTiO_3 , SrTiO_3 , and other titanium-based perovskite materials have also shown better photodegradation of the pollutants.^{101,102,170}





Fig. 8 Schematic of the Schottky barrier.¹²⁶

Fig. 9 Strategies for tuning bandgap.

Ferrites-based perovskite ($AFeO_3$, where A can be La, Bi, Ca, Sr, Gd, etc.) attracted researchers due to their low cost and small bandgap compared to the titanium-based perovskite.¹⁷¹ The widely used ferrite-based perovskite is bismuth ferrite ($BiFeO_3$). The small bandgap (2.0–2.77 eV), excellent stability, and strong photoabsorption of $BiFeO_3$ allow the efficient photodegradation of organic dyes from textile and pharmaceutical industries under visible light.^{172–174} The pure $BiFeO_3$ in the sunlight showed 69% photodegradation of methyl blue. The doping at different sites of $BiFeO_3$ has shown better results. Sc doped $BiFeO_3$ showed 100% photodegradation of the methyl blue in 3 hours under sunlight. The improved efficiency was attributed to improved ferroelectric properties due to lattice distortion

produced by doping.⁹⁸ Mesh of $BiFeO_3$ showed 98% photodegradation of the methyl blue within 4 hours. The excellent photocatalytic activity of $BiFeO_3$ was due to the high interaction of the dye molecules and photocatalyst. $Bi_{0.90}La_{0.10}Fe_{0.95-}Mn_{0.05}O_3$ showed 97% photodegradation of Congo-red within 2 hours under the sunlight.²⁵

Tantalite-based perovskite is also reported for the degradation of water pollutants. Due to excellent photochemical stability, sodium tantalite ($NaTaO_3$) showed photocatalytic degradation properties. The efficiency of the $NaTaO_3$ based photocatalytic system is quite less due to the wide bandgap of the material. Still, the doping of nonmetals increases its efficiency by creating a local state between the conduction and






Fig. 10 Energy levels of the semiconductor/electrolyte interface before (a and b) and after contact (c and d).¹⁵⁰




Fig. 11 Photocatalytic pollutant degradation.

valence band. The reported photodegradation of methyl blue is 95.21% by nitrogen-based NaTaO_3 photocatalyst using sunlight as an irradiation source.^{175,176} Different perovskite materials used for photocatalytic pollutant degradation are given in Table 2.

Photocatalytic water splitting. Hydrogen is considered a green and clean fuel and one of the best alternatives to fossil

and other non-renewable energy resources. The photocatalytic splitting of the water produces H_2 and O_2 oxygen by the four-electron process. The overall reaction of water splitting is depicted in eqn (9).




Table 2 Reported perovskite materials for photocatalytic pollutant degradation

Material	Morphology	Bandgap (eV)	Pollutants/dyes	Light source	Degradation rate
CaTiO ₃ (ref. 177)	Bare	~3	MO	UV light	54% after 60 minutes
CaTiO ₃ –graphene ¹⁷⁸	Composites	~3	MO	UV light	98% after 60 minutes
C doped SrTiO ₃ (ref. 179)	Cubic particle, nanorod, nanotube	Less than 3.2	MB, MO, RhB, phenol, and BPA	Visible light	95% of MB, MO, RhB, and 70% of phenol and BPA after 3 hours irradiation
S–SrTiO ₃ (ref. 180)	Powder	<3.2	2-Propanol	500 W-Xenon lamp	After 60 min of irradiation, 80% of propanol is converted into acetone
Cu doped SrTiO ₃ (ref. 181)	Nanoparticle	2.96	Methyl blue	Visible light	66% within 120 minutes
Fe doped SrTiO ₃ (ref. 182)	—	2.6	Tetracyclin TC	Visible light	71.6% in 80 minutes
Mn-doped SrTiO ₃ (ref. 183)	Nanocubes	2.76	Tetracyclin TC	Visible light	66.7% in 60 minutes
N doped NaTaO ₃ (ref. 184)	Cubic	2.48	MB, MO	UV-visible light	95.1% in 60 minutes
Ag/AgGaO ₂ (ref. 185)	Composite	—	MB	Visible light	95% in 180 minutes
LaFeO ₃ (ref. 186)	Nanoparticle	2.36	MB	Visible light	100% after 60 minutes
Z-scheme MoS ₂ /CaTiO ₃ (ref. 187)	Nanospheres	3.23	TC	Simulated solar light	70% in 60 minutes
p–n type (30–60% Ag ₃ PO ₄)/NaTaO ₃ (ref. 188)	Crystalline	2.32–3.78	RhB	Visible light	87% in 25 minutes
BiOI/KTaO ₃ p–n heterostructure ¹⁸⁹	Composite	1.76–2.23	RhB and phenol	Visible light	91% after three cycles
BiFeO ₃ /BiVO ₄ (ref. 190)	Nanocomposites	2.23	RhB	Visible light	69% within 120 minutes
In ₂ S ₃ /NaTaO ₃ (ref. 191)	Composite	2.1–4.0	TC	Stimulated solar irradiation	53.2% for 20 wt% In ₂ S ₃ /NaTaO ₃ within 180 minutes
(10 wt%) LaFeO ₃ /SnS ₂ (ref. 192)	Composite Z-scheme heterojunction	2.11	TC	Visible light	28.8% in 120 minutes
(1.7 wt%) Ag–KNbO ₃ (ref. 193)	Nanowires	2.2–3.35	RhB	UV-visible	95% with UV in 90 minutes and 65% with VIS in 120 minutes
7% Ni-doped BiFeO ₃ (ref. 194)	Nanoparticle	~2.28	MB	Visible light	92% within 60 minutes
LaNiO ₃ (ref. 195)	—	2.26	MO	Visible light	74.5% after 5 hours
(5 wt%)NiS/LaFeO ₃ (ref. 196)	LFO nanoparticle NiS nanosheets (heterostructure)	1.2–2.0	MO	Simulated sunlight	90.9% higher than pure LFO
NaTaO ₃ /rGO (1.5%) ¹⁹⁷	Composite	3.87	MB	8 W UV lamp	95% after 90 minutes
N-doped NaTaO ₃ (ref. 176)	Cubic	Less than 3.94	MO	Visible light	95.21% after 14 hours
(50% wt) BiFeO ₃ /V ₂ O ₅ (ref. 198)	Nanoplates	2.05–2.19	MB	Visible light	96% after 120 minutes
BiFeO ₃ /25% wt ZnFe ₂ O ₄ (ref. 199)	Nanocomposites	2.2–1.96	MB	Visible light	96% after 30 minutes
Sm and Mn doped BiFeO ₃	Nanoparticles	1.45–2.08	MB, MV	Visible light	65%,64% after 2 hours
Carbon dots/BaZrO ₃ (ref. 200)	Hybrid nano nanomaterial	4.8	MB	UV light	90% after 60 minutes
Z-scheme LaCoO ₃ /g-C ₃ N ₄ –60 wt% (ref. 135)	Composites	2.46	Phenol	Visible light	85% in 5 hours
CuS/Bi ₂ WO ₆ (ref. 201)	Composites	1.76–2.69	RhB	Visible light	90.0% in 50 min
Bi ₂ WO ₆ (ref. 202)	—	2.7–2.85	EBT	Visible light	74% in 180 min
Sm-doped Bi ₂ WO ₆ (ref. 203)	—	2.4–2.5	RhB	Visible light	98.4% in 30 min
(0.3 : 1) Bi ₂ WO ₆ /ZnO ²⁰⁴	Flower-like composite	2.6–3.2	MB, TC	Visible light	98.4% for MB in 120 min, 90% for TC in 120 min
Bi ₂ MoO ₆ (ref. 205)	Nano sheets	2.6–2.9	MB	Visible light	90% of MB in 120 min
BiFeO ₃ /Bi ₂ Fe ₄ O ₉ (ref. 206)	Nanofibers	1.96–2.15	RhB	Visible light	65% in 1.5 h
2% Ag/Bi ₂ WO ₆ (ref. 207)	3D hierarchical hybrid material	—	RhB, TC	Visible light	100% in 50 min/90% in 70 min
CQD/Bi ₂ WO ₆ (ref. 208)	Composite	2.6	MO, BPA	Visible/IR light	(94.1%/18.3%) in 120/90 min, (99.5%/25.5%) in 60/90
g-C ₃ N ₄ /Bi ₂ WO ₆ (ref. 209)	Nanosheets	2.69	Ibuprofen	Visible light	96.1% in 60 min
Bi ₂ WO ₆ /RGO ²¹⁰	Microsphere	2.3–2.69	Phenol, MO, RhB, SMM, SN	Sunlight	65.5% in 480 min, 78.5% in 480 min, 99.5% in 480 min, 70.9% in 480 min, 57.6% in 480 min
La ₂ NiO ₄ /ZnO ²¹¹	Heterosystem	1.87–3.1	MO	Sunlight	99.9% in 60 min
SnSe/LaNdZr ₂ O ₇ (ref. 212)	Composites	1.69–3.34	Foron blue	Visible light	86.3% in 60 min
m-Bi ₂ O ₄ /Bi ₂ O ₂ CO ₃ (ref. 213)	Composite	1.53–2.0	RhB	Visible light	95.3% in 50 min



The positive Gibbs free energy shows that with the help of some external stimuli, the reaction proceeds in the forward direction. The use of some sacrificial layer (or agent) in combination with the photocatalyst material produces hydrogen and oxygen, and the reaction is known as hydrogen or oxygen evolution reaction. The process of producing hydrogen and oxygen from water by using semiconductor photocatalyst material and light as an irradiation source to innate the reaction is known as photocatalytic water splitting.^{214–216} The photocatalytic reaction mainly depends upon the reduction potential required for water splitting. The minimum potential energy needed to convert H₂ and O₂ from water is 1.23 eV.²¹⁷

One-step photo reaction requires only one semiconductor photocatalyst material, and the overall process is depicted in Fig. 12. The use of two photocatalytic materials to form composite or heterojunction can enhance the performance of the perovskite material. Z-scheme mainly employs two materials in photocatalytic water splitting. Z-scheme is an eight electrons process. The selection of the photocatalyst depends upon the target product. In Z-scheme, the hydrogen-evolving or oxygen-evolving photocatalysts are combined, and both catalysts perform their function separately. The mediators (solid or aqueous) help transfer charge in the Z-scheme. Direct Z-scheme is a process without any mediator. The thermodynamic requirement for the water splitting can be decreased in the Z-scheme by allowing only hydrogen and oxygen-evolving semiconductors. Still, the kinetics of the Z-scheme reactions are challenging, and nearly half of the hydrogen and oxygen are produced compared to a one-step reaction.^{218–221}

The performance of the photocatalyst can be evaluated by the quantity of H₂ evolved and the recyclability of the photocatalyst. The reaction rate is not always proportional to the use of photocatalyst mass; therefore, the preferred way is H₂ evolved per unit time (μmol h⁻¹) with the mass utilized during reaction rather than writing the amount of H₂ produced in a mass normalized from (μmol h⁻¹ g⁻¹).^{222,223} The intensity of the

incident light for the photocatalytic performance is the number of photons collected per particle is directly related to the particle size. The reaction rate for the photocatalyst is proportional to the intensity of the incident light. In some cases, the rate of reaction increases with excitation intensity. In contrast, the increase in intensity in some reactions leads to decreased photocatalytic efficiency due to the second-order recombination of the photo-induced charges.²²⁴ At low intensity, the concentration of the photogenerated charge carrier is insignificant compared to the concentration of intrinsic majority carriers. Thus, it can also be assumed that the concentration of minority charges varies with incident light's intensity, whereas the concentration of majority charges stays nearly constant.^{225–227}

The recombination of the photogenerated charges can be determined by the quasi-first-order reaction with respect to the concentration of minority carriers induced by the light source. In simple words, the order of a photocatalytic reaction at a specific intensity gives an idea about the photoexcited charge carrier concentration. For comparison, a standard parameter of the apparent quantum efficiency (AQE) and the solar to hydrogen conversion (STH) are reported for measurements of photocatalytic activity.^{228–230}

Apparent quantum efficiency (AQE)

$$\text{number of reacted electron} \over \text{number of incident photon} \times 100\%$$

$$= \frac{2 \times \text{number of H}_2 \text{ molecule evolved in 1 hour}}{\text{number of incident photon in 1 hour}} \times 100$$

$$\text{STH} = \frac{\text{energy of generated H}_2}{\text{solar energy irradiating the reaction cell}} \times 100\%$$

Moreover, the stability of photocatalyst for real-world applications is vital as these materials need a life cycle of about ten years with an efficiency of about 5–10% STH to meet the goal




Fig. 12 Photocatalytic water splitting.



Table 3 Perovskite materials for photocatalytic water splitting

Material	Co-catalyst	Morphology	Amount of H ₂ and O ₂ evolved/AQE value	Bandgap (eV)	Reaction conditions	Light source
CaTiO ₃ -MoS ₂ -RGO ²⁴⁵	None	Nanocomposite	808.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$ 5.4% at 365 nm	3.42–3.60	25 vol% lactic acid	Sunlight
Defected CaTiO ₃ (ref. 167)	None	Nanosheets	2.29 $\text{mmol g}^{-1} \text{h}^{-1}$	2.85	For the synthesis of the defected sheet, the hydrogenation treatment for 5 hours and 50% methanol	300 W Xe lamp
Cu-doped CaTiO ₃ (ref. 246)	None	Powder	295.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$	3.40–3.9	20 vol% methanol	300 W Xe lamp ($\lambda > 415 \text{ nm}$)
Er-doped CaTiO ₃ (ref. 247)	Pt	Nanocrystal	461.25 $\mu\text{mol h}^{-1}$	3.30	20 vol% methanol	300 W Xe lamp (320–390 nm)
CaTiO ₃ /Pr ³⁺ -Y ₂ SiO ₅ /RGO ²⁴⁸	Pt	Composite	0.19 $\mu\text{mol g}^{-1} \text{h}^{-1}$ / 0.003% at 400 nm	—	None	300 W Xe lamp ($\lambda > 400 \text{ nm}$)
CdSe/CaTiO ²⁴⁹	Pt	Nanocomposite	3.01 $\text{mmol g}^{-1} \text{h}^{-1}$	1.6–3.27	Na ₂ S and Na ₂ SO ₃	300 W Xe lamp
CaTiO ₃ (ref. 250)	Pt	—	0.39 $\mu\text{mol min}^{-1}$	3.4	None	300 W Xe lamp
AgCl/Ag/CaTiO ₃ (ref. 133)	None	Nano sheets	226.53 $\mu\text{mol g}^{-1} \text{h}^{-1}$	—	10 vol% methanol	300 W Xe lamp
SrTiO ₃ (ref. 251)	Pt cluster	Powder	23.0 $\mu\text{mol h}^{-1}$ /8.0% at 3.2 350 nm	—	None	300 W Xe lamp
SrTiO ₃ : C, N ²⁵²	Pt	Nanocuboid	68.0 $\mu\text{mol h}^{-1}$	2.97	20 vol% methanol	300 W Xe lamp
Cr, Ta codoped SrTiO ₃ (ref. 253)	Pt	—	122.6 $\mu\text{mol h}^{-1}$ /2.6% at 420 nm	2.3	10 vol% methanol	300 W Xe lamp ($\lambda > 420 \text{ nm}$)
Pt@CdS/3DOM-SrTiO ¹³⁴	Pt	Composite	57.9 $\text{mmol g}^{-1} \text{h}^{-1}$	2.4–3.2	10 vol% lactic acid	300 W Xe lamp
CdS/Au/3DOM-SrTiO ₃ (ref. 254)	None	Composite	5.46 $\text{mmol g}^{-1} \text{h}^{-1}$ / 42.2% at 420 nm	2.4–3.2	0.1 M Na ₂ SO ₃ and Na ₂ S	300 W Xe lamp ($\lambda > 420 \text{ nm}$)
CdSe/BaTiO ₃ (ref. 255)	None	Nanocube composite	53.4 $\mu\text{mol g}^{-1} \text{h}^{-1}$	1.8–3.2	0.05 M Na ₂ SO ₃ and Na ₂ S	300 W Xe lamp ($\lambda > 420 \text{ nm}$)
CdS/NiTiO ₃ /Co ²⁵⁶ TiO ₂ /MgTiO ₃ /C ²⁵⁷	None Pt	Nanocomposite Nanocomposite	476.20 $\mu\text{mol h}^{-1}$ 33.30 $\text{mmol g}^{-1} \text{h}^{-1}$ / 1.46 $\mu\text{mol g}^{-1} \text{h}^{-1}$	2.1–2.4 —	Lactic acid 30 vol% methanol	Vis-NIR Solar light/ visible light
NaTaO ₃ (ref. 258)	RuO ₂	Powder	430.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$	3.92–4.00	None	400 W Hg lamp
NaTaO ₃ microspheres microcubes ⁸⁷	NiO	Microsphere	0.26 $\mu\text{mol h}^{-1}$ /0.05 $\mu\text{mol h}^{-1}$	—	None	8 W UV lamp, 254 nm
NaTaO ₃ /RGO ²⁵⁹	None	Composite	267.50 $\mu\text{mol g}^{-1} \text{h}^{-1}$	—	0.05 M Na ₂ SO ₃ and Na ₂ S	250 W Hg lamp
Ag–NaTaO ₃ (ref. 260)	None	Nanocubes	3.54 $\mu\text{mol g}^{-1} \text{h}^{-1}$	3.0–4.7	25 vol% methanol	300 W Xe lamp
C-doped KTaO ₃ (ref. 261)	Pt	Nanocubes	592.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$	—	20 vol% methanol	300 W Xe lamp
Ag–KTaO ₃ (ref. 260)	None	—	185.60 $\mu\text{mol g}^{-1} \text{h}^{-1}$	2.9	25 vol% methanol	300 W Xe lamp
Porphyrin-KTa(Zr)O ₃ (ref. 262)	None	—	53.7 $\mu\text{mol h}^{-1}$ /29.4 $\mu\text{mol h}^{-1}$	—	None	300 W Xe lamp
LiTaO ₃ (ref. 263)	None	Nanoparticles	712.0 $\mu\text{mol h}^{-1}$	4.6–4.7	None	250 W high- pressure Hg lamp
Nb-substituted AgTaO ₃ (ref. 264)	Pt and Co-Pt	—	1.68 $\mu\text{mol h}^{-1}$	—	None	Xe lamp
N-rGO/N-NaNbO ₃ (ref. 265)	Pt	Nanocrystal	2.34 $\text{mmol g}^{-1} \text{h}^{-1}$ / 5.1% at 320 nm	3.4–3.7	20 vol% methanol	300 W Xe lamp
NaNbO ₃ wires ⁹¹	Pt	—	26.6 $\mu\text{mol h}^{-1}$	—	20 vol% methanol	300 W Xe arc lamp
C-doped KNbO ₃ (ref. 266)	Pt	—	211.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$	3.06	20 vol% methanol	300 W Xe lamp
CdS/Ni/KNbO ₃ (ref. 267)	None	Nanocomposite	23.5 $\mu\text{mol h}^{-1}$	—	50 vol% methanol	500 W lamp
MoS ₂ /C-doped KNbO ₃ (ref. 97)	Pt	—	1.30 $\text{mmol g}^{-1} \text{h}^{-1}$	—	20 vol% methanol	300 W Xe lamp
g-C ₃ N ₄ /SrTiO ₃ (ref. 79)	Pt	Nanocomposite	966.80 $\mu\text{mol g}^{-1} \text{h}^{-1}$	2.68–3.16	10 vol% TEOA	300 W Xe lamp ($\lambda > 420 \text{ nm}$)
KNbO ₃ /g-C ₃ N ₄ (ref. 268)	Pt	Composite	180.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$	2.7–3.06	20 vol% methanol	300 W Xe lamp ($\lambda > 420 \text{ nm}$)
	NiS	Composite		2.0–2.6	10 vol% TEOA	

Table 3 (Contd.)

Material	Co-catalyst	Morphology	Amount of H ₂ and O ₂ evolved/AQE value	Bandgap (eV)	Reaction conditions	Light source
LaFeO ₃ /g-C ₃ N ₄ (ref. 269)	None	Heterostructure nanofiber	121.0 $\mu\text{mol g}^{-1} \text{h}^{-1}$ / 2.01% at 420 nm	—	300 W Xe lamp ($\lambda > 400 \text{ nm}$)	—
BiFeO ₃ /Bi ₂ Fe ₄ O ₉ (12.3% Bi ₂ Fe ₄ O ₉) ²⁰⁶	1 wt% Pt for H ₂ production (water reduction) and 1 wt% CoO for O ₂ production (water oxidation)	Nanopowder	800 $\mu\text{mol g}^{-1} \text{H}_2$	1.96–2.15	A sacrificial layer of triethanolamine	—
Sr ₂ CuWO ²⁷⁰	—	—	No H ₂ was produced, and the quantum efficiency of O ₂ produced was 0.034	2.07	A sacrificial agent such as sodium sulfite for H ₂ production	Visible light ($\lambda \geq 420 \text{ nm}$)
g-C ₃ N ₄ /Ba ₅ Ta ₄ O ₁₅ (33.47 wt% g-C ₃ N ₄) ²¹⁸	1 wt% Pt	Nanosheets wrapped by g-C ₃ N ₄ foil/nanosheets heterostructure	60–70 $\mu\text{mol of H}_2$ evolved in 5 hours	2.8–4.3	A sacrificial layer of oxalic acid	Visible light
Cs ₂ AgBiBr ₆ (ref. 271)	2.5% RGO	Composite	489 $\mu\text{mol g}^{-1} \text{H}_2$ in 10 h	2.77	H ₂ evolution in saturated HBr aqueous solution	Visible light
Ba ₅ Ta ₄ O ₁₅ (ref. 272)	Cr ₂ O ₃ /0.0125 wt% Rh	Nanoparticle	465 $\mu\text{mol h}^{-1} \text{H}_2$ and 228 $\mu\text{mol h}^{-1} \text{O}_2$ /100 $\mu\text{mol h}^{-1} \text{H}_2$	4.5	Ba ₅ Ta ₄ O ₁₅ prepared by the citrate method	Visible light
Zn ₂ Ti ₃ O ₈ (ref. 273)	5 wt% RuO ₂	Nanorods	4 $\mu\text{mol h}^{-1}$ (0.1 gram) of H ₂ and 2 mmol h ⁻¹ (0.1 g) of O ₂	3.56	Before the photocatalytic activity, the solution is deaerated by evacuation	300 W Xe lamp
Ca ₂ NiWO ₆ (ref. 274)	None	Nanoparticle	1.38 mmol g ⁻¹ h ⁻¹ O ₂	2.8	Ca ₂ NiWO ₆ is prepared by a solid-state reaction	Visible light
W-doped Sr ₂ FeNbO ₆ (Sr ₂ FeNb _{1-x} W _x O ₆) ($x = 0.01$ –0.09) ²⁷⁵	0.2 wt% Pt	Nano particles	1.1–33 $\mu\text{mol h}^{-1}$ of H ₂ depending upon x and 28–605 $\mu\text{mol h}^{-1}$ of O ₂ depending upon x	2.17	The reaction is carried out in an aqueous methanol solution	Visible light
Cr–PbBi ₂ Nb ₂ O ₉ (ref. 276)	1 wt% of Pt	Layered perovskite system	9.4 $\mu\text{mol h}^{-1}$ of H ₂ and 671 $\mu\text{mol h}^{-1}$ of O ₂	2.63–2.88	—	Visible light
Bi ₂ WO ₆ (ref. 277)	None	Nanoparticle	188.25 $\mu\text{mol g}^{-1} \text{h}^{-1}$ of 3.1 H ₂	—	1 : 1 of glycerol–water is used	Visible light
Cr _x La _{2-x} Ti ₂ O ₇ ($x = 0.01$ –0.05%) ²¹⁶	1.0 wt% Pt	Nanopowder	50–90 $\mu\text{mol h}^{-1}$ of H ₂ produced	2.2	Methanol as hole scavenger	UV irradiation ($\lambda > 200 \text{ nm}$)
Fe _x La _{2-x} Ti ₂ O ₇ ($x = (0.01$ –0.05%) ²⁷⁸	1.0 wt% Pt	Nanopowder	32–45 $\mu\text{mol h}^{-1}$ of H ₂ produced	2.6	Methanol as hole scavenger	UV-visible
Sr ₂ NiWO ₆ (ref. 279)	1.0 wt% Pt	Nanoparticles	420 $\mu\text{mol g}^{-1} \text{h}^{-1}$ of O ₂ /8.6 at 420 nm	2.88	AgNO ₃ and FeNO ₃ as sacrificial layer	Visible light
La ₂ Ti ₂ O ₇ (ref. 280)	1.0 wt% NiO	Nanoparticles	400 $\mu\text{mol h}^{-1}$ of H ₂ produced	< 3.0	Photoreduction reaction was performed in an aqueous CH ₃ OH solution	UV-visible
MA ₂ CuCl ₂ Br ₂ (ref. 281)	1.0% loading of CuO	Powder	141 $\mu\text{mol of H}_2/\text{geal}$ in 24 hours/144.11 $\mu\text{mol of O}_2$ produced	—	Argon was introduced into the reactor to avoid the presence of oxygen and 1 mL of water was used as a reagent	Solar simulator
CsCa ₂ Nb ₃ O ₁₀ (ref. 282)	None/0.05 wt% Rh	Nanosheets	450–500 $\mu\text{mole of H}_2$ in 2 hours/1700 μmole in 3 hours	3.6	Photoreduction reaction was performed in an aqueous CH ₃ OH solution	UV light
KCa ₂ Nb ₃ O ₁₀ (ref. 283)	None	Nanosheets	550 $\mu\text{mol of H}_2$ in 2 hours	3.6	CH ₃ OH is used	UV light



price of \$ 2.00–4.00 per kg. The absorption wavelength for water splitting should be around 526 nm (2.36 eV) because below this wavelength, the photon's energy is not sufficient to achieve STH efficiency of 5–10%, considering that the reaction takes place for a lower wavelength at the AQE = 1. To meet the industrial demand, the practical need for the evolution of H_2 under sunlight, the photocatalyst with the bandgap of less than 2.36 must be developed. The perovskites-based photocatalytic materials gained significant attention for the practical application of water splitting under UV light and visible light.^{231–234}

Titanium-based perovskite materials are widely reported for photocatalytic water splitting. Doping and co-doping change the morphology and bandgap of $SrTiO_3$, thus are making it a suitable visible light photocatalyst for water splitting reaction. The use of the Pt as a co-catalyst induces the Schottky barrier and can make the photocatalyst responsive to visible light. The presence of the Pt also provides the site for the proton reduction. The quantum yield efficiency by using the visible light as an irradiation source is 0.9% while using the UV light, the quantum yield efficiency of the system is 1.9%. The use of the other metals as Au, Ag, Fe, Ce, and Ni are also reported.^{235–239}

Alkali tantalates are the best perovskite material reported for photocatalytic water splitting when the parameters like the doping of the metal cations and morphology (nanocubes) of tantalates-based material are optimized well. The reported hydrogen evolution by $KTaO_3$ nanocubes is $375 \mu\text{mol g}^{-1} \text{h}^{-1}$. The Ag doping at the surface of the $KTaO_3$ increases the hydrogen evolution in UV light. The irradiation of the UV light generates oscillations in the conduction band of absorbed silver and thus allows the easy excitation of the particles to the conduction band of $KTaO_3$. The local electric field of $KTaO_3$ was enhanced with the doping of the silver nanoparticles. The enhanced field promotes the electron–hole pair generation, and therefore, increases the photocatalytic splitting. The reported evolution of the hydrogen in the presence of Ag as a dopant in $KTaO_3$ is $2072 \mu\text{mol g}^{-1} \text{h}^{-1}$.^{240–243} The lanthanum and ferrite-based perovskite material are also reported.²⁴⁴ Table 3 lists various perovskite materials used for water splitting.

Photocatalytic CO_2 reduction. The atmospheric concentration of CO_2 is increasing at an alarming rate due to increased human activities, deforestation, burning of fuels, and industrialization. The increased CO_2 emission is causing global warming, and for environmental sustainability, it is essential to convert CO_2 into valuable products. Mother Nature blessed humans with photosynthesis, in which chlorophyll act as a natural photocatalyst and, in the presence of sunlight, converts CO_2 into water, oxygen, and food for plants. The photocatalyst also converts CO_2 into valuable products in sunlight.^{16,277,284,285}

Photocatalytic CO_2 reduction requires more electrons than hydrogen evolution reaction. The end product from depending upon the number of available electrons. One of the limiting factors is the low water solubility of CO_2 . The complete reduction of the CO_2 in water also produces H_2 . The Z-scheme or heterojunction process for CO_2 reduction is reported frequently.^{30,122}

The first step in CO_2 reduction involves the radical anion formation at -1.9 eV, which is impossible for most perovskite material due to less negative CB potentials of the perovskite material; therefore, high activation energy is required. The surface adsorption of CO_2 by catalyst generates the charge $\text{CO}_2^{\delta-}$ which facilitates the reaction to proceed. Surface engineering can enhance the CO_2 adsorption to the photocatalyst's surface and thus, increases the conversion efficiency. The low conversion efficiency of the CO_2 is considered a significant concern in dealing with photocatalytic CO_2 reduction.^{286,287} The co-catalyst can lower the activation energy resulting in enhanced photocatalytic activity. The reaction mechanism is shown in Fig. 13. In CO_2 reduction, the CO_2 gets adsorbed on the photocatalyst's surface, and electron–hole pair is produced upon irradiation. The photo-generated charges then move to the surface of the photocatalyst, and CO_2 is reduced into the valuable fuel. After the reduction of CO_2 by the photogenerated electrons and the formation of O_2 by photogenerated holes, the reduced and the oxidized product is formed by the desorbed hole and electron, and the cycle continues. The end product depends upon the total number of electrons used in the procedure. For a better photocatalytic activity, a significant number of electrons should migrate towards the surface of the photocatalyst, and the bottom level of the photocatalyst's conduction band should be more negative than the redox potential of CO_2 . The water or additional sacrificial reagents must consume the photogenerated holes; otherwise, holes recombine with the oxygen. The photocatalytic CO_2 reduction can be enhanced by optimizing CO_2 adsorption, charge separation, and desorption of the products. The process of CO_2 reduction in the presence of co-catalyst is shown in Fig. 14.^{288,289}

The CO_2 reduction by photocatalyst takes place in the presence of a water molecule, while the reaction in the gaseous or aqueous phase. The reduction potential of CO_2 should be small compared to the reduction potential of conduction band minimum and water to obtain valuable solar fuel. During the oxidation, the oxygen molecule is formed by the reaction of the water with a valence band hole.

Calculation of the AQE is used to access the performance of the perovskite material for photocatalytic CO_2 reduction.^{290–292}




Fig. 13 Photocatalytic CO_2 reduction.





Fig. 14 Photocatalytic reaction in presence of co-catalyst.

The reactions are shown as:



Titanium-based perovskite oxides exhibit excellent photostability for CO_2 compared to the tantalates and niobates. SrTiO_3 perovskite material is widely reported due to better charge transport properties and bandgap equivalent to TiO_2 (3.2 eV), but the poor CO_2 surface adsorption of photocatalyst (SrTiO_3) creates a problem. This problem can be solved by using the metal as a co-catalyst and introducing the oxygen vacancies to improve the adsorption. In the gas phase reactor using visible light, Fe doped SrTiO_3 photocatalyst with Pd (0.5 wt%) as a co-catalyst reduces CO_2 to CH_4 . The yield of the product is 421, and the CO selectivity is 84%.^{16,293-295}

Tantalum-based perovskites are not widely reported for CO_2 reduction because of their wide bandgap. NaTaO_3 photocatalyst in combination with Au (0.5 wt%) as a co-catalyst reduces CO to CH_4 fuel in the gas phase reactor and uses UV-vis light as the irradiation source. The selectivity of CO is 96%, but the yield is small.²⁹⁶ Table 4 lists perovskite materials used for CO_2 reduction.

Nitrogen fixation. Nitrogen plays a vital part in building biomolecules such as amino acids, proteins, and other molecules. Earth's atmosphere has 78% of the dinitrogen (N_2). Dinitrogen air converts into ammonia by the process known as nitrogen fixation. Plants and soil then use the ammonia formed by atmospheric nitrogen to build several processes. The mechanism to create ammonia by nitrogen is the Haber cycle.³¹⁴ At standard conditions, the ammonia formation is a thermodynamically spontaneous process ($\Delta H = -92.2 \text{ kJ mol}^{-1}$). Due to its high ionization energy of 15.58 eV and low electron affinity, the dinitrogen in the air is highly stable; therefore, the atmospheric dinitrogen in the normal conditions cannot be used to prepare the ammonia unless some catalyst or some industrial fixation is used. In industry, by using iron or ruthenium as a base catalyst at high temperatures, the dinitrogen is converted into ammonia by the Haber–Borsch process. But even after the century's advancement, the production of the industrial fixation is still quite low. The NH_3 is one of the essential components in manufacturing fertilizers and hydrogen storage. Therefore, it is essential to synthesize an alternative green route to deal with energy crises and global warming.^{77,315}

Recently the photocatalyst material for nitrogen fixation has gained much attention from researchers. The nitrogen fixation by the photocatalyst utilizes only sunlight and water in the presence of the dinitrogen. The six electrons do the complete conversion of N_2 into NH_3 due to the high activation energy of the process, which makes the process completely impractical. Furthermore, direct electron transfer and proton-coupled electron transfer are not possible for the semiconductor material. Hence, photocatalyst design and surface engineering play an important role in nitrogen fixation.³¹⁶⁻³¹⁸ The reaction by using the photocatalyst is designed to reduce the activation energy and weakens the $\text{N}\equiv\text{N}$ bond. Light irradiation generates the electron–hole pair. These photogenerated charge carriers then



Table 4 Perovskite materials for photocatalytic CO₂ reduction

Perovskite	Co-catalyst	Morphology	Band gap (eV)	Synthesis method/reaction condition	Product	Product concentration or conversion efficiency	Light source
NaTaO ₃ (ref. 297)	2 wt% CuO	Nanocubes	4.1	The hydrothermal method is used for catalyst synthesis. And co-catalyst is loaded <i>via</i> impregnation method/	Methanol and acetone	137.48 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$ 335.93 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$	UV-visible
KTaO ₃ (ref. 298)	None	Nanoflakes	3.6	Perovskite material is prepared by solid-state reaction	CH ₄	19.35 ppm $\text{g}_{\text{cat}}^{-1} \text{h}^{-1}$	UV-visible
NaNbO ₃ (ref. 299)	1.5 wt% Pt	Nanoparticles (cubic)	3.29	Photocatalytic activity is carried out in a gas-phase reactor	CH ₄ and H ₂	0.486 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$ 127 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$	UV-visible
BiFeO ₃ –ZnO (ref. 300)	None	Composites	2.1–3.2	Photocatalytic activity is carried out in a gas-phase	CH ₄	The conversion efficiency of CO ₂ into CH ₄ is 21%	UV-visible
Au–SrTiO ₃ (ref. 301)	0.5 wt% Rh	Nanoparticles	—	Ru is loaded by the impregnation method, CH ₄ and at optimized conditions, 0.5 wt% of Au is used	CO, H ₂ , and CH ₄	66.8 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$ 50.5 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$ 2.8 $\mu\text{mol g}_{\text{cat}}^{-1} \text{h}^{-1}$	Visible light
Basalt fiber@perovskite	None	Core-shell composites	1.92	The hydrothermal method is used for catalyst synthesis	CH ₄	290 $\mu\text{mol g}^{-1} \text{L}^{-1}$ in 6 hours	UV light
PbTiO ₃ (ref. 302)	None	Nanocomposites	2.5	The reaction is carried out in a gas phase reactor	CO, CH ₃ OH	The conversion efficiency of CO ₂ into CO and CH ₃ OH is 24	UV-visible
g-C ₃ N ₄ /KNbO ₃ (ref. 79)	None	Composites	2.7–3.2	KNbO ₃ is synthesized by hydrothermal, and g-C ₃ N ₄ powder is deposited by using the sonication method	CH ₄	1.94 $\mu\text{mol g}^{-1} \text{h}^{-1}$	Visible light
N-doped LaFeO ₃ (ref. 304)	None	Nanocomposites	1.82	—	CH ₄ , CO, O ₂	~110 $\mu\text{mol g}^{-1} \text{h}^{-1}$ 150 $\mu\text{mol g}^{-1} \text{h}^{-1}$ 230 $\mu\text{mol g}^{-1} \text{h}^{-1}$	Visible light
RuO ₂ on SrTiO ₃ (ref. 305)	Ru 0.1–0.4 wt%	Nanoparticles	2.7	The reaction is carried out in a gas phase	Ethanol	80 $\mu\text{mol g}^{-1} \text{h}^{-1}$	Simulated sunlight
BaCeO ₃ (ref. 306)	Ag cocatalyst (0.3 wt%)	Nanoparticles	3.2	Pechini method is used to deposit the co-catalyst	CH ₄	0.55 $\mu\text{mol g}^{-1} \text{h}^{-1}$	UV light
BaZrO ₃ (ref. 200)	0.5 wt% Cu	Nanoparticles	3.2	The photocatalytic reaction is carried out in a cylindrical quartz cell	CH ₄	0.98 $\mu\text{mol g}^{-1} \text{h}^{-1}$	UV light
C-doped LaCoO ₃ (ref. 307)	None	—	2.16	Pechini method is used to deposit the co-catalyst	HCOOH	A minimal amount of HCOOH	UV-visible
LaNi _x Co _{1-x} O ($x = 0.4$) ³⁰⁸	None	Nano particles	1.42	Sol-gel combustion method is used to prepare the catalyst	CH ₄ –CH ₃ OH	678.57 $\mu\text{mol g}^{-1}$, 20.83 $\mu\text{mol g}^{-1}$ in 6 h	Visible light
H ₂ SrTa ₂ O ₇ (ref. 309)	0.5 wt% Ag	Layered perovskite structure	3.75	H ₂ SrTa ₂ O ₇ photocatalyst was prepared by PC and ion-exchange methods, and a photo deposition method was used to load Ag co-catalyst on HST	CO and H ₂	0.39 $\mu\text{mol g}^{-1} \text{h}^{-1}$ of CO and 0.25 of H ₂ $\mu\text{mol g}^{-1} \text{h}^{-1}$	UV light ($\lambda > 200$ nm)
x Bi ₂ WO ₆ /BiOI ($x = 8\%$) ¹²³	None	Nano-composites	2.2–2.9	CO ₂ is reduced to give CH ₄ /CO	CH ₄ /CO	18.32 $\mu\text{mol g}^{-1}$ of CH ₄ and 320.19 $\mu\text{mol g}^{-1}$ in 8 hours	Visible light



Table 4 (Contd.)

Perovskite	Co-catalyst	Morphology	Band gap (eV)	Synthesis method/ reaction condition	Product	Product concentration or conversion efficiency	Light source
Bi ₂ WO ₆ (ref. 310)	None	Nano sheets	2.7	CO is reduced to give CH ₄ experiment is conducted into gas phase reactor	CH ₄	19 ppm g ⁻¹ h ⁻¹ of CH ₄	Visible light
Al ₄ Ti ₄ O ₁₅ , A = Sr, Ca ⁷⁸	Ag	Layered perovskite structure	3.79–3.85	Catalyst is loaded <i>via</i> liquid-phase reduction and impregnation method	CO/O ₂ /H ₂	10 µmol h ⁻¹ of H ₂ and A 400 W high-pressure 16 µmol h ⁻¹ of O ₂ , 22 µmol h ⁻¹ of CO	400 W high-pressure mercury lamp, an inner irradiation quartz cell
BaLa ₄ Ti ₄ O ₁₅ (ref. 78)	0.5–2% Ag	Layered perovskite structure	3.9	Catalyst is loaded <i>via</i> liquid-phase reduction	H ₂ , O ₂ , CO	20–3.2 µmol h ⁻¹ of H ₂ , A 400 W high-pressure 5.7–16 µmol h ⁻¹ of H ₂ and 5.00–22 µmol h ⁻¹ CO	400 W high-pressure mercury lamp, an inner irradiation quartz cell
Bi ₂ WO ₆ (ref. 311)	0.5% wt PtO _x	Ultra-thin nanosheets	—	The PtO _x /Bi ₂ WO ₆ was prepared by photoreduction method	CH ₄	108.8 ppm g ⁻¹ h ⁻¹	500 W Xe lamp as a light source
Bi ₄ O ₅ Br ₂ (ref. 312)	None	Ultra-thin nanosheets/bulk	2.64–3.05	Ultra-thin sheets are prepared by precursor method	CO	63.13 µmol g ⁻¹ of CO in 2 hours/27.56 µmol g ⁻¹ of CO in 2 hours	UV-visible light
A ₃ Bi ₂ I ₉ (Cs ₃ Bi ₂ I ₉) ²⁸⁴	None	Nanocrystals	2.2	Gas-phase reaction the photoreduction to carbon take place at the gas-solid interface, the reaction medium was CO ₂ and H ₂ O vapors	CH ₄ /CO	14.9 µmol g ⁻¹ of methane and 77.6 µmol g ⁻¹ of CO	32 W UV lamp ($\lambda = 305$ nm)
Cs ₂ AgBiBr ₆ (ref. 313)	None	Nanocrystals	1.72	Medium in which reaction is carried is ethyl acetate solvent	CH ₄ /CO	14.1 µmol g ⁻¹ of methane and 9.6 µmol g ⁻¹ of CO	100 W Xe lamp

move to the photocatalyst's surface, and at the conduction band, the dinitrogen is reduced to the ammonia by multi-step transfer of the electron and proton available from the water. The hole in the valence band oxidizes the water molecule and gives O₂. The chemisorption of the N₂ and H⁺ ions occurs on the surface of the conduction band accompanied by the association or dissociation by H₂ incorporation of N₂ molecules absorption and NH₃ formation. Lastly, desorption of NH₃ from the photocatalyst's surface after the ammonia formation occurs.^{85,319–321}

The nitrogen fixation in the presence of the photocatalyst takes place in two ways, either by the associative way or by the dissociative way. The breakage of the N≡N bond occurs in the dissociative pathway before adding the hydrogen atom as a reducing agent, which is impossible in an ambient environment.³²² In an associative pathway, breaking the N≡N bond is unnecessary, so nitrogen fixation is possible at ambient conditions. The nitrogen is adsorbed at the surface of the photocatalyst and then converted into the NH₃, which is then desorbed after the breakage of the N-N bond. In the associative pathway, the hydrogenation takes place with the sideway nitrogen, which is not directly attached to the surface of the photocatalyst, which generates the NH₃.^{323,324} The remaining

nitrogen attached photocatalyst's surface undergoes hydrogenation and generates NH₃. But this route is challenging because the chemisorption of nitrogen molecules on the surface of the catalyst is not easy; therefore, surface engineering is an important parameter to enhance the photocatalyst activity for nitrogen fixation.^{8,321,325} The yield and the efficiency of the reaction are given by the apparent quantum efficiency (AQE) and can be calculated as;³²⁶


$$\text{AQE} = \frac{6 \times \text{number of ammonia molecule evolved}}{\text{number of incident photons}} \times 100\%$$

Limited numbers of the perovskite materials are reported due to the less AQE and yield. The reported materials are SrTiO₃, KNbO₃, LaCoO₃, and layered double perovskite Bi₂WO₆.^{129,327–329} The efficiency of the perovskite material is less due to the selectivity of N₂ and adsorption of N₂ at the surface of the photocatalyst material; however, more research is needed in the field of photocatalytic nitrogen fixation to compete with the available industrial method of nitrogen fixation (Haber cycle).^{319,330} Some of the reported perovskite photocatalyst materials for nitrogen fixation are listed in Table 5.



Table 5 Perovskite materials in photocatalytic nitrogen fixation

Material	Band gap (eV)	NH ₃ concentration/generation rate	Light source	Reaction conditions
BaTiO ₃ (ref. 331)	3.2	0.09 mg h ⁻¹ L ⁻¹	UV-visible	Water as the proton source in the process of photocatalysis
Defective La ₂ TiO ₅ (R-LTO) ³³²	4.07	158.13 μmol g ⁻¹ h ⁻¹	Simulated sunlight	Defects at the surface of the LTO are introduced by NaBH ₄ reduction
CeO ₂ –BiFeO ₃ (ref. 320)	—	117.77 μmol g ⁻¹ h ⁻¹	UV-visible	Deionized water + nitrogen
LaCoO ₃ : Er ³⁺ /ATP ³²⁸	2.88–3.45	71.51 μmol g ⁻¹ h ⁻¹	Visible	Water + nitrogen and ethanol as a sacrificial layer
Ag/KNbO ₃ (0.5% Ag) ³³³	3.13	385.0 μmol g ⁻¹ h ⁻¹ L ⁻¹	Simulated sunlight	Ethanol as a sacrificial layer
NiS/KNbO ₃ (5% NiS) ¹²⁹	3.11	155.6 μmol g ⁻¹ h ⁻¹ L ⁻¹	Simulated sunlight	Ethanol is used as a hole scavenger
TiO ₂ /SrTiO ₃ /g-C ₃ N ₄ (ref. 125)	2.75–3.1	2192 μmol g ⁻¹ h ⁻¹ L ⁻¹	Simulated sunlight	Methanol + nitrogen and ethanol as a sacrificial layer
CaTiO ₃ (ref. 334)	3.49	236.12 μmol g ⁻¹ h ⁻¹	Natural sunlight irradiation	3D leaf-templated defective CaTiO ₃ is prepared by using NaBH ₄ + nitrogen environment

Fig. 15 Schematic representation of a double perovskite structure (B), derived starting from a perovskite structure (A).⁴⁹

Double perovskite and photocatalysis

Double perovskites can accommodate different cations at the A and B sites, forming $\text{AA}'\text{BB}'\text{O}_6$ (Fig. 15). Accommodation of other cations at the A and B sites can alter the double perovskite's photophysical properties to a great extent. Among the binary oxides, only a few double perovskites exhibit visible region bandgap because of their small bandgap, such as Fe_2O_3 , WO_6 , Bi_2O_3 , etc. However, for hydrogen evolution, these materials have deficient conduction band potential. Some materials also have low mobility of the photoexcited carriers and poor stability. Many binary oxides show efficient photocatalytic activity under UV irradiation because of their wide bandgap.

Complex compounds with a combination of 'narrow bandgap' and 'wide bandgap' materials can make use of properties of both types, and therefore, can be exploited as visible light photocatalysts.^{124,125}

The researchers have investigated photocatalytic activity of rare earth and bismuth-based double perovskites under visible light. Double perovskites $\text{Ba}_2\text{XB}_2\text{O}_6$ (X = Ce, La, Nd, Pr, Eu, Sm, Dy, Gd) were synthesized and degraded MB. Researchers reported that rare-earth cation-dependent compounds ($\text{Ba}_2\text{-SmBiO}_6$, $\text{Ba}_2\text{EuBiO}_6$, and $\text{Ba}_2\text{CeBiO}_6$) showed significant photocatalytic activity. $\text{CaCu}_3\text{Ti}_4\text{O}_{12}$ possessed an indirect bandgap of 1.27 eV, and Pt loaded $\text{CaCu}_3\text{Ti}_4\text{O}_{12}$ showed the degradation of MO under visible irradiation. Double perovskite



materials such as Sr_2CoWO_6 , Ba_2CoWO_6 , and Sr_2NiWO_6 , $\text{Ba}_2\text{-NiWO}_6$, are reported to be stable for O_2 evolution with sacrificial agents.^{124,125} Although the photophysical properties of certain double perovskites also have been investigated and reported, still a lot of efforts are required before utilizing these materials on an industrial scale.

Summary

In summary, the abundantly available sun energy can be harvested through photocatalysis to deal with the concerns pertaining to the environment and humankind. This article aimed to discuss the imperative properties of perovskite materials which play vital role in photocatalysis, and will assist in understanding the fundamentals of photocatalytic mechanisms involved in designing highly efficient photocatalysts. The three alteration sites (A, B, and O sites) of perovskite materials make them suitable for numerous applications, particularly photocatalysis. These sites help in tailoring chemical, physical, optical, and photocatalytic properties for desired photocatalytic reactions. The structural and compositional suppleness in perovskite photocatalyst strongly affects photo-generated carriers' mobility, separation, and recombination. The current article also describes the defect engineering in perovskite materials for enhanced photocatalytic performance. Recently, defect engineering gained much attention among researchers because it resulted in visible light photocatalytic activity without doping. Furthermore, surface defects provide reactive sites beneficial for a process like nitrogen fixation at ambient conditions. The review also provides an insight into the different applications of photocatalysis, including wastewater treatment, water splitting, CO_2 reduction, and nitrogen fixation. The critical perovskite materials for each photocatalytic application are also listed with their properties in this study. Overall, it can be inferred that although perovskite oxide-based materials have exhibited significant photocatalytic performance still, extensive challenges are ahead of their design, fabrication, cost, and efficiency for industrial and large-scale production. The biggest challenge in the industrialization of photocatalyst technology is the development of an ideal photocatalyst, which should possess four features, including high photocatalytic efficiency, a large specific surface area, full utilization of sunlight, and recyclability. Nonetheless, there is no doubt that perovskite-based oxide materials will be investigated more intensively in the coming years due to their exceptional properties and applications for a sustainable future.

Author contributions

All authors verify their contribution to the current review article as follows: design, study conception, and supervision of the whole article is done by Muneeb Irshad and Quar tul Ain; data collection is done by Asif Nadeem Tabish, Muhammad Usman, Masood ul Hassan Farooq, Mohammed A. Assiri, Muhammad Imran; analysis and interpretation of results by; Muneeb Irshad, Quar tul Ain, Muhammad Zaman, Muhammad Zeeshan Aslam, Naila Kousar, Muhammad Asim, Muhammad Rafique, and

Khurram Siraj; draft manuscript preparation and proofreading by; Muneeb Irshad, Quar tul Ain, and Muhammad Zaman. Moreover, Mohammed A. Assiri and Muhammad Imran provided the necessary funding to complete the article. All authors reviewed the results and approved the final version of the manuscript.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors, especially M. A. Assiri and M. Imran, express their appreciation to the Deanship of Scientific Research at King Khalid University, Saudi Arabia, through research groups program, under grant number R.G.P. 2/153/42.

References

- 1 A. R. Chaurasia, Population effects of the environment, in *Population and Sustainable Development in India*, Springer Singapore, Singapore, 2020, pp. 243–255.
- 2 Y. Li, *et al.*, Influence of Industrialization and Environmental Protection on Environmental Pollution: A Case Study of Taihu Lake, China, *Int. J. Environ. Res. Public Health*, 2018, **15**(12), 2628.
- 3 N. J. Waltham, *et al.*, UN Decade on Ecosystem Restoration 2021–2030—What Chance for Success in Restoring Coastal Ecosystems?, *Front. Mar. Sci.*, 2020, **7**(71), 1–5.
- 4 Y. Cui, B. A. Schubert and A. H. Jahren, A 23 m.y. record of low atmospheric CO_2 , *Geology*, 2020, **48**(9), 888–892.
- 5 L. Guppy, *et al.*, *Global-Water-Crisis-The-Facts*, 2017.
- 6 G. Nabi, *et al.*, The crisis of water shortage and pollution in Pakistan: risk to public health, biodiversity, and ecosystem, *Environ. Sci. Pollut. Res. Int.*, 2019, **26**(11), 10443–10445.
- 7 W. Wang, M. O. Tade and Z. Shao, Research progress of perovskite materials in photocatalysis- and photovoltaics-related energy conversion and environmental treatment, *Chem. Soc. Rev.*, 2015, **44**(15), 5371–5408.
- 8 A. Kumar, A. Kumar and V. Krishnan, Perovskite Oxide Based Materials for Energy and Environment-Oriented Photocatalysis, *ACS Catal.*, 2020, **10**(17), 10253–10315.
- 9 S. Zhu and D. Wang, Photocatalysis: Basic Principles, Diverse Forms of Implementations and Emerging Scientific Opportunities, *Adv. Energy Mater.*, 2017, **7**, 1700841.
- 10 P. Kanhere and Z. Chen, A review on visible light active perovskite-based photocatalysts, *Molecules*, 2014, **19**(12), 19995–20022.
- 11 X. Yang and D. Wang, Photocatalysis: From Fundamental Principles to Materials and Applications, *ACS Appl. Energy Mater.*, 2018, **1**(12), 6657–6693.
- 12 A. A. Yaqoob, *et al.*, Role of Nanomaterials in the Treatment of Wastewater: A Review, *Water*, 2020, **12**(2), 495.
- 13 J. Ran, M. Jaroniec and S. Z. Qiao, Cocatalysts in Semiconductor-based Photocatalytic CO_2 Reduction:



Achievements, Challenges, and Opportunities, *Adv. Mater.*, 2018, **30**, 1704649.

14 F. J. Beltran, *et al.*, Ozone and photocatalytic processes to remove the antibiotic sulfamethoxazole from water, *Water Res.*, 2008, **42**(14), 3799–3808.

15 M. M. Khan, S. F. Adil and A. Al-Mayouf, Metal oxides as photocatalysts, *J. Saudi Chem. Soc.*, 2015, **19**(5), 462–464.

16 S. Zeng, *et al.*, A review on photocatalytic CO₂ reduction using perovskite oxide nanomaterials, *Nanotechnology*, 2018, **29**(5), 052001.

17 T. Garcia, *et al.*, Vapor-Phase Photocatalytic Overall Water Splitting Using Hybrid Methylammonium Copper and Lead Perovskites, *Nanomaterials*, 2020, **10**(5), 960.

18 X. Xue, *et al.*, Efficient photocatalytic nitrogen fixation under ambient conditions enabled by the heterojunctions of n-type Bi₂MoO₆ and oxygen-vacancy-rich p-type BiOBr, *Nanoscale*, 2019, **11**(21), 10439–10445.

19 J. M. Coronado, A historical introduction to photocatalysis, in *Design of Advanced Photocatalytic Materials for Energy and Environmental Applications*, 2013, pp. 1–4.

20 A. Eibner, Action of light on pigments I, *Chem.-Ztg.*, 1911, **35**, 753–755.

21 K. Hashimoto, H. Irie and A. Fujishima, TiO₂ Photocatalysis: A Historical Overview and Future Prospects, *Jpn. J. Appl. Phys.*, 2005, **44**(12), 8269–8285.

22 Chapter 1 history of catalysis, in *Studies in Surface Science and Catalysis*, ed. J. A. Moulijn, P. W. N. M. van Leeuwen and R. A. van Santen, Elsevier, 1993, pp. 3–21.

23 A. Fujishima and K. Honda, Electrochemical Photolysis of Water at a Semiconductor Electrode, *Nature*, 1972, **238**(5358), 37–38.

24 M. B. Tahir, *et al.*, Nanomaterials for photocatalysis, in *Nanotechnology and Photocatalysis for Environmental Applications*, 2020, pp. 65–76.

25 S. Fatima, *et al.*, Congo Red Dye Degradation by Graphene Nanoplatelets/Doped Bismuth Ferrite Nanoparticle Hybrid Catalysts under Dark and Light Conditions, *Catalysts*, 2020, **10**(4), 367.

26 D. B. Mitzi, Introduction: Perovskites, *Chem. Rev.*, 2019, **119**(5), 3033–3035.

27 J. F. W. Bowles, Oxides, in *Encyclopedia of Geology*, ed. D. Alderton and S. A. Elias, Academic Press, Oxford, 2nd edn, 2021, pp. 428–441.

28 L. Ortega-San-Martin, Correction to: introduction to perovskites: a historical perspective, in *Revolution of Perovskite: Synthesis, Properties and Applications*, ed. N. S. Arul and V. D. Nithya, Springer Singapore, Singapore, 2020, p. C1.

29 E. A. Katz, Perovskite: Name Puzzle and German-Russian Odyssey of Discovery, *Helv. Chim. Acta*, 2020, **103**(6), 00061.

30 W.-J. Yin, *et al.*, Oxide perovskites, double perovskites and derivatives for electrocatalysis, photocatalysis, and photovoltaics, *Energy Environ. Sci.*, 2019, **12**(2), 442–462.

31 N. F. Atta, A. Galal and E. H. El-Ads, Perovskite nanomaterials – synthesis, characterization, and applications, in *Perovskite Materials – Synthesis, Characterisation, Properties, and Applications*, 2016.

32 A. S. Bhalla, R. Guo and R. Roy, The perovskite structure – a review of its role in ceramic science and technology, *Mater. Res. Innovations*, 2016, **4**(1), 3–26.

33 M. A. Peña and J. L. G. Fierro, Chemical Structures and Performance of Perovskite Oxides, *Chem. Rev.*, 2001, **101**(7), 1981–2018.

34 C. N. R. Rao, Perovskites, in *Encyclopedia of Physical Science and Technology*, ed. R. A. Meyers, Academic Press, New York, 3rd edn, 2003, pp. 707–714.

35 M. T. Sebastian, Chapter six – ABO₃ type perovskites, in *Dielectric Materials for Wireless Communication*, ed. M. T. Sebastian, Elsevier, Amsterdam, 2008, pp. 161–203.

36 R. Mouta, R. X. Silva and C. W. Paschoal, Tolerance factor for pyrochlores and related structures, *Acta Crystallogr., Sect. B: Struct. Sci., Cryst. Eng. Mater.*, 2013, **69**(Pt 5), 439–445.

37 V. Goldschmidt, Crystal structure and chemical correlation, *Ber. Dtsch. Chem. Ges.*, 1927, **60**, 1263–1296.

38 I. M. Reaney and R. Ubic, Dielectric and structural characteristics of perovskites and related materials as a function of tolerance factor, *Ferroelectrics*, 1999, **228**(1), 23–38.

39 R. S. Roth, Classification of Perovskite and Other ABO₃-Type, *J. Res. Natl. Bur. Stand.*, 1957, **58**(2), 75.

40 J. Attfield, Structure–property relations in doped perovskite oxides, *Int. J. Inorg. Mater.*, 2001, **3**(8), 1147–1152.

41 C. Li, K. C. K. Soh and P. Wu, Formability of ABO₃ perovskites, *J. Alloys Compd.*, 2004, **372**(1–2), 40–48.

42 M. Johnsson and P. Lemmens, Crystallography and chemistry of perovskites, 2005, arXiv preprint cond-mat/0506606.

43 T. K. Todorova, M. V. Ganduglia-Pirovano and J. Sauer, Vanadium Oxides on Aluminum Oxide Supports. 3. Metastable κ -Al₂O₃ (001) Compared to α -Al₂O₃ (0001), *J. Phys. Chem. C*, 2007, **111**(13), 5141–5153.

44 R. J. Tilley, *Perovskites: Structure-Property Relationships*, John Wiley & Sons, 2016.

45 E. A. R. Assirey, Perovskite synthesis, properties and their related biochemical and industrial application, *Saudi Pharm. J.*, 2019, **27**(6), 817–829.

46 L. Pan and G. Zhu, *Perovskite Materials: Synthesis, Characterisation, Properties, and Applications*, BoD–Books on Demand, 2016.

47 N. Solanki, P. D. Lodhi and N. Kaurav, Structural and Raman analysis of double perovskite La₂CoTi_{0.7}Ni_{0.3}O₆, *AIP Conf. Proc.*, 2019, **2100**, 020161.

48 M. T. Anderson, *et al.*, B-cation arrangements in double perovskites, *Prog. Solid State Chem.*, 1993, **22**(3), 197–233.

49 T. Saha-Dasgupta, Double perovskites with 3d and 4d/5d transition metals: compounds with promises, *Mater. Res. Express*, 2020, **7**, 014003.

50 G. King and P. M. Woodward, Cation ordering in perovskites, *J. Mater. Chem.*, 2010, **20**(28), 5785–5796.

51 S. Vasala and M. Karppinen, A₂B' B "O₆ perovskites: a review, *Prog. Solid State Chem.*, 2015, **43**(1–2), 1–36.

52 M. J. Winiarski and P. Dereń, Electronic structure of A₂B'B''O₆-type (A= Ca, Sr, Ba; B'= Mg, Zn; B''= Mo, W) double perovskite oxides, *Opt. Mater.*, 2019, **90**, 95–98.

53 P. Ksoll, *et al.*, B-Site Cation Ordering in Films, Superlattices, and Layer-by-Layer-Grown Double Perovskites, *Crystals*, 2021, **11**(7), 734.

54 J.-W. G. Bos and J. P. Attfield, Structural, Magnetic, and Transport Properties of (La_{1+x}Sr_{1-x})CoRuO₆ Double Perovskites, *Chem. Mater.*, 2004, **16**(9), 1822–1827.

55 D. Serrate, J. M. D. Teresa and M. R. Ibarra, Double perovskites with ferromagnetism above room temperature, *J. Phys.: Condens. Matter*, 2007, **19**, 023201.

56 X. Xu, Y. Zhong and Z. Shao, Double Perovskites in Catalysis, Electrocatalysis, and Photo(electro)catalysis, *Trends Chem.*, 2019, **1**(4), 410–424.

57 M. T. Sebastian, Chapter nine – cation-deficient perovskites, in *Dielectric Materials for Wireless Communication*, ed. M. T. Sebastian, Elsevier, Amsterdam, 2008, pp. 335–360.

58 W. Xiao, *et al.*, Cubic perovskite polymorph of strontium metasilicate at high pressures, *Am. Mineral.*, 2013, **98**(11–12), 2096–2104.

59 G. Burns and A. M. Glazer, Chapter 7 – space group applications, in *Space Groups for Solid State Scientists*, ed. G. Burns and A. M. Glazer, Academic Press, Oxford, 3rd edn, 2013, pp. 187–274.

60 Chapter 10 ABX₃, perovskite-ilmenite structure, in *Developments in Geochemistry*, ed. S. Mitra, Elsevier, 2004, pp. 711–792.

61 B. Kurniawan, *et al.*, Effect of Temperature and Duration of Sintering on Perovskite Material (La_{1-x}Ag_x)_{0.8}Ca_{0.2}MnO₃, *IOP Conf. Ser.: Mater. Sci. Eng.*, 2018, **367**, 012055.

62 P. Woodward, Octahedral Tilting in Perovskites. II. Structure Stabilizing Forces, *Acta Crystallogr., Sect. B: Struct. Sci.*, 1997, **53**(1), 44–66.

63 J. S. Bechtel and A. Van der Ven, Octahedral tilting instabilities in inorganic halide perovskites, *Phys. Rev. Mater.*, 2018, **2**(2), 025401.

64 S. Mukherjee, *et al.*, Structure and Electronic Effects from Mn and Nb Co-doping for Low Band Gap BaTiO₃ Ferroelectrics, *J. Phys. Chem. C*, 2021, **125**(27), 14910–14923.

65 L. Fu, *et al.*, Magnetic, electronic, and optical properties of perovskite materials, in *Revolution of Perovskite: Synthesis, Properties and Applications*, ed. N. S. Arul and V. D. Nithya, Springer Singapore, Singapore, 2020, pp. 43–59.

66 Y. Du, *et al.*, Strain accommodation by facile WO₆ octahedral distortion and tilting during WO₃ heteroepitaxy on SrTiO₃(001), *ACS Appl. Mater. Interfaces*, 2014, **6**(16), 14253–14258.

67 M. Madi, M. Tahir and S. Tasleem, Advances in Structural Modification of Perovskite Semiconductors for Visible Light Assisted Photocatalytic CO₂ Reduction to Renewable Solar Fuels: A Review, *J. Environ. Chem. Eng.*, 2021, **9**(11), 106264.

68 S. Khalfin and Y. Bekenstein, Advances in lead-free double perovskite nanocrystals, engineering band-gaps and enhancing stability through composition tunability, *Nanoscale*, 2019, **11**(18), 8665–8679.

69 R. Alagheband, *et al.*, Synthesis and Evaluation of ABO₃ Perovskites (A=La and B=Mn, Co) with Stoichiometric and Over-stoichiometric Ratios of B/A for Catalytic Oxidation of Trichloroethylene, *Bull. Chem. React. Eng. Catal.*, 2018, **13**(1), 47–56.

70 S. Krishnamurthy, *et al.*, Organic-inorganic hybrid and inorganic halide perovskites: structural and chemical engineering, interfaces and optoelectronic properties, *J. Phys. D: Appl. Phys.*, 2021, **54**(13), 133002.

71 Y. Zhou, *et al.*, Metal-Doped Lead Halide Perovskites: Synthesis, Properties, and Optoelectronic Applications, *Chem. Mater.*, 2018, **30**(19), 6589–6613.

72 K. S. Schanze, *et al.*, Progress in Perovskite Photocatalysis, *ACS Energy Lett.*, 2020, **5**(8), 2602–2604.

73 S. Mazumdar, Y. Zhao and X. Zhang, Stability of Perovskite Solar Cells: Degradation Mechanisms and Remedies, *Frontiers in Electronics*, 2021, **2**, 712785.

74 N. Labhsetwar, *et al.*, Perovskite-type catalytic materials for environmental applications, *Sci. Technol. Adv. Mater.*, 2015, **16**(3), 036002.

75 B.-M. Bresolin, Y. Park and D. W. Bahnemann, Recent Progresses on Metal Halide Perovskite-Based Material as Potential Photocatalyst, *Catalysts*, 2020, **10**(6), 709.

76 H. Anwer, *et al.*, Photocatalysts for degradation of dyes in industrial effluents: Opportunities and challenges, *Nano Res.*, 2019, **12**(5), 955–972.

77 R. Li, Photocatalytic nitrogen fixation: An attractive approach for artificial photocatalysis, *Chin. J. Catal.*, 2018, **39**(7), 1180–1188.

78 K. Iizuka, *et al.*, Photocatalytic reduction of carbon dioxide over Ag cocatalyst-loaded ALA₄Ti₄O₁₅ (A = Ca, Sr, and Ba) using water as a reducing reagent, *J. Am. Chem. Soc.*, 2011, **133**(51), 20863–20868.

79 D. Xu, *et al.*, Heterojunction composites of g-C₃N₄/KNbO₃ enhanced photocatalytic properties for water splitting, *Int. J. Hydrogen Energy*, 2018, **43**(34), 16566–16572.

80 R. Molinari, C. Lavorato and P. Argurio, Visible-Light Photocatalysts and Their Perspectives for Building Photocatalytic Membrane Reactors for Various Liquid Phase Chemical Conversions, *Catalysts*, 2020, **10**(11), 1334.

81 M. Mishra and D.-M. Chun, α -Fe₂O₃ as a photocatalytic material: A review, *Appl. Catal., A*, 2015, **498**, 126–141.

82 O. V. Nkwachukwu and O. A. Arotiba, Perovskite Oxide-Based Materials for Photocatalytic and Photoelectrocatalytic Treatment of Water, *Front. Chem.*, 2021, **9**, 634630.

83 C.-H. Lu, *et al.*, Doping and ion substitution in colloidal metal halide perovskite nanocrystals, *Chem. Soc. Rev.*, 2020, **49**(14), 4953–5007.

84 Z. Guo, *et al.*, Band gap engineering in huge-gap semiconductor SrZrO₃ for visible-light photocatalysis, *Int. J. Hydrogen Energy*, 2014, **39**(5), 2042–2048.

85 R. Shi, *et al.*, Defect engineering in photocatalytic nitrogen fixation, *ACS Catal.*, 2019, **9**(11), 9739–9750.





86 S. Suzuki, A. Iwase and A. Kudo, Long wavelength visible light-responsive SrTiO_3 photocatalysts doped with valence-controlled Ru for sacrificial H_2 and O_2 evolution, *Catal. Sci. Technol.*, 2020, **10**(15), 4912–4916.

87 Y. Li, *et al.*, A two-step synthesis of NaTaO_3 microspheres for photocatalytic water splitting, *Int. J. Hydrogen Energy*, 2014, **39**(25), 13481–13485.

88 L. Ernawati, *et al.*, Experimental data of CaTiO_3 photocatalyst for degradation of organic pollutants (Brilliant green dye) – Green synthesis, characterization and kinetic study, *Data Brief*, 2020, **32**, 106099.

89 S. Sharma and M. Kumar, Band gap tuning and optical properties of BiFeO_3 nanoparticles, *Mater. Today: Proc.*, 2020, **28**, 168–171.

90 M. Ismael and M. Wark, Perovskite-type LaFeO_3 : Photoelectrochemical Properties and Photocatalytic Degradation of Organic Pollutants Under Visible Light Irradiation, *Catalysts*, 2019, **9**(4), 342.

91 Q. Liu, *et al.*, Highly efficient Pt/NaNbO_3 nanowire photocatalyst: Its morphology effect and application in water purification and H_2 production, *Appl. Catal., B*, 2017, **205**, 505–513.

92 T. Jia, *et al.*, First-principles study on the electronic, optical and thermodynamic properties of ABO_3 ($\text{A} = \text{La}, \text{Sr}$, $\text{B} = \text{Fe}, \text{Co}$) perovskites, *RSC Adv.*, 2017, **7**(62), 38798–38804.

93 C. Huang, *et al.*, Synthesis and application of Bi_2WO_6 for the photocatalytic degradation of two typical fluoroquinolones under visible light irradiation, *RSC Adv.*, 2019, **9**(48), 27768–27779.

94 D. Arney, *et al.*, New molten-salt synthesis and photocatalytic properties of $\text{La}_2\text{Ti}_2\text{O}_7$ particles, *J. Photochem. Photobiol., A*, 2008, **199**(2–3), 230–235.

95 P. Li, H. Abe and J. Ye, Band-Gap Engineering of NaNbO_3 for Photocatalytic H_2 Evolution with Visible Light, *Int. J. Photoenergy*, 2014, **2014**, 1–6.

96 A. Suzuki and T. Oku, Effects of transition metals incorporated into perovskite crystals on the electronic structures and magnetic properties by first-principles calculation, *Heliyon*, 2018, **4**(8), e00755.

97 J. Yu, *et al.*, Giant enhancement of photocatalytic H_2 production over KNbO_3 photocatalyst obtained via carbon doping and MoS_2 decoration, *Int. J. Hydrogen Energy*, 2018, **43**(9), 4347–4354.

98 A. Haruna, I. Abdulkadir and S. O. Idris, Photocatalytic activity and doping effects of BiFeO_3 nanoparticles in model organic dyes, *Heliyon*, 2020, **6**(1), e03237.

99 N. D. Phu, *et al.*, Photocatalytic activity enhancement of Bi_2WO_6 nanoparticles by Ag doping and Ag nanoparticles modification, *J. Alloys Compd.*, 2020, **824**, 153914.

100 A. Kumar, *et al.*, Three-Dimensional Carbonaceous Aerogels Embedded with Rh- SrTiO_3 for Enhanced Hydrogen Evolution Triggered by Efficient Charge Transfer and Light Absorption, *ACS Appl. Energy Mater.*, 2020, **3**(12), 12134–12147.

101 T. S. Jamil, *et al.*, The synthesis of nano-sized undoped, Bi doped and Bi, Cu co-doped SrTiO_3 using two sol-gel methods to enhance the photocatalytic performance for the degradation of dibutyl phthalate under visible light, *C. R. Chim.*, 2017, **20**(2), 97–106.

102 B. G. Anitha and L. G. Devi, Study of reaction dynamics of photocatalytic degradation of 4-chlorophenol using SrTiO_3 , sulfur doped SrTiO_3 , silver metallized SrTiO_3 and silver metallized sulfur doped SrTiO_3 catalysts: Detailed analysis of kinetic results, *J. Photochem. Photobiol., A*, 2019, **16**, 50–58.

103 H. Bentour, M. Boujnah, M. Houmad and M. Yadari, DFT Study of Se and Te Doped SrTiO_3 for Enhanced Visible-Light Driven Photocatalytic Hydrogen Production, *Opt. Quantum Electron.*, 2021, **53**, 589.

104 S. Shahajan, *et al.*, Optimization and detailed stability study on Pb doped ceria nanocubes for enhanced photodegradation of several anionic and cationic organic pollutants, *Arabian J. Chem.*, 2020, **13**(1), 1309–1322.

105 H. Wang, *et al.*, Synthesis and application of perovskite-based photocatalysts in environmental remediation: A review, *J. Mol. Liq.*, 2021, **334**, 116029.

106 L. Zhang, *et al.*, Kinetics and mechanisms of charge transfer processes in photocatalytic systems: A review, *J. Photochem. Photobiol., C*, 2012, **13**(4), 263–276.

107 R. Qian, *et al.*, Charge carrier trapping, recombination and transfer during TiO_2 photocatalysis: An overview, *Catal. Today*, 2019, **335**, 78–90.

108 A. Bumajdad and M. Madkour, Understanding the superior photocatalytic activity of noble metals modified titania under UV and visible light irradiation, *Phys. Chem. Chem. Phys.*, 2014, **16**(16), 7146–7158.

109 S. Natarajan, H. C. Bajaj and R. J. Tayade, Recent advances based on the synergistic effect of adsorption for removal of dyes from waste water using photocatalytic process, *J. Environ. Sci.*, 2018, **65**, 201–222.

110 J. Liang, *et al.*, Recent progress and development in inorganic halide perovskite quantum dots for photoelectrochemical applications, *Small*, 2020, **16**(15), 1903398.

111 M. Adly, S. M. El-Dafrawy and S. El-Hakam, Application of nanostructured graphene oxide/titanium dioxide composites for photocatalytic degradation of rhodamine B and acid green 25 dyes, *J. Mater. Res. Technol.*, 2019, **8**(6), 5610–5622.

112 K. Takanabe, Photocatalytic Water Splitting: Quantitative Approaches toward Photocatalyst by Design, *ACS Catal.*, 2017, **7**(11), 8006–8022.

113 L. M. Peter, Chapter 1 photoelectrochemistry: from basic principles to photocatalysis, in *Photocatalysis: Fundamentals and Perspectives*, The Royal Society of Chemistry, 2016, pp. 1–28.

114 W. Leng, *et al.*, Electron Diffusion Length in Mesoporous Nanocrystalline TiO_2 Photoelectrodes during Water Oxidation, *J. Phys. Chem. Lett.*, 2010, **1**(6), 967–972.

115 J. Li and N. Wu, Semiconductor-based photocatalysts and photoelectrochemical cells for solar fuel generation: a review, *Catal. Sci. Technol.*, 2015, **5**(3), 1360–1384.

116 F. M. Pesci, *et al.*, Efficient Suppression of Electron–Hole Recombination in Oxygen-Deficient Hydrogen-Treated

TiO₂ Nanowires for Photoelectrochemical Water Splitting, *J. Phys. Chem. C*, 2013, **117**(48), 25837–25844.

117 W. Wang, M. O. Tadé and Z. Shao, Research progress of perovskite materials in photocatalysis- and photovoltaics-related energy conversion and environmental treatment, *Chem. Soc. Rev.*, 2015, **44**(15), 5371–5408.

118 A. Gnanaprakasam, V. M. Sivakumar and M. Thirumurugan, Influencing Parameters in the Photocatalytic Degradation of Organic Effluent via Nanometal Oxide Catalyst: A Review, *Indian Journal of Materials Science*, 2015, **2015**, 1–16.

119 M. Antonopoulou, *et al.*, An overview of homogeneous and heterogeneous photocatalysis applications for the removal of pharmaceutical compounds from real or synthetic hospital wastewaters under lab or pilot scale, *Sci. Total Environ.*, 2021, **765**, 144163.

120 V. Kitsiou, *et al.*, Heterogeneous and homogeneous photocatalytic degradation of the insecticide imidacloprid in aqueous solutions, *Appl. Catal., B*, 2009, **86**(1–2), 27–35.

121 E. Pelizzetti and N. Serpone, *Homogeneous and Heterogeneous Photocatalysis*, Springer Science & Business Media, 2012, vol. 174.

122 K. Li, B. Peng and T. Peng, Recent Advances in Heterogeneous Photocatalytic CO₂ Conversion to Solar Fuels, *ACS Catal.*, 2016, **6**(11), 7485–7527.

123 X. Y. Kong, *et al.*, Effective steering of charge flow through synergistic inducing oxygen vacancy defects and p–n heterojunctions in 2D/2D surface-engineered Bi₂WO₆/BiOI cascade: Towards superior photocatalytic CO₂ reduction activity, *Chem. Eng. J.*, 2019, **372**, 1183–1193.

124 A. Kumar, *et al.*, Perovskite-structured CaTiO₃ coupled with g-C₃N₄ as a heterojunction photocatalyst for organic pollutant degradation, *Beilstein J. Nanotechnol.*, 2018, **9**, 671–685.

125 R. Tao, *et al.*, TiO₂/SrTiO₃/g-C₃N₄ ternary heterojunction nanofibers: gradient energy band, cascade charge transfer, enhanced photocatalytic hydrogen evolution, and nitrogen fixation, *Nanoscale*, 2020, **12**(15), 8320–8329.

126 H. Wang, *et al.*, Semiconductor heterojunction photocatalysts: design, construction, and photocatalytic performances, *Chem. Soc. Rev.*, 2014, **43**(15), 5234–5244.

127 S. N. Ahmed and W. Haider, Heterogeneous photocatalysis and its potential applications in water and wastewater treatment: a review, *Nanotechnology*, 2018, **29**(34), 342001.

128 Z. Zhang, *et al.*, Review on constructed strategies of heterojunctional nanocomposites as efficient visible-light catalysts by modulating excited electrons with appropriate thermodynamic energy, *J. Mater. Chem. A*, 2019, **7**, 10879–10897.

129 W. Zhang, *et al.*, Facile preparation of novel nickel sulfide modified KNbO₃ heterojunction composite and its enhanced performance in photocatalytic nitrogen fixation, *J. Colloid Interface Sci.*, 2021, **590**, 548–560.

130 J. Low, *et al.*, Heterojunction Photocatalysts, *Adv. Mater.*, 2017, **29**, 01694.

131 H. Cai, *et al.*, Orienting the charge transfer path of type-II heterojunction for photocatalytic hydrogen evolution, *Appl. Catal., B*, 2019, **256**, 117853.

132 X. Zhang, *et al.*, NiSe₂/Cd0.5Zn0.5S as a type-II heterojunction photocatalyst for enhanced photocatalytic hydrogen evolution, *Int. J. Hydrogen Energy*, 2021, **46**(29), 15389–15397.

133 Z. Jiang, *et al.*, Two dimensional Z-scheme AgCl/Ag/CaTiO₃ nano-heterojunctions for photocatalytic hydrogen production enhancement, *Appl. Surf. Sci.*, 2018, **436**, 519–526.

134 Y. Chang, *et al.*, Z-Scheme Pt@CdS/3DOM-SrTiO₃ composite with enhanced photocatalytic hydrogen evolution from water splitting, *Catal. Today*, 2019, **327**, 315–322.

135 Z. Jin, *et al.*, One-step impregnation method to prepare direct Z-scheme LaCoO₃/g-C₃N₄ heterojunction photocatalysts for phenol degradation under visible light, *Appl. Surf. Sci.*, 2019, **491**, 432–442.

136 X. Wang, *et al.*, Synthesis of p–n heterojunction Ag₃PO₄/NaTaO₃ composite photocatalyst for enhanced visible-light-driven photocatalytic performance, *Mater. Lett.*, 2019, **251**, 192–195.

137 J. Ge, *et al.*, Advanced Design and Synthesis of Composite Photocatalysts for the Remediation of Wastewater: A Review, *Catalysts*, 2019, **9**(2), 122.

138 L. Zhang and M. Jaroniec, Toward designing semiconductor-semiconductor heterojunctions for photocatalytic applications, *Appl. Surf. Sci.*, 2018, **430**, 2–17.

139 H. Chen, *et al.*, Structuring a TiO₂-based photonic crystal photocatalyst with Schottky junction for efficient photocatalysis, *Environ. Sci. Technol.*, 2010, **44**(1), 451–455.

140 J. S. Jang, H. G. Kim and J. S. Lee, Heterojunction semiconductors: A strategy to develop efficient photocatalytic materials for visible light water splitting, *Catal. Today*, 2012, **185**(1), 270–277.

141 A. Murali, *et al.*, Synergetic effect of surface plasmon resonance and schottky junction in Ag–AgX–ZnO–rGO (X=Cl & Br) nanocomposite for enhanced visible-light driven photocatalysis, *Colloids Surf., A*, 2020, **595**, 124684.

142 Y. S. Fu, J. Li and J. Li, Metal/Semiconductor Nanocomposites for Photocatalysis: Fundamentals, Structures, Applications and Properties, *Nanomaterials*, 2019, **9**(3), 359.

143 S. Bai, *et al.*, Defect engineering in photocatalytic materials, *Nano Energy*, 2018, **53**, 296–336.

144 W. Zhou and H. Fu, Defect-mediated electron–hole separation in semiconductor photocatalysis, *Inorg. Chem. Front.*, 2018, **5**(6), 1240–1254.

145 A. Kumar and V. Krishnan, Vacancy Engineering in Semiconductor Photocatalysts: Implications in Hydrogen Evolution and Nitrogen Fixation Applications, *Adv. Funct. Mater.*, 2021, **31**(28), 2009807.

146 H. Arandian, *et al.*, Defect engineering of oxide perovskites for catalysis and energy storage: synthesis of chemistry and materials science, *Chem. Soc. Rev.*, 2021, **50**, 10116–10211.



147 Y. Sun, *et al.*, Defect engineering in perovskite oxide thin films, *Chem. Commun.*, 2021, **57**(68), 8402–8420.

148 Q. Ji, *et al.*, The role of oxygen vacancies of ABO₃ perovskite oxides in the oxygen reduction reaction, *Energy Environ. Sci.*, 2020, **13**(5), 1408–1428.

149 Q. Shen, *et al.*, A Review on the Catalytic Decomposition of NO by Perovskite-Type Oxides, *Catalysts*, 2021, **11**(5), 622.

150 H. L. Tan, F. F. Abdi and Y. H. Ng, Heterogeneous photocatalysts: an overview of classic and modern approaches for optical, electronic, and charge dynamics evaluation, *Chem. Soc. Rev.*, 2019, **48**(5), 1255–1271.

151 T. Shi, *et al.*, Recyclable Perovskite as Heterogeneous Photocatalyst for Aminomethylation of Imidazo-Fused Heterocycles, *Adv. Synth. Catal.*, 2020, **362**(11), 2143–2149.

152 A. Kumar, *et al.*, Recyclable, bifunctional composites of perovskite type N-CaTiO₃ and reduced graphene oxide as an efficient adsorptive photocatalyst for environmental remediation, *Mater. Chem. Front.*, 2017, **1**(11), 2391–2404.

153 J. J. Rueda-Marquez, *et al.*, A critical review on application of photocatalysis for toxicity reduction of real wastewaters, *J. Cleaner Prod.*, 2020, **258**(4), 120694.

154 M. F. Hossain, Water, in *Sustainable Design and Build*, 2019, pp. 301–418.

155 M. L. Sikosana, *et al.*, Municipal wastewater treatment technologies: A review, *Procedia Manuf.*, 2019, **35**, 1018–1024.

156 H. Xiao, *et al.*, Industrial disposal processes for treatment of polychlorinated dibenzo-p-dioxins and dibenzofurans in municipal solid waste incineration fly ash, *Chemosphere*, 2020, **243**, 125351.

157 N. N. Yunus, *et al.*, Effect of Catalyst Loading on Photocatalytic Degradation of Phenol by Using N, S Codoped TiO₂, *IOP Conf. Ser.: Mater. Sci. Eng.*, 2017, **206**, 012092.

158 S. Singh, *et al.*, Ti doped BaMnO₃ perovskite structure as photocatalytic agent for the degradation of noxious air and water pollutants, *SN Appl. Sci.*, 2020, (2), 310.

159 K. Khan, *et al.*, Recent Progress, Challenges, and Prospects in Two-Dimensional Photo-Catalyst Materials and Environmental Remediation, *Nano-Micro Lett.*, 2020, **12**(1), 167.

160 A. Kumar, A Review on the Factors Affecting the Photocatalytic Degradation of Hazardous Materials, *Material Science & Engineering International Journal*, 2017, **1**(3), 106–114.

161 S. Em, *et al.*, Sn-Doped Hematite Nanoparticles for Potential Photocatalytic Dye Degradation, *IOP Conf. Ser.: Mater. Sci. Eng.*, 2020, **739**(1), 012042.

162 M. Tsvetkov, J. Zaharieva and M. Milanova, Ferrites, modified with silver nanoparticles, for photocatalytic degradation of malachite green in aqueous solutions, *Catal. Today*, 2020, **357**, 453–459.

163 W. Zhang, *et al.*, Photocatalytic Performance of SiO₂/CNOs/TiO₂ to Accelerate the Degradation of Rhodamine B under Visible Light, *Nanomaterials*, 2019, **9**(12), 1671.

164 K. A. Huynh, *et al.*, Halide perovskite photocatalysis: progress and perspectives, *J. Chem. Technol. Biotechnol.*, 2020, 6342.

165 J. Kong, *et al.*, Perovskite-based photocatalysts for organic contaminants removal: Current status and future perspectives, *Catal. Today*, 2019, **327**, 47–63.

166 A. M. Ferrari, *et al.*, CaTiO₃ Perovskite in the Photocatalysis of Textile Wastewater, *Rev. Ambient. Água*, 2019, **14**(3), 2336.

167 J. Cai, *et al.*, Understanding oxygen vacancies in disorder-engineered surface and subsurface of CaTiO₃ nanosheets on photocatalytic hydrogen evolution, *Appl. Catal., B*, 2020, **267**, 118378.

168 Y. Yan, *et al.*, A Hydrothermal Route to the Synthesis of CaTiO₃ Nanocuboids Using P25 as the Titanium Source, *J. Electron. Mater.*, 2018, **47**(5), 3045–3050.

169 H. Yang, C. Han and X. Xue, Photocatalytic activity of Fe-doped CaTiO(3) under UV-visible light, *J. Environ. Sci.*, 2014, **26**(7), 1489–1495.

170 S. Kappadan, *et al.*, Tetragonal BaTiO₃ nanoparticles: An efficient photocatalyst for the degradation of organic pollutants, *Mater. Sci. Semicond. Process.*, 2016, **51**, 42–47.

171 P. Mehdizadeh, *et al.*, Effective removal of organic pollution by using sonochemical prepared LaFeO₃ perovskite under visible light, *Ultrason. Sonochem.*, 2020, **61**, 104848.

172 S. Irfan, *et al.*, Critical review: Bismuth ferrite as an emerging visible light active nanostructured photocatalyst, *J. Mater. Res. Technol.*, 2019, **8**(6), 6375–6389.

173 T. Gao, *et al.*, Synthesis of BiFeO₃ nanoparticles for the visible-light induced photocatalytic property, *Mater. Res. Bull.*, 2014, **59**, 6–12.

174 S. R. Khan, *et al.*, A Versatile Material: Perovskite Bismuth Ferrite Microparticles as a Potential Catalyst for Enhancing Fuel Efficiency and Degradation of Various Organic Dyes, *J. Inorg. Organomet. Polym. Mater.*, 2020, **30**(9), 3761–3770.

175 S. Chang, Y. Sang and H. Liu, Efficient Photocatalytic Degradation of RhB by Constructing Sn₃O₄ Nanoflakes on Sulfur-Doped NaTaO₃ Nanocubes, *Crystals*, 2021, **11**(1), 59.

176 D.-R. Liu, Y.-S. Jiang and G.-M. Gao, Photocatalytic degradation of an azo dye using N-doped NaTaO₃ synthesized by one-step hydrothermal process, *Chemosphere*, 2011, **83**(11), 1546–1552.

177 L. Ernawati, *et al.*, Experimental data of CaTiO₃ photocatalyst for degradation of organic pollutants (Brilliant green dye) – Green synthesis, characterization and kinetic study, *Data Brief*, 2020, **32**, 106099.

178 Y. Yan, *et al.*, Enhanced photocatalytic activity of surface disorder-engineered CaTiO₃, *Mater. Res. Bull.*, 2018, **105**, 286–290.

179 C.-W. Chang and C. Hu, Graphene oxide-derived carbon-doped SrTiO₃ for highly efficient photocatalytic degradation of organic pollutants under visible light irradiation, *Chem. Eng. J.*, 2020, **383**, 123116.

180 T. Ohno, *et al.*, Preparation of S, C cation-codoped SrTiO₃ and its photocatalytic activity under visible light, *Appl. Catal., A*, 2005, **288**(1–2), 74–79.



181 Q. I. Rahman, *et al.*, Efficient degradation of Methylene Blue dye over highly reactive Cu doped strontium titanate (SrTiO₃) nanoparticles photocatalyst under visible light, *J. Nanosci. Nanotechnol.*, 2012, **12**(9), 7181–7186.

182 M. Abdi, V. Mahdikhah and S. Sheibani, Visible light photocatalytic performance of La-Fe co-doped SrTiO₃ perovskite powder, *Opt. Mater.*, 2020, **102**, 109803.

183 G. Wu, *et al.*, Hydrothermal synthesis and visible-light-driven photocatalytic degradation for tetracycline of Mn-doped SrTiO₃ nanocubes, *Appl. Surf. Sci.*, 2015, **333**, 39–47.

184 D. R. Liu, Y. S. Jiang and G. M. Gao, Photocatalytic degradation of an azo dye using N-doped NaTaO₃ synthesized by one-step hydrothermal process, *Chemosphere*, 2011, **83**(11), 1546–1552.

185 X. Zhang, *et al.*, Enhanced visible-light-driven photocatalytic performance of Ag/AgGaO₂ metal semiconductor heterostructures, *J. Alloys Compd.*, 2017, **701**, 16–22.

186 P. Tang, *et al.*, Microwave-assisted synthesis of nanoparticulate perovskite LaFeO₃ as a high active visible-light photocatalyst, *Curr. Appl. Phys.*, 2013, **13**(2), 340–343.

187 E. Jiang, *et al.*, Construction of a Z-scheme MoS₂/CaTiO₃ heterostructure by the morphology-controlled strategy towards enhancing photocatalytic activity, *Chem. Eng. J.*, 2020, **399**, 125721.

188 X. Wang, *et al.*, Synthesis of p-n heterojunction Ag₃PO₄/NaTaO₃ composite photocatalyst for enhanced visible-light-driven photocatalytic performance, *Mater. Lett.*, 2019, **251**(15), 192–195.

189 X. Lu, *et al.*, Fabrication of a novel BiOI/KTaO₃ p-n heterostructure with enhanced photocatalytic performance under visible-light irradiation, *RSC Adv.*, 2020, **10**(18), 10921–10931.

190 T. Soltani, A. Tayyebi and B.-K. Lee, BiFeO₃/BiVO₄ p-n heterojunction for efficient and stable photocatalytic and photoelectrochemical water splitting under visible-light irradiation, *Catal. Today*, 2020, **340**, 188–196.

191 J. Xu, *et al.*, Fabrication of In₂S₃/NaTaO₃ composites for enhancing the photocatalytic activity toward the degradation of tetracycline, *New J. Chem.*, 2018, **42**(7), 5052–5058.

192 J. Luo, *et al.*, Rational design of Z-scheme LaFeO₃/SnS₂ hybrid with boosted visible light photocatalytic activity towards tetracycline degradation, *Sep. Purif. Technol.*, 2019, **210**, 417–430.

193 T. Zhang, *et al.*, Organic Pollutant Photodecomposition by Ag/KNbO₃ Nanocomposites: A Combined Experimental and Theoretical Study, *J. Phys. Chem. C*, 2016, **120**(5), 2777–2786.

194 L. G. Betancourt-Cantera, *et al.*, Structural transitions and multiferroic properties of high Ni-doped BiFeO₃, *J. Magn. Magn. Mater.*, 2018, **456**, 381–389.

195 Y. Li, *et al.*, Sol-gel combustion synthesis and visible-light-driven photocatalytic property of perovskite LaNiO₃, *J. Alloys Compd.*, 2010, **491**(1), 560–564.

196 X.-T. Wang, *et al.*, Design and fabrication of NiS/LaFeO₃ heterostructures for high efficient photodegradation of organic dyes, *Appl. Surf. Sci.*, 2020, **504**, 144363.

197 Z. Fu, S. Zhang and Z. Fu, Hydrothermal preparation of NaTaO₃/rGO composite photocatalyst to enhance UV photocatalytic activity, *Results Phys.*, 2019, **15**, 102669.

198 V. Jayaraman, *et al.*, Synergistic effect of band edge potentials on BiFeO₃/V₂O₅ composite: Enhanced photo catalytic activity, *J. Environ. Manage.*, 2019, **247**, 104–114.

199 B. Safizade, *et al.*, Photocatalytic activity of BiFeO₃/ZnFe₂O₄ nanocomposites under visible light irradiation, *RSC Adv.*, 2018, **8**, 6988–6995.

200 Y. Yuan, *et al.*, Synthesis and photocatalytic characterization of a new photocatalyst BaZrO₃, *Int. J. Hydrogen Energy*, 2008, **33**(21), 5941–5946.

201 S. Yuan, *et al.*, Investigation of photocatalytic performance of CuS/Bi₂WO₆ and degradation pathway of RhB in water, *Journal of Water Supply: Research and Technology-Aqua*, 2020, **69**(2), 145–159.

202 M. Shang, *et al.*, Bi₂WO₆ Nanocrystals with High Photocatalytic Activities under Visible Light, *J. Phys. Chem. C*, 2008, **112**(28), 10407–10411.

203 X. Zhang, M. Zhang and K. Cao, Hydrothermal synthesis of Sm-doped Bi₂WO₆ flower-like microspheres for photocatalytic degradation of rhodamine B, *CrystEngComm*, 2019, **21**(41), 6208–6218.

204 J. Cheng, *et al.*, Flower-like Bi₂WO₆/ZnO composite with excellent photocatalytic capability under visible light irradiation, *Chin. J. Catal.*, 2018, **39**(4), 810–820.

205 L. Zhang, *et al.*, Controllable synthesis of Bi₂MoO₆ and effect of morphology and variation in local structure on photocatalytic activities, *Appl. Catal., B*, 2010, **98**(3), 138–146.

206 T. Zhang, *et al.*, Facial Synthesis and Photoreaction Mechanism of BiFeO₃/Bi₂Fe₄O₉ Heterojunction Nanofibers, *ACS Sustainable Chem. Eng.*, 2017, **5**(6), 4630–4636.

207 L. Zhang, *et al.*, AgBr-Ag-Bi₂WO₆ nanojunction system: A novel and efficient photocatalyst with double visible-light active components, *Appl. Catal., A*, 2009, **363**(1), 221–229.

208 Y. Liu, *et al.*, In situ assembly of CQDs/Bi₂WO₆ for highly efficient photocatalytic degradation of VOCs under visible light, *New J. Chem.*, 2020, **44**(8), 3455–3462.

209 L. Ge, C. Han and J. Liu, Novel visible light-induced g-C₃N₄/Bi₂WO₆ composite photocatalysts for efficient degradation of methyl orange, *Appl. Catal., B*, 2011, **108–109**, 100–107.

210 S. Dong, *et al.*, Self-assembled hollow sphere shaped Bi₂WO₆/RGO composites for efficient sunlight-driven photocatalytic degradation of organic pollutants, *Chem. Eng. J.*, 2017, **316**, 778–789.

211 S. Boumaza, *et al.*, Photoelectrochemical study of La₂NiO₄ synthesized using citrate sol gel method—application for hydrogen photo-production, *J. Solid State Electrochem.*, 2020, **24**(2), 329–337.

212 N. Karamat, *et al.*, Synthesis, characterization and photocatalytic activity of LaNdZr₂O₇ supported SnSe



nanocomposites for the degradation of Foron blue dye, *Appl. Surf. Sci.*, 2019, **463**, 1019–1027.

213 Y. Zhang, *et al.*, Hydrothermal synthesis of Bi₂O₄/NaBiO₃ heterostructures with enhanced visible light photocatalytic properties, *J. Phys. Chem. Solids*, 2021, **149**, 109766.

214 S. Tasleem and M. Tahir, Recent progress in structural development and band engineering of perovskites materials for photocatalytic solar hydrogen production: A review, *Int. J. Hydrogen Energy*, 2020, **45**(38), 19078–19111.

215 Y. Qu, *et al.*, Facile Synthesis of Porous Zn₂Ti₃O₈Nanorods for Photocatalytic Overall Water Splitting, *ChemCatChem*, 2014, **6**(8), 2258–2262.

216 J. S. Lee, Photocatalytic Water Splitting Under Visible Light with Particulate Semiconductor Catalysts, *Catal. Surv. Asia*, 2006, **9**(4), 217–227.

217 J. Kang, *et al.*, Design of Three-Dimensional Hollow-Sphere Architecture of Ti₃C₂Tx MXene with Graphitic Carbon Nitride Nanoshells for Efficient Photocatalytic Hydrogen Evolution, *ACS Appl. Energy Mater.*, 2020, **3**(9), 9226–9233.

218 E. Hua, *et al.*, In situ fabrication of two-dimensional g-C₃N₄/Ba₅Ta₄O₁₅ nanosheet heterostructures with efficient charge separations and photocatalytic hydrogen evolution under visible light illumination, *Dalton Trans.*, 2018, **47**(12), 4360–4367.

219 E. Hua, *et al.*, Double perovskite compounds A₂CuWO₆ (A = Sr and Ba) with p-type semiconductivity for photocatalytic water oxidation under visible light illumination, *Inorg. Chem. Front.*, 2019, **6**(8), 2096–2103.

220 A. M. Idris, *et al.*, A Novel Double Perovskite Oxide Semiconductor Sr₂CoWO₆as Bifunctional Photocatalyst for Photocatalytic Oxygen and Hydrogen Evolution Reactions from Water under Visible Light Irradiation, *Sol. RRL*, 2019, **4**(3), 00456.

221 A. Kudo and Y. Miseki, Heterogeneous photocatalyst materials for water splitting, *Chem. Soc. Rev.*, 2009, **38**(1), 253–278.

222 A. Kudo, H. Kato and S. Nakagawa, Water splitting into H₂ and O₂ on new Sr₂M₂O₇ (M= Nb and Ta) photocatalysts with layered perovskite structures: factors affecting the photocatalytic activity, *J. Phys. Chem. B*, 2000, **104**(3), 571–575.

223 N. Fajrina and M. Tahir, A critical review in strategies to improve photocatalytic water splitting towards hydrogen production, *Int. J. Hydrogen Energy*, 2019, **44**(2), 540–577.

224 M. B. Tahir, *et al.*, Role of nanotechnology in photocatalysis, in *Encyclopedia of Smart Materials*, ed. A.-G. Olabi, Elsevier, Oxford, 2022, pp. 578–589.

225 N. M. Gupta, Factors affecting the efficiency of a water splitting photocatalyst: a perspective, *Renewable Sustainable Energy Rev.*, 2017, **71**, 585–601.

226 H. Kato and A. Kudo, Photocatalytic water splitting into H₂ and O₂ over various tantalate photocatalysts, *Catal. Today*, 2003, **78**(1–4), 561–569.

227 S. Chandrasekaran, *et al.*, Advanced nano-structured materials for photocatalytic water splitting, *J. Electrochem. Sci. Technol.*, 2016, **7**(1), 1–12.

228 T. Takata, *et al.*, Photocatalytic water splitting with a quantum efficiency of almost unity, *Nature*, 2020, **581**(7809), 411–414.

229 C.-F. Fu, *et al.*, Intrinsic electric fields in two-dimensional materials boost the solar-to-hydrogen efficiency for photocatalytic water splitting, *Nano Lett.*, 2018, **18**(10), 6312–6317.

230 Q. Wang, *et al.*, Scalable water splitting on particulate photocatalyst sheets with a solar-to-hydrogen energy conversion efficiency exceeding 1%, *Nat. Mater.*, 2016, **15**(6), 611–615.

231 T. Hisatomi and K. Domen, Reaction systems for solar hydrogen production via water splitting with particulate semiconductor photocatalysts, *Nat. Catal.*, 2019, **2**(5), 387–399.

232 S. Cao, L. Piao and X. Chen, Emerging Photocatalysts for Hydrogen Evolution, *Trends Chem.*, 2019, **2**(1), 57–70.

233 X. Sun, *et al.*, Activating layered perovskite compound Sr₂TiO₄ via La/N codoping for visible light photocatalytic water splitting, *ACS Catal.*, 2018, **8**(4), 3209–3221.

234 H. Xiao, *et al.*, Ruddlesden–Popper Perovskite Oxides for Photocatalysis-Based Water Splitting and Wastewater Treatment, *Energy Fuels*, 2020, **34**(8), 9208–9221.

235 C. Wang, *et al.*, Band gap engineering of SrTiO₃ for water splitting under visible light irradiation, *Int. J. Hydrogen Energy*, 2014, **39**(24), 12507–12514.

236 Y. Liu, *et al.*, Synthesis and high photocatalytic hydrogen production of SrTiO₃ nanoparticles from water splitting under UV irradiation, *J. Power Sources*, 2008, **183**(2), 701–707.

237 Y. Fan, *et al.*, Photocatalytic Overall Water Splitting by SrTiO₃ with Surface Oxygen Vacancies, *Nanomaterials*, 2020, **10**(12), 2572.

238 K. Ikeue, Y. Yamamoto and M. Suzuki, Photocatalytic Activity for Hydrogen Evolution of Heteroatom-Doped SrTiO₃ Prepared Using a Graphitic-Carbon Nitride Nanosheet, *Ceramics*, 2020, **3**(1), 22–30.

239 A. K. Wahab, *et al.*, Comparing Pt/SrTiO₃ to Rh/SrTiO₃ for hydrogen photocatalytic production from ethanol, *Appl. Petrochem. Res.*, 2013, **3**(3), 83–89.

240 C. R. Kalaiselvi, *et al.*, Synthesis of Ag and N doped potassium tantalate perovskite nanocubes for enhanced photocatalytic hydrogen evolution, *Mater. Lett.*, 2020, **275**, 128166.

241 T. Ahmad, U. Farooq and R. Phul, Fabrication and photocatalytic applications of perovskite materials with special emphasis on alkali-metal-based niobates and tantalates, *Ind. Eng. Chem. Res.*, 2018, **57**(1), 18–41.

242 Y. W. Teh, *et al.*, An insight into perovskite-based photocatalysts for artificial photosynthesis, *Sustainable Energy Fuels*, 2020, **4**(3), 973–984.

243 T. Fujiwara, *et al.*, Single-Crystal Model of Highly Efficient Water-Splitting Photocatalysts: A KTaO₃ Wafer Doped with Calcium Cations, *Chem. Mater.*, 2020, **32**(4), 1439–1447.

244 L. I. Ibarra-Rodriguez, *et al.*, Photocatalytic evolution of H₂ over visible-light active LaMO₃ (M: Co, Mn, Fe) perovskite



materials: Roles of oxygenated species in catalytic performance, *J. Phys. Chem. Solids*, 2020, **136**, 109189.

245 A. Kumar, *et al.*, Interplay between Mesocrystals of CaTiO₃ and Edge Sulfur Atom Enriched MoS₂ on Reduced Graphene Oxide Nanosheets: Enhanced Photocatalytic Performance under Sunlight Irradiation, *ChemPhotoChem*, 2020, **4**(6), 427–444.

246 L. Meng, *et al.*, Controlled synthesis of CaTiO₃:Ln³⁺ nanocrystals for luminescence and photocatalytic hydrogen production, *RSC Adv.*, 2016, **6**(7), 5761–5766.

247 S. N. Lim, *et al.*, H₂ Production Under Visible Light Irradiation from Aqueous Methanol Solution on CaTiO₃:Cu Prepared by Spray Pyrolysis, *J. Electron. Mater.*, 2017, **46**(10), 6096–6103.

248 W. Gao, *et al.*, Visible light driven water splitting over CaTiO₃/Pr₃–Y₂SiO₅/RGO catalyst in reactor equipped artificial gill, *Appl. Catal., B*, 2018, **224**, 553–562.

249 J. Han, *et al.*, Fabrication of CdSe/CaTiO₃ nanocomposites in aqueous solution for improved photocatalytic hydrogen production, *Appl. Surf. Sci.*, 2018, **459**, 520–526.

250 H. Yoshida, R. Yamada and T. Yoshida, Platinum Cocatalyst Loaded on Calcium Titanate Photocatalyst for Water Splitting in a Flow of Water Vapor, *ChemSusChem*, 2019, **12**(9), 1958–1965.

251 M. Qureshi, *et al.*, Catalytic consequences of ultrafine Pt clusters supported on SrTiO₃ for photocatalytic overall water splitting, *J. Catal.*, 2019, **376**, 180–190.

252 I. Tamiolakis, *et al.*, Mesoporous implantable Pt/SrTiO₃:C,N nanocuboids delivering enhanced photocatalytic H₂-production activity via plasmon-induced interfacial electron transfer, *Appl. Catal., B*, 2018, **236**, 338–347.

253 W. Chen, *et al.*, Polymerizable complex synthesis of SrTiO₃:(Cr/Ta) photocatalysts to improve photocatalytic water splitting activity under visible light, *Appl. Catal., B*, 2016, **192**, 145–151.

254 Y. Chang, *et al.*, Ternary CdS/Au/3DOM-SrTiO₃ composites with synergistic enhancement for hydrogen production from visible-light photocatalytic water splitting, *Appl. Catal., B*, 2017, **215**, 74–84.

255 D. Zhong, *et al.*, Insights into the synergy effect of anisotropic {001} and {230} facets of BaTiO₃ nanocubes sensitized with CdSe quantum dots for photocatalytic water reduction, *Appl. Catal., B*, 2018, **227**, 1–12.

256 Z. Wang, *et al.*, Wide spectrum responsive CdS/NiTiO₃/CoS with superior photocatalytic performance for hydrogen evolution, *Catal. Sci. Technol.*, 2017, **7**(12), 2524–2530.

257 Z. Yang, *et al.*, Solid-State, Low-Cost, and Green Synthesis and Robust Photochemical Hydrogen Evolution Performance of Ternary TiO₂/MgTiO₃/C Photocatalysts, *iScience*, 2019, **14**, 15–26.

258 C. Gómez-Solís, *et al.*, Facile solvo-combustion synthesis of crystalline NaTaO₃ and its photocatalytic performance for hydrogen production, *Fuel*, 2014, **130**, 221–227.

259 L. Huang, *et al.*, Improved Photocatalytic Hydrogen Production Performance Over NaTaO₃/Reduced Graphene Oxide Composite Photocatalyst, *J. Nanosci. Nanotechnol.*, 2018, **18**(7), 4982–4986.

260 D. Xu, *et al.*, Ag-Decorated ATaO₃ (A = K, Na) Nanocube Plasmonic Photocatalysts with Enhanced Photocatalytic Water-Splitting Properties, *Langmuir*, 2015, **31**(35), 9694–9699.

261 Z. Chen, *et al.*, Synthesis of carbon doped KTaO₃ and its enhanced performance in photocatalytic H₂ generation, *Catal. Commun.*, 2018, **109**, 6–9.

262 H. Hagiwara, *et al.*, Effect of Porphyrin Molecular Structure on Water Splitting Activity of a KTaO₃ Photocatalyst, *Catalysts*, 2016, **6**(3), 42.

263 S. Takasugi, *et al.*, The hydrothermal and solvothermal synthesis of LiTaO₃ photocatalyst: Suppressing the deterioration of the water splitting activity without using a cocatalyst, *Int. J. Hydrogen Energy*, 2015, **40**(16), 5638–5643.

264 T. Takashima, T. Sano and H. Irie, Cocatalyst modification of niobium-substituted silver tantalate photocatalyst for enhanced solar water-splitting activity, *Int. J. Hydrogen Energy*, 2019, **44**(42), 23600–23609.

265 F. Yang, *et al.*, Facile synthesis of highly efficient Pt/N-rGO/N-NaNbO₃ nanorods toward photocatalytic hydrogen production, *Appl. Catal., B*, 2019, **257**, 117901.

266 J. Yu, *et al.*, Synthesis of carbon-doped KNbO₃ photocatalyst with excellent performance for photocatalytic hydrogen production, *Sol. Energy Mater. Sol. Cells*, 2018, **179**, 45–56.

267 W. C. Balcerksi, S. Y. Ryu and M. R. Hoffmann, Photocatalytic hydrogen production with visible light using nanocomposites of CdS and Ni on niobium oxide, *Sep. Purif. Technol.*, 2015, **156**, 915–921.

268 J. Yu, *et al.*, Synthesis of KNbO₃/g-C3N4 composite and its new application in photocatalytic H₂ generation under visible light irradiation, *J. Mater. Sci.*, 2018, **53**(10), 7453–7465.

269 K. Xu, *et al.*, Photocatalytic hydrogen evolution performance of NiS cocatalyst modified LaFeO₃/g-C3N4 heterojunctions, *New J. Chem.*, 2017, **41**(23), 14602–14609.

270 S. Vasala, *et al.*, Magnetic structure of Sr 2 CuWO 6, *J. Phys.: Condens. Matter*, 2014, **26**, 496001.

271 E. Greul, *et al.*, Highly stable, phase pure Cs₂AgBiBr₆ double perovskite thin films for optoelectronic applications, *J. Mater. Chem. A*, 2017, **5**(37), 19972–19981.

272 K. Wang, *et al.*, Ba₅Ta₄O₁₅ Nanosheet/AgVO₃ Nanoribbon Heterojunctions with Enhanced Photocatalytic Oxidation Performance: Hole Dominated Charge Transfer Path and Plasmonic Effect Insight, *ACS Sustainable Chem. Eng.*, 2018, **6**(5), 6682–6692.

273 J. Yang and J. H. Swisher, The phase stability of Zn₂Ti₃O₈, *Mater. Charact.*, 1996, **37**(2), 153–159.

274 C. López, *et al.*, Magnetic behavior of Ca₂NiWO₆ double perovskite, *Phys. B*, 2007, **398**, 256–258.

275 P. Borse, *et al.*, Improved Photolysis of Water from Ti Incorporated Double Perovskite Sr₂FeNbO₆ Lattice, *Bull. Korean Chem. Soc.*, 2012, **33**, 3407–3412.



276 S. Hong, *et al.*, Structure of PbBi₂Nb₂O₉ and Its Cr-Doped Layered Perovskite System and Their Photocatalytic Activities, *J. Korean Phys. Soc.*, 2007, **51**, S27–S31.

277 C. Peng, *et al.*, Perspective: Photocatalytic reduction of CO₂ to solar fuels over semiconductors, *J. Chem. Phys.*, 2017, **147**(3), 030901.

278 D. W. Hwang, *et al.*, Photocatalytic Hydrogen Production from Water over M-Doped La₂Ti₂O₇ (M = Cr, Fe) under Visible Light Irradiation ($\lambda > 420$ nm), *J. Phys. Chem. B*, 2005, **109**(6), 2093–2102.

279 A. M. Idris, *et al.*, Sr₂NiWO₆ Double Perovskite Oxide as a Novel Visible-Light-Responsive Water Oxidation Photocatalyst, *ACS Appl. Mater. Interfaces*, 2020, **12**(23), 25938–25948.

280 S. Nanamatsu, *et al.*, A new ferroelectric: La₂Ti₂O₇, *Ferroelectrics*, 1974, **8**(1), 511–513.

281 D. Cortecchia, *et al.*, Lead-Free MA₂CuCl_xBr_{4-x} Hybrid Perovskites, *Inorg. Chem.*, 2016, 55.

282 N. Kulischow, C. Ladasiu and R. Marschall, Layered Dion-Jacobson type niobium oxides for photocatalytic hydrogen production prepared via molten salt synthesis, *Catal. Today*, 2017, **287**, 65–69.

283 H. Fukuoka, T. Isami and S. Yamanaka, Crystal Structure of a Layered Perovskite Niobate KCa₂Nb₃O₁₀, *J. Solid State Chem.*, 2000, **151**(1), 40–45.

284 S. S. Bhosale, *et al.*, Mechanism of Photocatalytic CO₂ Reduction by Bismuth-Based Perovskite Nanocrystals at the Gas-Solid Interface, *J. Am. Chem. Soc.*, 2019, **141**(51), 20434–20442.

285 R. Shi, G. I. N. Waterhouse and T. Zhang, Recent Progress in Photocatalytic CO₂ Reduction Over Perovskite Oxides, *Sol. RRL*, 2017, **1**(11), 00126.

286 C. Lu, *et al.*, Synthesis of lead-free Cs₃Sb₂Br₉ perovskite alternative nanocrystals with enhanced photocatalytic CO₂ reduction activity, *Nanoscale*, 2020, **12**(5), 2987–2991.

287 A. Razzaq, *et al.*, Layered Double Hydroxide (LDH) Based Photocatalysts: An Outstanding Strategy for Efficient Photocatalytic CO₂ Conversion, *Catalysts*, 2020, **10**(10).

288 J. Ran, M. Jaroniec and S. Z. Qiao, Cocatalysts in semiconductor-based photocatalytic CO₂ reduction: achievements, challenges, and opportunities, *Adv. Mater.*, 2018, **30**(7), 1704649.

289 J. Albero, Y. Peng and H. García, Photocatalytic CO₂ reduction to C₂₊ products, *ACS Catal.*, 2020, **10**(10), 5734–5749.

290 Y.-F. Xu, *et al.*, A CsPbBr₃ perovskite quantum dot/graphene oxide composite for photocatalytic CO₂ reduction, *J. Am. Chem. Soc.*, 2017, **139**(16), 5660–5663.

291 R. Shi, G. I. Waterhouse and T. Zhang, Recent progress in photocatalytic CO₂ reduction over perovskite oxides, *Sol. RRL*, 2017, **1**(11), 1700126.

292 B. N. Nunes, *et al.*, Recent Advances in Niobium-Based Materials for Photocatalytic Solar Fuel Production, *Catalysts*, 2020, **10**(1), 126.

293 K. Kočí, L. Obalová and Z. Lacný, Photocatalytic reduction of CO₂ over TiO₂ based catalysts, *Chem. Pap.*, 2008, **62**(1), 1–9.

294 L. F. Da Silva, *et al.*, An improved method for preparation of SrTiO₃ nanoparticles, *Mater. Chem. Phys.*, 2011, **125**(1–2), 168–173.

295 S. Kahng, H. Yoo and J. H. Kim, Recent advances in earth-abundant photocatalyst materials for solar H₂ production, *Adv. Powder Technol.*, 2020, **31**(1), 11–28.

296 F. Fresno, *et al.*, CO₂ reduction over NaNbO₃ and NaTaO₃ perovskite photocatalysts, *Photochem. Photobiol. Sci.*, 2017, **16**(1), 17–23.

297 C.-C. Hu and H. Teng, Influence of structural features on the photocatalytic activity of NaTaO₃ powders from different synthesis methods, *Appl. Catal., A*, 2007, **331**, 44–50.

298 K. Li, *et al.*, Photocatalytic reduction of CO₂ and protons using water as an electron donor over potassium tantalate nanoflakes, *Nanoscale*, 2014, **6**(16), 9767–9773.

299 H. Shi, *et al.*, Polymeric g-C₃N₄ Coupled with NaNbO₃ Nanowires toward Enhanced Photocatalytic Reduction of CO₂ into Renewable Fuel, *ACS Catal.*, 2014, **4**(10), 3637–3643.

300 E. Karamian and S. Sharifnia, Enhanced visible light photocatalytic activity of BiFeO₃-ZnO p–n heterojunction for CO₂ reduction, *Mater. Sci. Eng., B*, 2018, **238**–239, 142–148.

301 D. Li, *et al.*, Synergistic effect of Au and Rh on SrTiO₃ in significantly promoting visible-light-driven syngas production from CO₂ and H₂O, *Chem. Commun.*, 2016, **52**(35), 5989–5992.

302 J. Y. Do, *et al.*, Preparation of basalt fiber@perovskite PbTiO₃ core-shell composites and their effects on CH₄ production from CO₂ photoreduction, *Ceram. Int.*, 2016, **42**(5), 5942–5951.

303 Z. Qu, *et al.*, Preparation of a coated Z-scheme and H-type SrTiO₃/(BiFeO₃@ZnS) composite photocatalyst and application in degradation of 2,4-dichlorophenol with simultaneous conversion of Cr(VI), *Sep. Purif. Technol.*, 2020, **240**, 116653.

304 M. Humayun, *et al.*, Exceptional Visible-Light Activities of TiO₂-Coupled N-Doped Porous Perovskite LaFeO₃ for 2,4-Dichlorophenol Decomposition and CO₂ Conversion, *Environ. Sci. Technol.*, 2016, **50**(24), 13600–13610.

305 L. O. Paulista, *et al.*, Turning Carbon Dioxide and Ethane into Ethanol by Solar-Driven Heterogeneous Photocatalysis over RuO₂- and NiO-co-Doped SrTiO₃, *Catalysts*, 2021, **11**(4), 461.

306 Y. Yuan, *et al.*, BaCeO₃ as a novel photocatalyst with 4f electronic configuration for water splitting, *Solid State Ionics*, 2008, **178**(33), 1711–1713.

307 L. Jia, *et al.*, Visible-light-induced photocatalyst based on C-doped LaCoO₃ synthesized by novel microorganism chelate method, *Catal. Commun.*, 2009, **10**(8), 1230–1234.

308 A. A. Shah, S. Ahmad and A. Azam, Investigation of structural, optical, dielectric and magnetic properties of LaNiO₃ and LaNi_{1-x}M_xO₃ (M = Fe, Cr & Co; x = 5%) nanoparticles, *J. Magn. Magn. Mater.*, 2020, **494**, 165812.



309 Y. Wang, *et al.*, Ag loaded on layered perovskite H₂SrTa₂O₇ to enhance the selectivity of photocatalytic CO₂ reduction with H₂O, *J. Alloys Compd.*, 2019, **786**, 149–154.

310 S. Murcia-Lopez, *et al.*, Photocatalytic reduction of CO₂ over platinised Bi₂WO₆-based materials, *Photochem. Photobiol. Sci.*, 2015, **14**(4), 678–685.

311 Q. Wang, *et al.*, Photocatalytic reduction of CO₂ to methane over PtOx-loaded ultrathin Bi₂WO₆ nanosheets, *Appl. Surf. Sci.*, 2019, **470**, 832–839.

312 Y. Bai, *et al.*, Ultrathin Bi₄O₅Br₂ nanosheets for selective photocatalytic CO₂ conversion into CO, *Chem. Eng. J.*, 2019, **360**, 473–482.

313 P. Chen, *et al.*, Improving the Catalytic CO₂ Reduction on Cs₂AgBiBr₆ by Halide Defect Engineering: A DFT Study, *Materials*, 2021, **14**(10), 2469.

314 J. M. Modak, Haber process for ammonia synthesis, *Resonance*, 2002, **7**(9), 69–77.

315 J. Humphreys, R. Lan and S. Tao, Development and Recent Progress on Ammonia Synthesis Catalysts for Haber–Bosch Process, *Advanced Energy and Sustainability Research*, 2020, **2**(1), 00043.

316 Y. Shiraishi, *et al.*, Nitrogen fixation with water on carbon-nitride-based metal-free photocatalysts with 0.1% solar-to-ammonia Energy Conversion Efficiency, *ACS Appl. Energy Mater.*, 2018, **1**(8), 4169–4177.

317 H. Huang, *et al.*, Toward visible-light-assisted photocatalytic nitrogen fixation: A titanium metal organic framework with functionalized ligands, *Appl. Catal., B*, 2020, **267**, 118686.

318 K. Vikrant, *et al.*, Photocatalytic platforms for removal of ammonia from gaseous and aqueous matrixes: status and challenges, *ACS Catal.*, 2020, **10**(15), 8683–8716.

319 S. Mansingh, *et al.*, Recent advances in wireless photofixation of dinitrogen to ammonia under the ambient condition: A review, *J. Photochem. Photobiol., C*, 2021, **47**, 100402.

320 S. Mansingh, *et al.*, Efficient Photon Conversion via Double Charge Dynamics CeO₂-BiFeO₃ p-n Heterojunction Photocatalyst Promising toward N₂ Fixation and Phenol-Cr(VI) Detoxification, *Inorg. Chem.*, 2020, **59**(6), 3856–3873.

321 S. Zhang, *et al.*, Photocatalytic ammonia synthesis: Recent progress and future, *EnergyChem*, 2019, **1**(2), 100013.

322 K. Ithisuphalap, *et al.*, Photocatalysis and Photoelectrocatalysis Methods of Nitrogen Reduction for Sustainable Ammonia Synthesis, *Small Methods*, 2018, **3**(6), 00352.

323 Y. Bo, *et al.*, Altering Hydrogenation Pathways in Photocatalytic Nitrogen Fixation by Tuning Local Electronic Structure of Oxygen Vacancy with Dopant, *Angew. Chem., Int. Ed.*, 2021, **60**(29), 04001.

324 R. Shi, *et al.*, The journey toward low temperature, low pressure catalytic nitrogen fixation, *Adv. Energy Mater.*, 2020, **10**(19), 2000659.

325 G. Zhang, *et al.*, Nanostructured photocatalysts for nitrogen fixation, *Nano Energy*, 2020, **71**, 104645.

326 S. Chen, D. Liu and T. Peng, Fundamentals and Recent Progress of Photocatalytic Nitrogen-Fixation Reaction over Semiconductors, *Sol. RRL*, 2021, **5**(2), 2000487.

327 B. Huang, *et al.*, Boosting the photocatalytic activity of mesoporous SrTiO₃ for nitrogen fixation through multiple defects and strain engineering, *J. Mater. Chem. A*, 2020, **8**(42), 22251–22256.

328 H. Zhang, *et al.*, Sol-gel synthesis of upconversion perovskite/attapulgite heterostructures for photocatalytic fixation of nitrogen, *J. Sol-Gel Sci. Technol.*, 2019, **92**(1), 154–162.

329 S. Zhou, *et al.*, Formation of an oriented Bi₂WO₆ photocatalyst induced by in situ Bi reduction and its use for efficient nitrogen fixation, *Catal. Sci. Technol.*, 2019, **9**(20), 5562–5566.

330 R. Huang, *et al.*, Recent advances in photocatalytic nitrogen fixation: from active sites to ammonia quantification methods, *RSC Adv.*, 2021, **11**(24), 14844–14861.

331 Z. Zhao, *et al.*, Magnetic-Field-Stimulated Efficient Photocatalytic N₂ Fixation over Defective BaTiO₃ Perovskites, *Angew. Chem., Int. Ed. Engl.*, 2021, **60**(21), 11910–11918.

332 M. Song, *et al.*, Defect density modulation of La₂TiO₅: An effective method to suppress electron-hole recombination and improve photocatalytic nitrogen fixation, *J. Colloid Interface Sci.*, 2021, **602**, 748–755.

333 P. Xing, *et al.*, New Application and Excellent Performance of Ag/KNbO₃ Nanocomposite in Photocatalytic NH₃ Synthesis, *ACS Sustainable Chem. Eng.*, 2019, **7**(14), 12408–12418.

334 A. Kumar, *et al.*, Unraveling the structural and morphological stability of oxygen vacancy engineered leaf-templated CaTiO₃ towards photocatalytic H₂ evolution and N₂ fixation reactions, *J. Mater. Chem. A*, 2021, **9**(31), 17006–17018.

