


Cite this: *RSC Adv.*, 2022, 12, 8466

# Spontaneous *in situ* generation of photoemissive aurophilic oligomers in water solution based on the 2-thiocytosine ligand†

Daniel Blasco,<sup>ID</sup> María Rodríguez-Castillo,<sup>ID</sup> M. Elena Olmos,<sup>ID</sup> Miguel Monge<sup>ID</sup> and José M. López-de-Luzuriaga<sup>ID</sup> \*

Complexes  $[\text{Au}(\text{S-2-thiocytosine})(\text{PMe}_3)]$  (**2**, 2-thiocytosine = 4-amino-2-mercaptopyrimidine) and  $[\text{Au}(\text{S-2-thiocytosine})(\text{PMe}_3)](\text{CF}_3\text{CO}_2)$  (**3**) have been prepared by the reaction of  $[\text{Au}(\text{acac})(\text{PMe}_3)]$  (**1**, acac = acetylacetonate) or  $[\text{Au}(\text{OCOCF}_3)(\text{PMe}_3)]$  with 2-thiocytosine, respectively. The equimolecular mixture of complexes **1** and **3** also produces  $[\{\text{Au}(\text{PMe}_3)\}_2(\mu\text{-S},\text{N}^1\text{-2-thiocytosine})](\text{CF}_3\text{CO}_2)$  (**4**), which features two distinct  $[\text{Au}(\text{PMe}_3)]^+$  groups coordinated to the S and  $\text{N}^1$  atoms of the heterocycle. Complex **4** experiences a ligand redistribution process in water solution that liberates  $[\text{Au}(\text{PMe}_3)_2](\text{CF}_3\text{CO}_2)$  and a brightly coloured and luminescent species of  $[\text{Au}_n(\mu\text{-S},\text{N}^1\text{-2-thiocytosine})_n]$  stoichiometry, presumably as a tetraauracycle ( $n = 4$ ).

Received 18th January 2022  
Accepted 8th March 2022

DOI: 10.1039/d2ra00368f

rsc.li/rsc-advances

## Introduction

A feature that attracts the attention of inorganic chemists towards the production of water-soluble gold(I) complexes is in some cases their dynamic behaviour in solution. This is because of aurophilicity as the origin of the self-aggregation of gold(I) centres at sub-van der Waals distances.<sup>1,2</sup> This close approximation of coordinatively unsaturated gold(I) atoms is by no means innocent, as it induces (a) a deviation from the hardly-photoemissive ideal dicoordinate linearity of gold(I), and (b) the mixing of suitable “atomic orbitals” (fully gold(I)-centered molecular orbitals would be a more realistic image) into pairs of new  $\text{Au}^{\text{I}}\cdots\text{Au}^{\text{I}}$  axis-centered molecular orbitals. Those new orbitals are now accessible by optical excitation of the sample, giving rise to one of the most appealing properties of gold(I) complexes, photoluminescence.<sup>3</sup>

As devoted “aurophilic” chemists ourselves, we have considered in the recent years natural nucleobases as convenient ligands for the stabilization of molecular gold(I) compounds. In those, the co-existence of strong aurophilic interactions and numerous hydrogen bonds in an “orthogonal” fashion allows their effective self-aggregation in water and, hence, the design of low-molecular-weight gelators and/or


luminophores.<sup>4</sup> On the other side, thiol-functionalized nucleobases are not unfamiliar ligands for the stabilization of gold(I) complexes. Indeed, they are interesting polydentate S,N-donor heterocycles and, for this reason, they had been considered for achieving the main goals of nowadays’ gold(I) chemistry (see Scheme 1). That resulted, for instance, in the discovery of diauracyclic 2-thiouracyl and 6-methyl-2-thiouracyl salts featuring tribochromic luminescence,<sup>5</sup> or in the synthesis of a wide plethora of antiproliferative and/or antimicrobial complexes sharing the  $[\text{Au}(\text{PR}_3)(\text{SR})]$  scaffold of antiarthritic  $[\text{Au}(\text{PET}_3)\{\text{S-(2,3,4,6-tetra-O-acetyl-1-thio-}\beta\text{-pyranosate)}\}]$  (trade name Auranofin®).<sup>6</sup> The presence of amino and/or hydroxy groups in the nucleobases’ moieties also confers potential water solubility to the (thiolate)gold(I) complexes, converting them in non-toxic “liquid gold” sources for the deposition of thin metal layers over glass and ceramics, showing an industrial application of such.<sup>7</sup> Furthermore, surprising structural arrangements have to be expected for their X-ray structures, *e.g.*, the astonishingly simple complex bis(*S*-2-pyridinethione)gold(I) perchlorate  $[\text{Au}(\text{C}_5\text{H}_5\text{-NS})_2](\text{ClO}_4)$ , where five of the six cations that are present in the unit cell form a discrete pentamer by  $\text{Au}^{\text{I}}\cdots\text{Au}^{\text{I}}$  interactions of *ca.* 3.3 Å, whereas the remaining sixth is segregated.<sup>8</sup>

Hence, recalling both our reported results for extremely simple complexes featuring the natural nucleobase adenine (6-aminopurine), and those displayed by thiol-functionalized nucleobase-containing ones, we decided to investigate the properties of the products of the mono- and diauration of 2-thiocytosine (4-amino-2-mercaptopyrimidine). The choice of 2-thiocytosine responds to the existence of a previous report by H. Schmidbaur *et al.* that demonstrates its feasibility as a substrate for an analogous chemistry to that developed by us for adenine.<sup>9</sup> Moreover, their study was completed with the crystal structure


Departamento de Química, Centro de Investigación en Síntesis Química (CISQ), Universidad de La Rioja, Madre de Dios 53, 26006 Logroño, Spain. E-mail: josemaria.lopez@unirioja.es

† Electronic supplementary information (ESI) available: Instrumentation, syntheses, spectroscopic characterization, structural characterization, optical properties, computational studies, NMR kinetic studies, atomic coordinates of computational optimizations (xyz format). CCDC 2123504 and 2123505. For ESI and crystallographic data in CIF or other electronic format see DOI: 10.1039/d2ra00368f





RSC Adv., 2022, 12, 8466–8473 | 8467



Scheme 2 Syntheses of complexes 1–4.

position of 2-thiocytosine, a process that takes place even at 200 K (Fig. S17†).

The ESI-MS(+) spectra of complexes 2–4 feature identical major peaks, corresponding to  $[\text{Au}(\text{PMe}_3)_2]^+$  (349.0 Da),  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PMe}_3)]^+$  (400.0 Da) and  $[\{\text{Au}(\text{PMe}_3)_2\}_2(\mu\text{-S}, \text{N}^1\text{-2-thiocytosinate})]^+$  (672.0 Da), which represent extraordinary stable complex ions that, if not naturally present in the sample, are formed under the harsh ESI-MS measuring conditions. A peak corresponding to homoleptic  $[\text{Au}(\text{S-2-thiocytosinate})_2]^-$  (449.0 Da) is also detected in the ESI-MS(–) spectra of 2 and 3.

Finally, molar conductivity measurements of complexes 3 (80.9  $\text{cm}^2 \Omega^{-1} \text{mol}^{-1}$ ) and 4 (83.2  $\text{cm}^2 \Omega^{-1} \text{mol}^{-1}$ ) in methanol solution pertain to the 1 : 1 electrolyte range, according with the proposed ion-pair stoichiometry.

### X-ray crystal structure determination

Suitable single crystals for the elucidation of the structure of complexes 2–4 by X-ray diffraction were obtained by slow diffusion of diethyl ether into solutions of 95% ethanol (for 2) or acetone (for 4), or *n*-hexane into acetone (for 3), all of them at room temperature. The interested reader is referred to Tables S1–S6† in the ESI for further data collection details and selected bond lengths and angles.

Complex 2 crystallizes in the orthorhombic *Pbca* space group ( $Z = 8$ ). Its asymmetric unit, which corresponds to one single  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PMe}_3)]$  molecule (Fig. 1), reveals the binding of the phosphinegold(i) fragment (Au–P distance, 2.2564(7) Å) to the deprotonated sulphur atom (Au–S distance, 2.3222(7) Å) of 2-thiocytosine, in an almost linear fashion (S–Au–P angle,  $177.14(3)^\circ$ ). The relative *syn* position of the  $\text{C}^4\text{-NH}_2$  group with respect to the gold(i) center is also noteworthy, although the  $\text{H}\cdots\text{Au}^{\text{I}}$  distance is considerably long (4.518 Å) to suggest any kind of stabilizing interaction between them. The aforementioned work of H. Schmidbaur *et al.*<sup>9</sup> and another one of A. Laguna, M. C. Gimeno *et al.*<sup>6a</sup> provided valuable structural information of several  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PR}_3)]$  examples. In all cases, the coordination sphere of gold(i) is identical to that of 2, but displaying notably shorter Au–S distances despite bearing bulkier phosphine

ligands:  $\text{PR}_3 = \text{PEt}_3$ , 2.291(3)–2.307(2) Å;  $\text{PPh}_3$ , 2.303(1)–2.308(1) Å;  $\text{PPh}_2\text{py}$ , 2.3068(8)–2.3083(8) Å;  $\text{PPh}_2\text{NHpy}$ , 2.3130(8) Å;  $\mu\text{-dppm}$ , 2.3052(9)–2.309(1) Å. However, the most significant fact is that the supramolecular network of these five examples is exclusively built-up by hydrogen bonds only (a long intramolecular  $\text{Au}^{\text{I}}\cdots\text{Au}^{\text{I}}$  interaction of 3.3317(2) Å is present in dinuclear  $[\{\text{Au}(\text{S-2-thiocytosinate})\}_2(\mu\text{-dppm})]$ , giving rise to intricate 3-D structures. The authors explain the remarkable absence of aurophilic interactions as a result of competing weak forces that include hydrogen bonding rather than by the steric hindrance of the phosphines. Complex  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PMe}_3)]$  (2) is not an exception, because no  $\text{Au}^{\text{I}}\cdots\text{Au}^{\text{I}}$  distances within the interaction range are found. Instead, the crystalline structure grows along the *b* axis by a combination of  $\text{C}^4\text{-N}\cdots\text{N}^1$ ,  $\text{C}^4\text{-N}\cdots\text{S}$  and  $\text{C}^5\text{-H}\cdots\text{S}$  hydrogen bonds (Fig. S24†), and through the other two axes by weaker  $\text{C}^6\text{-H}\cdots\text{N}^3$  and  $\text{PC}\cdots\text{H}\cdots\text{N}$  bonds.

The ionic analogue  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PMe}_3)](\text{CF}_3\text{CO}_2)$  (3) also crystallizes in the *Pbca* space group of the orthorhombic system ( $Z = 8$ ). The molecular structure of the gold(i) cation is





Fig. 1 Asymmetric unit of complex 2, with the labelling scheme for the atom positions (50% probability ellipsoids) and selected bond distances. Colour code: C, grey; H, white; Au, yellow; N, blue; P, orange; S, brown.






Lastly, the crystalline structure of dinuclear  $[\{\text{Au}(\text{PME}_3)_2(\mu\text{-}S,N^1\text{-2-thiocytosinate})\}(\text{CF}_3\text{CO}_2) \cdot 0.25\text{H}_2\text{O} (4 \cdot 0.25\text{H}_2\text{O})]$  has been determined. This complex crystallizes in the monoclinic  $P2_1/c$  space group ( $Z = 8$ ), with two formula units integrating the asymmetric unit. The cationic part of the formula (Fig. 3, left) features one  $[\text{Au}(\text{PME}_3)]^+$  fragment coordinated to the S-donor position of 2-thiocytosine (as in complexes 2 and 3), in a relative *syn* fashion with respect to the  $\text{C}^4\text{-NH}_2$  group, and with Au–S bond distances of 2.331(3) and 2.324(3) Å. The second  $[\text{Au}(\text{PME}_3)]^+$  unit, by its side, coordinates to the endocyclic  $\text{N}^1$  position, with identical Au–N bond distances of 2.091(10) Å for both cations in the asymmetric unit. The Au–P bond distances are clearly affected by the nature of the second donor atom bound to gold(I), shortening from 2.251(3), 2.254(3) Å (phosphorus *trans* to sulphur) to 2.235(4), 2.238(3) Å (phosphorus

## Solid-state optical properties

The DRUV-Vis absorption spectra of complexes **2–4** (Fig. S4†) are featureless and, in general, resemble that of free 2-thiocytosine, suggesting an intraligand origin for all of them. From those, only the band-edge of complex **4**, also the only one where polymeric intermolecular  $\text{Au}^{\text{I}}\cdots\text{Au}^{\text{I}}$  interactions are observed within its crystalline structure, is notably red-shifted with respect to that of the ligand.

From the three complexes 2–4, only  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PMe}_3)]$  (2) and  $[\{\text{Au}(\text{PMe}_3)_2(\mu\text{-S}, \text{N}^1\text{-2-thiocytosinate})\}(\text{CF}_3\text{CO}_2)]$  (4) display visible photoluminescence when irradiated with 365 nm UV light at room temperature (see Fig. 4). In both cases, the yellowish emission corresponds to a non-structured band with respective maxima at 515 nm (for 2,  $\lambda_{\text{ex}} = 370$  nm,  $\phi = 1.7\%$ ) and 531 nm (for 4,  $\lambda_{\text{ex}} = 406$  nm,  $\phi =$








Fig. 4 Excitation (dashed lines) and emission (solid lines) spectra in the solid state of complexes 2–4 (from left to right), at room temperature (black lines) and 77 K (red lines).

Table 1 Summary of the photophysical properties of complexes 2–4 in the solid state

	Absorption (nm)	Photoluminescence			
		$\lambda_{\text{em}}$ (nm) ( $\lambda_{\text{ex}}$ (nm))		$\tau$ (ns) ( $\lambda_{\text{ex}}$ (nm))	$\phi$ (%)
		RT	77 K		
2	244, 275, 298, 309	515 (370)	521 (366)	512 (370)	1.7
3	253, 281, 291	—	458 (357)	722 (370) <sup>a</sup>	—
4	254, 275, 291	531 (406)	494 (362)	550 (390)	6.6

<sup>a</sup> Measured at 77 K.

6.6%), and associated long lifetimes of 512 ns (2) and 550 ns (4) that suggest a phosphorescent deactivation process of the optically accessible excited states. When the temperature is lowered to 77 K, a poorly resolved vibronic profile with negligible energy shifting arises for 2 (spacings of 1425, 1334 and 569  $\text{cm}^{-1}$  between consecutive peaks), suggesting the ligand participation in the emission as the spacings' energies match those of C=C or C=N stretching modes. Upon cooling, complex 4 shifts its greenish emission up to 494 nm ( $\lambda_{\text{ex}}$  = 362 nm). Also, complex 3 turns photoluminescent, displaying an asymmetric broad emission with a maximum at 458 nm ( $\lambda_{\text{ex}}$  = 357 nm,  $\tau$  = 722 ns) and a low-energy tail extending up to 800 nm (Table 1).

### Computational studies

The photoluminescent emission that gold(i) thiolates commonly display has been traditionally assigned to a spin-forbidden (phosphorescent) charge transfer from sulphur to gold(i) ( $^3\text{LMCT}$ ) or to the gold(i)  $\cdots$  gold(i) axis ( $^3\text{LMMCT}$ ), in the basis of the observation of large Stokes shifts in their luminescence spectra and long emission lifetimes.<sup>12</sup>

A possible origin of the photoluminescent emission of complexes 2 and 4 in the solid state is proposed in here with the aid of DFT and TD-DFT calculations. For modelling complex 2, a single molecule of  $[\text{Au}(\text{S-2-thiocytosinate})(\text{PMe}_3)]$  was considered, whereas for complex 4, which possesses a more intricate supramolecular structure in terms of gold(i)-related interactions, two consecutive  $[\{\text{Au}(\text{PMe}_3)\}_2(\mu\text{-S}, N^1\text{-2-thiocytosinate})]^+$  cations were picked from the X-ray structure. Both respective models 2a and 4a were freely optimized (DFT-D3/PBE

level of theory) and then employed as inputs for further TD-DFT calculations including singlet-to-singlet and, as possible phosphors, singlet-to-triplet vertical excitations. A comparison between the calculated transitions and the experimental absorption and excitation profiles is shown in Fig. 5; for a full description of the labelled ones (transition, wavelength, oscillator strength, involved orbitals, their shapes and population analysis), the ESI† should be checked.

Regarding the superimposition of model 2a (Fig. 5, top), the excitation and absorption spectra only overlap in the low energy




Fig. 5 Superimposition of the TD-DFT singlet-to-singlet (black bars) and first singlet-to-triplet (red bar, arbitrary oscillator strength of 0.5) transitions with the absorption (black line, anhydrous KBr mull) and excitation (red line, pure solid sample) spectra, for models 2a (top) and 4a (bottom).



region of the latter, what accords with the speculated spin forbiddance of the excitation transition. Also, the calculated singlet-to-triplet transition energy nicely matches with that of the overlap and, according to the population analysis, is composed of the mixture of  $^3\text{LMCT}$  and  $^3\text{IL}$  charge transfers from HOMO to LUMO, and a second  $^3\text{IL}$  contribution from HOMO to LUMO+4. Whereas this qualitative description provided for model **2a** also serves for **4a**, the orbitalic origin of the forbidden singlet-to-triplet transition of the latter is less evident, since any relevant MO surface is clearly located over definite areas of the model. It can be roughly concluded, however, that a metal-perturbed intraligand transition ( $^3\text{IL}$ ) is responsible for the vertical excitation of the model.

### Absorption and emission properties in aqueous solution

Among the series of complexes **2–4**, only the trifluoroacetate salts, namely  $[\text{Au}(S\text{-}2\text{-thiocytosine})(\text{PMe}_3)](\text{CF}_3\text{CO}_2)$  (**3**) and  $[\{\text{Au}(\text{PMe}_3)_2(\mu\text{-}S,N^1\text{-}2\text{-thiocytosinate})\}](\text{CF}_3\text{CO}_2)$  (**4**), are freely water-soluble. This probably may be because the numerous and varied hydrogen bonds that are found in the crystalline structure of neutral  $[\text{Au}(S\text{-}2\text{-thiocytosinate})(\text{PMe}_3)]$  (**2**) preclude its solvation by usual organic solvents or water. Strikingly, those complexes **3** and **4** give rise to brightly coloured solutions of a vivid yellow hue, even at concentrations as low as 1 mM, with its colour intensity gradually augmenting upon aging (see Fig. S32<sup>†</sup>).

The poor thermodynamic stability of complex **3** in water solution precluded the completion of a full photophysical study (grey decomposition is observed after few hours); however, aqueous solutions of **4** are perfectly stable even for days, allowing the collection of absorption data for extremely long periods of time. For this reason, variable absorption spectra of a diluted aqueous solution of **4** (0.1 mM) were collected at constant intervals of 900 s (15 min) for 12 h (720 min), which are superimposed in Fig. 6. In the initial measurement, only three high-energy absorptions are registered at 205, 241 and 280 nm, matching the energies of the corresponding absorption bands of free 2-thiocytosine (Fig. S33<sup>†</sup>). Thus, those absorptions may

be assigned to spin-allowed intraligand transitions ( $^1\text{IL}$ ) with negligible contributions of the phosphinegold(i) fragments. Immediately afterwards, a new band arises at 405 nm with no appreciable energy-shifting within the considered time interval of 12 h. The appearing of this absorption in the violet-to-blue region of the visible spectrum would be responsible for the vivid yellow colour of the solution, and its increase with respect to time for the attractive color saturation. The original absorption at 241 nm is not static either, as its absorbance decreases at a more pronounced rate; thus, an isosbestic point near 280 nm appears, suggesting chemical equilibria between coexisting entities in solution. Besides, yellow solutions of **4** are photoluminescent, emitting orange light when irradiated with a 365 nm UV hand lamp (see inset in Fig. 7). Neither special solvent handling (argon bubbling, *etc.*) is needed for achieving such luminescence, which is even observed in aerated water solutions. The emission profile that is recorded from a 5 mM aged solution is structureless, centered at 603 nm, and associated to a lifetime of 129 ns which, in fact, is notably shorter than that of complex **4** in the solid state. The nature of the radiant process cannot be securely elucidated from the lifetime value itself due to the high spin-orbit coupling effect of gold, although it is likely that is associated to a fluorescent one. The excitation profile shows two different bands associated with a dynamic equilibrium within the experimental timescale, although the emission energy is apparently independent from the excitation wavelength (Fig. S34<sup>†</sup>).

These results prompted us to deepen in its study through time-resolved  $^1\text{H}$  and  $^{31}\text{P}\{^1\text{H}\}$  NMR. For this purpose, a solution of complex **4** in deuterium oxide was monitored between constant dwell times for 3 h (180 min). The most clarifying fact that revealed such experiment, which is depicted in the ESI,<sup>†</sup> is the increasing appearance of the homoleptic cation  $[\text{Au}(\text{PMe}_3)_2]^+$ , which is easily identified by its characteristic  $^1\text{H}$  triplet-like resonance that exhibits in deuterium oxide,<sup>13</sup> and by a singlet in the  $^{31}\text{P}\{^1\text{H}\}$  NMR spectrum.

The steady formation of  $[\text{Au}(\text{PMe}_3)_2](\text{CF}_3\text{CO}_2)$  leaves a second neutral species of empirical formula  $[\text{Au}(\mu\text{-}S,N^1\text{-}2\text{-thiocytosine})(\text{PMe}_3)]$  (**2a**).




Fig. 6 UV-Vis spectra collection of complex **4** (0.1 mM in distilled water), recorded at constant intervals of 900 s (15 min) for 12 h (720 min) and at room temperature. Inset: absorbance at 405.0 nm (black dots) and 241.0 nm (red dots) versus time.





Fig. 7 Luminescence spectra of an aqueous solution of complex **4** (0.5 mM), as freshly prepared and after 3 h. The arrows denote the direction of the excitation and emission bands' intensity variation. Inset: sample under 365 nm UV light.



Scheme 3 Proposed rearrangement process for complex **4** in aqueous solution.

thiocytosinate)] (Scheme 3). This product is insoluble in all common organic solvents and precludes single crystal seeding methods. Therefore, its exact structure and nuclearity remain non-elucidated. The photophysical properties of complex **4**, however, give a clue of the effective establishing of additional  $\text{Au}^{\text{I}} \cdots \text{Au}^{\text{I}}$  interactions. In a similar example, N. W. Mitzel *et al.* demonstrated that certain rigid bis((phosphine)gold(i))-substituted 1,8-diethynylanthracenes rearrange towards diauracyclization for releasing torsional strain.<sup>14</sup> That does not seem to be the underlying reason in here (much less bulkier phosphines are coordinating to both gold(i) atoms) but, according to the numerous examples of eight-membered diauracycles that are findable in the literature,<sup>15</sup> such a cyclization process may also happen in here. A wide range of solid-state structures has been described in the literature for neutral homoleptic digold(i) complexes, spanning from discrete dimers to higher nuclearities' forms, including tetramers, triangular or arrow tip-shaped hexamers, and infinite arrays of 1-D polymers. Even, some of them present an additional degree of self-assembly through intermolecular  $\text{Au}^{\text{I}} \cdots \text{Au}^{\text{I}}$  interactions.<sup>15c</sup> This evinces the potential polymorphic character of  $[\text{Au}_n(\text{L}\wedge\text{L})_n]$  complexes ( $\text{L}\wedge\text{L}$  = anionic ditopic ligand) and, in particular, those where  $n = 2$ . Thus, to propose a likely molecular geometry for  $[\text{Au}_n(\mu\text{-S},N^1\text{-2-thiocytosinate})_n]$ , the ground state energies and the first singlet-to-singlet vertical transitions of two additional tetragold(i) models, namely  $[\text{Au}_2(\mu\text{-S},N^1\text{-2-thiocytosinate})_2]_2$  (**4b**) and  $[\text{Au}_4(\mu\text{-S},N^1\text{-2-thiocytosinate})_4]$  (**4c**, Chart 1), were computed and compared. The energetic difference of  $34.61 \text{ kJ mol}^{-1}$  favouring model **4c** indicates it to be a more stable species, which may be attributed to the additional aurophilic interactions that are established within the square tetragold(i) cluster. Also, the most intense among the lowest-lying singlet-to-singlet transitions of models **4b** and **4c**, which are summarized in the ESI,<sup>†</sup> are suggested to have a different origin. For model **4b**, the HOMO  $\rightarrow$  LUMO transition has a major  $^1\text{MLCT}$  character and a minor  $^1\text{IL}$  contribution, whereas for model **4c**,  $^1\text{LMCT}$  and  $^1\text{IL}$  contributions are identified in the symmetry-related HOMO-2  $\rightarrow$  LUMO and HOMO-1  $\rightarrow$  LUMO transitions.




Chart 1 Theoretical models  $[\text{Au}_2(\mu\text{-S},N^1\text{-2-thiocytosinate})_2]_2$  (**4b**) and  $[\text{Au}_4(\mu\text{-S},N^1\text{-2-thiocytosinate})_4]$  (**4c**).

## Conclusions

The products of the mono- and diauration of 2-thiocytosine show different photoluminescence behaviour depending on the ionic charge (complexes **2** versus **3**) or the number of gold atoms coordinated to the thiol-functionalized nucleobase (complexes **2** and **3** versus **4**). Likewise, the nature of the emission-leading excitation is fully different ( $^3\text{LMCT} + ^3\text{IL}$  for **2**, metal-perturbed  $^3\text{IL}$  for **4**). When left free in fluid solution, gold(i) complexes rearrange themselves by, for instance, ligand exchange, to reach a more stable form. In the present case, this implies the water-promoted breakage of the structure of  $[\{\text{Au}(\text{PMe}_3)_2\}(\mu\text{-S},N^1\text{-2-thiocytosinate})](\text{CF}_3\text{CO}_2)$  (**4**) towards ionic  $[\text{Au}(\text{PMe}_3)_2](\text{CF}_3\text{CO}_2)$  and neutral  $[\text{Au}_n(\mu\text{-S},N^1\text{-2-thiocytosinate})_n]$  species. The excellent properties of water molecules for solvating ionic pairs or hydrogen-bond donors/acceptors may explain this spontaneous process, rather than structural strain loss.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

Grant PID2019-104379RB-C22 funded by MCIN/AEI/10.13039/501100011033 and by "ERDF A way of making Europe".

## Notes and references

- (a) H. Schmidbaur and A. Schier, A briefing on aurphilicity, *Chem. Soc. Rev.*, 2008, **37**, 1931–1951; (b) H. Schmidbaur and A. Schier, Aurphilic interactions as a subject of current research: an up-date, *Chem. Soc. Rev.*, 2012, **41**, 370–412.
- (a) J. C. Lima and L. Rodríguez, Supramolecular gold metallogelators: the key role of metallophilic interactions, *Inorganics*, 2015, **3**, 1–18; (b) A. Pinto, N. Svahn, J. C. Lima and L. Rodríguez, Aggregation induced emission of gold(i) complexes in water or water mixtures, *Dalton Trans.*, 2017, **46**, 11125–11139; (c) N. Mirzadeh, S. H. Privér, A. J. Blake,



- H. Schmidbaur and S. K. Bhargava, Innovative molecular design strategies in materials science following the aurophilicity concept, *Chem. Rev.*, 2020, **120**, 7551–7591; (d) G. Romo-Isilas and R. Gavara, Recent progress on supramolecular luminescent assemblies based on aurophilic interactions in solution, *Inorganics*, 2021, **9**, 1–36.
- 3 (a) J. M. Forward, J. P. Fackler Jr and Z. Assefa, in *Optoelectronic properties of inorganic compounds*, ed. J. P. Fackler Jr, Plenum Press, 1999, ch. 6, pp. 195–229; (b) J. M. López-de-Luzuriaga, in *Modern supramolecular gold chemistry: gold-metal interactions and applications*, ed. A. Laguna, Wiley-VCH, 2008, ch. 6, pp. 347–401.
- 4 (a) D. Blasco, J. M. López-de-Luzuriaga, M. Monge, M. E. Olmos, D. Pascual and M. Rodríguez-Castillo, Cooperative Au(I)⋯Au(I) interactions and hydrogen bonding as origin of a luminescent adeninate hydrogel formed by ultrathin molecular nanowires, *Inorg. Chem.*, 2018, **57**, 3805–3817; (b) D. Blasco, J. M. López-de-Luzuriaga, M. Monge, M. E. Olmos and M. Rodríguez-Castillo, Balancing ionic and H-bonding interactions for the formation of Au(I) hydrometallogels, *Dalton Trans.*, 2019, **48**, 7519–7526; (c) D. Blasco, J. M. López-de-Luzuriaga, M. Monge, M. E. Olmos, D. Pascual and M. Rodríguez-Castillo, Time-dependent molecular rearrangement of [Au( $N^9$ -adeninate)(PTA)] in aqueous solution and aggregation-induced emission in a hydrogel matrix, *Inorg. Chem.*, 2021, **60**, 3667–3676; (d) D. Blasco, J. M. López-de-Luzuriaga, M. Monge, M. E. Olmos, M. Rodríguez-Castillo, H. Amaveda, M. Mora, V. García Sakai and J. A. Martínez-González, *Inorg. Chem. Front.*, 2021, **8**, 3707–3715.
- 5 Y.-A. Lee and R. Eisenberg, Luminescence tribochromism and bright emission in gold(I) thiouracilate complexes, *J. Am. Chem. Soc.*, 2003, **125**, 7778–7779.
- 6 (a) M. F. Fillat, M. C. Gimeno, A. Laguna, E. Latorre, L. Ortego and M. D. Villacampa, Synthesis, structure and bactericide activity of (aminophosphane)gold(I) thiolate complexes, *Eur. J. Inorg. Chem.*, 2011, **9**, 1487–1495; (b) L. A. Mullice, H. J. Mottram, A. J. Hallett and S. J. A. Pope, Gold(I) complexes incorporating emissive mercapto-pteridine ligands: syntheses, X-ray structure, luminescence and preliminary cytotoxic evaluation, *Eur. J. Inorg. Chem.*, 2012, **18**, 3054–3060; (c) H. Goitia, Y. Nieto, M. D. Villacampa, C. Kasper, A. Laguna and M. C. Gimeno, Antitumoral gold and silver complexes with ferrocenyl-amide phosphines, *Organometallics*, 2013, **32**, 6069–6078; (d) L. Ortego, F. Cardoso, S. Martins, M. F. Fillat, A. Laguna, M. Meireles, M. D. Villacampa and M. C. Gimeno, Strong inhibition of thioredoxin reductase by highly cytotoxic gold(I) complexes. DNA binding studies, *J. Inorg. Biochem.*, 2014, **130**, 32–37; (e) E. Abas, R. Pena-Martínez, D. Aguirre-Ramírez, A. Rodríguez-Díez, M. Laguna and L. Grasa, New selective thiolate gold(I) complexes inhibit the proliferation of different human cancer cells and induce apoptosis in primary cultures of mouse colon tumors, *Dalton Trans.*, 2020, **49**, 1915–1927.
- 7 E. Vergara, S. Miranda, F. Mohr, E. Cerrada, E. R. T. Tiekink, P. Romero, A. Mendía and M. Laguna, Gold(I) and palladium(II) thiolate complexes containing water-soluble phosphane ligands, *Eur. J. Inorg. Chem.*, 2007, **18**, 2926–2933.
- 8 R. Usón, A. Laguna, M. Laguna, J. Jiménez, M. P. Gómez, A. Sáinz and P. G. Jones, Gold complexes with heterocyclic thiones as ligands. X-ray structure determination of [Au(C<sub>5</sub>H<sub>5</sub>NS)<sub>2</sub>][ClO<sub>4</sub>], *J. Chem. Soc., Dalton Trans.*, 1990, **11**, 3457–3463.
- 9 J. D. E. T. Wilton-Ely, A. Schier, N. W. Mitzel, S. Nogai and H. Schmidbaur, Hydrogen-bonded networks: (phosphine) gold(I) 4-amino-2-pyrimidine-thiolates, *J. Organomet. Chem.*, 2002, **643–644**, 313–323.
- 10 E. Aguiló, R. Gavara, C. Baucells, M. Guitart, J. C. Lima, J. Llorca and L. Rodríguez, Tuning supramolecular aurophilic structures: the effect of counterion, positive charge and solvent, *Dalton Trans.*, 2016, **45**, 7328–7339.
- 11 M. Preisenberger, A. Schier and H. Schmidbaur, (Phosphine) gold(I) trifluoromethanesulfonates, trifluoroacetates and trichlorothioacetates, *J. Chem. Soc., Dalton Trans.*, 1999, **10**, 1645–1650.
- 12 (a) J. M. Forward, D. Bohmann, J. P. Fackler Jr and R. J. Staples, Luminescence studies of gold(I) thiolates, *Inorg. Chem.*, 1995, **34**, 6330–6336; (b) W. B. Jones, J. Yuan, R. Narayanaswamy, M. A. Young, R. C. Elder, A. E. Bruce and M. R. M. Bruce, Solid state EXAFS and luminescence studies of neutral, dinuclear gold(I) complexes. Gold(I)–gold(I) interactions in the solid state, *Inorg. Chem.*, 1995, **34**, 1996–2001; (c) S. D. Hanna and J. I. Zink, Analysis of the vibronic structure in the emission and absorption spectra of (μ-1,1-dicyanoethylene-2,2-dithiolato-*S,S'*) bis(triphenylphosphine)digold(I) and assignment of the emissive state, *Inorg. Chem.*, 1996, **35**, 297–302.
- 13 H. Schmidbaur and R. Franke, Organogold-chemie. X. Methylgold(I) und gold(I)-halogenide als komplexbildende zentren für trimethylphosphin und trimethylphosphit, *Chem. Ber.*, 1972, **105**, 2985–2997.
- 14 P. Niermeier, L. Wickemeyer, B. Neumann, H.-G. Stämmler, L. Goett-Zink, T. Kottke and N. W. Mitzel, Aurophilicity in action: stepwise formation of dinuclear Au(I) macrocycles with rigid 1,8-dialkynylanthracenes, *Dalton Trans.*, 2019, **48**, 4109–4113.
- 15 (a) L. Hao, R. J. Lachicotte, H. J. Gysling and R. Eisenberg, Novel luminescent Au(I) pyrimidinethiolate dimer having an unusual π-stacking structure, *Inorg. Chem.*, 1999, **38**, 4616–4617; (b) W. J. Hunks, M. C. Jennings and R. J. Puddephatt, Supramolecular gold(I) thiobarbiturate chemistry: combining aurophilicity and hydrogen bonding to make polymers, sheets, and networks, *Inorg. Chem.*, 2002, **41**, 4590–4598; (c) M.-R. Azani, O. Castillo, M. L. Gallego, T. Parella, G. Aullón, O. Crespo, A. Laguna, S. Álvarez, R. Más-Ballesté and F. Zamora, The structural diversity triggered by intermolecular interactions between Au<sup>1</sup>S<sub>2</sub> groups: aurophilia and beyond, *Chem.–Eur. J.*, 2012, **18**, 9965–9976 (and references therein). (d) J. Grote, B. Neumann, H.-G. Stämmler and N. W. Mitzel, Diversity of aggregation motifs in gold(I) dithiocarboxylate complexes, *Dalton Trans.*, 2018, **47**, 4701–4706.

