


 Cite this: *RSC Adv.*, 2022, 12, 12672

Recent advances in the application of magnetic bio-polymers as catalysts in multicomponent reactions

 Zohreh Kheilkordi,^{id a} Ghodsi Mohammadi Ziarani,^{id *a} Fatemeh mohajer,^{id a} Alireaza Badiei^{id b} and Mika Sillanpää^{cde}

Magnetic nanoparticles have attracted significant attention due to their high surface area and superparamagnetic properties. Bio-polymers composed of polysaccharides including alginate, cellulose, glucose, dextrin, chitosan, and starch can be immobilized on magnetic nanoparticles. Bio-polymers can be obtained from natural sources, such as plants, tunicates, algae, and bacteria. Bio-polymers obtained from natural sources have attracted attention due to their various properties including efficient functional groups, non-toxicity, low cost, availability, and biocompatibility. According to the targets of "green chemistry", the application of bio-polymers is effective in reducing pollution. Furthermore, they are excellent agents for the functionalization of magnetic nanoparticles to yield nanomagnetic bio-polymers, which can be applied as recoverable and eco-friendly catalysts in multicomponent reactions.

Received 25th February 2022

Accepted 7th April 2022

DOI: 10.1039/d2ra01294d

rsc.li/rsc-advances

1. Introduction

Among the various magnetic nanoparticles, nano magnetic iron oxide (Fe_3O_4) is very important because of its low cost, easy synthesis, and high magnetic ability. Recently, magnetic nanoparticles have been extensively applied in various fields including drug delivery, sensing, water treatment, removal of heavy metals, and catalysis. However, they are unstable in alkaline and acidic media due to the easy oxidation of their surface area.^{1–8} These drawbacks can be alleviated *via* the modification of Fe_3O_4 nanoparticles with materials such as silanes,^{9,10} activated carbon,¹¹ and biocompatible polymers.^{12,13} Another class of magnetic nanoparticles is ferrite magnetic nanomaterials and hexaferrite (M-type). Ferrite magnetic nanomaterials and hexaferrite have various applications including high chemical strength materials, home appliances, supercapacitors, loudspeakers, electromagnetic wave absorption, and permanent magnets.^{14–18} Overall, due to the properties of ferrite magnetic nanomaterials and hexaferrite (M-type), they

can be used for the adsorption of various metals ions, cationic and anionic dyes from wastewater.^{19–23}

The design and synthesis of biocompatible magnetic nanoparticles are important subjects in green chemistry.²⁴ Bio-polymers including alginate, cellulose, glucose, dextrin, chitosan, and starch are known as polysaccharides, which are present in the carbohydrates in plants, animals, microbes, and algae (Fig. 1).²⁴ These bio-polymers have different properties such as biodegradable nature, biocompatibility, non-toxicity, availability, low cost, and heat resistance.²⁵ They are excellent agents for the functionalization of magnetic nanoparticles to yield nanomagnetic bio-polymers, promoting their longevity, hardness, and strength. These composites have many applications such as drug delivery,^{26–28} chemotherapy,^{29,30} magnetic resonance imaging (MRI) agents,^{31,32} solar cells,³³ chemical sensors,^{34,35} catalysts,³⁶ water treatment,^{37,38} and biomedical sensors.³⁹

In comparison to conventional catalysts, heterogeneous magnetic bio-polymers have various advantages such as non-toxicity, easy separation, and eco-friendly nature. According to the functional groups on the magnetic nanoparticles, the catalysts can be grouped in various categories including, Lewis and Brønsted acids and bases.^{40,41} In continuation of our research,^{42–44} in this review, the importance of nanomagnetic bio-polymers is studied in multicomponent reactions. Multicomponent reactions (MCRs) are essential tools in medicinal and organic chemistry, which have various advantages including simplicity, easy workup, availability, and reduced generation of waste. Hence, the design and application of MCRs for the synthesis of organic compounds are highly important.^{45–50}

^aDepartment of Chemistry, Faculty of Physics and Chemistry, Alzahra University, Tehran, Iran, 1993893979. E-mail: gmohammadi@alzahra.ac.ir; Fax: +98 2188613937; Tel: +98 2188613937

^bSchool of Chemistry, College of Science, University of Tehran, Tehran, Iran

^cDepartment of Chemical Engineering, School of Mining, Metallurgy and Chemical Engineering, University of Johannesburg, P. O. Box 17011, Doornfontein 2028, South Africa. E-mail: Mika.Sillanpaa@uef.fi

^dDepartment of Applied Physics, Faculty of Science and Technology, Universiti Kebangsaan Malaysia, 43600 Bangi, Selangor, Malaysia

^eInternational Research Centre of Nanotechnology for Himalayan Sustainability (IRCNS), Shoolini University, Solan, 173212, Himachal Pradesh, India






Fig. 1 Various bio-polymers.

2. Synthesis of various magnetic bio polymers

2.1. Magnetic bio-polymers based on cellulose

2.1.1. Synthesis and application of Fe_3O_4 /cellulose/Co-MOF nanocomposite. Initially, Fe_3O_4 nanoparticles **4** were modified with cellulose **5** using urea **6**/NaOH **7** to provide Fe_3O_4 /cellulose **8**, which was reacted with $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ **9**, terephthalic acid **10**, and imidazole (IM) **11** in DMF to form Fe_3O_4 /cellulose/Co-MOF nanocomposite **12** (Scheme 1).⁵¹

Fe_3O_4 /cellulose/Co-MOF **12** has two sites including Lewis acidic sites (Co^{2+}) and basic sites (IM), which were used in the Knoevenagel condensation reaction of aromatic aldehydes **13** with malononitrile **14** under solvent-free conditions (Scheme 2). This catalyst was reused five times without a decrease its catalytic activity.⁵¹

2.1.2. Synthesis and application of Fe_3O_4 @NCs/Sb(v). Initially, raw cotton was converted to nano-cellulose (NCs) **5** in the presence of NaOH **7**, NaClO **16**, and H_2SO_4 **17** at 80 °C. Then, Fe_3O_4 was functionalized with nano-cellulose (NCs) **5**, providing Fe_3O_4 @NCs **8**. In the next step, SbCl_5 was mixed with the reaction mixture in chloroform to provide Fe_3O_4 @NCs/Sb(v) **18** (Scheme 3).⁵²

Fe_3O_4 @NCs/Sb(v) was used as a Lewis acid for the activation of carbonyl groups, which was investigated in the synthesis of 4*H*-pyrimido[2,1-*b*]benzothiazoles **22** *via* the three-component reaction of aldehydes **19**, 2-aminobenzothiazole **20**, and ethyl-acetoacetate **21** under solvent-free conditions at 90 °C (Scheme 4). This catalyst was used five times without loss in its catalytic activity, which was compared with Fe_3O_4 with 39% yield in 3 h.⁵²

2.1.3. Synthesis and application of Fe_3O_4 @NFC@Co(II). Fe_3O_4 MNPs were synthesized *via* the reaction of $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ and $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ in the presence of NH_4OH solution at 80 °C under an N_2 atmosphere. The Fe_3O_4 nanoparticles were dispersed in H_2O , and then nanofiber cellulose (NFC) **24** was

added to the reaction mixture at room temperature to obtain Fe_3O_4 @NFC **25** precipitate, which was reacted with an ethanolic solution of cobalt(II) acetate to form Fe_3O_4 @NFC@Co(II) **26** (Scheme 5).⁵³

Its catalytic activity was useful for the synthesis of 4*H*-pyrans *via* the multicomponent reaction of aldehydes, ethyl-acetoacetate, and malononitrile in H_2O (Scheme 6).⁵³


Also, the catalytic activity of **26** was tested for the synthesis of pyranopyrazole derivatives **29** *via* the four-component reaction of hydrazine hydrate **28**, ethyl acetoacetate **21**, benzaldehyde **19**, and malononitrile **14** in H_2O (Scheme 7). The metal ions on the catalyst surface act as Lewis acids, which were activated by the malononitrile and carbonyl groups. Also, the catalyst was used five times in the model reaction without a reduction in activity.⁵³

2.1.4. Synthesis and application of cellulose@pumice. Initially, the microcrystalline cellulose was mixed with a solution of NaOH **7** and urea **6** in H_2O , and then was cooled in an ice bath at 8 °C to form a gel solution, which was mixed with pumice powder **32** and stirred for 24 h to obtain cellulose@pumice **33** (Scheme 8).⁵⁴

Cellulose@pumice as an acidic catalyst activated carbonyl groups in the synthesis of 2,4,5-triarylimidazoles **36** through the reaction of benzaldehyde **19** and ammonium acetate **35** in EtOH under ultrasonic irradiation (Scheme 9). In the reusability test, this catalyst was used ten times without a reduction in activity.⁵⁴

2.1.5. The synthesis and application of (Fe_3O_4 @NFC@NSalophCu)CO₂H. Nanofiber cellulose **37** was functionalized with Fe_3O_4 *via* the sol-gel method to give Fe_3O_4 @NFC nanoparticles **39**, which were functionalized with (3-aminopropyl)triethoxysilane (APTES) **40** to obtain Fe_3O_4 @NFC@APTES **41**. The reaction of salicylaldehyde **42**, paraformaldehyde **43**, and HCl solution under reflux conditions provided 5-chloromethyl salicylaldehyde **44**, which was reacted with 3,5-diaminobenzoic acid **45** in CH_2Cl_2 at room temperature to give the Schiff base 3,5-bis((*E*)-5-(chloromethyl)-2-





Scheme 1 Synthesis of Fe_3O_4 /cellulose/Co-MOF nanocomposite 12.

hydroxybenzylidene)amino) benzoic acid ((5-Cl-Saloph) CO_2H) 46, followed by reaction with copper acetate in EtOH at room temperature to obtain complex [(5-Cl-Saloph) Cu(II)] CO_2H 47. Finally, the reaction of [(5-Cl-Saloph) Cu(II)] CO_2H complex 47 and Fe_3O_4 @NFC@APTES 41 at 70 °C for 24 h gave (Fe_3O_4 @NFC@NSalophCu) CO_2H 48 (Scheme 10).⁵⁵

(Fe_3O_4 @NFC@NSalophCu) CO_2H 48 was tested in the synthesis of 5-substituted-1H-tetrazole 51 *via* the multicomponent reaction of various aldehydes 19, hydroxylamine 49, and sodium azide 50 (Scheme 11), and also in the synthesis of 1-substituted-1H-tetrazoles 54 *via* the multicomponent reaction of aniline 52, triethyl orthoformate 53, and sodium azide 50 (Scheme 12). This catalyst was used in the click reaction four times without a decrease in its activity. In this catalyst, copper metal plays a vital role in the click reactions.⁵⁵


2.1.6. Synthesis and application of Fe_3O_4 @NFC@NNSM-Mn(III). Fe_3O_4 nanoparticles were functionalized with NFC nanospheres to prepare Fe_3O_4 @NFC 39, which was dispersed in toluene, and then 3-chloropropyl-trimethoxy silane 55 was added to the reaction mixture under N_2 gas and reflux conditions to obtain Fe_3O_4 @NFC-Cl 56, followed by reaction with *o*-phenylenediamine 54 in CH_2Cl_2 under reflux conditions to give Fe_3O_4 @NFC@NN 57. Then, 5-(chloromethyl)-2-hydroxy benzaldehyde 58 was reacted with Fe_3O_4 @NFC@NN 57 to form Fe_3O_4 @NFC@NNS 59, which was complexed with

$\text{Mn}(\text{OAc})_3 \cdot 2\text{H}_2\text{O}$ 60 in EtOH to prepare Fe_3O_4 @NFC@NNS-Mn 61, followed by reaction with melamine 62 in the presence of triethylamine in MeOH to generate Fe_3O_4 @NFC@NNSM-Mn(III) 63 (Scheme 13).⁵⁶

The activity of Fe_3O_4 @NFC@NNSM-Mn(III) 63 was tested for the synthesis of xanthenes 65 *via* the pseudo-three-component reaction of aldehydes 19 and dimedone 64 in EtOH at 45 °C (Scheme 14). The manganese metal on the surface of Fe_3O_4 @NFC@NNSM-Mn(III) acts as a Lewis acid to activate the carbonyl groups. This catalyst was used five times without a decrease in its activity.⁵⁶

2.1.7. Synthesis and application of Fe_3O_4 @NFC@ONSM-Ni(II). Initially, Fe_3O_4 @NFC 39 was functionalized with 3-chloropropyl-trimethoxy silane 55 to obtain Fe_3O_4 @NFC@CPTMS 56. Subsequently, 2-hydroxy 4-chloromethyl benzaldehyde 44 was prepared *via* the reaction of salicylaldehyde 42, paraformaldehyde 43, and HCl 37% in the presence of H_2SO_4 as a catalyst at 70 °C for 20 h. In the next step, the Schiff base ligand was synthesized *via* the reaction of 2-aminophenol 66 and 5-chloromethylsalicylaldehyde 67 in dichloromethane at 40 °C for 3 h. Then, Fe_3O_4 @NFC@ONS 68 was obtained through the reaction of 4-(chloromethyl)-2-(((2-hydroxyphenyl)imino)methyl) phenol 67 and Fe_3O_4 @NFC@CPTMS 56 in the presence of triethylamine in acetonitrile under reflux conditions. In the next step, Fe_3O_4 @NFC@ONS 68 was reacted with $\text{Ni}(\text{OAc})_2$






Scheme 2 Knoevenagel condensation in the presence of Fe₃O₄/cellulose/Co-MOF 12.

in EtOH at room temperature for 12 h to obtain Fe₃O₄@NFC@ONS-Ni(II) **69**. Finally, Fe₃O₄@NFC@ONSM-Ni(II) **70** was synthesized as a nanocatalyst *via* the reaction of Fe₃O₄@NFC@ONS-Ni(II) **69** and melamine **62** in the presence of triethylamine in the MeOH under reflux conditions and N₂ gas for 12 h (Scheme 15).⁵⁷

This catalyst was used in the synthesis of polyhydroquinolines **72** through the Hantzsch reaction among benzaldehydes **19**, dimedone **64**, ethyl acetoacetate **21**, and ammonium acetate **71** (Scheme 16).⁵⁷

Also, Bagherzade *et al.* applied this catalyst in the synthesis of 1,4-dihydropyridine **72** *via* the multicomponent reaction of aldehydes **19**, ethyl acetoacetate **21**, and ammonium acetate **71** (Scheme 17). The carbonyl groups in the multi-component reaction were activated in the presence of nickel metal on the surface of Fe₃O₄@NFC@ONSM-Ni(II) as a Lewis acid. Also, this catalyst was tested 6 times without loss in its activity.⁵⁷

2.1.8. Synthesis and application of cell-LA-TEA⁺/Fe₃O₄. Initially, cellulose **5** was reacted with tosyl chloride **74** in the




Scheme 4 Synthesis of 4*H*-pyrimido[2,1-*b*]benzothiazole derivatives **22**.

presence of Et₃N to form cell-tosyl **75**, which was reacted with lactic acid **76** to produce cell-LA **77**, followed by reaction with triethanolamine **78** to prepare cell-LA-TEA⁺ **79**. Finally, cell-LA-TEA⁺ **79** was magnetized *via* the reaction of FeCl₃·6H₂O, FeCl₂·4H₂O, and ammonium solution in aqueous media to form cell-LA-TEA⁺/Fe₃O₄ **80** (Scheme 18).⁵⁸

Cell-LA-TEA⁺/Fe₃O₄ was used as a catalyst for the regioselective synthesis of pyrazolo quinolones **82** *via* the three-component reaction of dimedone **64**, 5-amino pyrazolone **81**, and aromatic aldehydes **19** in EtOH/H₂O under ultrasonic irradiation (Scheme 19). The catalyst was used with high stability in 7 cycles without loss in its activity.⁵⁸




2.1.9. Synthesis and application of Fe₃O₄@nano-cellulose-OPO₃H. Initially, nano-cellulose **5** was prepared from cotton. Then, Fe₃O₄@nano-cellulose (Fe₃O₄@NCS) **8** was obtained through the reaction of nano-cellulose solution in acetic acid with FeCl₃·6H₂O, FeCl₂·4H₂O, and ammonium hydroxide at 80 °C. Finally, Fe₃O₄@NCS were immobilized with P₄O₁₀ at room temperature under grinding conditions to produce Fe₃O₄@NCS-PA **83** (Scheme 20).⁵⁹

2,3-Dihydroquinazolin-4(1*H*)-ones **85** were prepared *via* the condensation reaction of 2-aminobenzamide **84** and aldehydes **19** in the presence of Fe₃O₄@NCS-PA **83** as a Brønsted acid in H₂O: EtOH under reflux conditions (Scheme 21). The main




Scheme 3 Synthesis of Fe₃O₄@NCS/Sb(v).



Scheme 5 Synthesis of $\text{Fe}_3\text{O}_4@\text{NFC}@\text{Co(II)}$ 26.Scheme 6 Synthesis of 4H-pyrans 27 in the presence of $\text{Fe}_3\text{O}_4@\text{NFC}@\text{Co(II)}$.

Scheme 9 Synthesis of 2,4,5-triarylimidazoles derivatives 36.

Scheme 7 Synthesis of pyranopyrazole derivatives 29 using $\text{Fe}_3\text{O}_4@\text{NFC}@\text{Co(II)}$.

advantages of this method are its excellent yields, simple workup, and eco-friendly catalyst. This reaction was accomplished in H_2O : EtOH under reflux conditions in the presence of Fe_3O_4 with 60% yield; however, $\text{Fe}_3\text{O}_4@\text{NCS-PA}$ performed better than Fe_3O_4 in this reaction.⁵⁹


2.1.10. Synthesis and application of $\text{Fe}_3\text{O}_4@\text{NCS}/\text{Cu(II)}$. Fe_3O_4 was functionalized with nano-cellulose 5 to obtain

$\text{Fe}_3\text{O}_4@\text{NCS}$ 8, which was added to NaOH solution to give $\text{Fe}_3\text{O}_4@\text{NCS}$ 8, followed by reaction with CuCl_2 to provide $\text{Fe}_3\text{O}_4@\text{NCS}/\text{Cu(II)}$ 86 (Scheme 22).⁶⁰

$\text{Fe}_3\text{O}_4@\text{NCS}/\text{Cu(II)}$ as a Lewis acid activated the carbonyl groups of the starting materials by copper metal in the synthesis of indenopyrido[2,3-*d*]pyrimidines 89 through the three-component reaction of 6-amino-2-(methylthio)pyrimidin-4(3*H*)-one 88, 1,3-indanedione 87 and aldehydes 19 in EtOH (Scheme 23). The activity of the catalyst was preserved after four runs.⁶⁰




2.1.11. Synthesis and application of $\text{Fe}_3\text{O}_4@\text{nano-cellulose}/\text{Cu(II)}$. The reaction of nano-cellulose 5, $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$, and NH_4OH at 80 °C gave $\text{Fe}_3\text{O}_4@\text{nano-cellulose}$ 8, which was reacted with CuCl_2 using sodium hydroxide at room temperature to obtain $\text{Fe}_3\text{O}_4@\text{nano-cellulose}/\text{Cu(II)}$ 90 (Scheme 24).⁶¹

Cu(II) in $\text{Fe}_3\text{O}_4@\text{nanocellulose}/\text{Cu(II)}$, as a Lewis acid, activated the carbonyl groups in the three-component reaction of



Scheme 8 Synthesis of cellulose@pumice 33.




Scheme 10 Synthesis of $(\text{Fe}_3\text{O}_4@\text{NFC}@\text{NSalophCu})\text{CO}_2\text{H}$.Scheme 11 Synthesis of 5-substituted-1*H*-tetrazole 47 using $(\text{Fe}_3\text{O}_4@\text{NFC}@\text{NSalophCu})\text{CO}_2\text{H}$.Scheme 12 Synthesis of 1-substituted-1*H*-tetrazoles using $(\text{Fe}_3\text{O}_4@\text{NFC}@\text{NSalophCu})\text{CO}_2\text{H}$.

aromatic aldehydes **19**, 2-aminobenzothiazole **20**, and ethyl acetoacetate **21** for the synthesis of 4*H*-pyrimido[2,1-*b*]benzothiazoles **22** (Scheme 25). The catalyst activity of $\text{Fe}_3\text{O}_4@\text{nano-cellulose}/\text{Cu}(\text{II})$ was preserved after four runs. The yield of this reaction in the presence of Fe_3O_4 as a catalyst after 3 h was reported to be about 37%. Therefore, $\text{Fe}_3\text{O}_4@\text{nano-cellulose}/\text{Cu}(\text{II})$ is more active than Fe_3O_4 .⁶¹

2.1.12. Synthesis and application of $\text{Fe}_3\text{O}_4@\text{NFC-ImSalophCu}(\text{II})$. Initially, imidazole **11** was treated with 3-

chloropropyl-trimethoxy silane **55** in toluene to produce imidazole-propyl-trimethoxy silane **91**, which was immobilized on $\text{Fe}_3\text{O}_4@\text{NFC}$ **39** using Et_3N as a catalyst in dry toluene to give $\text{Fe}_3\text{O}_4@\text{NFC-Im}$ **92**. The reaction of salicylaldehyde **42** and paraformaldehyde **43** in the presence of $\text{HCl}/\text{H}_2\text{SO}_4$ gave 5-(chloromethyl)-2-hydroxybenzaldehyde **44**, which was reacted with 1,2-phenylenediamine **93** in dichloromethane under reflux




Scheme 13 Synthesis of $\text{Fe}_3\text{O}_4@NFC@NNSM-\text{Mn}(\text{III})$.

conditions to produce *N,N*-bis(5-chloromethylsalicylidene)-1,2-phenylenediamine **94**, followed by reaction with $\text{Cu}(\text{OAc})_2$ in EtOH at room temperature to prepare 5-Cl-Salophen-Cu(II) **95**. Finally, $\text{Fe}_3\text{O}_4@NFC-\text{ImSalophCu}(\text{II})$ **96** was synthesized *via* the

reaction of $\text{Fe}_3\text{O}_4@NFC-\text{Im}$ **92** and 5-Cl-Salophen-Cu(II) **95** in toluene under reflux conditions (Scheme 26).⁶²

The copper of $\text{Fe}_3\text{O}_4@NFC-\text{ImSalophCu}$ **96** was applied in the click reaction of phenacyl bromides **97**, sodium azide **90**,





Scheme 14 Synthesis of xanthenes **65** in the presence of $\text{Fe}_3\text{O}_4@\text{NFC}@\text{NNSM}-\text{Mn}(\text{III})$.

and alkynes **98** in H_2O to synthesize 1,2,3-triazoles **99** (Scheme 27). The reusability of this catalyst was tested in the click reaction four times without loss in its activity.⁶²

2.1.13. Synthesis and application of $\text{Fe}_3\text{O}_4@\text{walnut shell}/\text{Cu}(\text{II})$. Nanomagnetic $\text{Fe}_3\text{O}_4@\text{walnut shell}/\text{Cu}(\text{II})$ was prepared by Mirjalili's research group. Nanomagnetic $\text{Fe}_3\text{O}_4@\text{walnut shell}/\text{Cu}(\text{II})$ **100** was prepared *via* the reaction of dried powdered walnut shell with NaOH, hypochlorite solution, and sulfuric acid aqueous to afford a nano walnut shell, followed by reaction with CH_3COOH , $\text{FeCl}_2 \cdot 6\text{H}_2\text{O}$ **1**, $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}_2$, and NH_4OH to generate nanomagnetic $\text{Fe}_3\text{O}_4@\text{walnut shell}$ **8**, which was modified by $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}/\text{NaOH}$ to produce nanomagnetic $\text{Fe}_3\text{O}_4@\text{walnut shell}/\text{Cu}(\text{II})$ **100** (Scheme 28).⁶³

Its catalytic activity was explored using 2-aryl/alkyl-2,3-dihydro-1*H*-naphtho[1,2-*e*][1,3]oxazines **102** or **104** or **106** *via* the pseudo-three-component reaction of β -naphthol **101** or α -naphthol **103** or phenol derivatives **105**, formaldehyde **52**, and various amines **43** (Scheme 29). The catalytic activity of nano- $\text{Fe}_3\text{O}_4@\text{walnut shell}/\text{Cu}$ did not decrease after five-times use. The copper metal on the nano- $\text{Fe}_3\text{O}_4@\text{walnut shell}/\text{Cu}(\text{II})$ increased the reaction rate *via* interaction with the carbonyl group of the starting materials.⁶³

2.2. Magnetic bio-polymers based on dextrin

2.2.1. Synthesis and application of magnetic dextrin nanocomposite. Dextrin **107** is a water-soluble polysaccharide obtained *via* the hydrolysis of starch and glycogen. Magnetic dextrin nanocomposite **108** was prepared *via* the addition of dextrin **107** to a solution of $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$, and ammonium hydroxide at 90°C under an N_2 atmosphere *via* the co-precipitation method (Scheme 30).⁶⁴

The magnetic dextrin was tested as a catalyst in the synthesis of polyhydroquinolines *via* four-component reactions of aromatic aldehydes **19**, ethyl acetoacetate **21**, dimedone **61**, ammonium acetate **71** in EtOH under reflux conditions (Scheme 31). The yield of the products did not decrease after five runs. This reaction was performed in the presence of dextrin in ethanol in 28% yield, and thus magnetic dextrin is better than dextrin to catalyze this reaction.⁶⁴

2.2.2. Synthesis and application of magnetized dextrin. Magnetized dextrin **72** was obtained *via* the reaction of $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$, dextrin **71**, and NH_4OH in H_2O at 90°C under a nitrogen atmosphere (Scheme 32).⁶⁵

Maleki *et al.* studied the catalytic activity of magnetized dextrin **29** for the synthesis of dihydropyrano[2,3-*c*]pyrazoles **29** through the reaction of hydrazine hydrate **28**, ethyl acetoacetate **21**, aromatic aldehydes **19**, and malononitrile **14** under reflux conditions in EtOH (Scheme 33). This catalyst was used for five runs without a decrease in its catalytic activity.⁶⁵

2.2.3. Synthesis and application of FND-Ti(IV). $\text{Fe}_3\text{O}_4@\text{nano-dextrin}$ **108** was prepared through the reaction of nano-dextrin **107**, $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$, and ammonia solution in H_2O at 80°C . $\text{Fe}_3\text{O}_4@\text{nano-dextrin}$ **108** was coated with TiCl_4 in CH_2Cl_2 to prepare FND-Ti(IV) **109** (Scheme 34).⁶⁶

Its catalytic activity as a Lewis acid was investigated in the synthesis of 2,3-dihydroquinazolin-4(1*H*)-ones **85** *via* the condensation reaction of 2-aminobenzamide **84** and aldehydes **19** under mild conditions (Scheme 35). This catalyst was used five times without loss in its catalytic activity.⁶⁶

2.3. Magnetic bio-polymers based on starch

2.3.1. Synthesis and application of magnetic $\text{Ag}/\text{Fe}_3\text{O}_4@\text{starch}$ nanocatalyst. To aqueous starch solution **110**, citric acid **111** and sodium hypophosphite **112** were added and refluxed to give the precipitate crude product, which was crushed and dried to give cross-linked starch **113**, followed by dissolving in H_2O to produce gelatinized starch **114**. The obtained gelatinized starch was reacted with $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, and $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ in H_2O at room temperature, and then mixed with NH_3 dropwise to give the $\text{Fe}_3\text{O}_4@\text{starch}$ nanocatalyst, which was treated with AgNO_3 (aq) to generate the magnetic $\text{Ag}/\text{Fe}_3\text{O}_4@\text{starch}$ **115** nanocatalyst (Scheme 36).⁶⁷


The catalytic activity of $\text{Ag}/\text{Fe}_3\text{O}_4@\text{starch}$ as Lewis acid **115** was evaluated in the one-pot reaction of benzaldehydes **19**, malononitrile **14**, and dimedone **64** in EtOH for the synthesis of 4*H*-pyran **116** (Scheme 37). Also, the magnetic nanocatalyst was reused five times with no loss in its activities.⁶⁷

2.3.2. Synthesis and application of magnetic $\text{CuFe}_2\text{O}_4@\text{starch}$. To obtain $\text{CuFe}_2\text{O}_4@\text{starch}$ **122**, $\text{Cu}(\text{NO}_3)_2$ **117** was reacted with $\text{Fe}(\text{NO}_3)_3$ **118** using sodium hydroxide in H_2O to give CuFe_2O_4 nanoparticles **121**, followed by reaction with starch to obtain $\text{CuFe}_2\text{O}_4@\text{starch}$ **122**. Its catalytic activity was tested in the synthesis of 4*H*-chromene **125** or **126** *via* the three-component reaction of various aldehydes **19**, malononitrile **14**, 2-hydroxy-1,4-naphthoquinone **123**, or 4-hydroxycoumarin **124** (Scheme 38).⁶⁸

In another attempt, 2-amino-5-oxo-5,6,7,8-tetrahydro-4*H*-benzo[*b*]pyrans **27** or **116** were synthesized *via* the reaction of aldehydes **19**, malononitrile **14**, and enolizable C-H-activated acidic compounds, including dimedone **64** and ethyl acetoacetate **21**, in the presence of $\text{CuFe}_2\text{O}_4@\text{starch}$ **122** as a Lewis acid in EtOH. The reaction rate for aldehydes with electron-withdrawing groups was faster than that with electron-donating groups (Scheme 39 and 40), respectively. This catalyst was used in six runs without a decrease in its activity.⁶⁸

2.3.3. Synthesis and application of magnetic starch/SPION@ SO_3H . Superparamagnetic iron oxide nanoparticles (SPION) **127** were synthesized *via* the reaction of Fe^{2+} , Fe^{3+} , and ammonia in aqueous media. Then, SPION **127** was coated with




Scheme 15 Synthesis of $\text{Fe}_3\text{O}_4@\text{NFC@ONSM-Ni(II)}$.

tetraethyl orthosilicate (TEOS) to give SPION@SiO_2 **128**, which was reacted with starch **110** to give magnetic starch, followed by reaction with allyltrimethoxysilane **130** to prepare allyl-functionalized magnetic starch **131**. Finally, starch/ $\text{SPION@SO}_3\text{H}$ **133** was synthesized *via* the polymerization of


allyl-functionalized magnetic starch **131** and 4-styrenesulfonic acid **132** (Scheme 41).⁶⁹

Starch/ $\text{SPION@SO}_3\text{H}$ **133** as a Brønsted acid (SO_3H) activated the carbonyl groups in the multicomponent reaction of 4-hydroxycoumarin **124**, benzaldehydes **19**, dimedone **64**, and






Scheme 16 Synthesis of polyhydroquinolines **72** in the presence of Fe₃O₄@NFC@ONSM-Ni(II).



Scheme 19 Synthesis of pyrazolo quinolones **82** in the presence of Cell-LA-TEA⁺/Fe₃O₄.



Scheme 17 Synthesis of 1,4-dihydropyridine **73** in the presence of Fe₃O₄@NFC@ONSM-Ni(II).


ammonium acetate **71** in the synthesis of chromeno[4,3-*b*]quinoline-6,8(9*H*)-dione derivatives **134** (Scheme 42). This catalyst was applied ten times without any loss in its activity.⁶⁹

2.3.4. Synthesis and application of magnetic Fe₃O₄@GOTfOH/Ag/St-PEG-AcA. Initially, through the Hummers' method, graphite **135** was treated with H₂SO₄, KMnO₄, and H₂O to give GO **136**, which was treated with FeCl₃, FeCl₂, and ammonium solution at 80 °C to achieve Fe₃O₄@GO **137**, followed by reaction with trifluoro methanesulfonic acid in CH₂CH₂ to give Fe₃O₄@GOTfOH **138**. In the next step, starch **139** was dissolved in water at 80 °C. Subsequently, *N,N*-

methylene acrylene acrylamide (MBA) **140** was dissolved in water. Then, the above-mentioned two mixtures were mixed to obtain a homogeneous viscous mixture. Then, a certain amount of acrylic acid **141** and PEG-poly **142** was added to the reaction mixture. Then, ammonium persulfate (APS) **143** solution was added to the reaction mixture until a hydrogel was obtained. The above-mentioned homogeneous solution, AgNP **144** colloidal solution and Fe₃O₄@GOTfOH **138** were mixed to obtain Fe₃O₄@GOTfOH/Ag/St-PEG-AcA **146** (Scheme 43).⁷⁰



The catalytic activity of Fe₃O₄@GOTfOH/Ag/St-PEG-AcA **146** was examined in the synthesis of 2,4,6-triarylpyridines **137** through the pseudo-three-component reaction of aryl aldehydes **19**, acetophenone **147** and ammonium acetate **71** (Scheme 44). According to the catalyst structure, the carbonyl groups were activated *via* interaction with the Brønsted acid site and Lewis acid of Fe³⁺. Also, the catalytic activity of **146** did not decrease after 10 runs.⁷⁰

2.3.5. Synthesis and application of magnetic γ-Fe₂O₃@starch-*n*-butyl SO₃H. Fe₃O₄ nanoparticles **4** were synthesized *via* the reaction of FeCl₂·4H₂O **2** and FeCl₃·6H₂O **1** and NH₄OH solution in H₂O an under argon atmosphere at room




Scheme 18 Synthesis of Cell-LA-TEA⁺/Fe₃O₄.



Scheme 20 Synthesis of Fe₃O₄@NCS-PA.R = H, 4-NO₂, 3-NO₂, 2-NO₂, 4-OH, 2-Cl, 4-Cl, 2,4-(Cl)₂, 2,4-(OMe)₂, 4-N(Me)₂




Scheme 21 Synthesis of 2,3-dihydroquinazolin-4(1H)-ones.


Scheme 22 Synthesis of Fe₃O₄@NCS/Cu(II) 86.

temperature. Then, γ -Fe₂O₃ was synthesized using Fe₃O₄ at 250 °C. In the next step, γ -Fe₂O₃ was coated with starch at room temperature to obtain γ -Fe₂O₃@starch **150**, followed by reaction with 1,4-butane sultone **151** in dry toluene under reflux conditions to produce γ -Fe₂O₃@starch-*n*-butylSO₃H **152** nanoparticles (Scheme 45).⁷¹


γ -Fe₂O₃@starch-*n*-butylSO₃H **152** as Brønsted acid activated the carbonyl groups in the multicomponent reactions of



Scheme 23 Synthesis of indenopyrido [2,3-*d*] pyrimidines in the presence of Fe₃O₄@NCs/Cu(II).Scheme 24 Synthesis of Fe₃O₄@nano-cellulose/Cu(II).Scheme 25 Synthesis of 4*H*-pyrimido[2,1-*b*]benzothiazole derivatives 22 using Fe₃O₄@nano-cellulose/Cu(II).



Scheme 26 Synthesis of 4H-pyrimido[2,1-*b*]benzothiazole derivatives using $\text{Fe}_3\text{O}_4@\text{NFC-ImSalophCu(II)}$ **96**.



Scheme 27 Synthesis of 1,2,3-triazoles **99** using $\text{Fe}_3\text{O}_4@\text{NFC-ImSalophCu}$.




aldehydes **19**, dimedone **64**, and 2-aminobenzimidazole **153** or phthalhydrazide **154** to synthesize tetrahydrobenzimidazo[2,1-*b*]quinazolin-1(2*H*)-ones **155** or 2*H*-indazolo[2,1-*b*]phthalazine-trione **156** (Scheme 46). This catalyst was used seven times without loss in any of its activities.⁷¹

2.4. Magnetic bio-polymers based on alginate


2.4.1. Synthesis and application of $\text{Fe}_3\text{O}_4@\text{Alg@CPTMS@Arg}$. Alginate **157** was immobilized on Fe_3O_4 **4** via

the co-precipitation method. Initially, $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ **1**, $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ **2**, and sodium alginate **157** were dissolved in H_2O under a nitrogen atmosphere. Then, an ammonia solution was added to this mixture to give $\text{Fe}_3\text{O}_4@\text{Alg}$ nanoparticles **158**, which were functionalized with 3-chloropropyltrimethoxysilane **55** to prepare $\text{Fe}_3\text{O}_4@\text{Alg@CPTMS}$ **159**, followed by reaction with *L*-arginin **160** using trimethylamine in EtOH for 48 h to give $\text{Fe}_3\text{O}_4@\text{Alg@CPTMS@Arg}$ **161** (Scheme 47).⁷²




Scheme 28 Synthesis of nano-Fe₃O₄@walnut shell/Cu.Scheme 29 Synthesis of 2-aryl/alkyl-2,3-dihydro-1H-naphtho[1,2-e][1,3]oxazines 102 or 104 or 106 using nano-Fe₃O₄@walnut shell/Cu(II).

Scheme 30 Synthesis of magnetic dextrin.




Scheme 31 Synthesis of polyhydroquinolines 72 in the presence of magnetic dextrin.





Scheme 32 Synthesis of magnetized dextrin.

Scheme 33 Synthesis of dihydropyrano[2,3-c]pyrazoles **29** using magnetized dextrin.



Subsequently, Fe₃O₄@Alg@CPTMS@Arg, which has two acidic and basic functional sites, activated the carbonyl groups in the synthesis of 2,4,5-triarylimidazoles through the reaction of ammonium acetate, aldehydes, and benzil in EtOH under reflux conditions (Scheme 48). The recyclability of the catalyst




was tested 7 times using the model reaction without loss in any of its activities. When Fe₃O₄ was used as the catalyst, the yield of this reaction was about 65%.⁷²

2.4.2. Synthesis and application of Fe₃O₄@Alg@CPTMS@Arg. The reaction of Fe₃O₄@Alg **165** and 3-chloropropyltrimethoxysilane (CPTMS) **55** in toluene under reflux conditions and nitrogen atmosphere gave Fe₃O₄@Alg@CPTMS **166**, which was reacted with arginine **167** in the presence of trimethylamine in dry toluene to provide Fe₃O₄@Alg@CPTMS@Arg nanocomposites **168** (Scheme 49).⁷³

The activity of Fe₃O₄@Alg@CPTMS@Arg was tested as a catalyst in the synthesis of 2,4,5-triarylimidazoles **36** via the reaction of ammonium acetate **71**, aldehyde derivatives **19**, and benzil **34** in EtOH (Scheme 50). Its catalytic activity did not decrease after seven uses. It has two functional groups including a Lewis base (NH₂) and Brønsted acidic (COOH), which catalyzed the synthesis of 2,4,5-triarylimidazoles.⁷³

2.4.3. Synthesis and application of Fe₃O₄@FU. Fe₃O₄@FU **170** was prepared via the reaction of fucoidan powder **169**,

Scheme 34 Synthesis of FND-Ti(IV) **109**.Scheme 35 Synthesis of 2,3-dihydroquinazolin-4(1H)-ones **85** using Fe₃O₄@nano-dextrin/Ti(IV).

Scheme 36 Synthesis of Ag/Fe₃O₄@starch 115.Scheme 37 Synthesis of 4*H*-pyran 116 in the presence of Ag/Fe₃O₄@starch.Scheme 39 Synthesis of 4*H*-chromenes using CuFe₂O₄@starch.

FeCl₂·4H₂O 2, and FeCl₃·6H₂O 1 in aqueous ammonia solution (25%) in distilled water under a nitrogen atmosphere at 80 °C (Scheme 51).⁷⁴


The activity of Fe₃O₄@FU was evaluated as a catalyst in the synthesis of *tri*- and *tetra*-substituted imidazoles 36 or 171 *via* three- and four-component reactions of benzil 34, aldehydes 19, NH₄OAc 71, and amine 52 under reflux conditions in EtOH (Scheme 52), respectively. The catalyst was used six times in the model reaction without loss in any of its activities. This reaction was accomplished in ethanol under reflux conditions in the presence of Fe₃O₄ as a catalyst after 40 min with 55% yield. The carbonyl groups were activated *via* hydrogen bonding with Fe₃O₄@FU as a catalyst.⁷⁴


2.5. Magnetic bio-polymers based on glucose

2.5.1. Synthesis and application of Fe₃O₄@C@ONa.

Initially, FeCl₃·6H₂O solution, CO(NH₂)₂, and glucose were added to ethylene glycol 172 to produce a black powder of carbon-coated magnetic nanoparticles (CCMNPs: Fe₃O₄@C) 173, followed by reaction with NaOH solution to obtain basic carbon-coated magnetic nanoparticles (BCCMNPs: Fe₃O₄@C@ONa) 174 (Scheme 53).⁷⁵

Subsequently, the catalytic activity of Fe₃O₄@C@ONa was tested for the synthesis of 4*H*-chromene derivatives 174 *via* the reaction of salicylaldehyde 42, dimedone 64, and β-naphthol 101 in water at 60 °C (Scheme 54). Also, the catalyst was used five times in the model reaction without loss in any of its

Scheme 38 Synthesis of CuFe₂O₄@starch.



Scheme 40 Synthesis of 2-amino-5-oxo-5,6,7,8-tetrahydro-4H-benzo[b]pyrans **116** or **27**.


activities. This catalyst has two functional groups, including Fe^{3+} as a Lewis acid and oxygen group as a Lewis base, which increased the reaction rate.⁷⁵

2.6. Magnetic bio-polymers based on chitosan

2.6.1. Synthesis and application of CSSNH@Arg. Chitosan-silica sulfate nanohybrid (CSSNH@Arg) **178** was synthesized *via*



the reaction of chitosan **176** and silica sulfuric acid (SSA) **177** under ultrasonic irradiation (Scheme 55).⁷⁶

A green method for the synthesis of 3,4-dihydropyrimidine-2(1H)-one/thione derivatives **179** was described by Behrouz and co-workers *via* the Biginelli reaction of (thio)urea **23** or urea **6**, methyl acetoacetate **21**, and aldehydes **19** using CSSNH@Arg **178** under solvent-free conditions (Scheme 56).



Scheme 41 Synthesis of starch/SPION@SO₃H.






Scheme 42 Synthesis of chromeno[4,3-b]quinoline-6,8(9H)-diones in the presence of Starch/SPION@SO₃H.Scheme 43 Synthesis of Fe₃O₄@GOTfOH/Ag/St-PEG-AcA 146.

According to the reusability test, this catalyst was used five times without a decrease in any of its activities. The various functional groups including hydroxyl and amine on the

CSSNH@Arg can activate the carbonyl groups *via* hydrogen bonding.⁷⁶


2.6.2. Synthesis and application of Fe₃O₄@C-SO₃H. Initially, starch was mixed with sulfuric acid, and then the reaction mixture was transferred to an autoclave for 24 h at 180 °C, resulting in the formation of a solid black product (C-SO₃H). The magnetic Fe₃O₄ nanoparticles, carbon-based solid acid (C-SO₃H) 180, and H₂O were placed in an oil bath at 100 °C to remove H₂O, and then the reaction mixture was poured into a Teflon-sealed autoclave and heated at 180 °C for 6 h to achieve Fe₃O₄@C-SO₃H 181 (Scheme 57).⁷⁷


Scheme 44 Synthesis of 2,4,6-triarylpyridine derivatives 148 using Fe₃O₄@GOTfOH/Ag/St-PEG-AcA.

Scheme 45 Synthesis of $\gamma\text{-Fe}_2\text{O}_3\text{@starch-}n\text{-butyl SO}_3\text{H}$.Scheme 46 Synthesis of tetrahydrobenzimidazo[2,1-*b*]quinazolin-1(2*H*)-ones **155** or 2*H*-indazolo[2,1-*b*]phthalazine-triones **156** using $\gamma\text{-Fe}_2\text{O}_3\text{@starch-}n\text{-butyl SO}_3\text{H}$.

CSSNH was applied as a Brønsted acid catalyst in the synthesis of 2-amino-3-cyano-4*H*-pyrans **126** and 2-amino-4*H*-chromenes **116** or **182** *via* the three-component reactions of malononitrile **14**,

benzaldehyde **19**, and β -naphthol **101** or dimedone **64** or 4-hydroxycoumarin **124**, respectively (Scheme 58). This catalyst was used four times without any loss in its activity.⁷⁷

Scheme 47 Synthesis of $\text{Fe}_3\text{O}_4\text{@Alg@CPTMS@Arg}$ **161**.



Scheme 48 Synthesis of 2,4,5-triarylimidazoles **163** using Fe₃O₄@Alg@CPTMS@Arg.


2.6.3. Synthesis and application of magnetic chitosan-terephthaloyl-creatine bio-nanocomposite. The reaction of terephthaloyl chloride **183** and creatine powders **184** in CH₂Cl₂ under reflux conditions provided creatine-terephthaloyl chloride ligand **185**, which was added to chitosan **176** powder in a hydrochloric acid solution, and then refluxed to give chitosan-terephthaloyl-creatine bio-nanocomposite **186**, followed by immobilization on Fe₃O₄ to provide magnetic chitosan-terephthaloyl-creatine bio-nanocomposite **187** (Scheme 59).⁷⁸

Its catalytic activity was tested in the synthesis of polyhydroquinolines **72** *via* the reaction of aldehydes **19**, dimedone **67**, ammonium acetate **71**, and ethyl acetoacetate or methyl acetoacetate **21** in EtOH (Scheme 60). In another attempt, it was

used in the synthesis of 1,4-dihydropyridines **73** *via* the pseudo-three-component reaction of aldehydes **19**, methyl acetoacetate **21**, and ammonium acetate **71** (Scheme 61). The acidic site of the catalyst activated the carbonyl groups of the primary compounds. The activity of this catalyst did not decrease after use eight times.⁷⁸


2.6.4. Synthesis and application of magnetic cyanoguanidine-modified chitosan (MCGC). Firstly, chitosan **176** was obtained *via* the deacetylation of chitin **74**, and then it was modified by treatment with cyanoguanidine **188** in HCl solution to produce cyanoguanidine-modified chitosan (CGC) **189**, which was immobilized on Fe₃O₄ nanoparticles to afford magnetic cyanoguanidine-modified chitosan (MCGC) **190** (Scheme 62). Its catalytic activity was investigated in the synthesis of benzimidazoloquinazolines **155** *via* the reaction of aldehydes **19**, 2-aminobenzimidazole **153**, and dimedone **64** in EtOH under reflux conditions. The sonochemical method afforded better yields in shorter reaction times than the conventional method (Scheme 63).⁷⁹

1,4-Dihydropyridines **73** were synthesized *via* the Hantzsch reaction of ethyl acetoacetate **35**, aromatic aldehydes **19**, and ammonium acetate **71** under ultrasonic irradiation in the presence of MCGC **190** as a catalyst, which activated the carbonyl groups *via* hydrogen bonding. Also, the yield of the reaction did not decrease after eight times usage of the catalyst (Scheme 64).⁷⁹



Scheme 49 Synthesis of Fe₃O₄@Alg@CPTMS@Arg.







Scheme 50 Synthesis of 2,4,5-triarylimidazoles derivatives in the presence of Fe₃O₄@Alg@CPTMS.

2.6.5. Synthesis and application of magnetic MnFe₂O₄-CS-Bu-SO₃H. Manganese ferrite nanoparticles were synthesized *via* the co-precipitation of Fe(III) **1** and Mn(II) **189** in the presence of NaOH solution at 97 °C to give MnFe₂O₄ **191**, which was immobilized on chitosan **176** and 4-butane sultone **151** to prepare MnFe₂O₄-CS-Bu-SO₃H **192** (Scheme 65).⁸⁰


The catalyst activity of MnFe₂O₄-CS-Bu-SO₃H was investigated in the synthesis of *spiro*[acenaphthylene-1,9'-acridine]




Scheme 51 Synthesis of magnetic Fe₃O₄@FU **170**.



Scheme 52 Synthesis of imidazole derivatives.




Scheme 53 Synthesis of Fe₃O₄@C@ONa.




Scheme 54 Synthesis of 4H-chromene derivatives using Fe₃O₄@C@ONa **174**.





Scheme 55 Synthesis of CSSNH@Arg 178.



Scheme 56 Synthesis of 3,4-dihydropyrimidine-2(1H)-(thio)ones using of CSSNH@Arg 178.


triones **194** *via* the multicomponent reaction of dimedone **64**, aldehydes **19**, and acenaphthoquinone **193** under ultrasonic irradiation in H₂O (Scheme 66). Also, MnFe₂O₄-CS-Bu-SO₃H as a Brønsted acid increased the reaction rate *via* hydrogen bonding with the carbonyl group. According to the reusability test, this catalyst was used five times without any loss in its activity.⁸⁰

2.6.6. Synthesis and application of magnetic Cu-MCS. Fe₃O₄ NPs **4** were reacted with carboxymethylated chitosan to obtain magnetic chitosan MCS **195**, which was reacted with

CuCl₂·2H₂O in H₂O to generate Cu NPs@Fe₃O₄-chitosan (Cu-MCS) **196** (Scheme 67).


The catalytic activity of Cu-MCS was verified in the synthesis of various tetrazoles **198** or **199** *via* the reaction of cyanamides **197** and NaN₃ **50** in H₂O under reflux conditions (Scheme 68). This catalyst could be used five times without loss in its activity.⁸¹

2.6.7. Synthesis and application of magnetic Ch-Fe₃O₄ NCs. Chitosan was dissolved in an acetic acid solution, and then FeCl₃·6H₂O **1** and FeCl₂·4H₂O **2** were added to the reaction mixture for 6 h at 80 °C under an N₂ atmosphere. Then, NH₄OH




Scheme 57 Synthesis of 3,4-dihydropyrimidine-2(1H)-(thio)ones in the presence of CSSNH 178.






Scheme 58 Synthesis of 2-amino-4H-chromenes **116** and 2-amino-3-cyano-4H-pyrans **126** in the presence of $\text{Fe}_3\text{O}_4\text{@C-SO}_3\text{H}$.




Scheme 59 Synthesis of magnetic chitosan-terephthaloyl-creatine bio-nanocomposite.





Scheme 60 Synthesis of polyhydroquinoline derivatives 72.




Scheme 61 Synthesis of 1,4-dihydropyridine derivatives 73 in the presence of terephthaloyl-creatine bio-nanocomposite.

was added to the reaction mixture to obtain Ch- Fe_3O_4 NCs **200**. Finally, the chitosan magnetic nanocomposite of Ch-rhomboclase NCs **201** was synthesized *via* the reaction of Ch- Fe_3O_4 NCs **200** with chlorosulfonic acid at room temperature under N_2 gas (Scheme 69).⁸²

The condensation reaction of benzaldehyde **19**, ethyl acetoacetate **35** or dimedone **64**, and ammonium acetate **71** gave 1,4-dihydropyridine derivatives **73** or **202** in the presence of Ch-


rhomboclase NCs **201** under solvent-free conditions at 80 °C (Scheme 70). In the Hantzsch reaction, this acidic catalyst activated carbonyl groups *via* hydrogen bonding. Also, according to the reusability test, the catalyst was used seven times without any decrease in its activity.⁸²

2.6.8. Synthesis and application of magnetic Fe_3O_4 /CS/COF/Cu. After the preparation of an $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ solution in ethylene glycol at room temperature, chitosan, sodium acetate,




Scheme 62 Synthesis of magnetic cyanoguanidine-modified chitosan (MCGC).








Scheme 63 Synthesis of benzimidazoquinazoline derivatives.




Scheme 64 Synthesis of 1,4-dihydropyridines.


Scheme 65 Synthesis of MnFe₂O₄-CS-Bu-SO₃H 192.Scheme 66 Synthesis of spiro[acenaphthylene-1,9'-acridine] triones 194 in the presence of MnFe₂O₄@CS-Bu-SO₃H NPs.



Scheme 67 Synthesis of Cu-MCS.



Scheme 68 Synthesis of various tetrazoles 198 or 199 using Cu-MCS.





Scheme 69 Synthesis of Ch-rhomboclase NCs 201.

and ethylenediamine were added to it. Then, this mixture was placed in a Teflon-lined autoclave and heated at 200 °C for 8 h to obtain $\text{Fe}_3\text{O}_4/\text{CS}$ 205, which was dispersed in DMSO under ultrasound irradiation to give CS-coated Fe_3O_4 , followed by mixing with melamine 63 and terephthalaldehyde 203. The obtained mixture was transferred in a Teflon-lined autoclave at 180 °C for 12 h to obtain $\text{Fe}_3\text{O}_4/\text{CS}/\text{COF}$ 206, which was reacted with $\text{Cu}(\text{NO}_3)_2 \cdot 3\text{H}_2\text{O}$ in EtOH under reflux conditions and

argon atmosphere for 24 h to generate $\text{Fe}_3\text{O}_4/\text{CS}/\text{COF}/\text{Cu}$ 207 (Scheme 71).⁸³

The catalytic activity of $\text{Fe}_3\text{O}_4/\text{CS}/\text{COF}/\text{Cu}$ 207 was tested in the synthesis of polyhydroquinolines 72 *via* the Hantzsch reaction of aldehydes 19, dimedone 64, ammonium acetate 71, and ethyl acetoacetate 35 (Scheme 72). $\text{Fe}_3\text{O}_4/\text{CS}/\text{COF}/\text{Cu}$ with two sites including a Lewis acid (Cu^{2+}) and Lewis base (imine) catalyzed the Hantzsch reaction, which was used five times without a decrease in its activity.⁸³






Scheme 70 Synthesis of 1,4-dihydropyridine derivatives **73** or **202**.Scheme 71 Synthesis of the $\text{Fe}_3\text{O}_4/\text{CS}/\text{COF}/\text{Cu}$.

2.7. Synthesis and application of magnetic $\text{ZnS}/\text{CuFe}_2\text{O}_4/\text{agar}$



$\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ **1**, $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$ **208**, $\text{Zn}(\text{OAc})_2 \cdot 2\text{H}_2\text{O}$ **209**, and thioacetamide were dissolved in distilled H_2O . Then, agar **211** and ammonia solution were added to the reaction mixture to obtain $\text{ZnS}/\text{CuFe}_2\text{O}_4/\text{agar}$ **212** (Scheme 73).⁸⁴

The catalytic activity of $\text{ZnS}/\text{CuFe}_2\text{O}_4/\text{agar}$ **212** was examined in the reaction of dimedone **64**, malononitrile **14**, and aldehydes **19** to synthesize 2-amino-tetrahydro-4*H*-chromene-3-carbonitriles **116** (Scheme 74). The carbonyl groups were activated in the presence of $\text{ZnS}/\text{CuFe}_2\text{O}_4$ *via* interaction with the hydroxyl groups of agar and Zn metal as a Lewis acid. The catalyst was reused five times with no reduction in its activity.⁸⁴

Scheme 72 Synthesis of polyhydroquinoline derivatives *via* Hantzsch reaction.

Scheme 73 Synthesis of ZnS/CuFe₂O₄/agar 212.

R = 4-NO₂, 3-NO₂, 2-Cl, 3-Cl, 4-Cl, 3-Me, 4-Me, 4-CH(Me)₂, 2-OMe, 3-OMe, 4-OMe, 3,4,5-(OMe)₃, 3-OH, 4-OH, 2,4-Cl₂

Scheme 74 Synthesis of 2-amino-tetrahydro-4*H*-chromene-3-carbonitrile derivatives.Scheme 75 Synthesis of Fe₃O₄@xanthan gum 214.

R = 2-Cl, 4-Cl, 2,4-Cl₂, 2,6-Cl₂, 2-Br, 4-CN, 3-Me

Scheme 76 Synthesis of 2-amino-3-cyano-4*H*-pyran derivatives 116 using Fe₃O₄@xanthan gum.

2.8. Synthesis and application of magnetic Fe₃O₄@xanthan gum

NH₄OH solution was added to a mixture of the FeCl₂·4H₂O, FeCl₃·6H₂O (1 : 2), and an aqueous suspension of xanthan gum 213 to give Fe₃O₄@xanthan gum 214 (Scheme 75).⁸⁵

Fe₃O₄@xanthan gum was applied in the synthesis of 2-amino-3-cyano-4H-pyran derivatives 116 via the reaction of aldehydes 19, dimedone 64, and malononitrile 14 in EtOH (Scheme 76). The model reaction was performed about nine times and the yields did not decrease. This reaction was accomplished in the presence of Fe₃O₄ after 45 min in 30% yield. It was shown that Fe₃O₄@xanthan gum activated the carbonyl groups via hydrogen bonding, which was more effective than Fe₃O₄.⁸⁵

3. Conclusion

Many bio-polymers can be obtained from natural sources. According to the importance of green chemistry in organic reactions, in this review, the application of bio-polymers as a catalyst in multicomponent reactions was grouped and summarized. Herein, we highlighted the immobilization of magnetic nanoparticles with bio-polymers. Due to the excellent properties of magnetic nano-catalysts, including their non-toxic nature, high surface area, simple preparation, easy surface modification, and simple separation, these systems have been applied as catalysts in multicomponent reactions. Various organic compounds such as bio-polymers were used for the modification of magnetic nanoparticles. Bio-polymers have various advantages such as biodegradable, biocompatible, and heat-resistant nature. Therefore, herein, their synthesis and catalytic activities in multicomponent reactions were studied. We believe that this article will guide researchers in the design and synthesis of various compounds according to green chemistry. Magnetic nanocomposites have many applications in various fields including, drug delivery, solar cells, chemical sensors, water treatment, biomedical sensors, and catalysts. The importance of these topics could be discussed as a review article in the future.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

We are grateful for the Research Council's support of Alzahra University.

References

- 1 A. Ali, H. Zafar, M. Zia, U. HAQ, A. Phull, J. Ali and A. Hussain, *Nanotechnol., Sci. Appl.*, 2016, **9**, 49–67.
- 2 F. Erogbogbo, K.-T. Yong, R. Hu, W.-C. Law, H. Ding, C.-W. Chang, P. N. Prasad and M. T. Swihart, *ACS Nano*, 2010, **4**, 5131–5138.

- 3 M. Esmaeilpour, J. Javidi, F. N. Dodeji and H. Hassannezhad, *J. Iran. Chem. Soc.*, 2014, **11**, 1703–1715.
- 4 L. Lai, Q. Xie, L. Chi, W. Gu and D. Wu, *J. Colloid Interface Sci.*, 2016, **465**, 76–82.
- 5 A. Abou-Hassan, O. Sandre, S. Neveu and V. Cabuil, *Angew. Chem.*, 2009, **121**, 2378–2381.
- 6 N. O. Mahmoodi, F. Ghanbari Pirbasti and Z. Jalalifard, *J. Chin. Chem. Soc.*, 2018, **65**, 383–394.
- 7 M. Esmaeilpour, J. Javidi and M. Zandi, *New J. Chem.*, 2015, **39**, 3388–3398.
- 8 X. Chen, Y. Zhou, H. Han, X. Wang, L. Zhou, Z. Yi and L. Zeng, *Mater. Today Chem.*, 2021, **22**, 100556.
- 9 G. U. I. Sheng, S. H. E. N. Xiaodong and L. I. N. Benlan, *Rare Met.*, 2006, **25**, 426–430.
- 10 S. S. Khasraghi, M. Shojaei, M. Janmaleki and U. Sundararaj, *Eur. Polym. J.*, 2021, **159**, 110735.
- 11 X. Liu, J. Tian, Y. Li, N. Sun, S. Mi, Y. Xie and Z. Chen, *J. Hazard. Mater.*, 2019, **373**, 397–407.
- 12 M. Muthiah, I. K. Park and C. S. Cho, *Biotechnol. Adv.*, 2013, **3**, 1224–1236.
- 13 R. Mohammadi, A. Saboury, S. Javanbakht, R. Foroutan and A. Shaabani, *Eur. Polym. J.*, 2021, **153**, 110500.
- 14 M. A. Almessiere, Y. Slimani, A. Demir Korkmaz, A. Baykal, H. Albetran, T. A. Saleh, M. Sertkol and I. Ercan, *Ultrason. Sonochem.*, 2020, **62**, 104847.
- 15 H. Javadian, M. Ruiz, T. A. Saleh and A. M. Sastre, *J. Mol. Liq.*, 2020, **306**, 112760.
- 16 A. A. Basaleh, M. H. Al-Malack and T. A. Saleh, *J. Environ. Chem. Eng.*, 2021, **9**, 105126.
- 17 A. A. Basaleh, M. H. Al-Malack and T. A. Saleh, *Sustainable Chem. Pharm.*, 2021, **23**, 100503.
- 18 N. Dhenadhayalan, K. C. Lin and T. A. Saleh, *Small*, 2020, **6**, 1905767.
- 19 A. M. Alansi, M. Al-Qunaibit, I. O. Alade, T. F. Qahtan and T. A. Saleh, *J. Mol. Liq.*, 2018, **253**, 297–304.
- 20 A. M. Alansi, T. F. Qahtan and T. A. Saleh, *Adv. Mater. Interfaces*, 2021, **8**, 2001463.
- 21 A. M. Alansi, T. F. Qahtan, N. Al Abass, J. M. AlGhamdi, M. Al-Qunaibit and T. A. Saleh, *Adv. Sustainable Syst.*, 2021, 2100267.
- 22 T. A. Saleh, *Environ. Technol. Innovation*, 2021, **24**, 101821.
- 23 J. Wang, Z. Shi, J. Fan, Y. Ge, J. Yin and G. Hu, *J. Mater. Chem.*, 2012, **22**, 22459.
- 24 T. A. Debele, S. L. Mekuria and H. C. Tsai, *Mater. Sci. Eng., C*, 2016, **68**, 964–981.
- 25 A. Maleki and M. Kamalzare, *Catal. Commun.*, 2014, **53**, 67–71.
- 26 V. Omid, F. M. Kievit, C. Fang, N. Mu, S. Jana, M. C. Leung, H. Mok, R. G. Ellenbogen, J. O. Park and M. Zhang, *Biomaterials*, 2010, **31**, 8032–8042.
- 27 Z. M. Avval, L. Malekpour, F. Raeisi, A. Babapoor, S. M. Mousavi, S. A. Hashemi and M. Salari, *Drug Metab. Rev.*, 2020, **52**, 157–184.
- 28 S. Mirza, M. S. Ahmad, M. I. A. Shah and M. Ateeq, In *Metal nanoparticles for drug delivery and diagnostic applications*, Elsevier, 2020, pp. 189–213.



Review

- 29 A. Gholami, S. M. Mousavi, S. A. Hashemi, Y. Ghasemi, W.-H. Chiang and N. Parvin, *Drug Metab. Rev.*, 2020, **52**, 205–224.
- 30 X. Sun, G. Zhang, R. Du, R. Xu, D. Zhu, J. Qian, G. Bai, C. Yang, Z. Zhang, X. Zhang and D. Zou, *Biomaterials*, 2019, **194**, 151–160.
- 31 Z. Zhou, L. Yang, J. Gao and X. Chen, *Adv. Mater.*, 2019, **31**, 1804567.
- 32 D. D. Stueber, J. Villanova, I. Aponte, Z. Xiao and V. L. Colvin, *Pharmaceutics*, 2021, **13**, 943.
- 33 N. M. El-Shafai, M. M. Abdelfatah, M. E. El-Khouly, I. M. El-Mehasseb, A. El-Shaer, M. S. Ramadan, M. S. Masoud and M. A. El-Kemary, *Appl. Surf. Sci.*, 2020, **506**, 144896.
- 34 L. Gloag, M. Mehdipour, D. Chen, R. D. Tilley and J. J. Gooding, *Adv. Mater.*, 2019, **31**, 1904385.
- 35 S. Khizar, H. Ben Halima, N. M. Ahmad, N. Zine, A. Errachid and A. Elaissari, *Electrophoresis*, 2020, **41**, 1206–1224.
- 36 M. P. Conte, J. K. Sahoo, Y. M. Abul-Haija, K. A. Lau and R. V. Ulijn, *ACS Appl. Mater. Interfaces*, 2018, **10**, 3069–3075.
- 37 S. Mallakpour and M. Hatami, *Appl. Clay Sci.*, 2019, **174**, 127–137.
- 38 N. Shabani, A. Javadi, H. Jafarizadeh-Malmiri, H. Mirzaei and J. Sadeghi, *Food Hyg.*, 2021, **10**, 61–71.
- 39 R. Banerjee, Y. Katsenovich, L. Lagos, M. McIntosh, X. Zhang and C.-Z. Li, *Curr. Med. Chem.*, 2010, **17**, 3120–3141.
- 40 S. Mallakpour, M. Tikhani and C. M. Hussain, *Int. J. Biol. Macromol.*, 2021, **179**, 429.
- 41 S. Kamel and T. A. Khattab, *Cellulose*, 2021, **28**, 4545.
- 42 G. Mohammadi Ziarani, Z. Kheilkordi, F. Mohajer, A. Badiei and R. Luque, *RSC Adv.*, 2021, **11**, 17456–17477.
- 43 G. Mohammadi Ziarani, S. Rohani, A. Ziarati and A. Badiei, *RSC Adv.*, 2018, **8**, 41048–41100.
- 44 F. Mohajer, G. Mohammadi Ziarani and A. Badiei, *RSC Adv.*, 2021, **11**, 6517–6525.
- 45 Z. Kheilkordi, G. Mohammadi Ziarani and F. Mohajer, *Curr. Org. Chem.*, 2022, **26**, 287–298.
- 46 G. Mohammadi Ziarani, R. Moradi, T. Ahmadi and N. Lashgari, *RSC Adv.*, 2018, **8**, 12069–12103.
- 47 G. Mohammadi Ziarani, F. Aleali and N. Lashgari, *RSC Adv.*, 2016, **6**, 50895–50922.
- 48 G. Mohammadi Ziarani, N. H. Nasab and N. Lashgari, *RSC Adv.*, 2016, **6**, 38827–38848.
- 49 L. A. Thompson, *Curr. Opin. Chem. Biol.*, 2000, **4**, 324–337.
- 50 A. Dömling, *Curr. Opin. Chem. Biol.*, 2002, **6**, 306–313.
- 51 E. Zare and Z. Rafiee, *Appl. Organomet. Chem.*, 2020, **34**, e5516.
- 52 S. S. Hosseinihah and B. B. F. Mirjalili, *RSC Adv.*, 2020, **10**, 40508–40513.
- 53 P. G. Kargar, G. Bagherzade and H. Eshghi, *RSC Adv.*, 2020, **10**, 37086–37097.
- 54 A. Maleki, S. Gharibi, K. Valadi and R. Taheri-Ledari, *J. Phys. Chem. Solids*, 2020, **142**, 109443.
- 55 G. Bagherzade, *RSC Adv.*, 2021, **11**, 19203–19220.
- 56 G. Bagherzade and H. Eshghi, *RSC Adv.*, 2021, **11**, 4339–4355.
- 57 P. G. Kargar, M. Noorian, E. Chamani, G. Bagherzade and Z. Kiani, *RSC Adv.*, 2021, **11**, 17413–17430.
- 58 M. Zahedifar, B. Pouramiri and R. Razavi, *Res. Chem. Intermed.*, 2020, **46**, 2749–2765.
- 59 B. B. F. Mirjalili, Z. Zaghaghi and A. Monfared, *J. Chin. Chem. Soc.*, 2020, **67**, 197–201.
- 60 N. Safajoo, B. B. F. Mirjalili and A. Bamoniri, *Polycyclic Aromat. Compd.*, 2021, **41**, 1241–1248.
- 61 N. Safajoo, B. B. F. Mirjalili and A. Bamoniri, *RSC Adv.*, 2019, **9**, 1278–1283.
- 62 G. Bagherzade and H. Eshghi, *RSC Adv.*, 2020, **10**, 32927–32937.
- 63 A. D. Tafti and B. B. F. Mirjalili, *RSC Adv.*, 2020, **10**, 31874–31880.
- 64 A. Maleki, F. Hassanzadeh-Afruzi, Z. Varzi and M. S. Esmaili, *Mater. Sci. Eng., C*, 2020, **109**, 110502.
- 65 Z. Amiri-Khamakani, F. Hassanzadeh-Afruzi and A. Maleki, *Chem. Process.*, 2020, **3**, 101.
- 66 E. Babaei and B. B. F. Mirjalili, *Iran. J. Catal.*, 2020, **10**, 219–226.
- 67 A. Mohammadzadeh, A. P. Marjani and A. Zamani, *S. Afr. J. Chem.*, 2020, **73**, 55–63.
- 68 M. Kamalzare, M. Bayat and A. Maleki, *R. Soc. Open Sci.*, 2020, **7**, 200385.
- 69 M. H. Sayahi, F. Shamkhani, M. Mahdavi and S. Bahadorikhalili, *Starch-Stärke*, 2021, **73**, 2000257.
- 70 S. Forouzandehdel, M. Meskini and M. R. Rami, *J. Mol. Struct.*, 2020, **1214**, 128142.
- 71 M. Shamsi-Sani, F. Shirini and M. Mohammadi-Zeydi, *J. Nanosci. Nanotechnol.*, 2019, **19**, 4503–4511.
- 72 S. Amirnejat, A. Nosrati and S. Javanshir, *Appl. Organomet. Chem.*, 2020, **34**, e5888.
- 73 S. Amirnejat, A. Nosrati, S. Javanshir and M. R. Naimi-Jamal, *Int. J. Biol. Macromol.*, 2020, **152**, 834–845.
- 74 M. Banazadeh, S. Amirnejat and S. Javanshir, *Front. Chem.*, 2020, **8**, 1023.
- 75 H. Ghavidel, B. Mirza and S. Soleimani-Amiri, *Polycyclic Aromat. Compd.*, 2021, **41**, 604–625.
- 76 S. Behrouz, M. N. Abi and M. A. Piltan, *Acta Chim. Slov.*, 2021, **68**, 374–386.
- 77 S. Behrouz, M. N. Abi and M. A. Piltan, *J. Appl. Chem.*, 2019, **14**, 109–124.
- 78 S. Asgharnasl, R. Eivazzadeh-Keihan, F. Radinekiyan and A. Maleki, *Int. J. Biol. Macromol.*, 2020, **144**, 29–46.
- 79 K. Javanmiri and R. Karimian, *Monatsh. Chem.*, 2020, **151**, 199–212.
- 80 H. Naeimi and S. Lahouti, *J. Org. Chem. Res.*, 2020, **6**, 54–68.
- 81 N. Motahharifar, M. Nasrollahzadeh, A. Taheri-Kafrani, R. S. Varma and M. Shokouhimehr, *Carbohydr. Polym.*, 2020, **232**, 115819.
- 82 P. Kamalzare, B. Mirza and S. Soleimani-Amiri, *J. Nanostructure Chem.*, 2021, **11**, 229–243.
- 83 E. Zare and Z. Rafiee, *J. Taiwan Inst. Chem. Eng.*, 2020, **116**, 205–214.
- 84 S. Bahrami, F. Hassanzadeh-Afruzi and A. Maleki, *Appl. Organomet. Chem.*, 2020, **34**, e5949.
- 85 M. S. Esmaili, M. R. Khodabakhshi, A. Maleki and Z. Varzi, *Polycyclic Aromat. Compd.*, 2021, **41**, 1953–1971.

