



Cite this: *RSC Adv.*, 2022, **12**, 22367

## Synthesis of a $\text{UiO-66/g-C}_3\text{N}_4$ composite using terephthalic acid obtained from waste plastic for the photocatalytic degradation of the chemical warfare agent simulant, methyl paraoxon<sup>†</sup>

Dung Van Le,<sup>ab</sup> Manh B. Nguyen,<sup>\*c</sup> Phuong T. Dang,<sup>c</sup> Taeyoon Lee<sup>\*d</sup> and Trinh Duy Nguyen  <sup>ae</sup>

In our study, Zr-based  $\text{UiO-66}$  (Zr) was synthesized using terephthalic acid obtained from waste plastic. Thereafter,  $\text{UiO-66/g-C}_3\text{N}_4$  composites were prepared by the solvothermal method, and their photocatalytic activity in the photodegradation of the chemical warfare agent simulant, dimethyl 4-nitrophenyl phosphate (DMNP), was evaluated. The as-synthesized  $\text{UiO-66/g-C}_3\text{N}_4$  exhibited a high surface area ( $1440 \text{ m}^2 \text{ g}^{-1}$ ) and a high capillary volume ( $1.49 \text{ cm}^3 \text{ g}^{-1}$ ). The  $\text{UiO-66/g-C}_3\text{N}_4$  samples absorbed a visible light band with bandgap energies of  $2.13\text{--}2.88 \text{ eV}$ . The as-synthesized  $\text{UiO-66/g-C}_3\text{N}_4$  composites exhibited highly efficient degradation of DMNP with a short half-life ( $t_{1/2}$  of  $2.17 \text{ min}$ ) at pH 7 under visible light irradiation. The trapping experiments confirmed that the  $\text{h}^+$  and  $\text{O}_2^-$  radicals played an important role in the photocatalytic degradation of DMNP. The  $\text{UiO-66/g-C}_3\text{N}_4$  catalyst simultaneously performed two processes: the hydrolysis and photocatalytic oxidation of DMNP in water. During irradiation, a p–n heterojunction between  $\text{UiO-66}$  and  $\text{g-C}_3\text{N}_4$  restricted the recombination of photogenerated electrons and holes, resulting in the enhancement in the degradation rate of DMNP.

Received 5th June 2022

Accepted 3rd August 2022

DOI: 10.1039/d2ra03483b

rsc.li/rsc-advances

## 1 Introduction

Organophosphate ester compounds have been used to synthesize a variety of organic chemicals, such as drugs, pesticides, herbicides, fungicides, flame retardants, surfactants, and dangerous neurotoxins.<sup>1,2</sup> The highly dangerous neurotoxins known as chemical warfare agents (CWAs) can affect the respiratory system, cause severe damage, and destroy the central nervous system, leading to death.<sup>2</sup> Therefore, the rapid decomposition and conversion of CWAs into environmentally friendly and non-toxic products have been considered an urgent

issue.<sup>3,4</sup> Several disinfectants have been applied to treat CWAs, such as bleach or salt, porous organic polymers, metal oxides, potassium persulphate, ozone, sodium hypochlorite, and hydrogen peroxide.<sup>5–7</sup> However, the above disinfectants have limitations, such as high corrosiveness, instability, environmental impact, and long processing duration.<sup>8</sup>

The degradation of CWAs over photocatalysts has recently been receiving considerable attention because these materials can degrade CWAs into non-toxic products. For example, Zr-based metal–organic frameworks (MOFs), including  $\text{UiO-66}$  and  $\text{NH}_2\text{-UiO-66}$ , have recently been used as effective photocatalysts to degrade CWAs and its simulant, dimethyl 4-nitrophenyl phosphate (DMNP).<sup>3,8</sup> However, the DMNP treatment process is performed in alkaline media (pH = 10) using *N*-ethylmorpholine buffer solution; thus, it is difficult to apply in the industry.<sup>6</sup> Furthermore, Zr-based MOFs become less stable at pH greater than 9.5, in which the surface area of the Zr-based MOFs significantly decreases, and a large amount of terephthalic acid is released into the solution.<sup>9</sup> Similarly, Song *et al.*<sup>8</sup> reported that the treatment efficiency of DMNP over graphene@ $\text{UiO-66-NH}_2$  composite is strongly influenced by the pH and concentration of the *N*-ethylmorpholine buffer solution. Further, they have shown that the graphene@ $\text{UiO-66-NH}_2$  composite exhibits a low efficiency for DMNP removal (approximately 49%) in water media without using the *N*-ethylmorpholine buffer solution. Additionally, organophosphates

<sup>a</sup>Graduate University of Science and Technology, Vietnam Academy of Science and Technology, 18 Hoang Quoc Viet Street, Cau Giay, Ha Noi, Vietnam

<sup>b</sup>Center for Technology Environmental Treatment, 282 Lac Long Quan Street, Tay Ho, Ha Noi, Vietnam

<sup>c</sup>Institute of Chemistry, Vietnam Academy of Science and Technology, 18 Hoang Quoc Viet Street, Cau Giay, Ha Noi, Vietnam. E-mail: nguyenbamanh@ich.vast.vn

<sup>d</sup>Department of Environmental Engineering, College of Environmental and Marine, Pukyong National University, 45 Yongso-ro, Nam-gu, Busan, 48513, Republic of Korea. E-mail: badger74w@pknu.ac.kr

<sup>e</sup>Institute of Applied Technology and Sustainable Development, Nguyen Tat Thanh University, Ho Chi Minh City, Vietnam. E-mail: ndtrinh@ntt.edu.vn

<sup>†</sup> Electronic supplementary information (ESI) available: HPLC spectrum of  $\text{H}_2\text{BDC}$ , schematic synthesis of  $\text{UiO-66/g-C}_3\text{N}_4$ , XRD analysis, EDS spectra, SEM images, UV-vis spectra of DMNP, images of DMNP solution, LC-mass spectra of DMNP, photo-stability test, element composition, and a comparison of photocatalytic activity of photocatalysts. See <https://doi.org/10.1039/d2ra03483b>



can be slowly hydrolyzed in water to form other toxic substances, such as methyl 4-nitrophenyl phosphate (M4NP).<sup>2</sup> To enhance the removal efficiency of the CWAs in an aqueous medium, MOF (Zr) catalysts modified with amines, graphene, and metal alkoxides groups have been reported.<sup>10–12</sup> Song *et al.*<sup>8</sup> reported that graphene@UiO-66-NH<sub>2</sub> significantly increased the degradation rate of DMNP, and the half-life decreased from 3.4 to 1.6 min using sunlight irradiation.

Recently, a metal-free semiconductor, g-C<sub>3</sub>N<sub>4</sub>, has been widely studied and applied as a photocatalyst for energy production, electrocatalysis, and electrochemiluminescence.<sup>13–19</sup> The g-C<sub>3</sub>N<sub>4</sub> semiconductor possesses many advantages, such as low production cost, simple fabrication, strong oxidizing properties, high thermal stability, high chemical stability, and excellent optical and thermal properties.<sup>20–22</sup> However, g-C<sub>3</sub>N<sub>4</sub> has a low surface area (10–30 m<sup>2</sup> g<sup>-1</sup>), easily formed electron–hole pairs, fast charge recombination, nature chemical inertness, bulky structure, and bulky size.<sup>23–28</sup> Therefore, modifying g-C<sub>3</sub>N<sub>4</sub> with carbon-based materials<sup>29</sup> or MOFs<sup>30</sup> or dissecting g-C<sub>3</sub>N<sub>4</sub> into monolayer nanosheets produces thin layers that improve the surface area and enhance the diffusion rate of reactants/products.<sup>31</sup> MOFs/g-C<sub>3</sub>N<sub>4</sub> heterojunction catalysts have been studied because they can effectively block the fast recombination ability of electron (e<sup>-</sup>) and hole (h<sup>+</sup>) pairs and absorb high visible light, thereby increasing the efficiency of the photocatalyst. Furthermore, the  $\pi$ – $\pi$  conjugate structure between g-C<sub>3</sub>N<sub>4</sub> and UiO-66 can induce a high charge-separation rate.<sup>32</sup>

In our study, we use terephthalic acid produced from waste plastics to synthesize low-cost UiO-66 catalysts. The conversion of plastic waste to valuable products is considered an economically and environmentally friendly solution. Afterward, the UiO-66/g-C<sub>3</sub>N<sub>4</sub> heterojunction catalysts are synthesized by the solvothermal method. The UiO-66/g-C<sub>3</sub>N<sub>4</sub> catalysts are applied for the hydrolysis and photocatalytic oxidation of the CWA simulant, DMNP, in an aqueous environment. The UiO-66/g-C<sub>3</sub>N<sub>4</sub> catalysts possess advantages, such as (i) high surface area, (ii) enhanced visible light absorption, and (iii) low recombination of photogenerated electrons and holes. Therefore, the photocatalytic oxidation of the DMNP is improved.

## 2 Materials and methods

### 2.1 Material

Polyethylene terephthalate (PET) water bottles were used as a source of plastic waste to prepare terephthalic acid (H<sub>2</sub>BDC). The chemical reagents used in this study, including sulphuric acid (H<sub>2</sub>SO<sub>4</sub>, 98%), hydroxyl sodium (NaOH, 98%), dimethylformamide (DMF, 98%), ethylene glycol (EG), *N*-ethylmorpholine, zirconyl chloride octahydrate (ZrOCl<sub>2</sub>·8H<sub>2</sub>O, 98%), cetyltrimethylammonium bromide (CTABr, 98%) and dimethyl 4-nitrophenyl phosphate (DMNP, 99%), were supplied by Sigma-Aldrich.

### 2.2 Synthesis of H<sub>2</sub>BDC from waste plastic

PET water bottles purchased from recycling facilities were cleaned, dried, and cut into 4 × 4 mm pieces. Next, a mixture of

the waste PET pieces (24 g), NaOH (44 g), and EG (110 mL) was added to a 500 mL three-necked flask equipped with a condenser. The mixture was vigorously stirred at 300 rpm and heated at 190 °C for 3 h. Afterward, the mixture was cooled to 80 °C, and 200 mL of distilled water was added; the mixture was stirred until completely dissolved. The pH of the mixture was adjusted to 3 using 2 M H<sub>2</sub>SO<sub>4</sub> to obtain a white slurry. Finally, the obtained H<sub>2</sub>BDC was filtered and washed four times with distilled water and dried overnight at 60 °C. HPLC spectrum of H<sub>2</sub>BDC product (Fig. S1†) shows a large peak at retention time at 3.171 minutes and a small peak at a retention time at 3.976 minutes, indicating that the main component H<sub>2</sub>BDC is about 99% after the refining process. The H<sub>2</sub>BDC production obtained about 73.4% yields.

### 2.3 Synthesis of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites

The g-C<sub>3</sub>N<sub>4</sub> was synthesized by calcination, as reported in the literature.<sup>31,33</sup> Briefly, 10 g of urea and 10 g of NH<sub>4</sub>Cl were mixed and ground in an agate mortar. Thereafter, the solid mixture was transferred to a porcelain crucible with a melamine foam cover (45 × 60 × 30 mm<sup>3</sup>) and fired in a furnace at 550 °C for 3 h with a ramping rate of 5 °C min<sup>-1</sup>. The UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites were fabricated by the solvothermal method (Fig. S2†). First, H<sub>2</sub>BDC (1.71 g) was dissolved in DMF (60 mL), whereas ZrOCl<sub>2</sub>·8H<sub>2</sub>O (2.52 g) and CTABr (0.356 g) were dissolved in distilled water (40 mL). Afterward, these solutions were uniformly mixed by vigorously stirring for 60 min to form a clear solution (solution A). Homogeneous suspension B was prepared by dispersing 0.8 g of g-C<sub>3</sub>N<sub>4</sub> into 20 mL of distilled water under ultrasonic treatment for 30 min. Solution A was slowly added to homogeneous suspension B under vigorous stirring. After further stirring for 60 min, the mixture was placed in a Teflon-lined autoclave and heated at 100 °C for 12 h. The products were filtered and washed with DMF and ethanol to remove unreacted substances. Finally, the obtained UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites were dried overnight in an oven at 80 °C. The obtained UiO-66/g-C<sub>3</sub>N<sub>4</sub> catalysts were identified as UiO-66, UiO-66/g-C<sub>3</sub>N<sub>4</sub>-10%, UiO-66/g-C<sub>3</sub>N<sub>4</sub>-20%, UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30%, and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-40%, according to the weight ratios of g-C<sub>3</sub>N<sub>4</sub> : 0 wt%, 10 wt%, 20 wt%, 30 wt%, and 40 wt%, respectively.

### 2.4 Characterization of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub>

X-ray diffraction (XRD) of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples was performed on a D8 Advance diffractometer (Bruker, Germany) with CuK $\alpha$  as the radiation source ( $\lambda = 0.154$  06 nm and a  $2\theta$  range of 2–50°). The morphology of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples was characterized by scanning electron microscopy (SEM) and transmission electron microscopy (TEM) on Hitachi S4700 and Leica LEO 906E instruments, respectively. Energy-dispersive X-ray spectroscopy (EDS) was used to determine the composition of the elements in the UiO-66/g-C<sub>3</sub>N<sub>4</sub> sample on a JEOL JED-2300 instrument. The elemental components were analyzed using a Thermo VG RSCAKAB 250 $\times$  high-resolution X-ray photoelectron spectrometer (XPS). Surface area ( $S_{BET}$ ), total pore volume ( $V_{pore}$ ), and



mean Barrett–Joyner–Halenda (BJH) pore diameter were analyzed on a Tristar-3030 instrument (Micromeritics-USA) with  $N_2$  adsorbed at  $-196^\circ\text{C}$ . The UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples were degassed with  $N_2$  gas at  $150^\circ\text{C}$  for 12 h before measuring  $N_2$  adsorption. The surface functional groups of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples were analyzed on a Nicolet Nexus 670 Fourier-transform infrared (FT-IR) spectrometer. UV-vis absorption spectra, UV-vis diffuse reflectance spectra (UV-vis DRS), and photoluminescence (PL) spectra were acquired using a Shimadzu UV-2600 spectrometer, a Shimadzu UV-3100 spectrometer, and Varian, respectively.

## 2.5 Electrochemical measurements

The electrodes used for Mott–Schottky measurements were prepared by dispersing the powder samples in ethanol (0.1 mL: 0.05 g mL<sup>-1</sup>) and placing them in a fluorine-doped tin oxide (FTO) plate (0.283 cm<sup>2</sup>) to dry naturally at room temperature for 24 h. Thereafter, the powder samples dispersed on the FTO plates were placed in a 0.1 M Na<sub>2</sub>SO<sub>4</sub> solution and applied to a voltage of 10 mV at 10 kHz. The Mott–Schottky measurements were performed in the dark over a potential range from  $-1.5$  to  $+1.5$  V (V vs. Ag/AgCl).

## 2.6 Photocatalytic activity

The photodegradation and hydrolysis of the DMNPs over UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> were performed according to a previous report.<sup>34,35</sup> First, 2.5 mg (0.0015 mmol) of the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples and 1 mL of water (pH = 7) were added to a 2 mL reactor and vigorously stirred at 1300 rpm. Thereafter, 4  $\mu\text{L}$  (0.025 mmol) of DMNP was added to the above suspension and irradiated with 30 W pseudo-sunlight. The molar ratio of catalyst and DMNP was fixed as 6 mol%. The intensity of incident light is about 2880 Lux. The distance between the surface of the reaction solution and the light source was fixed at about 15 cm. During 60 min of irradiation, 20  $\mu\text{L}$  of the mixture in the reaction system was removed at a certain time intervals and diluted with 10 mL of 0.15 M *N*-ethyl morphine solution to monitor *p*-nitrophenoxide. To evaluate the reusability of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample, the catalyst was washed several times with aqueous *N*-ethyl morphine, soaked in ethanol, and dried at  $80^\circ\text{C}$  for 12 h to be used for the next reaction cycle. Radical scavengers, including ammonium oxalate monohydrate (AO), *tert*-butanol (TBA), potassium dichromate (K<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub>), and 1,4-benzoquinone (BQ), with a concentration of 1 mM, were employed to capture holes (h<sup>+</sup>), hydroxyl (OH), electrons (e<sup>-</sup>), and superoxide anion (O<sub>2</sub><sup>-</sup>), respectively.

# 3 Results and discussion

## 3.1 Structure and morphology characterization of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites

The crystalline structure of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites was investigated by XRD analysis. The powder XRD patterns of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites (Fig. 1A and S3†) showed eight main diffraction peaks at  $2\theta$  of  $7.2^\circ$ ,  $8.3^\circ$ ,  $12^\circ$ ,  $17^\circ$ ,  $22^\circ$ ,  $26^\circ$ ,  $31^\circ$ , and  $44^\circ$ , corresponding to the reflection

planes of (111), (200), (022), (004), (044), (006), (117) and (339) of UiO-66 (Zr) (CCDC No. 733458), respectively.<sup>8,36,37</sup> Additionally, the characteristic peak of the g-C<sub>3</sub>N<sub>4</sub> phase was detected at  $27.3^\circ$  (JCPDS No. 87-1526) (Fig. 1A),<sup>38</sup> implying that the UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites were produced. Further, we observed that the intensity of the peak at  $27.3^\circ$  increased when the g-C<sub>3</sub>N<sub>4</sub> content in the composites increased from 10 to 40 wt%. These outcomes indicated that the addition of g-C<sub>3</sub>N<sub>4</sub> did not affect the structure of the UiO-66 material.

The FTIR spectra of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples (Fig. 1B) were obtained to investigate the composition of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples. The vibrations at 3200 to 3600 cm<sup>-1</sup> were attributed to the –OH of water molecules that were physically adsorbed inside the capillaries of the UiO-66 or g-C<sub>3</sub>N<sub>4</sub> materials.<sup>39</sup> The band oscillations at 1583, 1437, and 1388 cm<sup>-1</sup> were assigned to the asymmetrical stretching and symmetrical stretching variations of the carboxyl groups.<sup>36</sup> The bands at 746 cm<sup>-1</sup> and 661 cm<sup>-1</sup> were assigned to the Z–O stretching oscillations.<sup>41</sup> In the FTIR spectrum of g-C<sub>3</sub>N<sub>4</sub> (Fig. 1B), the bands at 1254, 1320, and 1456 cm<sup>-1</sup> were related to aromatic g-C<sub>3</sub>N<sub>4</sub> stretching,<sup>40</sup> while the bands at 1574 and 1638 cm<sup>-1</sup> were attributed to the of C=N bond.<sup>41</sup> However, the absence of these fluctuations in the FTIR spectra of the UiO-66/




Fig. 1 (A) XRD patterns and (B) FT-IR spectra of UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites.






Fig. 2 TEM images of UiO-66 (A), UiO-66/g-C<sub>3</sub>N<sub>4</sub>-10% (B), UiO-66/g-C<sub>3</sub>N<sub>4</sub>-20% (C), UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (D), UiO-66/g-C<sub>3</sub>N<sub>4</sub>-40% (E) composites and g-C<sub>3</sub>N<sub>4</sub> (F).

g-C<sub>3</sub>N<sub>4</sub> composites (Fig. 1B) may be due to the overlapping of the bands in the UiO-66 sample.

The SEM and TEM images of UiO-66 showed nanoparticles with a diameter of 80–120 nm, while g-C<sub>3</sub>N<sub>4</sub> plates with un-uniform length were observed in the SEM and TEM images of g-C<sub>3</sub>N<sub>4</sub> (Fig. S4† and 2). For the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples, as shown in the TEM image (Fig. 2), there were dark areas on the micrograph of the MOF nanocrystals mounted on top of the g-C<sub>3</sub>N<sub>4</sub> plates, and the relatively light contours corresponded to the g-C<sub>3</sub>N<sub>4</sub> sheets decorated with UiO-66 nanoparticles. Similarly, the SEM image of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-40% sample showed that there was a clustering of the UiO-66 nanoparticles into large particles of 100–150 nm (Fig. S4†).

The chemical composition of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% samples was analyzed by EDS. The EDS (Fig. S5†) and EDS-mapping spectra (Fig. 3) confirmed the presence and uniform distribution of C, O, Zr, and N throughout the composites. Further, the mass ratios of C, O, and Zr decreased in sample UiO-66/g-C<sub>3</sub>N<sub>4</sub>%, while the N content increased by 17.22 wt% (Table S1†). The N content accounted for 17.22 wt% in sample UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30%, showing that the weight ratio of the g-C<sub>3</sub>N<sub>4</sub>/UiO-66 determined by EDS was considerably close to the estimated value of 30%.

The porosity properties of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples were obtained by N<sub>2</sub> adsorption–desorption isotherms and pore size distributions (Fig. 4). The UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples exhibited a type IV isotherm with hysteresis upon desorption in the P/P<sub>0</sub> of 0.45–1, presenting typical mesoporous materials.<sup>42</sup> However, UiO-66 exhibited a type I isotherm with an existing micro-sized pore.<sup>43</sup> The UiO-66 sample had the highest estimated  $S_{\text{BET}}$  (1440 m<sup>2</sup> g<sup>-1</sup>) and  $V_{\text{pore}}$  value (1.05 cm<sup>3</sup> g<sup>-1</sup>) and the smallest pore diameter (3.44 nm) (Table 1). The UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples had a surface area of 583–1162 m<sup>2</sup> g<sup>-1</sup>, pore volume of 0.79–1.49 cm<sup>3</sup> g<sup>-1</sup>, and an average pore diameter of 4.08–5.56 nm (Table 1). Thus, the addition of the g-C<sub>3</sub>N<sub>4</sub> in the UiO-

66 sample, UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples, significantly reduced the surface area compared to the pure UiO-66 sample. However, because of the expansion of the pore diameter from 3.44 to




Fig. 3 EDS mapping element layered image (A), EDS element mapping images of C (B), O (C), Zr (D) and N (E) of UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample.






Fig. 4 (A)  $N_2$  adsorption–desorption isotherms and (B) pore size distributions of  $\text{UiO-66}$  and  $\text{UiO-66/g-C}_3\text{N}_4$  composite.

4.08 nm, the total pore volume increased from 1.05 to  $1.49 \text{ cm}^3 \text{ g}^{-1}$  (Table 1). The pore volume and pore diameter significantly increased, favoring the adsorption and degradation of DMNP because the  $\text{Zr}_6$  metal sites expanded the decomposition reaction.<sup>44</sup> Furthermore, the addition of the  $\text{g-C}_3\text{N}_4$  helped to generate more defects, which improved the degradation performance of the catalyst.<sup>45</sup>

The chemical states and surface compositions of the  $\text{UiO-66}$  and  $\text{UiO-66/g-C}_3\text{N}_4$ -30% samples were analyzed by XPS (Fig. 5). The full-scan XPS spectra of  $\text{UiO-66}$  (Fig. 5A) showed peaks of C 1s (285.6 eV), O 1s (532.6 eV), and Zr (184.6 eV). Similarly, the full-scan XPS spectra of the  $\text{UiO-66/g-C}_3\text{N}_4$ -30% sample (Fig. 5B) showed peaks of C 1s (285.5 eV), O 1s (531.8 eV), Zr (183.7 eV),

Table 1 Textual characteristics and energy gap-band ( $E_g$ ) of  $\text{g-C}_3\text{N}_4$ ,  $\text{UiO-66}$ , and  $\text{UiO-66/g-C}_3\text{N}_4$  samples

Samples	$S_{\text{BET}}$ ( $\text{m}^2 \text{ g}^{-1}$ )	$V$ ( $\text{cm}^3 \text{ g}^{-1}$ )	$D_{\text{BJH}}$ (nm)	$E_g$ (eV)
UiO-66	1440	1.05	3.44	3.50
UiO-66/g-C <sub>3</sub> N <sub>4</sub> -10%	1162	1.49	4.08	3.28
UiO-66/g-C <sub>3</sub> N <sub>4</sub> -20%	994	1.28	4.99	3.11
UiO-66/g-C <sub>3</sub> N <sub>4</sub> -30%	827	1.06	5.32	2.91
UiO-66/g-C <sub>3</sub> N <sub>4</sub> -40%	583	0.79	5.56	2.82

and N 1s (401.7 eV).<sup>46</sup> The C 1s spectra of the  $\text{UiO-66}$  sample showed four peaks with binding energies at 282.52, 284.07, 286.53, and 290.02 eV, which were assigned to  $\text{C}=\text{C/C-C}$ ,  $\text{C}-\text{O}$ ,  $\text{C}=\text{O}$ , and  $\text{O}-\text{C}=\text{O}$  groups, respectively (Fig. 5C).<sup>32,47</sup> The C 1s spectra of the  $\text{UiO-66/g-C}_3\text{N}_4$ -30% sample (Fig. 5D) showed six peaks and their binding energies at  $\text{C}=\text{C/C-C}$  (281.74 eV),  $\text{C}-\text{O}$  (283.78 eV),  $\text{C}=\text{O}$  (286.73 eV),  $\text{O}-\text{C}=\text{O}$  (288.70 eV),  $\text{sp}^2$  bonded carbon ( $\text{N}-\text{C}=\text{N}$ , 286.23 eV), and graphite carbon group ( $\text{sp}^3 \text{ C}$ , 282.34 eV).<sup>32</sup> The high-resolution O 1s XPS spectra of the  $\text{UiO-66}$  sample (Fig. 5E) showed that three peaks at 530.81, 532.35, and 533.53 eV were attached to the O in the metal-bonded crystal lattice ( $\text{Zr}-\text{O}$ ), the chemisorbed O, and the O in group  $\text{O}-\text{C}=\text{O}$ .<sup>48</sup> The O 1s spectra of the  $\text{UiO-66/g-C}_3\text{N}_4$ -30% sample (Fig. 5F) showed that three peaks at 530.69, 531.99, and 533.25 eV were attached to the O in the metal-bound crystal lattice ( $\text{Zr}-\text{O}$ ), chemisorbed O species, and O in the  $\text{O}-\text{C}=\text{O}$  group.<sup>48</sup> The high-resolution spectrum Zr 3d of the  $\text{UiO-66}$  sample (Fig. 5G) showed signals at 182.88 and 185.19 eV related to  $\text{Zr 3d}_{5/2}$  and  $\text{Zr 3d}_{3/2}$ , respectively. The high-resolution spectra Zr 3d of the  $\text{UiO-66}$  sample (Fig. 5H) showed signals at 181.92 and 184.75 eV related to  $\text{Zr 3d}_{5/2}$  and  $\text{Zr 3d}_{3/2}$ , respectively.<sup>49</sup> The N 1s spectra of the  $\text{g-C}_3\text{N}_4$  sample (Fig. 5K) showed three peaks attached to the binding energy  $\text{sp}^2 \text{ N}$  ( $\text{C}-\text{N}=\text{C}$ , 399.25 eV), tertiary N atom ( $\text{sp}^3 \text{ N}$ , 400.42 eV), and amine functional group ( $\text{C}_2\text{-NH}$ , 402.25 eV).<sup>50</sup> The high-resolution O 1s and Zr 3d XPS spectra of the  $\text{UiO-66/g-C}_3\text{N}_4$ -30% sample shifted to a lower binding energy region than that of the  $\text{UiO-66}$  sample; this was due to the shift in the electron from  $\text{g-C}_3\text{N}_4$  to  $\text{UiO-66}$ .<sup>50</sup>

### 3.2 The optical and electrochemical performances

The optical properties of the  $\text{g-C}_3\text{N}_4$ ,  $\text{UiO-66}$  and  $\text{UiO-66/g-C}_3\text{N}_4$  composites were analyzed by UV-vis DRS (Fig. 6A). The maximum light absorption boundary of  $\text{UiO-66}$  appeared in the UV range (380 nm), whereas the absorption edge of the  $\text{UiO-66/g-C}_3\text{N}_4$  and  $\text{g-C}_3\text{N}_4$  samples appeared in the visible region (450–550 nm). This outcome indicates that the *in situ* hydrothermal synthesis of the  $\text{UiO-66}$  sample onto the  $\text{g-C}_3\text{N}_4$  sheets increased the visible light absorption capacity of the  $\text{UiO-66/g-C}_3\text{N}_4$  materials. The bandgap energy ( $E_g$ ) of the  $\text{g-C}_3\text{N}_4$ ,  $\text{UiO-66}$ , and  $\text{UiO-66/g-C}_3\text{N}_4$  samples were estimated using a Tauc plot. The  $E_g$  values of the  $\text{UiO-66}$  and  $\text{g-C}_3\text{N}_4$  samples were 3.5 and 2.72 eV, respectively (Fig. 6B and Table 1). The  $E_g$  values of the  $\text{UiO-66/g-C}_3\text{N}_4$  samples were 2.82–3.28 eV (Fig. 6B and Table 1). The conduction band potentials ( $E_{\text{CB}}$ ) of the  $\text{g-C}_3\text{N}_4$ ,  $\text{UiO-66}$ , and  $\text{UiO-66/g-C}_3\text{N}_4$ -30 samples were determined by the Mott–Schottky plots (Fig. 6C). The  $E_{\text{CB}}$  values of  $\text{g-C}_3\text{N}_4$ ,  $\text{UiO-66}$ , and  $\text{UiO-66/g-C}_3\text{N}_4$ -30% were found to be –0.91, –0.66 and 0.78 eV, respectively. The valence band positions ( $E_{\text{VB}}$ ) can be estimated based on the relation between the  $E_g$  and  $E_{\text{CB}}$  (eqn (1)):

$$E_{\text{VB}} = E_g + E_{\text{CB}} \quad (1)$$

The  $E_{\text{VB}}$  value of  $\text{g-C}_3\text{N}_4$ ,  $\text{UiO-66}$ , and  $\text{UiO-66/g-C}_3\text{N}_4$ -30% were estimated to be 1.81, 2.84 and 2.13 eV, respectively. The PL spectra were used to evaluate the effect of  $\text{g-C}_3\text{N}_4$  on the recombination process of the hole and electron pairs in the  $\text{UiO-66/g-C}_3\text{N}_4$  samples.






Fig. 5 XPS survey spectra of UiO-66 (A) and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (B); high-resolution C 1s XPS spectra of UiO-66 (C) and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (D); high-resolution O 1s XPS spectra of UiO-66 (E) and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (F); high-resolution Zr 3d XPS spectra of UiO-66 (G) and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (H); high-resolution N 1s XPS spectra of UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (I).




Fig. 6 UV-vis diffuse reflectance spectra (A), band-gap energies (B), Mott–Schottky plot (C) and photoluminescence spectra (D) of g-C<sub>3</sub>N<sub>4</sub>, UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> composites.



66, g-C<sub>3</sub>N<sub>4</sub>, and UiO-66/g-C<sub>3</sub>N<sub>4</sub> materials (Fig. 6D). The g-C<sub>3</sub>N<sub>4</sub> sample showed an intense emission peak at 442 nm because of the electron-hole recombination and n- $\pi^*$  electron transition.<sup>39</sup> Meanwhile, sample UiO-66 had an emission peak at 440 nm because of the recombination of the electron and hole pairs.<sup>25</sup> The emission intensity at 440 nm was significantly reduced after applying UiO-66 to the g-C<sub>3</sub>N<sub>4</sub> sheets; the recombination of the electron and hole pairs in the material was reduced by the electron capture of g-C<sub>3</sub>N<sub>4</sub> by the UiO-66 material. The PL intensity of the samples decreased in the following order: g-C<sub>3</sub>N<sub>4</sub> > UiO-66 > UiO-66/g-C<sub>3</sub>N<sub>4</sub>-10% > UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% > UiO-66/g-C<sub>3</sub>N<sub>4</sub>-20% > UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30%.

### 3.3 Photocatalytic performances

The photocatalytic activity of the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples was evaluated by the decomposition of DMNP under visible light irradiation (Fig. 7A). The DMNP treatment efficiency over the g-C<sub>3</sub>N<sub>4</sub> photocatalyst reached 28.2% after 60 min of irradiation. Meanwhile, catalyst UiO-66 achieved a DMNP degradation efficiency of 54.65% after 60 min of reaction. Notably, the DMNP removal efficiency over the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples was significantly enhanced compared with that of bare g-C<sub>3</sub>N<sub>4</sub> or UiO-66. The DMNP removal efficiency over the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples increased from 86.84% to 98.55% with increasing g-C<sub>3</sub>N<sub>4</sub> content from 10 to 30 wt%. However, when the g-C<sub>3</sub>N<sub>4</sub> content increased to 40 wt%, the DMNP treatment efficiency decreased from 98.55% to 91.56%, which was due to the significant reduction in surface area and capillary volume (Table 1).

1). The significant increase in the DMNP processing efficiency of the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples was attributed to the enhancement of visible light absorption, as confirmed by the UV-vis DRS and PL results (Fig. 7 and Table 1). Moreover, the pore size of the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples was improved, making the phase contact of reactants more favorable instead of the contact between the catalysts and the phosphate ester linkage, which occurs only on the outer surface of the catalyst.<sup>3</sup> Additionally, the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples contained acidic Lewis octahedral Zr6 oxo clusters that cleaved the phosphate ester bond to yield dimethyl phosphate and 4-nitrophenol (Fig. S6†).<sup>11</sup>

Further, the effect of the photocatalyst dose on the photocatalytic activity of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample was investigated. When the amount of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample increased from 2 to 10 mol%, the degradation rate of the DMNP significantly increased from 84.1% to 98.9% after 60 min of light irradiation (Fig. 7B). This increase may be due to the uniform dispersion of the catalyst in a solution, which significantly increased the contact between the DMNP molecules and the active sites of the catalyst.<sup>24,48</sup> When increasing the catalyst dose from 12 mol%, the rate of the DMNP degradation reaction slightly increased. Thus, with a catalytic mass of 2, 4, 6, 8, and 12 mol%, the half-life of DMNP was 11.89, 6.95, 4.67, 2.38, and 2.17 min, respectively.

The kinetic curve of the adsorption and degradation of the DMNP by the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% samples are shown in Fig. 7C. In the dark, the UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% samples exhibited a low DMNP removal by adsorption




Fig. 7 The conversion of DMNP as a function of reaction time over g-C<sub>3</sub>N<sub>4</sub>, UiO-66, and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples (A), effect of different UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% catalysts does on the conversion of DMNP (B); the conversion of DMNP under dark and lighting conditions under dark and lighting conditions over UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% (C) and active species trapping experiments (D).



( $\approx 50\%$ ); this was because of the number of octahedral Zr6 oxo clusters of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% model was lower than that of UiO-66 (Table S1†). After 60 min of irradiation, the degradation rate of DMNP over UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% significantly increased to 98.9%, indicating the resonant light absorption effect between UiO-66 and g-C<sub>3</sub>N<sub>4</sub>. The DMNP removal rate over UiO-66 slightly increased under light irradiation because the UiO-66 catalyst had poor visible light absorption.<sup>51</sup>

The half-life of the DMNP based on previously published heterogeneous catalysts is presented in Table S2.† The shortest half-life of 1.6 min was reported by Song *et al.*<sup>8</sup> However, DMNP removal reactions are conventionally performed in 0.45 M *N*-ethylmorpholine buffer (pH of 10) to speed up DMNP removal. Daniel Bůžek *et al.*<sup>9</sup> used UiO-66 to hydrolyze DMNPs at a pH of 7, showing that the half-life of DMNP was 7 min. In this study, the heterogeneous catalyst, UiO-66/g-C<sub>3</sub>N<sub>4</sub>, degraded DMNP with a half-life of 2.38 min, which indicates that UiO-66/g-C<sub>3</sub>N<sub>4</sub> is a fast DMNP-removing photocatalyst.

The UV-vis spectra of DMNP (Fig. S7†) in water showed that the wavelength intensity at 280 nm decreased because of the decomposition of the DMNP, and the wavelength intensity at 403 nm increased because of the formation of a hydrolysis product, 4-nitrophenoxide. Fig. S8† shows that DMNP was mixed with 0.15 M *N*-ethylmorpholine buffer, and with increasing sunlight irradiation time, the color of the transparent solution gradually changed to pale yellow.

The LC-MS spectra of the UiO-66 sample (Fig. S9A†) showed that the products of the hydrolysis of DMNPs in water (pH of 7) included dimethyl phosphate (*m/z* of 126.08), methyl phosphate (*m/z* of 109.24), 4-nitrophenol (*m/z* of 137.80), and methyl 4-nitrophenyl phosphate (*m/z* of 231.77). Notably, methyl 4-nitrophenyl phosphate is more toxic than the DMNP.<sup>2</sup> The LC-MS spectra of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample (Fig. S9B†) showed that the products of the photocatalysis and hydrolysis of DMNPs were mainly dimethyl phosphate (*m/z* of 126.12), methyl phosphate (*m/z* of 109.23), and 4-nitrophenol (*m/z* of 137.83). This result showed that the degradation of DMNPs by the combination of hydrolysis and photocatalysis afforded less-toxic products than conventional hydrolysis in aqueous media. Additionally, the products of hydrolysis and photocatalysis can oxidize these organic compounds to CO<sub>2</sub> and H<sub>2</sub>O.

The stability of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample was confirmed by repeating the DMNP removal reaction for five catalytic regenerations (Fig. S10†). The DMNP removal efficiency remained unchanged after five reaction cycles, indicating that the photocatalytic activity of the UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% sample was highly stable. The stability of UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% was further confirmed by the XRD results because no noticeable difference was found between the XRD patterns of UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% before and after reaction (Fig. S11†).

### 3.4 Mechanism of the photocatalytic reaction

To determine the role of free radicals in the DMNP removal efficiency, reactive radical trapping experiments were performed. Radical scavengers, including AO, TBA, K<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub>, and BQ, were employed to capture h<sup>+</sup>, ·OH, e<sup>-</sup> and ·O<sub>2</sub><sup>-</sup>, respectively.<sup>52</sup> As shown in Fig. 7D, the degradation rate of DMNPs was strongly influenced by AO and BQ, indicating that the h<sup>+</sup> and ·O<sub>2</sub><sup>-</sup> radicals had a strong influence on the degradation of DMNP. Meanwhile, TBA and K<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> slightly decreased the removal rate of DMNPs. Thus, ·O<sub>2</sub><sup>-</sup> radicals play an essential role in the degradation of DMNP. Based on the UV-vis DRS and Mott-Schottky plots measurements above, we analyzed the band structure of the g-C<sub>3</sub>N<sub>4</sub>, UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples (Fig. 8A). The E<sub>CB</sub> values of g-C<sub>3</sub>N<sub>4</sub>, UiO-66 and UiO-66/g-C<sub>3</sub>N<sub>4</sub>-30% were estimated to be -0.91, -0.66 and -0.78 eV, respectively, which can produce ·O<sub>2</sub><sup>-</sup> radicals because the CB positions of the samples were more negative than the redox potential of O<sub>2</sub>/·O<sub>2</sub><sup>-</sup> (-0.33 eV). The ·OH radicals can be generated on the surface of UiO-66 because the VB position of UiO-66 (+2.48 eV) was more positive than the standard potential of ·OH/H<sub>2</sub>O (+2.40 eV). For the g-C<sub>3</sub>N<sub>4</sub> sample, ·OH radicals cannot be generated on the surface of g-C<sub>3</sub>N<sub>4</sub> because the VB position of g-C<sub>3</sub>N<sub>4</sub> (+1.81 eV) was less than the standard potential of ·OH/H<sub>2</sub>O.

Based on previous studies<sup>16,26-28</sup> and an experimental database, we proposed the photocatalytic mechanism of sample UiO-66/g-C<sub>3</sub>N<sub>4</sub>, as illustrated in Fig. 8B. The heterojunction catalyst UiO-66/g-C<sub>3</sub>N<sub>4</sub> was formed by light integration between UiO-66 and g-C<sub>3</sub>N<sub>4</sub> with the appropriate CB and VB sites. Under solar light irradiation, a heterojunction was formed between UiO-66 and g-C<sub>3</sub>N<sub>4</sub>. First, when the g-C<sub>3</sub>N<sub>4</sub> and UiO-66 catalysts




Fig. 8 The schematic of the separation and transfer of photogenerated charges over UiO-66/g-C<sub>3</sub>N<sub>4</sub> before contact (A) and after contact (B).



were exposed to a light source greater than the bandgap energy of the material, the  $e^-$  moved from CB binding to VB binding to form  $e^-$  in CB and  $h^+$  in VB as reducing and oxidizing agents, respectively, (eqn (2)).



Thereafter, the  $e^-$  in the CB of UiO-66 recombined with the  $h^+$  in the VB of g-C<sub>3</sub>N<sub>4</sub>. The  $e^-$  in CB of g-C<sub>3</sub>N<sub>4</sub> reacted with the O<sub>2</sub> adsorbed on the surface of g-C<sub>3</sub>N<sub>4</sub> to generate 'O<sub>2</sub><sup>-</sup> radicals (eqn (3)).



Besides, the  $h^+$  in the VB position of UiO-66 reacted with H<sub>2</sub>O to form 'OH radicals (eqn (4)).



Finally, the radicals, such as 'O<sub>2</sub><sup>-</sup>,  $h^+$ , and 'OH, oxidized the DMNP molecule to afford less-toxic products (eqn (5)).



## 4 Conclusions

UiO-66 was successfully synthesized using an H<sub>2</sub>BDC linker obtained from waste plastic. Afterward, this material was combined with g-C<sub>3</sub>N<sub>4</sub> to form a p-n UiO-66/g-C<sub>3</sub>N<sub>4</sub> heterojunction composite as an effective photocatalyst for the conversion of DMNP to non-toxic compounds. The UiO-66/g-C<sub>3</sub>N<sub>4</sub> material exhibited a high surface area (1440 m<sup>2</sup> g<sup>-1</sup>) and a high capillary volume (1.49 cm<sup>3</sup> g<sup>-1</sup>). Additionally, the as-developed UiO-66/g-C<sub>3</sub>N<sub>4</sub> heterojunction composite enhanced the ability to harvest visible light and restrict the recombination of photogenerated electrons and holes. This outcome was presented by UV-vis DRS, PL, and photoelectrochemical test data. Further, compared to the bare UiO-66 and g-C<sub>3</sub>N<sub>4</sub>, the UiO-66/g-C<sub>3</sub>N<sub>4</sub> samples exhibited the rapid oxidation degradation of DMNP with a short half-life ( $t_{1/2}$  of 2.17 min) under mild conditions. Our study is expected to shed light on the design of more efficient MOF-based catalysts for the conversion of CWAs to non-toxic compounds.

## Author contributions

Dung Van Le: writing – original draft, methodology, data curation. Manh B. Nguyen: writing – original draft, data curation, visualization. Phuong T. Dang: writing – review & editing, supervision. Taeyoon Lee: writing – review & editing, methodology, formal analysis. Trinh Duy Nguyen: conceptualization, writing – review & editing, supervision.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This research is funded by Graduate University of Science and Technology under Grant Number GUST.STS.DT2019-HH04.

## References

- I. M. Raju, T. S. Rao, K. V. D. Lakshmi, M. R. Chandra, J. S. Padmaja and G. Divya, *J. Environ. Chem. Eng.*, 2019, **7**, 103211.
- C. Wilson, N. J. Cooper, M. E. Briggs, A. I. Cooper and D. J. Adams, *Org. Biomol. Chem.*, 2018, **16**, 9285–9291.
- M. J. Katz, J. E. Mondloch, R. K. Totten, J. K. Park, S. T. Nguyen, O. K. Farha and J. T. Hupp, *Angew. Chem., Int. Ed.*, 2014, **53**, 497–501.
- A. Yao, X. Jiao, D. Chen and C. Li, *ACS Appl. Mater. Interfaces*, 2020, **12**, 18437–18445.
- J. Dong, J. Hu, Y. Chi, Z. Lin, B. Zou, S. Yang, C. L. Hill and C. Hu, *Angew. Chem., Int. Ed.*, 2017, **56**, 4473–4477.
- M. C. de Koning, M. van Grol and T. Breijaert, *Inorg. Chem.*, 2017, **56**, 11804–11809.
- Y. Hou, H. An, Y. Zhang, T. Hu, W. Yang and S. Chang, *ACS Catal.*, 2018, **8**, 6062–6069.
- L. Song, T. Zhao, D. Yang, X. Wang, X. Hao, Y. Liu, S. Zhang and Z.-Z. Yu, *J. Hazard. Mater.*, 2020, **393**, 122332.
- D. Bůžek, J. Demel and K. Lang, *Inorg. Chem.*, 2018, **57**, 14290–14297.
- R. Gil-San-Millan, E. López-Maya, M. Hall, N. M. Padial, G. W. Peterson, J. B. DeCoste, L. M. Rodríguez-Albelo, J. E. Oltra, E. Barea and J. A. R. Navarro, *ACS Appl. Mater. Interfaces*, 2017, **9**, 23967–23973.
- R. Gil-San-Millan, E. López-Maya, A. E. Platero-Prats, V. Torres-Pérez, P. Delgado, A. W. Augustyniak, M. K. Kim, H. W. Lee, S. G. Ryu and J. A. R. Navarro, *J. Am. Chem. Soc.*, 2019, **141**, 11801–11805.
- H.-B. Luo, A. J. Castro, M. C. Wasson, W. Flores, O. K. Farha and Y. Liu, *ACS Catal.*, 2021, **11**, 1424–1429.
- N. Iqbal, A. Afzal, I. Khan, M. S. Khan and A. Qurashi, *Sci. Rep.*, 2021, **11**, 16886.
- A. K. Singh, N. Jaiswal, R. K. Gautam and I. Tiwari, *J. Electroanal. Chem.*, 2021, **887**, 115170.
- J. L. Silva, B. Brena and C. M. Araujo, *J. Phys. Chem. C*, 2020, **124**, 8726–8735.
- F. Chang, Y. Xie, C. Li, J. Chen, J. Luo, X. Hu and J. Shen, *Appl. Surf. Sci.*, 2013, **280**, 967–974.
- L. Liu, H. Huang, Z. Chen, H. Yu, K. Wang, J. Huang, H. Yu and Y. Zhang, *Angew. Chem., Int. Ed.*, 2021, **60**, 18303–18308.
- F. Chen, Z. Ma, L. Ye, T. Ma, T. Zhang, Y. Zhang and H. Huang, *Adv. Mater.*, 2020, **32**, 1908350.
- S. Wang, X. Han, Y. Zhang, N. Tian, T. Ma and H. Huang, *Small Struct.*, 2021, **2**, 2000061.
- J. Wen, J. Xie, X. Chen and X. Li, *Appl. Surf. Sci.*, 2017, **391**, 72–123.
- M. Ismael and Y. Wu, *Sustainable Energy Fuels*, 2019, **3**, 2907–2925.
- T. Wang, C. Nie, Z. Ao, S. Wang and T. An, *J. Mater. Chem. A*, 2020, **8**, 485–502.



23 A. Naseri, M. Samadi, A. Pourjavadi, A. Z. Moshfegh and S. Ramakrishna, *J. Mater. Chem. A*, 2017, **5**, 23406–23433.

24 X. N. Pham, H. T. Nguyen, T. N. Pham, T.-T.-B. Nguyen, M. B. Nguyen, V. T.-T. Tran and H. V. Doan, *J. Taiwan Inst. Chem. Eng.*, 2020, **114**, 91–102.

25 M. Hassannezhad, M. Hosseini, M. R. Ganjali and M. Arvand, *Anal. Methods*, 2019, **11**, 2064–2071.

26 G. Liao, C. Li, X. Li and B. Fang, *Cell Rep. Phys. Sci.*, 2021, **2**, 100355.

27 G. Liao, Y. Gong, L. Zhang, H. Gao, G.-J. Yang and B. Fang, *Energy Environ. Sci.*, 2019, **12**, 2080–2147.

28 G. Liao, C. Li, S. Y. Liu, B. Fang and H. Yang, *Trends Chem.*, 2022, **4**, 111–127.

29 L. Jiang, X. Yuan, Y. Pan, J. Liang, G. Zeng, Z. Wu and H. Wang, *Appl. Catal., B*, 2017, **217**, 388–406.

30 Y. Li, Y. Fang, Z. Cao, N. Li, D. Chen, Q. Xu and J. Lu, *Appl. Catal., B*, 2019, **250**, 150–162.

31 Y. Zhou, W. Lv, B. Zhu, F. Tong, J. Pan, J. Bai, Q. Zhou and H. Qin, *ACS Sustainable Chem. Eng.*, 2019, **7**, 5801–5807.

32 X. Zhang, Y. Yang, W. Huang, Y. Yang, Y. Wang, C. He, N. Liu, M. Wu and L. Tang, *Mater. Res. Bull.*, 2018, **99**, 349–358.

33 J. H. Zhang, Y. J. Hou, S. J. Wang, X. Zhu, C. Y. Zhu, Z. Wang, C. J. Li, J. J. Jiang, H. P. Wang, M. Pan and C. Y. Su, *J. Mater. Chem. A*, 2018, **6**, 18252–18257.

34 J. E. Mondloch, M. J. Katz, W. C. Isley III, P. Ghosh, P. Liao, W. Bury, G. W. Wagner, M. G. Hall, J. B. DeCoste, G. W. Peterson, R. Q. Snurr, C. J. Cramer, J. T. Hupp and O. K. Farha, *Nat. Mater.*, 2015, **14**, 512–516.

35 C. Hu, W.-F. Tsai, W.-H. Wei, K.-Y. A. Lin, M.-T. Liu and K. Nakagawa, *Carbon*, 2021, **175**, 467–477.

36 Z. S. Moghaddam, M. Kaykhaii, M. Khajeh and A. R. Oveisi, *Spectrochim. Acta, Part A*, 2018, **194**, 76–82.

37 J. H. Cavka, S. Jakobsen, U. Olsbye, N. Guillou, C. Lamberti, S. Bordiga and K. P. Lillerud, *J. Am. Chem. Soc.*, 2008, **130**, 13850–13851.

38 N. Tian, H. Huang and Y. Zhang, *Appl. Surf. Sci.*, 2015, **358**, 343–349.

39 N. T. Dung, N. V. Hiep, M. B. Nguyen, V. D. Thao and N. N. Huy, *Korean J. Chem. Eng.*, 2021, **38**, 2034–2046.

40 R. Ye, H. Fang, Y.-Z. Zheng, N. Li, Y. Wang and X. Tao, *ACS Appl. Mater. Interfaces*, 2016, **8**, 13879–13889.

41 J. Ma, Q. Yang, Y. Wen and W. Liu, *Appl. Catal., B*, 2017, **201**, 232–240.

42 M. D. Donohue and G. L. Aranovich, *Adv. Colloid Interface Sci.*, 1998, **76**–77, 137–152.

43 N. Assaad, G. Sabeh and M. Hmadeh, *ACS Appl. Nano Mater.*, 2020, **3**, 8997–9008.

44 Y. Liu, A. J. Howarth, N. A. Vermeulen, S.-Y. Moon, J. T. Hupp and O. K. Farha, *Coord. Chem. Rev.*, 2017, **346**, 101–111.

45 G. W. Peterson, M. R. Destefano, S. J. Garibay, A. Ploskonka, M. McEntee, M. Hall, C. J. Karwacki, J. T. Hupp and O. K. Farha, *Chem. – Eur. J.*, 2017, **23**, 15913–15916.

46 S. Pareek and J. K. Quamara, *J. Mater. Sci.*, 2018, **53**, 604–612.

47 R. Zhang, B. Du, Q. Li, Z. Cao, G. Feng and X. Wang, *Appl. Surf. Sci.*, 2019, **466**, 956–963.

48 M. B. Nguyen, G. H. Le, T. D. Nguyen, Q. K. Nguyen, T. T. Pham, T. Lee and T. A. Vu, *J. Hazard. Mater.*, 2021, **420**, 126560.

49 A. S. Eltaweil, E. M. A. El-Monaem, G. M. El-Subruiti, M. M. A. El-Latif and A. M. Omer, *RSC Adv.*, 2020, **10**, 19008–19019.

50 B. Ng, L. K. Putri, X. Y. Kong, Y. W. Teh, P. Pasbakhsh and S. Chai, *Adv. Sci.*, 2020, **7**, 1903171.

51 M. Taddei, G. M. Schukraft, M. E. A. Warwick, D. Tiana, M. J. McPherson, D. R. Jones and C. Petit, *J. Mater. Chem. A*, 2019, **7**, 23781–23786.

52 M. B. Nguyen, X. N. Pham and H. V. Doan, *RSC Adv.*, 2021, **11**, 31738–31745.

