RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2022, 12, 24439

Received 8th June 2022 Accepted 22nd August 2022

DOI: 10.1039/d2ra03545f

rsc.li/rsc-advances

Introduction

Removal of methyl orange from water by Fenton oxidation of magnetic coconut-clothed biochar

Jia Xu, ២ Qianhui Ma, Wen Feng, Xiaopeng Zhang, ២ Qiang Lin, ២ Chenghang You 🖻 * and Xianghui Wang *

Water pollution has become a serious environmental problem to date. Advanced oxidation processes (AOP) have been widely applied in water treatments. However, the traditional Fenton reaction based on the Fe²⁺– H₂O₂ system has obvious drawbacks, limiting further practical applications. In this work, an Fe₃O₄ and nano-clothed biochar (Fe₃O₄/CBc) composite was prepared through a precipitation method and used for the degradation of methyl orange (MO) in water. The Fe₃O₄/CBc composite was characterized by FTIR, BET, SEM, TEM, XRD, and VSM. In addition, the adsorption/catalytic oxidation of MO were also tested. Specifically, Fe₃O₄/CBc had a rough surface, abundant porous structure, high surface area of 835.82 m² g⁻¹, and obvious magnetization. The catalyst showed rather high performance towards MO removal. The optimal conditions for MO removal were as follows: the dosage of hydrogen peroxide was 16 mmol L⁻¹, pH = 3, the temperature was 35 °C, and the addition amount of adsorbent was 10 mg. Under optimal conditions, the MO removal rate can be higher than 99%. The synergistic effect between catalytic degradation and adsorption in removing MO was also observed. Besides high performance in removing MO, Fe₃O₄/CBc also exhibited high stability, easy magnetic separation, and great reusability, as well as the potential to be developed as a new heterogeneous Fenton catalyst.

With the continuous development of modern industry, water pollution is becoming more and more serious. For example, the textile industry is one of the most important industries. There are many production processes in this industry, which have produced highly polluted wastewater containing dyes with different structures. If the treatment method is improper, this kind of wastewater has color and toxicity, which will cause serious environmental problems. Therefore, it is urgent to develop efficient approaches to control water pollution. As compared with other advanced oxidation processes, the Fenton reaction¹ is an advanced oxidation method with the advantages of mild conditions, low cost, and high efficiency. It can oxidize and degrade almost all kinds of organic pollutants without selectivity.^{2,3} Therefore, it has been widely used in wastewater treatments in areas like papermaking, printing, dyeing, etc. Unfortunately, the traditional Fenton reaction⁴⁻⁶ usually suffers from several defects including difficult reuse of catalyst, low utilization of H2O2, and easy production of iron sludge. Thus, it would be of great importance to improve the Fenton system7 in water treatment.

Fe₃O₄ NPs have the characteristics of super-paramagnetism, great thermal stability, high reaction activity, and simple preparation.8-10 They can replace Fe2+ in the traditional homogeneous Fenton reaction and stimulate H2O2 to produce 'OH as a new Fenton reaction catalyst. It not only retains the characteristics of high catalytic activity of Fenton reaction, but also utilizes magnetic separation with efficient recovery, which might overcome the defects of homogeneous Fenton reactions and attract extensive attention. In this work, a superparamagnetic Fenton catalyst (Fe₃O₄/CBc) was fabricated by loading Fe₃O₄ NPs on coconut-clothed biochar^{11,12} through an in situ precipitation procedure.13 Methyl orange (MO) was selected as the target pollutant to evaluate the degradation performance of organic contaminants. The effects of addition amount, H2O2 content, pH, temperature, and free radical inhibitor on MO removal were also studied.14

Experimental

Reagents

Self-made coconut-clothed (coconut-clothed was obtained from the discarded coconuts after eating). KOH, HCL, Methyl orange (MO), FeCl₃·6H₂O, FeCl₂·7H₂O, 30% H₂O₂ and C₂H₅OH were ordered from Sinopharm Chemical Reagent Co., Ltd All reagents were analytical pure grade.

Preparation of modified coconut-clothed biochar (CBc). Coconut-clothed material (5.0 g), KOH (15.0 g), and deionized

Key Laboratory of Water Pollution Treatment and Resource Reuse of Hainan Province, Key Laboratory of Soil Pollution Remediation and Resource Reuse of Haikou City, College of Chemistry and Chemical Engineering, Hainan Normal University, Haikou 571158, China. E-mail: youchh@163.com; god820403@163.com

water (50 mL) were placed in a 100 mL glass beaker. The mixture was stirred for 2 h, which was then placed into an oven at 80 °C for drying. The dried sample was placed in a quartz boat and pyrolyzed at 700 °C for 270 min with a heating rate of $10 \,^{\circ}$ C min⁻¹ under the protection of pure nitrogen. After cooling down naturally, the sample obtained was washed to neutral and dried at 70 °C under the vacuum.

Preparation for Fe₃O₄/CBc. Deionized water (300 mL) was added into a 500 mL three-port flask equipped with a mechanical stirring device. Nitrogen was purged into the flask for 30 min to remove the air inside the flask. Then $FeCl_3 \cdot 6H_2O$ (4.49 g, 16.61 mmol) and FeSO₄ · 7H₂O (2.31 g, 8.30 mmol) were added and stirred for 20 min to obtain a homogeneous orangered solution. Then CBc (1.9 g, the mass ratio of CBc and Fe₃O₄ is (1:1) was added and stirred for another 3 h before adjusting the pH to about 10 using NH₃·H₂O. The obtained black suspension was aged at 60 °C for 4 h, followed by cooling down naturally, separating by a magnet, washing with deionized water five times and C₂H₅OH three times, and drying at 60 °C under the vacuum over 20 h. Finally, the biomass carbon composite was obtained and named as Fe₃O₄/CBc. Samples with other proportions $(m(CBc): m(Fe_3O_4) = 3: 1, 2: 1)$ were also prepared through the same above experimental steps.

MO Removal experiments

Methyl orange solution (25 mL, 100 mg L^{-1}) was added into a 50 mL conical flask to simulate wastewater. The pH of the solution was adjusted with 0.1 mol L^{-1} hydrochloric acid or sodium hydroxide. After adding a certain mass of H_2O_2 and Fe_3O_4/CBc , the mixture was vibrated for 120 min under room temperature. After that, the concentration of methyl orange was measured using visible spectrophotometry.

Characterizations

Brunauer–Emmett–Teller (ASAP2460) was used to measure the nitrogen adsorption capacity of samples at 77 K and the specific surface area of each sample. Scanning electron microscopy (JSM-7401F) and Transmission electron microscopy (JEM-F200) were employed to record the micro surface morphology of materials. Fourier transform infrared spectroscopy (FT-IR6700) was used for further infrared spectrum analysis of materials. X-ray diffraction (UItima IV) was utilized to test the crystal structure of materials. Vibrating sample magnetometer (SQUID-VSM) was used to test the hysteresis loop of catalyst. The concentration change of methyl orange solution was analyzed by a ultraviolet-visible spectrophotometer (UV, 752N).

Results and discussion

SEM, TEM, and EDS analysis

The morphology and structure of the as-prepared catalysts were characterized by SEM and TEM. As shown in Fig. 1a and d, the CBc had a rather rough surface with numerous porous structures,^{15,16} and the Fe_3O_4 nanoparticles had an average diameter of about 50 nm and the surface was rough, which can be attributed to the fact that each Fe_3O_4 nanospheres are

BET analysis

The surface area and the porosity of the CBc and Fe_3O_4/CBc were summarized in Fig. 2. In Fig. 2, the surface area of the CBc was higher as compared to the surface area of the Fe_3O_4/CBc . The immobilization of the Fe_3O_4 on the biochar surface didn't provide the additional surface area for adsorption, which is possible due to the particles clogged the pores in the surface of the biochar. In fact, the pore volume of the Fe_3O_4/CBc was slightly lower as compared to that of the CBc, which changed from 0.475 cm³ g⁻¹ to 0.411 cm³ g⁻¹. It indicated that the introduction of Fe_3O_4 nanoparticles can make the surface of the material rough, in which the nanoparticles were overlapped and piled up with each other, resulting in the reduction of the empty volume and the decrease of the specific surface area.

FT-IR analysis

The IR spectra of the CBc and Fe₃O₄/CBc were shown in Fig. 3. CBc and Fe₃O₄/CBc composite had roughly the same absorption peaks. The adsorption peaks around 3420, 891, and 1620 cm⁻¹ can be assigned to the stretching vibration peaks of O–H, C=C, and C=O, respectively, indicating that the surface of the composite was rich in oxygen-containing functional groups, which was conducive to the adsorption of organic compounds. Specifically, Fe₃O₄/CBc showed an absorption peak at 607 cm⁻¹ in the infrared image, which was the bending vibration peak of Fe–O–Fe,^{18,19} suggesting that Fe₃O₄ was successfully loaded on the surface of coconut-clothed biochar.

XRD analysis

As shown in Fig. 4, the Fe_3O_4/CBc composite had five diffraction peaks at 30.56, 35.58, 43.32, 57.2, and 62.84°, which were consistent with the characteristic peaks of Fe_3O_4 .

VSM analysis

Fig. 5 showed the hysteresis loops of Fe_3O_4 and Fe_3O_4/CBc . It can be found that Fe_3O_4/CBc had a saturation magnetization of 23.4 emu g^{-1} , *vs.* 69.48 emu g^{-1} for Fe_3O_4 . There was no hysteresis phenomenon. Furthermore, the values of residual coercivity and magnetization were zero, which reflects that the target materials were superparamagnetic.²⁰ Although the saturation magnetization of the composite was less than that of Fe_3O_4 , the value was still higher than 16.3 emu g^{-1} ,²¹ which was required for general magnetic separations. Therefore, Fe_3O_4 /CBc can be easily separated through the external magnetic field, which can be further confirmed by the rapid magnetic separation of the catalyst.



Fig. 1 SEM, TEM, EDS, and HRTEM of CBc and Fe₃O₄/CBc. (a) CBc SEM. (b) Fe₃O₄/CBc SEM. (c) Fe₃O₄/CBc EDS. (d) Fe₃O₄/CBc TEM. (e) Fe₃O₄/CBc HRTEM.

Removal effect of MO under different conditions

As shown in Fig. 6, the removal effect of MO was studied under different conditions. The initial temperature was 25 °C, the initial pH was 3.0, the amount of catalyst was 5 mg and the concentration of $30\% H_2O_2$ was 16 mmol L⁻¹.

The experimental results showed that when sole H_2O_2 was added, the MO removal rate was only 10.3%. This was because H_2O_2 without the presence of a catalyst produces 'OH slowly and cannot achieve rapid oxidative degradation of MO. When Fe_3O_4 was used alone, since Fe_3O_4 cannot produce 'OH, MO was removed only by the adsorption of Fe_3O_4 . As a reasonable result, the MO removal rate was very low (6.1%). For Fe_3O_4/CBc , it can be found that it can exhibit a MO removal rate of 59.8%, much higher than those using sole CBc or Fe₃O₄, suggesting that there might exist a synergistic effect between CBc and Fe₃O₄. In the catalyst/hydrogen peroxide system, the catalytic degradation rate of MO by Fe₃O₄/CBc was much higher than that using Fe₃O₄ alone, and the MO removal rate was as high as 78.9% in the first 45 min, much higher than those of adding H₂O₂ and Fe₃O₄ + H₂O groups. This result should be attributed to the more 'OH due to the interaction between Fe₃O₄ and H₂O₂, which can easily attack the MO adsorbed on the surface of CBc. Therefore, the efficient removal of MO by Fe₃O₄/CBc and hydrogen peroxide system was resulted from the synergistic effect of efficient catalytic oxidation and CBc adsorption.



Fig. 2 Nitrogen adsorption and desorption curve and pore size distribution of CBc and ${\rm Fe}_3{\rm O}_4/{\rm CBc}.$



Fig. 3 FT-IR spectra of CBc and Fe_3O_4/CBc .



Fig. 4 XRD patterns of CBc and Fe_3O_4/CBc .



Fig. 5 Magnetization curves of CBc and Fe₃O₄/CBc composites.

Effect of the amount of Fe_3O_4/CBc and H_2O_2 on the degradation of MO

The effect of Fe_3O_4/CBc and H_2O_2 usages on the MO removal were shown in Fig. 7 and 8, respectively. The MO removal rate increased from 41.9% to 99.4% as Fe_3O_4/CBc usage raised from 1 mg to 10 mg. In addition, the removal rate of MO was enhanced with the increase of Fe_3O_4/CBc amount. When the addition amount of catalyst was fixed to be 5.0 mg, the MO removal rate increased from 70.2% to 76.8% as the hydrogen peroxide usage increased from 10 to 100 µL. When the addition amount of hydrogen peroxide exceeds 16 mmol L⁻¹, the removal rate of MO also decreased slightly.

According to research reports, we proposed the possible mechanism of the Fenton reaction *as follows*:

$$Fe^{2+} + H_2O_2 \rightarrow Fe^{3+} + OH^- + OH$$
 (1)

$$Fe^{3+} + H_2O_2 \rightarrow Fe^{2+} + H^+ + O_2H$$
 (2)



Fig. 6 Effect of different conditions on MO removal.



Fig. 7 Fe_3O_4/CBc Effect of addition amount on oxidation and degradation of MO.

$$Fe^{2+} + OH \rightarrow Fe^{3+} + OH^{-}$$
 (3)

$$Fe^{3+} + O_2H \rightarrow Fe^{2+} + H^+ + O_2$$
 (4)

$$H_2O_2 \cdot + OH \to H_2O \cdot + O_2H$$
(5)

From the reaction mechanism, when the amount of Fe_3O_4/CBc and H_2O_2 is sufficient,²² the Fe^{2+} reacted sufficiently with H_2O_2 to produce hydroxyl radicals. When the amount of Fe_3O_4/CBc and hydrogen peroxide was gradually increased, the formed 'OH increases, which can improve MO removal;²³ However, when the addition amount of Fe_3O_4/CBc or H_2O_2 exceeded the critical value, excess 'OH would act with H_2O_2 to quench the free radical reaction, which was not conducive to the oxidative degradation of MO.

Effect of initial pH value on MO degradation process

At an ambient temperature of 25 °C, the dosage of Fe_3O_4/CBc was 5 mg and the concentration of 30% hydrogen peroxide was 15.99 mmol L^{-1} . The influence of the solution pH values on the



Fig. 8 Effect of hydrogen peroxide addition on MO oxidation and degradation process.

MO degradation was also studied, as is shown in Fig. 8. As seen from Fig. 9a that the pH of the solution has a great influence. With the pH value between 5 and 8, the removal efficiency was low, which should be attributed to the formation of hydrate iron and hydrated ferrous complexes. Since the divalent iron ions cannot be effectively dissociated, the generation of 'OH was inhibited, resulting in the obvious weakening of the oxidative degradation ability of Fenton system.²⁴ In this case, the removal of MO mainly depended on the adsorption of catalyst materials. When the pH of the solution was between 2 and 4, there was electrostatic adsorption between Fe₃O₄/CBc and MO, which increases the adsorption capacity of MO at lower pH, as well as the contact of active sites, and eventually improves the degradation rate. When the pH value was 4, the MO removal rate was 53.3%, and when the pH value was 3, the MO removal rate reached up to 78.6%. So the best removal rate can be obtained with the pH at 3.

In Fig. 9b, when the pH values were 4, 3 and 2, the dissolution amount of Fe were 0.34 mg $L^{-1},\ 3.89$ mg L^{-1} and



Fig. 9 Effect of initial pH value on MO degradation.



12.6 mg L^{-1} respectively. The dissolution amount of Fe increased as the pH decreases. The change of Fe dissolution amount can directly reflect the relationship between MO removal rate and pH value. Finally, Fe²⁺ produced in Fenton system reached up to the critical value when the pH value was 3;²⁵ When the pH value was 2, because the dissolution of Fe exceeded the adjacent value, the free radical quenching reaction between H₂O₂ and 'OH occurred, resulting in the decrease of the concentration of hydrogen peroxide and 'OH in the system. At the same time, due to the synergistic effect of adsorption, the MO removal rate did not significantly change. Considering the environmental impact and the analysis of the experimental results, the optimal pH value in the experiment was 3.

Effect of ambient temperature on the degradation process of MO

When the initial pH of the solution was 3, the dosage of $Fe_3O_4/$ CBc was 2 mg and the dosage of H_2O_2 was 16 mmol L^{-1} . The effect of temperature on the MO removal process was shown in Fig. 10. The experimental results showed that at 25 °C, 35 °C, and 45 °C, the removal rates of MO were 78.9%, 82.2%, and 87.3% respectively. It was proved that a higher temperature can facilitate the removal of MO due to the higher dissolution of Fe and the faster reaction rates at a higher temperature. However, if the temperature was too high, the decomposition rate of hydrogen peroxide was also accelerated and additional facilities or equipment were required to maintain the reaction temperature, resulting in a large amount of energy consumption. Therefore, based on the cost assessment, the reaction was carried out at room temperature. Since the heat energy can be improved in combination with the production process, 35 °C would be the best treatment temperature.

Effect of inhibitors on MO degradation

MO degradation reaction was carried out by the Fenton reaction,^{26,27} which depends on the strong oxidizing free radical 'OH produced by the system. Therefore, the free radical scavenger in the reaction system would have a very direct impact on the degradation process of MO. In the experiment, the dosage of Fe_3O_4/CBc was 5 mg and the dosage of H_2O_2 was 16 mmol L⁻¹. When the initial pH of the solution was 3 and the temperature was 25 °C, t-butanol was used as a free radical scavenger to explore the relationship between the removal effect of MO and the addition amount of t-butanol. The experimental results were shown in Fig. 11. There was a close relationship between the MO removal rates and the additional amounts of tert butyl. With only 10 µL t-butanol addition, the MO removal rate decreased drastically from 99.6% to 86.3%. When the t-butanol usage reached up to 39 mmol L⁻¹, the MO²⁸ removal rate decreased to only 60.5%. When the addition amount of tbutanol continued to increase up to 78 mmol L^{-1} , the MO removal rate was no longer changed. According to the experimental data, when the amount of t-butanol was more than 39 mmol L^{-1} , the Fenton system was almost completely inhibited, resulting in the complete stop of oxidative degradation, the MO removal mainly depended on the adsorption of MO by Fe₃O₄/CBc (Fig. 7, the adsorption of MO on Fe₃O₄/CBc was 59.5% without H_2O_2). Therefore, the existence of free radical inhibitors like t-butanol should be avoided in the Fenton reaction system.



Fig. 11 Effect of *t*-butanol inhibitor on MO removal.



Fig. 12 The effect of catalyst reuse on MO removal and the dissolution of Fe.

Catalyst regeneration performance

When the initial pH of the solution was 3, the ambient temperature was 25 °C, the dosage of Fe₃O₄/CBc was 10 mg and the dosage of H_2O_2 was 16 mmol L⁻¹ to test the reuse efficiency of the catalyst. After the experiment, the Fe₃O₄/CBc was separated by magnetic separation, washed with deionized water and microwaved for 1 h, and reuse 4 times. The experimental data were shown in Fig. 12. After the catalyst was utilized five times, the MO removal rates showed a downward trend, and the removal rates of MO were 99.4%, 98.2%, 94.3%, and 86.7% respectively. Although the removal efficiency slightly decreased, it was still higher than 85%, indicating that it had a great reuse rate. There might be two reasons for the decline of the MO removal effect. On the one hand, there was a certain loss of Fe₃O₄ in the degradation process. The dissolution amount of Fe decreased from 3.89 to 2.67 mg L^{-1} with the increase in catalyst use times, resulting in the decline of catalytic efficiency. On the other hand, some MO molecules were firmly adsorbed on the material surface, which occupied the adsorbed active sites and cannot be effectively removed by activation. In a comprehensive analysis, Fe₃O₄/CBc was stable,^{29,30} easily separately, and had a high reuse efficiency.

Conclusion

In summary, a Fe₃O₄ and coconut-clothed biochar (Fe₃O₄/CBc) composite is prepared through a precipitation method and employed for the degradation of methyl orange (MO) in water. The Fe₃O₄/CBc composite was characterized by FTIR, BET, SEM, TEM, XRD, and VSM. The adsorption and catalytic oxidation of MO were also tested. Specifically, Fe₃O₄/CBc has a rough surface, abundant porous structures, a high surface area of 638.10 m² g⁻¹, and obvious magnetization. The catalyst showed rather high performance towards MO removal. The optimal conditions for MO removal were obtained as follows: the dosage of hydrogen peroxide was 16 mmol L⁻¹, pH = 3, the temperature was 35 °C, and the addition amount of adsorbent was

10 mg. Under optimal conditions, the MO removal rate can be higher than 99.4%. The synergistic effect between catalytic degradation and adsorption in removing MO was also discovered. Besides high performance in the depredating MO, $Fe_3O_4/$ CBc also exhibited high stability, easy magnetic separation, and good reusability, as well as the potential to be developed as a new heterogeneous Fenton catalyst.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by a key research and development planned project in Hainan Natural Science Foundation Project (221MS035), Key Research and Development Project of Hainan Province (ZDYF2022XDNY158), Postgraduate Innovation and scientific research project of Hainan Normal University (RC2200001110), Innovation team project of the Ministry of Education (IRT-16R19), College Students' innovation project of Hainan Normal University.

References

- 1 A.-R. A. Giwa, I. A. Bello, A. B. Olabintan, *et al.*, Kinetic and thermodynamic studies of fenton oxidative decolorization of methylene blue, *Heliyon*, 2020, **6**(8), 44–54.
- 2 M. Usman and Y.-S. Ho, A bibliometric study of the Fenton oxidation for soil and water remediation, *J. Environ. Manage.*, 2020, **270**(C), 1–10.
- 3 R. Hu, Pollution control and remediation of rural water resource based on urbanization perspective, *Environ. Technol. Innovation*, 2020, **20**(20), 1–12.
- 4 B. O. Unal, Z. Bilici, N. Ugur, *et al.*, Adsorption and Fenton oxidation of azo dyes by magnetite nanoparticles deposited on a glass substrate, *J. Water Proc. Eng.*, 2019, **32**, 1–11.
- 5 J. Zhang, G. Zhang, Q. Ji, *et al.*, Carbon nanodot-modified FeOCl for photo-assisted Fenton reaction featuring synergistic in-situ H_2O_2 production and activation, *Appl. Catal.*, *B*, 2020, **266**(C), 1–8.
- 6 S. Yoon and S. Bae, Novel synthesis of nanoscale zerovalent iron from coal fly ash and its application in oxidative degradation of methyl orange by Fenton reaction, *J. Hazard. Mater.*, 2018, **365**, 751–758.
- 7 L. Shen, W. Wang, T. Li, *et al.*, Powdered activated coke for COD removal in the advanced treatment of mixed chemical wastewaters and regeneration by Fenton oxidation, *Chem. Eng. J.*, 2019, **371**, 631–638.
- 8 J. Bi, X. Huang, J. Wang, *et al.*, Oil-phase cyclic magnetic adsorption to synthesize Fe₃O₄@C@TiO₂-nanotube composites for simultaneous removal of Pb(II) and Rhodamine B, *Chem. Eng. J.*, 2019, **366**, 50–61.
- 9 Q. Zhang, W. Zhang and K. Peng, In-situ synthesis and magnetic properties of core-shell structured Fe/Fe₃O₄ composites, *J. Magn. Magn. Mater.*, 2019, **484**, 418–423.

- 10 L. Qian, J. Peng, Z. Xiang, *et al.*, Effect of annealing on magnetic properties of Fe/Fe₃O₄ soft magnetic composites prepared by in-situ oxidation and hydrogen reduction methods, *J. Alloys Compd.*, 2018, 778, 712–720.
- 11 Y. Yi, Z. Huang, B. Lu, *et al.*, Magnetic biochar for environmental remediation: A review, *Bioresour. Technol.*, 2020, **298**, 1–14.
- 12 Z. Hao, C. Wang, Z. Yan, *et al.*, Magnetic particles modification of coconut shell-derived activated carbon and biochar for effective removal of phenol from water, *Chemosphere*, 2018, **211**, 962–969.
- 13 Z. Li, Z. Chen, Q. Zhu, *et al.*, Improved performance of immobilized laccase on Fe₃O₄@C-Cu²⁺ nanoparticles and its application for biodegradation of dyes, *J. Hazard. Mater.*, 2020, **399**, 1–7.
- 14 M. Godwin Patrick, Y. Pan, H. Xiao, *et al.*, Progress in Preparation and Application of Modified Biochar for Improving Heavy Metal Ion Removal From Wastewater, *J. Bioresour. Bioprod.*, 2019, **4**(1), 31–42.
- 15 J.-H. Park, J. J. Wang, Y. Meng, *et al.*, Adsorption/desorption behavior of cationic and anionic dyes by biochars prepared at normal and high pyrolysis temperatures, *Colloids Surf.*, *A*, 2019, 572, 274–282.
- 16 S. Chen, C. Qin, T. Wang, *et al.*, Study on the adsorption of dyestuffs with different properties by sludge-rice husk biochar: Adsorption capacity, isotherm, kinetic, thermodynamics and mechanism, *J. Mol. Liq.*, 2019, **285**, 62–74.
- 17 L. Wu, C. Wei, S. Zhang, *et al.*, MgO-modified biochar increases phosphate retention and rice yields in saline-alkaline soil, *J. Cleaner Prod.*, 2019, **235**, 901–909.
- 18 Y. Qiu, X. Xu, Z. Xu, *et al.*, Contribution of different iron species in the iron-biochar composites to sorption and degradation of two dyes with varying properties, *Chem. Eng. J.*, 2020, **389**, 1–40.
- 19 S. Xu, J. Li, Z. Yin, *et al.*, A highly efficient strategy for enhancing the adsorptive and magnetic capabilities of biochar using Fenton oxidation, *Bioresour. Technol.*, 2020, 315, 1–28.
- 20 W. Cai, J. Wei, Z. Li, *et al.*, Preparation of aminofunctionalized magnetic biochar with excellent adsorption

performance for Cr(VI) by a mild one-step hydrothermal method from peanut hull, *Colloids Surf.*, *A*, 2018, **563**, 102–111.

- 21 K. S. D. Premarathna, A. U. Rajapaksha, N. Adassoriya, *et al.*, Clay-biochar composites for sorptive removal of tetracycline antibiotic in aqueous media, *J. Environ. Manage.*, 2019, **238**, 315–322.
- 22 S. Liu, J. Li, S. Xu, *et al.*, A modified method for enhancing adsorption capability of banana pseudostem biochar towards methylene blue at low temperature, *Bioresour. Technol.*, 2019, **282**, 48–55.
- 23 M. Schwarze, D. Seo, B. Bibouche, *et al.*, Comparison of positively charged polymer species and cationic surfactants for methyl orange removal via polyelectrolyte and micellar enhanced ultrafiltration, *J. Water Proc. Eng.*, 2020, **36**, 1–6.
- 24 C. Xiao, H. Li, Y. Zhao, *et al.*, Green synthesis of iron nanoparticle by tea extract (polyphenols) and its selective removal of cationic dyes, *J. Environ. Manage.*, 2020, 275, 1–11.
- 25 A. Babuponnusami and K. Muthukumar, A review on Fenton and improvements to the Fenton process for wastewater treatment, *J. Chem. Environ. Eng.*, 2014, 2(1), 557–572.
- 26 Y. Yu, F. Huang, Y. He, X. Liu, *et al.*, Heterogeneous Fentonlike degradation of ofloxacin over sludge derived carbon as catalysts: Mechanism and performance, *Sci. Total Environ.*, 2019, **654**, 942–947.
- 27 B. García-Leiva, L. A. C. Teixeira and M. L. Torem, Degradation of xanthate in waters by hydrogen peroxide, Fenton and simulated solar photo-Fenton processes, *J. Mater. Res. Technol.*, 2019, **8**(6), 5698–5706.
- 28 L. Meili, P. V. Lins, C. L. P. S. Zanta, *et al.*, MgAl-LDH/Biochar composites for methylene blue removal by adsorption, *Appl. Clay Sci.*, 2019, **168**, 11–20.
- 29 J. Wang, Q. Ma, Z. Zhang, *et al.*, Bacteria mediated Fentonlike reaction drives the biotransformation of carbon nanomaterials, *Sci. Total Environ.*, 2020, **746**, 1–36.
- 30 H. Shang, Q. Wang, Y. S. Ok, *et al.*, Magnetic biochar production alters the molecular characteristics and biological response of pyrolysis volatile-derived water-soluble organic matter, *Sci. Total Environ.*, 2021, 778, 142–146.