## Sustainable Energy & Fuels



## CORRECTION

View Article Online
View Journal | View Issue



Cite this: Sustainable Energy Fuels, 2022, 6, 5199

## Correction: Solid oxide fuel cells for ammonia synthesis and energy conversion

Valentina Goldstein,<sup>a</sup> Manasa Kumar Rath,\*a Alexey Kossenko,<sup>ab</sup> Natali Litvak,<sup>a</sup> Alexander Kalashnikov<sup>c</sup> and Michael Zinigrad<sup>ab</sup>

DOI: 10.1039/d2se90070j

rsc.li/sustainable-energy

Correction for 'Solid oxide fuel cells for ammonia synthesis and energy conversion' by Valentina Goldstein et al., Sustainable Energy Fuels, 2022, 6, 4706–4715, https://doi.org/10.1039/D2SE00954D.

Table 2 in the original article shows the incorrect unit for the rate of  $NH_3$  in two locations. The correct unit of the rate of  $NH_3$  is  $10^{-9}$  mol cm<sup>-2</sup> s<sup>-1</sup>. Below is the correct version of Table 2.

Table 2 The parameters of the tested cells, including the current and voltage used for the NH<sub>3</sub> synthesis, the NH<sub>3</sub> synthesis rate (mol cm<sup>-2</sup> s<sup>-1</sup>), energy consumption, the fraction of energy expended for NH<sub>3</sub> synthesis, the faradaic efficiency ( $\Lambda_{\rm F}$ ), and the energy efficiency ( $\Lambda_{\rm E}$ )

#	Parameter/cell	CH₄ cell ⊕ air	CH₄ cell ⊕ air	CH₄ cell ② air	H₂ cell ⑥ air
1	Wet, %	20	14	5	20
2	Current (mA)	16	16	1.3	3.36
3	Voltage (V)	0.039	0.05	0.9	0.9
4	Mass of NH <sub>3</sub> (mg)	2.166	0.437	0.640	3
5	Time (min)	107	12	46	60
6	Energy consumption (kJ mol <sub>NH3</sub> <sup>-1</sup> )	22.7	22.4	85.78	61.7
7	Fraction of energy applied for NH <sub>3</sub> synthesis (%)	3.6	7	24.6	7
8	Rate of NH <sub>3</sub> $(10^{-9} \text{ mol cm}^{-2} \text{ s}^{-1})$	1.2	1.4	0.85	3
9	$\Lambda_{\rm F}$ , Faraday efficiency	_	_	3.0	4
10	$\Lambda_{\rm E}$ , energy efficiency	2	2.8	0.72	1
	Rate of NH <sub>3</sub> at OCV ( $10^{-9}$ mol cm <sup>-2</sup> s <sup>-1</sup> )	1.4	1.4	0.97	2.6

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

<sup>&</sup>quot;Materials Research Center, Ariel University, Ariel 40700, Israel. E-mail: manas.physics@gmail.com

<sup>&</sup>lt;sup>b</sup>Department of Chemical Engineering, Biotechnology and Materials, Faculty of Engineering, Ariel University, Ariel 40700, Israel

<sup>&</sup>lt;sup>c</sup>3Rock Capital Partners, Moscow, Russia