# ChemComm

## **COMMUNICATION**



Cite this: *Chem. Commun.*, 2023, 59, 944

Received 30th August 2022, Accepted 19th December 2022

DOI: 10.1039/d2cc04810h

[rsc.li/chemcomm](https://rsc.li/chemcomm)

### Hybrid photocathode based on a Ni molecular catalyst and  $\text{Sb}_2\text{Se}_3$  for solar H<sub>2</sub> production†

D. Alicia Garcia-Osorio,<sup>a</sup> Thomas P. Shalvey,<sup>a</sup> Liam Banerji,<sup>a</sup> Khezar Saeed, Dab Gaia Neri, ‡<sup>a</sup> Laurie J. Phillips,<sup>a</sup> Oliver S. Hutter, D<sup>ac</sup> Carla Casadevall, D<sup>c</sup> Daniel Antón-García, D<sup>d</sup> Erwin Reisner, D<sup>d</sup> Jonathan D Major<sup>\*a</sup> and Alexander J Cowan  $\mathbb{D}^{*a}$ 

We report a H<sub>2</sub> evolving hybrid photocathode based on  $\text{Sb}_2\text{Se}_3$  and a precious metal free molecular catalyst. Through the use of a high surface area TiO<sub>2</sub> scaffold, we successfully increased the Ni molecular catalyst loading from 7.08  $\pm$  0.43 to 45.76  $\pm$  0.81 nmol cm $^{-2}$ , achieving photocurrents of 1.3 mA  $cm^{-2}$  at 0 V vs. RHE, which is 81-fold higher than the device without the  $TiO<sub>2</sub>$  mesoporous layer.

Photoelectrodes for the production of solar fuels, for example by splitting water to generate  $H_2$  and  $O_2$ ,<sup>1</sup> have the potential to play a key role in future energy systems. However, advances in both photoanodes for water oxidation<sup>2</sup> and photocathodes for hydrogen evolution (HER) are needed to improve the stability and to lower the cost for industrial scaling, since most longlasting devices rely on precious metals.<sup>3–5</sup> Sb<sub>2</sub>Se<sub>3</sub> has recently gained interest from the photovoltaic (PV) community due to its near-direct band gap of 1.18 eV, a high absorption coefficient across the visible region, $6$  and an unusual 1D nanoribbon structure that enables effective charge transport.<sup>7</sup> These properties, combined with improvements in material processability and the use of earth-abundant elements, have led to the suggestion that  $Sb_2Se_3$  could be a viable thin film PV material for use on a global scale.<sup>8</sup>  $Sb<sub>2</sub>Se<sub>3</sub>$  has also been studied as a photocathode for HER, the conduction band minimum at  $-0.5$  V vs. RHE provides enough driving force for producing  $\mathrm{H_2,}^9$  and its band gap  $(E_\mathrm{g})$  is very close to the optimal calculated for the bottom electrode in dual absorber standalone device for water splitting.<sup>10</sup> Reported solar to hydrogen efficiencies, using state-of-the-art  $Sb_2Se_3$  photocathodes, have now exceeded 10%.<sup>11,12</sup> These photocathodes consist of a  $\text{Sb}_2\text{Se}_3/\text{CdS}$  buried

† Electronic supplementary information (ESI) available. See DOI: [https://doi.org/](https://doi.org/10.1039/d2cc04810h) [10.1039/d2cc04810h](https://doi.org/10.1039/d2cc04810h)



The complete device  $FTO/Au/Sb_2Se_3/CdS/TiO_2/TiO_2-mesol$ NiP is shown in Fig. 1a.  $Sb_2Se_3$  (1.5 µm) was deposited on Au (70 nm) coated fluorine-doped  $SnO<sub>2</sub>$ -glass (FTO) by a two-step fast-cooling close space sublimation process, which generates a compact preferentially orientated nanoribbon crystal structure that facilitates rapid hole transfer to the Au contact.<sup>7,11,12</sup> Then, a thin sputtered CdS buffer layer (20 nm) was added which forms a  $Sb<sub>2</sub>Se<sub>3</sub>$  heterojunction with a negligible conduction band offset, thereby allowing efficient charge separation and electron transfer towards TiO<sub>2</sub> (Fig. 1c).<sup>6</sup> In this way, the onset potential and fill factor of the  $Sb<sub>2</sub>Se<sub>3</sub>$  photocathodes are improved despite the parasitic absorption of photons below  $\lambda$  < 500 nm in the CdS causing a decrease in the photocurrent.<sup>11,12</sup> After, TiO<sub>2</sub> (100 nm) was sputtered to provide a physical barrier preventing contact between the light absorber

<sup>&</sup>lt;sup>a</sup> Stephenson Institute for Renewable Energy, University of Liverpool, L69 7ZF, UK. E-mail: acowan@liverpool.ac.uk

 $b$  Department of Chemistry, Aarhus University, Aarhus C 8000, Denmark

<sup>&</sup>lt;sup>c</sup> Department of Mathematics, Physics and Electrical Engineering,

Northumbria University, NE1 8ST, UK

<sup>d</sup> Yusuf Hamied Department of Chemistry, University of Cambridge, CB2 1EW, UK

<sup>‡</sup> Current address: Enapter S.R.L, via di Lavoria 56/g, 56040 Pisa.



Fig. 1 (a) Schematic diagram of  $\mathrm{Sb}_2\mathrm{Se}_3/\mathrm{CdS}/\mathrm{TiO}_2$ -meso/NiP hybrid photocathode. (b) Chemical structure of NiP catalyst molecular catalyst, panel a and b are not drawn to scale. (c) Equilibrium band alignment diagram of Sb<sub>2</sub>Se<sub>3</sub>/CdS/TiO<sub>2</sub> heterojunction based on VBM<sup>11</sup> and  $E_a$ measured separately for each layer (Fig. S2.1, ESI†), note that NiP redox couple is pH independent.<sup>21</sup>

and the electrolyte. $^{22}$  Full details of the synthetic procedures, the device characterisation and SEM images are provided in the ESI,† Fig. S2.1-3.

The molecular catalyst was first immobilized overnight onto the sputtered  $TiO<sub>2</sub>$  (without the  $TiO<sub>2</sub>-meso$ ) by soaking the photoelectrode in dry methanolic solution  $(0.5 \text{ mM } \text{NiP})$ ,  $^{19,23,24}$  and from now on labelled as  $Sb_2Se_3/CdS/TiO_2/NiP$ . It was removed from the soaking solution, thoroughly washed in methanol to remove the non-chemisorbed catalyst and dried under vacuum. NiP loadings were determined by stripping the catalyst off using NaOH and then quantified by UV-vis spectroscopy, as shown in Table S1 (ESI†). When  $NIP$  was attached to the sputtered TiO<sub>2</sub> layer, a loading of 7.08  $\pm$  0.43 nmol cm $^{-2}$  was achieved. All the photoelectrochemical tests were done under 100 mW  $cm^{-2}$ illumination (unless otherwise stated) and with  $\lambda > 340$  nm in  $0.1$  M Na<sub>2</sub>SO<sub>4</sub> at pH 3. pH 3 was chosen due to past studies that showed NiP was most active at this  $pH.<sup>23,25</sup>$  Fig. 2 shows a photocurrent of only  $-16$   $\mu$ A cm<sup>-2</sup> at 0 V vs. RHE, which exceeds only slightly the current in the absence of any catalyst  $(-3 \mu A \text{ cm}^{-2} \text{ for } Sb_2Se_3/CdS/TiO_2$ , Fig. S2.4, ESI†). The spikes in the light chopped Linear Sweep Voltammetry (LSV) of  $Sb_2Se_3/CdS/$  $TiO<sub>2</sub>/NiP$  demonstrated that the photoelectrons are not being utilised at a fast-enough rate by the catalyst, instead recombination is dominating.26

The low photocurrent of the  $Sb_2Se_3/CdS/TiO_2/NiP$  electrode is due to the low loading of NiP compared with previous devices.<sup>23,24</sup> A common approach to achieve higher catalyst loadings on a photoelectrode is to increase the available surface area for catalyst binding by using a mesoporous  $TiO<sub>2</sub>$  layer



Fig. 2 Chopped light LSV of the hybrid photocathodes  $\text{Sb}_2\text{Se}_3/\text{CdS/TiO}_2/$ NiP (blue trace) and Sb<sub>2</sub>Se<sub>3</sub>/CdS/TiO<sub>2</sub>-meso/NiP (purple trace) at 10 mV s<sup>-1</sup>. The TiO<sub>2</sub>-meso enables a higher loading of the **NiP** catalysts and increased photocurrents. All experiments were carried out in 0.1 M Na<sub>2</sub>SO<sub>4</sub> pH 3 at 100 mW cm<sup>-2</sup> and  $\lambda > 340$  nm.

(TiO<sub>2</sub>-meso). Typically, following deposition of a TiO<sub>2</sub> nanoparticleorganic binder paste, thermal annealing is carried out in air ( $\sim$  450 °C) to remove the binder and sinter the TiO<sub>2</sub> nanoparticles forming conductive pathways.<sup>26</sup> Sb<sub>2</sub>Se<sub>3</sub> is unstable at these temperatures in air,<sup>8</sup> therefore we modified a UV curing approach successfully developed by the Grätzel group for  $CuO<sub>2</sub>/AZO/TiO<sub>2</sub>$ photocathodes.<sup>27</sup> Following doctor blading of an anatase  $TiO<sub>2</sub>$ paste (av. particle size 20 nm diameter) the sample was UV cured for 68 h using a 365 nm LED, Fig. S2.5 (ESI<sup>†</sup>). Note that the  $Sb_2Se_3/$  $CdS/TiO<sub>2</sub>-meso$  also included the sputtered 100 nm TiO<sub>2</sub> layer since it was found to be essential during the UV curing to protect the  $Sb<sub>2</sub>Se<sub>3</sub>/CdS$ . The photocathode was then annealed at lower temperature (350 °C) under  $N_2$  to improve the electrochemical properties of the TiO<sub>2</sub>-meso layer (Fig. S2.6-7, ESI<sup>+</sup>) without hindering the light absorber capabilities (Fig. S2.9, ESI†). The TiO<sub>2</sub>-meso was  $ca.$  4–6  $\mu$ m thick determined by profilometry, the cross-sectional image and energy-dispersive X-ray spectroscopy (EDX) maps are shown Fig. 3a and Fig. S2.10 (ESI†), respectively. Neither the UV curing nor the  $N_2$  annealing alone resulted in a TiO<sub>2</sub>-meso layer with electrical and mechanical features suitable for a molecular catalyst scaffold (Fig. S2.5 and S2.8, ESI†). The NiP immobilization on the  $TiO<sub>2</sub>$ -meso device was carried out using the same experimental protocol as for the planar structure. The resultant  $Sb_2Se_3/$  $CdS/TiO<sub>2</sub>-meso/NiP$  photocathode achieved an increased NiP loading (45.76  $\pm$  0.81 nmol cm<sup>-2</sup>), in line with the literature.<sup>24</sup> Top view EDX mapping shows the catalyst is evenly distributed on the photocathode surface (Fig. S2.11, ESI†). X-Ray photoelectron spectroscopy (XPS) analysis of the  $NiP$  on the  $Sb_2Se_3/CdS/TiO_2$ meso/NiP electrode is shown in Fig. 3b–d. The energies of the Ni 2p (Fig. 3b, 1/2 at 872.1 eV and 3/4 at 854.6), P 2p (Fig. 3c, 132.6 eV) and N 1s (Fig. 3d, 399.6 eV) peaks are in good agreement with the NiP catalyst prior to immobilisation (all the XPS peak positions are shown in Table S2, ESI†).<sup>23-25</sup> The complete  $Sb_2Se_3/CdS/TiO_2-mesol$ **NiP** photocathode achieves a photocurrent of  $-1.3$  mA cm<sup>-2</sup> at 0 V vs. RHE with an onset potential of  $ca. +0.37$  V vs. RHE (Fig. 2). The photocurrent for this electrode structure is amongst the highest reported for a NiP decorated photocathode, Table S3 (ESI†)



Fig. 3 (a) Cross-sectional SEM image of  $Sb_2Se_3/CdS/TiO_2-meso/NiP$ . (b-d) XPS spectra of NiP molecular catalyst (blue trace) after it is immobilized on  $TiO<sub>2</sub>$  (pre-CPP, black trace), and after 5 h of CPP test at 0 V vs. NHE (post-CPP, red trace) with light intensity of 100 mW  $cm^{-2}$  and  $\lambda$  > 340 nm in 0.1 M Na<sub>2</sub>SO<sub>4</sub> at pH 3. (b–d) XPS spectra showing Ni 2p, P 2p and N 1s regions respectively

provides the state-of-the-art hybrid photocathodes for  $H_2$  production. NiP has been previously used with a  $Si/TiO<sub>2</sub>-meso$  photocathode to achieve a photocurrent of  $-0.3$  mA cm<sup>-2</sup> at 0 V vs. RHE<sup>24</sup> and  $-0.6$  mA cm<sup>-2</sup> at 0 V vs. RHE for a La<sub>5</sub>Ti<sub>2</sub>Cu<sub>0.9</sub>Ag<sub>0.1</sub>S<sub>5</sub>O<sub>7</sub>/  $TiO<sub>2</sub>$  photocathode.<sup>23</sup> A control experiment without the catalyst  $(Sb<sub>2</sub>Se<sub>3</sub>/CdS/TiO<sub>2</sub>-meso, Fig. S2.4. ESI<sup>+</sup>) demonstrates the impor$ tance of the NiP catalyst, it showed a photocurrent of only  $-0.12$  mA cm<sup>-2</sup> at 0 V vs. RHE. Incident photon to current efficiency (IPCE, Fig. S2.12, ESI†) demonstrates the device is active at wavelengths up to 900 nm (at 0 V vs. RHE), in-line with the  $E_g$  of  $Sb_2Se_3.^{6,7}$ 

Controlled potential photoelectrolysis (CPP) carried out at 0 V vs. RHE assessed the stability of the  $Sb_2Se_3/CdS/TiO_2-mesol$ NiP electrode, results shown in Fig. 4. The  $H_2$  faradaic efficiency after 1 h was 77.5  $\pm$  9.1%, giving a TON $_{\mathrm{NiP}}$  of 12.8  $\pm$  2.8. However, the photocurrent decreased significantly in the first hour reaching  $-40 \mu A \text{ cm}^{-2}$  and by 5 hours, it decreased to only  $-15$  µA cm<sup>-2</sup> (Fig. S2.13, ESI†). The loss of photoactivity of NiP photoelectrodes has previously been attributed to the hydrolysis of the phosphonic anchoring group from the  $\text{TiO}_2$ .<sup>23,24</sup> XPS analysis of the hybrid photocathode post CPP shows the loss of the  $Ni^{2+}$  bands (red trace, Fig. 3b). However, it is clear that both the N 1s and P 2p signals are still present, although significantly shifted. A broadening of the N 1s band has previously been assigned to protonation of the amine in the acidic electrolyte<sup>23</sup> and the shifting of the P band is due to the loss of the metal centre.<sup>28</sup> The XPS results suggest the phosphonate linkage has been retained but the Ni is no longer coordinated to the ligand, in-line with the stability of the phosphonate linkage at pH  $< 7.^{29}$  Past studies have shown that NiP degradation occurs on photocathodes but with a slower decay rate.<sup>23,24</sup>



Fig. 4 CPP at 0 V vs. RHE of the hybrid photocathodes  $\text{Sb}_2\text{Se}_3/\text{CdS/TiO}_2/$ NiP (a) and  $\text{Sb}_2\text{Se}_3/\text{CdS/TiO}_2$ -meso/NiP (b) in 0.1 M Na<sub>2</sub>SO<sub>4</sub> pH 3 at 100 mW cm<sup>-2</sup> and  $\lambda > 340$  nm.

To explore the mechanism of the hybrid photocathode decay here, we examined the TiO<sub>2</sub>-meso/NiP interface (without  $Sb_2Se_3/$ CdS). CPE at  $-0.24$  V vs. RHE (Fig. S2.7b, ESI†), shows that following an initial drop in the current in the first 600 s, the electrode maintains a stable current of  $-0.24$  mA cm<sup>-2</sup> for 1 h suggesting that the  $TiO<sub>2</sub>-meso/NiP$  interface is stable at this potential and capable of dealing with low current density. However, the current spikes observed with  $Sb_2Se_3/CdS/TiO_2-meso/NiP$ when the light is turned off in Fig. 2 are typical features of electron accumulation in the  $TiO<sub>2</sub>$ , suggesting that the NiP catalyst was unable to turnover at the rate of photoelectron generation under 100 mW  $cm^{-2}$  illumination. Based on the concentration of immobilised NiP (45.76  $\pm$  0.81 nmol cm<sup>-2</sup>), and the highest reported turnover frequency of  $NIP$  (460  $\pm$  5 h<sup>-1</sup>),<sup>21</sup> we calculate that the NiP on the surface could support a photocurrent of  $-1.15$  mA cm<sup>-2</sup>. This magnitude of photocurrent is achieved briefly in the LSV, but CPP shows the photocurrent decreases rapidly as the NiP catalyst degrades. To assess the photoelectron generation of  $Sb_2Se_3/CdS/TiO_2-meso$ , we used Pt as co-catalyst (see ESI, $\dagger$  for synthetic details, Fig. S2.14). The  $Sb_2Se_3/CdS/TiO_2-mesol$ Pt electrode achieved a stable photocurrent of  $-3$  mA cm<sup>-2</sup> at 0 V vs. RHE for 5 hours. It is clear that the rate of photoelectron generation at the  $Sb_2Se_3/CdS$  interface greatly exceeds the maximum current density that NiP can sustain. The catalytic mechanism of NiP is shown in Fig. S2.15 (ESI†),<sup>20</sup> H<sub>2</sub> production occurs following the Ni<sup>II/I</sup> reduction. Further reduction from Ni<sup>I</sup> to Ni<sup>0</sup> can also potentially occur deactivating the catalyst if the rate of photoelectron generation is too high.<sup>30</sup> To explore if limiting the photoelectron generation on the  $Sb<sub>2</sub>Se<sub>3</sub>$  would be beneficial, experiments at 20 mW  $cm^{-2}$  (Fig S2.16 and S17, ESI†) were carried out. Notably, only a small decrease in photocurrent was observed from 1.30 to 0.81 mA  $cm^{-2}$  at 0 V vs. RHE, and 20% of photocurrent was retained after 1800 s compared with the 11% at  $100 \, \text{mW cm}^{-2}$ . ChernComm **and the commons are commons are the commons are commons are commons are common and the commons are commons are commons are commons are commons are commons at the common and distinguished under a creative Common** 

> Past studies using precious metal HER catalysts like Pt on planar TiO<sub>2</sub> coated  $Sb_2Se_3$  photocathodes have noted that

dissolution of  $TiO<sub>2</sub>$  can also occur due to photoelectron accumulation.<sup>11,13</sup> The SEM images post-CPP  $Sb_2Se_3/CdS/$ TiO<sub>2</sub>-meso/NiP electrodes (tested at 100 mW cm<sup>-2</sup>) did not show significant change in the morphology of the device (Fig. S2.18, ESI†) despite the demonstration of electron accumulation in the device. XRD analysis of a post-CPP sample only showed the typical peaks of  $Sb_2Se_3$  and TiO<sub>2</sub> (Fig. S2.19, ESI<sup>†</sup>) and no indication of  $Sb<sub>2</sub>O<sub>3</sub>$  formation, which has been associated with the deactivation of the  $Sb<sub>2</sub>Se<sub>3</sub>$  photoelectrodes (Fig. S2.20, ESI†).<sup>12,13</sup> However experiments where  $Sb_2Se_3/$  $CdS/TiO<sub>2</sub>-meso/NiP$  underwent (i) LSV and CPP at 0 V vs. RHE for 1 h, (ii) removal of any remaining NiP by NaOH stripping, and (iii) Pt addition and photoelectrochemical testing showed evidence of partial failure of the sputtered  $TiO<sub>2</sub>$  layer due to photoelectron accumulation. Significantly higher dark currents  $(<$  –5 mA cm $^{-2}$ , Fig. S2.21, ESI†) and decreased photocurrents were measured compared to a pristine platinized photoelectrode, reinforcing the importance of preventing photoelectron accumulation in the  $Sb_2Se_3/CdS/TiO_2-meso/NiP$  photocathode. Communication<br>
Schemation <sup>2</sup> Open Access Articles. Published on 19 December 2022. The *Creation* 2022. The *Creatio* 

Emergent chalcogenide semiconductors such as  $Sb<sub>2</sub>Se<sub>3</sub>$  are promising photocathodes due to their ability to achieve a high rate of photoelectron generation but they suffer from thermal instability limiting processing opportunities. Furthermore,  $Sb<sub>2</sub>Se<sub>3</sub>$  interfaces need to be protected by metal oxide capping layers where corrosion could occur due to photoelectron accumulation. To prevent electron accumulation research has focused on the use of these absorbers with precious metal HER catalysts. Here we present an alternative approach using a  $Sb_2Se_3/CdS/TiO_2-meso$  photocathode. The high surface area  $TiO<sub>2</sub>$  support, prepared by a UV and low temperature N<sub>2</sub> annealing process that is compatible with  $Sb_2Se_3$ , enables a high loading of an earth abundant molecular HER catalyst, NiP. An 81-fold increase in the photocurrent was achieved when compared to a similar device without the mesoporous  $TiO<sub>2</sub>$ . Despite the high catalyst loading, stability and activity under 100 mW  $cm^{-2}$  is still limited by the turnover frequency of the HER catalyst. However, initial experiments under low light intensities indicate that improved stability is achievable with further advances in the catalytic turnover frequency.

We thank the studentship financial support from CONACYT-SENER (556479, DAGO), EPSRC (DTA, DAG), the UKRI Cambridge Creative Circular Plastics Centre (EP/ S025308, ER, CC), and the European Commission for Horizon 2020 Marie Skłodowska-Curie Individual Fellowships (890745- SmArtC, CC). EPSRC is acknowledged for funding though EP/ P034497/1, EP/N014057/1 and EP/V011863/1. Prof L. Hardwick and Facility for XPS (''HarwellXPS'') are thanked for the Raman spectroscopy access and the XPS data collection (Contract No. PR16195).

#### Conflicts of interest

There are no conflicts to declare.

#### Notes and references

- 1 S. Ye, C. Ding, R. Chen, F. Fan, P. Fu, H. Yin, X. Wang, Z. Wang, P. Du and C. Li, J. Am. Chem. Soc., 2018, 140, 3250–3256.
- 2 S. Ye, C. Ding, M. Liu, A. Wang, Q. Huang and C. Li, Adv. Mater., 2019, 31, 1902069.
- 3 H. Song, S. Luo, H. Huang, B. Deng and J. Ye, ACS Energy Lett., 2022, 7, 1043–1065.
- 4 R. M. Irfan, D. Jiang, Z. Sun, L. Zhang, S. Cui and P. Du, J. Catal., 2017, 353, 274–285.
- 5 S. Ye, W. Shi, Y. Liu, D. Li, H. Yin, H. Chi, Y. Luo, N. Ta, F. Fan, X. Wang and C. Li, J. Am. Chem. Soc., 2021, 143, 12499–12508.
- 6 H. Shiel, O. S. Hutter, L. J. Phillips, J. E. N. Swallow, L. A. H. Jones, T. J. Featherstone, M. J. Smiles, P. K. Thakur, T. L. Lee, V. R. Dhanak, J. D. Major and T. D. Veal, ACS Appl. Energy Mater., 2020, 3, 11617–11626.
- 7 O. S. Hutter, L. J. Phillips, K. Durose and J. D. Major, Sol. Energy Mater. Sol. Cells, 2018, 188, 177–181.
- 8 A. Mavlonov, T. Razykov, F. Raziq, J. Gan, J. Chantana, Y. Kawano, T. Nishimura, H. Wei, A. Zakutayev, T. Minemoto, X. Zu, S. Li and L. Qiao, Sol. Energy, 2020, 201, 227–246.
- 9 S. Chen, T. Liu, Z. Zheng, M. Ishaq, G. Liang, P. Fan, T. Chen and J. Tang, J. Energy Chem., 2022, 67, 508–523.
- 10 B. A. Pinaud, J. D. Benck, L. C. Seitz, A. J. Forman, Z. Chen, T. G. Deutsch, B. D. James, K. N. Baum, G. N. Baum, S. Ardo, H. Wang, E. Miller and T. F. Jaramillo, Energy Environ. Sci., 2013, 6, 1983–2002.
- 11 W. Yang, J. Park, H.-C. C. Kwon, O. S. Hutter, L. J. Phillips, J. Tan, H. Lee, J. Lee, S. D. Tilley, J. D. Major and J. Moon, Energy Environ. Sci., 2020, 13, 4362–4370.
- 12 W. Yang, J. H. Kim, O. S. Hutter, L. J. Phillips, J. Tan, J. Park, H. Lee, J. D. Major, J. S. Lee and J. Moon, Nat. Commun., 2020, 11, 1–10.
- 13 J. Tan, W. Yang, Y. Oh, H. Lee, J. Park, R. Boppella, J. Kim and J. Moon, Adv. Energy Mater., 2019, 1900179.
- 14 J. Park, W. Yang, J. Tan, H. Lee, J. W. Yun, S. G. Shim, Y. S. Park and J. Moon, ACS Energy Lett., 2020, 5, 136–145.
- 15 W. Yang, S. Lee, H.-C. Kwon, J. Tan, H. Lee, J. Park, Y. Oh, H. Choi and J. Moon, ACS Nano, 2018, 12, 11088–11097.
- 16 R. R. Prabhakar, W. Septina, S. Siol, T. Moehl, R. Wick-Joliat and S. D. Tilley, J. Mater. Chem. A, 2017, 5, 23139–23145.
- 17 F. Niu, D. Wang, F. Li, Y. Liu, S. Shen and T. J. Meyer, Adv. Energy Mater., 2019, 1900399.
- 18 W. Jiang, X. Yang, F. Li, Q. Zhang, S. Li, H. Tong, Y. Jiang and L. Xia, Chem. Commun., 2019, 55, 1414–1417.
- 19 M. L. Helm, M. P. Stewart, R. M. Bullock, M. R. DuBois and D. L. DuBois, Science, 2011, 333, 863–866.
- 20 W. J. Shaw, M. L. Helm and D. L. du Bois, Biochim. Biophys. Acta, Bioenerg., 2013, 1827, 1123–1139.
- 21 M. A. Gross, A. Reynal, J. R. Durrant and E. Reisner, J. Am. Chem. Soc., 2014, 136, 356–366.
- 22 A. Paracchino, V. Laporte, K. Sivula, M. Grätzel and E. Thimsen, Nat. Mater., 2011, 10, 456–461.
- 23 T. E. Rosser, T. Hisatomi, S. Sun, D. Antón-García, T. Minegishi, E. Reisner and K. Domen, Chem. – Eur. J., 2018, 24, 18393–18397.
- 24 J. J. Leung, J. Warnan, D. H. Nam, J. Z. Zhang, J. Willkomm and E. Reisner, Chem. Sci., 2017, 8, 5172–5180.
- 25 T. E. Rosser, M. A. Gross, Y. H. Lai and E. Reisner, Chem. Sci., 2016, 7, 4024–4035.
- 26 T. Berger, D. Monllor-Satoca, M. Jankulovska, T. Lana-Villarreal and R. Gomez, ChemPhysChem, 2012, 13, 2824–2875.
- 27 M. Schreier, J. Luo, P. Gao, T. Moehl, M. T. Mayer and M. Grätzel, J. Am. Chem. Soc., 2016, 138, 1938–1946.
- 28 NIST X-ray Photoelectron Spectroscopy (XPS) Database, Version 3.5, <https://srdata.nist.gov/xps/>, accessed 26 July 2022.
- 29 K. L. Materna, R. H. Crabtree and G. W. Brudvig, Chem. Soc. Rev., 2017, 46, 6099–6110.
- 30 A. Ruff, S. Janke, J. Szczesny, S. Alsaoub, I. Ruff, W. Lubitz and W. Schuhmann, ACS Appl. Energy Mater., 2019, 2, 2921–2929.