# PCCP

## PAPER

Check for updates

Cite this: Phys. Chem. Chem. Phys., 2023, 25, 8574

Received 25th January 2023, Accepted 21st February 2023

DOI: 10.1039/d3cp00392b

rsc.li/pccp

## 1. Introduction

The ever-increasing  $CO_2$  concentration in the atmosphere is one of the main causes of global warming.<sup>1–3</sup> The Paris Agreement at COP 21 aims to limit the global peak of greenhouse gas emissions in the second half of this century. To attain this objective,  $CO_2$  emitted into the atmosphere must be removed. Thus, the use of technological solutions capable of storing, capturing and/or converting  $CO_2$  are receiving a lot of attention.  $CO_2$  conversion towards generating value-added compounds is becoming one of the major scientific challenges, especially in the field of heterogeneous catalysis, because a harmful byproduct like  $CO_2$  can be converted to an economical feedstock.<sup>4</sup>

The conversion of  $CO_2$  into valuable compounds requires a new generation of efficient and robust catalysts.<sup>5–7</sup> Heterogeneous catalysis is widely used in industrial applications because of the possibility of facile separation, which reduces the operating costs, although heterogeneous catalysts often have limited selectivity.

## 2D carbon nitride as a support with single Cu, Ag, and Au atoms for carbon dioxide reduction reaction<sup>†</sup>

Sergio Posada-Pérez, (1) \*<sup>a</sup> Anna Vidal-López, <sup>ab</sup> Miquel Solà (1)<sup>a</sup> and Albert Poater (1) \*<sup>a</sup>

The electrochemical conversion of  $CO_2$  into value-added chemicals is an important approach to recycling  $CO_2$ . In this work, we have combined the most efficient metal catalysts for this reaction, namely Cu, Ag, and Au, as single-atom particles dispersed on a two-dimensional carbon nitride support, with the aim of exploring their performance in the  $CO_2$  reduction reaction. Here, we report density functional theory computations showing the effect of single metal-atom particles on the support. We found that bare carbon nitride needed a high overpotential to overcome the energy barrier for the first proton–electron transfer, while the second transfer was exergonic. The deposition of single metal atoms enhances the catalytic activity of the system as the first proton–electron transfer is favored in terms of energy, although strong binding energies were found for CO adsorption on Cu and Au single atoms. Our theoretical interpretations are consistent with the experimental evidence that the competitive H<sub>2</sub> generation is favored due to the strong CO binding energies. Our computational study paves the road to finding suitable metals that catalyze the first proton–electron transfer in the carbon dioxide reduction reaction and produce reaction intermediates with moderate binding energies, promoting a spillover to the carbon nitride support and thereby serving as bifunctional electrocatalysts.

> In contrast, homogeneous catalysts are very selective although they have limited industrial applications due to their cost, the use of precious metals, and the difficulty in separating and recovering the catalysts. Currently, the research community is trying to combine the properties of homogeneous and heterogeneous catalysts.<sup>8</sup> From the heterogeneous catalyst perspective, research has been focused on creating smaller and dispersed catalyst particles. Single-atom catalysts (SACs), which comprise atoms of metal species dispersed on a solid support, are expected to bridge the homogeneous and heterogeneous catalyst properties.<sup>9</sup> SACs can mimic a homogeneous catalyst, providing similar reactivity and product selectivity. Since the seminal work by Zhang and coworkers, who reported in 2011 that the  $Pt_1/FeO_x$  SAC was three times more active than its nano-Pt counterpart in CO oxidation,<sup>10</sup> SACs have become a new frontier in heterogeneous catalysis.

> The work described herein explores the electrocatalytic  $CO_2$ reduction reaction ( $CO_2RR$ ) using single metal atoms (Cu, Ag, and Au) anchored in 2D graphitic carbon nitride (g- $C_3N_4$ ). On the one hand, we selected the group XI transition metals since they include Cu, the only transition metal capable of reducing  $CO_2$  to hydrocarbons and alcohols with acceptable faradaic efficiencies.<sup>11-19</sup> Furthermore, the Cu–In<sup>20,21</sup> and Cu–Sn<sup>22,23</sup> bimetallic catalysts have been shown to selectively reduce  $CO_2$ to CO at low overpotentials. With respect to gold<sup>24,25</sup> and silver<sup>26</sup> catalysts, CO is detected as a product of the  $CO_2$

**View Article Online** 

View Journal | View Issue

<sup>&</sup>lt;sup>a</sup> Institut de Química Computacional i Catàlisi and Departament de Química, Universitat de Girona, C/Maria Aurèlia Capmany 69, 17003, Girona, Catalonia, Spain. E-mail: sergio.posada@udg.edu, alber.poater@udg.edu

<sup>&</sup>lt;sup>b</sup> Departament de Química, Universitat Autònoma de Barcelona, 08193, Cerdanyola

del Vallès, Catalonia, Spain

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: https://doi.org/ 10.1039/d3cp00392b

#### Paper

reduction reaction. In addition, the Cu-Ag tandem catalysts<sup>27</sup> display high selectivity towards ethanol and methane production. On the other hand, g-C<sub>3</sub>N<sub>4</sub> has emerged as a greener and low-cost material with unique attributes, such as facile synthesis, metal-free nature, earth-abundant resources, excellent thermal-physical-chemical stability, and exceptional catalytic properties.<sup>28,29</sup> 2D g-C<sub>3</sub>N<sub>4</sub> has been demonstrated to be a competitive candidate for electrocatalytic CO<sub>2</sub> reduction since it can act as an active support for single metal-atom catalysts, mainly Cu, Pd, and Pt.30-32 Moreover, single Au atom deposition on g-C3N4 has been experimentally studied.<sup>33</sup> The single metal atoms deposited on different supports are often unstable, and the isolated metal atoms tend to aggregate into nanoparticles and small clusters.34,35 However, g-C<sub>3</sub>N<sub>4</sub> is an excellent substrate to stabilize metal atoms mainly due to the strong metal-nitrogen interactions. The stability and catalytic activity of the Cu/g-C<sub>3</sub>N<sub>4</sub> system have been investigated by several authors, revealing strong copper-nitrogen interactions due to the confinement in its structural cavities.<sup>31,36</sup> In these experimental studies, no copper clusters or nanoparticles were observed, suggesting the successful formation of copper single atoms. Moreover, in a very recent study, Jurado and coworkers demonstrated the stable deposition of single Rh atoms on g-C<sub>3</sub>N<sub>4</sub> by means of experiments and theory.<sup>37</sup> Dobrota *et al.* have shown the stability of single metal atoms on N<sub>4</sub>-graphene systems by means of density functional simulations,<sup>38</sup> concluding that Cu, Ag, and Au show lower stability than other transition metals. However, the experimental studies using Cu1@g-C3N4 reveal its stability under electrochemical reaction conditions.<sup>31</sup> Experimental studies focusing on the Cu1@g-C3N4 system have revealed the production of formic acid and H<sub>2</sub> depending on the electrolyte solution.31 Furthermore, N-doped carbon nanotubes39 and Ndoped carbon nanofibers<sup>40</sup> show excellent catalytic activity toward CO<sub>2</sub> reduction to produce formate (HCO<sub>2</sub><sup>-</sup>) and CO, respectively. In addition, the anchoring of single metal atoms on familiar materials like N-doped porous carbon (M-N-C catalysts) enhances the electrocatalytic activity of these systems for CO2RR.41-44 Other supports, such as metal oxides, strongly interact with single metal atoms and small metal clusters,45-49 showing large catalytic activity as in the work of Zhang et al.,<sup>10</sup> although it is important to remark that the oxygens in metal oxide materials may oxidize the single metal atoms, decreasing their catalytic activity.<sup>50,51</sup>

This work outlines the reaction mechanism of the two electronproton transfers involved in  $CO_2RR$  computed by means of periodic density functional simulations (DFT) using bare g- $C_3N_4$  and single Cu, Ag, and Au atoms deposited on a 2D carbon nitride monolayer. Our work can potentially help the design of low-cost catalysts by avoiding the use of pure transition metals (mainly Cu) and combining the excellent catalytic properties of precious metal catalysts at single metal atom sites using 2D carbon nitrides.

## 2. Computational details

The periodic spin-polarized DFT calculations were performed using the Perdew–Burke–Ernzerhof (PBE) exchange–correlation functional<sup>52</sup> and by including the semi-empirical method of

Grimme (D3) to describe the dispersion effects.<sup>53</sup> The electronic density of the valence electrons was expanded onto a planewave basis set. The effects caused by the core electrons on the valence electrons were described using the projected augmented wave (PAW) method of Blöch<sup>54</sup> as implemented by Kresse and Joubert.55 The threshold for electronic relaxation was less than  $10^{-5}$  eV, and relaxation of the atomic positions was allowed until the forces acting on the atoms were always lower than 0.01 eV  $Å^{-1}$ . The kinetic energy cut-off for the plane wave basis set was set to 520 eV, which has been proven enough to gain converged results for adsorbates in previous studies.<sup>37</sup> All DFT simulations were performed using VASP code.<sup>56</sup> Calculations that included the solvent were carried out without remarkable differences, as illustrated in Fig. S1 (ESI<sup>†</sup>), and thus, all the calculations in the main manuscript were performed without solvent effects. For example, the variation in HCOO\* and COOH\* binding energies on Cu<sub>1</sub>@C<sub>3</sub>N<sub>4</sub> was lower than 0.01 eV when solvent effects were included, while that for CO\* was 0.04 eV.

The (001) monolayer of g-C<sub>3</sub>N<sub>4</sub> was considered (*Cmcm* space group) as it is the most favorable among those available on the materials project database.<sup>57</sup> The monolayer contained 24C and 32N atoms. A Monkhorst–Pack grid<sup>58</sup> of  $5 \times 5 \times 1$  *k*-points was used for integration in the reciprocal space of all surfaces. The binding energy of a single metal atom was calculated by following eqn (1),

$$E_{\rm ads} = E_{\rm M@C_3N_4} - (E_{\rm C_3N_4} + E_{\rm M})$$
(1)

where  $E_{M@C_3N_4}$  is the DFT energy of the monolayer including the anchored single metal atom,  $E_{C_3N_4}$  is the energy of the g-C<sub>3</sub>N<sub>4</sub> monolayer, and  $E_M$  is the energy of one Cu, Ag, or Au atom in its ground state.

The two-electron reaction mechanism of  $CO_2RR$  generally proceeds in two steps (eqn (2)–(4)), with different possible intermediates and products.

$$\operatorname{CO}_2(\mathbf{g}) + * \to \operatorname{CO}_2^*$$
 (2)

$$\text{CO}_2^* + \text{H}^+ + \text{e}^- \rightarrow \text{COOH}^*$$
 (3a)

$$\mathrm{CO}_2^* + \mathrm{H}^+ + \mathrm{e}^- \to \mathrm{HCOO}^*$$
 (3b)

 $COOH^*/HCOO^* + H^+ + e^- \rightarrow CO^* + H_2O(g) \qquad (4a)$ 

 $COOH^*/HCOO^* + H^+ + e^- \rightarrow HCOOH(g) \qquad (4b)$ 

$$CO^* \rightarrow CO(g) + *$$
 (4c)

where \* represents the g- $C_3N_4$  monolayer with and without anchored metals, and  $CO_2^*$ , COOH\*, HCOO\*, and CO\* represent the adsorbed species on M@g- $C_3N_4$ . According to the computational hydrogen electrode (CHE) scheme proposed by Norskov and coworkers,<sup>59</sup> it is commonly assumed that the energy of H<sup>+</sup> + e<sup>-</sup> can be computed as half the Gibbs energy of the H<sub>2</sub> molecule at 0 V *vs.* SHE. The Gibbs energy of each reaction can be obtained by computing the binding energies of the adsorbed and gas phase species. The vibrational frequencies of the adsorbed and gas phase reactants were calculated to account for zero-point energy and entropic effects. Constrained dynamics were employed while computing adsorbates and the anchored metal atom by following the same scheme used for the  $Rh/C_3N_4$  system.<sup>37</sup> Using this methodology, one can evaluate the Gibbs energies of the species involved in the reaction network. The computed energies can be directly related to the electrode potential, as shown in eqn (4), which demonstrates reaction 3b as an example:

$$\Delta G_{3b} = \Delta G_{\text{HCOO}*} - 1/2\Delta G_{\text{H}_2} - \Delta G_{\text{CO}*} + eU_{\text{SHE}}$$
(5)

where *e* is the charge of the transferred electron, and *U* is the voltage. The maximum potential required is the electrode potential, at which all the reaction steps are energetically favored, *i.e.*, the reaction path is exergonic. Thus, the maximum potential is the Gibbs energy of the rate-limiting step. The overpotential required is the difference between the equilibrium potential of this reaction (-0.12 V) and the limiting potential. More accurate predictions of the overpotentials implied the calculation of the energy barrier of each step in the reaction mechanism along the pathway. Nevertheless, the electrochemical proton-transfer barriers have been previously shown to be very small, for instance, using Pt as the catalyst.<sup>60,61</sup>

### 3. Results

#### 3.1 Surface corrugation and M deposition

The deposition of Cu, Ag, and Au single metal atoms was explored on the  $g-C_3N_4$  (001) monolayer. The adsorption at the center site was energetically favored over adsorption at the 6-fold cavity, closing the 6-membered ring. Initially, the deposition of metal atoms did not modify monolayer planarity (see Fig. 1). Nevertheless, during the adsorption of the reaction moieties, a slight surface bending was observed due to the surface–adsorbate interaction. To further investigate the stability of this slightly bent monolayer, the structure was calculated by removing the adsorbate. From the point of view of surface



Fig. 1 Sketches of the planar (left) and bent (right)  $g-C_3N_4$  monolayers: (a) bare surface, (b)  $Cu_1@g-C_3N_4$ , (c)  $Ag_1@g-C_3N_4$ , and (d)  $Au_1@g-C_3N_4$ .

energy, the corrugated surface had a monolayer stability close to 2 eV, either by clean or metal-deposited monolayer. Monolayer corrugation occurs in order to minimize the electronic repulsions experienced by the nitrogen lone pairs located in the structural holes. This implies, on the one hand, the stabilization of the Fermi level and the generation of active catalytic sites.<sup>62</sup> Therefore, we considered the energy of the bent monolayer with and without the anchored single metal atoms as references. The same process was performed after including the single metal atoms, as observed in Fig. 1. The binding energies for Cu, Ag, and Au deposition were -1.17 eV, -0.84 eV, and -1.91 eV, respectively, revealing attractive and favorable interactions. With respect to stability under electrochemical conditions, the adsorption of H is considered one of the key factors. In our system, the adsorption of H was slightly repulsive for Cu and Ag (0.29 and 0.72 eV, respectively) while it was highly favored for Au (-0.92 eV); therefore, the Au sites are probably covered by H atoms under electrochemical conditions.

#### 3.2 CO<sub>2</sub> adsorption on bare g-C<sub>3</sub>N<sub>4</sub> and M<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub>

The first step that determines the electrocatalytic reduction of  $CO_2$  is its adsorption on the  $M_1$ @g- $C_3N_4$  support. As mentioned above, the adsorption process is usually omitted to compute the  $CO_2RR$  profile using the CHE model, thus passing directly from the gas phase molecule to the COOH/HCOO adsorbed species. Nevertheless, the adsorbate–surface interactions can be large, which may hinder  $CO_2$  conversion. The adsorption of  $CO_2$  was studied on a clean monolayer (through the interaction with an N and a C atom on the g- $C_3N_4$  surface) and on top of the single metal atom. As reported in Table 1, the energy of adsorption, which takes place through the C atom of  $CO_2$ , reached values between -0.24 and -0.28 eV. The similar binding energies point to the fact that  $CO_2$  maintains the gas-phase geometry after adsorption since the C=O bond length reported in Table 1 is the same, and the molecule is not bent.

#### 3.3 CO<sub>2</sub>RR on bare g-C<sub>3</sub>N<sub>4</sub>

In this work, we have explored the formation of formic acid and carbon monoxide in a two-electron-proton transfer reaction. The first reaction step involves the formation of the carboxyl (COOH) and formate (HCOO) intermediates, which can evolve into CO and  $H_2O$  or HCOOH after the second electron-proton transfer step. This reaction pathway competes directly with the hydrogen evolution reaction. According to the literature, the binding energy of the reaction intermediates determines the favored reaction path.<sup>63-65</sup> The interaction of the gas-phase

**Table 1** Binding energy ( $E_{ads}$ ), C=O distance (d(C-O)), and angle of CO<sub>2</sub> ( $\alpha$ (OCO)) adsorbed on the bent bare and M<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> surfaces

Surface	$E_{\rm ads}$ (eV)	d(C-O) (Å)	α(OCO) (°)
g-C <sub>3</sub> N <sub>4</sub>	-0.27	1.177/1.176	178
Cu@g-C <sub>3</sub> N <sub>4</sub>	-0.28	1.176/1.178	179
Ag@g-C <sub>3</sub> N <sub>4</sub>	-0.22	1.176/1.178	179
Au@g-C <sub>3</sub> N <sub>4</sub>	-0.24	1.175/1.178	178



**Fig. 2** The reaction mechanism of CO<sub>2</sub>RR on the bare g-C<sub>3</sub>N<sub>4</sub> monolayer at 0 V (red), and the limiting potential required to overcome the thermodynamic barriers (blue), showing (a) the formation of CO and (b) HCOOH production. The left and right panels illustrate the energy diagrams considering the formation of COOH (solid lines) and HCOO (dashed lines) as intermediates, respectively.

species with the support is commonly neglected when applying the CHE model. In this work, we have computed the  $CO_2RR$ reaction mechanism with and without considering the binding energies of  $CO_2$ , CO, and HCOOH on the M<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> surface.

First of all, the electrocatalytic activity of the bare support was investigated. The conversion of CO2 to COOH and HCOO intermediates was not favored on the clean g-C<sub>3</sub>N<sub>4</sub> monolayer. As shown in Fig. 2, the first electron-proton transfer required a potential higher than -1.5 V according to the CHE model, with the formation of COOH being slightly more favorable than that of HCOO. Interestingly, the second electron-proton transfer (eqn (3a) and (3b)) was exergonic. The generation of  $CO^*$  + H<sub>2</sub>O(g) from both the COOH and HCOO intermediates (Fig. 2a) was favored by more than 0.80 eV. In addition, the desorption of CO only required 0.18 eV, showing very weak interaction with the support. Regarding HCOOH production from the COOH and HCOO moieties (Fig. 2b), the DFT simulations showed that this process was (1.65 eV) favored in terms of energy. Thus, the first electron-proton transfer is the rate-limiting step of the reaction due to the large overpotential required to generate

COOH and HCOO. Fig. S2 (ESI<sup>†</sup>) shows the reaction mechanism considering the CO<sup>\*</sup><sub>2</sub> and HCOOH\* interactions with the support. The potential required to produce CO and/or HCOOH increased to compensate for the adsorption energy of CO<sub>2</sub><sup>\*</sup>. On the other hand, to include the Gibbs energy of the formic acid molecule adsorbed on the support helped to analyze the desorption energy of the process, sorting the contribution of HCOOH generation from the HCOO\* and COOH\* intermediates and its desorption energy. The second electron-proton transfer implies the formation of adsorbed HCOOH\*, and the process was exergonic by 1.77 eV (HCOO) and 1.35 eV (COOH). The HCOOH\* desorption then only needed 0.19 eV. Despite these excellent and promising results for the second protonelectron transfer reaction, including very low desorption energies of both products, the first proton-electron transfer step hinders the catalytic activity of the bare g-C<sub>3</sub>N<sub>4</sub> monolayer.

#### 3.4 CO<sub>2</sub>RR on M<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub>

The deposition of single metal atoms drastically modifies the electrocatalytic activity of the system. As for the Cu atom, the conversion of CO2 to both COOH and HCOO intermediates was energetically favored (see Fig. 3), in contrast to the results obtained on the bare support. The binding energy of HCOO (Fig. 3a and b, right panels) was larger than that of COOH (Fig. 3a and b, left panels). This is not unexpected since HCOO is typically observed in CO2 hydrogenation using Cu-based catalysts.50,66-68 This strong interaction required a limiting potential of -0.30 V to undergo the second electron-proton transfer process to produce CO, whereas, the moderate interaction of the carboxyl moiety with the Cu atom favored the second reaction step without an overpotential. Thus, an overpotential of 0.42 was required. The difference in the binding energies of both reaction intermediates can be attributed to the adsorption mode. As depicted in Fig. 3, HCOO is adsorbed in a bidentate mode, with both O atoms in contact with the Cu single atom, while in the case of COOH, the intermediate is adsorbed via the C atom. This leads to the large binding energy of HCOO. Including the binding energy of CO<sub>2</sub> with the Cu atom in the CHE model (see Fig. S3, ESI<sup>†</sup>), a limiting potential of 0.1 V is required. However, one important shortcoming was observed. The binding energy of CO on a Cu single atom was strong (1.54 eV), making the desorption process the ratelimiting step of the reaction. Thus, to release CO from the electrocatalytic active site, more electron-proton transfer steps are required to promote CO conversion. It is important to mention that metals that bind CO strongly produce few CO2RR products, and consequently, the competing water reduction reaction can produce H<sub>2</sub> as the main product.<sup>69</sup> Fig. 3b depicts the reaction mechanism of HCOOH production, where the COOH intermediate favors its formation compared with HCOO. A limiting potential of -0.37 V is predicted to make the second electron-proton step thermodynamically feasible since the first protonation is energetically favored. As illustrated in Fig. S3 (ESI<sup>†</sup>), the COOH<sup>\*</sup> + H<sup>+</sup> + e<sup>-</sup>  $\rightarrow$  HCOOH<sup>\*</sup> reaction step is isoenergetic, i.e. the production of formic acid adsorbed on



**Fig. 3** The reaction mechanism of  $CO_2RR$  on the  $Cu_1@g-C_3N_4$  monolayer at 0 V (red) and the limiting potential required to overcome the thermodynamic barriers (blue), showing (a) the formation of CO and (b) HCOOH production. The left and right panels illustrate the energy diagrams considering COOH (solid lines) and HCOO (dashed lines) as intermediates, respectively.

top of a Cu single atom does not require an overpotential. The potential required to generate HCOOH (g) (0.37 eV) is linked with HCOOH desorption. Again, the strong binding energy of the HCOO moiety in a bidentate adsorption mode on top of the Cu atom makes the formation of HCOOH difficult since the threshold of the second electron-proton transfer step is 1.09 eV higher in energy. In contrast to the observations using the COOH intermediate, the HCOO\* + H<sup>+</sup> + e<sup>-</sup>  $\rightarrow$  HCOOH\* step was not isoenergetic but endergonic by 0.73 eV (Fig. S3, ESI<sup>†</sup>). In summary, our simulations show that Cu<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> catalyzes the first proton-electron transfer, favoring the formation of COOH and HCOO, with the latter showing the largest binding energy with the Cu atom. This fact implies a large overpotential for the second proton-electron transfer step. Nevertheless, the production of CO and HCOOH from the COOH intermediate is favored. Furthermore, the binding energy of CO hinders its desorption and can enhance the formation of C2 compounds after more proton-electron transfer steps or promote the competitive H<sub>2</sub> generation (HER) reaction. To further explore the HER vs CO<sub>2</sub>RR competition, the energy profile of HER was



### **Reaction Coordinate**

Fig. 4 The reaction mechanism of HER on the  $Cu_1@g-C_3N_4$  monolayer at 0 V (red) and the overpotential required to overcome the thermodynamic barriers (blue).

obtained, as illustrated in Fig. 4. One can observe that an overpotential of 0.29 V is required to produce  $H_2$ . Indeed, CO production is energetically favored, although the strong Cu–CO interaction prevents its desorption. In contrast, the  $H_2$  molecule binds weakly to Cu, at only 0.42 eV, and the overpotential required is slightly lower than that needed for the formation of HCOOH. Our DFT results agree with experimental studies, wherein only  $H_2$  and HCOOH were found as products.<sup>31</sup> On the one hand, the large binding energy of CO with the Cu single atom prevents its production, favoring the hydrogen evolution reaction. On the other hand, our calculations predict the facile formation of formic acid by means of COOH due to its moderate binding energy with Cu and the energetically favored proton–electron transfer step to generate HCOOH.

The use of Ag as a single-atom catalyst presented different activity than that of Cu. Regarding the first proton-electron transfer, the formation of HCOO was energetically favored, as reported for the Cu single atom, whereas, an overpotential was required to generate COOH (see Fig. 5a). Therefore, the discussion is focused on the second proton-transfer step starting from the HCOO intermediate (the right panels in Fig. 5a and b). The production of CO from HCOO was endergonic, and consequently, a limiting potential of -0.55 V was needed to overcome the thermodynamic barrier. Although the desorption energy of CO was around 1 eV lower than the energy predicted using a Cu single atom, it was still energetically demanding (0.56 eV). The production of formic acid, as reported in Fig. 5b, was the most favored reaction pathway since it required only a potential of -0.37 V, with the second proton-electron transfer step being the most energy-demanding. Regarding the possible competition of HER, in this case, the  $H_{ads}$  on top of Ag was unstable at 0.72 eV, which is a higher overpotential than that required for CO<sub>2</sub>RR. To conclude, the Ag<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> system promotes the production of HCOOH, with a slightly lower overpotential than



**Fig. 5** The reaction mechanism of CO<sub>2</sub>RR on the Ag<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> monolayer at 0 V (red) and the limiting potential required to overcome the thermodynamic barriers (blue), showing (a) the formation of CO and (b) HCOOH production. The left and right panels illustrate the energy diagrams considering COOH (solid lines) and HCOO (dashed lines) as intermediates, respectively.

that of the formation of CO. In addition, when the adsorption energy of HCOOH was included in the CHE model, it could be observed that the HCOO\* + H<sup>+</sup> + e<sup>-</sup>  $\rightarrow$  HCOOH\* reaction required only -0.17 V, whereas the desorption energy of adsorbed HCOOH was 0.19 eV, which is lower than the desorption energy of the CO molecule on top of the Ag single atom (see Fig. S4, ESI†).

Prior to analyzing the results of  $Au_1@g-C_3N_4$ , the large binding energy of the H atoms on top of the Au atom must be evaluated. It may imply that the catalytic active site is covered by H atoms at operational conditions, which can poison the single Au atom site. However, this does not mean that Au favors the HER since the binding energy is too large to favor H<sub>2</sub> production. Focusing on the results of CO<sub>2</sub>RR (see Fig. 6), the first proton–electron transfer was exergonic, with COOH (-1.00 eV) being a slightly more favored intermediate than HCOO (-0.88 eV), which is in contrast to Cu and Ag. Though the exergonicity of this step was also observed over the Cu<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> catalyst, in the Cu system, the formation of HCOO is clearly favored. In the Au<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> catalyst, the interaction of





**Fig. 6** The reaction mechanism of  $CO_2RR$  on the Au<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> monolayer at 0 V (red) and the limiting potential required to overcome the thermodynamic barriers (blue), showing (a) the formation of CO and (b) HCOOH production. The left and right panels illustrate the energy diagrams considering COOH (solid lines) and HCOO (dashed lines) as intermediates, respectively.

both intermediates with the anchored Au atom was strong. For the second proton-electron transfer, a lower overpotential was required to produce CO (Fig. 6a) rather than HCOOH (Fig. 6b). Nevertheless, as observed for Cu<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub>, the desorption of CO was not feasible due to the strong interaction with the Au atom (1.50 eV). According to experiments using a Cu single atom on  $C_3N_4$ , this strong binding energy favors H<sub>2</sub> generation.<sup>31</sup> Furthermore, our simulations rule out the a priori production of HCOOH due to this large overpotential. On the other hand, we computed the reaction mechanism considering HCOOH adsorption in the CHE model. As illustrated in Fig. S5 (ESI<sup>+</sup>), a large overpotential was required to perform the second electron-proton transfer (COOH\*/HCOO\* +  $H^+ + e^- \rightarrow HCOOH^*$ ). In the case of the Cu<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> system, this process was isoenergetic, and the main shortcoming was the HCOOH desorption energy. However, when using Au instead of Cu, this process is not feasible. The adsorption of HCOOH\* is less favored on top of Au.

In summary, Cu and Au single-metal atoms anchored on  $g-C_3N_4$  catalyze the first electron-proton transfer to generate COOH and HCOO as intermediates without an overpotential,

#### PCCP

while Ag only favors the formation of HCOO. The main drawback of these systems is the strong binding energy of the metal with the HCOO intermediate and CO, which implies the need for large overpotentials, and the strong Au-H interaction. For HCOOH production from HCOO and COOH intermediates, Ag<sub>1</sub>@ g-C<sub>3</sub>N<sub>4</sub> and Cu<sub>1</sub>(@g-C<sub>3</sub>N<sub>4</sub> require only a limiting potential of -0.37 V. With respect to CO generation, the Cu<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> system does not require an overpotential although the strong interaction of CO with Cu (also observed with Au) hinders its production. Finally, we have evaluated the role of the 2D carbon nitride on the CO2RR. Large overpotentials are required to overcome the thermodynamic barrier of the first electron-proton transfer, whereas it is significant that the second transfer is exergonic. This opens the possibility for  $M_1$ (a)g- $C_3N_4$  to function as bifunctional catalysts, where the single metal atoms are responsible for the first electron-proton transfer to generate the carboxyl and formate intermediates, and after the HCOO and COOH spillover to the g-C<sub>3</sub>N<sub>4</sub> monolayer, HCOOH and CO production becomes feasible. The strong interaction of CO with single metal atoms probably will hinder its diffusion to the surface, promoting the competitive reaction, namely H<sub>2</sub> generation.

## 4. Conclusions

The computational hydrogen electrode model has been used to explore the suitability of Cu, Ag, and Au single atoms supported on 2D carbon nitride as electrocatalysts for  $CO_2RR$ . Our DFT simulations reveal that bare  $g-C_3N_4$  is a good electrocatalyst for the second electron–proton transfer to generate CO and HCOOH, although according to the calculations, the initial conversion of  $CO_2$  to COOH and/or HCOO moieties requires a very large overpotential.

The deposition of single metal atoms changes the ratelimiting step of the reaction. The Cu, Ag, and Au single atoms carry out the first proton-electron transfer without an overpotential (except for Ag to generate the COOH intermediate). Nevertheless, the drawbacks of these systems are linked to the strong interaction of HCOO and CO with the single-metal atoms. The Cu<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> system can produce CO without an overpotential and HCOOH with a low limiting potential of -0.37 V. However, HCOO formation is preferred due to its strong interaction with Cu, which hinders further HCOO conversion towards CO and/or HCOOH. The carboxyl intermediate shows a moderate binding energy and helps the production of CO, although a desorption energy higher than 1.50 eV is predicted, which can make its production difficult. Moreover, the overpotential required for HER is slightly lower, and as confirmed by experiments, can promote the HER instead of  $CO_2RR$ . The Ag<sub>1</sub>@g-C<sub>3</sub>N<sub>4</sub> system promotes the formation of the HCOO intermediate. The Au1@g-C3N4 system exhibits the same drawback as Cu1@g-C3N4, with a similar desorption energy for CO, and slightly large overpotentials with respect to the Cu and Ag systems to produce HCOOH. Furthermore, Au shows large binding energy toward H atoms, which can block the active surface sites. Taken together, our work suggests that these systems may work as bifunctional catalysts, with the metal

atom being responsible for the first electron-proton transfer and the support facilitating the second transfer and product desorption.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

S. P. P. thanks Marie Curie fellowship (H2020-MSCA-IF-2020-101020330). A. P. is a Serra Húnter Professor and thanks ICREA Academia 2019. A. P. and M. S. thank the Spanish Ministerio de Ciencia e Innovación for projects PID2021-127423NB-I00 and PID2020-13711GB-I00 and the Generalitat de Catalunya for project 2021SGR623. Computational time at the *MARENOS-TRUM* supercomputer has been provided by the Barcelona Supercomputing Centre through a grant from *Red Española de Supercomputación (QHS-2022-1-0017 and QHS-2022-2-0012).* 

## References

- 1 X. Lim, Nature, 2015, 526, 628.
- 2 Intergovernmental Panel on Climate Change, Climate Change 2013 – The Physical Science Basis, Cambridge University Press, 1st edn, 2014.
- 3 M. Aresta, ed. *Carbon Dioxide as Chemical Feedstock*, Wiley-VCH, New York, 2010.
- 4 D. Preti, C. Resta, S. Squarcialupi and G. Fachinetti, *Angew. Chem., Int. Ed.*, 2011, **50**, 12551.
- H. Zhou, Z. Chen, A. Vidal-López, E. Díaz López, E. Lam,
   A. Tsoukalou, E. Willinger, D. A. Kuznetsov, D. Mance,
   A. Kierzkowska, F. Donat, P. M. Abdala, A. Comas-Vives,
   C. Copéret, A. Fedorov and C. R. Müller, *Nat. Catal.*, 2021, 4, 860.
- 6 W. Al Maksoud, A. Saidi, M. K. Samantaray, E. Abou-Hamad, A. Poater, S. Ould-Chikh, X. Guo, E. Guan, T. Ma, B. C. Gates and J.-M. Basset, *Chem. Commun.*, 2020, 56, 3528.
- 7 V. D'Elia, H. Dong, A. Rossini, C. Widdifield, S. V. C. Vummaleti, Y. Minenkov, A. Poater, E. Abou-Hamad, J. D. A. Pelletier, L. Cavallo, L. Emsley and J.-M. Basset, *J. Am. Chem. Soc.*, 2015, 137, 7728.
- 8 F. Poovanm, V. G. Chandrashekhar, K. Natte and R. V. Jagadeesh, *Catal. Sci. Technol.*, 2022, **12**, 6623.
- 9 X. Cui, W. Li, P. Ryabchuk, K. Junge and M. Beller, *Nat. Catal.*, 2018, **1**, 385.
- 10 B. Qiao, A. Wang, X. Yang, L. F. Allard, Z. Jiang, Y. Cui, J. Liu, J. Li and T. Zhang, *Nat. Chem.*, 2011, 3, 634.
- 11 X. Nie, W. Luo, M. J. Janik and A. Asthagiri, *J. Catal.*, 2014, **312**, 108.
- 12 H. Xiao, T. Cheng, W. A. Goddard and R. Sundararaman, *J. Am. Chem. Soc.*, 2016, **138**, 483.
- 13 J. D. Goodpaster, A. T. Bell and M. J. Head-Gordon, *Phys. Chem. Lett.*, 2016, 7, 1471.
- 14 R. Reske, H. Mistry, F. Behafarid, B. Roldan-Cuenya and P. Strasser, J. Am. Chem. Soc., 2014, **136**, 6978.

- 15 A. R. Woldu, Z. Huang, P. Zhao, L. Hu and D. Astruc, *Coord. Chem. Rev.*, 2022, 454, 214340.
- 16 A. A. Peterson, F. Abild-Pedersen, F. Studt, J. Rossmeisl and J. K. Norskov, *Energy Environ. Sci.*, 2010, 3, 1311.
- 17 A. Rendón-Calle, S. Builes and F. Calle-Vallejo, *Curr. Opin. Electrochem.*, 2018, 9, 158.
- 18 I. Ledezma-Yanez, E. Perez-Gallent, M. T. M. Koper and F. Calle-Vallejo, *Catal. Today*, 2016, 262, 90.
- 19 A. Rendón-Calle, Q. H. Low, S. H. L. Hong, S. Builes, B. S. Yao and F. Calle-Vallejo, *Appl. Catal.*, 2021, **285**, 119776.
- 20 S. Rasul, D. H. Anjum, A. Jedidi, Y. Minenkov, L. Cavallo and K. Takanabe, *Angew. Chem., Int. Ed.*, 2015, **127**, 2174.
- 21 M. Zhu, P. Tian, J. Li, J. Chen, J. Xu and Y. F. Han, *ChemSusChem*, 2019, **12**, 3955.
- 22 S. Sarfraz, A. T. Garcia-Esparza, A. Jedidi, L. Cavallo and K. Takanabe, *ACS Catal.*, 2016, **6**, 2842.
- H. Hu, Y. Wang, N. Du, Y. Sun, Y. Tang, Q. Hu, P. Wang, L. Dai,A. C. Fisher and X. J. Yang, *ChemElectroChem*, 2018, 5, 3854.
- 24 Y. Chen, C. W. Li and M. W. Kanan, J. Am. Chem. Soc., 2012, 134, 19969.
- 25 H. Mistry, R. Reske, Z. Zeng, Z. J. Zhao, J. Greeley, P. Strasser and B. Roldan-Cuenya, *J. Am. Chem. Soc.*, 2014, **136**, 16473.
- 26 H. Mistry, Y. W. Choi, A. Bagger, F. Scholten, C. S. Bonifacio, I. Sinev, N. J. Divins, I. Zegkinoglou, H. S. Jeon, K. Kisslinger, E. A. Stach, J. C. Yang, J. Rossmeisl and B. Roldan-Cuenya, *Angew. Chem., Int. Ed.*, 2017, **56**, 11394.
- 27 P. Iyengar, M. J. Kolb, J. R. Pankhurst, F. Calle-Vallejo and R. Bounsanti, ACS Catal., 2021, 11, 4456.
- 28 Q. Lu, K. Eid, W. Li, A. M. Abdullah, G. Xu and R. S. Varma, *Green Chem.*, 2021, 23, 5394.
- 29 S. Kumar, S. Karthikeyan and A. F. Lee, *Catalysts*, 2018, 8, 74.
- 30 G. Gao, Y. Jiao, E. Waclawik and A. Du, J. Am. Chem. Soc., 2016, 138, 6292.
- 31 C. Cometto, A. Ugolotti, E. Grazietti, A. Moretto, G. Bottaro, L. Armelao, C. Di Valentin, L. Calvillo and G. A. Granozzi, *npj 2D Mater. Appl.*, 2021, 5, 63.
- 32 Y. Peng, B. Lu and S. Chen, Adv. Mater., 2018, 30, 1801995.
- 33 J. Yu, C. Chen, Q. Zhang, J. Lin, X. Yang, L. Gu, H. Zhang, Z. Liu, Y. Wang, S. Zhang, X. Wang and L. Guo, *J. Am. Chem. Soc.*, 2022, 144, 21908.
- 34 J. H. Kwak, J. Hu, D. Mei, C. W. Yi, D. H. Kim, C. H. Peden, L. F. Allard and J. Szanyi, *Science*, 2009, 325, 1670.
- 35 X. F. Yang, A. Wang, B. Qiao, J. Li, J. Liu and T. Zhang, Acc. Chem. Res., 2013, 46, 1740–1748.
- 36 J. Wang, T. Heil, B. Zhu, C. W. Tung, J. Yu, H. M. Chen, M. Antonietti and S. Cao, ACS Nano, 2020, 14, 8584–8593.
- 37 L. Jurado, J. Esvan, L. A. Luque-Álvarez, L. F. Bobadilla, J. A. Odriozola, S. Posada-Pérez, A. Poater, A. Comas-Vives and M. R. Axet, *Catal. Sci. Technol.*, 2023, DOI: 10.1039/ D2CY02094G.
- 38 A. S. Dobrota, N. V. Skorodumova, S. V. Mentus and I. A. Pašti, *Electrochim. Acta*, 2022, 412, 140155.
- 39 S. Zhang, P. Kang, S. Ubnoske, M. K. Brennaman, N. Song, R. L. House, J. T. Glass and T. J. Meyer, *J. Am. Chem. Soc.*, 2014, **136**, 7845.

- 40 B. Kumar, M. Asadi, D. Pisasale, S. Sinha-Ray, B. A. Rosen, R. Haasch, J. Abiade, A. L. Yarin and A. Salehi-Khojin, *Nat. Commun.*, 2013, 4, 2819.
- 41 A. S. Varela, N. R. Sahraie, J. Steinberg, W. Ju, H.-S. Oh and P. Strasser, *Angew. Chem., Int. Ed.*, 2015, 54, 10758.
- 42 D. M. Koshy, S. Chen, D. U. Lee, M. B. Stevens, A. M. Abdellah, S. M. Dull, G. Chen, D. Nordlund, A. Gallo, C. Hahn, D. C. Higgins, Z. Bao and T. F. Jaramillo, *Angew. Chem., Int. Ed.*, 2022, 61, e202206233.
- 43 S. Chen, X. Li, C. W. Kao, T. Luo, K. Chen, J. Fu, C. Ma, H. Li,
  M. Li, T. S. Chan and M. Liu, *Angew. Chem., Int. Ed.*, 2022,
  61, e202206233.
- 44 A. S. Varela, W. Ju, A. Bagger, P. Franco, J. Rossmeisl and P. Strasser, *ACS Catal.*, 2019, **9**, 7270.
- 45 W. Zhang, Q. Fu, Q. Luo, L. Sheng and J. Yang, *JACS Au*, 2021, 1, 2130.
- 46 M. A. Centeno, T. Ramirez-Reina, S. Ivanova, O. Hernando-Laguna and J. A. Odriozola, *Catalysts*, 2016, **6**, 158.
- 47 R. Lang, X. Du, Y. Huang, X. Jiang, Q. Zhang, Y. Guo, K. Liu, B. Qiao, A. Wang and T. Zhang, *Chem. Rev.*, 2020, **120**, 11986.
- 48 C. Schilling, M. Ziemba, C. Hess and M. V. Ganduglia-Pirovano, J. Catal., 2020, 383, 264.
- 49 Y. Zhang, Y. Mo and Z. Cao, ACS Appl. Mater. Interfaces, 2022, 14, 1002.
- 50 C. Liu, B. Yang, E. Tyo, S. Seifert, J. DeBartolo, B. von Issendorff, P. Zapol, S. Vajda and L. A. Curtiss, *J. Am. Chem. Soc.*, 2015, 137, 8676.
- 51 A. A. Herzing, C. J. Kiely, A. F. Carley, P. Landon and G. J. Hutchings, *Science*, 2008, **321**, 1331.
- 52 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, 77, 3865.
- 53 S. Grimme, J. Anthony, S. Ehrlich and H. Krieg, *J. Chem. Phys.*, 2010, **132**, 154104.
- 54 P. E. Blöchl, Phys. Rev. B: Condens. Matter Mater. Phys., 1994, 50, 17953.
- 55 G. Kresse and D. Joubert, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1999, **59**, 1758.
- 56 G. Kresse and J. Furthmüller, Phys. Rev. B: Condens. Matter Mater. Phys., 1996, 54, 11169.
- 57 A. Jain, S. P. Ong, G. Hautier, W. Chen, W. D. Richards, S. Dacek, S. Cholia, D. Gunter, D. Skinner, G. Ceder and K. A. Persson, *APL Mater.*, 2013, 1, 011002.
- 58 H. J. Monkhorst and J. D. Pack, Phys. Rev. B: Solid State, 1976, 13, 5188.
- 59 J. K. Nørskov, J. Rossmeisl, A. Logadottir, L. Lindqvist, J. R. Kitchin, T. Bligaard and H. Jónsson, *J. Phys. Chem. B*, 2004, **108**, 17886.
- 60 V. Tripkovic, E. Skulason, S. Siahrostami, J. Nørskov and J. Rossmeisl, *Electrochim. Acta*, 2010, **55**, 7975.
- 61 M. J. Janik, C. D. Taylor and M. Neurock, *J. Electrochem. Soc.*, 2009, **156**, B126.
- 62 L. M. Azofra, D. R. MacFarlane and C. Sun, *Phys. Chem. Chem. Phys.*, 2016, **18**, 18507.
- 63 W. Ju, A. Bagger, G. P. Hao, A. S. Varela, I. Sinev, V. Bon, B. Roldan-Cuenya, S. Kaskel, J. Rossmeisl and P. Strasser, *Nat. Commun.*, 2017, 8, 944.

- 64 A. Bagger, W. Ju, A. S. Varela, P. Strasser and J. Rossmeisl, *Chem. Phys. Chem.*, 2015, **18**, 3226.
- 65 Q. He, J. H. Lee, D. Liu, Y. Liu, Z. Lin, Z. Xie, S. Hwang, S. Kattel, L. Song and J. G. Chen, *Adv. Funct. Mater.*, 2020, **30**, 2000407.
- 66 S. Posada-Pérez, P. J. Ramirez, R. A. Gutierrez, D. J. Stacchiola, F. Viñes, P. Liu, F. Illas and J. A. Rodriguez, *Catal. Sci. Technol.*, 2016, 6, 6766.
- 67 F. Studt, M. Behrens, E. L. Kunkes, N. Thomas, S. Zander, A. Tarasov, J. Schumann, E. Frei, J. B. Varley, F. Abil-Pedersen, J. K. Norskov and R. Schlogl, *ChemCatChem*, 2015, 7, 1105.
- 68 Y. Kim, T. S. B. Trung, S. Yang, S. Kim and H. Lee, ACS Catal., 2016, 6, 1037.
- 69 K. P. Kuhl, T. Hatsukade, E. R. Cave, D. N. Abram, J. Kibsgaard and T. F. Jaramillo, *J. Am. Chem. Soc.*, 2014, **136**, 14107.