

Cite this: *Chem. Sci.*, 2023, **14**, 12331

All publication charges for this article have been paid for by the Royal Society of Chemistry

## Designing complex $\text{Pb}_3\text{SBr}_{x}\text{I}_{4-x}$ chalcohalides: tunable emission semiconductors through halide-mixing†

Alison N. Roth,<sup>ab</sup> Yunhua Chen,<sup>ab</sup> Anuluxan Santhiran,<sup>ID ab</sup> Jemima Opare-Addo,<sup>ab</sup> Eunbyeol Gi,<sup>ID ab</sup> Emily A. Smith,<sup>ID ab</sup> Aaron J. Rossini,<sup>ID ab</sup> and Javier Vela<sup>ID \*ab</sup>

Chalcohalides are desirable semiconducting materials due to their enhanced light-absorbing efficiency and stability compared to lead halide perovskites. However, unlike perovskites, tuning the optical properties of chalcohalides by mixing different halide ions into their structure remains to be explored. Here, we present an effective strategy for halide-alloying  $\text{Pb}_3\text{SBr}_{x}\text{I}_{4-x}$  ( $1 \leq x \leq 3$ ) using a solution-phase approach and study the effect of halide-mixing on structural and optical properties. We employ a combination of X-ray diffraction, electron microscopy, and solid-state NMR spectroscopy to probe the chemical structure of the chalcohalides and determine mixed-halide incorporation. The absorption onsets of the chalcohalides blue-shift to higher energies as bromide replaces iodide within the structure. The photoluminescence maxima of these materials mimics this trend at both the ensemble and single particle fluorescence levels, as observed by solution-phase and single particle fluorescence microscopy, respectively. These materials exhibit superior stability against moisture compared to traditional lead halide perovskites, and IR spectroscopy reveals that the chalcohalide surfaces are terminated by both amine and carboxylate ligands. Electronic structure calculations support the experimental band gap widening and volume reduction with increased bromide incorporation, and provide useful insight into the likely atomic coloring patterns of the different mixed-halide compositions. Ultimately, this study expands the range of tunability that is achievable with chalcohalides, which we anticipate will improve the suitability of these semiconducting materials for light absorbing and emission applications.

Received 29th May 2023  
Accepted 12th October 2023

DOI: 10.1039/d3sc02733c  
[rsc.li/chemical-science](http://rsc.li/chemical-science)

## Introduction

Lead halide perovskites are well known semiconducting materials for light harvesting and light emitting devices.<sup>1</sup> Their impressive optical properties, such as tunable band gaps over the visible and near-IR regions<sup>2</sup> and high photoluminescence quantum yields (PLQY)<sup>3</sup> are often attainable due to their high defect tolerance.<sup>4</sup> However, halide perovskites notoriously suffer from poor thermal and phase stability under irradiation due to the weak ionic interactions of metal–halide bonds, often resulting in halide migration, phase segregation, and PL instability.<sup>5,6</sup> This challenge continues to limit full-scale implementation of halide perovskites into their anticipated technologically relevant applications.<sup>7,8</sup>

In light of this challenge, chalcohalides are gaining attention as promising alternative materials to halide perovskites.<sup>9–11</sup> In

principle, chalcohalides are expected to combine the optimal features of both chalcogenides and halide perovskites: that is, enhanced stability and light absorbing efficiency, respectively.<sup>12,13</sup> Multinary chalcohalides have already demonstrated favorable structural and optical properties for photovoltaics.<sup>14,15</sup> Other compositions are also being explored for applications including thermoelectrics,<sup>16,17</sup> photocatalysis,<sup>18</sup> and second harmonic generation.<sup>19,20</sup> While solid-state reactions are primarily used to isolate these materials, the solution-phase chemistry of colloidal chalcohalides is rapidly expanding as a way to achieve better control over phase purity, particle size and morphology and, consequently, optoelectronic properties.<sup>21–23</sup>

An exciting opportunity is to explore the effects of halide-alloying on chalcohalide semiconductors.<sup>24</sup> Similar to mixed-halide perovskites (MHPs), introducing various types of halide ions into the structure of chalcohalides could lead to desirable band gap tunability while maintaining the enhanced stability and other characteristics displayed by chalcogenide-based materials. A suitable candidate for exploring this halide-alloying strategy is one of the few existing mixed-halide chalcohalides,  $P2_1/m$   $\text{Pb}_3\text{SBrI}_3$ . Recently isolated from a hydrothermal process,  $\text{Pb}_3\text{SBrI}_3$  features a pseudo-two-dimensional

<sup>a</sup>US DOE Ames National Laboratory, Ames, Iowa 50010, USA

<sup>b</sup>Department of Chemistry, Iowa State University, Ames, Iowa 50011, USA. E-mail: [vela@iastate.edu](mailto:vela@iastate.edu)

† Electronic supplementary information (ESI) available: Experimental details, XRD, TEM, SEM, EDS, PL movies, unit cell coloring patterns, DOS. See DOI: <https://doi.org/10.1039/d3sc02733c>






Fig. 1 Unit cell of monoclinic ( $P2_1/m$ )  $\text{Pb}_3\text{SBrI}_3$ .<sup>25</sup>

layered structure with a narrow indirect band gap (Fig. 1).<sup>25</sup> The low dimensionality of  $\text{Pb}_3\text{SBrI}_3$  makes it unique among other mixed-halide chalcohalide compositions,<sup>25,26</sup> as these features may be suggestive of anisotropic optical properties that are worth exploring in more detail.<sup>27,28</sup> Furthermore, based on similarities with related quaternary chalcohalides, such as  $\text{Pb}_2\text{SbS}_2\text{I}_3$ , we hypothesized that  $\text{Pb}_3\text{SBrI}_3$  and other mixed-halide compositions may be accessible using a thiocyanate-based solution-phase synthesis.<sup>21–23</sup>

In this work, we explore the structural and optical properties of quaternary mixed-halide chalcohalides with the general composition  $\text{Pb}_3\text{SBr}_{x}\text{I}_{4-x}$  ( $1 \leq x \leq 3$ ). X-ray diffraction (XRD) in combination with  $^{207}\text{Pb}$  solid-state (ss) NMR and electron microscopy (EM) confirm successful halide alloying and reveal that the materials adopt highly anisotropic morphologies. Interestingly, solution-phase spectroscopy and fluorescence microscopy show that the mixed-halide chalcohalides are photoluminescent both as an ensemble and at the single particle level. Their band gap and PL emission energies blue-shift as the content of bromine relative to iodine increases. We used DFT calculations to assess the atomic coloring pattern of the bromine-rich mixed-halide compositions and their


corresponding optical properties. Our results suggest that halide-alloying may be a useful strategy for further modifying and enhancing the opto-electronic properties of chalcohalide semiconductors.

## Results and discussion

### Chalcohalide synthesis and halide mixing

$\text{Pb}_3\text{SBrI}_3$  adopts a monoclinic ( $P2_1/m$ ) structure composed of three lead sites with possible coordination environments of  $[\text{PbS}_3\text{I}_5]$ ,  $[\text{PbSBr}_2\text{I}_5]$ , and  $[\text{PbBr}_3\text{I}_4]$ , respectively (Fig. 1). We prepare  $\text{Pb}_3\text{SBrI}_3$  from solution using a heat-up approach—additional Experimental details appear in the ESI File† (Scheme 1). Standard starting mixtures consist of 19 mM  $\text{Pb}(\text{SCN})_2$ , 19–57 mM each of  $\text{PbBr}_2$  and  $\text{PbI}_2$ , 0.25 mL each of oleylamine (oleylNH<sub>2</sub>) and oleic acid, and 10 mL of 1-octadecene (ODE). Upon heating to temperatures above 150 °C, the reaction mixture initially undergoes a distinct color change from light yellow to dark red, indicating decomposition of the thiocyanate precursor.<sup>29,30</sup> Once the temperature reaches 180 °C, the reaction mixture gradually transforms to a vivid yellow-orange color over the course of  $\geq 1$  h, indicating the formation of the chalcohalide. Varying the initial concentrations of  $\text{PbI}_2$  and  $\text{PbBr}_2$ , respectively, from 57 mM and 19 mM, to 38 mM and 19 mM, 19 mM and 19 mM, and 19 mM and 38 mM enables the preparation of  $\text{Pb}_3\text{SBr}_{x}\text{I}_{4-x}$  ( $1 \leq x \leq 3$ ) phases with nominal halide synthetic loadings of 25%, 33%, 50%, and 66% Br, respectively. These reactions generally occur at 180–200 °C for 60–90 min, resulting in bright yellow-colored suspensions (Table 1, see ESI†).

Powder X-ray diffraction (XRD) shows that the reaction with a synthetic loading of 25% Br—relative to total halides—results in the known  $P2_1/m$   $\text{Pb}_3\text{SBrI}_3$  phase, although a few reflections appear broadened and/or selectively attenuated (Fig. 2). We hypothesized that this may be caused by size (Scherrer) effects as well as by anisotropic (preferred) particle growth, similar to what is observed for mixed-cation chalcohalide nanorods<sup>23,31</sup> and  $\text{Pb}_5\text{S}_2\text{I}_6$  nanoparticles.<sup>32</sup> Indeed, scanning electron microscopy (SEM) confirms that the mixed-halide chalcohalides consist of elongated, high-aspect ratio, rod- and needle-like particles (Fig. 2d). The average rod



Scheme 1 Solution-phase synthesis of quaternary mixed-halide chalcohalides.<sup>23,29</sup>

Table 1 Synthesis of mixed-halide chalcohalides

Precursors		Ligands <sup>a</sup> (mL)	$T$ (°C)	$t$ (min)	Product <sup>b</sup>	Band gap <sup>c</sup> (eV)	Width <sup>d</sup> (Scherrer) <sup>e</sup> ( $w$ , nm)	Length <sup>d</sup> ( $l$ , $\mu\text{m}$ )	Aspect ratio ( $l/w$ )
Pb-S (mmol)	PbX <sub>2</sub> (mmol)								
Pb(SCN) <sub>2</sub> (0.2)	Br (0.2), I (0.6)	OleylNH <sub>2</sub> (0.25) Oleic acid (0.25)	180	90	$\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$	2.22	$94 \pm 22$ ( $70 \pm 31$ )	$1.0 \pm 0.4$	11
Pb(SCN) <sub>2</sub> (0.2)	Br (0.2), I (0.4)	OleylNH <sub>2</sub> (0.25) Oleic acid (0.25)	180	60	$\text{Pb}_{3.0}\text{SBr}_{1.2}\text{I}_{2.8}$	2.26	$150 \pm 30$ ( $129 \pm 56$ )	$3.1 \pm 1.3$	21
Pb(SCN) <sub>2</sub> (0.2)	Br (0.2), I (0.2)	OleylNH <sub>2</sub> (0.25) Oleic acid (0.25)	180	60	$\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$	2.29	$170 \pm 28$ ( $152 \pm 92$ )	$3.0 \pm 0.9$	18
Pb(SCN) <sub>2</sub> (0.2)	Br (0.4), I (0.2)	OleylNH <sub>2</sub> (0.25) Oleic acid (0.25)	200	60	$\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$	2.33	$270 \pm 80$ ( $245 \pm 116$ )	$4.3 \pm 1.5$	16

<sup>a</sup> ODE = 1-octadecene (10 mL); oleylNH<sub>2</sub> = oleylamine. <sup>b</sup> From EDS. <sup>c</sup> From Tauc plots.<sup>50</sup> <sup>d</sup> From SEM. <sup>e</sup> From XRD.






Fig. 2 (a) Powder XRD patterns of mixed-halide chalcohalides prepared with different concentrations of  $\text{PbI}_2$  and  $\text{PbBr}_2$  (see details in ESI†). (b) Normalized XRD patterns showing the shift in the (200) reflection to higher  $2\theta$  with increasing %Br. (c) Position of the (200) and (003) reflections and a lattice parameter as a function of %Br. (d) SEM images showing the rod-like morphology of the mixed-halide chalcohalides:  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$ ,  $\text{Pb}_{3.0}\text{SBr}_{1.2}\text{I}_{2.8}$ ,  $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$ , and  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$ . (e) EDS analysis of mixed-halide chalcohalides as a function of %Br.

length of the mixed-halides is between 1–4  $\mu\text{m}$ , and the average rod diameter 100–300 nm, in close agreement with their average Scherrer size from XRD (see Table 1). In general, the average rod diameter increases with higher %Br synthetic loading, suggesting a higher reactivity for the bromide precursor.<sup>33</sup>

Powder X-ray diffraction (XRD) shows that higher Br synthetic loadings between 33% and 66% result in crystalline solids with patterns similar to that of  $\text{Pb}_3\text{SBrI}_3$ . However, the diffraction peaks in these patterns progressively shift to higher  $2\theta$  values—corresponding to lower  $d$ -spacings—with the largest shift observed for the material with the highest (66%) Br loading (Fig. 2a–c). These XRD features are very characteristic of similar materials such as mixed-halide perovskites (MHPs), where XRD reflections shift to wider ( $2\theta$ ) angles with increasing incorporation of smaller halide ions.<sup>34–36</sup> The shift in XRD reflections indicates a steady reduction of lattice parameters and, consequently, a compression of the unit cell volume relative to the original  $\text{Pb}_3\text{SBrI}_3$  crystal structure. Thus, the volume compression observed with increasing %Br is consistent with smaller  $\text{Br}^-$  ( $r_{\text{crys}} = 1.82$  Å) replacing larger  $\text{I}^-$  ( $r_{\text{crys}} = 2.06$  Å)<sup>37</sup> within the structure, supporting the idea of successful halide-alloying in  $\text{Pb}_3\text{SBr}_{4-x}$  ( $1 \leq x \leq 3$ ). Interestingly, attempts to incorporate more Br into the chalcohalide were unsuccessful. For example, 75% or higher Br synthetic loadings lead to powder XRD patterns that showed crystalline impurities along with the quaternary material.

Energy dispersive spectroscopy (EDS) confirms mixed-halide phases within the successful alloying regime become richer in Br and poorer in I with increasing Br loading, yielding quaternary phases corresponding to  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  (25% Br),  $\text{Pb}_{3.0}\text{SBr}_{1.2}\text{I}_{2.8}$  (33% Br),  $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$  (50% Br), and  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$  (66% Br), respectively (Fig. 2e). High-resolution transmission electron microscopy (HRTEM) of  $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$  shows that (002) and (001) lattice planes stack along the narrow diameter dimension of the rods while (111) lattice planes stack along the longer rod length (see ESI†). These findings are consistent with the rods growing along the [010]  $b$ -direction (rod length) and their diameter being along the [001]  $c$ -direction (rod width). In a few cases, high resolution TEM revealed a few small  $\leq 4$ –5 nm spots— $\text{PbI}_2$  or  $\text{PbS}$ —along the rods. Nonetheless, EM confirms that the quaternary chalcohalides are indeed alloyed with bromine and iodine, in agreement with the XRD results.

### Effect of precursor on phase evolution

As part of our initial efforts aimed at finding suitable syntheses for mixed chalcohalide semiconductors, we screened different sulfur precursors. Under identical conditions to those in the first row of Table 1 (see ESI†), the use of  $\text{Pb}(\text{SCN})_2$  results in quick formation of chalcohalide; only the desired  $\text{Pb}_3\text{SBrI}_3$  quaternary phase is observed after 0.5 h reaction (Fig. 3). In contrast, both thiourea ( $\text{SC}(\text{NH}_2)_2$ ) and elemental sulfur ( $\text{S}_8$ ) react much more slowly, achieving only *ca.* 40–50% quaternary phase purity after 1.5 h reaction. In both cases, unreacted




Fig. 3 Phase evolution of mixed-halide quaternary chalcohalide  $\text{Pb}_3\text{SBrI}_3$  vs. ternary and binary impurities over time as a function of sulfur precursor used (under identical conditions to those in the first row of Table 1; see Experimental in the ESI†).

crystalline  $\text{PbI}_2$  is still present; further, the ternary chalcohalide  $\text{Pb}_5\text{S}_2\text{I}_6$  is also observed. Because the appearance of  $\text{Pb}_3\text{SBrI}_3$  coincides with the disappearance of  $\text{Pb}_5\text{S}_2\text{I}_6$ , we speculate that the formation of the lower order, ternary phase may precede the formation of the desired, mixed-halide, quaternary phase.

We believe the key to understanding these differences is the existence of preformed Pb–S bonds in  $\text{Pb}(\text{SCN})_2$ .<sup>21,23,29</sup> According to the literature, Pb–S bonds ( $\Delta H_{\text{diss}} = 398 \text{ kJ mol}^{-1}$ ) are much stronger than Pb–X bonds (X = Br or I,  $\Delta H_{\text{diss}} = 248\text{--}194 \text{ kJ mol}^{-1}$ ).<sup>38</sup> The stronger, more robust Pb–S bonds thus require a higher activation energy to make (or break) than the Pb–halide bonds (this trend is also evident when the solubility product constants of the corresponding binaries are used as surrogates for a stability measure:  $K_{\text{sp}} = 3.0 \times 10^{-28}$  for  $\text{PbS}$ ,  $9.8 \times 10^{-9}$  for  $\text{PbI}_2$ , and  $6.6 \times 10^{-6}$  for  $\text{PbBr}_2$ ).<sup>38</sup> Because  $\text{Pb}(\text{SCN})_2$  already contains preformed Pb–S bonds, it is able to more quickly react and deliver [Pb–S] building blocks needed for the effective nucleation and growth of multinary chalcohalide nanocrystals. Thiourea and elemental sulfur lack this advantage, and must overcome a larger kinetic barrier to form Pb–S bonds; therefore, these alternative precursors are inferior in kinetics, phase purity, and yield compared to  $\text{Pb}(\text{SCN})_2$ .

### Enhanced stability of chalcohalides

In order to further assess the stability of mixed-halide chalcohalides compared to traditional halide perovskites, we compared them to standard samples of  $\text{CsPbBr}_3$  and  $\text{CsPbI}_3$  as reference materials.<sup>35</sup> After stirring all individual samples in water for 48 h, the chalcohalides demonstrate impressive stability compared to the halide perovskites. Specifically, powder XRD reveals that  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  and  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$  remain largely intact with  $\geq 85\%$  of the original semiconductor remaining (Fig. 4, see ESI†) after water treatment; in contrast,  $\text{CsPbI}_3$  and  $\text{CsPbBr}_3$  easily decompose to  $\text{PbI}_2$  and  $\text{PbBr}_2$ , respectively. Furthermore, the chalcohalides display good stability over time under standard atmospheric conditions. After 3 weeks under air at room temperature ( $21^\circ\text{C}$ ),  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$  remains intact without any evidence of crystalline impurities or decomposition, while  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  only slightly decomposes to  $\text{PbI}_2$  over time. Thus, the more bromine-rich compositions appear to have higher overall stability compared to the more iodine-rich compositions, suggesting that stability increases with the incorporation of the slightly harder, more




Fig. 4 Relative stability of  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  and  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$  over time in water (left) and under air (right).

electronegative bromine ions into the structure. These findings mirror similar trends in the photo- and thermal stability along the  $\text{CsPbX}_3$  series (X = Cl, Br, or I).<sup>39,40</sup> From these analyses, we conclude that mixed-halide chalcohalides possess better ambient and moisture stability compared to halide perovskites, which we anticipate will help stimulate their incorporation into energy conversion devices.

### Surface carboxylates, halides, and hydrogen bonded amines

To determine if any of the ligands used during synthesis coordinates to the chalcohalide particles after purification, we studied their surface chemistry using infrared (IR) spectroscopy (Fig. 5, see ESI†). A combination of  $\nu(\text{N–H})$  ( $3400\text{--}3200 \text{ cm}^{-1}$ )




Fig. 5 IR spectra of mixed-halide chalcohalides compared to oleylamine in the  $3100\text{--}3500 \text{ cm}^{-1}$  region.



and  $\nu(\text{C}-\text{N})$  ( $1100\text{ cm}^{-1}$ ) vibrations indicates the presence of surface-bound amine ligands, which are commonly present on chalcogenide nanocrystals,<sup>41,42</sup> as well as halides (see below). Interestingly, the  $\nu(\text{N}-\text{H})$  stretch at  $3330\text{ cm}^{-1}$  in  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  gradually weakens as additional Br is incorporated into the lattice. This is accompanied by the appearance of a new  $\nu(\text{N}-\text{H})$  stretch at  $\sim 3200\text{ cm}^{-1}$ , which gradually increases with Br incorporation and becomes the dominant peak in the most bromine-rich composition,  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$ .

Free carboxylic acid fails to account for any of these peaks, as the characteristic  $\text{C}=\text{O}$  band at  $\sim 1700\text{ cm}^{-1}$  indicative of a protonated carboxylate ( $-\text{COOH}$ ) is absent from all samples. Rather, we hypothesize that the two  $\nu(\text{N}-\text{H})$  peaks correspond to two distinct surface-bound primary amines, each of which is hydrogen bonded to a surface-bound halide. This can be primarily iodide as in  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$ , or bromide as in  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$ , as shown at the top of Fig. 5. Such red-shift (to lower energy) of a hydrogen bonded amine  $(\text{RHN}-\text{H})\cdots\text{X}$  when X goes from I ( $3330\text{ cm}^{-1}$ ) to the more electronegative Br ( $3200\text{ cm}^{-1}$ ) has ample precedent in the literature, for example in methylammonium halides as well as in multiple organometallic compounds.<sup>43–47</sup> In addition to halides and hydrogen-bonded amine ligands, we also observe vibrations between  $1400\text{--}1600\text{ cm}^{-1}$  that correspond to  $\nu_{\text{as}}(\text{COO}^-)$  and  $\nu_{\text{s}}(\text{COO}^-)$ . The small separation between these two bands of less than  $100\text{ cm}^{-1}$  indicates that chelating ( $\eta^2$ ) carboxylate (oleate) ligands are also bound to the particle surface.<sup>48,49</sup>

### Ensemble and single particle photoluminescence

Diffuse reflectance demonstrates that the chalcohalides absorb strongly within the visible region, consistent with their bright yellow color (Fig. 6). Indirect Tauc plots<sup>50</sup>—assuming the mixed-halides to be indirect semiconductors based on the electronic structure of  $\text{P}2_1/\text{m}$   $\text{Pb}_3\text{SBrI}_3$ —show that the band gaps gradually widen as more Br is incorporated into the structure. Specifically, the band gap changes from  $2.22\text{ eV}$  ( $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$ ) to  $2.26\text{ eV}$  ( $\text{Pb}_{3.0}\text{SBr}_{1.2}\text{I}_{2.8}$ ),  $2.29\text{ eV}$  ( $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$ ), and  $2.33\text{ eV}$  ( $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$ ), respectively (Table 1). These results are also consistent with the increased band gap energy observed in mixed-halide perovskites (MHPs) with the incorporation of more electronegative—and smaller—halide ions.<sup>34,35,51</sup>




Fig. 6 (a) Tauc plots and (b) photoluminescence spectra of  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  (red),  $\text{Pb}_{3.0}\text{SBr}_{1.2}\text{I}_{2.8}$  (orange),  $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$  (yellow), and  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$  (green).

Photoluminescence (PL) measurements reveal that the mixed-halide chalcohalides are emissive in the visible region, with PL emission maxima ( $\text{PL}_{\text{max}}$ ) between  $540$  and  $570\text{ nm}$  (Fig. 6). Furthermore,  $\text{PL}_{\text{max}}$  values gradually blue-shift with increasing Br-loading and content, in close agreement with the respective band gap energies. Critically, in addition to solution-phase (ensemble) PL measurements, we also successfully measured PL of single mixed-halide chalcohalide particles using fluorescence microscopy. Steady shape-correlated PL emission lacking blinking or OFF periods is observed over time under continuous photoexcitation (see ESI†).<sup>23</sup> This finding strongly suggests that the PL originates from the rods themselves rather than from lower order impurities or unreacted precursor(s).

### $^{207}\text{Pb}$ ssNMR spectroscopy

To probe the chemical speciation of the three mixed-halide chalcohalides, we resorted to solid-state  $^{207}\text{Pb}$  NMR spectroscopy (Fig. 7).<sup>34,52–54</sup> Our data show that the NMR signals generally shift to more negative chemical shifts with the incorporation of more electronegative Br<sup>–</sup> ions into the structure, which is consistent with what is observed in binary lead halides,<sup>54,55</sup> as well as in mixed-halide perovskites (MHPs).<sup>56</sup> Specifically, three observable  $^{207}\text{Pb}$  NMR signals for  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$  resonate at *ca.*  $701.6$ ,  $-7.9$ , and  $-531.7\text{ ppm}$  respectively, with an integral ratio of  $\sim 1:6.5:2.6$  (note: the  $^{207}\text{Pb}$  NMR spectra are not quantitative because we cannot measure the  $^{207}\text{Pb}$  longitudinal ( $T_1$ ) and transverse relaxation time constants ( $T_2'$ ) due to low sensitivity). We assign the three distinct signals to the fully occupied sites Pb(1), Pb(2), and Pb(3) (see ESI†). While one could expect other compositions to also show three peaks based on the Pb environments in the chalcohalide crystal structure, the specific chemical shifts of some of these environments are closely positioned, appearing as a single peak. We are able to resolve two distinct Pb chemical shifts in the more bromine-rich compositions. These broadened signals appear at *ca.*  $-302.0$  and  $-639.6\text{ ppm}$  with a  $1:2.5$  integral ratio in  $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$  and at  $-3.02$  and  $-691.1\text{ ppm}$  with a  $1:3.7$  integral ratio in  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$ . We conclude that the chalcohalide samples are free of any  $\text{PbBr}_2$  impurity because of the absence of a peak at *ca.*  $-980\text{ ppm}$ .<sup>55,57</sup> Further, while it is difficult to discern the presence of  $\text{PbI}_2$  based on ssNMR chemical shifts alone,<sup>58</sup> the XRD patterns of all of the chalcohalides are inconsistent with the presence of any such crystalline binary impurities.

### Atom coloring and electronic calculations

To better understand our experimental findings, we evaluated the crystal structure and electronic properties of the different mixed-halide compositions using DFT calculations. After first generating isocompositional coloring models<sup>59,60</sup> to represent plausible atomic ordering patterns for  $\text{Pb}_3\text{SBrI}_3$ ,  $\text{Pb}_3\text{SBr}_2\text{I}_2$ , and  $\text{Pb}_3\text{SBr}_3\text{I}$ , we fully relaxed their structures using the Vienna *Ab initio* Simulation Package (VASP).<sup>61</sup> We find that the lowest energy structures for the three different mixed-halides all adopt similar atomic coloring patterns. Specifically, the smaller




Fig. 7  $^{207}\text{Pb}$  spin echo ssNMR spectra of  $\text{Pb}_{2.9}\text{SBr}_{1.1}\text{I}_{3.0}$ ,  $\text{Pb}_{3.0}\text{SBr}_{1.2}\text{I}_{2.8}$ ,  $\text{Pb}_{2.8}\text{SBr}_{1.8}\text{I}_{1.9}$ , and  $\text{Pb}_{3.0}\text{SBr}_{2.6}\text{I}_{1.5}$ .

bromine atoms are localized on the  $\text{Pb}(3)$  site<sup>25</sup> toward the center of the unit cell in  $\text{Pb}_3\text{SBrI}_3$  and  $\text{Pb}_3\text{SBr}_2\text{I}_2$ , which then branch outward onto the  $\text{Pb}(2)$  site in  $\text{Pb}_3\text{SBr}_3\text{I}$  (Fig. 8). Interestingly, the lowest energy structure for  $\text{Pb}_3\text{SBrI}_3$  corresponds to the  $P2_1/m$  structure previously determined from single crystal data.<sup>25</sup> Upon closer inspection of the relaxed structures, we observe a steady reduction of the unit cell volume from  $\text{Pb}_3\text{SBrI}_3$  to  $\text{Pb}_3\text{SBr}_2\text{I}_2$  and  $\text{Pb}_3\text{SBr}_3\text{I}$  (Fig. 8). Even though the calculated volumes are overestimated by  $\sim 9\text{--}11\%$  compared to volumes extracted from the refined XRD patterns (see ESI†), the overall trend is fully consistent with the increasing bromine incorporation into the chalcohalide structure.

A comparison of density of states (DOS) curves shows that the band gap ( $E_g$ ) values of the chalcohalides progressively widen from 1.92 eV in  $\text{Pb}_3\text{SBrI}_3$  to 1.98 eV and 2.06 eV in  $\text{Pb}_3\text{SBr}_2\text{I}_2$  and  $\text{Pb}_3\text{SBr}_3\text{I}$ , respectively, which agrees well with the experimentally determined values (Fig. 8, see ESI†). The




Fig. 8 Atomic coloring patterns of the lowest energy unit cells of  $\text{Pb}_3\text{SBrI}_3$ ,  $\text{Pb}_3\text{SBr}_2\text{I}_2$ , and  $\text{Pb}_3\text{SBr}_3\text{I}$ . Comparison of the calculated and experimental unit cell volume and band gaps ( $E_g$ ) of these mixed-halide chalcohalides.

calculated band gaps for the three lowest energy structures underestimate their respective experimental values by *ca.* 11–13%, well within an acceptable range of underestimation often seen using VASP.<sup>21,62</sup> Furthermore, analysis of the partial DOS reveals that the relative Br-p and I-p orbital contributions closely correlate with the relative halide ratio expected in each quaternary chalcohalide. In summary, the results of the electronic structure calculations closely support our experimentally observed trend of band gap widening with increased bromine incorporation into the mixed-halide chalcohalides.

## Conclusions

In conclusion, we have demonstrated an effective strategy for synthesizing quaternary chalcohalides with mixed-halide compositions using a solution-phase approach. Electron microscopy reveals that the  $\text{Pb}_3\text{SBr}_x\text{I}_{4-x}$  ( $1 \leq x \leq 3$ ) semiconductors exhibit highly anisotropic growth in the form of rods and needles with high aspect ratios, and their structural features are validated using a combination of XRD and  $^{207}\text{Pb}$  ssNMR. Not only do these materials exhibit indirect band gaps that widen with increased Br incorporation, but they also show promising photoluminescence between 2.2–2.3 eV in solution as an ensemble as well as at the single particle level. These materials also demonstrate impressive stability upon exposure to moisture, showing minimal or no degradation when compared to traditional lead halide perovskites. Lastly, relative energy and DOS calculations showcase atomic coloring patterns and electronic structures that agree well with our experimental findings. Overall, this work provides fundamental materials chemistry knowledge that can be applied toward halide-alloying many other complex chalcohalide compositions, which remains a critical goal for tuning the optical properties of next generation semiconductors and devices.

## Data availability

All necessary information is included in the ESI.†

## Author contributions

ANR designed the experiments, synthesized, and characterized all materials, performed the electronic structure calculations, and wrote the manuscript. YC and AS performed ssNMR measurements and analyses. JOA performed single particle microscopy experiments. EG performed transmission electron microscopy. All authors contributed to the characterization, data analysis, and discussion. ANR and JV conceived the project, and JV, AJR, and EAS guided and supervised the work. All authors have given approval to the final version of the manuscript.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was supported by the US Department of Energy, Office of Science, Basic Energy Sciences, Materials Science and Engineering Division. The Ames National Laboratory is operated for the US Department of Energy by Iowa State University under contract DE-AC02-07CH11358.

## Notes and references

- 1 J. Ye, M. M. Byranvand, C. O. Martínez, R. L. Z. Hoye, M. Saliba and L. Polavarapu, *Angew. Chem.*, 2021, **133**, 21804–21828.
- 2 C. M. Sutter-Fella, Y. Li, M. Amani, J. W. Ager, F. M. Toma, E. Yablonovitch, I. D. Sharp and A. Javey, *Nano Lett.*, 2016, **16**, 800–806.
- 3 C. Bi, S. Wang, W. Wen, J. Yuan, G. Cao and J. Tian, *J. Phys. Chem. C*, 2018, **122**, 5151–5160.
- 4 H. Huang, M. I. Bodnarchuk, S. V. Kershaw, M. V. Kovalenko and A. L. Rogach, *ACS Energy Lett.*, 2017, **2**, 2071–2083.
- 5 P. V. Kamat and M. Kuno, *Acc. Chem. Res.*, 2021, **54**, 520–531.
- 6 A. J. Barker, A. Sadhanala, F. Deschler, M. Gandini, S. P. Senanayak, P. M. Pearce, E. Mosconi, A. J. Pearson, Y. Wu, A. R. S. Kandada, T. Leijtens, F. De Angelis, S. E. Dutton, A. Petrozza and R. H. Friend, *ACS Energy Lett.*, 2017, **2**, 1416–1424.
- 7 Z. Ni, H. Jiao, C. Fei, H. Gu, S. Xu, Z. Yu, G. Yang, Y. Deng, Q. Jiang, Y. Liu, Y. Yan and J. Huang, *Nat. Energy*, 2022, **7**, 65–73.
- 8 K. L. Wang, Y. H. Zhou, Y. H. Lou and Z. K. Wang, *Chem. Sci.*, 2021, **12**, 11936–11954.
- 9 U. V. Ghorpade, M. P. Suryawanshi, M. A. Green, T. Wu, X. Hao and K. M. Ryan, *Chem. Rev.*, 2023, **123**, 327–378.
- 10 F. Palazon, *Sol. RRL*, 2022, **6**, 21008291–21008299.
- 11 D. W. Davies, K. T. Butler, J. M. Skelton, C. Xie, A. R. Oganov and A. Walsh, *Chem. Sci.*, 2018, **9**, 1022–1030.
- 12 Y. T. Huang, S. R. Kavanagh, D. O. Scanlon, A. Walsh and R. L. Z. Hoye, *Nanotechnology*, 2021, **32**, 1320041–13200460.
- 13 A. M. Ganose, C. N. Savory and D. O. Scanlon, *Chem. Commun.*, 2017, **53**, 20–44.
- 14 R. Nie, B. Kim, S. T. Hong and S. I. Seok, *ACS Energy Lett.*, 2018, **3**, 2376–2382.
- 15 C. Yang, Z. Wang, G. He, H. Zhang and C. Liao, *ACS Appl. Nano Mater.*, 2022, **5**, 16033–16038.
- 16 P. Govindaraj and K. J. Venugopal, *J. Alloys Compd.*, 2022, **929**, 1673471–16734711.
- 17 J. Mark, W. Zhang, K. Maeda, T. Yamamoto, H. Kageyama and T. Mori, *J. Mater. Chem. A*, 2023, **11**, 10213–10221.
- 18 M. Y. Ran, S. H. Zhou, W. Wei, B. J. Song, Y. F. Shi, X. T. Wu, H. Lin and Q. L. Zhu, *Inorg. Chem.*, 2021, **60**, 3431–3438.
- 19 X. H. Li, Z. H. Shi, M. Yang, W. Liu and S. P. Guo, *Angew. Chem., Int. Ed.*, 2022, **61**, e2021158711–e2021158716.
- 20 J. Li, S. S. Han and S. P. Guo, *Eur. J. Inorg. Chem.*, 2022, e2022004191–e20220041911.
- 21 S. Toso, Q. A. Akkerman, B. Martín-García, M. Prato, J. Zito, I. Infante, Z. Dang, A. Moliterni, C. Giannini, E. Bladt, I. Lobato, J. Ramade, S. Bals, J. Buha, D. Spirito, E. Mugnaioli, M. Gemmi and L. Manna, *J. Am. Chem. Soc.*, 2020, **142**, 10198–10211.
- 22 M. Imran, L. Peng, A. Pianetti, V. Pinchetti, J. Ramade, J. Zito, F. Di Stasio, J. Buha, S. Toso, J. Song, I. Infante, S. Bals, S. Brovelli and L. Manna, *J. Am. Chem. Soc.*, 2021, **143**, 1435–1446.
- 23 A. N. Roth, J. Opare-Addo, E. Gi, S. Mena, G. Guirado, R. D. Schaller, E. A. Smith and J. Vela, *Chem. Mater.*, 2023, **35**, 2165–2172.
- 24 L. Bindia, A. Garavellib, D. Pintob, G. Pratesia and F. Vurro, *J. Solid State Chem.*, 2008, **181**, 306–312.
- 25 M. Yan, R. L. Tang, W. Zhou, W. Liu and S. P. Guo, *Dalton Trans.*, 2022, **51**, 12921–12927.
- 26 N. V. Pervukhina, S. A. Magarill, D. Y. Naumov, S. V. Borisov, V. I. Vasil'yev and B. G. Nenashev, *J. Struct. Chem.*, 2006, **47**, 312–317.
- 27 L. T. Jiang, M. Z. Li, X. M. Jiang, B. W. Liu and G. C. Guo, *Dalton Trans.*, 2022, **51**, 6638–6645.
- 28 Q. Jing, Z. Yang, S. Pan and D. Xue, *Phys. Chem. Chem. Phys.*, 2015, **17**, 21968–21973.
- 29 Q. A. Akkerman, B. Martín-García, J. Buha, G. Almeida, S. Toso, S. Marras, F. Bonaccorso, U. Petralanda, I. Infante and L. Manna, *Chem. Mater.*, 2019, **31**, 8145–8153.
- 30 B. Ptaszyński, E. Skiba and J. Krystek, *J. Therm. Anal. Calorim.*, 2001, **65**, 231–239.
- 31 S. M. Islam, C. D. Malliakas, D. Sarma, D. C. Maloney, C. C. Stoumpos, O. Y. Kontsevoi, A. J. Freeman and M. G. Kanatzidis, *Chem. Mater.*, 2016, **28**, 7332–7343.
- 32 H. Wang, G. Chen, J. Xu, Y. Xu and Q. Yang, *Cryst. Growth Des.*, 2018, **18**, 1987–1994.
- 33 T. P. A. Ruberu, H. R. Albright, B. Callis, B. Ward, J. Cisneros, H. J. Fan and J. Vela, *ACS Nano*, 2012, **6**, 5348–5359.
- 34 B. A. Rosales, L. Men, S. D. Cady, M. P. Hanrahan, A. J. Rossini and J. Vela, *Chem. Mater.*, 2016, **28**, 6848–6859.



35 L. Protesescu, S. Yakunin, M. I. Bodnarchuk, F. Krieg, R. Caputo, C. H. Hendon, R. X. Yang, A. Walsh and M. V. Kovalenko, *Nano Lett.*, 2015, **15**, 3692–3696.

36 A. Sadhanala, S. Ahmad, B. Zhao, N. Giesbrecht, P. M. Pearce, F. Deschler, R. L. Z. Hoye, K. C. Gödel, T. Bein, P. Docampo, S. E. Dutton, M. F. L. De Volder and R. H. Friend, *Nano Lett.*, 2015, **15**, 6095–6101.

37 R. D. Shannon, *Acta Crystallogr.*, 1976, **A32**, 751–767.

38 W. M. Haynes, D. R. Lide and T. J. Bruno, *CRC Handbook of Chemistry and Physics*, CRC Press, Boca Raton, FL, 103rd edn, 2022.

39 B. W. Boote, H. P. Andaraarachchi, B. A. Rosales, R. Blome-Fernández, F. Zhu, M. D. Reichert, K. Santra, J. Li, J. W. Petrich, J. Vela and E. A. Smith, *ChemPhysChem*, 2019, **20**, 2647–2656.

40 M. Liao, B. Shan and M. Li, *J. Phys. Chem. Lett.*, 2019, **10**, 1217–1225.

41 A. N. Roth, Y. Chen, M. A. S. Adamson, E. Gi, M. Wagner, A. J. Rossini and J. Vela, *ACS Nano*, 2022, **16**, 12024–12035.

42 A. M. Medina-Gonzalez, B. A. Rosales, U. H. Hamdeh, M. G. Panthani and J. Vela, *Chem. Mater.*, 2020, **32**, 6085–6096.

43 E. W. Dahl and N. K. Szymczak, *Angew. Chem.*, 2016, **128**, 3153–3157.

44 A. Cabana and C. Sandordy, *Spectrochim. Acta*, 1962, **18**, 843–861.

45 F. Cariati, G. Ciani, L. Menabue, G. C. Pellacani, G. Rassu and A. Sironi, *Inorg. Chem.*, 1983, **22**, 1897–1902.

46 T. Glaser, C. Müller, M. Sendner, C. Krekeler, O. E. Semonin, T. D. Hull, O. Yaffe, J. S. Owen, W. Kowalsky, A. Pucci and R. Lovrincic, *J. Phys. Chem. Lett.*, 2015, **6**, 2913–2918.

47 M. D. Fryzuk, P. A. MacNeil and S. J. Rettig, *J. Am. Chem. Soc.*, 1987, **109**, 2803–2812.

48 V. Zelenak, Z. Vargova and K. Gyoryova, *Spectrochim. Acta, Part A*, 2007, **66**, 262–272.

49 J. Zhang, H. Zhang, W. Cao, Z. Pang, J. Li, Y. Shu, C. Zhu, X. Kong, L. Wang and X. Peng, *J. Am. Chem. Soc.*, 2019, **141**, 15675–15683.

50 B. D. Viezbicke, S. Patel, B. E. Davis and D. P. Birnie, *Phys. Status Solidi B*, 2015, **252**, 1700–1710.

51 A. Karmakar, A. Bhattacharya, D. Sarkar, G. M. Bernard, A. Mar and V. K. Michaelis, *Chem. Sci.*, 2021, **12**, 3253–3263.

52 J. P. Yesinowski, *Top. Curr. Chem.*, 2011, **306**, 229–312.

53 M. P. Hanrahan, L. Men, B. A. Rosales, J. Vela and A. J. Rossini, *Chem. Mater.*, 2018, **30**, 7005–7015.

54 R. E. Taylor, P. A. Beckmann, S. Bai and C. Dybowski, *J. Phys. Chem. C*, 2014, **118**, 9143–9153.

55 A. Glatfelter, C. Dybowski, D. D. Kragten, S. Bai, D. L. Perry and J. Lockard, *Spectrochim. Acta, Part A*, 2007, **66**, 1361–1363.

56 K. Datta, A. Caiazzo, M. A. Hope, J. Li, A. Mishra, M. Cordova, Z. Chen, L. Emsley, M. M. Wienk and R. A. J. Janssen, *ACS Energy Lett.*, 2023, **8**, 1662–1670.

57 Y. S. Kye, S. Connolly, B. Herreros and G. S. Harbison, *Main Group Met. Chem.*, 1999, **22**, 373–383.

58 R. E. Taylor, P. A. Beckmann, S. Bai and C. Dybowski, *J. Phys. Chem. C*, 2014, **118**, 9143–9153.

59 G. J. Miller, *Eur. J. Inorg. Chem.*, 1998, 523–536.

60 J. Pham and G. J. Miller, *Inorg. Chem.*, 2018, **57**, 4039–4049.

61 G. Kresse and J. Furthmüller, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, **54**, 11169–11186.

62 L. Sun, C. Wang, L. Xu, J. Wang, X. Chen and G. Yi, *J. Mater. Chem. C*, 2018, **6**, 7188–7194.

