



Cite this: *Nanoscale Adv.*, 2024, 6, 1790

DOI: 10.1039/d4na90024c

rsc.li/nanoscale-advances

Correction: Mechanistic insights into Ag^+ induced size-growth from $[\text{Au}_6(\text{DPPP})_4]^{2+}$ to $[\text{Au}_7(\text{DPPP})_4]^{2+}$ clusters

Ying Lv,^a Xiaohang Wu,^a Shuping He^a and Haizhu Yu^{*ab}

Correction for 'Mechanistic insights into Ag^+ induced size-growth from $[\text{Au}_6(\text{DPPP})_4]^{2+}$ to $[\text{Au}_7(\text{DPPP})_4]^{2+}$ clusters' by Ying Lv *et al.*, *Nanoscale Adv.*, 2022, 4, 3737–3744, <https://doi.org/10.1039/D2NA00301E>.

The authors regret that Fig. 2 and Fig. 3 in the published paper are identical. The correct Fig. 2 is given here.




Fig. 2 The isosurface of the f^- for $\text{Au}_6\text{AgP}_8-2$, using the width of Gaussian function of 0.01 au and the energy (in kcal mol^{-1}) and structural changes for the doping of second Ag^+ into $\text{Au}_6\text{AgP}_8-2$. The Hirshfeld charge of $\text{Au}^{5/6}$ in starting structure is given in blue and bold.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

^aDepartment of Chemistry, Centre for Atomic Engineering of Advanced Materials, Anhui Province Key Laboratory of Chemistry for Inorganic/Organic Hybrid Functionalized Materials, Key Laboratory of Structure and Functional Regulation of Hybrid Materials of Ministry of Education, Anhui University, Hefei 230601, Anhui, P. R. China. E-mail: yuhaizhu@ahu.edu.cn

^bInstitute of Energy, Hefei Comprehensive National Science Center, Hefei, Anhui, 230031, P. R. China