


 Cite this: *RSC Adv.*, 2024, 14, 18978

Synthesis and properties of anhydrous rare-earth phosphates, monazite and xenotime: a review

 Saehwa Chong,^{id}*^a Brian J. Riley,^{id}*^a Xiaonan Lu,^{id}^a Jincheng Du,^{id}^b Thiruvillamalai Mahadevan^b and Vinay Hegde^c

The synthesis methods, crystal structures, and properties of anhydrous monazite and xenotime (REPO₄) crystalline materials are summarized within this review. For both monazite and xenotime, currently available Inorganic Crystal Structure Database data were used to study the effects of incorporating different RE cations on the unit cell parameters, cell volumes, densities, and bond lengths. Domains of monazite-type and xenotime-type structures and other AXO₄ compounds (A = RE; X = P, As, V) are discussed with respect to cation sizes. Reported chemical and radiation durabilities are summarized. Different synthesis conditions and chemicals used for single crystals and polycrystalline powders, as well as first-principles calculations of the structures and thermophysical properties of these minerals are also provided.

 Received 14th February 2024
 Accepted 26th May 2024

DOI: 10.1039/d4ra01142b

rsc.li/rsc-advances

1 Introduction

Monazite and xenotime compounds are anhydrous rare-earth (RE) phosphates with the chemical formula REPO₄ but with different crystal symmetries. The mineral name “monazite” is derived from “monazein” meaning “to be solitary” in Greek, and the mineral name “xenotime” is derived from the combined words of “xenos” and “time” meaning “foreign” and “honor” in Greek.¹ Naturally occurring monazite and xenotime minerals are often found as accessory minerals along with allanite, sphene, fluorite, and apatite in granitic rocks, pegmatites, carbonatites, and gneisses.^{1,2} The monazite and xenotime minerals found in nature often contain mixed RE elements as well as thorium and/or uranium along with other oxides, and the deposits are found in various countries including Australia, Brazil, Canada, China, India, Italy, Madagascar, Sri Lanka, and the United States.^{1,3–5} For example, the compositions of natural monazites from seven different regions were 35–65 mass% of mixed REs, 24–30 mass% of P₂O₅, 0–16 mass% of UO₂, 4–14 mass% of ThO₂, and 2–7 mass% of other oxides, and among the mixed REs, La, Ce, and Nd were the major components.^{2,3,6} The natural xenotime mineral generally contains mixed heavy REs (*i.e.*, RE = Gd → Lu + Y, Sc) and less actinides compared to monazite (*i.e.*, RE = La → Dy). The compositions of natural xenotime from two regions were 62–65 mass% of mixed RE oxides, 29–36 mass% of P₂O₅, 0.1–1.6 mass% of UO₂, 0.2–0.3 mass% of ThO₂, and 0.1–1.3 mass% of other oxides, and among

the mixed REs, Y, Gd, Dy, and Er were the major components.^{7,8} Rhabdophane minerals are hydrated RE-phosphates with the chemical formula of REPO₄·xH₂O and they are found as accessory minerals in granitic rocks. Rhabdophane minerals generally contains mixed REs with relatively high amounts of Ce and La elements, U and Th actinides, and one water molecule (7–8 mass%) per formula unit.⁹ Studies have shown that the rhabdophane structure can transform to the monoclinic monazite structure through heat treatments.^{10,11}

Both monazite and xenotime compounds have attractive physical and chemical properties over a wide range of applications including nuclear waste forms,^{12–20} light emitting materials (*e.g.*, as scintillators for γ -ray or X-ray detection, as thermophosphors),^{1,21–25} and coating materials.^{26–28} For applications in nuclear waste forms, the REPO₄ compounds have been studied extensively due to high chemical durabilities, resistance to radiation damage, a wide variety of natural analogs, and their potential to incorporate RE, U, and Th elements in the structures.^{12–15,17,29} The flexibility of the RE–O bond distances in REO_x polyhedra, while maintaining the structure, enables the incorporation and substitution of different heavy radioactive cations. This possibility of monazite and xenotime to incorporate many different radionuclides into a single structure makes it an ideal waste form that eliminates the need to determine the radionuclide partition coefficients between phases and concerns for differences in mechanical properties and corrosion mechanisms.¹² Both monazite and xenotime can be synthesized relatively easily (see Section 2 for details), and their chemical durabilities are much higher (up to a factor of 20 in leach rates for certain elements) than borosilicate glass waste forms.¹² Natural monazite was shown to maintain high retention of fission products during erosion,

^aPacific Northwest National Laboratory, Richland, WA 99354, USA. E-mail: saehwa.chong@pnnl.gov; brian.riley@pnnl.gov; Tel: +1-509-375-2469; +1-509-372-4651

^bUniversity of North Texas, Denton, TX 76203, USA

^cCitrine Informatics, Redwood City, CA 94063, USA



which was attributed to its slow dissolution rate.¹³ In addition, both compounds have high thermal stabilities with melting temperatures above 2000 °C.¹²

Monazite compounds can be used as light emitting materials with interesting optical properties.^{21–23} Wang *et al.*²¹ investigated the luminescence behavior of Eu-doped LaPO₄ nanorods and showed the emission spectrum dependency on polarization for electric and magnetic dipole transitions. With high quantum efficiency and a high degree of polarization, the Eu-doped LaPO₄ nanorods can be used as high resolution probes in 3D flow-shear tomography.²¹ Hashimoto *et al.*²² observed that doping a small amount of Th and borate into monazite compounds containing mixed RE cations of La, Ce, and/or Tb improved the light emission intensity and stability of green light, and these phosphors used in fluorescent lamps can minimize the brightness loss at high temperatures. Jeon *et al.*²³ doped La- and Ca-containing monazite compounds with Eu and/or Dy ions, and single-phase white-light emission was observed at near-ultraviolet excitation.

The LaPO₄ monazite has also been explored as a coating material to minimize high-temperature oxidation.^{26–28} Morgan *et al.*²⁷ showed that LaPO₄ and alumina interfaces without impurities were stable and retained the ability to debond after heat treatment at 1600 °C in air but observed the formation of La-containing β-alumina-magnetoplumbite in the presence of alkali metal or divalent elements near the interface. Kuo and Kriven²⁶ showed that three laminates composed of LaPO₄ as one component and Al₂O₃, Y₃Al₅O₁₂, or LaAl₁₁O₁₈ as the other component were thermally stable up to 1600 °C and could be used as high-temperature materials in an oxidizing environment. Boakye *et al.*²⁸ showed that coating the SiC fibers with LaPO₄ did not degrade fiber strength, and a heat treatment at 1200 °C for 1–20 h in argon resulted in the formation of La₂Si₂O₇, while the monazite was stable with SiC when the same heat treatment was done in air.

In this review, synthesis methods, crystal structures, and properties of anhydrous REPO₄ compounds are summarized. Studies on the chemical durability and radiation stability, as well as different models for phase stability of monazite and xenotime are also summarized.

2 Synthesis methods

Different methods, including flux-assisted, solid state, hydrothermal, aqueous, dehydration, and gel-based methods, have been used for the synthesis of monazite and xenotime compounds. Table 1 summarizes the synthesis conditions for REPO₄ compounds.

Feigelson³⁰ synthesized single crystals of LaPO₄, CePO₄, PrPO₄, NdPO₄, SmPO₄, EuPO₄, and GdPO₄ monazite compounds as well as TbPO₄ and YbPO₄ xenotime compounds using Pb₂P₂O₇ flux. The mixture of RE oxides and lead hydrogen phosphate (PbHPO₄) with the mass ratio of 1 : 24 was placed in the Pt crucible and heated to 1300 °C at 300 °C h⁻¹ and dwelled for 12 h at 1300 °C, and PbHPO₄ was converted to lead pyrophosphate (Pb₂P₂O₇) on heating. The mixture was slowly cooled to 975 °C at <4 °C h⁻¹ and then naturally cooled to room

temperature as the authors believed that crystallization did not proceed below 975 °C. The single crystals of monazite compounds were separated from the flux using diluted HNO₃ solution. The monazite crystals had platelike morphologies, and the crystal sizes of LaPO₄, PrPO₄, and NdPO₄ were ~6 mm × ~3 mm × ~0.5 mm (the crystal sizes of other monazites were not reported). Decreasing cooling rate increased the crystal sizes of xenotime compounds. For YbPO₄, a plate crystal with dimensions of 45 mm × 25 mm × 0.25 mm was obtained when cooled at 0.5 °C h⁻¹. The single crystal or polycrystalline compound of TbPO₄ could be prepared using TbO_{2-x} with PbHPO₄ or H₃PO₄ respectively, and similar optical characteristics were observed from each compound. For the flux matrix, Pb₂P₂O₇ was the main phase, but other phosphates including Pb₃P₄O₁₅, Pb₄P₂O₉, and/or Pb₃P₂O₈ were found with loss of phosphorus after formation of REPO₄.

Similar to Feigelson's flux method, Mullica *et al.*^{31,40,45} synthesized the single crystals of LaPO₄, PrPO₄, NdPO₄, SmPO₄, EuPO₄, and GdPO₄ using Pb₂P₂O₇ as a flux. The mixture of RE oxides and PbHPO₄ with the mass ratio of 1 : 17 was placed in a Pt crucible and heated to 1360 °C for 16 h. After heat treatment, the mixture was slowly cooled to 900 °C at 1 °C h⁻¹ and then naturally cooled to room temperature.

Hirsch *et al.*³⁵ used a solid-state method to prepare polycrystalline powders of LaPO₄, PrPO₄, and mixed La_{1-x}Pr_xPO₄ monazite compounds. The appropriate amounts of RE oxides and NH₄H₂PO₄ (ADP) were homogenized, pressed into pellets, placed in alumina crucibles, and heated at 1250 °C for 24 h at ambient atmosphere, and the final products were pure monazites.³⁵ Perrière *et al.*³⁴ used a similar method to synthesize LaPO₄, CePO₄, PrPO₄, NdPO₄, SmPO₄, EuPO₄, and GdPO₄. The mixture of RE oxides and ADP was heated at 1350 °C for 2 h in air twice to make pure monazite powders.³⁴

Khalili *et al.*³⁶ prepared LaPO₄ monazite, Lu₂O₃ xenotime, and Yb₂O₃ xenotime using RE₂O₃ and H₃PO₄. Powder of RE₂O₃ (0.002 mol) was added to round bottomed flask containing 13.7 mL of 14.6 M H₃PO₄ and stirred with magnetic stir for 1–24 h. The solution was diluted by adding 100 mL of water and refluxed at 130 °C for 2 h. The precipitate was filtered and washed with DIW. The sample was dried overnight and then heated to 80 °C for 1 h, and half of sample was heated at 200 °C for up to 48 h for complete dehydration. Sample heated at 80 and 200 °C were compared. The synthesized LaPO₄ monazite was a polycrystalline powder containing some rhabdophane, and the xenotime powders were pure LuPO₄ and YbPO₄ compounds.

Cao *et al.*³² synthesized LaPO₄ and CePO₄ nanorods using LaNO₃, CeNO₃, and H₃PO₄ precursors. Here, 1 M La(NO₃)₃ or 1 M Ce(NO₃)₃ and 0.7 M H₃PO₄ were added to a solution of cetrimonium bromide in cyclohexane and *n*-pentanol. Solutions were mixed for 30 min and transferred to autoclaves. The autoclaves were heated at 140 °C for 12 h and cooled to room temperature. The crystals were washed with ethanol and DIW several times and dried in vacuum at room temperature. The obtained LaPO₄ and CePO₄ nanorods had about 5 μm lengths and 20–60 nm diameters.



Table 1 Summary of monazite and xenotime synthesis. La → Dy* are monazite compounds, and Tb → Lu + Y, Sc are xenotime compounds. For the synthesized compound, S and P denote single crystal and polycrystalline compound. The ratio represents the mass ratio of RE oxide to flux

| RE | Form | Method | Precursors | Flux | Ratio | <i>T</i> (°C) | <i>t_d</i> (h) | <i>T_c</i> (°C) | <i>r_c</i> (°C h ⁻¹) | Ref. |
|-----|------|--------------|--|---|---------------------|---------------|--------------------------|---------------------------|--|------|
| La | S | Flux | La ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | 2 | 30 |
| La | S | Flux | La ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 17 | 1360 | 16 | 900 | 1 | 31 |
| La | S | Hydrothermal | LaCl ₃ ·7H ₂ O, H ₃ PO ₄ | — | — | 140 | 12 | — | — | 32 |
| La | S | Hydrothermal | La(NO ₃) ₃ ·6H ₂ O, NaH ₂ PO ₄ | — | — | 120–200 | — | — | — | 33 |
| La | P | Solid state | La ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| La | P | Solid state | La ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1250 | 24 | — | — | 35 |
| La | P | Aqueous | La ₂ O ₃ , H ₃ PO ₄ | — | — | 80–200 | 1–48 | — | — | 36 |
| La | P | Dehydration | LaPO ₄ ·xH ₂ O | — | — | 500 | 1 | — | — | 10 |
| Ce | S | Flux | CeO ₂ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | 1 | 30 |
| Ce | S | Hydrothermal | Ce(NO ₃) ₃ ·6H ₂ O, H ₃ PO ₄ | — | — | 140 | 12 | — | — | 32 |
| Ce | P | Solid state | CeO ₂ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| Ce | P | Dehydration | CePO ₄ ·xH ₂ O | — | — | 800 | 1 | — | — | 37 |
| Ce | P | Dehydration | CePO ₄ ·xH ₂ O | — | — | 600 | 1 | — | — | 10 |
| Pr | S | Flux | Pr ₆ O ₁₁ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | 2 | 30 |
| Pr | P | Solid state | Pr ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1250 | 24 | — | — | 35 |
| Pr | P | Solid state | Pr ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| Pr | P | Dehydration | PrPO ₄ ·xH ₂ O | — | — | 700 | 1 | — | — | 10 |
| Nd | S | Flux | Nd ₂ O ₃ , KH ₂ PO ₄ | K ₆ P ₄ O ₁₃ | 1 : 4 | 1000 | 24 | 840 | <0.2 | 38 |
| Nd | S | Flux | Nd ₂ O ₃ , Li ₂ CO ₃ , MoO ₃ | Li ₂ Mo ₂ O ₇ | 1 : 4 | 1020 | 720 | — | <0.2 | 39 |
| Nd | S | Flux | Nd ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | 2 | 30 |
| Nd | S | Flux | Nd ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 17 | 1360 | 16 | 900 | 1 | 40 |
| Nd | P | Solid state | Nd ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| Nd | P | Dehydration | NdPO ₄ ·xH ₂ O | — | — | 700 | 1 | — | — | 10 |
| Sm | S | Flux | Sm ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | <4 | 30 |
| Sm | P | Solid state | Sm ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| Sm | P | Dehydration | SmPO ₄ ·xH ₂ O | — | — | 700 | 1 | — | — | 10 |
| Eu | S | Flux | Eu ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | <4 | 30 |
| Eu | P | Solid state | Eu ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| Gd | S | Flux | Gd ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | <4 | 30 |
| Gd | P | Solid state | Gd ₂ O ₃ , NH ₄ H ₂ PO ₄ | — | — | 1350 | 2 | — | — | 34 |
| Gd | P | Dehydration | GdPO ₄ ·xH ₂ O | — | — | 800 | 1 | — | — | 10 |
| Tb* | P | Aqueous | Tb(NO ₃) ₃ ·nH ₂ O, H ₃ PO ₄ | — | — | 950 | 8 | — | — | 41 |
| Dy* | P | Aqueous | Dy(NO ₃) ₃ ·nH ₂ O, H ₃ PO ₄ | — | — | 730 | 4 | — | — | 41 |
| Tb | S | Flux | Gd ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | <4 | 30 |
| Tb | P, S | Aqueous-flux | Tb(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | Na ₂ CO ₃ -MoO ₃ | 1 : 50 ^a | 1350 | 15 | 870 | 3 | 42 |
| Dy | P | Dehydration | DyPO ₄ ·xH ₂ O | — | — | 1050 | 1 | — | — | 10 |
| Dy | P, S | Aqueous-flux | Dy(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | NaHCO ₃ -MoO ₃ | 1 : 50 ^a | 1375 | 144–168 | 870 | 3 | 43 |
| Ho | P, S | Aqueous-flux | Ho(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | Na ₂ CO ₃ -MoO ₃ | 1 : 50 ^a | 1350 | 15 | 870 | 3 | 42 |
| Er | P, S | Aqueous-flux | Er(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | NaHCO ₃ -MoO ₃ | 1 : 50 ^a | 1375 | 144–168 | 870 | 3 | 43 |
| Tm | P, S | Aqueous-flux | Tm(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | Na ₂ CO ₃ -MoO ₃ | 1 : 50 ^a | 1350 | 15 | 870 | 3 | 42 |
| Yb | S | Flux | Yb ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1300 | 12 | 975 | 0.5 | 30 |
| Lu | P, S | Aqueous-flux | Lu(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | Na ₂ CO ₃ -MoO ₃ | 1 : 50 ^a | 1350 | 15 | 870 | 3 | 42 |
| Y | P, S | Aqueous-flux | Y(NO ₃) ₃ ·xH ₂ O, NH ₄ H ₂ PO ₄ | NaHCO ₃ -MoO ₃ | 1 : 50 ^a | 1375 | 144–168 | 870 | 3 | 43 |
| Y | S | Flux | Y ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1357 | Several days | 897 | 1 | 44 |
| Sc | S | Flux | Sc ₂ O ₃ , PbHPO ₄ | Pb ₂ P ₂ O ₇ | 1 : 24 | 1357 | Several days | 897 | 1 | 44 |

^a The molar ratio of REPO₄ to flux. The *t_d* is the dwell time, “*T_c*” represents the temperature that the mixture was slowly cooled to grow single crystals, and *r_c* is the cooling rate.

Li and Ma³³ synthesized LaPO₄:Eu crystals using La(NO₃)₃·6H₂O and Eu(NO₃)₃·5H₂O with a molar ratio of 1 : 0.05 dissolved in DIW, and addition 5 mL of 1 M NaH₂PO₄ aqueous solution was done while stirring. Here, HNO₃ or NaOH were added to adjust to a specific pH. The solution was put into an autoclave and heated at different temperature (120–180 °C). The resulting product was centrifuged and washed with DIW and dried at 60 °C for 12 h.

Wang *et al.*³⁹ synthesized a single crystal of NdPO₄ using Li₂Mo₂O₇ as a flux. The Li₂CO₃ and MoO₃ powders were used to prepare the Li₂Mo₂O₇ flux. The mixture of Nd₂O₃ and Li₂Mo₂O₇

with the mass ratio of 1 : 4 was placed in the Pt crucible and heated to 1020 °C for 24 h. A seed crystal was immersed in the solution and rotated at 30 rpm, and the single crystal was grown in the mixture cooling at 0.05–0.2 °C h⁻¹ for ~30 d. The resulting single crystal had the size of several millimeters.

Poitrasson *et al.*⁴⁶ synthesized polycrystalline NdPO₄ and GdPO₄ compounds using a combined method of gelation and flux-assisted growth. The NdPO₄ gel was prepared by dissolving Nd(NO₃)₃ and adding (NH₄)₂HPO₄ solution. Precipitation of NdPO₄ occurred while drying for several days, and the final NdPO₄ product was obtained after briefly heating above 600 °C



to remove NH_3 and nitrates. The recovered NdPO_4 powder was mixed with Li_2MoO_4 and MoO_3 in the mass ratio of $\sim 2:1:1$, respectively, and placed in a Pt crucible. The crucible was heated at 800°C for 24 h, and polycrystalline NdPO_4 powder was recovered by dissolving the flux in boiling water. A similar method was used for GdPO_4 synthesis.

Different studies showed that monazite compounds can be easily synthesized by heat-treating rhabdophane. Jonasson and Vance¹⁰ showed that La-, Ce-, Pr-, Nd-, Sm-, and Gd-rhabdophane compounds converted to corresponding monazite compounds in $500\text{--}900^\circ\text{C}$ range after dehydration in $100\text{--}400^\circ\text{C}$ range. They observed that Dy rhabdophane compound converted to mixed phases of monazite and xenotime compounds at 950°C and complete xenotime compound at 1050°C .¹⁰ Adelstein *et al.*³⁷ prepared CePO_4 monazite by heating Ce rhabdophane at 800°C for 1 h. However, a different study by Mesbah *et al.*⁴⁷ showed that heating Nd, Eu, Gd, and Dy rhabdophane compounds at $200\text{--}500^\circ\text{C}$ converted them to NdPO_4 , EuPO_4 , GdPO_4 , and DyPO_4 with tetragonal $P3_121$ space group, which is different symmetry from monazite or xenotime.

Heuser *et al.*⁴¹ synthesized TbPO_4 and DyPO_4 with monazite structures using rhabdophane of $\text{TbPO}_4 \cdot n\text{H}_2\text{O}$ and $\text{DyPO}_4 \cdot n\text{H}_2\text{O}$. The rhabdophane compounds were made using a similar precipitation method by Boakye *et al.*⁴⁸ Solutions containing $\text{RE}(\text{NO}_3)_3 \cdot n\text{H}_2\text{O}$ and H_3PO_4 were mixed while controlling the RE:P ratio and pH, and the precipitates were collected. The rhabdophane powders were heated at 200°C for 2 h. Subsequently, Tb and Dy rhabdophane powders were heated at 950°C for 8 h and 730°C for 4 h, respectively, to convert to corresponding monazite compounds. The heating temperature and time were selected to avoid possible formation of xenotime structures.

3 Crystal structures

Monazite crystallizes in the monoclinic $P2_1/n$ space group (REs are coordinated by nine oxygens), and xenotime crystallizes in the tetragonal $I4_1/amd$ space group (REs are coordinated by eight oxygens) and is isostructural to zircon (ZrSiO_4). Monazite compounds of lanthanides contain the lanthanide elements with larger ionic radii (r_i) including La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, and Dy whereas xenotime compounds contain the heavy lanthanide elements with smaller r_i including Gd, Tb, Dy, Ho, Er, Tm, and Lu along with Sc and Y. The structural parameters of monazite and xenotime compounds at ambient conditions ($293\text{--}300\text{ K}$ and 1 atm) reported in the Inorganic Crystal Structure Database (ICSD) are provided in Tables 2 and 3, respectively. It should be noted that, for the REPO_4 compounds with RE elements, the mid-range of lanthanides (*i.e.*, Gd, Tb, Dy) can crystallize in both monazite and xenotime structures. Formation of monazite or xenotime for Gd, Tb, and Dy elements can be controlled by synthesis conditions (see Section 2 for details). Fig. 1 shows the relationship of monazite and xenotime structures with respect to the crystal radii (r_c) from Shannon.⁴⁹ The unit cell parameters of the PmPO_4 compound have been reported,⁵⁰ but the overall structure data has not been reported in the ICSD. As for other RE elements, namely Y and Sc, YPO_4 and

ScPO_4 (pretulite) have the xenotime structure. Both monazite and xenotime structures are commonly found in non-phosphate compounds including RE vanadates (REVO_4) and RE arsenates (REAsO_4).¹ Details of the monazite and xenotime structures are discussed in the following sections.

The nine oxygen atoms coordinating the REs in monazite include five oxygen atoms forming a nearly equatorial pentagon whereas the other four oxygen atoms form a tetrahedron interpenetrating the pentagon (Fig. 2), and this coordination of REO_9 was described as a pentagonal interpenetrating tetrahedral polyhedron (PITP).^{31,45} The interpenetrating tetrahedron of REO_9 shares the edges with two adjacent PO_4 tetrahedra (Fig. 2a), resulting in a chain-like structure along the c axis (Fig. 2b). Fig. 2c shows the atomic arrangement of RE and P atoms projected down $[001]$.

Distortion of REO_9 polyhedra and PO_4 tetrahedra in the monazite structure was reported in the literature.^{1,59} The monazite structure has four oxygen atom positions (*i.e.*, O1, O2, O3, and O4), and the O2 atom is shared by three RE cations and a P cation whereas O1, O3, and O4 atoms are shared by only two RE cations and a P cation. This bonding results in REO_9 polyhedra with one longer RE–O2 distance compared to other eight RE–O distances. For example, the difference in RE–O bonding results in one longer $\sim 2.8\text{ \AA}$ RE–O2 bond length compared to $\sim 2.5\text{--}2.6\text{ \AA}$ of other eight RE–O bond lengths in CePO_4 .⁵⁹ This RE–O coordination also affected the distortion of PO_4 tetrahedra with different P–O bond lengths and O–P–O bond angles within a given PO_4 tetrahedron.⁵⁹ The distortion index⁵⁴ value (D) can be used to show the average deviation of RE–O bond distances from their means within the REO_9 polyhedra of monazite, and this is shown in eqn (1) where l_i is the distance from the central atom (*i.e.*, RE) to the i th coordinating atom, and l_{av} is the average bond length. The distortion indices of REO_9 in monazite are in the range of $0.03\text{--}0.11$ and were relatively higher than the distortion indices ($0.01\text{--}0.06$) of REO_8 in the xenotime structures. The larger D value of REO_x in monazite compared to xenotime was largely due to the one long RE–O2 bond. The distorted REO_9 polyhedron in monazite has a set of nine different RE–O bond lengths, and this coordination is correlated to its capability to incorporate various cations and polyoxoanions in the structure.¹⁴ Generally, this type of irregular coordination of metal ions does not induce severe symmetry, charge, or size constraints on the incorporated cation.^{15,59}

$$D = \frac{1}{n} \sum_{i=1}^n \frac{|l_i - l_{\text{av}}|}{l_{\text{av}}} \quad (1)$$

As mentioned earlier, the monazite structures incorporate light RE cations, including La \rightarrow Dy. With larger RE cations (*i.e.*, larger r_c values)⁴⁹ in the crystal structure, the unit cell parameters (*i.e.*, a , b , c) and volumes (V) increase linearly whereas the densities (ρ) decrease nonlinearly (Fig. 3). Fig. 3 was drawn using the average values of a , b , c , V , and ρ of monazite compounds at atmospheric conditions reported in ICSD for each given RE. The crystal structure data of PmPO_4 was not



Table 2 Structural parameters of REPO₄ monazite compounds at ambient conditions (293–300 K and 1 atm) including unit cell parameters (*a*, *b*, *c*), β angle, cell volume (*V*), cell density (ρ), bond distances (*i.e.*, RE–O, P–O), and the entry number for the Inorganic Crystal Structure Database (ICSD). The space group of listed compounds is *P*₂₁/*n* (SG# 14). Volume and density are calculated values, and RE–O and P–O are the average distances

| RE | <i>a</i> (Å) | <i>b</i> (Å) | <i>c</i> (Å) | β (°) | <i>V</i> (Å ³) | ρ (g cm ⁻³) | RE–O (Å) | P–O (Å) | ICSD | Ref. |
|----|--------------|--------------|--------------|-------------|----------------------------|------------------------------|----------|---------|--------|------|
| La | 6.7825 | 6.9896 | 6.6218 | 102.9602 | 305.92 | 5.08 | 2.5845 | 1.5493 | 46788 | 36 |
| La | 6.8313 | 7.0705 | 6.5034 | 103.27 | 305.73 | 5.08 | 2.5787 | 1.5384 | 79747 | 51 |
| La | 6.8413 | 7.078 | 6.5153 | 103.322 | 307 | 5.06 | 2.5855 | 1.6602 | 92155 | 52 |
| La | 6.825 | 7.057 | 6.482 | 103.21 | 303.94 | 5.11 | 2.5739 | 1.5350 | 201479 | 31 |
| La | 6.84133 | 7.07590 | 6.51233 | 103.28918 | 306.8 | 5.06 | 2.5729 | 1.5591 | 431743 | 35 |
| Ce | 6.77 | 7.04 | 6.46 | 104 | 298.74 | 5.23 | 2.6188 | 1.5421 | 22265 | 53 |
| Ce | 6.77 | 7.01 | 6.45 | 103.63 | 297.48 | 5.25 | 2.5467 | 1.5662 | 27860 | 54 |
| Ce | 6.79 | 7 | 6.46 | 104 | 297.92 | 5.24 | 2.5971 | 1.5154 | 33598 | 55 |
| Ce | 6.77 | 6.99 | 6.45 | 103.6 | 296.67 | 5.26 | 2.5360 | 1.6405 | 39135 | 56 |
| Ce | 6.77 | 6.99 | 6.45 | 103.63 | 296.63 | 5.26 | 2.5413 | 1.6024 | 43077 | 57 |
| Ce | 6.77 | 7.04 | 6.46 | 104 | 298.74 | 5.23 | 2.6084 | 1.6128 | 64850 | 53 |
| Ce | 6.7902 | 7.0203 | 6.4674 | 103.38 | 299.93 | 5.21 | 2.5586 | 1.5333 | 79746 | 51 |
| Ce | 6.788 | 7.0163 | 6.4650 | 103.43 | 299.49 | 5.21 | 2.5554 | 1.5375 | 79748 | 51 |
| Ce | 6.8072 | 7.00689 | 6.47476 | 103.781 | 299.94 | 5.21 | 2.5652 | 1.5318 | 133669 | 58 |
| Ce | 6.7551 | 6.9804 | 6.4687 | 103.707 | 296.33 | 5.27 | 2.5450 | 1.5316 | 133670 | 58 |
| Ce | 6.8004 | 7.0231 | 6.4717 | 103.46 | 300.6 | 5.19 | 2.5615 | 1.5397 | 182582 | 37 |
| Ce | 6.777 | 6.993 | 6.445 | 103.54 | 296.95 | 5.26 | 2.5506 | 1.5271 | 201029 | 59 |
| Ce | 6.78985 | 7.01813 | 6.46662 | 103.42415 | 299.72 | 5.21 | 2.5580 | 1.5330 | 243620 | 60 |
| Pr | 6.741 | 6.961 | 6.416 | 103.63 | 292.59 | 5.35 | 2.5323 | 1.5320 | 62161 | 40 |
| Pr | 6.7596 | 6.9812 | 6.4344 | 103.53 | 295.21 | 5.31 | 2.5395 | 1.5368 | 79749 | 51 |
| Pr | 6.77078 | 6.99017 | 6.44265 | 103.52914 | 296.46 | 5.28 | 2.5325 | 1.5631 | 431753 | 35 |
| Nd | 6.722 | 6.933 | 6.390 | 103.72 | 289.3 | 5.49 | 2.5192 | 1.5321 | 62162 | 40 |
| Nd | 6.732 | 6.930 | 6.383 | 103.61 | 289.42 | 5.49 | 2.5183 | 1.5369 | 62311 | 61 |
| Nd | 6.7352 | 6.9500 | 6.4049 | 103.68 | 291.31 | 5.45 | 2.5242 | 1.5371 | 79750 | 51 |
| Sm | 6.6818 | 6.8877 | 6.3653 | 103.86 | 284.42 | 5.73 | 2.4988 | 1.5370 | 79751 | 51 |
| Sm | 6.73167 | 6.94489 | 6.44964 | 103.899 | 292.7 | 5.57 | 2.5358 | 1.5305 | 133668 | 58 |
| Sm | 6.669 | 6.868 | 6.351 | 103.92 | 282.35 | 5.77 | 2.4932 | 1.5310 | 201839 | 45 |
| Eu | 6.6813 | 6.8618 | 6.3491 | 103.96 | 282.48 | 5.81 | 2.4902 | 1.5393 | 79752 | 51 |
| Eu | 6.639 | 6.823 | 6.318 | 104.00 | 277.69 | 5.91 | 2.4749 | 1.5299 | 201840 | 45 |
| Gd | 6.6435 | 6.8414 | 6.3281 | 103.976 | 279.1 | 6 | 2.4760 | 1.5383 | 79753 | 51 |
| Gd | 6.621 | 6.823 | 6.310 | 104.16 | 276.39 | 6.06 | 2.4693 | 1.5298 | 201841 | 45 |
| Gd | 6.652 | 6.847 | 6.336 | 103.99 | 280.02 | 5.98 | 2.4833 | 1.5373 | 230368 | 62 |
| Gd | 6.33571 | 6.84840 | 6.6516 | 104.023 | 280 | 5.98 | 2.4827 | 1.5325 | 252925 | 63 |
| Tb | 6.61993 | 6.81106 | 6.31653 | 104.1091 | 276.21 | 6.11 | 2.4571 | 1.5579 | 18864 | 41 |
| Dy | 6.59737 | 6.78650 | 6.30380 | 104.1887 | 273.63 | 6.25 | 2.4487 | 1.5536 | 18863 | 41 |

reported in the ICSD, and the unit cell parameter values from a study by Weigel *et al.*⁵⁰ were used to fit the trendline.

The RE–O bond distances of monazite compounds were compared, and larger cations in REO₉ polyhedra resulted in longer average RE–O bond distances (Fig. 4a). As discussed above, the RE cation in the monazite structure is coordinated by nine oxygen atoms, but presenting a single-digit coordination number might not be accurate in relatively distorted coordination polyhedra. The effective coordination numbers (CN_{eff})^{85–87} can be used to express more reasonable coordination numbers by accounting for all the surrounding atoms with a weighting scheme. The CN_{eff} values of REO₉ were calculated using eqn (2) and (3) where w_i is the bond weight of the i _{th} bond, l_{av} is defined in eqn (4), l_i was defined above, and l_{min} is the shortest bond distance in the coordination polyhedron. These equations were formulated by combining the concepts of Pauling with effective coordination numbers and mean fictive r_i values.⁸⁷ The average CN_{eff} value calculated for each RE element

in monazites is plotted in Fig. 4b, and REO₉ polyhedra with larger cations generally show higher CN_{eff} values.

$$CN_{eff} = \sum_i w_i \quad (2)$$

$$w_i = \exp \left[1 - \left(\frac{l_i}{l_{av}} \right)^6 \right] \quad (3)$$

$$l_{av} = \frac{\sum_i l_i \exp \left[1 - \left(\frac{l_i}{l_{min}} \right)^6 \right]}{\sum_i \exp \left[1 - \left(\frac{l_i}{l_{min}} \right)^6 \right]} \quad (4)$$

For the REO₈ coordination in xenotime, each oxygen atom is shared by two RE atoms and one P atom. Similar to monazite, the REO₈ polyhedra share the edges with two adjacent PO₄ tetrahedra (Fig. 2d), forming a chain-like structure along the *c*



Table 3 Structural parameters of REPO₄ xenotime compounds at ambient conditions (293–300 K and 1 atm) including unit cell parameters (*a*, *b*, *c*), cell volume (*V*), cell density (ρ), bond distances (i.e., RE–O, P–O), and the entry number for the Inorganic Crystal Structure Database (ICSD). The space group of listed compounds is *I*₄₁/*amd* (SG# 141). Volume and density are calculated values, and RE–O and P–O are the average distances

| RE | <i>a</i> (Å) | <i>b</i> (Å) | <i>c</i> (Å) | <i>V</i> (Å ³) | ρ (g cm ⁻³) | RE–O (Å) | P–O (Å) | ICSD | Ref. |
|----|--------------|--------------|--------------|----------------------------|------------------------------|----------|---------|--------|------|
| Gd | 6.9670 | 6.9670 | 6.1112 | 296.63 | 5.64 | 2.3758 | 1.5541 | 118105 | 64 |
| Tb | 6.9414 | 6.9414 | 6.0704 | 292.49 | 5.77 | 2.3726 | 1.5302 | 29316 | 65 |
| Tb | 6.940 | 6.940 | 6.068 | 292.26 | 5.77 | 2.3822 | 1.5228 | 35704 | 66 |
| Tb | 6.9309 | 6.9309 | 6.0606 | 291.14 | 5.79 | 2.365 | 1.5359 | 79755 | 51 |
| Tb | 6.9391 | 6.9391 | 6.0694 | 292.25 | 5.77 | 2.3575 | 1.546 | 168751 | 67 |
| Dy | 6.91 | 6.91 | 6.04 | 288.4 | 5.93 | 2.3469 | 1.548 | 26440 | 68 |
| Dy | 6.907 | 6.907 | 6.046 | 288.43 | 5.93 | 2.3496 | 1.5491 | 35705 | 66 |
| Dy | 6.9052 | 6.9052 | 6.0384 | 287.92 | 5.94 | 2.3513 | 1.5372 | 79756 | 51 |
| Dy | 6.909 | 6.909 | 6.038 | 288.22 | 5.93 | 2.5927 | 1.3327 | 192553 | 69 |
| Ho | 6.882 | 6.882 | 6.025 | 285.36 | 6.05 | 2.3465 | 1.5326 | 35706 | 66 |
| Ho | 6.8773 | 6.8773 | 6.0176 | 284.62 | 6.07 | 2.3428 | 1.5319 | 79757 | 51 |
| Ho | 6.8842 | 6.8842 | 6.0255 | 285.56 | 6.05 | 2.34 | 1.5408 | 246677 | 70 |
| Ho | 6.8919 | 6.8919 | 6.0336 | 286.59 | 6.02 | 2.335 | 1.5525 | 257644 | 71 |
| Ho | 6.886 | 6.886 | 6.027 | 285.78 | 6.04 | 2.3499 | 1.5251 | 257646 | 71 |
| Er | 6.863 | 6.863 | 6.007 | 282.93 | 6.16 | 2.3289 | 1.542 | 15670 | 72 |
| Er | 6.860 | 6.860 | 6.003 | 282.5 | 6.17 | 2.3361 | 1.5313 | 36052 | 73 |
| Er | 6.8507 | 6.8507 | 5.9968 | 281.44 | 6.19 | 2.3303 | 1.5356 | 79758 | 51 |
| Tm | 6.839 | 6.839 | 5.986 | 279.98 | 6.26 | 2.3252 | 1.5326 | 36053 | 73 |
| Tm | 6.8293 | 6.8293 | 5.9798 | 278.89 | 6.29 | 2.3098 | 1.5544 | 79759 | 51 |
| Tm | 6.8219 | 6.8219 | 5.97988 | 278.29 | 6.3 | 2.3238 | 1.5195 | 257645 | 71 |
| Yb | 6.816 | 6.816 | 5.966 | 277.17 | 6.42 | 2.3095 | 1.5439 | 36054 | 73 |
| Yb | 6.8093 | 6.8093 | 5.9639 | 276.53 | 6.44 | 2.313 | 1.5319 | 79760 | 51 |
| Lu | 6.792 | 6.792 | 5.955 | 274.71 | 6.53 | 2.3045 | 1.5327 | 2505 | 74 |
| Lu | 6.7443 | 6.7443 | 6.0105 | 273.39 | 6.56 | 2.2974 | 1.5481 | 46792 | 36 |
| Lu | 6.7827 | 6.7827 | 5.9467 | 273.58 | 6.55 | 2.3002 | 1.5337 | 79761 | 51 |
| Lu | 6.7895 | 6.7895 | 5.9560 | 274.56 | 6.53 | 2.3093 | 1.5327 | 162336 | 75 |
| Lu | 6.792 | 6.792 | 5.954 | 274.67 | 6.53 | 2.2998 | 1.5386 | 201133 | 76 |
| Lu | 6.7967 | 6.7967 | 5.9593 | 275.29 | 6.51 | 2.3096 | 1.533 | 246684 | 70 |
| Y | 6.876 | 6.876 | 6.186 | 292.47 | 4.18 | 2.243 | 1.7179 | 24514 | 77 |
| Y | 6.878 | 6.878 | 6.036 | 285.54 | 4.28 | 2.387 | 1.5365 | 28554 | 78 |
| Y | 6.9 | 6.9 | 6.026 | 286.9 | 4.26 | 2.2494 | 1.6709 | 56113 | 79 |
| Y | 6.8947 | 6.8947 | 6.0276 | 286.53 | 4.26 | 2.345 | 1.54 | 79754 | 51 |
| Y | 6.885 | 6.885 | 6.022 | 285.46 | 4.28 | 2.3324 | 1.5503 | 117962 | 80 |
| Y | 6.90706 | 6.90706 | 6.0348 | 287.91 | 4.24 | 2.403 | 1.5302 | 133671 | 58 |
| Y | 6.8817 | 6.8817 | 6.0177 | 284.99 | 4.29 | 2.3365 | 1.5435 | 201131 | 76 |
| Sc | 6.578 | 6.578 | 5.796 | 250.79 | 3.71 | 2.2295 | 1.5606 | 16648 | 81 |
| Sc | 6.5787 | 6.5787 | 5.7963 | 250.86 | 3.7 | 2.2116 | 1.5336 | 74483 | 82 |
| Sc | 6.574 | 6.574 | 5.791 | 250.27 | 3.71 | 2.2067 | 1.5341 | 201132 | 76 |
| Sc | 6.578 | 6.578 | 5.796 | 250.79 | 3.7 | 2.2078 | 1.5367 | 257305 | 83 |

axis (Fig. 2e). Fig. 2f shows the atomic arrangement of RE and P atoms projected down [001]. With smaller RE cations in the xenotime structures compared to monazite, the D values of REO₈ polyhedra in xenotime structures are lower than those reported for monazite structures. The xenotime compounds have shorter RE–O distances (2.2–2.4 Å) compared to monazites (2.4–2.6 Å) (Fig. 4a). The P–O bond distances of tetrahedra in xenotime compounds are generally shorter than those in monazite, but the differences are not significant. Xenotime has only one atomic position for the oxygen atom whereas monazite has four oxygen atomic positions. For both monazite and xenotime compounds, RE–P distances are dependent on the RE size, and xenotime has one RE–P distance along the chain whereas the monazite has two different RE–P distances. The RE–P distances of xenotime crystals are generally longer than

those of monazite, and RE–P distances between RE³⁺ and P⁵⁺ cations in xenotime are generally <3 Å. The CN_{eff} values of xenotime compounds are smaller, in the range of 7.8–8.0, and smaller than monazite as expected (Fig. 4b). The unit cell parameters and volumes increase linearly with larger RE cations in the structures whereas the densities decrease nonlinearly (Fig. 5).

The RE³⁺ cations at RE sites in the monazite and xenotime structures can be substituted by mixed +3 cations, a combination of +2 and +4 cations, or a combination of +2, +3, and +4 cations. Table 4 shows the list of synthetic monazite and xenotime compounds with mixed RE and summarizes the compositional effects. For monazites with mixed RE cations, increasing the average size of mixed cations in the structures increases the unit cell parameters and volumes as expected.^{88–90}






Fig. 1 Illustration showing the relationship of (a) xenotime and (b) monazite structures of REPO₄ to the RE crystal radii (r_c) from Shannon.⁴⁹ LuPO₄ (ICSD 46792) and LaPO₄ (ICSD 46788) were used to create the (a) xenotime and (b) monazite unit cell structures, respectively.

De Biasi *et al.*⁸⁸ synthesized La_{1-x}Ce_xPO₄ ($x = 0-1$) monazite compounds and showed that increasing La contents increased the unit cell parameters and cell volumes. Similarly, Terra *et al.*⁸⁹ observed that increasing La contents in La_{1-x}Gd_xPO₄ ($x = 0-1$) monazites increased the unit cell parameters and cell volumes. Thus *et al.*⁹¹ observed that increasing Eu content in La_{1-x}Eu_xPO₄ ($x = 0-1$) monazite compounds increased the elastic stiffness coefficients, densities, heat capacities, and coefficients of thermal expansion (CTE). Arinicheva *et al.*⁹² observed that microhardness, fracture toughness, unit cell parameters, and cell volumes decreased linearly with increasing Eu content in La_{1-x}Eu_xPO₄ ($x = 0-1$) monazite compounds. Van Emden *et al.*⁹⁰ synthesized Nd_{1-x}Y_xPO₄ ($x = 0.05-0.3$) monazite compounds using a solid state method at 1000 °C and showed that increasing Nd content increased the unit cell parameters and cell volumes. The same group also observed co-crystallization of both monazite and xenotime in Nd_{1-x}Y_xPO₄ compounds when synthesized at 1200 °C.⁹⁰ Hay *et al.*⁹³ synthesized the Gd_{1-x}Dy_xPO₄ ($x = 0-1$) xenotime compounds and observed that pressure and/or shear stress can cause phase transformation of xenotime to monazite. Strzelecki *et al.*⁹⁴ investigated the thermodynamic properties of Er_{1-x}Yb_xPO₄ ($x = 0-1$) xenotime compounds and observed that increasing Er content increased the enthalpies of formation and decreased the Gibbs free energies. The unit cell parameters and cell volumes of Er_{1-x}Yb_xPO₄ ($x = 0-1$) increased with higher Er content as predicted by Vegard's law.⁹⁴ Xiao *et al.*⁹⁵ synthesized Eu³⁺-doped xenotime single crystals including TbPO₄, HoPO₄, ErPO₄, YbPO₄, LuPO₄, and YPO₄ with the Eu concentration of 200 ppm relative to the host RE cations. They observed that incorporation of Eu cations distorted the local structure around

RE sites and affected the rotations of PO₄ tetrahedra in the xenotime structures, and distortion levels were worse for xenotimes with large RE cations.⁹⁵ Rafiuddin *et al.*⁹⁶ synthesized solid solutions of La_{1-x}Yb_xPO₄, La_{1-x}Y_xPO₄, and Sm_{1-x}Ho_xPO₄ ($x = 0-1$) and observed that these compounds with large differences in RE sizes resulted in the presence of both monazite and xenotime phases in the final product, and the phase fractions were dependent on the corresponding RE contents.

For the monazites with a mixed combination of +2 and +4 cations at RE sites, Pb, Cd, or alkaline earth metals (*e.g.*, Mg, Ca, Sr, Ba) can be incorporated with actinide cations (*e.g.*, Th, U, Np), respectively. The chemical formula is (M_x²⁺)(M_(1-x)⁴⁺)PO₄ and many examples have been documented, including Ca_{0.5}-Th_{0.5}PO₄,⁹⁷ Mg_{0.5}Th_{0.5}PO₄,⁹⁸ Sr_{0.5}Th_{0.5}PO₄,⁹⁹ Pb_{0.5}Th_{0.5}PO₄,⁹⁹ Ca_{0.5}U_{0.5}PO₄,¹⁰⁰ Mg_{0.5}U_{0.5}PO₄,⁹⁸ Sr_{0.5}U_{0.5}PO₄,⁹⁸ Ca_{0.5}Np_{0.5}PO₄,¹⁰¹ Ca_{0.5}Np_{0.35}Pu_{0.15}PO₄,¹⁰² and Ca_{0.5}Th_{0.4}U_{0.1}PO₄.¹⁰³ For the monazites with mixed combinations of +2 cations (*e.g.*, Ba, Ca, Cd, Mg, Pb, Sr), +3 cations (REs), and +4 cations (actinides) can occupy RE sites, and the site occupancies of cations with different oxidation states can vary at the RE sites (*e.g.*, Ca_{1/3}Nd_{1/3}U_{1/3}PO₄, La_{0.808}Ba_{0.096}Th_{0.096}PO₄, Ca_{0.146}Nd_{0.716}Th_{0.151}PO₄).^{98,99,104} The monovalent cations (*e.g.*, Li, Na, K, Rb, Cs) with +3 RE cations or Ce⁴⁺ can occupy the RE site of compounds that have similar structures to monazites [*e.g.*, Na₃La(PO₄)₂, LiCe₂(-PO₄)₃, K₂Ce(PO₄)₂].^{105,106}

AXO₄ monazite-type structure stabilities can be dependent on various factors such as composition, temperature, pressure, and the irradiation conditions. Clavier *et al.*¹⁴ reviewed crystal chemistry of the AXO₄ monazite-type compounds in terms of field of stability *versus* composition, with all the substitution






Fig. 2 Structures of (a–c) monazite and (d–f) xenotime compounds. (a) Nine-fold coordination of the RE cation, (b) the chain of REO₉ and PO₄ along the *c* axis, and (c) atomic arrangements of RE and P viewed from the [001] direction in the monazite structure. (d) Eight-fold coordination of the RE cation, (e) the chain of REO₈ and PO₄ along the *c* axis, and (f) atomic arrangements of RE and P viewed from the [001] direction in the xenotime structure. The figure was made using CIFs of ICSD 431743 and ICSD 46792 for LaPO₄ monazite and LuPO₄ xenotime, respectively.

possibilities on the cationic and anionic sites leading to the monazite structure.

Several models, which include structure-field maps (Fig. 6a)^{107,108} and classification diagrams (see Fig. 6b for a modified Bastide diagram),^{109–112} have been developed to correlate the stability of the monazite-type structure with geometric criteria. These representations provide opportunities to predict the structure of a compound. The challenge persists regarding the boundaries of the stability domain within this field. Numerous studies have investigated the stability domain of the monazite-type structure, aiming to develop predictive models that could anticipate whether a compound might take on the monazite structure. Carron *et al.*¹¹³ calculated that a value of 1.86 (ratio between the X–O bond length in the AXO₄ compounds and the r_i , denoted as X/r_i) seems to specify the size limit of both the cation and the anion at the xenotime-monazite structural frontier. This ratio led to them¹¹³ proposing the potential for anionic isomorphous substitution among RE-phosphates, RE-silicates, RE-arsenates, and RE-vanadates. Macey¹¹⁴ further determined that monazite and zircon structures have $X/r_i < 1/1.56$ and $X/r_i > 1/1.56$, respectively.

Podor and Cuney⁹⁷ subsequently explored the stability range of the monazite structure, primarily concentrating on $(M_{1-2x}^{3+})(M_x^{2+})(M_x^{4+})PO_4$ compounds, where stability depends on three parameters (x , average r_i , and the ratio of M elements). Nonetheless, discrepancies with experimental observations could still occur, particularly concerning miscibility gaps. Kolitsch and Holtstam¹¹⁶ devised a visual representation outlining the stability regions of both monazite and zircon-type structures, relying on existing data for REOX₄ (X = P, As, V) compounds. While this diagram offers a broad view of the monazite structure stability field, it is insufficient to correctly describe the partial solid solutions between two REOX₄ compounds, especially those involving a light RE element and a heavy RE element, and the presence of a miscibility gap.¹⁴

4 Properties

4.1 Mechanical and thermal properties

Monazite and xenotime compounds exhibit interesting mechanical and thermal properties across different compositions and structures. Table 5 summarizes the mechanical






Fig. 3 Relationships of (a–c) unit cell parameters, (d) unit cell volumes, and (e) densities with respect to RE r_c of monazite compounds. Where multiple values were given, averages and standard deviations are reported.

properties of monazite and xenotime including Young's modulus (E), bulk modulus (B), shear modulus (G), hardness (H), and flexural strength (FS). Fig. 7 shows the relationships between Young's, bulk, and shear moduli and RE r_c of monazite and xenotime. As the RE r_c values decrease, this results in

increases for the Young's modulus, bulk modulus, and shear modulus, and this can be due to stronger interatomic bonding as the average RE–O distances are smaller for RE cations.¹¹⁷ Different modulus values from various studies are also affected




Fig. 4 (a) Average RE–O bond distances and (b) effective coordination numbers of REO_x polyhedral with respect to RE r_c in monazite and xenotime structures.






Fig. 5 Relationships of (a and b) unit cell parameters, (c) unit cell volumes, and (d) densities with respect to RE r_c of xenotime compounds. Where multiple values were given, averages and standard deviations are reported.

by sample preparation and sintering conditions for the pellets.^{117,118}

Table 6 summarizes the thermal properties of monazite and xenotime including heat capacity (C_p), the CTE, thermal conductivity (k), thermal diffusivity (α), and melting temperatures (T_m). In general, the CTE values of monazite compounds seem to increase with smaller RE cations and RE–O distances in the structures. In general, the CTE values of monazite compounds seem to increase with the larger RE cations and RE–O distances in the structures. The CTE value is related to the inter-atomic potential and depends on the dissymmetry of the potential well.³⁴ Examples of calculated CTE values for both monazites and xenotimes are shown in Fig. 8.¹²¹ The C_p values of monazite compounds are similar. The total heat capacity is the sum of the lattice component and an excess electronic term. The excess electronic heat capacity term increases for CePO₄, PrPO₄, NdPO₄, SmPO₄, and EuPO₄ monazites but not for LaPO₄ and GdPO₄ due to empty and half-filled electron shell configurations, respectively, and this results in similar heat capacities among CePO₄ → EuPO₄, and slightly lower values for LaPO₄ and GdPO₄.^{34,117}

Du *et al.*¹¹⁷ synthesized polycrystalline monazite compounds of LaPO₄, CePO₄, NdPO₄, SmPO₄, EuPO₄, and GdPO₄ and

pressed into pellets using a spark plasma sintering apparatus at 1350 °C and 40 MPa for 3 min. Young's modulus increased linearly from LaPO₄ to GdPO₄ as the RE r_c values decreased. The specific heat values of all the monazites were similar at a given temperatures from 25 °C to 1000 °C and increased as the temperature increased except Gd monazite, which showed lower values at higher temperatures (>600 °C) compared to other monazites. The thermal conductivities of monazite compounds decreased as the temperature increased from 25 to 1000 °C, except EuPO₄ and GdPO₄ that showed increased thermal conductivities from 800 to 1000 °C. This is possibly due to the contribution of radiation transport effect, which becomes more important at higher temperatures. The thermal diffusivity values showed similar behavior as thermal conductivity with respect to temperature.

Perrière *et al.*³⁴ investigated the structural dependence of the mechanical and thermal properties of monazite compounds including LaPO₄, CePO₄, PrPO₄, NdPO₄, SmPO₄, EuPO₄, and GdPO₄. The synthesized monazite powders were pressed into pellets at 1500 °C and 65 MPa for 0.1–20 h. Both Young's modulus and shear modulus values increased with larger RE cations in the structure. The bending strengths of 94–122 MPa and fracture toughness around 1 MPa m^{1/2} showed the brittle



Table 4 Monazite and xenotime compounds with mixed cations and their compositional effects. M and X denote monazite and xenotime structures, respectively

| Composition | Struct. | Compositional effect | Ref. |
|--|---------|---|------|
| $\text{La}_{1-x}\text{Ce}_x\text{PO}_4$ ($x = 0-1$) | M | Increasing La content increased the unit cell lengths and volumes | 88 |
| $\text{La}_{1-x}\text{Gd}_x\text{PO}_4$ ($x = 0-1$) | M | Increasing La content increased the unit cell lengths and volumes | 89 |
| $\text{La}_{1-x}\text{Eu}_x\text{PO}_4$ ($x = 0-1$) | M | Increasing Eu content increased the elastic stiffness coefficients, density, heat capacity, and CTE | 91 |
| $\text{La}_{1-x}\text{Eu}_x\text{PO}_4$ ($x = 0-1$) | M | Increasing Eu content decreased the hardness, toughness, unit cell lengths, and cell volume | 92 |
| $\text{Nd}_{1-x}\text{Y}_x\text{PO}_4$ ($x = 0.05-0.3$) | M | Increasing Nd content increased the unit cell parameters and cell volumes | 90 |
| $\text{Gd}_{1-x}\text{Dy}_x\text{PO}_4$ ($x = 0-1$) | X | Increasing Gd content increased the maximum indentation loadings | 93 |
| $\text{Er}_{1-x}\text{Yb}_x\text{PO}_4$ ($x = 0-1$) | X | Increasing Er content increased the enthalpies of formation and unit cell parameters and decreased the Gibbs free energy values | 94 |
| REPO_4 (RE = Tb, Ho, Er, Yb, Lu, Y) doped with Eu^{3+} | X | Incorporation of Eu cations distorted the local structure around RE sites and affected the rotations of PO_4 tetrahedra, and the distortion level was worse for xenotimes with larger RE cations | 95 |
| $\text{La}_{1-x}\text{Yb}_x\text{PO}_4$, $\text{La}_{1-x}\text{Y}_x\text{PO}_4$, $\text{Sm}_{1-x}\text{Ho}_x\text{PO}_4$ ($x = 0-1$) | M, X | Both monazite and xenotime phases were present in the final product depending on the concentration of corresponding RE elements | 96 |

behavior of monazite compounds, and this brittleness could cause inaccuracies when using micro-indentation analysis. The CTE values of monazites increased with smaller RE cations and RE–O distances in the structures and were in the $10-11.5 \times 10^{-6} \text{ K}^{-1}$ range. The heat capacities of all the synthesized monazites

were $\sim 105-112 \text{ J mol}^{-1} \text{ K}^{-1}$ (with La and Gd having the lowest values). Controlling porosity during fabrication was important for achieving accurate measurements of both thermal and mechanical properties.




Fig. 6 (a) Structure-field map of monazite and xenotime compounds based on the ionic radius (r_i) of A (e.g., RE) and X (e.g., P) in AXO_4 compounds.¹⁰⁷ Reprinted with permission from Aldred.¹⁰⁷ Copyright 1984 American Chemical Society. (b) Modified Bastide diagram for ABX_4 compounds. Reprinted with permission from Hay *et al.*¹¹⁵ Copyright 2013 Elsevier.



Table 5 Mechanical properties of monazite and xenotime compounds including Young's modulus (E), bulk modulus (B), shear modulus (G), hardness (H), and flexural strength (FS). M and X denote monazite and xenotime, and * denotes calculated values

| RE | Struct. | E (GPa) | B (GPa) | G (GPa) | H (GPa) | FS (Mpa) |
|----|---------|--|---|---|------------------------------------|-----------------------------------|
| La | M | 132, ¹¹⁸ 133, ¹¹⁷ 134, ¹¹⁹ 139.1*, ¹²⁰ 144*, ¹¹⁹ 151 (ref. 34) | 99, ¹¹⁹ 117, ¹¹⁷ 107*, ¹¹⁹ 109.8*, ¹²⁰ 134* ¹²¹ | 51, ¹¹⁷ 53, ¹¹⁹ 54*, ¹²⁰ 56*, ¹¹⁹ 58 (ref. 34) | 4.6, ¹¹⁸ 5 (ref. 122) | 109, ³⁴ 100 (ref. 123) |
| Ce | M | 146.5*, ¹²⁰ 150, ¹¹⁷ 162* ¹¹⁹ | 118.6*, ¹²⁰ 121, ¹¹⁷ 126*, ¹¹⁹ 137.2* ¹²¹ | 56.6*, ¹²⁰ 58, ¹¹⁷ 63* ¹¹⁹ | — | 183 (ref. 123) |
| Pr | M | 150.1*, ¹²⁰ 164 (ref. 34) | 113.5*, ¹²⁰ 139.7* ¹²¹ | 58.6*, ¹²⁰ 64 (ref. 34) | — | 94 (ref. 34) |
| Nd | M | 154.1*, ¹²⁰ 157, ¹¹⁷ 164, ³⁴ 168* ¹¹⁹ | 114.1*, ¹²⁰ 127, ¹¹⁷ 135*, ¹¹⁹ 142.3* ¹²¹ | 60.4*, ¹²⁰ 61, ¹¹⁷ 63, ³⁴ 65* ¹¹⁹ | — | 122, ³⁴ 97 (ref. 123) |
| Pm | M | 157.4* ¹²⁰ | 117.1* ¹²⁰ | 61.7* ¹²⁰ | — | — |
| Sm | M | 160, ¹¹⁷ 160.3*, ¹²⁰ 172* ¹¹⁹ | 116.2*, ¹²⁰ 127, ¹¹⁷ 140*, ¹¹⁹ 146* ¹²¹ | 62, ¹¹⁷ 63.1*, ¹²⁰ 66* ¹¹⁹ | — | 135 (ref. 123) |
| Eu | M | 162, ¹¹⁷ 163.1*, ¹²⁰ 174*, ¹¹⁹ 202 (ref. 34) | 118.1*, ¹²⁰ 127, ¹¹⁷ 143*, ¹¹⁹ 147.1* ¹²¹ | 62, ¹¹⁷ 64.2*, ¹²⁰ 67*, ¹¹⁹ 79 (ref. 34) | — | 99 (ref. 34) |
| Gd | M | 165.2*, ¹²⁰ 172, ¹¹⁷ 180*, ¹¹⁹ 199 (ref. 93) | 121*, ¹²⁰ 137, ¹¹⁷ 150*, ¹¹⁹ 149* ¹²¹ | 64.9*, ¹²⁰ 67, ¹¹⁷ 69* ¹¹⁹ | 7.8, ⁹³ 7.9 (ref. 124) | — |
| Tb | M | 164.5* ¹²⁰ | 123.3* ¹²⁰ | 64.4* ¹²⁰ | — | — |
| Dy | M | 165.4* ¹²⁰ | 127.6* ¹²⁰ | 64.4* ¹²⁰ | — | — |
| Tb | X | 48 (ref. 93) | 138.8* ¹²¹ | — | 1.3, ⁹³ 5.7 (ref. 124) | — |
| Dy | X | 127 (ref. 32) | 141.5* ¹²¹ | — | 4.6, ¹¹⁸ 6.6 (ref. 124) | — |
| Ho | X | 166.2* ⁷¹ | 138.9*, ⁷¹ 143.4* ¹²¹ | 63.9* ⁷¹ | — | — |
| Er | X | 178* ¹²⁵ | 144*, ¹²⁵ 146.1*, ¹²¹ 168 (ref. 125) | 69* ¹²⁵ | — | 100 (ref. 126) |
| Tm | X | 178.1* ⁷¹ | 144.1*, ⁷¹ 147.2* ¹²¹ | 68.8* ⁷¹ | — | — |
| Yb | X | 160* ¹²⁵ | 129*, ¹²⁵ 150* ¹²¹ | 62* ¹²⁵ | — | 135 (ref. 126) |
| Lu | X | 192.1, ⁷¹ 210* ¹²⁵ | 152.8*, ¹²¹ 169.3, ⁷¹ 170* ¹²⁵ | 73.3, ⁷¹ 81* ¹²⁵ | 7.42 (ref. 71) | 155 (ref. 126) |
| Y | X | 145.5, ⁷¹ 224*, ¹²⁵ 186 (ref. 127) | 132.4, ⁷¹ 144.4*, ¹²¹ 173* ¹²⁵ | 55.2, ⁷¹ 87* ¹²⁵ | 5.83 (ref. 71) | 95 (ref. 126) |
| Sc | X | 203, ¹²⁷ 211* ¹²⁵ | 175.1*, ¹²¹ 140* ¹²⁵ | 84* ¹²⁵ | — | — |

Li *et al.*¹²¹ calculated theoretical mechanical and thermal properties of monazite (La → Gd) and xenotime (Tb → Lu, Y, and Sc) compounds using the chemical bond theory of dielectric description. The CTE values increased with larger RE cations in the structures whereas the bulk moduli and lattice energies decreased. The CTE values were in the range of 7.78–7.47 × 10⁻⁶ K⁻¹ for the La → Gd monazite compounds and 5.88–5.72 × 10⁻⁶ K⁻¹ range for Tb → Lu xenotime compounds. The CTE and bulk modulus values were dependent on the RE–O bonds. The RE–O distances were ionically dominated and changed with different RE cations due to lanthanide contraction, and PO₄ tetrahedra showed relatively high lattice energies and behaved nearly rigidly during deformation.

Kenges *et al.*¹¹⁸ synthesized pellet samples of LaPO₄ monazite compounds with different sintering temperatures from 900 °C to 1500 °C and measured mechanical and thermal properties. The LaPO₄ compounds contained a small amount of impurity phase La(PO₃)₃ (lanthanum metaphosphate). The LaPO₄ monazite pellet sintered at 1100 °C showed the highest Young's modulus, toughness, and thermal conductivity. Increasing the sintering temperature increased the crystallite size and decreased the porosities of pellets. The LaPO₄ monazite pellet sintered at 1100 °C had a Young's modulus of 132 GPa, a hardness of 4.6 GPa, a toughness of 1.6 MPa m^{1/2}, a CTE of 8.2 × 10⁻⁶ K⁻¹, and a thermal conductivity of 3.2 W m⁻¹ K⁻¹ at 25 °C.

Deepthi and Balamurugan¹³¹ compared the flexural strength and Young's modulus of LaPO₄ and LaPO₄ mixed with 20

mass% Y₂O₃. The LaPO₄/Y₂O₃ pellets were sintered at 1000–1600 °C, and a pellet sintered at 1400 °C resulted in more uniform grain structure with less porosity. The LaPO₄/Y₂O₃ pellet showed a reduction in flexural strength by 22% but increase of 1.05% in Young's modulus compared to the LaPO₄ pellet.

Popa and Konings¹²⁸ synthesized EuPO₄ and SmPO₄ monazite compounds and calculated their heat capacities. They used the enthalpy data of Sm and Eu monazites along with data from other La, Ce, Nd, and Gd monazites and calculated the heat capacity as a sum of lattice contributions and an excess electronic term. The calculated heat capacities of La → Gd monazites were in the range of 101.28–111.49 J mol⁻¹ K⁻¹ range, and these values were in good agreement with the experimental values.

Hay *et al.*⁹³ investigated the phase transformations and deformation mechanisms of GdPO₄, TbPO₄, and DyPO₄ compounds using scanning electron microscopy (SEM) and transmission electron microscopy (TEM) after indentation. The synthesized powders of TbPO₄ and DyPO₄ had xenotime structures whereas GdPO₄ had a monazite structure. These materials were cold pressed at ~300 MPa and sintered at 1600 °C for 20 h and 1700 °C for 1 h. The GdPO₄, TbPO₄, and DyPO₄ compounds showed Young's moduli of 199, 48, and 127 GPa and hardness values of 7.8, 1.3, and 4.6 GPa, respectively. The authors observed stress-induced transformations from xenotime to monazite and suggested ferroelastic behavior under certain conditions.






Fig. 7 (a and c) Young's modulus and (b and d) bulk modulus values of (a and b) monazite and (c and d) xenotime compounds as functions of crystal radius of the RE cation (r_c).

Hikichi *et al.*¹²⁶ measured the specific heats, thermal diffusivities, thermal conductivities, and bending strengths of xenotime pellets including ErPO_4 , YbPO_4 , LuPO_4 , and YPO_4 . The xenotime pellets were sintered at 700 °C to 1700 °C. The YbPO_4 and LuPO_4 pellets sintered above 1300 °C as well as YPO_4 and ErPO_4 pellets sintered above 1500 °C showed relative densities of $\geq 98\%$. The bending strengths increased with larger RE cations in the structures. The heat capacities of Er, Yb, Lu, and Y xenotime compounds were 0.40, 0.38, 0.38, and 0.48 $\text{J mol}^{-1} \text{K}^{-1}$ at 20 °C, respectively. The CTE values were $6.0 \times 10^{-6} \text{K}^{-1}$ for Er and Yb compounds and $6.2 \times 10^{-6} \text{K}^{-1}$ for Lu and Y compounds.

Wilkinson *et al.*¹²⁴ studied bulk modulus and hardness properties of EuPO_4 , GdPO_4 , TbPO_4 , and DyPO_4 compounds using *in situ* nanoindentation for a range of loading rates and indentation depths. EuPO_4 and GdPO_4 formed monazite structures, and TbPO_4 and DyPO_4 formed xenotime structures. The bulk modulus values were decreasing in order of Gd, Eu, Dy, and Tb compounds. Both Eu and Gd compounds showed hardnesses of 8–9 GPa whereas Tb and Dy compounds showed hardnesses of 6–7 GPa. Hardnesses for all four compounds were not impacted by indentation depth or strain rate.

In addition to experimental methods, first principles calculations were also used to calculate the structural and physical

properties of monazite and xenotime crystals. Kowalski and Li¹²⁰ calculated elastic moduli of La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, and Dy monazites using *ab initio* density functional theory (DFT). The Margules interaction parameters, which is related to excess enthalpy of mixing in a $\text{RE}_1\text{xRE}_2(1-\text{x})\text{PO}_4$ solid solution, and moduli were related to the mismatch in the endmember volumes of different RE cations within the structures. The computed Young's moduli, bulk moduli, and shear moduli increased with decreases in RE cation radii. The range of Young's moduli, bulk moduli, and shear moduli were 139–165 GPa, 110–129 GPa, and 54–65 GPa, respectively. Feng *et al.*¹¹⁹ calculated theoretical mechanical and thermal properties of monazite compounds using the results of local spin density approximation and compared to the experimental values. The Young's moduli, bulk moduli, and shear moduli of LaPO_4 , CePO_4 , NdPO_4 , SmPO_4 , EuPO_4 , and GdPO_4 increased with smaller RE cations and shorter RE–O distances in the structures. The Young's modulus of monazite compounds showed high anisotropy. The calculated coefficients of linear thermal expansion were similar to experimental values, but the calculated thermal conductivities were higher than experimental values measured at $>800 \text{K}$.

Blanca-Romero *et al.*¹³² used the DFT + U method to calculate the structures and thermodynamic properties of monazite type



Table 6 Thermal properties of monazite and xenotime compounds including heat capacity (C_p), coefficient of thermal expansion (CTE), thermal conductivity (k), thermal diffusivity (α), and melting temperature (T_m). The measured and calculated temperatures are shown in the parentheses and * denotes values that were calculated

| RE | Struct. | C_p (J mol ⁻¹ K ⁻¹) | CTE ($\times 10^{-6}$ K ⁻¹) | k (W m ⁻¹ K ⁻¹) | α (mm ² s ⁻¹) | T_m (°C) |
|----|---------|--|--|--|---|-----------------|
| La | M | 101.28 (25 °C), ¹²⁸ 101.28* (25 °C), ¹²⁸ 106 (50 °C) ³⁴ | 7.78*, ¹²¹ 8.2 (25–1050 °C), ¹¹⁸ 8.894*, ¹¹⁹ 10 (20–1000 °C), ¹²³ 10.3 (200–1000 °C) ³⁴ | 3.2 (25 °C), ¹¹⁸ 3.61 (25 °C), ¹¹⁷ 5.3 (50 °C) ³⁴ | 1.629 (25 °C) ¹¹⁷ | 2072 (ref. 129) |
| Ce | M | 106.4 (25 °C), ¹²⁸ 106.63* (25 °C), ¹²⁸ 110 (50 °C) ³⁴ | 7.71*, ¹²¹ 9.029*, ¹¹⁹ 9.9 (20–1000 °C), ¹²³ 10.7 (200–1000 °C) ³⁴ | 3.14 (25 °C) ¹¹⁷ | 1.334 (25 °C) ¹¹⁷ | 2045 (ref. 129) |
| Pr | M | 106.04* (25 °C), ¹²⁸ 108 (50 °C) ³⁴ | 7.66*, ¹²¹ 10.9 (200–1000 °C) ³⁴ | 3.4 (50 °C) ³⁴ | — | 1938 (ref. 129) |
| Nd | M | 104.8 (25 °C), ¹²⁸ 104.92* (25 °C), ¹²⁸ 108 (50 °C) ³⁴ | 7.61*, ¹²¹ 8.093*, ¹¹⁹ 9.4*, ¹¹⁹ 9.8 (20–1000 °C), ¹²³ 10.7 (200–1000 °C) ³⁴ | 3.05 (25 °C), ¹¹⁷ 4.4 (50 °C) ³⁴ | 1.274 (25 °C) ¹¹⁷ | 1975 (ref. 129) |
| Sm | M | 105.59* (25 °C), ¹²⁸ 112 (50 °C) ³⁴ | 7.54*, ¹²¹ 9.7 (20–1000 °C), ¹²³ 9.738*, ¹¹⁹ 11 (200–1000 °C) ³⁴ | 2.87 (25 °C), ¹¹⁷ 3.9 (50 °C) ³⁴ | 1.160 (25 °C) ¹¹⁷ | 1916 (ref. 129) |
| Eu | M | 110 (50 °C), ³⁴ 111.49 (25 °C) ¹²⁸ | 7.51*, ¹²¹ 8.303*, ¹¹⁹ 11.1 (200–1000 °C) ³⁴ | 2.99 (25 °C), ¹¹⁷ 5.8 (50 °C) ³⁴ | 1.135 (25 °C) ¹¹⁷ | 2200 (ref. 119) |
| Gd | M | 102.21 (25 °C), ¹²⁸ 102.21* (25 °C), ¹²⁸ 105 (50 °C) ³⁴ | 7.47*, ¹²¹ 8.303*, ¹¹⁹ 11.4 (200–1000 °C) ³⁴ | 3.22 (25 °C), ¹¹⁷ 4.8 (50 °C) ³⁴ | 1.322 (25 °C) ¹¹⁷ | 2200 (ref. 119) |
| Tb | X | 101.4* (25 °C) ¹³⁰ | 5.88* ¹²¹ | — | — | 2150 (ref. 1) |
| Dy | X | 102.5* (25 °C) ¹³⁰ | 5.85* ¹²¹ | — | — | 2150 (ref. 1) |
| Ho | X | 102.4* (25 °C) ¹³⁰ | 5.82* ¹²¹ | — | — | — |
| Er | X | 102.3* (25 °C) ¹³⁰ | 5.79*, ¹²¹ 6 (1000 °C) ¹²⁶ | 12.01 (20 °C) ¹²⁶ | 0.5 (20 °C) ¹²⁶ | 1896 (ref. 129) |
| Tm | X | 102.7* (25 °C) ¹³⁰ | 5.78* ¹²¹ | — | — | — |
| Yb | X | 102.8* (25 °C) ¹³⁰ | 5.75*, ¹²¹ 6 (1000 °C) ¹²⁶ | 11.71 (20 °C) ¹²⁶ | 0.5 (20 °C) ¹²⁶ | — |
| Lu | X | 100.2* (25 °C) ¹³⁰ | 5.72*, ¹²¹ 6.2 (1000 °C) ¹²⁶ | 11.97 (20 °C) ¹²⁶ | 0.5 (20 °C) ¹²⁶ | — |
| Y | X | 100.3* (25 °C) ¹³⁰ | 6.2 (1000 °C), ¹²⁶ 6.7* ¹²¹ | 12.02 (20 °C) ¹²⁶ | 0.6 (20 °C) ¹²⁶ | 1995 (ref. 129) |
| Sc | X | — | 6.95* ¹²¹ | — | — | — |




Fig. 8 Summary of calculated CTE values for both monazite and xenotime REPO₄ crystals from Li *et al.*¹²¹ as a function of RE r_c .

crystals, with a goal to test the accuracy of the method for modeling f electron-containing systems such as RE-monazites. They found significant improvement both in terms of structures (lattice parameters, unit cell volumes, and RE–O distances for both RE oxides and phosphates) and properties (formation energies for RE phosphates and band gaps for RE oxides) of the DFT + U method as compared to the standard DFT in

comparison to experimental values. Overall, the DFT + U method with the PBEsol (Perdew–Burke–Ernzerhof functional revised for solids) exchange correlation functional and Hubbard U parameters derived from linear response-based *ab initio* calculations was found to be a good choice for studying RE oxides and monazites.

Beridze *et al.*¹³³ further investigated the DFT + U method for *ab initio* calculations of xenotime- and actinide-bearing complexes. The accuracy of the description of RE–O bond distances in xenotime was compared for two standard DFT xc functionals (PBEsol with f electrons in the core and f electrons in the valence shells) and the DFT + U (PBEsol + U_{LR} , with the U values calculated from *ab initio* linear response). It was found that the DFT + U method has the best description of RE–O distances in xenotime crystals while both DFT + U and DFT (PBEsol with f electrons in the core) describe formation energies with good agreement with experiment, when accounting for the overestimation of P₂O₅ volume, similar to the case of monazites.¹³²

4.2 Chemical durability

In general, the chemical durabilities of RE-phosphate and actinide-phosphate compounds documented in the literature are very high. Solubility product constants (K_{sp}) for hydrated actinide-phosphate (AnPO₄·xH₂O) and RE-phosphate (REPO₄·xH₂O) compounds, which cover rhabdophane, monazite, and xenotime compounds, have been found within the range of



$\log(K_{s,0}^{\circ}) = -27.4$ to -24.5 for $\text{LaPO}_4 \cdot 0.5\text{H}_2\text{O}^{134-136}$ to $\log(K_{s,0}^{\circ}) = -66.6$ for $\text{Th}_2(\text{PO}_4)_2(\text{HPO}_4) \cdot \text{H}_2\text{O}^{135,136}$ at 25 °C. Values for $\log(K_{s,0}^{\circ})$ at 100 °C were reported at -26.0 for $\text{NdPO}_4 \cdot 0.5\text{H}_2\text{O}$ (rhabdophane), -25.7 for $\text{PrPO}_4 \cdot 0.5\text{H}_2\text{O}$ (rhabdophane), and -25.5 for $\text{ErPO}_4 \cdot n\text{H}_2\text{O}$ (xenotime).^{46,134,136} Documented apparent activation energy (E_a) values fall within the 39–45 kJ mol⁻¹ range.^{89,137} Oftentimes, the REPO_4 compounds are used as surrogates for the actinide-equivalent analogs because they are easier and less costly to study than the actinide-containing phases.^{138,139} A summary of normalized release rate (NR_i) data from the literature on these types of phosphate compounds is provided in Table 7.

In a study by Teng *et al.*,¹⁴⁰ a mixed $\text{Ce}_{0.5}\text{Pr}_{0.5}\text{PO}_4$ monazite sample set was produced from Pr_6O_{11} , $\text{Ce}_2(\text{C}_2\text{O}_4)_3 \cdot 10\text{H}_2\text{O}$, and ADP. Particles were ball milled in ethanol (4 h), dried at 60 °C (18 h), and calcined at 1000 °C (2 h). Calcined products were mixed with 5–10% polyvinyl alcohol (PVA). The calcined material was cold uniaxially pressed at 60 MPa, cold isostatically pressed at 200 MPa, and then calcined at 500 °C (6 h). Finally, samples were hot-pressed in evacuated graphite molds (<10 Pa of atmosphere, 30 MPa applied load) at temperatures of 1050–1250 °C for 0.5–4 h. A select set of samples (1150 °C for 2 h) were subjected to MCC-1 (ASTM C1220) chemical durability tests at

a 1 : 10 cm⁻¹ surface-area-to-volume (sample : leachant) ratio at 90 °C in PTFE containers for different testing durations ranging from 3 d to 42 d where leachates were quantitatively measured using inductively coupled plasma mass spectrometry (ICP-MS). After 42 d of leaching, the NR_i values were found to be 5.7×10^{-6} g m⁻² d⁻¹ for Ce and 5.3×10^{-5} g m⁻² d⁻¹ for Pr.

In a study by Oelkers and Poitrasson,¹³⁷ dissolution tests were run on natural monazite from Manangotry (Madagascar) in open mixed flow reactors under different conditions of 50–229 °C (pH = 2) and 70 °C (pH = 1.6, 2.6, or 10) and closed reactors at 70 °C (pH = 2, 6, or 10). The starting material was ground to a 50–100 μm particle size fraction. The results showed a range of leach rates with the highest releases revealed for the highest test temperatures (≥ 200 °C).

In a study by Terra *et al.*,⁸⁹ several monazites were made in the solid solution system of $\text{La}_{(1-x)}\text{Gd}_x\text{PO}_4$ ($x = 0, 0.2, 0.3, 0.35, 0.4, 0.5, 0.6, 0.65, 0.7, 0.8, \text{ and } 1.0$). Starting materials included $\text{La}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$, $\text{LaCl}_3 \cdot 7\text{H}_2\text{O}$, $\text{Gd}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$, $\text{GdCl}_3 \cdot 6\text{H}_2\text{O}$, and H_3PO_4 . An excess of H_3PO_4 was included to prevent RE_2O_3 formation during synthesis. Aqueous solutions of the RE reagents (*i.e.*, 0.6–1.4 M) were prepared and these were added to 5 M H_3PO_4 . Three different methods were used to synthesize the compounds. In the first approach, heat was applied in different

Table 7 Summary of chemical durability data for REPO_4 compounds^a including the composition (if given), test conditions, normalized release rate (NR_i) for element “*i*” (if given), and the reference

| Composition | Test conditions | NR_i (g m ⁻² d ⁻¹) | Ref. |
|---|--|---|------|
| $\text{Ce}_{0.5}\text{Pr}_{0.5}\text{PO}_4$ | MCC-1 (ASTM C1220); $T = 90$ °C, pH = 7, $t = 42$ days, PTFE, DIW | 5.7×10^{-6} [Ce] 5.3×10^{-5} [Pr] | 140 |
| Natural ^b | 50 °C < T < 229 °C; 1.62 < pH < 10.04; 50–100 μm particles | 8.13×10^{-7} [Ce] (70 °C, pH = 6) 4.13×10^{-5} [Ce] (70 °C, pH = 1.6) 9.29×10^{-7} [Ce] (50 °C, pH = 2) 2.69×10^{-3} [Ce] (229 °C, pH = 2) | 137 |
| GdPO_4 | 200 mg in 5 mL acidic solution; removed 100 μL for time resolved data points and replaced with fresh solution; 90 °C; 0.1 M HNO_3 | $2.2 \pm 0.7 \times 10^{-5}$ [Gd] (RT) $5.9 \pm 2.1 \times 10^{-4}$ [Gd] (90 °C) | 89 |
| (La,Nd,Pr) PO_4 | Under saturation in either static tests (in HDPE with low leachate renewal) or dynamic tests (in PTFE with high leachate removal) | 10^{-3} to 10^{-7} | 136 |
| REPO_4 | 25 °C < T < 90 °C | 1.17×10^{-3} [La] (90 °C) 4.3×10^{-4} [Ce] (90 °C) 1.01×10^{-3} [Nd] (90 °C) 4.02×10^{-3} [Gd] (90 °C) | 141 |
| REPO_4 | $T = 90$ °C; 0.1 M HNO_3 | 1.4×10^{-3} [La] 1.8×10^{-3} [Ce] 1.0×10^{-3} [Nd] 1.6×10^{-3} [Eu] 1.0×10^{-3} [Gd] | 142 |
| REPO_4 | 50% H_2O vapor balanced with O_2 at 0.3 cm s ⁻¹ , 1500 °C, and 1 atm for 80 h. | 5.6×10^{-2} [Sc] 6.0×10^{-2} [Y] 9.8×10^{-2} [Er] 1.0×10^{-1} [Yb] 4.5×10^{-2} [Lu] | 125 |

^a ASTM denotes American Society for Testing and Materials International; DIW denotes deionized water; MCC denotes Materials Characterization Center; NR_i denotes the *i*-th element normalized release rate; PTFE denotes polytetrafluoroethylene; RT denotes room temperature (*i.e.*, ~20–25 °C).

^b Natural monazite from Manangotry (Madagascar) listed with composition of $(\text{Ca}_{0.04}\text{La}_{0.21}\text{Ce}_{0.43}\text{Pr}_{0.05}\text{Nd}_{0.15}\text{Sm}_{0.02}\text{Gd}_{0.01}\text{Th}_{0.13})\text{P}_{0.90}\text{Si}_{0.09}\text{O}_4$ with a calculated (normalized) molecular weight of 248.85 g mol⁻¹.



steps: (1) samples were dried through direct evaporation using a sand bath, (2) dried material was ground to finer particle size and heated at 400 °C (14 h), and (3) heated at 1300 °C (10–14 h). In the second approach, the mixture was placed in a PTFE container at 150 °C in a sand bath for 1–2 weeks. The third approach utilized a hydrothermal synthesis process with additives in PTFE Parr autoclaves at 150–200 °C for 1–2 months. The GdPO_4 compound was subjected to chemical durability testing as shown in Table 7.

In a study by Du Fou de Kerdaniel,¹³⁶ $\text{AnPO}_4 \cdot x\text{H}_2\text{O}$ compounds (An = Th, U) were produced using low-temperature methods based on procedures by Terra *et al.*¹⁴³ and Clavier *et al.*¹⁴⁴ or using dry chemistry routes by grinding mixtures and heating these mixtures to 1100–1400 °C where the target cations were Th, U, and REs. Leaching studies were performed under saturation in either static tests (in HDPE with low leachate renewal) or dynamic tests (in PTFE with high leachate removal) where solutions were analyzed with ICP-MS, time-resolved laser fluorescence spectroscopy, or α -scintillation counting. Dissolved solids were determined as mass loss and reported as $R_{L(i)}$ (i = element of interest) where $R_{L(i)}$ values ranged from 10^{-7} to $10^{-3} \text{ g m}^{-2} \text{ d}^{-1}$.

In a study by Hikichi *et al.*,¹²⁶ the stabilities of RE elements of ErPO_4 , YbPO_4 , LuPO_4 , and YPO_4 xenotime compounds in acidic or basic aqueous environments were investigated. The mass% losses of RE elements from xenotime compounds were measured using HCl, H_2SO_4 , HNO_3 , NaOH, NH_4OH solutions with concentrations of 6–36 N, and the test was conducted at 20 °C for 30 d. The results showed that the tested xenotime compounds were stable in these solutions, and the mass losses of RE elements were < 0.7 mass%.

In a study by Han *et al.*,¹²⁵ xenotime powders including ErPO_4 , YbPO_4 , LuPO_4 , ScPO_4 , and YPO_4 were cold pressed into pellets at 50 MPa and sintered at 1500 °C for 20 h in air. Chemical durability tests were performed using a vapor flow of 50% H_2O balanced with O_2 at 0.3 cm s^{-1} at 1500 °C and 1 atm for 80 h. The results showed dissolution rates of $5\text{--}10 \times 10^{-2} \text{ g m}^{-2} \text{ d}^{-1}$ for xenotime compounds. However, the tests were performed in an alumina tube furnace, and formation of $\text{Al}_5\text{RE}_3\text{O}_{12}$ compounds were observed.

Rafuiddin and Grosvenor¹⁴⁵ investigated the room-temperature chemical durabilities of monazite-type, xenotime-type, and rhabdophane-type compounds on fine particles with specific surface areas ranging $1.3\text{--}15.1 \text{ m}^2 \text{ g}^{-1}$. Two types of tests were run including dynamic tests over 84 d and static tests over 3 months. The tests revealed that the rhabdophane ($\text{GdPO}_4 \cdot \text{H}_2\text{O}$) structure released higher quantities of Gd and P ions in deionized water within the initial week of exposure. Analysis of the long-range and local structures of these materials indicates that the structures of these materials remained unchanged after seven months of leaching.

Wronkiewicz *et al.*¹⁴⁶ studied the chemical durabilities of glass-crystal composites (GCCs) containing different crystalline phases, including apatite, monazite $[(\text{Ce,U})\text{PO}_4]$, and spinel. The tests run included the product consistency test (PCT, $t = 7$ d, 28 d, and 91 d),¹⁴⁷ the vapor hydration test (VHT),¹⁴⁸ and the Toxicity Characteristic Leach Procedure (TCLP).¹⁴⁹ The

monazite was noted as having fewer elements (*i.e.*, Ce, U, Th) compared to the apatite sample. The leachate from the PCTs ($t = 7\text{--}91$ d) was noted as being slightly acidic ($\text{pH} \approx 5.6\text{--}6.2$). The apatite and monazite samples were noted as being 100–300× more durable than a glass waste form (*i.e.*, SRL-202U) for U release.

Poitrasson *et al.*¹⁵⁰ studied naturally formed magmatic monazites from European-based Paleozoic granites. Their studies showed that the hydrothermal alteration of these monazites was notably complex including a variety of mechanisms such as monoclinic \rightarrow hexagonal crystal structure transitions, chemical exchanges, cation substitutions, selective Th removal, dissolution followed by precipitation, and dissolution with replacement by different minerals. They also noted that temperatures up to 300 °C likely occurred within the vicinity of the minerals.

Mikhailova *et al.*¹⁵¹ studied Pu-containing Eu-monazite and have documented Pu release being attributed to the formation of hydrated (rhabdophane) PuPO_4 by storage in air. This calls into question the long-term disposal potential for actinides stored in REPO_4 compounds if moisture is present in the atmosphere, which could be reduced if storage was performed in inert and dry conditions.

4.3 Radiation stability

The majority of naturally occurring monazites have been affected by radiation due to α decay of actinides within these minerals.¹⁵² This radiation has the potential to cause metamict alterations in the crystal structures of minerals, consequently elevating their solubility. In contrast to many radioactive minerals, monazite retains its crystalline structure under substantial cumulative radiation doses. Monazites are known to remain within the crystalline states by an α -healing mechanism through radiation-induced defects.^{153–155} Self-recovery of damaged structure was not observed in zircon minerals (isostructural to xenotime) with SiO_4 , but partial structural recovery was observed in xenotimes with PO_4 .^{156–158} Table 8 summarizes the critical amorphization dose of monazite and xenotime compounds.

Meldrum *et al.*¹⁵⁵ studied the effect of irradiation on monazite (LaPO_4), xenotime (ScPO_4), ZrSiO_4 , and ThSiO_4 using 800 keV Kr^+ ions. Recrystallization energies for the compounds were calculated to be 3.1–3.3 eV for the silicates and 1–1.5 eV for the phosphates. Radiation damage was monitored as a function of temperature, and above 700 °C, the amorphization of ZrSiO_4 could not be induced as the recrystallization process was faster than damage accumulation. The critical temperature was calculated to be only 35 °C for LaPO_4 , and the monazite would not undergo phase decomposition at the tested conditions. In another study by the same group,¹⁵⁹ monazite could not be amorphized when exposed to 800 keV Kr^+ ions at temperatures surpassing 175 °C. On the contrary, zircon underwent amorphization at temperatures reaching up to 740 °C. It was found that materials with the zircon structure (*i.e.*, ZrSiO_4 and ScPO_4) could be amorphized at slightly elevated temperatures



Table 8 Critical amorphization dose for monazite and xenotime

| Materials | Critical amorphization dose | Ref. |
|---|---|------|
| LaPO ₄ | 0.15 dpa (0 K) | 159 |
| Natural monazite | $7 \times 10^{16} \alpha \text{ mg}^{-1}$ | 160 |
| Natural monazite | 0.13 dpa (0 K) | 159 |
| Synthetic monazite (La,Pu)PO ₄ | $\sim(0.2\text{--}0.3) \times 10^{16} \alpha \text{ mg}^{-1}$ | 161 |
| Natural xenotime with Th and U | $(1.4\text{--}14) \times 10^{16} \alpha \text{ mg}^{-1}$ | 160 |
| CePO ₄ | $\sim 0.35\text{--}0.47 \text{ dpa}$ ($\sim 298 \text{ K}$) | 162 |
| ErPO ₄ xenotime | $(0.3\text{--}7.3) \times 10^{16} \alpha \text{ mg}^{-1}$ | 163 |
| Nanocrystal phosphate Rb ₃ Nd(PO ₄) ₂ | $\sim 0.52 \text{ dpa}$ | 164 |

compared to compounds with the monazite structure under equivalent irradiation conditions.

Seydoux-Guillaume *et al.*¹⁶⁵ studied the healing of radiation damage in natural monazite with annealing at 500–1200 °C. The natural monazite contained two domains with distorted lattice areas with α -dose of $2.5 \times 10^{16} \alpha \text{ mg}^{-1}$ accumulated since 474 Ma ago. From 500–900 °C, partial healing of the lattice occurred. At 900 °C after 10 days, only one domain remained, and a well-crystallized lattice was observed. The same group performed structural analysis using X-ray diffraction (XRD), TEM, SEM, and electron probe microanalysis and showed that monazites are not metamict despite the old ages of samples ranging from 24 to 1928 Ma.¹⁶⁶

Bregiroux *et al.*¹⁶⁷ synthesized monazite powders containing plutonium(III), plutonium(IV) and americium(III). They examined the response of the monazite structure to α self-irradiation using XRD. The results revealed a total amorphization of the crystalline structure after 300 days, reaching a cumulative dose of $1.65 \times 10^{25} \alpha \text{ m}^{-3}$.

Picot *et al.*¹⁶⁸ explored the impact of Au²⁺ and He⁺ ion irradiation on monazite to simulate α -decay effects. The Au²⁺ ion-irradiation induced significant alterations in the material properties. At a damage level of 6.7 dpa, monazite displayed an approximately 8.1% increase in volume, a 59% decrease in hardness, and complete structural amorphization. Conversely, no changes in the properties of these compounds were noted following He⁺ ion implantation.

Deschanel *et al.*¹⁶⁹ investigated α -induced swelling in monazite and zirconolite ceramics. It was found that the macroscopic swelling and amorphization of monazite relied on the type of irradiation. Monazite samples irradiated externally with Au became amorphous and exhibited a maximum swelling of 8%. In contrast, the swelling in samples doped with ²³⁸Pu was significantly smaller, at approximately 1%.

Radiuddin and Grosvenor¹⁵⁷ studied the structural stabilities of La_{1-x}Yb_xPO₄ materials implanted with Au ions. The long- and short-range order of La_{1-x}Yb_xPO₄ ($x = 0, 0.3, 0.7, 1.0$) are influenced by ion-implantation, indicating the materials are prone to structural damage. Interestingly, in certain members of the La_{1-x}Yb_xPO₄ series ($x = 0.7$ and 1.0), partial recovery of the structure was observed following high-dose Au ion implantation.

Sadhasivam and Rajesh³⁸ studied the effect of γ -irradiation on the NdPO₄ monazite compound using ⁶⁰Co γ -cell source at

a dose rate of 4.5 kGy h⁻¹. Defect center, ionization, and charge trapping did not occur during irradiation, and no significant structural change was observed up to 150 kGy γ dose. The high level of γ dose did not affect the crystallinity and optical properties.

Rafiuddin *et al.*¹⁶³ evaluated irradiation effects on the ErPO₄ xenotime compound structure using high-energy dual ion-beam irradiation of 1.5 MeV Au²⁺ and 160 keV He⁺. The xenotime structure was found to undergo amorphization at a lower Au²⁺ ion-fluence than the monazite structure. Moreover, subsequent He⁺ ion-irradiation on the amorphized ErPO₄ samples did not lead to the structural restoration of xenotime. Simultaneous ion-irradiation of Au²⁺ and He⁺ prevented the amorphization of ErPO₄ as higher amounts of electronic energy was applied, similar to the α -healing mechanism in the monazite structures where high energies cause recrystallization faster than damage accumulation. However, the α -healing mechanism for xenotime required ~ 4 times more energy compared to monazite.

Overstreet *et al.*¹⁷⁰ investigated the structural stability of SmPO₄ and TbPO₄ under swift heavy ion irradiation using 1.1 GeV ¹⁹⁷Au ions. Both SmPO₄ monazite and TbPO₄ xenotime structures experienced amorphization at comparable rates with increasing fluence, and complete amorphization occurred $\sim 5 \times 10^{12}$ ions cm⁻² for both compounds. No irradiation-induced recrystallization was observed at higher fluences for both compounds. Findings from this study differed from other radiation damage using relatively low-energy ions, where the monazite compounds were more resistant to amorphization compared to xenotime compounds. The results from this study suggested that the crystal chemistries and structures of monazite and xenotime will not greatly affect the radiation tolerance to highly energetic ions.

Tisdale *et al.*¹⁶⁴ synthesized single crystals of Rb₃RE(PO₄)₂ (RE = Y, La, Pr, Nd, and Sm → Lu) by high-temperature flux growth methods. The 1.2 MeV Xe³⁺ ions were used on the Rb₃Nd(PO₄)₂ sample to investigate the radiation effect, and complete amorphization was observed by 0.22 dpa for a single crystal sample and ~ 0.52 dpa for a polycrystalline sample. DFT calculations were performed for trivalent actinide analogs of Rb₃M(PO₄)₂ (M = Am, Cm), and the results indicated high tolerance to radiation damage.

Burakov *et al.*¹⁶¹ studied radiation resistance effects, including amorphization, of different crystalline host phases on



Pu storage to simulate the effects of long-term disposal. The study included Pu-doped cubic zirconia ($Zr_{0.79}Gd_{0.14}Pu_{0.07}O_{1.99}$), monazites [(La,Pu)PO₄, PuPO₄, and (Eu,Pu)PO₄], zircon [(Zr,Pu)SiO₄], and pyrochlore [(Ca,Gd,Hf,Pu,U)₂Ti₂O₇]. The (La,Pu)PO₄ and PuPO₄ monazites remained crystalline until receiving cumulative doses of $1.19 \times 10^{25} \alpha \text{ m}^{-3}$ and $4.2 \times 10^{24} \alpha \text{ m}^{-3}$.

4.4 Optical properties and applications

Several studies have documented the study of optical properties of REPO₄ compounds, including optical spectroscopy^{171,172} and Raman spectroscopy.^{173–175} Hernández and Martín¹⁷² studied the ultraviolet-visible-near-infrared (UV-Vis-NIR, *i.e.*, 200–3000 nm) absorption spectra of EuPO₄. Absorption spectra show low to medium absorption within the $\lambda = 400\text{--}1700$ nm region of the spectrum (Vis-NIR) but high absorptions in the UV ($\lambda < 400$ nm) and NIR ($\lambda > 1700$ nm). They noted that the absorption spectra remained unchanged, even after 18 kGy irradiation with ⁶⁰Co. Studies have shown the utility of doped REPO₄ compounds to function as scintillators when exposed to X-rays or γ -rays.¹ Examples of these types of materials include LuPO₄:Ce,¹⁷⁶ LuPO₄:Nd,¹⁷⁷ YPO₄:Nd,¹⁷⁷ as well as Sm-doped or Eu-doped YPO₄, ScPO₄, and LuPO₄.¹⁷⁸ REPO₄ compounds can also be used as thermophosphors to provide a remote-sensing probe for temperature determination, which was demonstrated using LuPO₄: (Dy,Eu).^{24,25} An example of where this would have utility is where it is not practical to use metal thermocouples, *e.g.*, remote sensors within a microwave environment.

5 Future work and perspectives

After considering the wealth of data collected on the wide range of anhydrous REPO₄ compounds discussed within this paper, more work is needed to fill in research gaps summarized within this section. Additional thoughts and perspectives are provided throughout where future work could be done.

Regarding mechanical properties, extensive datasets are available for *E*, *B*, and *G* while several experimental gaps exist in datasets for *H* and FS (see Table 5). Many of the datasets from single studies do not correlate well with data from other studies or measured data fall far from calculated data (see Fig. 7), leading to difficulty in making accurate predictions in some cases. Gaps exist in the thermal properties for the different series (Table 6) and the data spread across literature values for single properties of a given REPO₄ compound tends to be rather high in some cases. For one dataset of calculated CTE values, the spread was very low (see Fig. 8), but that was anomalous against the entire set of summarized data. Two of the most populated datasets include *C_p* and CTE. More work needs to be done to better elucidate the variabilities in these properties across the full RE dataset.

Since APO₄ compounds are promising as stable options for long-term disposal of radionuclides, including rare earths and actinides, more detailed studies on their chemical durabilities are needed. The normalized release rates (NR_{*i*}) for tested REPO₄ compounds show very low values (Table 7) as compared to other

nuclear waste forms, such as borosilicate glass. Understanding potential incongruent elemental release from these compounds is important, including comparisons between NR_P and NR_{RE} over long time scales under dilute conditions.

While some radiation stability tests have been documented in the literature for REPO₄ compounds (see Table 8 for examples), additional studies are needed. This includes wider compositional ranges as well as more high-energy exposure studies (*e.g.*, γ -rays). Several studies have demonstrated amorphization doses for a variety of REPO₄ compounds and types of irradiations. A study by Nasdala *et al.*¹⁷⁹ provided evidence that α -assisted annealing can prevent irradiation-induced amorphization in CePO₄ monazite, but only above a specific damage level. Understanding how REPO₄ compounds behave in potential geological repository environments and the transition of REPO₄ compounds to the hydrated (*i.e.*, rhabdophane or REPO₄·*x*H₂O) forms is very important from a waste form perspective for long-term disposal.

An overview of DFT-based first principles calculations on mechanical, structural, and thermodynamic properties was briefly covered due to the effectiveness of the method to predict the structures and properties of this class of materials. It was found that the usage of the DFT + *U* method^{180,181} to treat *f* electrons in RE elements was essential to improve the description of both structures and properties. More work can be done to study defect formation energies and mixing of RE elements in REPO₄ compounds using first principles methods. First principles calculations can also be used to study high-entropy monazite-based or xenotime-based ceramics formation and properties through mixing of various RE elements. In addition, classical molecular dynamics (MD) simulations can be used to study radiation effects and thermomechanical behaviors.¹⁸² Recent advances using machine learning potentials¹⁸³ based on first principles calculations can help to alleviate the bottleneck of interatomic potential availability. However, extensive testing and validation of these new potentials will be needed. Combining these techniques, one can expect computational methods to provide valuable information regarding the distribution of RE elements within the crystal lattice, the role of dopants in controlling properties, radiation induced structural change and amorphization, and the mechanisms governing phase transformations under extreme conditions.

With the rapid development of applying machine learning techniques in material science,¹⁸⁴ the integration of predictive models and machine learning holds transformative potential across various applications of REPO₄ compounds.^{185–187} These models can be utilized to predict properties such as phase stability, mechanical behavior, and chemical reactivity under various/extreme conditions. Future efforts, including constructing a more consistent dataset including trace elements, developing high-throughput parallel simulation routines, and standardizing characterization methods, would greatly benefit the implementation of machine learning in studying monazite and xenotime composition–structure–property relationships. By training models on experimental and/or simulation data, researchers can extrapolate insights beyond the limits of



traditional analysis, guiding experimental design and hypothesis generation.

6 Summary and conclusions

The synthesis methods, crystal structures, and properties of anhydrous monazite and xenotime crystalline materials are summarized within this review. Monazite and xenotime compounds can be synthesized with a variety of different methods including flux-assisted, solid state, hydrothermal, aqueous, dehydration, and gel-based methods. For both monazite and xenotime structures, with larger and lighter RE cations in the crystal structure, the unit cell parameters (*i.e.*, *a*, *b*, *c*) and volumes (*V*) increase linearly whereas the densities (ρ) decrease nonlinearly. Similar trends were observed for solid solution compounds containing mixed RE cations. Some solid solutions containing RE cations with large difference in sizes (*e.g.*, La and Yb) showed the presence of both monazite and xenotime phases. For RE cations, the distortions of REO_x polyhedra were greater in monazites when compared to xenotimes. Decreasing RE radii increased the Young's modulus, bulk modulus, and shear modulus, and this can be due to stronger interatomic bonding as the average RE–O distances decreased with smaller RE cations. Different modulus values from different studies are also affected by different sample preparation and sintering conditions for the pellets. In general, the CTE values of monazite compounds seem to increase with the larger RE cations and RE–O distances in the structures. The calculated CTE values usually followed the trends, but the experimental CTE values from different studies often varied greatly, and it was difficult to create a general trendline. First-principles DFT calculations have been shown to be a reliable predictive method for both the structures and properties of monazite and xenotime crystals, although care was needed in the description of the f-electrons and the DFT + *U* method was found to be reliable and computationally feasible approach for this purpose. The chemical and radiation resistance of monazite and xenotime are similar to that of zircon, and thus the natural minerals are often used in geochronology. Monazite compounds are generally more resistant to irradiation damage compared to the xenotime compounds.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The information, data, or work presented herein was funded in part by the Advanced Research Projects Agency-Energy (ARPA-E), U.S. Department of Energy, under Award Number DE-AR0001613. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof. Pacific Northwest National Laboratory (PNNL) is operated by Battelle Memorial Institute for the DOE under contract DE-AC05-76RL01830. Authors thank John Vienna (PNNL) for helpful comments.

References

- 1 L. A. Boatner, *Rev. Mineral. Geochem.*, 2002, **48**, 87–121.
- 2 R. P. Rapp and E. B. Watson, *Contrib. Mineral. Petrol.*, 1986, **94**, 304–316.
- 3 A. Kumari, R. Panda, M. K. Jha, J. R. Kumar and J. Y. Lee, *Miner. Eng.*, 2015, **79**, 102–115.
- 4 L. Richter, L. W. Diamond, P. Atanasova, D. A. Banks and J. Gutzmer, *Geology*, 2018, **46**, 263–266.
- 5 M. Rabiei, G. Chi, C. Normand, W. J. Davis, M. Fayek and N. J. Blamey, *Econ. Geol.*, 2017, **112**, 1483–1507.
- 6 H.-J. Förster, *Am. Mineral.*, 1998, **83**, 259–272.
- 7 C. J. Hetherington, D. E. Harlov and B. Budzyń, *Mineral. Petrol.*, 2010, **99**, 165–184.
- 8 C. J. Hetherington, M. J. Jercinovic, M. L. Williams and K. Mahan, *Chem. Geol.*, 2008, **254**, 133–147.
- 9 A. Berger, E. Gnos, E. Janots, A. Fernandez and J. Giese, *Chem. Geol.*, 2008, **254**, 238–248.
- 10 R. G. Jonasson and E. R. Vance, *Thermochim. Acta*, 1986, **108**, 65–72.
- 11 B. Glorieux, M. Matecki, F. Fayon, J. P. Coutures, S. Palau, A. Douy and G. Peraudeau, *J. Nucl. Mater.*, 2004, **326**, 156–162.
- 12 R. C. Ewing and W. Lutze, *Ceram. Int.*, 1991, **17**, 287–293.
- 13 E. H. Oelkers and J.-M. Montel, *Elements*, 2008, **4**, 113–116.
- 14 N. Clavier, R. Podor and N. Dacheux, *J. Eur. Ceram. Soc.*, 2011, **31**, 941–976.
- 15 L. A. Boatner, G. W. Beall, M. M. Abraham, C. B. Finch, P. G. Huray and M. Rappaz, in *Scientific Basis for Nuclear Waste Management*, ed. C. J. M. Northrup, Springer US, Boston, MA, 1980, DOI: [10.1007/978-1-4684-3839-0_35](https://doi.org/10.1007/978-1-4684-3839-0_35), pp. 289–296.
- 16 A. I. Orlova, *J. Nucl. Mater.*, 2022, **559**, 153407.
- 17 M. R. Rafiuddin, G. Donato, S. McCaugherty, A. Mesbah and A. P. Grosvenor, *ACS Omega*, 2022, **7**, 39482–39490.
- 18 S. Chong, B. J. Riley and Z. J. Nelson, *J. Rare Earths*, 2021, **40**, 365–380.
- 19 B. J. Riley, *Ind. Eng. Chem. Res.*, 2020, **59**, 9760–9774.
- 20 B. J. Riley, J. McFarlane, G. D. DelCul, J. D. Vienna, C. I. Contescu and C. W. Forsberg, *Nucl. Eng. Des.*, 2019, **345**, 94–109.
- 21 Z. Wang, J. Kim, L. Magermans, F. Corbella, I. Florea, E. Larquet, J. Kim and T. Gacoin, *Nanoscale*, 2021, **13**, 16968–16976.
- 22 N. Hashimoto, Y. Takada, K. Sato and S. Ibuki, *J. Lumin.*, 1991, **48–49**, 893–897.
- 23 Y. I. Jeon, L. K. Bharat and J. S. Yu, *J. Alloys Compd.*, 2015, **649**, 531–536.
- 24 S. W. Allison, L. A. Boatner and G. T. Gillies, *Appl. Opt.*, 1995, **34**, 5624–5627.
- 25 S. W. Allison, M. R. Cates, L. A. Boatner and G. T. Gillies, High Temperature Thermometric Phosphors for Use in a Temperature Sensor, *US Pat.*, 5730528A, 1998.
- 26 D.-H. Kuo and W. M. Kriven, *Mater. Sci. Eng., A*, 1996, **210**, 123–134.



- 27 P. E. D. Morgan, D. B. Marshall and R. M. Housley, *Mater. Sci. Eng., A*, 1995, **195**, 215–222.
- 28 E. E. Boakye, P. Mogilevsky, T. A. Parthasarathy, R. S. Hay, J. Welter and R. J. Kerans, *J. Am. Ceram. Soc.*, 2006, **89**, 3475–3480.
- 29 L. Boatner and B. Sales, in *Radioactive Waste Forms for the Future*, ed. R. C. Ewing and W. Lutze, North-Holland, New York, 1988, ch. 8, pp. 495–564.
- 30 R. Feigelson, *J. Am. Ceram. Soc.*, 1964, **47**, 257–258.
- 31 D. F. Mullica, W. O. Milligan, D. A. Grossie, G. W. Beall and L. A. Boatner, *Inorg. Chim. Acta*, 1984, **95**, 231–236.
- 32 M. Cao, C. Hu, Q. Wu, C. Guo, Y. Qi and E. Wang, *Nanotechnology*, 2005, **16**, 282.
- 33 X. Li and J. Ma, *J. Lumin.*, 2011, **131**, 1355–1360.
- 34 L. Perrière, D. Bregiroux, B. Naitali, F. Audubert, E. Champion, D. S. Smith and D. Bernache-Assollant, *J. Eur. Ceram. Soc.*, 2007, **27**, 3207–3213.
- 35 A. Hirsch, P. Kegler, I. Alencar, J. Ruiz-Fuertes, A. Shelyug, L. Peters, C. Schreinemachers, A. Neumann, S. Neumeier, H. P. Liermann, A. Navrotsky and G. Roth, *J. Solid State Chem.*, 2017, **245**, 82–88.
- 36 R. Khalili, A.-C. Larsson, V.-V. Telkki, P. Lantto and A. M. Kantola, *J. Solid State Chem.*, 2022, **311**, 123097.
- 37 N. Adelstein, B. S. Mun, H. L. Ray, P. N. Ross, J. B. Neaton and L. C. De Jonghe, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2011, **83**, 205104.
- 38 S. Sadhasivam and N. P. Rajesh, *Mater. Res. Bull.*, 2016, **74**, 117–123.
- 39 Y. Wang, J. Li, J. Wang, S. Han and Y. Guo, *J. Cryst. Growth*, 2010, **312**, 2779–2782.
- 40 D. F. Mullica, D. A. Grossie and L. A. Boatner, *J. Solid State Chem.*, 1985, **58**, 71–77.
- 41 J. M. Heuser, S. Neumeier, L. Peters, H. Schlenz, D. Bosbach and G. Deissmann, *J. Solid State Chem.*, 2019, **273**, 45–52.
- 42 A. P. Gysi and D. Harlov, *Chem. Geol.*, 2021, **567**, 120072.
- 43 A. P. Gysi, D. Harlov, D. C. Filho and A. E. Williams-Jones, *Thermochim. Acta*, 2016, **627–629**, 61–67.
- 44 L. A. Boatner, K. B. Helean, A. Navrotsky and S. V. Ushakov, *J. Mater. Res.*, 2001, **16**, 2623–2633.
- 45 D. F. Mullica, D. A. Grossie and L. A. Boatner, *Inorg. Chim. Acta*, 1985, **109**, 105–110.
- 46 F. Poitrasson, E. Oelkers, J. Schott and J.-M. Montel, *Geochim. Cosmochim. Acta*, 2004, **68**, 2207–2221.
- 47 A. Mesbah, N. Clavier, E. Elkaim, S. Szenknect and N. Dacheux, *J. Solid State Chem.*, 2017, **249**, 221–227.
- 48 E. E. Boakye, P. Mogilevsky, R. S. Hay and G. E. Fair, *J. Am. Ceram. Soc.*, 2008, **91**, 3841–3849.
- 49 R. D. Shannon, *Acta Crystallogr., Sect. A*, 1976, **32**, 751–767.
- 50 F. Weigel, V. Scherer and H. Henschel, *J. Am. Ceram. Soc.*, 1965, **48**, 383–384.
- 51 Y. Ni, J. M. Hughes and A. N. Mariano, *Am. Mineral.*, 1995, **80**, 21–26.
- 52 G. B. Callejas, M. Cabrera, S. Prieto, O. Luna, I. Choque and V. Crespo, *Rev. Boliv. Quim.*, 2000, **17**, 22–27.
- 53 K. Ghouse, *Indian J. Pure Appl. Phys.*, 1968, **6**, 265–268.
- 54 R. C. L. Mooney, *J. Chem. Phys.*, 1948, **16**, 1003.
- 55 M. P. Kokkoros, *Prakt. Akad. Athenon*, 1942, **17**, 163–174.
- 56 T. Ueda, in *Memoirs of the College of Science, University of Kyoto, Series B*, 1953, vol. 20, pp. 227–246.
- 57 T. Ueda, *J. Jpn. Assoc. Mineral., Petrol. Econ. Geol.*, 1967, **58**, 170–179.
- 58 M. M. Zaman and S. M. Antao, *Minerals*, 2021, **11**, 16.
- 59 G. W. Beall, L. A. Boatner, D. F. Mullica and W. O. Milligan, *J. Inorg. Nucl. Chem.*, 1981, **43**, 101–105.
- 60 S. Bevara, K. K. Mishra, S. J. Patwe, T. R. Ravindran, M. K. Gupta, R. Mittal, P. S. R. Krishna, A. K. Sinha, S. N. Achary and A. K. Tyagi, *Inorg. Chem.*, 2017, **56**, 3335–3348.
- 61 K. M. Kurbanov, V. A. Efremov and V. P. Orlovskij, *Kristallografiya*, 1986, **31**, 800–802.
- 62 P. Halappa, A. Mathur, M.-H. Delville and C. Shivakumara, *J. Alloys Compd.*, 2018, **740**, 1086–1098.
- 63 K. M. Heffernan, N. L. Ross, E. C. Spencer and L. A. Boatner, *J. Solid State Chem.*, 2016, **241**, 180–186.
- 64 S. Rodriguez-Liviano, A. I. Becerro, D. Alcántara, V. Grazú, J. M. de la Fuente and M. Ocaña, *Inorg. Chem.*, 2013, **52**, 647–654.
- 65 J. Coing-Boyat, F. Sayetat and A. Apostolov, *J. Phys.*, 1975, **36**, 1165–1174.
- 66 W. O. Milligan, D. F. Mullica, G. W. Beall and L. A. Boatner, *Inorg. Chim. Acta*, 1983, **70**, 133–136.
- 67 J. López-Solano, P. Rodríguez-Hernández, A. Muñoz, O. Gomis, D. Santamaria-Perez, D. Errandonea, F. J. Manjón, R. S. Kumar, E. Stavrou and C. Raptis, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, **81**, 144126.
- 68 W. Schäfer, *Eine Apparatur für polarisierte Neutronen und Neutronenbeugungsuntersuchungen im System DyXO₄ (X = P, V, As)*, *Publikationen vor 2000, Kernforschungsanlage Jülich*, Verlag Jülich, 1972.
- 69 Z. Khadraoui, C. Bouzidi, K. Horchani-Naifer and M. Ferid, *J. Alloys Compd.*, 2014, **617**, 281–286.
- 70 S. Skanthakumar, C. K. Loong, L. Soderholm, J. W. Richardson, M. M. Abraham and L. A. Boatner, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1995, **51**, 5644–5648.
- 71 O. Gomis, B. Lavina, P. Rodríguez-Hernández, A. Muñoz, R. Errandonea, D. Errandonea and M. Bettinelli, *J. Phys.: Condens. Matter*, 2017, **29**, 095401.
- 72 E. Patscheke, H. Fuess and G. Will, *Chem. Phys. Lett.*, 1968, **2**, 47–50.
- 73 W. Milligan, D. Mullica, G. Beall and L. Boatner, *Acta Crystallogr., Sect. C: Cryst. Struct. Commun.*, 1983, **39**, 23–24.
- 74 V. G. Lohmüller, G. Schmidt, B. Deppisch, V. Gramlich and C. Scheringer, *Acta Crystallogr., Sect. B: Struct. Crystallogr. Cryst. Chem.*, 1973, **29**, 141–142.
- 75 S. J. Patwe, S. N. Achary and A. K. Tyagi, *Am. Mineral.*, 2009, **94**, 98–104.
- 76 W. O. Milligan, D. F. Mullica, G. W. Beall and L. A. Boatner, *Inorg. Chim. Acta*, 1982, **60**, 39–43.
- 77 M. Strada and G. Schwendimann, *Gazz. Chim. Ital.*, 1934, **64**, 662–674.
- 78 I. Krstanovic, *Z. Kristallogr.*, 1965, **121**, 315–316.
- 79 L. Vegard, *London, Edinburgh Dublin Philos. Mag. J. Sci.*, 1927, **4**, 511–525.



- 80 F. Angiuli, F. Mezzadri and E. Cavalli, *J. Solid State Chem.*, 2011, **184**, 1843–1849.
- 81 R. Mooney, *Acta Crystallogr.*, 1956, **9**, 677–678.
- 82 J.-E. Jørgensen, B. Lundtoft and S. E. Rasmussen, *Powder Diffr.*, 1993, **8**, 164–167.
- 83 R. Mi, J. Chen, Y.-g. Liu, M. Fang, L. Mei, Z. Huang, B. Wang and C. Zhaob, *RSC Adv.*, 2016, **6**, 28887–28894.
- 84 W. Baur, *Acta Crystallogr., Sect. B: Struct. Crystallogr. Cryst. Chem.*, 1974, **30**, 1195–1215.
- 85 C. Giacovazzo, *Fundamentals of Crystallography*, Oxford university press, USA, 2002.
- 86 R. Hoppe, *Z. Kristallogr. - Cryst. Mater.*, 1979, **150**, 23–52.
- 87 R. Hoppe, S. Voigt, H. Glaum, J. Kissel, H. P. Müller and K. Bernet, *J. Less-Common Met.*, 1989, **156**, 105–122.
- 88 R. De Biasi, A. Fernandes and J. Oliveira, *J. Appl. Crystallogr.*, 1987, **20**, 319–320.
- 89 O. Terra, N. Clavier, N. Dacheux and R. Podor, *New J. Chem.*, 2003, **27**, 957–967.
- 90 B. Van Emden, M. Thornber, J. Graham and F. Lincoln, *Advances in X-Ray Analysis-The Proceedings of the Denver X-ray Conferences*, 1996, pp. 2–15.
- 91 A. Thust, Y. Arinicheva, E. Haussühl, J. Ruiz-Fuertes, L. Bayarjargal, S. C. Vogel, S. Neumeier and B. Winkler, *J. Am. Ceram. Soc.*, 2015, **98**, 4016–4021.
- 92 Y. Arinicheva, A. Bukaemskiy, S. Neumeier, G. Modolo and D. Bosbach, *Prog. Nucl. Energy*, 2014, **72**, 144–148.
- 93 R. S. Hay, E. E. Boakye and P. Mogilevsky, *J. Eur. Ceram. Soc.*, 2014, **34**, 773–781.
- 94 A. C. Strzelecki, M. Reece, X. Zhao, W. Yu, C. Benmore, Y. Ren, C. Alcorn, A. Migdisov, H. Xu and X. Guo, *ACS Earth Space Chem.*, 2022, **6**, 1375–1389.
- 95 B. Xiao, H. Lösch, N. Huittinen and M. Schmidt, *Chem.-Eur. J.*, 2018, **24**, 13368–13377.
- 96 M. R. Rafiuddin, E. Mueller and A. P. Grosvenor, *J. Phys. Chem. C*, 2014, **118**, 18000–18009.
- 97 R. Podor and M. Cuney, *Am. Mineral.*, 1997, **82**, 765–771.
- 98 D. B. Kitaev, Y. F. Volkov and A. I. Orlova, *Radiochem*, 2004, **46**, 211–217.
- 99 J.-M. Montel, J.-L. Devidal and D. Avignant, *Chem. Geol.*, 2002, **191**, 89–104.
- 100 R. Podor, M. Cuney and T. C. Nguyen, *Am. Mineral.*, 1995, **80**, 1261–1268.
- 101 P. E. Raison, R. Jardin, D. Bouëxière, R. J. M. Konings, T. Geisler, C. C. Pavel, J. Rebizant and K. Popa, *Phys. Chem. Miner.*, 2008, **35**, 603–609.
- 102 A. Tabuteau, M. Pagès, J. Livet and C. Musikas, *J. Mater. Sci. Lett.*, 1988, **7**, 1315–1317.
- 103 O. Terra, N. Dacheux, N. Clavier, R. Podor and F. Audubert, *J. Am. Ceram. Soc.*, 2008, **91**, 3673–3682.
- 104 E. Gardés, O. Jaoul, J.-M. Montel, A.-M. Seydoux-Guillaume and R. Wirth, *Geochim. Cosmochim. Acta*, 2006, **70**, 2325–2336.
- 105 L. Schwarz, B. Finke, M. Kloss, A. Rohmann, U. Sasum and D. Haberland, *J. Lumin.*, 1997, **72–74**, 257–259.
- 106 A. I. Orlova, D. B. Kitaev, N. G. Kazantsev, S. G. Samoïlov, V. S. Kurazhkovskaya and E. N. Vopilina, *Radiochem*, 2002, **44**, 326–331.
- 107 A. T. Aldred, in *Geochemical Behavior of Disposed Radioactive Waste*, American Chemical Society, 1984, vol. 246, ch. 18, pp. 305–314.
- 108 O. Muller and R. Roy, in *The Major Ternary Structural Families*, Springer, 1974, vol. 4, p. 143.
- 109 O. Fukunaga and S. Yamaoka, *Phys. Chem. Miner.*, 1979, **5**, 167–177.
- 110 J. P. Bastide, *J. Solid State Chem.*, 1987, **71**, 115–120.
- 111 R. J. Finch and J. M. Hanchar, *Rev. Mineral. Geochem.*, 2003, **53**, 1–25.
- 112 D. Errandonea and F. J. Manjón, *Prog. Mater. Sci.*, 2008, **53**, 711–773.
- 113 M. K. Carron, M. E. Mrose and K. J. Murata, *Am. Mineral.*, 1958, **43**, 985–989.
- 114 B. J. Macey, Masters thesis, Virginia Tech, 1995.
- 115 R. S. Hay, P. Mogilevsky and E. Boakye, *Acta Mater.*, 2013, **61**, 6933–6947.
- 116 U. Kolitsch and D. Holtstam, *Eur. J. Mineral.*, 2004, **16**, 117–126.
- 117 A. Du, C. Wan, Z. Qu and W. Pan, *J. Am. Ceram. Soc.*, 2009, **92**, 2687–2692.
- 118 K. Kenges, O. Proskurina, D. Danilovich, M. Aldabergenov and V. Gusarov, *Russ. J. Appl. Chem.*, 2018, **91**, 1538–1548.
- 119 J. Feng, B. Xiao, R. Zhou and W. Pan, *Acta Mater.*, 2013, **61**, 7364–7383.
- 120 P. M. Kowalski and Y. Li, *J. Eur. Ceram. Soc.*, 2016, **36**, 2093–2096.
- 121 H. Li, S. Zhang, S. Zhou and X. Cao, *Inorg. Chem.*, 2009, **48**, 4542–4548.
- 122 P. E. Morgan and D. B. Marshall, *J. Am. Ceram. Soc.*, 1995, **78**, 1553–1563.
- 123 Y. Hikichi, T. Ota and T. Hattori, *Mineral. J.*, 1997, **19**, 123–130.
- 124 T. M. Wilkinson, D. Wu, M. A. Musselman, N. Li, N. Mara and C. E. Packard, *Mater. Sci. Eng., A*, 2017, **691**, 203–210.
- 125 J. Han, Y. Wang, R. Liu and F. Wan, *Sci. Rep.*, 2020, **10**, 13681.
- 126 Y. Hikichi, T. Ota, K. Daimon, T. Hattori and M. Mizuno, *J. Am. Ceram. Soc.*, 1998, **81**, 2216–2218.
- 127 F. Zhang, J. Wang, M. Lang, J. Zhang, R. C. Ewing and L. A. Boatner, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2009, **80**, 184114.
- 128 K. Popa and R. J. M. Konings, *Thermochim. Acta*, 2006, **445**, 49–52.
- 129 Y. Hikichi and T. Nomura, *J. Am. Ceram. Soc.*, 1987, **70**, C-252–C-253.
- 130 Y. Ji, G. Beridze, D. Bosbach and P. M. Kowalski, *J. Nucl. Mater.*, 2017, **494**, 172–181.
- 131 T. Deepthi and K. Balamurugan, *Ceram. Int.*, 2019, **45**, 18229–18235.
- 132 A. Blanca Romero, P. M. Kowalski, G. Beridze, H. Schlenz and D. Bosbach, *J. Comput. Chem.*, 2014, **35**, 1339–1346.
- 133 G. Beridze, A. Birnie, S. Koniski, Y. Ji and P. M. Kowalski, *Prog. Nucl. Energy*, 2016, **92**, 142–146.
- 134 R. G. Jonasson, G. M. Bancroft and H. W. Nesbitt, *Geochim. Cosmochim. Acta*, 1985, **49**, 2133–2139.
- 135 N. Clavier, DSc thesis, Université Paris Sud-Paris XI, 2004.



- 136 E. Du Fou de Kerdaniel, N. Clavier, N. Dacheux, O. Terra and R. Podor, *J. Nucl. Mater.*, 2007, **362**, 451–458.
- 137 E. H. Oelkers and F. Poitrasson, *Chem. Geol.*, 2002, **191**, 73–87.
- 138 G. J. McCarthy, W. B. White and D. E. Pfoertsch, *Mater. Res. Bull.*, 1978, **13**, 1239–1245.
- 139 B. C. Sales, C. W. White and L. A. Boatner, *Nucl. Chem. Waste Manage.*, 1983, **4**, 281–289.
- 140 Y. Teng, P. Zeng, Y. Huang, L. Wu and X. Wang, *J. Nucl. Mater.*, 2015, **465**, 482–487.
- 141 C. Gausse, S. Szenknect, A. Mesbah, N. Clavier, S. Neumeier and N. Dacheux, *Appl. Geochem.*, 2018, **93**, 81–93.
- 142 E. Du Fou de Kerdaniel, DSc thesis, Université Paris Sud-Paris XI, 2007.
- 143 O. Terra, N. Dacheux, F. Audubert and R. Podor, *J. Nucl. Mater.*, 2006, **352**, 224–232.
- 144 N. Clavier, N. Dacheux, G. Wallez and M. Quarton, *J. Nucl. Mater.*, 2006, **352**, 209–216.
- 145 M. R. Rafiuddin and A. P. Grosvenor, *J. Nucl. Mater.*, 2018, **509**, 631–643.
- 146 D. J. Wronkiewicz, S. F. Wolf and T. S. DiSanto, *Mater. Res. Soc.*, 1995, **412**, 345–352.
- 147 ASTM C1285-21, *Standard Test Methods for Determining Chemical Durability of Nuclear, Hazardous, and Mixed Waste Glasses and Multiphase Glass Ceramics: The Product Consistency Test (PCT)*, 2021.
- 148 ASTM C1663-18, *Standard Test Method for Measuring Waste Glass or Glass Ceramic Durability by Vapor Hydration Test (VHT)*, 2018.
- 149 EPA, *SW-846 Test Method 1311: Toxicity Characteristic Leaching Procedure*, 1992.
- 150 F. Poitrasson, S. Chenery and T. J. Shepherd, *Geochim. Cosmochim. Acta*, 2000, **64**, 3283–3297.
- 151 P. Mikhailova, B. Burakov, N. Eremin, A. Averin and A. Shiryaev, *Sustainab*, 2021, **13**, 1203.
- 152 B. I. Omel'yanenko, T. S. Livshits, S. V. Yudintsev and B. S. Nikonov, *Geol. Ore Deposits*, 2007, **49**, 173–193.
- 153 L. Nasdala, S. Akhmadaliev, A. Artac, C. Chanmuang N, G. Habler and C. Lenz, *Phys. Chem. Miner.*, 2018, **45**, 855–871.
- 154 A.-M. Seydoux-Guillaume, X. Deschanel, C. Baumier, S. Neumeier, W. J. Weber and S. Peuguet, *Am. Mineral.*, 2018, **103**, 824–827.
- 155 A. Meldrum, R. C. Ewing and L. A. Boatner, *Mineral. Mag.*, 2000, **64**, 185–194.
- 156 L. Nasdala, M. Wenzel, G. Vavra, G. Irmer, T. Wenzel and B. Kober, *Contrib. Mineral. Petrol.*, 2001, **141**, 125–144.
- 157 M. R. Rafiuddin and A. P. Grosvenor, *J. Alloys Compd.*, 2015, **653**, 279–289.
- 158 V. S. Urusov, A. E. Grechanovsky and N. N. Eremin, *Glass Phys. Chem.*, 2012, **38**, 55–62.
- 159 A. Meldrum, L. A. Boatner, W. J. Weber and R. C. Ewing, *Geochim. Cosmochim. Acta*, 1998, **62**, 2509–2520.
- 160 G. R. Lumpkin and T. Geisler-Wierwille, in *Comprehensive Nuclear Materials*, ed. R. J. M. Konings, Elsevier, Oxford, 2012, pp. 563–600, DOI: DOI: [10.1016/B978-0-08-056033-5.00111-7](https://doi.org/10.1016/B978-0-08-056033-5.00111-7).
- 161 B. E. Burakov, V. M. Garbuzov, A. A. Kitsay, M. A. Yagovkina and V. A. Zirlin, *Mater. Res. Soc. Symp. Proc.*, 2004, **824**, CC4.
- 162 F. Lu, Y. Shen, X. Sun, Z. Dong, R. C. Ewing and J. Lian, *Acta Mater.*, 2013, **61**, 2984–2992.
- 163 M. R. Rafiuddin, A.-M. Seydoux-Guillaume, X. Deschanel, A. Mesbah, C. Baumier, S. Szenknect and N. Dacheux, *J. Nucl. Mater.*, 2020, **539**, 152265.
- 164 H. B. Tisdale, M. S. Christian, G. Morrison, T. M. Besmann, K. Sun, G. S. Was and H.-C. zur Loye, *Chem. Mater.*, 2022, **34**, 3819–3830.
- 165 A. M. Seydoux-Guillaume, R. Wirth, L. Nasdala, M. Gottschalk, J. M. Montel and W. Heinrich, *Phys. Chem. Miner.*, 2002, **29**, 240–253.
- 166 A.-M. Seydoux-Guillaume, R. Wirth, A. Deutsch and U. Schärer, *Geochim. Cosmochim. Acta*, 2004, **68**, 2517–2527.
- 167 D. Bregiroux, R. Belin, P. Valenza, F. Audubert and D. Bernache-Assollant, *J. Nucl. Mater.*, 2007, **366**, 52–57.
- 168 V. Picot, X. Deschanel, S. Peuguet, B. Glorieux, A. M. Seydoux-Guillaume and R. Wirth, *J. Nucl. Mater.*, 2008, **381**, 290–296.
- 169 X. Deschanel, A. M. Seydoux-Guillaume, V. Magnin, A. Mesbah, M. Tribet, M. P. Moloney, Y. Serruys and S. Peuguet, *J. Nucl. Mater.*, 2014, **448**, 184–194.
- 170 C. Overstreet, J. Cooper, E. O'Quinn, W. Cureton, R. Palomares, J. Leys, G. Deissmann, S. Neumeier, C.-H. Chen and M. Lang, *Nucl. Instrum. Methods Phys. Res., Sect. B*, 2022, **527**, 34–39.
- 171 A. N. Trukhin and L. A. Boatner, *13th Int. Conf. Defects Insul. Cryst. Mater. Sci. Forum*, vol. 239–241, 1997.
- 172 T. Hernández and P. Martín, *J. Eur. Ceram. Soc.*, 2007, **27**, 109–114.
- 173 G. M. Begun, G. W. Beall, L. A. Boatner and W. J. Gregor, *J. Raman Spectrosc.*, 1981, **11**, 273–278.
- 174 P. C. Becker, N. Edelstein, G. M. Williams, J. J. Bucher, R. E. Russo, J. A. Koningstein, L. A. Boatner and M. M. Abraham, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1985, **31**, 8102–8110.
- 175 P. C. Becker, G. M. Williams, N. M. Edelstein, J. A. Koningstein, L. A. Boatner and M. M. Abraham, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1992, **45**, 5027–5030.
- 176 A. Lempicki, E. Berman, A. J. Wojtowicz, M. Balcerzyk and L. A. Boatner, *IEEE Trans. Nucl. Sci.*, 1993, **40**, 384–387.
- 177 D. Wisniewski, S. Tavernier, A. J. Wojtowicz, M. Wisniewska, P. Bruyndonckx, P. Dorenbos, E. van Loef, C. W. E. van Eijk and L. A. Boatner, *Nucl. Instrum. Methods Phys. Res., Sect. A*, 2002, **486**, 239–243.
- 178 W. W. Moses, M. J. Weber, S. E. Derenzo, D. Perry, P. Berdahl and L. A. Boatner, *IEEE Trans. Nucl. Sci.*, 1988, **45**, 462–466.
- 179 L. Nasdala, S. Akhmadaliev, B. E. Burakov, C. Chanmuang N and R. Škoda, *Sci. Rep.*, 2020, **10**, 14676.
- 180 W. Sun and J. Du, *Comput. Mater. Sci.*, 2017, **126**, 326–335.
- 181 J. Du, R. Devanathan, L. René Corrales and W. J. Weber, *Comput. Theor. Chem.*, 2012, **987**, 62–70.
- 182 J. Du, M. Motorsi, S. Barbi and X. Lu, in *Atomistic Simulations of Glasses Fundamentals and Applications*, John



- Wiley & Sons Inc., 2022, pp. 367–438, DOI: [10.1002/9781118939079.ch12](https://doi.org/10.1002/9781118939079.ch12).
- 183 A. M. Miksch, T. Morawietz, J. Kästner, A. Urban and N. Artrith, *Mach. Learn.: Sci. Technol.*, 2021, **2**, 031001.
- 184 R. Ramprasad, R. Batra, G. Pilania, A. Mannodi-Kanakithodi and C. Kim, *npj Comput. Mater.*, 2017, **3**, 54.
- 185 E. Di Napoli, X. Wu, T. Bornhake and P. M. Kowalski, *Front. Appl. Math. Stat.*, 2024, **10**, 1355726.
- 186 G. H. Alférez, O. A. Esteban, B. L. Clausen and A. M. M. Ardila, *Earth Sci. Inform.*, 2022, **15**, 1683–1698.
- 187 K. Itano, K. Ueki, T. Iizuka and T. Kuwatani, *Geosci.*, 2020, **10**, 63.

