# **RSC** Advances



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2024, 14, 13719

Received 15th March 2024 Accepted 14th April 2024 DOI: 10.1039/d4ra01985g rsc.li/rsc-advances

# 1. Introduction

With the continuous advancement of urbanization and industrialization, environmental pollution and energy shortage problems are deteriorating.<sup>1-4</sup> Photocatalytic CO<sub>2</sub> reduction technology is an environmentally friendly clean fuel production technology, which can not only effectively reduce CO<sub>2</sub> emissions, but also alleviate the energy shortage problem.<sup>5-7</sup> However, common single semiconductor photocatalysts have defects such as wide bandgap, fast photogenerated carrier complexation rate, and low visible light utilization efficiency. Therefore, researchers have compensated for the shortcomings of single semiconductors by elemental doping, co-catalyst loading, and constructing heterojunctions to improve the activity of photocatalysts.<sup>8-11</sup> Precious metal nanoparticles (Au, Ag, Pt) are widely used in enhancing the photocatalytic activity of semiconductors due to their localized surface plasmon resonance properties.<sup>12,13</sup> Ag nanoparticles can

# Accelerating carrier separation to boost the photocatalytic CO<sub>2</sub> reduction performance of ternary heterojunction Ag $-Ti_3C_2T_x/ZnO$ catalysts<sup>†</sup>

Qilin Han,<sup>a</sup> Zhiyao Wu,<sup>a</sup> Yu Zhou,<sup>a</sup> Yongxin Lei,<sup>a</sup> Bingying Nie,<sup>a</sup> Leilei Yang,<sup>\*b</sup> Wenbin Zhong,<sup>a</sup> Nannan Wang<sup>b</sup>\*<sup>a</sup> and Yangiu Zhu<sup>b</sup><sup>a</sup>

Developing low-cost and efficient photocatalyst/co-catalyst systems that promote CO<sub>2</sub> reduction remains a challenge. In this work, Ag–Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> composites were made using a self-reduction technique, and unique Ag–Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub>/ZnO ternary heterojunction structure photocatalysts were created using an electrostatic selfassembly process. The photocatalyst's close-contact heterogeneous interface increases photogenerated carrier migration efficiency. The combination of Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> and Ag improves the adsorption active sites and reaction centers for ZnO, making it a key site for CO<sub>2</sub> adsorption and activation. The best photocatalysts had CO and CH<sub>4</sub> reduction efficiencies of 11.985 and 0.768  $\mu$ mol g<sup>-1</sup> h<sup>-1</sup>, respectively. The CO<sub>2</sub> conversion was 3.35 times better than that of pure ZnO, which demonstrated remarkable stability even after four cycle trials with no sacrificial agent. Furthermore, *in situ* diffuse reflectance infrared Fourier transform spectroscopy (*in situ* DRIFTS) and valence band spectroscopy were utilized to propose the photocatalytic reaction mechanism and electron transfer channels of the Ag–Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub>/ZnO system, confirming that CHO\* and CO\* are the important intermediates in the generation of CH<sub>4</sub> and CO. This study introduces a novel method for the development of new and efficient photocatalysts and reveals that Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> MXene is a viable co-catalyst for applications.

> enhance the photocatalytic activity by exciting the localized surface plasmon into the conduction band of the semiconductor material. However, the contact area between the metal nanoparticles and the semiconductor material is small, which is not conducive to electron migration and high carrier recombination efficiency. The development of low-cost and efficient photocatalyst/co-catalyst systems to enhance the photocatalytic reduction of  $CO_2$  remains a challenge.

> Two-dimensional transition metal carbide-nitride and carbon-nitride MXenes materials have attracted a remarkable amount of attention in the materials field since their discovery in 2011.14,15 They are produced by selective etching of metalbonded layered solids. Among the MXenes materials, the easiest to prepare and most widely used is  $Ti_3C_2T_x$ , which has metallic properties and a larger work function to improve the migration and separation efficiency of photogenerated carriers.16-18 Meanwhile, extensive surface-active sites and vacancies (Ti) are available on Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub>.<sup>19</sup> Research has shown that suitable metal atoms exposed to the photocatalyst surface can act as adsorption sites and reaction sites for CO<sub>2</sub>, which can accept photogenerated electrons from the photocatalyst and transfer them to the reactants  $(CO_2, H_2O, and intermediates)$  to carry out redox reactions with enhanced separation of photogenerated electrons from holes.<sup>20–23</sup> Therefore,  $Ti_3C_2T_x$  shows great potential for application as a photoredox co-catalyst in clean energy conversion. Hong et al.<sup>24</sup> prepared BiOIO<sub>3</sub>/g-C<sub>3</sub>N<sub>4</sub>

<sup>&</sup>lt;sup>a</sup>State Key Laboratory of Featured Metal Materials and Life-cycle Safety for Composite Structures, MOE Key Laboratory of New Processing Technology for Nonferrous Metals and Materials, School of Resources, Environment and Materials, Guangxi University, Nanning 530004, China. E-mail: wangnannan@gxu.edu.cn

<sup>&</sup>lt;sup>b</sup>College of Mathematics and Physics, Guangxi Minzu University, Nanning 530006, China. E-mail: yangllei@gxmzu.edu.cn

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: https://doi.org/10.1039/d4ra01985g

Z-type heterojunctions modified by  $Ti_3C_2$  nanosheets, which significantly enhanced the efficiency of photocatalytic generation of CO and  $CH_4$  by the formed Z-type heterojunctions as well as the modification of two-dimensional  $Ti_3C_2$  co-catalysts, and the CO yield was 6.6 times higher than that of bare g- $C_3N_4$ . The nanoscale materials with a larger specific surface area are more favorable for the preparation of MXene/semiconductor composites with strong interfacial contacts.

ZnO is a direct bandgap semiconductor with a bandgap width of 3.37 eV and has superior photocatalytic activity in the ultraviolet region, which means that most of the sunlight cannot be fully utilized, seriously affecting the photocatalytic efficiency of ZnO photocatalysts.<sup>25-27</sup> In addition, the rapid complexation of carriers is also an important reason hindering the improvement of the photocatalytic activity of ZnO. Therefore, for ZnO-based photocatalysts, expanding their visible light absorption range and promoting the separation of photogenerated electron-hole pairs can be beneficial to enhance their photocatalytic performance.26 The common pure ZnO in particle or rod form exhibited large size, fewer surface active sites, and poor photogenerated charge separation efficiency, which as a result led to poor photocatalytic performance.<sup>28</sup> Hence, in attempt to solve the above problems, the investigation was carried out to enhance the photocatalytic reduction performance by changing the morphology size of ZnO or adding various co-catalysts. Li et al.29 synthesized ZnS/ZnO hollow spherical heterojunction photocatalysts by fine control of the nano/microstructure. Local lattice distortion was introduced on the surface of hollow ZnS/ZnO microspheres to activate lattice oxygen and obtain additional active reaction sites. Moreover, the construction of ZnS/ZnO heterojunctions accelerated the separation of photo-promoted carriers and significantly enhanced the photocatalytic CO<sub>2</sub> reduction performance, and the photocatalysts showed a CO yield of up to 35.85  $\mu$ mol g<sup>-1</sup>  $h^{-1}$  under the irradiation of a 300 W xenon lamp.

In this work, Ag-Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> composites and Ag-Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub>/ZnO (ATZ) ternary heterojunction structure were prepared by utilizing Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> self-reducing properties and electrostatic selfassembly technique. The catalysts possessed superior photocatalytic activity. The construction of ternary heterojunction effectively enhanced the separation and migration of photogenerated carriers. The larger specific surface area of the twodimensional material and the exposed metal atoms on the surface provided more active sites for CO2 adsorption. Meanwhile, in the ATZ system, both Ag and  $Ti_3C_2T_x$  can be employed as electron traps to capture electrons in ZnO, accelerating the migration of photogenerated electron-hole pairs and enlarging the photocatalytic CO<sub>2</sub> reduction efficiency. We believe that this study will provide a new pathway for the preparation of highperformance semiconductor photocatalysts and new MXenebased composite photocatalysts.

## 2. Experimental

#### 2.1 Materials

 $Ti_3AlC_2$  powder (98 wt%) was obtained from China Forsman Technology Co., Ltd. LiF powder (98 wt%) was purchased from

Sinopharm Group Chemical Reagent Co., Ltd. Zinc acetate hexahydrate and hydrochloric acid were analytically pure reagents purchased from Guangdong Guanghua Technology Co., Ltd. Sodium hydroxide powder was purchased from Shanghai Aladdin Reagent Co., Ltd. Cetyltrimethylammonium bromide (CTAB) was an analytically pure reagent purchased from Tianjin Damao Chemical Reagent Factory. The water used in the experiments was ultrapure.

#### 2.2 Preparation of $Ti_3C_2T_x$ nanosheets

1 g of LiF was dispersed in 20 mL of HCl solution (9 M) in a polytetrafluoroethylene liner with uniform stirring for 10 min. Subsequently, 1 g of Ti<sub>3</sub>AlC<sub>2</sub> (MAX) powder was slowly added to the above solution in several portions, and the resulting mixed solution was stirred in an oil bath (36 °C) for 48 h. The solution was then washed by repeated centrifugation (8000 rpm, 5 min) until the pH was ≥6. After, the black precipitate was taken and freeze-dried for 48 h to obtain organoid Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> (MX).<sup>30</sup> The appropriate amount of deionized water was added to the MX powder and sonicated for 2–4 h under the environment of the ice water bath, followed by centrifugation at 8000 rpm for 5 min, and the dark-green supernatant was taken and dispensed into a Petri dish and freeze-dried for 72 h, to obtain the less-layered Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> nanosheets (MXns).

#### 2.3 Preparation of Ag– $Ti_3C_2T_x$

Ag–Ti<sub>3</sub>C<sub>2</sub>T<sub>*x*</sub> was prepared by the self-reduction strategy, which is abbreviated as *x*AT according to the difference in the mass percentage of Ag added, as follows. 20 mg MXns was taken into 20 mL of water and sonicated for 30 min, 2 mL of 0.05 mg mL<sup>-1</sup> of AgNO<sub>3</sub> solution was added to the solution, stirred for 6 h, and freeze-dried for 24 h to obtain 0.5AT. Different contents of Ag– Ti<sub>3</sub>C<sub>2</sub>T<sub>*x*</sub> were prepared by adjusting the volume of AgNO<sub>3</sub> solution (5 and 10 mL), which were distinguished as 1AT and 2AT.

#### 2.4 Preparation of ZnO nanoflower

5.96 g of Zn  $(NO_3)_2 \cdot 6H_2O$  was added into 45 mL of ultrapure and ultrasonicated for 10 min until it was completely dissolved to produce solution A. Then 2.4 g of NaOH was incorporated into 15 mL of water to produce liquor B. Subsequently, liquor B was injected into solution A, and the solution was stirred vigorously at 90 °C for 2 h to obtain the ZnO nanoflowers.

#### 2.5 Preparation of Ag–Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> MXene/ZnO

Ag-Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> MXene/ZnO composites were prepared by electrostatic self-assembly method. First, 200 mg of surfactant CTAB was added to 200 mL of deionized water and stirred thoroughly for 10 min, and then 30 mg of ZnO was added and stirred for 3 h to obtain solution 1. Under the action of ultrasonication, 5 mg of AT was sufficiently dispersed into 20 mL of water to form suspension 1. Suspension 1 was added into solution 1, stirred for 3 h, rinsed with water, and freeze-dried for 24 h. The ATZ composite sample was finally obtained. To better distinguish the samples, they were named xATZ (x denotes the mass percentage of Ag, x = 0.5, 1 and 2). The ZnO/Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> (ZT) composite samples were prepared in the same way to facilitate subsequent comparative testing.

#### 2.6 Characterization

The constituent elements of the material were analyzed using an X-ray diffraction instrument (XRD, Rigaku D/MAX 2500 V, Japan) equipped with Cu-Ka radiation on a Cu target at a wavelength of  $\lambda = 1.5406$  Å. The morphology and microstructure of the samples were analyzed using a field emission scanning electron microscope (SEM, Sigma 300, CARL ZEISS, Germany) and a transmission electron microscope (TEM, TecnaiF20, FEI, USA). The catalysts were further characterized for structural changes using Fourier Transform Infrared Spectroscopy (FTIR, Nicolet iS50, Thermo Fisher Scientific, USA) and Laser Raman Spectroscopy (Raman, inVia Rdflex, Renishaw, UK). Laser Raman spectra were recorded by a Leica DM2700 microscope at a wavelength of 512 nm and a maximum output power of 5 mW. The surface structure and surface charge transfer of the materials were analyzed using an X-ray photoelectron spectrometer (XPS, ESCALAB 250Xi, Thermo Fisher, USA). The N<sub>2</sub> adsorption-desorption isothermal curves were tested using an automated specific surface area analyzer (BET, ASAP 2020, Micromeritics, USA) and all the samples were Degassing was carried out at 150 °C for 12 h. UV-visible diffuse reflectance spectra in the range of 200-800 nm were recorded using a UV/Vis spectrophotometer (DRS, UV-3600Plus, SHI-MADZU, Japan). Photoluminescence spectra (PL, FL3C-111 TCSPC, HORIBA, Japan) was obtained to study carrier separation of samples.

#### 2.7 Photocatalytic CO<sub>2</sub> reduction reaction

The photocatalytic reduction of CO2 test was carried out in a photoreactor with a total capacity of 150 mL. Firstly, 10 mg of photocatalyst was homogeneously dispersed in 800 µL of ethanol solution, and then it was coated on a 2.5 cm  $\times$  2.5 cm glass slice, which was dried in a vacuum drying oven for 4 h. 20 mL of 0.1 M NaHCO3 solution was placed in the reaction cell, and the glass slice was placed on the high platform of the reactor to avoid contacting the solution. The top of the reaction cell was sealed with rubber clamps, and high-purity CO<sub>2</sub> was introduced into the reaction cell and bubbled for 30 min. Finally, the photocatalytic reduction test was completed under the irradiation of a 300 W xenon lamp (PLS-SXE300D, Perfectlight, China) with the light intensity of 100 mW cm $^{-2}$ . Recirculating water was passed through the entire reaction process to ensure a constant test temperature. After the photocatalytic reaction, a gas bag driven by a peristaltic pump was used to collect the gases in the photoreactor and injected into a gas chromatograph (GC-2014C, Shimadzu, Japan) for gas analysis, and the liquid products were filtered and then detected and analyzed by an autosampler (AOC-20i, Shimadzu, Japan).

#### 2.8 Photoelectrochemical measurements

The photocurrent response, electrochemical impedance spectra, and Mott–Schottky curves were tested using an electrochemical workstation with a three-electrode system (CHI660E, Chenhua, Shanghai, China). Pt electrode was used as the counter electrode and an Ag/AgCl electrode was used as the reference electrode. The working electrode was prepared as follows: 10 mg of sample was dispersed in 0.2 mL of anhydrous ethanol and 20  $\mu$ L of Nafion solution to form a uniform electrode slurry. 50  $\mu$ L of the dispersion was taken and coated on a 1 cm  $\times$  1 cm fluorine-doped tin oxide (FTO) conductive glass. A 300 W Xe lamp was used as a light source and 0.5 M Na2SO<sub>4</sub> was used as the electrolyte solution.

# 3. Results and discussion

#### 3.1 Synthesis, structure, and morphology

The preparation process of *x*ATZ ternary heterojunction composite photocatalyst is shown in Fig. 1. Initially, HCl and LiF were utilized for *in situ* etching, and the few-layer MXns were obtained after ultrasonication in an ice-water bath. The reaction equations are as follows:<sup>24</sup>

$$HCl + LiF = LiCl + HF$$
(1)

$$3HF + Ti_3AlC_2 = Ti_3C_2 + AlF_3 + 3/2H_2$$
(2)

MXns was homogeneously dispersed in water, and then AgNO<sub>3</sub> solution was added to produce ATZ composite photocatalysts loaded with singlet Ag on the surface of MXns, leveraging the strong reducing property of the MXns surface. Then, the cationic surfactant CTAB was used to make the ZnO precursor surface loaded with a positive charge. Owing to the negative electric properties of MXns and the opposite charge of ZnO, the combination of positive and negative charges synthesized the *x*ATZ composites by electrostatic self-assembly.<sup>20,31,32</sup>

The materials were analyzed morphologically using scanning electron microscopy. Fig. 2a shows the few-layer titanium carbide nanosheets (MXns) obtained from Ti<sub>3</sub>AlC<sub>2</sub> after HF etching and Li<sup>+</sup> intercalation, and continuous sonication in an ice-water bath for 2 h. The Ti<sub>3</sub>AlC<sub>2</sub> is a lumpy morphology with a delamination tendency, whereas the un-sonicated MX is an accordion-like shape with a large spacing of layers (Fig. S1<sup>+</sup>), which is a change in the morphological characteristics that are corroborated with the characterization results of XRD.14 The nanoflower-like ZnO was obtained after morphology adjustment, as shown in Fig. 2b. As shown in Fig. S2a,† different amounts of Ag clusters were burdened on the surface of MXns through the self-reduction of AgNO<sub>3</sub>, providing more active sites for CO<sub>2</sub> adsorption for the photocatalytic reduction process. The dispersion of Ag clusters on the MXns surface was further demonstrated by SEM-EDS. The AT and ZnO were coupled by electrostatic self-assembly strategy to form xATZ composite samples, and it can be observed from Fig. 2c that the ZnO nanoflowers were uniformly loaded onto the AT to form a lamellar stacked nanosheet state, which in turn increased its specific surface area.

The morphology and structure of the materials were further analyzed by transmission electron microscopy. From Fig. 2e, it can be observed that the nanoflowers and ultrathin nanosheets



Fig. 1 Schematic illustration of the synthesis of MZx composite.



Fig. 2 The SEM spectras of (a) MXns, (b) ZnO and (c) 1ATZ. (d) TEM image of 1ATZ. (e and f) HR-TEM images of 1ATZ. (g) Elemental mapping of O, Zn, Ti, and Ag.

#### Paper

are coupled while forming well-defined interfaces at the junctions, proving the successful preparation of the composite samples. The presence of ultrathin nanosheets indicates that Ti<sub>3</sub>AlC<sub>2</sub> is sufficiently exfoliated into few-layers of MXns. Fig. 2(e and f) show the HRTEM images of the 1ATZ, with lattice fringes with lattice spacings of 0.263 nm and 0.281 nm attributed to the MXns (0 11 0) crystal plane of MXns and (1 0 0) crystal plane of fibrillated zincite ZnO, respectively, consistent with XRD characterization.<sup>22,33</sup> In addition, the lattice spacing of 0.206 nm is consistent with the (2 0 0) crystalline plane of Ag, and the appearance of this lattice stripe proves the successful selfreduction of AgNO3 on the surface of MXns. The EDS elemental mapping of Ti, Zn, Ag, and O is shown in Fig. 2g, which further confirms the close contact and positional relationship of ZnO and AT in 1ATZ composite samples, and ZnO is tightly loaded on the AT substrate.

The crystal structure and physical phase characteristics of the material were analyzed by XRD. As shown in Fig. 3a, the changes in the physical phase composition of the titanium carbide material before and after etching were displayed. The diffraction peaks located at 39° attributed to the Al (104) facet gradually weakened after HF etching of Ti<sub>3</sub>AlC<sub>2</sub> (MAX), and the diffraction peaks almost completely disappeared when few/ monolayer MXns were formed, which proved the successful etching of the Al layer in Ti<sub>3</sub>AlC<sub>2</sub>.<sup>21</sup> The diffraction peak belonging to the (002) crystal plane is gradually shifted to the left from 9° to 5.9° after etching, and at the same time, its diffraction peak is broadened, which proves that the layer spacing of the material is gradually increased and the MXns is successfully prepared.34 As shown in Fig. 3b, the composite xAT after self-reducing Ag on the surface of MXns maintains the original skeleton of the two-dimensional material, indicating that the introduction of metallic Ag did not destroy the crystal structure of the raw material. However, no characteristic diffraction peaks about Ag appeared in the pattern, which may be due to the low content of added Ag and weak crystallinity. Fig. 3c shows the XRD diffraction pattern of the xATZ composite sample. By comparing the standard PDF cards, most of the diffraction peaks of xATZ coincide with the hexagonal structure of ZnO (Hexagonal, P63mc), and there are three strong diffraction peaks at 31.77°, 34.42°, and 36.26°, which correspond to the (100), (002), and (101) of the ZnO crystal faces (PDF#36-1451).<sup>35</sup> A characteristic peak belonging to the MXns (002) crystal plane appears at  $2\theta = 5.9^\circ$ , proving that the AT was successfully loaded onto ZnO.

FTIR spectroscopy can be used to analyze the spatial structure of the materials as well as the composition of the functional groups. As can be seen from Fig. 3d, all the samples have a broad absorption band at  $3600-3400 \text{ cm}^{-1}$ , which can be attributed to the stretching vibration of the –OH group.<sup>36,37</sup> Meanwhile, a weak characteristic peak appeared at 1640 cm<sup>-1</sup>, which was attributed to the deformation vibration absorption



Fig. 3 XRD patterns of (a) MXns, MX and Ti<sub>3</sub>AlC<sub>2</sub>, (b) MXns and xAT, (c) ZnO and xATZ. FT-IR spectra of (d) ZnO, MXns, and xATZ.

View Article Online Paper

peak of the hydroxyl group on the surface of ZnO, and the peak could be generated by the adsorbed hydroxyl group formed by the final dissociation of adsorbed water on the surface of ZnO.<sup>26</sup> The absorption bands observed in the range of 850–500 cm<sup>-1</sup> for all the composite photocatalysts can be attributed to the Zn– O vibration.<sup>26</sup> Also, a stretching vibrational absorption band at 480 cm<sup>-1</sup> attributed to the Ti–C part can be observed, indicating that the MXns are retained in the ZnO structure, in other words proving the successful synthesis of the *x*ATZ material.<sup>38</sup>

Raman spectroscopy was further used to investigate the crystal structure of the material. It can be observed in Fig. 4a that pure ZnO has distinct characteristic peaks at 100 and 438.2 cm<sup>-1</sup> corresponding to the high and low-frequency branches of the E2 mode (E2-high and E2-low).39 These two E2 modes attributed to oxygen sublattice and heavy-atom vibrations together constitute the representative characteristic peaks of the ZnO structure of the fibrillated zincite hexagonal crystals. The peaks located at 332.1 and 381.9  $\text{cm}^{-1}$ , on the other hand, are caused by the multiphonon scattering processes E<sub>2</sub>H–E<sub>2</sub>L and A1(TO) of ZnO crystals.40 However, spectral peaks that do not belong to the ZnO structure appear in the composite sample. Combined with the Raman spectra of MXns in Fig. 4b, results show that the characteristic peaks located at 153 cm<sup>-1</sup> and 209 cm<sup>-1</sup> are attributed to the in-plane vibrations of Ti and C atoms and the out-of-plane vibrations of Ti atoms.<sup>41</sup> The characteristic peaks at 403 cm<sup>-1</sup> and 612 cm<sup>-1</sup> are attributed to the in-plane vibrations of the surface groups of the Ti atoms and the out-of-plane vibrations of C atoms.<sup>41</sup> The presence of special Raman signals D and G peaks at 1350 cm<sup>-1</sup> and 1580 cm<sup>-1</sup> attributed to amorphous carbon, which are triggered by defects and lattice vibrations present in amorphous carbon, respectively.22 xATZ contains Raman signals of ZnO and MXns, which successful preparation of the composite proves the photocatalyst.

The elemental composition of the material as well as the surface electron migration was analyzed by X-ray photoelectron spectroscopy (XPS). As shown in Fig. S3,<sup>†</sup> four elements, C, O, Ti, and Zn, are present in the 1ATZ composite, where the presence of Ti is attributed to the presence of the MXns substrate, and no obvious Ag characteristic peaks are observed

in the full spectrograms due to the relatively low content of Ag. However, significant Ag signals are found in the analysis of 1AT, thus demonstrating the inclusion of five elements, C, O, Ti, Zn, and Ag, in 1ATZ as well as the successful synthesis of the composite photocatalyst. Charge correction is performed using C 1 s (284.8 eV) as the reference. Fig. 5a shows the highresolution spectrum of C 1s. In all materials, the characteristic peaks with binding energies located at the position of 284.8 eV are attributed to the C-C of surface amorphous carbon, and the peaks at 288.87 and 286.50 eV correspond to C=O and C-O-C, respectively.42 ZT and 1ATZ convolve a new peak close to the position of 281 eV (281.45 and 281.04 eV), which is attributed to the interaction between Ti and C interaction (Ti-C).43 In the high-resolution XPS spectra of 1ATZ on Ti, Fig. 5b, the characteristic peaks with binding energies located at 454.42, 455.14, 456.49, 458.94, 460.38, 461.17, 462.05, and 464.56 eV are fitted as C-Ti, Ti<sup>2+</sup>, Ti<sup>3+</sup>, Ti-O, C-Ti, Ti<sup>2+</sup>, Ti<sup>3+</sup>, and Ti-O.<sup>41</sup> The binding energy of Ti 2p in ZT is shifted towards lower energy compared to MXns, indicating that the concentration of electrons around MXns is elevated and electrons are transferred from ZnO to MXns. The signals of Ti 2p in 1ATZ are significantly reduced due to the low content of MXns in 1ATZ. The change in the position of the Ti 2p binding energy between 1ATZ and MXns indicated the presence of electron transfer to MXns, further confirming the direction of the electron transfer. The characteristic peaks about Ti in AT are shifted, further demonstrating the electron transfer and strong interaction between Ag and MXns (Fig. S4<sup>†</sup>).

In the high-resolution spectra of Zn 2p (Fig. 5c), the double peaks on pure ZnO are attributed to Zn  $2p^{3/2}$  (1021.36 eV) and Zn  $2p^{1/2}$  (1044.38 eV) with a spin–orbit splitting fraction of 23.0 eV, suggesting the presence of oxidation state of Zn<sup>2+</sup> in the near-surface region.<sup>44</sup> In the 1ATZ composite sample, both peaks are shifted towards higher binding energy (1021.36 eV towards 1021.48 eV and 1044.38 eV towards 1044.53 eV), indicating a decrease in the electron density around the Zn atom. The shift in the binding energy in the composite sample suggests that the electrons are transferred from ZnO to AT due to electronic coupling at the interface. Fig. 5d shows the high-resolution XPS spectra of Ag 3d in 1AT, which can be



Fig. 4 Raman spectra of (a) ZnO, 1ATZ, ZT, and xATZ, (b) MXns and xATZ composites samples.



Fig. 5 XPS spectras of ZnO, AT, ZT, and 1ATZ for (a) C 1s (b) Ti 2p (c) Zn 2p (d) Ag 3d.

observed that the binding energy spacing of Ag 3d is 6 eV, and the characteristic peaks with binding energies located at 367.48 and 373.48 eV are attributed to Ag  $3d_{5/2}$  and Ag  $3d_{3/2}$ , which indicates that the AT material shouts to contain metallic Ag and Ag<sup>+</sup>.<sup>45</sup> The presence of Ag<sup>+</sup> may be attributed to the fact that some of the AgNO<sub>3</sub> has not been reduced. Unfortunately, due to the low content of Ag in the 1ATZ composite, there is only a weak Ag signal in its spectrum (Fig. S5†).

The nitrogen adsorption–desorption curve can be used to characterize the specific surface area size and structural features of the material. From Fig. 6a, it is observed that the isotherm rises sharply in the high-pressure region and stagnates during the desorption process, forming a hysteresis line. As the relative pressure trends to 1, the curve closes and a reversible type IV isotherm for mesoporous solid generation appears,<sup>38,46</sup> demonstrating that 1ATZ, ZnO, and MXns have crack-like pores, which is consistent with the lamellar morphology of the materials. The hysteresis lines are both H3 type with no obvious saturated adsorption platform and irregular pore structure.<sup>47</sup> Possibly related to the stacking of flakes. The specific surface area and pore size of the samples were calculated using the BET and BJH models, and the results are shown in Fig. 6b and Table S1,<sup>†</sup> which show that 1ATZ has a larger specific surface area compared with the nano-flake MXns and nano-flower ZnO. Generally, a larger specific surface area provides more surface active sites and also facilitates the loading of other materials. Meanwhile, the average pore size of 1ATZ is smaller than ZnO, and the smaller pore size has a stronger adsorption capacity.

#### 3.2 Optical properties and energy band structure

The catalytic performance of the photocatalysts was evaluated by the yield of CO and  $CH_4$  in the photocatalytic  $CO_2$  reduction system. As shown in Fig. 7a, MXns are not active in  $CO_2$ photoreduction, the photocatalytic activity is activated by loading ZnO, and the photocatalytic yield is further improved by the reduction of Ag on the MXns surface. The pure ZnO photocatalytic reduction products are mainly CO and the yields of  $CH_4$  were relatively low, which were 3.577 and 1.145 µmol g<sup>-1</sup> h<sup>-1</sup>, respectively. The photocatalytic  $CO_2$  reduction is significantly enhanced when MXns was used as a co-catalyst for ZnO, and it is also observed that the relative content of Ag in MXns has a significant effect on the photocatalytic reduction products. From Fig. S6,† it is observed that the photocatalytic  $CO_2$  yield of *x*AT is relatively low, indicating that the photocatalytic activity



Fig. 6 (a)  $N_2$  adsorption-desorption isotherms and (b) pore size distribution of 1ATZ, ZnO, and MXns.

of *x*AT composites is low. The photocatalytic performance of the catalysts is significantly enhanced with the increase of the relative content of Ag. Due to the reduction of Ag on the surface of MXns, the AT has a stronger conductivity, which accelerates the migration of carriers and facilitates the separation of photogenerated carriers in the heterojunction. However, excessive reduction of monolithic silver overconsumed the metal active

sites on the surface of MXns, leading to a decrease in the photocatalytic activity, which is consistent with the SEM image of 2ATZ (Fig. S7†). The optimal photocatalyst is 1ATZ with CO and CH<sub>4</sub> yields of 11.985 and 0.768 µmol g<sup>-1</sup> h<sup>-1</sup>, respectively (Fig. 7b). The catalytic activity of the composite is higher than that of most similar composite photocatalysts (Table S2†). Tests are carried out in the dark as well as in the presence of Ar, and



Fig. 7 (a) Photocatalytic CO and CH4 yield plots, (b) CO yield plots of MXns, ZnO, TZ, and xATZ composites. (c) Cycling activity of 1ATZ for the photocatalytic CO<sub>2</sub> reduction. (d) Control experiment.

#### Paper

no products are observed. These results indicate that the reaction system is initiated by photoexcitation and the CO<sub>2</sub> RR product originated from CO<sub>2</sub> conversion (Fig. 7d). To judge the stability of the photocatalyst, four cycling experiments were conducted on 1ATZ, which has the best reduction performance, and the yield of CO was found to be relatively stable (Fig. 7c). The samples after the cycling experiments are collected to analyze the differences before and after the reaction. The full XPS spectrum (Fig. S8a<sup>†</sup>) shows that the chemical composition of the samples does not change before and after catalysis. In the high-resolution spectrum of Ti 2p, the characteristic peaks are shifted towards low binding energy (Fig. S8c<sup>†</sup>). In the Zn 2p XPS spectrum, the characteristic peaks are shifted toward high binding energy, indicating that the transfer of electrons occurred during the reaction process and the electrons are migrated from ZnO to MXns (Fig. S8b<sup>†</sup>). Taken together, the above test results indicate that the 1ATZ photocatalyst has strong stability in CO2 RR.

UV-vis diffuse reflectance spectroscopy (UV-vis DRS) was utilized to investigate the optical properties of the photocatalysts. ZnO (Fig. 8a) has a distinct UV absorption peak at 360– 390 nm, whereas MXns (Fig. S9†) shows full-spectrum absorption properties due to its pure black coloration with no distinct absorption fringes in the whole region (220–800 nm).<sup>46</sup> Due to the low content of reduced Ag, no obvious surface plasmon resonance peaks about the singlet Ag appeared in the solid-state UV spectra.<sup>48</sup> After the introduction of MXns into ZnO, the optical absorption intensity of the composite samples in the (400–800 nm) visible region was significantly enhanced due to the full-spectrum absorption of MXns. This means that the *x*ATZ composites can fully capture photons in the entire spectral range, and although the improved light trapping ability in the visible range cannot enhance the electron transport, the light energy can be converted into heat energy due to the superior photothermal conversion properties of MXns, which can promote the catalytic reaction kinetics and enhance the photocatalytic CO<sub>2</sub>RR performance. Tauc plots were made according to equation  $(Ah\nu)^n = K(h\nu - E_g)$ , as shown in Fig. 8b. The band gaps  $(E_g)$  of ZnO and 1ATZ are 3.13 and 3.12 eV, which proves that the introduction of AT has almost no effect on the band gap of ZnO.<sup>49</sup>

Transient photocurrent response and electrochemical impedance spectroscopy (EIS) tests were performed using an electrochemical workstation to investigate the charge transfer efficiency of the photocatalysts. Fig. 8c shows that the photocatalysts all have a significant photocurrent response under light. The photocurrent intensity changed significantly under switching xenon lamps, and the current density of the photoelectrode was almost zero in the absence of light, and the current increased instantaneously when light was applied, indicating that the steeply rising current was generated by the introduction of light. 1ATZ had the highest photocurrent



Fig. 8 (a) UV-vis absorption spectra and (b) Tauc plots to estimate the band gap energies of ZnO and xATZ composites. (c) Transient photocurrent responses (d) EIS plots of. ZnO and xATZ.

intensity, suggesting that the MXns was an effective co-catalyst to hinder the complexation of the photogenerated carriers and to enhance the photogenerated electron and hole separation in 1ATZ, corresponding to its most superior photocatalytic performance.<sup>50</sup> The electrochemical performance and charge transfer of the photocatalysts were further illustrated using electrochemical impedance plots. As shown in Fig. 8d, 1ATZ has the smallest Nyquist circle radius, indicating the lowest charge transfer resistance and the highest transfer rate and separation efficiency of photogenerated carriers over the photocatalyst, which improves the photocatalytic  $CO_2$ reduction performance.51

To investigate the energy band structure of the photocatalyst, the Mott–Schottky (MS) curve test was performed. As shown in Fig. 9a, the slope of the curve is positive at 1000 and 1500 Hz, indicating that ZnO belongs to the n-type semiconductor material. The tangent intercept of the MS curve on the *x*-axis can be approximately equated to the flat-band band potential of the semiconductor material, which is -1.24 V (*vs.* Ag/AgCl, pH = 7) for ZnO.<sup>52,53</sup> In n-type semiconductors, the conduction band potential is generally close to the flat band potential.<sup>34</sup> The CB position of ZnO was calculated from the conversion equation of eqn (3), NHE potential to Ag/AgCl electrode potential.

$$E(\text{NHE}) = E(\text{Ag/AgCl}) - E_{\theta} + 0.059 \text{ pH}$$
(3)

When  $E_{\theta}$  (Ag/AgCl, pH = 7) is 0.197 V, the  $E_{CB}$  of ZnO is -1.024 V (*vs.* NHE, pH = 7). Based on the results of UV-vis DRS (Fig. 8a),  $E_{VB}$  for ZnO was calculated to be 2.106 V (*vs.* NHE, pH = 7) using the  $E_{VB} = E_{CB} + E_g$  formula.<sup>34</sup> The energy of the valence band position of ZnO relative to the Fermi energy level was measured as 2.35 eV by XPS valence band spectroscopy (Fig. 9b), and the valence band potential was calculated according to the conversion eqn (4):<sup>54</sup>

$$E(VB, NHE) = \varphi + E(VB, XPS) - 4.44$$
(4)

where  $\varphi$  is the power function of the XPS test instrument,  $\varphi = 4.2$  eV. The valence band potential of ZnO ( $E_{\rm VB}$ ) is 2.11 V. Combined with the  $E_{\rm g}$  value of ZnO, the conduction band

potential of ZnO ( $E_{CB}$ ) is calculated to be -1.02 V (vs. NHE, pH = 7), which is close to that estimated using the MS curve.

#### 3.3 Photocatalytic mechanisms

In situ diffuse reflectance infrared Fourier transform spectroscopy (DRIFTS) tests were performed to study the adsorption and activation of CO<sub>2</sub> molecules on the surface of photocatalysts and to understand the pathway of photocatalytic CO<sub>2</sub> reduction. The in situ spectroscopy of ZnO and 1ATZ were recorded in darkness and after 10, 20, 30, 40, 50, and 60 min of turning on the light under the CO2 atmosphere. As shown in Fig. 10b, symmetric stretching and asymmetric stretching vibrations belonging to HCO<sub>3</sub><sup>-</sup>, which is an existent form of adsorbed CO<sub>2</sub>, were observed at 1419 and 1456  $\text{cm}^{-1}$ , and the peaks of  $\text{HCO}_3^{-1}$ were not evident in ZnO (Fig. 10a). The appearance of the peaks of the monodentate carbonate (m-CO<sub>3</sub><sup>2-</sup>) at 1338, 1507, and 1558  $\text{cm}^{-1}$ , once again demonstrated that  $\text{CO}_2$  underwent chemical adsorption (Fig. 10(a-c)).55 Meanwhile, the peaks at 1636 and 1521 cm<sup>-1</sup> are attributed to bidentate carbonates (b-CO<sub>3</sub><sup>2-</sup>).<sup>56</sup> The intensity of the FTIR peaks in the 1ATZ spectra regarding the adsorption of CO<sub>2</sub> varied more significantly with time than that of ZnO, indicating that the introduction of AT can enhance the ability of the photocatalysts to adsorb CO<sub>2</sub>. On the contrary, the intensities of all FTIR peaks on ZnO were very low, which proved that ZnO itself had a weak adsorption of CO<sub>2</sub>. The four peaks at 3728, 3704, 3625, and 3597  $cm^{-1}$  bands correspond to the stretching vibration of -OH (Fig. S10<sup>†</sup>), and the generation of surface hydroxyl groups is attributed to the dissociative adsorption of H2O.57 The strong interaction between the catalyst and water molecule leads to the competition between H<sub>2</sub>O and CO<sub>2</sub> for the active sites on the catalyst surface, which reduces the performance of CO<sub>2</sub> photoreduction.<sup>41</sup> As shown in Fig. S8,<sup>†</sup> after maintaining in a CO<sub>2</sub> atmosphere for 5 min in the dark state, the surface hydroxyl groups of 1ATZ were observed to be less than that of pure ZnO, indicating that the MXns co-catalyst can effectively inhibit the competitive adsorption of H<sub>2</sub>O, which in turn facilitates the adsorption of CO2 and the CO2RR reaction.



Fig. 9 (a) Mott-Schottky plots at 1000 and 1500 Hz, (b) valence band spectra of ZnO.





Fig. 10 In situ DRIFTS spectra of (a) ZnO (b-d) 1ATZ in the presence of CO<sub>2</sub>/H<sub>2</sub>O under light irradiation for 0, 10, 20, 30, 40, 50, and 60 min.

After illumination, new spectral peaks appeared in the infrared spectra of both the original and composite samples. The peaks appearing at 1792, 1577, and 1363  $\text{cm}^{-1}$  are attributed to CO<sub>2</sub>RR intermediate COOH\* (\* represents the adsorption state on the surface of the photocatalyst) for the generation of various types of carbon-based fuels.<sup>58,59</sup> The appearance of the characteristic peaks of CHO\* (1772 cm<sup>-1</sup>) and CO\* (2077 cm<sup>-1</sup>) indicates that the reduction products contain CH<sub>4</sub> and CO, with CHO\* and CO\* are the key intermediates for the generation of CH<sub>4</sub> and CO, respectively.<sup>60</sup> It is noteworthy that the COOH\* peak is more prominent in the local amplified infrared spectrum of 1ATZ (Fig. 10d), and the intensity of the characteristic peaks gradually enhanced with the extension of the light time, indicating that more CO2 molecules were adsorbed and activated on the surface of 1ATZ under the light, and the intermediates COOH\* continues to be produced and accumulated. The spectral peaks corresponding to CHO\* and CO\* increased with the reaction time and the intensity of the CO<sub>2</sub> adsorption bands at 1772, 1577, and 1344 cm<sup>-1</sup> increased gradually, indicating that the continuous adsorption and activation of CO<sub>2</sub> on the 1ATZ samples favorable for the photocatalytic CO<sub>2</sub>RR. In conclusion, the introduction of AT significantly enhanced the adsorption and activation of CO<sub>2</sub>.

Based on the mentioned results and analyses, the pathway of 1ATZ photocatalytic  $CO_2$  reduction may be eqn (5)–(12).  $CO_2$  molecules are first adsorbed on the surface of the photocatalyst, and then  $CO_2^*$  interacts with H<sup>+</sup> divorced from adsorbed water

and photogenerated electrons to form an intermediate product, COOH\*. COOH\* gains a pair of electrons and  $H^+$  which are further dehydrated to produce CO\*. Finally, CO\* desorbs from the photocatalyst surface to produce CO molecules. On the other hand, a small amount of CO\* generates CHO\* and CH<sub>3</sub>O\* by hydrogenation reaction, and finally forms CH<sub>4</sub>.

$$\operatorname{CO}_2(\mathbf{g}) \to \operatorname{CO}_2^*$$
 (5)

$$CO_2^* + e^- + H^+ \rightarrow COOH^*$$
(6)

$$COOH^* + e^- + H^+ \rightarrow CO^* + H_2O$$
<sup>(7)</sup>

$$CO^* \to CO(g)$$
 (8)

or 
$$CO^* + e^- + H^+ \rightarrow CHO^*$$
 (9)

$$CHO^* + e^- + H^+ \rightarrow CH_2O^*$$
(10)

$$CH_2O^* + e^- + H^+ \to CH_3O^*$$
(11)

$$CH_3O^* + e^- + H^+ \to CH_4 (g) + O^*$$
 (12)

Based on the energy band structure and photocatalytic reaction pathways, a possible photocatalytic mechanism for the ternary heterostructure of ATZ is proposed. According to the literature, the  $E_{\rm f}$  values of Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> with terminal groups –F and – O are 0.18 V and 0.71 V (*vs.* NHE, pH = 7),<sup>34</sup> which are both



Fig. 11 Schematic illustration of charge transfer route and photocatalytic mechanism of ATZ heterojunction.

much lower than the conduction band position of ZnO, and thus the photoexcited electrons tend to be transferred from ZnO to MXns across the heterojunction interface. The Fermi energy level of pure MXns is lower than the  $E(CO_2/CO)$  and  $E(CO_2/CH_4)$ conversion energies, so  $CO_2$  cannot be reduced on its surface.<sup>61</sup> It is shown that the  $E_f$  of n-type semiconductors is close to the bottom of the conduction band, and after the Mott–Schottky curve and valence band spectrum tests, the Fermi energy level of ZnO is much higher than that of MXns before contact.

Consequently, the difference in Fermi energy levels between ZnO and MXns drives the electrons to migrate from ZnO to MXns to balance the  $E_{\rm f}$  of the two materials after contact. As the interface between ZnO and MXns is in direct contact, the  $E_{\rm f}$  of ZnO is positively displaced and the  $E_{\rm f}$  of MXns is negatively displaced, while the  $E_{\rm f}$  finally reaches equilibrium. During the equilibrium process, the energy bands of ZnO will bend upward, creating a Schottky barrier, as shown in Fig. 11. Therefore, two possible electron migration modes are proposed.62 When there is no silver cluster at the interface between ZnO and MXns, the photogenerated electrons on ZnO will rapidly migrate to the surface of MXns due to the good electron trapping ability of MXns and the close contact of the interface between ZnO and MXns, which greatly promotes the separation of the photogenerated carriers. At the same time, the Schottky barrier prevents the return flow of photogenerated electrons and inhibits the complexation of electron-hole pairs. The accumulated charges on the MXns surface can reduce the adsorbed CO<sub>2</sub> molecules to CO and CH<sub>4</sub> gases at this potential equilibrium. When Ag is present at the interface between ZnO and MXns, electrons are first transferred from ZnO to Ag and then from Ag to the MXns surface. Finally, the electrons are gathered on the AT surface for photocatalytic CO<sub>2</sub> reduction.

### 4. Conclusion

In this paper, AT composites were prepared by self-reduction on the  $Ti_3C_2T_r$  surface. The nanoflower ZnO was successfully coupled with the composite AT by an electrostatic self-assembly process to form ATZ ternary heterojunction photocatalysts, which were used for photocatalytic CO2 reduction. The prepared ATZ ternary heterojunction composites have excellent photocatalytic performance and photocatalytic CO<sub>2</sub> reduction efficiency. The ATZ photocatalysts showed the highest CO and CH<sub>4</sub> reduction efficiencies of 11.985  $\mu$ mol g<sup>-1</sup> h<sup>-1</sup> and 0.768  $\mu$ mol  $g^{-1}$  h<sup>-1</sup>, respectively, and the CO<sub>2</sub> conversion was 3.35 times higher than that of pure ZnO, which also showed excellent performance among similar catalysts. The prepared composite photocatalysts showed high stability after four cycling experiments. The presence of MXns and Ag provides ZnO nanomaterials with more adsorption active sites and reaction centers for CO<sub>2</sub> adsorption and activation. The unique Schottky heterojunction structure of ATZ promotes the separation and migration of photogenerated carriers, which significantly enhances the photocatalytic reduction efficiency. This study provides a new strategy for the design and preparation of efficient and stable semiconductor photocatalysts, which also leads up new directions for the preparation of MXene-based photocatalytic composites.

## Conflicts of interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

# Acknowledgements

This work was supported by the Guangxi Natural Science Foundation (GKAD22035212), the Scientific Research Project of Guangxi University for Nationalities (2021KJD07).

# References

- 1 X. Yan, J. Zhang, G. Hao, *et al.*, 2D Atomic Layers for CO<sub>2</sub> Photoreduction, *Small*, 2023, **20**, 2306742.
- 2 Y. J. Zheng, H. D. Yao, R. N. Di, *et al.*, Water coordinated on Cu(I)-based catalysts is the oxygen source in CO<sub>2</sub> reduction to CO, *Nat. Commun.*, 2022, **13**, 2577.
- 3 J. E. Huang, F. W. Li, A. Ozden, *et al.*, CO<sub>2</sub> electrolysis to multicarbon products in strong acid, *Science*, 2021, 372, 1074–1078.
- 4 L. Wang, H. O. Badr, Y. Yang, *et al.*, Unique hierarchical structures of one dimensional lepidocrocite titanate with cation-exchangeable sites for extraordinary selective actinide capture for water purification, *Chem. Eng. J.*, 2023, **474**, 145635.
- 5 J. M. Wu, K. Y. Li, S. Y. Yang, *et al.*, In-situ construction of BiOBr/Bi<sub>2</sub>WO<sub>6</sub> S-scheme heterojunction nanoflowers for highly efficient CO<sub>2</sub> photoreduction: Regulation of morphology and surface oxygen vacancy, *Chem. Eng. J.*, 2023, **452**, 139493.
- 6 Z. Xiao, P. Li, H. Zhang, *et al.*, A comprehensive review on photo-thermal co-catalytic reduction of  $CO_2$  to value-added chemicals, *Fuel*, 2024, **362**, 130906.
- 7 Z.-W. Huang, K.-Q. Hu, X.-B. Li, *et al.*, Thermally Induced Orderly Alignment of Porphyrin Photoactive Motifs in Metal–Organic Frameworks for Boosting Photocatalytic CO<sub>2</sub> Reduction, *J. Am. Chem. Soc.*, 2023, **145**, 18148–18159.
- 8 X. Sun, M. Ji, Y. Zhang, *et al.*, In-situ embedded ultrafine Bi<sub>12</sub>O<sub>17</sub>Br<sub>2</sub> nanotubes in MOF-derived hierarchical porous carbon for enhanced photocatalytic CO<sub>2</sub> conversion to CO, *J. Mater. Sci. Technol.*, 2024, **171**, 47–53.
- 9 W. N. Shi, R. Zhang, J. C. Wang, *et al.*, One-pot hydrothermal preparation of Ni and I co-doped brookite-anatase TiO<sub>2</sub> nanoparticles with remarkably enhanced photoreduction activity of CO<sub>2</sub> to CH<sub>4</sub>, *J. Catal.*, 2024, **429**, 115235.
- 10 T. T. Li, R. Tao, Y. X. Wang, *et al.*, Construction of bismuth oxide iodide (BiOI)/zinc titanium oxide  $(Zn_2TiO_4)$  p-n heterojunction nanofibers with abundant oxygen vacancies for improving photocatalytic carbon dioxide reduction, *J. Colloid Interface Sci.*, 2024, **655**, 841–851.
- 11 Z. Xiao, C. Zhang, P. Li, *et al.*, Engineering oxygen vacancies on Tb-doped ceria supported Pt catalyst for hydrogen production through steam reforming of long-chain hydrocarbon fuels, *Chin. J. Chem. Eng.*, 2024, **68**, 181–192.
- 12 Y. Chang, K. Yu, C. Zhang, *et al.*, Ternary CdS/Au/3DOM-SrTiO<sub>3</sub> composites with synergistic enhancement for hydrogen production from visible-light photocatalytic water splitting, *Appl. Catal.*, *B*, 2017, **215**, 74–84.
- 13 Y. Guo, X.-L. Jiang, Q.-Y. Wu, et al., 4f/5d Hybridization Induced Single-Electron Delocalization in an Azide-Bridged Dicerium Complex, J. Am. Chem. Soc., 2024, 146, 7088–7096.

- 14 M. Naguib, M. Kurtoglu, V. Presser, et al., Two-dimensional nanocrystals produced by exfoliation of Ti<sub>3</sub>AlC<sub>2</sub>, Adv. Mater., 2011, 23, 4248–4253.
- 15 M. Naguib, V. N. Mochalin, M. W. Barsoum, *et al.*, 25th anniversary article: MXenes: a new family of two-dimensional materials, *Adv. Mater.*, 2014, **26**, 992–1005.
- 16 R. Li, L. Zhang, L. Shi, *et al.*, MXene Ti<sub>3</sub>C<sub>2</sub>: An Effective 2D Light-to-Heat Conversion Material, *ACS Nano*, 2017, **11**, 3752–3759.
- 17 K. Huang, C. Li, H. Li, *et al.*, Photocatalytic applications of two-Dimensional Ti<sub>3</sub>C<sub>2</sub> MXenes: a review, ACS Appl. Nano Mater., 2020, 3, 9581–9603.
- 18 R. Tang, S. Xiong, D. Gong, et al., T<sub>3</sub>C<sub>2</sub> 2D MXene: Recent Progress and Perspectives in Photocatalysis, ACS Appl. Mater. Interfaces, 2020, 12, 56663–56680.
- 19 T. Simon, M. T. Carlson, J. K. Stolarczyk, *et al.*, Electron Transfer Rate vs. Recombination Losses in Photocatalytic H<sub>2</sub> Generation on Pt-Decorated CdS Nanorods, *ACS Energy Lett.*, 2016, 1, 1137–1142.
- 20 Y. Liu, Y. H. Li, X. Li, *et al.*, Regulating Electron-Hole Separation to Promote Photocatalytic H<sub>2</sub> Evolution Activity of Nanoconfined Ru/MXene/TiO<sub>2</sub> Catalysts, *ACS Nano*, 2020, **14**, 14181–14189.
- 21 C. Wu, W. Huang, H. Liu, *et al.*, Insight into synergistic effect of  $Ti_3C_2$  MXene and  $MoS_2$  on anti-photocorrosion and photocatalytic of CdS for hydrogen production, *Appl. Catal.*, *B*, 2023, **330**, 122653.
- 22 B. Y. Zhou, Y. Yang, Z. C. Liu, *et al.*, Boosting photocatalytic  $CO_2$  reduction via Schottky junction with ZnCr layered double hydroxide nanoflakes aggregated on 2D  $Ti_3C_2T_x$  cocatalyst, *Nanoscale*, 2022, **14**, 7538–7546.
- 23 Y. Wu, L. Wang, T. Bo, *et al.*, Boosting Hydrogen Evolution in Neutral Medium by Accelerating Water Dissociation with Ru Clusters Loaded on Mo<sub>2</sub>CT<sub>x</sub> MXene, *Adv. Funct. Mater.*, 2023, 33, 2214375.
- 24 L. F. Hong, R. T. Guo, Y. Yuan, *et al.*, 2D  $Ti_3C_2$  decorated Z-scheme BiOIO<sub>3</sub>/g-C<sub>3</sub>N<sub>4</sub> heterojunction for the enhanced photocatalytic CO<sub>2</sub> reduction activity under visible light, *Colloids Surf.*, *A*, 2022, **639**, 128358.
- 25 M. Y. Areeshi, A review on biological synthesis of ZnO nanostructures and its application in photocatalysis mediated dye degradation: An overview, *Luminescence*, 2023, **38**, 1111–1122.
- 26 A. Bhosale, J. Kadam, T. Gade, *et al.*, Efficient photodegradation of methyl orange and bactericidal activity of Ag doped ZnO nanoparticles, *J. Indian Chem. Soc.*, 2023, **100**, 100920.
- 27 R. A. Mahmud, K. A. Ali, L. K. Putri, *et al.*, ZnO with engineered surface defects as a competent photocatalyst for  $CO_2$  photoreduction into valuable fuels under simulated solar light irradiation, *J. Environ. Chem. Eng.*, 2023, **11**, 109637.
- 28 A. Sharma, A. Hosseini-Bandegharaei, N. Kumar, *et al.*, Insight into ZnO/carbon hybrid materials for photocatalytic reduction of CO<sub>2</sub>: An in-depth review, *J. CO2 Util.*, 2022, **65**, 102205.

- 29 D. Y. Li, H. P. Zhang, S. Z. Xie, *et al.*, Lattice Distortion in a Confined Structured ZnS/ZnO Heterojunction for Efficient Photocatalytic CO<sub>2</sub> Reduction, *ACS Appl. Mater. Interfaces*, 2023, **15**, 36324–36333.
- 30 R. Yang, X. Gui, L. Yao, *et al.*, Ultrathin, lightweight, and flexible CNT buckypaper enhanced using MXenes for electromagnetic interference shielding, *Nano-Micro Lett.*, 2021, **13**, 66.
- 31 L. Liu, S.-J. Zheng, H. Chen, *et al.*, Tandem Nitrate-to-Ammonia Conversion on Atomically Precise Silver Nanocluster/MXene Electrocatalyst, *Angew. Chem., Int. Ed.*, 2024, 63, e202316910.
- 32 T. Hu, Z. Li, M. Hu, *et al.*, Chemical Origin of Termination-Functionalized MXenes: Ti<sub>3</sub>C<sub>2</sub>T<sub>2</sub> as a Case Study, *J. Phys. Chem. C*, 2017, **121**, 19254–19261.
- 33 J. Li, Z. Wang, H. Chen, *et al.*, A surface-alkalinized  $Ti_3C_2$ MXene as an efficient cocatalyst for enhanced photocatalytic CO<sub>2</sub> reduction over ZnO, *Catal. Sci. Technol.*, 2021, **11**, 4953–4961.
- 34 S. Cao, B. Shen, T. Tong, *et al.*, 2D/2D heterojunction of ultrathin MXene/Bi<sub>2</sub>WO<sub>6</sub> nanosheets for improved photocatalytic CO<sub>2</sub> reduction, *Adv. Funct. Mater.*, 2018, 28, 1800136.
- 35 L. Xue, C. Zhang, T. Shi, *et al.*, Unraveling the improved CO<sub>2</sub> adsorption and COOH\* formation over Cu-decorated ZnO nanosheets for CO<sub>2</sub> reduction toward CO, *Chem. Eng. J.*, 2023, **452**, 139701.
- 36 N. Alhokbany, T. Ahamad and S. M. Alshehri, Fabrication of highly porous ZnO/Ag<sub>2</sub>O nanoparticles embedded in Ndoped graphitic carbon for photocatalytic degradation of tetracycline, *J. Environ. Chem. Eng.*, 2022, **10**, 107681.
- 37 K. Tanji, J. A. Navio, A. Chaqroune, *et al.*, Fast photodegradation of rhodamine B and caffeine using ZnO-hydroxyapatite composites under UV-light illumination, *Catal. Today*, 2022, **388**, 176–186.
- 38 F. He, B. Zhu, B. Cheng, *et al.*, 2D/2D/0D TiO<sub>2</sub>/C<sub>3</sub>N<sub>4</sub>/Ti<sub>3</sub>C<sub>2</sub> MXene composite S-scheme photocatalyst with enhanced CO<sub>2</sub> reduction activity, *Appl. Catal.*, *B*, 2020, 272, 119006.
- 39 A. K. Rana, Y. Kumar, P. Rajput, *et al.*, Search for Origin of Room Temperature Ferromagnetism Properties in Ni-Doped ZnO Nanostructure, *ACS Appl. Mater. Interfaces*, 2017, 9, 7691–7700.
- 40 X. Zong, Y. Jin, Y. Li, *et al.*, Morphology-controllable ZnO catalysts enriched with oxygen-vacancies for boosting CO<sub>2</sub> electroreduction to CO, *J. CO2 Util.*, 2022, **61**, 102051.
- 41 Y. Xiao, C. Men, B. X. Chu, *et al.*, Spontaneous reduction of copper on Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> as fast electron transport channels and active sites for enhanced photocatalytic CO<sub>2</sub> reduction, *Chem. Eng. J.*, 2022, **446**, 137028.
- 42 X. Su, T. Xu, R. Ye, *et al.*, One-pot solvothermal synthesis of In-doped amino-functionalized UiO-66 Zr-MOFs with enhanced ligand-to-metal charge transfer for efficient visible-light-driven  $CO_2$  reduction, *J. Colloid Interface Sci.*, 2023, **646**, 129–140.
- 43 X. Zhu, Z. W. Pan and W. Q. Lu, Hierarchical nanohybrid of  $CuS/NiS_2/Ti_3C_2$  heterostructure with boosting charge

transfer for efficient photocatalytic hydrogen evolution, *Int. J. Hydrogen Energy*, 2023, **48**, 26740–26756.

- 44 B. Saini, K. Harikrishna, D. Laishram, *et al.*, Role of ZnO in ZnO Nanoflake/Ti<sub>3</sub>C<sub>2</sub> MXene Composites in Photocatalytic and Electrocatalytic Hydrogen Evolution, *ACS Appl. Nano Mater.*, 2022, **5**, 9319–9333.
- 45 W. Lu, C. Duan, C. Liu, *et al.*, A self-cleaning and photocatalytic cellulose-fiber- supported "Ag@AgCl@MOF-cloth" membrane for complex wastewater remediation, *Carbohydr. Polym.*, 2020, **247**, 116691.
- 46 F.-D. Wu, J.-C. Chen and J.-P. Hu, Synthesis of TiO<sub>2</sub>/Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub>/ AgI Z-scheme photocatalyst for tetracycline hydrochloride photocatalytic degradation, *J. Environ. Chem. Eng.*, 2022, 10, 107117.
- 47 Q. R. Shi, X. Y. Zhang, Y. Yang, *et al.*, 3D hierarchical architecture collaborating with 2D/2D interface interaction in NiAl-LDH/Ti<sub>3</sub>C<sub>2</sub> nanocomposite for efficient and selective photoconversion of CO<sub>2</sub>, *J. Energy Chem.*, 2021, **59**, 9–18.
- 48 J. Yin, F. Zhan, T. Jiao, *et al.*, Facile preparation of selfassembled MXene@Au@CdS nanocomposite with enhanced photocatalytic hydrogen production activity, *Sci. China Mater.*, 2020, **63**, 2228–2238.
- 49 H. Y. Zhang, X. Zhang, C. Xie, *et al.*, Composite nanoarchitectonics with  $TiO_2$  nanocrystals and superior thin  $Ti_3C_2T_x$  nanosheets towards efficient NO removal, *Environ. Res.*, 2023, 227, 115793.
- 50 M. Yu, J. Wang, G. Li, *et al.*, Construction of 3D/2D indium vanadate/graphite carbon nitride with nitrogen defects Z-scheme heterojunction for improving photocatalytic carbon dioxide reduction, *J. Mater. Sci. Technol.*, 2023, **154**, 129–139.
- 51 W. Luo, A. Li, B. Yang, *et al.*, Synthesis of a Hexagonal Phase ZnS Photocatalyst for High CO Selectivity in  $CO_2$  Reduction Reactions, *ACS Appl. Mater. Interfaces*, 2023, **15**, 15387–15395.
- 52 W. Yin, L. Bai, Y. Zhu, *et al.*, Embedding Metal in the Interface of a p-n Heterojunction with a Stack Design for Superior Z-Scheme Photocatalytic Hydrogen Evolution, *ACS Appl. Mater. Interfaces*, 2016, **8**, 23133–23142.
- 53 S. Q. Zhang, W. W. Xiong, J. F. Long, *et al.*, High-throughput lateral and basal interface in CeO<sub>2</sub>@Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub>: Reverse and synergistic migration of carrier for enhanced photocatalytic CO<sub>2</sub> reduction, *J. Colloid Interface Sci.*, 2022, 615, 716–724.
- 54 X. Li, B. Kang, F. Dong, *et al.*, Enhanced photocatalytic degradation and H<sub>2</sub>/H<sub>2</sub>O<sub>2</sub> production performance of S-pCN/WO<sub>2.72</sub> S-scheme heterojunction with appropriate surface oxygen vacancies, *Nano Energy*, 2021, **81**, 105671.
- 55 H. Li, L. Geng, S. Si, *et al.*, Photoreduction of low concentrations of CO<sub>2</sub> into methane in self-assembled palladium/porous organic cages nanocomposites, *Chem. Eng. J.*, 2023, **474**, 145431.
- 56 H. L. Huo, H. He, C. X. Huang, *et al.*, Solar-driven CO<sub>2</sub>-toethanol conversion enabled by continuous CO<sub>2</sub> transport via a superhydrophobic Cu<sub>2</sub>O nano fence, *Chem. Sci.*, 2023, 15, 1638–1647.

- 57 R. A. Wang, X. Y. Wang, Y. H. Xiong, *et al.*, Modulation of Trivalent/Tetravalent Metallic Elements in Ni-Based Layered Double Hydroxides for Photocatalytic CO<sub>2</sub> Reduction, *ACS Appl. Mater. Interfaces*, 2022, 14, 35654– 35662.
- 58 C. G. Ban, Y. Y. Duan, Y. Wang, et al., Isotype Heterojunction-Boosted CO<sub>2</sub> Photoreduction to CO, Nano-Micro Lett., 2022, 14, 74.
- 59 S. Gong, Y. Niu, X. Liu, *et al.*, Selective CO<sub>2</sub> Photoreduction to Acetate at Asymmetric Ternary Bridging Sites, *ACS Nano*, 2023, **17**, 4922–4932.
- 60 D. Liu, M. Zeng, Z. Li, *et al.*, Interfacial construction of P25/ Bi<sub>2</sub>WO<sub>6</sub> composites for selective CO<sub>2</sub> photoreduction to CO in gas-solid reactions, *RSC Adv.*, 2023, 13, 8564–8576.
- 61 W. Zhang, A. R. Mohamed and W.-J. Ong, Z-scheme photocatalytic systems for carbon dioxide reduction: Where are we now?, *Angew. Chem., Int. Ed.*, 2020, **59**, 22894–22915.
- 62 X. Ding, Y. Li, J. Zhao, *et al.*, Enhanced photocatalytic H<sub>2</sub> evolution over CdS/Au/g-C<sub>3</sub>N<sub>4</sub> composite photocatalyst under visible-light irradiation, *APL Mater.*, 2015, **3**, 104410.

Paper