## **RSC** Advances



View Article Online

View Journal | View Issue

## PAPER

Check for updates

Cite this: RSC Adv., 2024, 14, 31398

# Luminescence properties of $Bi^{3+}/Sm^{3+}$ co-doped $K_3Gd_5(PO_4)_6$ phosphors for self-referencing optical thermometry<sup>†</sup>

Jing Wang, D <sup>a</sup> Mingjun Song, \*<sup>a</sup> Junpeng Xue, \*<sup>b</sup> Shala Bi<sup>c</sup> and Hyo Jin Seo 🗐 \*<sup>d</sup>

Potassium gadolinium phosphates [K<sub>3</sub>Gd<sub>5</sub>(PO<sub>4</sub>)<sub>6</sub>] co-doped with Bi<sup>3+</sup>/Sm<sup>3+</sup> phosphors were prepared by traditional solid-state method. Their structure, morphology, luminescence properties, energy transfer, temperature sensing performance and thermal stability have been systematically investigated. The emission and excitation spectra, as well as decay curves were recorded to study the luminescence mechanism. By co-doping Bi<sup>3+</sup>/Sm<sup>3+</sup>, white emission color can be obtained. In addition, the emission intensity ratios of Bi<sup>3+</sup> and Sm<sup>3+</sup> ions present excellent temperature sensing performance in a wide temperature range. The maximum relative sensitivities of K<sub>3</sub>Gd<sub>5</sub>(PO<sub>4</sub>)<sub>6</sub> doped with Bi<sup>3+</sup>/Sm<sup>3+</sup> can reach to 3.13% K<sup>-1</sup>. In addition, K<sub>3</sub>Gd<sub>5</sub>(PO<sub>4</sub>)<sub>6</sub>:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors exhibit high thermal stability of about 55.3% at 423 K compared to room temperature.

Received 28th August 2024 Accepted 27th September 2024

DOI: 10.1039/d4ra06205a

rsc.li/rsc-advances

## 1. Introduction

White light-emitting diodes (WLEDs) have been regarded as a promising next generation lighting source due to their advantages of long operation lifetime, low power consumption, small size, good chemical stability, and environmental friendliness.<sup>1-6</sup> The widely used method for fabricating w-LEDs is to combine a blue LED chip with a yellow YAG:Ce<sup>3+</sup> phosphor. The major drawback of this method is the lack of red components, resulting in a poor color rendering index and a high correlated color temperature. Recently, another method based on the combination of UV LED chips with blue, green, and red phosphors has been developed. However, this method also suffers from some drawbacks, such as low efficiency (reabsorption between phosphor particles) and high expenses. Therefore, the method by coating single-phased tunable emission phosphors on the UV LED chips has been exploited, which has been an active research area for w-LEDs. In a single-phased phosphor, the tunable emission color, including white, can be obtained by energy transfer from the sensitizer to the activator, and a number of energy transfer systems have been reported, such as Ce<sup>3+</sup>-Eu<sup>2+</sup>,<sup>1</sup> Eu<sup>2+</sup>-Mn<sup>2+</sup>,<sup>7</sup> Bi<sup>3+</sup>-Eu<sup>3+</sup>,<sup>8</sup> Ce<sup>3+</sup>-Tb<sup>3+</sup>,<sup>9</sup> Eu<sup>2+</sup>-

 $Mn^{2+}-Tb^{3+}$ ,<sup>10</sup> and  $Tm^{3+}-Dy^{3+}$ ,<sup>11</sup> *etc.*<sup>12-14</sup> The rare earth ions are extensively investigated for the modification of luminescence color based on the energy transfer from host or sensitizers. Tunable emission color can be obtained by controlling the dopants of rare earth ions. As is well known,  $Sm^{3+}$  can be used as an orange-red emission dopant due to its intense  ${}^{4}G_{5/2} \rightarrow {}^{6}H_{J}$  transitions. Bi<sup>3+</sup> can be used as a sensitizer as well as an activator, which has strong absorption in the UV region. Taking into account of  ${}^{3}P_{1} \rightarrow {}^{1}S_{0}$  emission of Bi<sup>3+</sup> in the blue-green region, it is possible to achieve white emission by combining Bi<sup>3+</sup> emission with  $Sm^{3+}$  emission in a single-phased phosphor.

As one of the basic physical quantities, temperature has an important influence on human daily life and industrial production. In recent years, optical thermometers have attracted wide attention due to their unique advantages of noncontact, fast response, high spatial resolution, and noninvasive operation. Various techniques have been used for the temperature sensing, such as emission intensity, fluorescence intensity ratio (FIR), lifetime, as well as bandwidth. In particularly, FIR technique is widely used because of its high accuracy and high resolution. Moreover, it can get rid of the influence of measurement conditions and high equipment and operational requirements. At present, most FIR techniques are based on the detection of two emissions which are from two thermal coupled levels (TCL) of single ions, such as  $Er^{3+}({}^{2}H_{11/2}/{}^{4}S_{3/2})$ ,<sup>15</sup> and  $Dy^{3+}({}^{4}I_{5/2}/{}^{4}F_{9/2})$ .<sup>16</sup> Whereas, the narrow energy gap between TCL suffers from the drawbacks of low relative sensitivities and large overlap of two emissions. To overcome these drawbacks, the strategies based on the energy transfer or diversity in the thermal quenching behaviors of two luminescence centers have been proposed, such as Pr<sup>3+</sup>-Tb<sup>3+</sup>,<sup>17</sup> Eu<sup>3+</sup>-Tb<sup>3+</sup>,<sup>18,19</sup> Bi<sup>3+</sup>- $Eu^{3+}$ ,<sup>20–22</sup> and  $Eu^{3+}$ – $Dy^{3+}$ .<sup>23</sup> It is known that the emission bands

<sup>&</sup>quot;School of Chemistry and Chemical Engineering, Weifang University, Weifang, Shandong, 261061, China. E-mail: smj521209@126.com

<sup>&</sup>lt;sup>b</sup>School of Science, Jiangsu University of Science and Technology, Zhenjiang, 212100, China

Xinjiang Technical Institute of Physics and Chemistry, Chinese Academy of Sciences, 830011, China

<sup>&</sup>lt;sup>d</sup>Department of Physics, Pukyong National University, Busan 608-737, South Korea † Electronic supplementary information (ESI) available. See DOI: https://doi.org/10.1039/d4ra06205a

of Bi<sup>3+</sup> and Sm<sup>3+</sup> are basically separated, and signal discrimination can be easily performed.<sup>24,25</sup> Thus, Bi<sup>3+</sup>/Sm<sup>3+</sup> co-doped materials have great potential application for temperature sensing.

In the present work, the luminescence properties of  $Bi^{3+}$ / $Sm^{3+}$  co-doped  $K_3Gd_5(PO_4)_6$  (host abbreviated as KGP) phosphor is investigated. Tunable emission color can be realized by co-doping  $Bi^{3+}$  and  $Sm^{3+}$  ions. Meanwhile,  $Bi^{3+}/Sm^{3+}$  co-doped KGP phosphors can be used for optical temperature sensor in a wide temperature range (44–182 K and 295–523 K) with maximum relative sensitivities of 3.13% K<sup>-1</sup>.

## 2. Experimental section

#### 2.1 Synthesis of samples

A series of  $K_3Gd_{5-x}(PO_4)_6:xBi^{3+}$  (x = 0.05, 0.1, 0.15, 0.5, 1, 1.5, 2, where  $KGP:Bi^{3+}$  represents x = 0.05),  $K_3Gd_{4.99}(PO_4)_6:0.01Sm^{3+}$ ( $KGP:Sm^{3+}$ ), and  $K_3Gd_{4.96}(PO_4)_6:0.05Bi^{3+},0.01Sm^{3+}$ ( $KGP:Bi^{3+},Sm^{3+}$ ) phosphors were prepared by solid state method. Stoichiometric amount of  $K_2CO_3$  (99.9%, Sigma),  $Gd_2O_3$  (99.99%, Sigma), NH\_4H\_2PO\_4 (99.9%, Sigma), Bi<sub>2</sub>O<sub>3</sub> (99.9%, Sigma), and Sm<sub>2</sub>O<sub>3</sub> (99.99%, Sigma) were carefully weighed and ground thoroughly in an agate mortar with ethanol. The mixture was firstly heated at 873 K for 2 h. The obtained powder was thoroughly mixed in a second time and then heated at 1123 K for 5 h. After cooling down to the room temperature, the white powder was collected for the next investigation.

#### 2.2 Characterization

The XRD patterns were recorded by Rigaku SmartLab X-ray diffractometer in the  $2\theta$  range from 10 to 70°. The diffuse reflectance spectra (DRS) were measured by a V-670 UV-Vis/NIR spectrophotometer and BaSO<sub>4</sub> as a background reference. The morphology was studied by JSM-6700F field emission scanning electron microscopy. The emission spectra and decay curves were measured by 266 nm Nd:YAG laser. The excitation spectra were recorded by Quanta Master 300 fluorescence spectrometer equipped with high power Xenon flash lamp. The temperature was controlled by a closed cycle helium cryostat in the range of 11–295 K. The high temperature from 295 to 523 K was done by a home-made temperature control system.

### 3. Results and discussion

#### 3.1 Crystal structure

Fig. 1(a) shows the XRD patterns of Bi<sup>3+</sup> single doped and Bi<sup>3+</sup>/ Sm<sup>3+</sup> co-doped KGP phosphors. Fig. 1(b) and (c) shows the crystal structure of the KGP host, which forms monoclinic phase with space group C2/c. A three-dimensional Gd<sub>5</sub>(PO<sub>4</sub>)<sub>6</sub><sup>3-</sup> anionic framework is formed by Gd polyhedral and P tetrahedral, while K atoms occupy the tunnel along *c* axis. And there are three crystallographic Gd<sup>3+</sup> sites, of which Gd1 and Gd3 are coordinated by eight O atoms and Gd2 is surrounded by nine O atoms. In Fig. 1(a), all the peaks match well with the ICSD standard card (No. 172528), and no trace of impurity phase can be observed, revealing the formation of the pure monoclinic C2/c phase. With the incorporation of Bi<sup>3+</sup> and Sm<sup>3+</sup> ions into host lattice, the crystal structure is not affected. This can be ascribed to the low doping concentration and similar radius of Bi<sup>3+</sup> (1.17 Å for C.N. = 8), Sm<sup>3+</sup> (1.079 Å for C.N. = 8, and 1.132 Å for C.N. = 9) with Gd<sup>3+</sup> (1.053 Å for C.N. = 8, and 1.107 Å for C.N. = 9). The SEM image of Bi<sup>3+</sup>/Sm<sup>3+</sup> co-doped KGP phosphor is shown in Fig. 2. The particles are in the size range of one to a few micrometers with smooth surface. EDS mapping of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor is shown in Fig. S1.† Due to the low doping concentration, Bi and Sm elements cannot be detected.

#### 3.2 Luminescence properties

**3.2.1** Photoluminescence characteristics KGP:Bi<sup>3+</sup> phosphor. Fig. 3(a) shows the DRS of KGP host and KGP:Bi<sup>3+</sup> phosphor in the range from 200 to 1300 nm. In the spectrum of KGP host, a broad absorption band from 200 to 320 nm can be observed, which can be ascribed to the band to band transition of host lattice.<sup>27,28</sup> An absorption peak at 312 nm can also be found, owing to the  ${}^{8}S_{7/2} \rightarrow {}^{6}P_{7/2}$  transition of Gd<sup>3+</sup> ions.<sup>29</sup> When the doping of Bi<sup>3+</sup>, a new absorption band centered at 255 nm appears, which can be attributed to the  ${}^{1}S_{0} \rightarrow {}^{1}P_{1}$  transition of Bi<sup>3+</sup> ions.<sup>30</sup>

The band gaps of the un-doped KGP and KGP:Bi<sup>3+</sup> phosphors were calculated according to the Kubelka–Munk theory<sup>31</sup> by using DRS data. The DRS can be transformed into absorption spectra by the following equation:

$$F(R) = \frac{(1-R)^2}{2R} = \frac{K}{S}$$
 (1)

where R is the diffuse reflectance of the sample, K is the absorption coefficient, and S is the scattering coefficient.

On the basis of Tauc relation, the relation between band gap  $(E_g)$  and linear absorption coefficient ( $\alpha$ ) for direct band gap can be expressed as:

$$\alpha h\nu = C(h\nu - E_g)^{1/2} \tag{2}$$

where, hv is the photon energy and C is the proportionality constant. Considering that the scattering coefficient S as a constant with respect to wavelength, and combining eqn (1) and (2), it can be derived that:

$$[F(R)h\nu]^2 = C(h\nu - E_g)$$
(3)

From the plot of  $[F(R)hv]^2$  versus hv, the value of  $E_g$  was acquired by extrapolating the linear fitted regions to  $[F(R)hv]^2 = 0$ , as shown in Fig. 3(b). The band gaps were calculated to be 4.78 and 4.59 eV for KGP and KGP:Bi<sup>3+</sup>. The values are close to K<sub>3</sub>Gd(PO<sub>4</sub>)<sub>2</sub> (4.8 eV) which has similar structure.<sup>32</sup> According to the literature, the doping of luminescent centers can change the band gap energy more or less.<sup>27</sup> In this work, the doping of Bi<sup>3+</sup> can decrease the band gap energy.

The emission spectrum of KGP:Bi<sup>3+</sup> sample under excitation at 266 nm is shown in Fig. 4(a). The sharp emission peaks at 312 and 624 nm are due to the  ${}^{6}P_{7/2} \rightarrow {}^{8}S_{7/2}$  transition of Gd<sup>3+</sup> ions and its second harmonics, respectively. The broad band from

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.



ions. Fig. 4(b) shows the normalized excitation spectra of KGP:Bi<sup>3+</sup> by monitoring the emissions at 410, 445, and 500 nm. Only one excitation band centered at 252 nm ranging from 220 to 280 nm can be found, which is due to the  ${}^{1}S_{0} \rightarrow {}^{1}P_{1}$  transition of Bi<sup>3+</sup> ion, and consistent with the absorption band in DRS.<sup>33</sup> Fig. 4(c) shows the emission spectra of KGP: $xBi^{3+}$  (x = 0.05-2) phosphors. With increasing Bi<sup>3+</sup> concentration, the emission intensity increases firstly and then decreases, reaching the maximum at x = 0.1. The integral emission intensities of Bi<sup>3+</sup> ions are shown in Fig. 4(d). It is known that energy transfer between Bi<sup>3+</sup> ions leads to the concentration quenching. To

confirm the energy transfer mechanism, the critical distance  $R_c$ was calculated by following equation<sup>34</sup>

$$R_{\rm c} = 2 \left[ \frac{3V}{4\pi X_{\rm c} N} \right]^{1/3} \tag{4}$$

Gd

0-2

where V is the cell volume of host and is 1998.48  $Å^3$  for  $K_3Gd_5(PO_4)_6$ . X<sub>c</sub> is the critical concentration of dopant (Bi<sup>3+</sup>) at which the maximum emission intensity is obtained and is 0.1. N is the number of sites available for activators in unit cell and is 4 for  $K_3Gd_5(PO_4)_6$ . In this case, the  $R_c$  is determined to be 21.21 Å. This value is greater than the shortest distance between the  $Gd^{3+}$  ions of 4.10 Å and larger than 5–8 Å, indicating that



(c)

K<sub>3</sub>Gd<sub>5</sub>(PO<sub>4</sub>)<sub>6</sub>:Bi<sup>3+</sup>,Sm<sup>3+</sup>

K<sub>3</sub>Gd<sub>5</sub>(PO<sub>4</sub>)<sub>6</sub>:Bi<sup>3</sup>

ICSD 172528

50

60

5µm

Fig. 2 SEM images of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor.



Fig. 3 (a) DRS of un-doped KGP and KGP:Bi<sup>3+</sup> phosphors; and (b) calculated band gaps of un-doped KGP and KGP:Bi<sup>3+</sup> phosphors by DRS data.

exchange interaction is not the main mechanism of concentration quenching. Therefore, the electric multipolar interactions dominate the non-radiative concentration quenching between Bi<sup>3+</sup> ions. Based on the Dexter theory,<sup>35</sup> the type of multipolar interaction can be determined by

$$\frac{I}{x} = \left[1 + \beta(x)^{\frac{\theta}{3}}\right]^{-1}$$
(5)

where *I* is emission intensity, *x* is doping concentration (Bi<sup>3+</sup>) beyond the optimal value,  $\beta$  is constant, and  $\theta$  represents the type of multipolar interaction (where  $\theta = 6$ , 8, and 10 corresponding to the dipole–dipole, dipole–quadrupole, and quadrupole–quadrupole interactions, respectively). By plotting the relationship between *x* and *I*/*x* in the log–log version, the slope value ( $-\theta/3$ ) of -1.67 can be obtained, as shown in the inset of Fig. 4(d). As a consequence, the value of  $\theta$  is determined to be 5.01, demonstrating that the dipole–dipole interaction is



Fig. 4 (a) Emission spectrum of KGP:Bi<sup>3+</sup> sample under 266 nm excitation; (b) excitation spectra of KGP:Bi<sup>3+</sup> sample by monitoring at 410, 445, and 500 nm; (c) emission spectra of KGP:xBi<sup>3+</sup> (x = 0.05, 0.1, 0.15, 0.5, 1, 1.5, 2) samples under 266 nm excitation; and (d) integral emission intensity of Bi<sup>3+</sup> ions at different doping concentration. Inset shows the correlation between log(*I*/*x*) and log(*x*).



Fig. 5 Decay curves of Bi<sup>3+</sup> ions by monitoring at 445 nm with 266 nm excitation

responsible for the concentration quenching between Bi3+ ions.

The decay curves of Bi<sup>3+</sup> ions were recorded by monitoring at 445 nm upon the excitation at 266 nm, as shown in Fig. 5. At low doping concentration, the decay curves are single exponential. With increasing Bi<sup>3+</sup> concentration, the decay curve deviates

from the single exponential characteristic. In this case, the decay times were calculated by the following equation:<sup>36</sup>

$$\tau = \frac{\int I(t)tdt}{\int I(t)dt}$$
(6)

where I(t) represents the emission intensity at time t. As shown in Fig. 5, the calculated decay time was reduced from 0.446 to 0.034 µs with increasing Bi<sup>3+</sup> concentration from x = 0.05 to x =2

Fig. 6(a) shows the temperature dependent emission spectra of KGP:Bi<sup>3+</sup> phosphor in the range of 12 to 294 K. At 12 K, strong Gd<sup>3+</sup> emission and relatively weak Bi<sup>3+</sup> emission can be observed, indicating that both host lattice and Bi<sup>3+</sup> ions can be excited at 266 nm. With the increase of temperature, Bi<sup>3+</sup> emission intensity shows temperature dependency, as shown in Fig. 6(b). In the 53–204 K temperature range, the enhancement in Bi<sup>3+</sup> emission intensity at the expense of the Gd<sup>3+</sup> emission is a result of the competition between two emitting centers.<sup>37</sup> The quenching of the Bi3+ emission above 204 K is presumably related to the thermal quenching process. Fig. 6(c) displays the decay curves of Bi<sup>3+</sup> ions. At low temperature, decay kinetics of the Bi<sup>3+</sup> emission is more complicated than room temperature. Therefore, the lifetime values are calculated based on eqn (6) and displayed in Fig. 6(d). With the increase of temperature, the decay lifetime decrease, which can be fitted by the equation:

$$\tau_T = \frac{\tau_0}{1 + A \exp(-E_a/kT)} \tag{7}$$



Fig. 6 (a) Temperature dependent emission spectra, (b) integral emission intensity, (c) temperature dependent decay curves, and (d) calculated lifetime of KGP:Bi<sup>3+</sup> sample under 266 nm excitation.

#### Paper



Fig. 7 (a) Emission spectra and (b) CIE diagram of KGP:Bi<sup>3+</sup>, KGP:Sm<sup>3+</sup>, and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors with 266 nm excitation; (c) excitation spectra of Sm<sup>3+</sup> ions in KGP:Sm<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors by monitoring at 596 nm; and (d) excitation spectra of Bi<sup>3+</sup> ions in KGP:Bi<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors by monitoring at 445 nm.

herein,  $\tau_T$  and  $\tau_0$  are the lifetimes at temperature of *T* and initial lifetime, respectively. *A* is the constant and *k* stands for Boltzmann constant, and  $\Delta E_a$  represents the activation energy. As shown in Fig. S2,† the activation energy is determined to be 0.049 eV at low temperature range.

3.2.2 Photoluminescence characteristics KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup>

**phosphor.** Fig. 7(a) exhibits the emission spectra of KGP:Bi<sup>3+</sup>,

KGP:Sm<sup>3+</sup>, and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors under 266 nm excitation, while Fig. 7(b) presents their CIE diagram. Accordingly, the emission color can be manipulated by controlling the dopants, and white emission color can also be achieved. In emission spectrum of KGP:Sm<sup>3+</sup>, typical Sm<sup>3+</sup> emissions at 562, 596, and 642 nm can be observed, which correspond to characteristic  ${}^{4}G_{5/2} \rightarrow {}^{6}H_{5/2}$ ,  ${}^{4}G_{5/2} \rightarrow {}^{6}H_{7/2}$ , and  ${}^{4}G_{5/2} \rightarrow {}^{6}H_{9/2}$ 



Fig. 8 (a) Decay curves of Sm<sup>3+</sup> ions in KGP:Sm<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors by monitoring at 596 nm; and (b) decay curves of Bi<sup>3+</sup> ions in KGP:Bi<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors by monitoring at 445 nm.



**Fig. 9** Energy level diagram of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors (NR stands for non-radiative transition, E.T. stands for energy transfer).

transitions of Sm<sup>3+</sup> ions respectively. When Bi<sup>3+</sup> is co-doped into host lattice, the band emission of Bi<sup>3+</sup> ions from 330 to 650 nm appears, and the emission intensity of Sm<sup>3+</sup> is enhanced. Compared with the spectrum of KGP:Bi<sup>3+</sup>, the co-doping of Sm<sup>3+</sup> leads to the decrease of emission intensities of Bi<sup>3+</sup>. There might be energy transfer from Bi<sup>3+</sup> ions to Sm<sup>3+</sup> ions.

In order to explore the energy transfer process, the excitation spectra and decay curves were measured. Fig. 7(c) displays the excitation spectra of Sm<sup>3+</sup> ions in KGP:Sm<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors by monitoring at the dominant emission at 596 nm. In the spectrum of KGP:Sm<sup>3+</sup>, excitation peaks located at 245, 273, and 310 nm are due to the Gd<sup>3+</sup> absorptions.<sup>38</sup> Meanwhile, several excitation peaks corresponding to the characteristic Sm<sup>3+</sup> absorptions can also be observed, which are located at 343 nm ( ${}^{6}\text{H}_{5/2} \rightarrow {}^{4}\text{D}_{7/2}$ ), 360 nm ( ${}^{6}\text{H}_{5/2} \rightarrow {}^{4}\text{D}_{3/2}$ ), 373 nm ( ${}^{6}\text{H}_{5/2}$  $\rightarrow$  <sup>6</sup>P<sub>7/2</sub>), 400 nm (<sup>6</sup>H<sub>5/2</sub>  $\rightarrow$  <sup>6</sup>P<sub>3/2</sub>), 414 nm (<sup>6</sup>H<sub>5/2</sub>  $\rightarrow$  <sup>4</sup>M<sub>19/2</sub>), 436 nm ( ${}^{6}\text{H}_{5/2} \rightarrow {}^{4}\text{M}_{17/2}$ ), and 450 nm ( ${}^{6}\text{H}_{5/2} \rightarrow {}^{4}\text{I}_{11/2} + {}^{4}\text{M}_{15/2}$ 2).<sup>39,40</sup> After co-doping with Bi<sup>3+</sup>, a new excitation band from 220 to 270 nm appears, which matches the excitation spectrum of  $Bi^{3+}$  ions in Fig. 4(b). Besides, the intensity of  $Sm^{3+}$  excitation peaks increases, which might due to the overlap of the emission spectrum of Bi<sup>3+</sup> and excitation spectrum of Sm<sup>3+</sup>. In other words, co-doping with Bi<sup>3+</sup> will enhance the excitation intensity of Sm<sup>3+</sup>. Fig. 7(d) exhibits the excitation spectra of Bi<sup>3+</sup> in KGP:Bi<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors by monitoring at 445 nm. Only one excitation band centered at 252 nm can be observed, and the co-doping of Sm<sup>3+</sup> ions leads to the decrease of excitation intensity of Bi<sup>3+</sup>. Thus, we can speculate that there is energy transfer from Bi<sup>3+</sup> to Sm<sup>3+</sup> in KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor. To further confirm the energy transfer process, the decay curves of Sm<sup>3+</sup> and Bi<sup>3+</sup> were studied. Fig. 8(a) exhibits the decay curves



**Fig. 10** (a) Temperature dependent emission spectra of KGP:Bi<sup>3+</sup>, Sm<sup>3+</sup> phosphor from 11 to 295 K under 266 nm excitation. Inset: Integral emission intensity of Bi<sup>3+</sup> and Sm<sup>3+</sup>. (b) Temperature dependent CIE diagram; (c) emission intensity ratio of Bi<sup>3+</sup> to Sm<sup>3+</sup> in the range of 44 to 182 K and the liner fitting curve; and (d) calculated relative sensitivity ( $S_r$ ) and absolute sensitivity ( $S_a$ ).



Fig. 11 (a) Temperature dependent emission spectra of KGP:Bi<sup>3+</sup>, Sm<sup>3+</sup> phosphor from 295 to 523 K under 266 nm excitation. Inset: Integral emission intensity of Bi<sup>3+</sup> and Sm<sup>3+</sup>. (b) Temperature dependent CIE diagram; (c) emission intensity ratio of Sm<sup>3+</sup> to Bi<sup>3+</sup> and the fitting curve; and (d) calculated relative sensitivity ( $S_r$ ) and absolute sensitivity ( $S_a$ ).

of Sm<sup>3+</sup> (596 nm) in KGP:Sm<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> samples. A rise time can be observed in the curve of KGP:Sm<sup>3+</sup>, and the decay lifetime is calculated to be 3.94 ms by using the mono-exponential fitting equation:

$$I(t) = I_0 \exp(-t/\tau) \tag{8}$$

where I(t) is the total intensity at time t,  $I_0$  is intensity at t = 0 and  $\tau$  is lifetime. After co-doping with Bi<sup>3+</sup>, the rise time disappears and the lifetime decreases to 2.93 ms, illustrating that Bi<sup>3+</sup> ions accelerate the population of Sm<sup>3+</sup> in the excited state. Fig. 8(b) exhibits the decay curves of Bi<sup>3+</sup> (445 nm) in KGP:Bi<sup>3+</sup> and KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphors. After co-doping with Sm<sup>3+</sup>, the lifetime values of Bi<sup>3+</sup> decreased from 0.412 µs to 0.394 µs. As aforementioned, there is an energy transfer process from Bi<sup>3+</sup> to Sm<sup>3+</sup>. The corresponding energy level diagram of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> sample is displayed in Fig. 9.

#### 3.3 Temperature sensing performance

Fig. 10(a) shows the temperature dependent emission spectra of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor in the range of 11 to 295 K with excitation at 266 nm. The integral emission intensities of Bi<sup>3+</sup> and Sm<sup>3+</sup> ions are shown in the inset. As the temperature increases, the emission intensity of Bi<sup>3+</sup> increases firstly and then decreases, similar to the variation in KGP:Bi<sup>3+</sup> phosphor. However, the emission intensity of Sm<sup>3+</sup> decreases gradually with raising temperature. Fig. 10(b) shows the temperature dependent CIE diagram of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor. The emission colors travel through yellow to with the temperature increases from 11 to 295 K, and the corresponding CIE coordinates are listed in Table S2.<sup>†</sup> Furthermore, the emission intensity ratio (*R*) of Bi<sup>3+</sup> to Sm<sup>3+</sup> was found to be temperature dependent and can be used for the temperature sensing. Fig. 10(c) shows the experimental data of *R* and the fitting curve.

Table 1	Comparison	of the	Sensitivities	with the	reported	phosphors

Material	Temperature range (K)	$Max S_a (\% K^{-1})$	Max $S_{\rm r}$ (% K <sup>-1</sup> )	Ref.	
Ca <sub>2</sub> YZr <sub>2</sub> Al <sub>3</sub> O <sub>12</sub> :Bi <sup>3+</sup> ,Sm <sup>3+</sup>	298-473	0.099	0.356	42	
La <sub>3</sub> Ta <sub>0.8</sub> Sb <sub>0.2</sub> O <sub>7</sub> :Bi <sup>3+</sup> ,Sm <sup>3+</sup>	303-523	5.9	1.32	43	
$Sr_{3}Y_{2}Ge_{3}O_{12}$ : Bi <sup>3+</sup> , Sm <sup>3+</sup>	298-498	0.17	0.57	44	
KGP:Bi <sup>3+</sup> ,Sm <sup>3+</sup>	44-182	1.57	3.135	This work	
KGP:Bi <sup>3+</sup> ,Sm <sup>3+</sup>	295-523	4.064	1.808	This work	



Fig. 12 (a) Normalized emission intensity of  $Bi^{3+}$ ,  $Sm^{3+}$ , and total emission intensity as a relation with temperature; (b) plot of  $\ln(I_0/I_T - 1)$  versus (1/kT) for the calculation for the  $E_a$  of KGP: $Bi^{3+}$ ,  $Sm^{3+}$  phosphor.

In the temperature range from 44 to 182 K, the data can be linearly fitted. The equation can be expressed as:

$$R = A \times T + B \tag{9}$$

where *A* is the slope of fitting curve, *B* is a constant. The parameters of *A* and *B* were determined to be 0.0157 and -0.19, respectively. The absolute sensitivity (*S*<sub>a</sub>) and relative sensitivity (*S*<sub>r</sub>) can be calculated by following equations:

$$S_{\rm a} = \left| \frac{\mathrm{d}R}{\mathrm{d}T} \right| = A \tag{10}$$

$$S_{\rm r} = \left| \frac{1}{R} \frac{\mathrm{d}R}{\mathrm{d}T} \right| = \frac{A}{A \times T + B} \tag{11}$$

For this sample, the absolute sensitivity is 1.57% K<sup>-1</sup>, and the maximum relative sensitivity is 3.135% K<sup>-1</sup> at 44 K, as shown in Fig. 10(d).

To further explore the temperature sensing performance above room temperature of KGP: $Bi^{3+}$ , $Sm^{3+}$  phosphor, the emission spectra in the temperature range from 295 to 523 K were studied with excitation at 266 nm. In Fig. 11(a), the emission intensity of  $Bi^{3+}$  decreases with increasing temperature due to thermal quenching effect, while the emission intensity of  $Sm^{3+}$  increases firstly and then decreases. The increase of  $Sm^{3+}$  intensity may be due to the accelerated energy transfer caused by heating. Fig. 11(b) and Table S3† displays the CIE diagram of KGP: $Bi^{3+}$ , $Sm^{3+}$  phosphor, in which the emission color can be turned from white to yellow with the increase of temperature.

For the application of temperature sensing, the emission intensity of  $\text{Sm}^{3+}$  can be regarded as a constant ( $I_{\text{C}}$ ) and can be used as a self-reference. Based on the Struck and Fonger theory,<sup>41</sup> the relationship between emission intensity and temperature can be expressed by following equation:

$$I(T) = \frac{I_0}{1 + A \exp(-\Delta E_a/kT)}$$
(12)

where I(T) and  $I_0$  represents the emission intensity at *T* and low temperature; *A* is a constant;  $\Delta E_a$  represents the activation energy related to thermal quenching; *k* is the Boltzmann constant.

Based on eqn (12), the emission intensity ratio (R) of Sm<sup>3+</sup> to Bi<sup>3+</sup> can be expressed as:

$$R = \frac{I_{\rm Sm}}{I_{\rm Bi}} = \frac{I_{\rm C}}{\frac{I_{0,\rm Bi}}{1 + A \exp(-\Delta E_{\rm a,Bi}/kT)}}$$
$$= \frac{I_{\rm C}}{I_{0,\rm Bi}} \left[ 1 + A_{\rm Bi} \exp\left(-\frac{\Delta E_{\rm a,Bi}}{kT}\right) \right] \approx B + C \exp(-\Delta E/kT)$$
(13)

where *B*, *C*, and  $\Delta E$  are parameters related to Bi<sup>3+</sup> and Eu<sup>3+</sup>. The corresponding absolute sensitivity *S*<sub>a</sub> and relative sensitivity *S*<sub>r</sub> can be expressed as:

$$S_{\rm a} = \left| \frac{\mathrm{d}R}{\mathrm{d}T} \right| = C \exp(-\Delta E/kT) \times \frac{\Delta E}{kT^2}$$
 (14)

$$S_{\rm r} = \left| \frac{1}{R} \frac{\mathrm{d}R}{\mathrm{d}T} \right| = \frac{C \exp(-\Delta E/kT)}{B + C \exp(-\Delta E/kT)} \times \frac{\Delta E}{kT^2}$$
(15)

As shown in Fig. 11(c), the emission intensity ratio of Sm<sup>3+</sup> to Bi<sup>3+</sup> can be adopted for the temperature sensing. By using eqn (13), the plot can be well fitted and corresponding parameters of *B*, *C*, and  $\Delta E/k$  were determined to be -0.075, 121.17, and 1443.75 cm<sup>-1</sup> respectively. Fig. 11(d) shows the calculated sensitivities by eqn (14) and (15). The absolute sensitivity increases with temperature and reaches maximum of 4.064% K<sup>-1</sup> at 523 K. By contrast, the relative sensitivity decreases with temperature and reaches the maximum of 1.808% K<sup>-1</sup> at 295 K, indicating that it is a good candidate for application of optical thermometer. The sensitivities of this phosphor are comparable to the reported phosphors, as shown in Table 1.

#### 3.4 Thermal stability

Thermal stability is an important parameter which affects the application of optical materials in LEDs. Fig. 12(a) displays the

#### View Article Online RSC Advances

thermal stability of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor. At 423 K, the emission intensities of Bi<sup>3+</sup>, Sm<sup>3+</sup>, and total emission quench to 20.8%, 91.8%, and 55.3% of its initial intensity at 295 K. Fig. 12(b) exhibits the plot of  $\ln(I_0/I_T - 1)$  against (1/*kT*), and the calculated slope correspond to the activation energy in the thermal quenching process of KGP:Bi<sup>3+</sup>,Sm<sup>3+</sup> phosphor, which is determined to be 0.276 eV.

## 4. Conclusion

In summary, a series  $Bi^{3+}$ ,  $Sm^{3+}$  single doped and co-doped KGP samples were successfully synthesized by high temperature solid state method. Based on the emission spectrum, excitation spectra, as well as decay curves, the energy transfer process from  $Gd^{3+}$  and  $Bi^{3+}$  to  $Sm^{3+}$  can be demonstrated. Furthermore, the tunable emission color can be obtained by co-doping  $Sm^{3+}$  with  $Bi^{3+}$ . The emission intensity ratio of  $Bi^{3+}$  and  $Sm^{3+}$  was found to be temperature dependent and can be used for the optical temperature sensing in a wide temperature range. The maximum relative sensitivity of KGP: $Bi^{3+}$ , $Sm^{3+}$  phosphor reaches 3.13% K<sup>-1</sup>. Meanwhile, a high thermal stability of 55.3% at 423 K can be obtained for KGP: $Bi^{3+}$ , $Sm^{3+}$  phosphors.

## Data availability

Data available within the article or its ESI.†

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This research was supported by Weifang Science and Technology Development Funds (2023GX011), the Natural Science Foundation of Jiangsu Province (Grant No. BK20241002).

## References

- 1 C.-K. Chang and T.-M. Chen, Appl. Phys. Lett., 2007, 91, 081902.
- 2 X. Huang, S. Wang, B. Li, Q. Sun and H. Guo, *Opt. Lett.*, 2018, **43**, 1307–1310.
- 3 M. Xia, X. Wu, Y. Zhong, H. T. Hintzen, Z. Zhou and J. Wang, J. Mater. Chem. C, 2019, 7, 2927–2935.
- 4 M. Song, J. Wang, Z. Xie, L. Liu, W. Zhao and W. Zhou, *J. Rare Earths*, 2023, in press.
- 5 X. Wang, W. Zeng, M. Song, F. Wang, X.-d. Hu, Q. Guo and Y. Liu, *Chem. Eng. J.*, 2019, 475–484.
- 6 M. Song, N. Zhang, Q. Meng, L. Wang, X.-y. Li and G. f. Wang, *J. Rare Earths*, 2017, **35**, 368–373.
- 7 N. Guo, Y. Huang, H. You, M. Yang, Y. Song, K. Liu and Y. Zheng, *Inorg. Chem.*, 2010, **49**, 10907–10913.
- 8 P. Dang, S. Liang, G. Li, Y. Wei, Z. Cheng, H. Lian, M. Shang, A. A. Al Kheraif and J. Lin, *Inorg. Chem.*, 2018, 57, 9251–9259.
- 9 G. Zhu, Y. Wang, Z. Ci, B. Liu, Y. Shi and S. Xin, *J. Lumin.*, 2012, **132**, 531–536.

- 10 G. Zhu, S. Xin, Y. Wen, Q. Wang, M. Que and Y. Wang, *RSC Adv.*, 2013, **3**, 9311–9318.
- 11 P. Yang, X. Yu, X. Xu, T. Jiang, H. Yu, D. Zhou, Z. Yang, Z. Song and J. Qiu, *J. Solid State Chem.*, 2013, **202**, 143–148.
- 12 Z. Zhang, J. Yan, Q. Zhang, G. Tian, W. Jiang, J. Huo, H. Ni, L. Li and J. Li, *Inorg. Chem.*, 2022, **61**, 16484–16492.
- 13 D. Wen, H. Liu, Z. Ma, L. Zhou, J. Li, Y. Guo, Q. Zeng, P. A. Tanner and M. Wu, *Angew. Chem., Int. Ed.*, 2023, 62, e202307868.
- 14 J. Feng, L. Chen, J. Xie, Q. Zhang, Y. Yu, L. Luo, Q. Tang, J. Zhou and J. Li, *Mater. Today Chem.*, 2024, 36, 101979.
- 15 K. Zhou, H. Zhang, Y. Liu, Y. Bu, X. Wang and X. Yan, *J. Am. Ceram. Soc.*, 2019, **102**, 6564–6574.
- 16 X. Wang, Q. Liu, Y. Bu, C.-S. Liu, T. Liu and X. Yan, *RSC Adv.*, 2015, **5**, 86219–86236.
- 17 Y. Gao, F. Huang, H. Lin, J. Zhou, J. Xu and Y. Wang, *Adv. Funct. Mater.*, 2016, **26**, 3139–3145.
- 18 C. D. Brites, P. P. Lima, N. J. Silva, A. Millán, V. S. Amaral, F. Palacio and L. D. Carlos, *Adv. Mater.*, 2010, 22, 4499–4504.
- 19 S. Zheng, W. Chen, D. Tan, J. Zhou, Q. Guo, W. Jiang, C. Xu, X. Liu and J. Qiu, *Nanoscale*, 2014, 6, 5675–5679.
- 20 J. Xue, H. M. Noh, B. C. Choi, S. H. Park, J. H. Kim, J. H. Jeong and P. Du, *Chem. Eng. J.*, 2020, **382**, 122861.
- 21 K. Li and R. Van Deun, J. Alloys Compd., 2019, 787, 86-95.
- 22 R. Wei, J. Guo, K. Li, L. Yang, X. Tian, X. Li, F. Hu and H. Guo, *J. Lumin.*, 2019, **216**, 116737.
- 23 J. Wang, Y. Bu, X. Wang and H. J. Seo, Sci. Rep., 2017, 7, 6023.
- 24 R.-R. Wang, G.-H. Li and G.-M. Cai, J. Mater. Chem. C, 2023, 11, 3616–3625.
- 25 B. V. Ratnam, M. Jayasimhadri and K. Jang, *Spectrochim. Acta, Part A*, 2014, **132**, 563–567.
- 26 S. Bevara, S. N. Achary, K. K. Mishra, T. R. Ravindran, A. K. Sinha, P. U. Sastry and A. K. Tyagi, *Phys. Chem. Chem. Phys.*, 2017, **19**, 6030–6041.
- 27 L. Yang, Z. Mu, S. Zhang, Q. Wang, D. Zhu, Y. Zhao, D. Luo, Q. Zhang and F. Wu, *J. Mater. Sci.: Mater. Electron.*, 2018, 29, 6548–6555.
- 28 P. Gupta, A. K. Bedyal, V. Kumar, Y. Khajuria, S. P. Lochab, S. S. Pitale, O. M. Ntwaeaborwa and H. C. Swart, *Mater. Res. Bull.*, 2014, **60**, 401–411.
- 29 D. D. Ramteke and R. S. Gedam, J. Rare Earths, 2014, 32, 389– 393.
- 30 B. Shen, B. Chen, Y. Zhang and J. Hu, *J. Lumin.*, 2020, 218, 116821.
- 31 A. E. Morales, E. S. Mora and U. Pal, *Rev. Mex. Fis.*, 2007, **53**, 18–22.
- 32 P. Gupta, A. K. Bedyal, V. Kumar, Y. Khajuria, V. Sharma, O. M. Ntwaeaborwa and H. C. Swart, *Mater. Res. Express*, 2015, **2**, 076202.
- 33 L. Wang, J. Qiao, Y. Liu, P. Huang, Q. Shi, Y. Tian, C. e. Cui and Z. Luo, *Opt. Mater.*, 2017, **67**, 78–83.
- 34 G. Blasse, Philips Res. Rep, 1969, 24, 131.
- 35 D. L. Dexter, J. Chem. Phys., 1953, 21, 836-850.
- 36 D. Chen, Y. Wang, Y. Yu, P. Huang and F. Weng, *Opt. Lett.*, 2008, **33**, 1884–1886.
- 37 A. M. Srivastava and W. Beers, J. Lumin., 1999, 81, 293-300.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

Open Access Article. Published on 03 October 2024. Downloaded on 7/30/2025 5:54:19 PM.

#### Paper

- 38 U. Vetter, J. Zenneck and H. Hofsäss, *Appl. Phys. Lett.*, 2003, 83, 2145–2147.
- 39 P. Gupta, A. K. Bedyal, V. Kumar, Y. Khajuria, V. Sharma, O. M. Ntwaeaborwa and H. C. Swart, *Mater. Res. Express*, 2015, 2, 076202.
- 40 J. Chen, W. Zhao, J. Wang, N. Wang, Y. Meng, J. He and X. Zhang, *Ceram. Int.*, 2015, **41**, 11945–11952.
- 41 C. Struck and W. Fonger, J. Appl. Phys., 1971, 42, 4515-4516.
- 42 C. Han, J. Tan, A. Xiong and T. Yuan, *Opt. Mater.*, 2021, **118**, 111232.
- 43 Y. Xue, Y. Chen, Q. Mao, Y. Ding, G. Bai, L. Chu, M. Liu and J. Zhong, *Mater. Des.*, 2023, **234**, 112375.
- 44 R. Sun, X. Wei, H. Yu, P. Chen, H. Ni, J. Li, J. Zhou and Q. Zhang, *Dalton Trans.*, 2023, **52**, 2825–2832.