



Cite this: *J. Mater. Chem. A*, 2024, **12**, 5540

DOI: 10.1039/d4ta90039a
rsc.li/materials-a

Correction: An oriented Ni–Co-MOF anchored on solution-free 1D CuO: a p–n heterojunction for supercapacitive energy storage

Iftikhar Hussain,^a Sarmad Iqbal,^b Tanveer Hussain,^c Yatu Chen,^a Muhammad Ahmad,^a Muhammad Sufyan Javed,^d Akram AlFantazi^{be} and Kaili Zhang^{*a}

Correction for 'An oriented Ni–Co-MOF anchored on solution-free 1D CuO: a p–n heterojunction for supercapacitive energy storage' by Iftikhar Hussain *et al.*, *J. Mater. Chem. A*, 2021, **9**, 17790–17800, <https://doi.org/10.1039/D1TA04855D>.

The authors would like to replace Fig. 2 with a new version, as shown below. The low magnification SEM images in Fig. 2c and g have been replaced with high magnification and clear SEM images.




Fig. 2 SEM images of (a) and (b) the bare Cu mesh; (c–e) CuO and (f) the cross-sectional view of CuO; and (g and h) Ni–Co-ZIF@CuO and (i) the cross-sectional view of Ni–Co-ZIF@CuO.

^aDepartment of Mechanical Engineering, City University of Hong Kong, 83 Tat Chee Avenue, Kowloon, Hong Kong. E-mail: kaizhang@cityu.edu.hk

^bDepartment of Chemical Engineering, Khalifa University, Abu Dhabi 127788, United Arab Emirates

^cSchool of Chemical Engineering, The University of Queensland, St Lucia, QLD 4072, Australia

^dSchool of Physical Science and Technology, Lanzhou University, Lanzhou 730000, China

^eNuclear Technology Center, Khalifa University, Abu Dhabi, United Arab Emirates



The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

