

Cite this: *Dalton Trans.*, 2025, **54**, 15009Received 28th July 2025,  
Accepted 7th August 2025

DOI: 10.1039/d5dt01784j

rsc.li/dalton

## What goes on in sub-critical solvothermal synthesis of metal ion complexes?

Lassaad Baklouti<sup>a,b</sup> and Jack Harrowfield  \*<sup>c</sup>

The remarkable success of solvothermal methods in providing an extraordinary range of new materials has somewhat obscured the fact that much of the underlying chemistry remains ill-understood. This is true, particularly in sub-critical solvothermal syntheses yielding coordination polymers and frameworks, making product selection and optimisation of yields a matter of empirical variations in reactant mixtures and reaction conditions. There are, however, many indications within known observations of the operation of factors that could be better understood by their independent direct study under solvothermal conditions. This article provides some suggestions to identify such factors.

### 1. Introduction

Two important steps in the development of metal ion coordination chemistry were the distinction of “inert” and “labile” complex ion species first proposed by Henry Taube<sup>1,2</sup> and the subsequent quantification of labile species of this distinction initiated by Manfred Eigen<sup>3,4</sup> and expanded in particular for the lanthanides by André Merbach.<sup>4</sup> Although there is not a simple dichotomy, and rate constants for water ligand exchange in metal aqua ions as reference species at room temperature vary over a range of nearly  $10^{20} \text{ s}^{-1}$ ,<sup>5</sup> Taube’s simple differentiation of labile complexes as those where ligand substitution occurred within the time it takes to mix the reagents, while inert complexes required observably longer periods, remains practically important in synthesis design. It is not, of course, the only consideration, and the development of the procedures referred to as “solvothermal” synthesis of coordination complexes, polymers and frameworks has depended on the recognition of many other factors surveyed, for example, in ref. 6–22. The terms “solvothermal” and “hydrothermal”, with the latter limited to cases where water is the sole solvent present, qualify the syntheses of a huge variety of materials other than metal ion complexes and involve conditions, in particular of temperature and pressure, that can also vary over a great range.<sup>23–31</sup> The following discussion is, however, limited to that of the sub-critical solvothermal synthesis of metal ion complexes, as it has become a standard technique of materials

chemistry and because there are fundamental aspects which warrant further study in order to be fully exploited.

Solvothermal methods in general<sup>29,30</sup> are characterised by the fact that they are conducted in closed vessels under autogenous pressure at temperatures which are close to or considerably exceed the boiling point of the solvent, very commonly a mixture of liquids with quite different solvation capacity. When the temperature is below the critical temperature of the solvent, the method can be termed “sub-critical solvothermal synthesis”.<sup>20</sup> Its application in metal ion coordination chemistry can be seen as a first logical step beyond “classical” procedures in which a metal ion source and a ligand are dissolved, by heating if necessary, under ambient pressure, in a solvent, and efforts are then made to isolate any product, most simply by cooling the reaction mixture. Such simple and familiar procedures work particularly well for labile metal ion complexes of unit or low nuclearity but are of limited utility for the synthesis of polymers and frameworks where, for example, rapid precipitation at relatively low temperatures leads to amorphous or heterogeneous products or where polymer formation depends on relatively slow assembly processes such as hydrolytic condensation.<sup>9</sup> In effect, sub-critical solvothermal synthesis provides a simple means of extending the temperature range of solution reactions, ideally a range in which decomposition of organic reagents can be ignored. Table 1 provides an indication of the diversity of systems and a range of experimental details known for this method.<sup>32–44</sup> It is a method largely compatible with what has been said of metal–organic (coordination) framework (MOF) synthesis that “The main goal in MOF synthesis is to establish the synthesis conditions that lead to defined inorganic building blocks without decomposition of the organic linker. At the same time, the kinetics of crystallisation must be appropriate to allow nucleation and growth of the desired phase to take

<sup>a</sup>Department of Chemistry, Faculty of Sciences of Sfax, University of Sfax, Tunisia<sup>b</sup>Laboratory of Applied Chemistry and Natural Substances, Resources and Environment, Faculty of Sciences of Bizerte, University of Carthage, Tunisia.

E-mail: lassaad.baklouti@fss.usf.tn

<sup>c</sup>ISIS, Université de Strasbourg, 8 allée Gaspard Monge, 67083 Strasbourg, France.

E-mail: harrowfield@unistra.fr



**Table 1** A representative selection of the conditions employed in the sub-critical hydro/solvothermal syntheses of coordination complexes

Metal(s)	Ligand(s)	Solvent(s)	$T_r^a/^\circ\text{C}$	$t_r^b$	$T_{\text{coll}}^c$	$n^d$	Ref.
Cu(I)	4,4'-Bipyridine	H <sub>2</sub> O	140	2 d	RT	1	32
Co(II), Cu(II), Zn(II)	5-Diacetatoamino-isophthalate	CH <sub>3</sub> OH/H <sub>2</sub> O (1 : 1)	90	3 d	RT	3	33
Cr(III), Mn(III)	O <sup>2-</sup>	Acetone	200	3 d	RT	2	34
U(VI)	CB6, CB7, CB8, <sup>e</sup> aliphatic dicarboxylates	H <sub>2</sub> O	180	14 d	RT	6	35
Pb(II) + K(I), Rb(I), or Cs(I)	Isophthalate, 4,4'-biphenyldisulfonate	DMF <sup>f</sup> /CH <sub>3</sub> OH (2 : 1)	150	3 d or 3 h	RT	5	36
Bi(III)	Pyridine-2,6-dicarboxylate	DMF, CH <sub>3</sub> OH or C <sub>2</sub> H <sub>5</sub> OH	100 and 125	3 d	RT	6	37
Zr(IV)	Tetrakis(4-carboxyphenyl)-porphyrin	DEF <sup>g</sup>	120	12 h	RT	2	38
Th(IV)	Terephthalate	DMF, H <sub>2</sub> O or DMF/H <sub>2</sub> O					39
Zn(II)	5-((4- <i>tert</i> -Butyl)-phenylazo)isophthalate, 1,2-di(4-pyridyl)ethene	C <sub>2</sub> H <sub>5</sub> OH/H <sub>2</sub> O (1 : 1)	120	24 h	RT	1	40
U(VI) + Co(II), Cu(II), Zn(II), or Cd(II)	2,2'-Bipyridine-4,4'-dicarboxylate	H <sub>2</sub> O	200 or 150	3 d	RT	7	41
Ln(III) Y(III)	F <sup>-</sup>	Ethylene glycol/H <sub>2</sub> O various ratios	190	12 h	RT	3	42
U(VI)	Zwitterionic and anionic dicarboxylates	H <sub>2</sub> O/CH <sub>3</sub> CN (3 : 1) or H <sub>2</sub> O/DMA <sup>h</sup> (3 : 1)	140	1–14 d	140	7	43
Sc(III)	Thiophenedicarboxylate, nitrate	CH <sub>3</sub> CN/H <sub>2</sub> O (1 : 1)	100	3 d	RT	1	44

<sup>a</sup>  $T_r$  = reaction temperature. <sup>b</sup>  $t_r$  = period of heating at  $T_r$ . <sup>c</sup>  $T_{\text{coll}}$  = temperature at which products were collected (not necessarily that at which crystallisation first occurred). <sup>d</sup>  $n$  = number of different products prepared. <sup>e</sup> CB = cucurbituril. <sup>f</sup> DMF = dimethylformamide. <sup>g</sup> DEF = diethylformamide. <sup>h</sup> DMA = dimethylacetamide.

place".<sup>14</sup> Crystallisation of the product is not just desirable to establish its purity but more importantly to enable X-ray crystal structure determination, crucial to an understanding of the product properties, and this of course is also the case for molecular complexes and coordination polymers (CPs).

In practice, the use of sub-critical solvothermal synthesis of metal ion complexes, CPs and MOFs in particular, has been associated principally with two needs. One is that of obtaining a homogeneous solution of both a metal ion source and a ligand (or a ligand source) and the other is that of producing a crystalline product suitable for structure determination by X-ray methods. The former is important in achieving the latter but neither step is free of complications.

## 2. Influence of the solvent used in sub-critical solvothermal reactions

The importance of both the physical and chemical properties of the solvent employed in solvothermal syntheses in general has been discussed in several reviews.<sup>9,14,15,20,23,31,45,46</sup> One physical property that is unlikely to be of significance in sub-critical syntheses is the solvent vapour pressure. This determines the actual pressure, usually simply defined as "autogenous", inside the container being heated and this is also determined by the fraction of the container volume occupied by the liquid reaction mixture.<sup>20,31</sup> While this occupancy factor is not always explicitly noted in reports of sub-critical syntheses, where it is (e.g. ref. 35), it is well below full, meaning that pressures would typically be ~1 MPa, well below values (~GPa) that might have a significant influence on chemical equilibria or kinetics.<sup>31,47</sup> What is a critical solvent property, of course, is the capacity to form a solution of the chosen reactants from which the desired reaction product can be precipitated. It is

quite commonly the case that metal ion and ligand sources have very different solubility characteristics, a perhaps extreme example being found in the formation of coordination polymers involving porphyrins and polyoxometallates.<sup>48</sup> The capacity to dissolve a wide range of compounds of greatly different polarity is a characteristic of dipolar aprotic solvents<sup>49,50</sup> such as dimethylsulfoxide (DMSO), *N,N*-dimethylformamide (DMF), *N,N*-dimethylacetamide (DMA), acetonitrile (AN), *N*-methylpyrrolidinone (NMP) and tetrahydrofuran (THF), all of which are Lewis bases and have a well-explored coordination chemistry,<sup>51,52</sup> certainly one factor favouring their capacity to dissolve metal ion sources. Significantly, such solvents are also water-miscible, meaning it is possible to mix an aqueous solution of a metal ion source with a dipolar aprotic solvent solution of a ligand source without phase separation resulting, and mixtures of water or hydrolytic species such as alcohols with dipolar aprotic solvents are the most common media employed in sub-critical solvothermal syntheses. This adds a level of complexity to synthesis design, since it has long been known<sup>50</sup> that different mixtures of the same two solvents can have quite different properties and indeed systematic variation of the solvent mixture composition used in sub-critical solvothermal syntheses has been shown to give rise to quite different products in a variety of different systems.<sup>9,39,42,53–58</sup> This work, however, has proceeded in an essentially empirical manner,<sup>59</sup> since the study of solvation in mixed solvents has been largely limited to temperatures and pressures below those employed in solvothermal syntheses.<sup>60,61</sup>

The sensitivity of solvothermal synthesis to variations in the mixing ratio of two solvents in the whole reaction mixture is mirrored in its sensitivity to changes in one component (usually the dipolar aprotic solvent).<sup>6–22</sup> In many instances, this can be considered as simply a consequence of the incorporation (or not) of the solvent in the product crystals through



direct coordination or weak interactions such as H-bond acceptance, thus giving materials with different compositions and therefore different structures. In many other instances, this is but part of the story. The fact that the product of a solvothermal synthesis is not necessarily the same as the product obtained from the same reactants under other conditions<sup>9,62,63</sup> is an indication of the special nature of solvothermal synthesis. It is rather difficult, however, to define why it is special because in the majority of instances only the crystal structure of the product is available as a guide to the chemistry leading to it and this can result, as noted early on,<sup>64,65</sup> in reports which are purely speculative. This is not to say that efforts to follow reaction during solvothermal treatment are unknown<sup>29,30,65–67</sup> but again they have been mainly focused on product formation and not upon any changes in the supernatant solution chemistry. Nonetheless intriguing examples of the former concern monitoring of the gradual formation of interpenetrated crystal structures,<sup>68,69</sup> interpenetration being a common feature of CP and MOF structures influencing their potential applications.<sup>8,14,15,45</sup>

To illustrate the difficulties involved in unravelling the many roles of the solvent in sub-critical solvothermal synthesis, it is convenient to consider the commonly employed (co)solvent *N,N*-dimethylformamide, DMF.<sup>70</sup> DMF is known to undergo reaction near its boiling point (153 °C) to give CO and (CH<sub>3</sub>)<sub>2</sub>NH (dimethylamine), a reaction exploited in organometallic carbonylation reactions,<sup>71</sup> and suggested to be the reason for facilitating the synthesis of crystalline


[(CH<sub>3</sub>)<sub>2</sub>NH<sub>2</sub>]<sub>3</sub>[Ln(dipic)<sub>3</sub>] complexes (Ln = lanthanide(III); dipic = pyridine-2,6-dicarboxylate) by simply boiling a solution of hydrated LnCl<sub>3</sub> with dipicH<sub>2</sub> in DMF for 1 hour.<sup>72</sup> DMF is also known to undergo rapid metal ion catalysed base hydrolysis,<sup>73</sup> though the reaction is relatively slow under acidic conditions.<sup>74</sup> The difference is that hydrolysis can be considered to give rise formally to dimethylammonium ion and formate, with the latter being a good ligand for metal ions in the higher oxidation states involved in most solvothermal syntheses. Consideration of the very large number of crystal structures involving dimethylammonium cations in the Cambridge Structural Database (CSD) shows that a large fraction involves crystal structures of CPs and MOFs produced in sub-critical solvothermal syntheses where DMF (or, in fewer cases, DMA) was used as a cosolvent. This could be taken in a positive sense as indicating that the utility of DMF (and other amides formed by dimethylamine) includes its capacity to provide a cation well-suited to the crystallisation of anionic CPs and MOFs, but the more important point to note presently is that, although the number of cases is a relatively small proportion of the total, there are instances where both formate and dimethylammonium are present in the isolated crystals and even some where formate is present without dimethylammonium. On this point, Table 2 refers to a selection of structures,<sup>75–92</sup> encompassing a wide range of metal ions and illustrating the range of compositions that can be observed for a single cation (uranyl ion), with some examples for DMA and AN as well as DMF. Fig. 1 provides an illustration of how solvent fragments

**Table 2** Examples of the composition of structurally characterised complexes obtained by sub-critical solvothermal syntheses in which dipolar aprotic solvents and solvent fragments (bold letters) are found

Metal	Crystal composition <sup>a</sup>	Solvent	Refcode	Ref.
Cu(II)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>3</sub> [(Cu <sub>4</sub> Cl) <sub>3</sub> (BTC) <sub>8</sub> ] <b>·9DMA</b>	DMA	ABEMIF	75
Co(II)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>2</sub> [Co <sub>2</sub> Cl <sub>2</sub> (BTC) <sub>4</sub> ] <sub>3</sub>	DMA/AN	ABAYIO	76
Cd(II)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>4</sub> [Cd <sub>2</sub> (TTCA) <sub>2</sub> Cl <sub>2</sub> ] <b>·7DMF·2Diox·6H<sub>2</sub>O</b>	DMF/dioxane	ADEGEY	77
Fe(II)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>4</sub> [Fe <sup>II</sup> (OH)(BPTC) <sub>1.5</sub> (DMSO) <sub>3</sub> ]	DMA/DMSO	BAZBIQ	78
Bi(III)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>4</sub> [Bi <sub>2</sub> (PDC) <sub>2</sub> (HPDC) <sub>2</sub> ] <b>·2DMF·NH(CH<sub>3</sub>)<sub>2</sub></b>	DMF	AHEZEV	79
Eu(III)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>4</sub> [Eu <sub>4</sub> (DDAC) <sub>3</sub> (HCO <sub>2</sub> )(OH) <sub>2</sub> ] <b>·8DMF·9H<sub>2</sub>O</b>	DMF/H <sub>2</sub> O	ABOXUL	80
Y(III)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>4</sub> [Y(BTEC)(H <sub>2</sub> O)]	DMF/H <sub>2</sub> O	ABUMUJ	81
U(VI)	[UO <sub>2</sub> (ADDC)]( <b>DMF</b> )	DMF/H <sub>2</sub> O	ZOZCEY	82
U(VI)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>4</sub> [(UO <sub>2</sub> ) <sub>4</sub> (ADDC) <sub>6</sub> ]	DMF/H <sub>2</sub> O	ZOZCIC	82
U(VI)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>2</sub> [(UO <sub>2</sub> ) <sub>2</sub> (ADDA) <sub>3</sub> ] <b>·3H<sub>2</sub>O</b>	DMF/H <sub>2</sub> O	IHOGIX	83
U(VI)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>2</sub> [(UO <sub>2</sub> ) <sub>2</sub> (KTA) <sub>3</sub> ]	DMA/H <sub>2</sub> O	QUKLAL	84
U(VI)	[UO <sub>2</sub> Pb(BTA)]( <b>HCO<sub>2</sub></b> )(phen)]	DMF/H <sub>2</sub> O	OSOMOA	85
U(VI)	[PPh <sub>4</sub> ][UO <sub>2</sub> (R-CHDC)]( <b>HCO<sub>2</sub></b> )	DMF/H <sub>2</sub> O	COVSOY	86
U(VI)	[NH <sub>4</sub> ] <sub>2</sub> [PPh <sub>4</sub> ] <sub>2</sub> [(UO <sub>2</sub> ) <sub>4</sub> (ADDA) <sub>6</sub> ]	DMF/AN	YEXDAJ	87
U(VI)	[Ni( <i>R,S</i> -Me <sub>6</sub> cyclam)] <sub>2</sub> [UO <sub>2</sub> (CAM)]( <b>HCO<sub>2</sub></b> ) <sub>2</sub> ]	DMF/H <sub>2</sub> O	JIVBAV	88
U(VI)	[PPh <sub>3</sub> Me] <sub>3</sub> [NH <sub>4</sub> ] <sub>3</sub> [(UO <sub>2</sub> ) <sub>6</sub> (CAM) <sub>9</sub> ]	DMF/AN/H <sub>2</sub> O	JIVBOI	88
U(VI)	[UO <sub>2</sub> (1,2-PDA)]- <b>CH<sub>3</sub>CN</b>	AN/H <sub>2</sub> O	FUDNOK	89
U(VI)	[C(NH <sub>2</sub> ) <sub>3</sub> ] <sub>2</sub> [(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>2</sub> [(UO <sub>2</sub> ) <sub>3</sub> (TDC) <sub>4</sub> ] <b>(HCO<sub>2</sub>)</b> ]	DMF/H <sub>2</sub> O	EWIQEJ	90
U(VI)	[UO <sub>2</sub> (ADP)]( <b>HCO<sub>2</sub></b> ) <sub>2</sub> Cu( <i>R,S</i> -Me <sub>6</sub> cyclam)] <b>·2H<sub>2</sub>O</b>	DMF/H <sub>2</sub> O	YAPSUH	91
U(VI)	[(CH <sub>3</sub> ) <sub>2</sub> NH <sub>2</sub> ] <sub>2</sub> [(UO <sub>2</sub> ) <sub>2</sub> (HTRT) <sub>2</sub> ] <b>(HCO<sub>2</sub>)<sub>2</sub>Ni(<i>R,S</i>-Me<sub>6</sub>cyclam)]<b>·2H<sub>2</sub>O</b></b>	DMF/H <sub>2</sub> O	VEXPEX	92
U(VI)	[Hquin] <sup>b</sup> [(UO <sub>2</sub> ) <sub>2</sub> (TRT)]( <b>CH<sub>3</sub>CO<sub>2</sub></b> )	AN/H <sub>2</sub> O	VEXPIB	92

<sup>a</sup> Ligand abbreviations: BTC = benzene-1,3,5-tricarboxylate; TTCA = triphenylene-2,6,10-tricarboxylate; BPTC = 3,3',5,5'-biphenyl-tetracarboxylate; PDC = pyridine-2,4,6-tricarboxylate; DDAC = aminoterphenyl-pentacarboxylate; BTEC = benzene-1,2,4,5-tetracarboxylate; ADDC = 1,3-adamantane-dicarboxylate; ADDA = 1,3-adamantane-diacetate; KTA = Kemp's triacetate = *cis,cis*-1,3,5-trimethylcyclohexane-1,3,5-tricarboxylate; phen = 1,10-phenanthroline; RCHDC = *R,R*-*trans*-1,2-cyclohexane-dicarboxylate; CAM = 1*R*,3*S*-camphorate; PDA = phenylene diacetate; TDC = thiophene-2,5-dicarboxylate; ADP = adipate = 1,6-hexanedioate; cyclam = 1,4,8,11-tetra-azacyclotetradecane; TRT = *R,R*-tartrate dianion. <sup>b</sup> Quin = quinuclidine = 1-azabicyclo[2.2.2]octane.






**Fig. 1** A fragment within the structure of  $[(\text{CH}_3)_2\text{NH}_2]_2[(\text{UO}_2)_2(\text{HTRT})_2(\text{HCO}_2)_2\text{Ni}(\text{R,S-Me}_6\text{cyclam})]\cdot 2\text{H}_2\text{O}$  ( $\text{HTRT}^- = \text{hydrogentartrate}$ )<sup>92</sup> showing the part of the intricate network of hydrogen bonds (dashed lines) that link dimethylammonium counterions, water and coordinated formate. For clarity, CH atoms are shown only on the coordinated tartrate and formate units, with formate oxygen shown in green and dimethylammonium nitrogen in pale blue. Otherwise U = yellow, Ni = sky blue, N = dark blue, and O = red, H = white spheres with an arbitrary radius of 0.1 Å, with other atom displacement ellipsoids shown at the 80% level (figure prepared using CrystalMaker 11.5 from CrystalMaker Software Ltd).

may influence the complete structure and divert the structure from one anticipated for a simple metal-ion/ligand complex. The relatively infrequent occurrence of formate and acetate binding, in general, is quite possibly just a reflection of competition from multidentate carboxylates present in many reaction mixtures. Note also that intact DMF, either coordinated or as a solvate molecule, can be found in many structures, indicating that the hydrolysis reaction may in fact attain an equilibrium. Overall, the evidence appears to favour hydrolysis as the reaction undergone by DMF under solvothermal conditions, but a study of the reaction and its possible metal ion catalysis under these conditions would be necessary to establish this as a true conclusion. The same can be said for solvents such as DMA and AN, also well known to be susceptible to hydrolytic cleavage.

While the chemical effects of solvent hydrolysis on product composition just described are readily understood, others are perhaps less obvious. Thus, the hydrolysis of DMF



produces a medium of significant buffering capacity, which, on the basis of the approximate expression  $\text{pH} = (\text{p}K_1 + \text{p}K_2)/2$

would be expected to give this medium a room-temperature pH of  $\sim 7.2$ . Reaction mixture pH values have not been reported systematically, since most ligand sources are added as the conjugate acid (*e.g.* carboxylic acids and phosphonic acids) initial values would be expected to be low, as indeed observed where such measurements have been made.<sup>93</sup> As initial DMF concentrations in the reaction mixtures typically greatly exceed those of the metal ions and ligands, the buffer created by gradual hydrolysis should dominate the mixture pH, meaning that the success in using DMF/H<sub>2</sub>O to provide crystalline products could be due to progressive deprotonation resulting in a form of “homogeneous precipitation”.<sup>94</sup> Gradual basification of an initially acid reaction mixture does seem, in any case, to be important in that the addition of NaOH or KOH to the initial reaction mixture is known to sometimes result in product contamination with amorphous solids.<sup>40,95</sup> Like DMF, both DMA and AN undergo hydrolysis under solvothermal conditions and thus could also control crystallisation rates. There is no evidence in the nature of isolated products that the cyclic amide NMP undergoes detectable ring opening under solvothermal conditions, although these products do contain deprotonated acids.<sup>96</sup> Once again, some basic kinetic studies could clarify the situation.

Redox chemistry is an intentional aspect of solvothermal syntheses of mixed metal oxides<sup>9,20,30</sup> but in the synthesis of



coordination polymers and frameworks, its occurrence is rather incidental and not always of obvious origin. The facts that heterometallic U(VI)Cu(II) complexes of a saturated tricarboxylate ligand can be obtained through hydrothermal synthesis<sup>97</sup> but a U(VI)Cu(I) complex is obtained with a very similar dicarboxylate and Cu(II) reactant when DMF/H<sub>2</sub>O is the solvent<sup>98</sup> indicate that the reducing power of DMF may be operative, but in other systems hydrothermal syntheses also result in reduction of Cu(II) to Cu(I).<sup>32,99</sup> Unlike DMF, DMSO can be both an oxidant and a reductant and has been deliberately employed as a reactant (in the ethylenediamine solvent) for solvothermal syntheses where it provides a source of sulfide.<sup>100</sup> As a single solvent, DMSO has been used in the synthesis of porphyrin-derived frameworks<sup>101</sup> but the present authors have avoided its use following some explosive reactions. A long-recognised drawback of solvothermal syntheses with organic ligands is the oxidative degradation of such ligands ultimately to oxalate,<sup>65,102</sup> a reaction which has been followed in detail for 2,3-pyrazinedicarboxylate,<sup>65</sup> where numerous intermediates were identified and the termination at oxalate rather than at CO<sub>2</sub> attributed to the very low solubility of its neodymium(III) complex. While dissolved oxygen was considered to play some role in the oxidation, nitrate counterions from metal salt reactants were obvious possible oxidants<sup>102</sup> and it has recently been shown<sup>103</sup> that the substitution of triflate for nitrate is an effective means of inhibiting ligand oxidation. Crown ethers are ligands which appear to be particularly sensitive to oxidation to oxalate,<sup>104</sup> and the removal of nitrate would presumably eliminate this reaction but it also must be asked whether a better understanding of the oxidation reactions might enable a better choice of reaction time to be made. As noted above, steps in the oxidation of 2,3-pyrazinedicarboxylate can be distinguished, and in the case of tris(carboxyethyl)phosphine, oxidation is even terminated at the stage of phosphine oxide.<sup>105</sup> Evidence that in a purely aqueous solution an oxidation process having no effect on the isolated product composition may still occur is provided by a pH increase (indicative of an oxidation reaction consuming acid) observed in a hydrothermal synthesis.<sup>93</sup> While superheated water can attack organic molecules in several ways including oxidation,<sup>106</sup> such reactions involve temperatures and pressures well above those of sub-critical solvothermal synthesis.

### 3. Duration of the reaction time in sub-critical solvothermal reactions

Another well-known disadvantage of solvothermal synthesis is the length of time conventionally assigned to the reaction, and, with product applications in mind, considerable research has been devoted to finding ways to shorten reaction times, microwave heating being one approach that has proved quite successful,<sup>23,107,108</sup> with “light-assisted” solvothermal synthesis in open vessels being a novel recent development.<sup>109</sup> The quest for “greener” methods continues.<sup>110</sup> Determination

of the optimal reaction time can be a difficult issue, largely because of the very nature of the solvothermal method. There are occasional references in the literature<sup>111–114</sup> to the method as a “black box” procedure because of the enclosure of the reaction mixture or filled reaction vessel within a stainless steel autoclave, meaning that visual observation of the reaction's progress is not possible. What goes in is known, what comes out can be characterised but what happens in between is often unclear. Is a homogeneous solution of the reactants formed immediately on attaining the temperature desired or is dissolution of the least soluble component a limiting factor? If a homogeneous solution forms at some stage, does product crystallisation begin to occur shortly thereafter or only after final cooling of the apparatus? If crystals do form rapidly, is an extended period of heating required in order that they attain a size suitable for X-ray structure determination? Is it possible that crystals deposited at the reaction temperature are not the same as those deposited at room temperature? These are questions that arise independently of whether time is also required for reactions (discussed above) other than that of metal ion to ligand coordination to occur. Partial responses are provided by studies, *e.g.*<sup>35,43,62,82–92,96–98,104,105</sup> using transparent glass reaction vessels and these show, at least for polycarboxylate complexes of uranyl ions, that the formation of a solution occurs readily but any deposition of crystals at the reaction temperature occurs in time periods ranging from hours to several weeks. In many cases, precipitation of crystalline or even amorphous material does not occur at all, though both can be induced by cooling. Although crystallisation at the reaction temperature precisely defines the conditions of crystal formation, it has the disadvantage that the yields of CPs and MOFs are often low, a handicap in relation to any application. In these cases, it is essentially unknown whether the crystallisation temperature has a significant influence on the nature of the product, while in contrast for mixed-metal oxides, where yields are high and formation rapid, it is well established<sup>9</sup> that it does. For CPs and MOFs where a reaction temperature dependence of products, isolated at room temperature, has been demonstrated (*e.g.* for Mn(II) carboxylate MOFs<sup>67</sup>), there is thus some uncertainty as to how it arises.

In addition to a lack of any knowledge of the dependence of product solubility on temperature, there is essentially no information on possible solution equilibria in mixed solvents at elevated temperatures. Available data, such as those for Eu(III) interactions with carboxylate ligands,<sup>115</sup> are typically limited to 298 K and show a complicated dependence of equilibrium constants, including those for solvent autoionisation, on solvent composition. Thus, while there are at least some data for the temperature dependence of aqua ion acidity in a single solvent, for example,<sup>116,117</sup> they are of little direct value. For labile metal ions of the transition, lanthanide and actinide series, however, complexation equilibria should be established essentially immediately upon dissolution of the reagents at the temperatures employed in sub-critical solvothermal syntheses, so what need there is for extended heating after this point is unclear unless it is simply to maintain crystal formation. Of



course, if product formation is dependent upon reactions such as solvent hydrolysis, time will be required, and thus it is important to know how much time is needed if there is a desire to optimise yields. Ligands may also show particular chemical reactivity; susceptibility to oxidation has already been discussed, and a wide variety of other reactions,<sup>62</sup> many of them metal-ion induced, are known and some of these have been deliberately exploited in crystal engineering.<sup>15,118</sup> In our own work on uranyl ion CP and MOF species formed by hydro/solvothermal syntheses in transparent vessels, the possibility of photocatalysed uranyl ion reactions<sup>119</sup> has been a necessary concern but only in a single case,<sup>120</sup> some evidence for one such reaction, H-atom abstraction, has been obtained. All these reactions complicate the choice of reaction time in solvothermal processes but any basis for this choice is largely empirical. If there is a desire to adhere to the “main goal in MOF synthesis”<sup>14</sup> referred to earlier, knowledge of how to avoid complications is essential.

#### 4. The nature of crystals deposited in sub-critical solvothermal syntheses

While kinetic control of crystal formation cannot be excluded,<sup>121</sup> presuming that the conditions of sub-critical solvothermal synthesis are such as to ensure equilibrium, then it is solubility which determines the nature of the crystals deposited at the reaction temperature. Thus, their nature does not necessarily reflect that of the dominant species in solution, so any analysis of structures simply in terms of metal-ligand coordination is speculative and while it may be said to be supported by, say, DFT calculations, any species for which comparison might be made is unknown in the absence of a detailed understanding of the solution equilibria. The question as to how crystals of CPs and MOFs may form has been described as “difficult”,<sup>122</sup> and the formation of partially interpenetrated crystal structures<sup>68,69</sup> is an illustration of just how complicated it may be. A simple model<sup>122</sup> for systems involving labile metal ions is that small cyclic oligomers may first form a crystal and that this is followed by ring-opening polymerisation in the solid state, but again the limited data on solution speciation renders this uncertain as a general mechanism. Some form of molecular 3D printing<sup>123</sup> is perhaps an alternative mechanism. Regardless of this issue, another sometimes unexpected feature of sub-critical solvothermal synthesis is that the composition of the product in terms of metal:ligand ratio often does not match that of the initial reaction mixture. Purely empirical procedures have been followed to optimise yields without it being clear whether kinetic or thermodynamic factors are the more important.

#### 5. Conclusions

A short answer to the question posed in the title of this manuscript is “Quite a lot”. It would seem that even under the rela-

tively mild conditions of sub-critical solvothermal synthesis, a variety of other reactions may accompany that of metal-ion-ligand coordination and that these reactions can determine the yield and nature of the product. The success of solvothermal methods in general in providing materials with a remarkable range of properties and uses has, however, left obscure much of the basic chemistry leading to these products. While formation and crystallisation of coordination complexes in mixed solvents at elevated temperatures are processes perhaps outside the comfort zone for kinetic and thermodynamic measurements, there are opportunities for basic studies to considerably clarify the nature of the “black box” in solvothermal synthesis. NMR spectroscopy is one technique clearly suited to the study of solvent hydrolysis in mixed aqueous systems and has already been shown<sup>65</sup> to be valuable in following the stepwise decomposition and redox reactions of 2,3-pyrazinedicarboxylate under solvothermal conditions. Ligand isomerisation and oligomerisation reactions<sup>15</sup> are further examples of processes that could be readily studied by this and other spectroscopic methods such as the measurement of infra-red and circular dichroism spectra. These reactions are those occurring in homogeneous solutions but of course there are reactions of major importance involved in crystal formation and growth, and this is an area where methods for their direct study in sealed vessels have recently undergone important development.<sup>124</sup> The sophisticated techniques involved here offer, amongst other things, the capacity to study surface interactions of small species possibly produced by homogeneous solution reactions and thus elaborate in remarkable detail the nature of solvothermal synthesis in general.

#### Conflicts of interest

There are no conflicts to declare.

#### Data availability

No new data were used in the preparation of this article.

#### Acknowledgements

Dedicated to Dr Pierre Thuéry on the occasion of his retirement.

#### References

- 1 H. Taube, Rates and Mechanisms of Substitution in Inorganic Complexes in Solution, *Chem. Rev.*, 1952, **50**, 69–126.
- 2 C. Creutz, P. C. Ford and T. J. Meyer, Henry Taube: Inorganic Chemist Extraordinaire, *Inorg. Chem.*, 2006, **45**, 7059–7068.



- 3 M. Eigen, *Nobel Prize Lecture, Immeasurably Fast Reactions*, Nobel Foundation 1967.
- 4 L. Helm and A. E. Merbach, Inorganic and Bioinorganic Solvent Exchange Mechanisms, *Chem. Rev.*, 2005, **105**, 1923–1959.
- 5 S. F. Lincoln, Mechanistic Studies of Metal Aqua Ions: A Semi-Historical Perspective, *Helv. Chim. Acta*, 2005, **88**, 523–545.
- 6 M. Viciano-Chumillas, X. Liu, A. Leyva-Pérez, D. Armentano, J. Ferrando-Sorio and E. Pardo, Mixed-component metal-organic frameworks: Heterogeneity and complexity at the service of application performances, *Coord. Chem. Rev.*, 2022, **451**, 214273.
- 7 W. Gong, Z. Chen, J. Dong, Y. Liu and Y. Cui, Chiral Metal-Organic Frameworks, *Chem. Rev.*, 2022, **122**, 9078–9144.
- 8 K. Lv, S. Fichter, M. Gu, J. März and M. Schmidt, An updated status and trends in actinide metal-organic frameworks (An-MOFs): from synthesis to application, *Coord. Chem. Rev.*, 2021, **446**, 214011.
- 9 R. I. Walton, Perovskite Oxides Prepared by Hydrothermal and Solvothermal Synthesis: A Review of Crystallisation, Chemistry and Compositions, *Chem. – Eur. J.*, 2020, **26**, 9041–9069.
- 10 E. A. Dolgoplova, O. A. Ejagbavwo, C. R. Martin, M. D. Smith, W. Setyawan, S. G. Karakalos, C. H. Henager, H.-C. zur Loye and N. B. Shustova, Multifaceted Modularity: A Key for Stepwise Building of Hierarchical Complexity in Actinide Metal-Organic Frameworks, *J. Am. Chem. Soc.*, 2017, **139**, 16852–16861.
- 11 C. R. Kim, T. Uemura and S. Kitagawa, Inorganic nanoparticles in porous coordination polymers, *Chem. Soc. Rev.*, 2016, **45**, 3828–3845.
- 12 Y. Zhao, K. Li and J. Li, Review: Solvothermal Synthesis of Multifunctional Coordination Polymers, *Z. Naturforsch., B: J. Chem. Sci.*, 2014, **65**, 976–998.
- 13 P. H. Mutin and A. Vioux, Recent advances in the synthesis of inorganic materials via non-hydrolytic condensation and related low temperature routes, *J. Mater. Chem. A*, 2013, **1**, 11504–11512.
- 14 N. Stock and S. Biswas, Synthesis of metal-organic frameworks (MOFs): routes to various MOF topologies, morphologies, and composites, *Chem. Rev.*, 2012, **112**, 933–969.
- 15 W. L. Leong and J. J. Vittal, One-dimensional coordination polymers: complexity and diversity in structures, properties and applications, *Chem. Rev.*, 2011, **111**, 688–764.
- 16 D. Zhao, D. J. Timmens, D. Yuan and H.-C. Zhou, Tuning the Topology and Functionality of Metal-Organic Frameworks by Ligand Design, *Acc. Chem. Res.*, 2011, **44**, 123–135.
- 17 W. Lin, W. J. Rieter and K. M. L. Taylor, Modular Synthesis of Functional Nanoscale Coordination Polymers, *Angew. Chem., Int. Ed.*, 2009, **48**, 650–658.
- 18 G. Férey, Hybrid porous solids: past, present and future, *Chem. Soc. Rev.*, 2008, **37**, 191–214.
- 19 O. Yaghi, M. O'Keeffe, N. W. Ockwig, H. K. Chae, M. Eddaoudi and J. Kim, Reticular synthesis and the design of new materials, *Nature*, 2003, **423**, 705–714.
- 20 R. I. Walton, Subcritical solvothermal synthesis of condensed inorganic materials, *Chem. Soc. Rev.*, 2002, **31**, 230–238.
- 21 C. Mellot-Draznieks, S. Girard, G. Férey, J. C. Schön, Z. Cancarevic and M. Jansen, Computational Design and Prediction of Interesting Not-Yet-Synthesised Structures of Inorganic Materials by Using Building-Unit Concepts, *Chem. – Eur. J.*, 2002, **8**, 4102–4113.
- 22 J. C. Bailar, Jr., Coordination polymers, in *Preparative Inorganic Reactions*, ed. W. L. Jolly, Wiley Interscience, New York, 1964, vol. 1, pp 1–27.
- 23 Y. Huo, S. Xiu, L.-Y. Meng and B. Quan, Solvothermal synthesis and applications of micro/nano carbons: A review, *Chem. Eng. J.*, 2023, **451**, 138572.
- 24 S. Efe, C. Schauerte and K. Merz, Crystal engineering under hydro-thermal conditions: cocrystals and reactions of 3-cyanopyridine with glutaric acid, *Cryst. Growth Des.*, 2022, **22**, 2272–2278.
- 25 L. Liu, S. Wang, G. Jiang, B. Zhang, J. Yang, J. Wang, W. Liu and Y. Li, Solvothermal synthesis of zirconia nanomaterials: Latest developments and future, *Ceram. Int.*, 2022, **48**, 32649–32676.
- 26 M. H. Mruthunjayappa, N. S. Kotrappanavar and D. Mondal, New prospects on solvothermal carbonisation assisted by organic solvents, ionic liquids and eutectic mixtures – A critical review, *Progr. Mater. Sci.*, 2022, **126**, 100932.
- 27 S. P. Sasikala, P. Poulin and C. Aymonier, Advances in subcritical hydro-/solvothermal processing of graphene materials, *Adv. Mater.*, 2017, **29**(22), 1605473.
- 28 J. Lai, W. Niu, R. Luque and G. Xu, Solvothermal synthesis of metal nanocrystals and their applications, *Nano Today*, 2015, **10**, 240–267.
- 29 G. Demazeau, Solvothermal processes: definition, key factors governing the involved chemical reactions and new trends, *Z. Naturforsch.*, 2010, **65**, 999–1006.
- 30 G. Demazeau, Solvothermal reactions: an original route for the synthesis of novel materials, *J. Mater. Sci.*, 2008, **43**, 2104–2114.
- 31 A. Rabeneau, The Role of Hydrothermal Synthesis in Preparative Chemistry, *Angew. Chem., Int. Ed. Engl.*, 1985, **24**, 1026–1040.
- 32 O. M. Yaghi and H. Li, Hydrothermal Synthesis of a Metal-Organic Framework containing Large Rectangular Channels, *J. Am. Chem. Soc.*, 1995, **117**, 10401–10402.
- 33 Y. Xu, D. Yuan, B. Wu, L. Han, M. Wu, F. Jiang and M. Hong, 1D Tube, 2D Layer, and 3D Framework Derived from a New Series of Metal(II)-5-Aminodiacetic Isophthalate Coordination Polymers, *Cryst. Growth Des.*, 2006, **6**, 1168–1174.
- 34 A. L. Willis, Z. Chen, J. He, Y. Zhu, N. J. Turro and S. O'Brien, Metal Acetylacetonates as General Precursors for the Synthesis of Early Transition Metal Oxide Nanomaterials, *J. Nanomater.*, 2007, **2007**, 14858.



- 35 P. Thuéry, Uranyl Ion Complexes with Cucurbit[n]urils (n = 6, 7 and 8): A New Family of Uranyl-Organic Frameworks, *Cryst. Growth Des.*, 2008, **8**, 4132–4143.
- 36 X.-Q. Li, H.-B. Zhang, S.-T. Wu, J.-D. Lin, P. Lin, Z.-H. Lia and S.-W. Du, Synthesis, structures and luminescent properties of new Pb(II)/M(I) (M = K, Rb and Cs) frameworks based on dicarboxylic acids: a novel icosahedral Pb<sub>6</sub>-M<sub>6</sub> SBU, *CrystEngComm*, 2012, **14**, 936–944.
- 37 A. Thirumurugan, W. Li and A. K. Cheetham, Bismuth 2,6-pyridinedicarboxylates: Assembly of molecular units into coordination polymers, CO<sub>2</sub> sorption and photoluminescence, *Dalton Trans.*, 2012, **41**, 4126–4134.
- 38 H.-L. Jiang, D. Feng, K. Wang, Z.-Y. Gu, Z. Wei, Y.-P. Chen and H.-C. Zhou, An Exceptionally Stable Porphyrinic Zr Metal-Organic Framework Exhibiting pH-Dependent Fluorescence, *J. Am. Chem. Soc.*, 2013, **135**, 13934–13938.
- 39 C. Falaise, J.-S. Charles, C. Volkringer and T. Loiseau, Thorium Terephthalates Coordination Polymers Synthesised in Solvothermal DMF/H<sub>2</sub>O System, *Inorg. Chem.*, 2015, **54**, 2235–2242.
- 40 J. S. Caddy, T. B. Faust, I. M. Walton, J. M. Cox, J. B. Benedict, M. B. Solomon, P. D. Southon, C. J. Kepert and D. M. D'Alessandro, Photoactive and Physical Properties of an Azobenzene-Containing Coordination Framework, *Aust. J. Chem.*, 2017, **70**, 1171–1179.
- 41 R. Zhao, L. Mei, K.-Q. Hu, M. Tian, Z.-F. Chai and W.-Q. Shi, Bimetallic Uranyl Organic Frameworks Supported by Transition-Metal-Ion-Based Metalloligand Motifs: Synthesis, Structure Diversity and Luminescence Properties, *Inorg. Chem.*, 2018, **57**, 6084–6094.
- 42 C. Sun, M. Schäferling, U. Resch-Genger and M. Gradziński, Solvothermal Synthesis of Lanthanide-doped NaYF<sub>4</sub> Upconversion Crystals with Size and Shape Control: Particle Properties and Growth Mechanism, *ChemNanoMat*, 2021, **7**, 174–183.
- 43 Y. H. Lee, Y. Atoini, S. Kusumoto, S. Hayami, Y. Kim, J. Harrowfield and P. Thuéry, Mixed-ligand uranyl ion complexes with two flexible, pyridinium-based dicarboxylate zwitterions and simple anionic dicarboxylates, *CrystEngComm*, 2025, **27**, 1034–1043.
- 44 Y. Gao, X. Yang, J. Su and L. Li, A stable scandium(III) metal-organic framework with introduced nitrate ion enhancing selectivity in the separation of MTO products, *Chin. J. Struct. Chem.*, 2025, **44**, 100576.
- 45 S. Huh, S.-J. Kim and Y. Kim, Porphyrinic metal-organic frameworks from custom-designed porphyrins, *CrystEngComm*, 2016, **18**, 345–368.
- 46 Q. Zha, X. Rui, T. Wei and Y. Xie, Recent advances in design strategies for porphyrin-based coordination polymers, *CrystEngComm*, 2014, **16**, 7371–7384.
- 47 M. Inoue, Solvothermal Synthesis, in *Chemical Processing of Ceramics*, CRC Press, Taylor and Francis Group, New York, 2nd edn, 2005, ch. 2.
- 48 C. Zou, Z. Zhang, X. Xu, Q. Gong, J. Li and C.-D. Wu, A Multifunctional Organic-Inorganic Hybrid Structure based on Mn(III)-Porphyrin and Polyoxometallate as a Highly Effective Dye Scavenger and Heterogeneous Catalyst, *J. Am. Chem. Soc.*, 2012, **134**, 87–90.
- 49 A. J. Parker, The effects of solvation on the properties of anions in dipolar aprotic solvents, *Q. Rev., Chem. Soc.*, 1962, **16**, 163–187.
- 50 A. J. Parker, Protic-Dipolar Aprotic Solvent Effects on Rates of Bimolecular Reactions, *Chem. Rev.*, 1969, **69**, 1–32.
- 51 P. L. Goggin, Sulphoxides, Amides, Amine Oxides and related ligands, in *Comprehensive Coordination Chemistry*, ed. G. Wilkinson, J. A. McCleverty and R. D. Gillard, Pergamon Press, Oxford, 1987, ch. 15.8, vol. 2, p. 487.
- 52 S. Funahashi and Y. Inada, Solvation Structures and Solvent Exchange Reactions of Metal Ions in Various Coordinating Solvents, *Bull. Chem. Soc. Jpn*, 2002, **75**, 1901–1925.
- 53 Y. He, Y. Zhu and N. Wu, Mixed solvents: a key in solvothermal synthesis of KTaO<sub>3</sub>, *J. Solid State Chem.*, 2004, **177**, 2985–2990.
- 54 D. Xu, Z. Liu, J. Liang and Y. Qian, Solvothermal synthesis of CdS nanowires in a mixed solvent of ethylenediamine and dodecanethiol, *J. Phys. Chem. B*, 2005, **109**, 14344–14348.
- 55 M.-G. Ma, F. Deng and K. Yao, Solvothermal synthesis and characterisation of LaPO<sub>4</sub> with hierarchical nanostructure in mixed solvents of ethanol and water, *Mater. Lett.*, 2014, **124**, 173–176.
- 56 A. Nohara, S. Takeshita and T. Isobe, Mixed-solvent strategy for solvothermal synthesis of well-dispersed YBO<sub>3</sub>: Ce<sup>3+</sup>, Tb<sup>3+</sup> nanocrystals, *RSC Adv.*, 2014, **4**, 11219–11224.
- 57 K.-Q. Hu, X. Jiang, C.-Z. Wang, L. Mei, Z.-N. Xie, W.-Q. Tao, X.; X.-L. Zhang, Z.-F. Chai and W.-Q. Shi, Solvent-Dependent Synthesis of Porous Anionic Uranyl-Organic Frameworks Featuring a Highly Symmetrical ctn or bor Topology for Selective Dye Adsorption, *Chem. – Eur. J.*, 2017, **23**, 529–532.
- 58 B. Tan, Y. Luo, X. Liang, S. Wang, X. Gao, Z. Zhang and Y. Fang, Mixed Solvothermal Synthesis of MIL-101(Cr) and Its Water Adsorption/Desorption Performance, *Ind. Eng. Chem. Res.*, 2019, **58**, 2983–2990.
- 59 S. K. Dey, P. Mitra and A. Mukherjee, Influence of Solvent in Solvothermal Syntheses: Change of Nuclearity in Mixed-Valence CoII/III Complexes of an O-Donor-Rich Schiff Base Ligand, *Cryst. Growth Des.*, 2015, **15**, 706–717.
- 60 O. A. El Seoud, Solvation in pure and mixed solvents: Some recent developments, *Pure Appl. Chem.*, 2007, **79**, 1135–1151.
- 61 W. E. Waghorne, Thermodynamics of solvation in mixed solvents, *Chem. Soc. Rev.*, 1993, **22**, 285–292.
- 62 S. Kusumoto, Y. Koide, S. Hayami, Y. Kim, J. Harrowfield and P. Thuéry, Synthesis of uranyl ion coordination polymers with zwitterionic carboxylate ligands: comparing solvothermal and ambient conditions, *J. Inclusion Phenom. Macrocyclic Chem.*, 2025, **105**, 167–174.
- 63 Y. Hao, P. Kegler, T. E. Albrecht-Schmitt, S. Wang, Q. Dong and E. V. Alexseev, Two-Dimensional Uranyl



- Borates: From Conventional to Extreme Synthetic Conditions, *Eur. J. Inorg. Chem.*, 2020, 407–416.
- 64 E. C. Constable, G. Zhang, C. E. Housecroft and J. A. Zampese, Zn(II) coordination polymers, metallohexacycles and metallocapsules - do we understand self-assembly in metallosupramolecular chemistry: algorithms or serendipity?, *CrystEngComm*, 2011, 13, 6864–6870.
- 65 K. E. Knope, H. Kimura, Y. Yasaka, M. Nakahara, M. B. Andrews and C. L. Cahill, Investigation of in Situ Oxalate Formation from 2,3-Pyrazinedicarboxylate under Hydrothermal Conditions using Nuclear Magnetic Resonance Spectroscopy, *Inorg. Chem.*, 2012, 51, 3883–3890.
- 66 K. M. O. Jensen, C. Tyrsted, M. Bremholm and B. B. Iversen, *In situ* Studies of Solvothermal Synthesis of Energy Materials, *ChemSusChem*, 2014, 7, 1594–1611.
- 67 P. Mahata, M. Prabu and S. Natarajan, Role of Temperature and Time in the Formation of Infinite -O-M-O- Linkages and Isolated Clusters in MOFs: A Few Illustrative Examples, *Inorg. Chem.*, 2008, 47, 8451–8463.
- 68 Y. Kim, Sa. Lee, Y.-P. Chen, B. Lee, Su. Lee and J. Park, Partial-Interpenetration-Controlled UiO-Type Metal-Organic Framework and its Catalytic Activity, *Small*, 2024, 20, 2305999.
- 69 A. Ferguson, L. Liu, S. J. Tapperwijn, D. Perl, F.-X. Coudert, S. Van Cleuvenbergen, T. Verbiest, M. A. van der Veen and S. G. Telfer, Controlled partial interpenetration in metal-organic frameworks, *Nat. Chem.*, 2016, 8, 250–257.
- 70 J. Muzart, N,N-dimethylformamide: much more than a solvent, *Tetrahedron*, 2009, 65, 8313–8323.
- 71 B. Panda and G. Albano, DMF as a CO Surrogate in Carbonylation Reactions: Principles and Applications to the Synthesis of Heterocycles, *Catalysis*, 2021, 11, 1531–1555.
- 72 T. J. Mooibroek, P. Gamez, A. Pevec, M. Kasunic, B. Kozlevcar, W.-T. Fu and J. Reedijk, Efficient, stable, tunable, and easy to synthesize, handle and recycle luminescent materials:  $[H_2NMe_2]_3[Ln(III)(2,6\text{-dipicolinate})_3]$  ( $Ln = Eu, Tb$ , or its solid solutions), *Dalton Trans.*, 2010, 39, 6483–6487.
- 73 D. A. Buckingham, J. M. Harrowfield and A. M. Sargeson, Metal Ion Activation in the Base Hydrolysis of amides. Hydrolysis of the Dimethylformamidepentaaamminecobalt (III) Ion, *J. Am. Chem. Soc.*, 1974, 96, 1726–1729.
- 74 T. Cottineau, M. Richard-Plouet and J.-Y. Mevellec, Hydrolysis and Complexation of N,N-Dimethylformamide in New Nanostructured Titanium Dioxide Hybrid Inorganic Sols and Gels, *J. Phys. Chem. C*, 2011, 115, 12269–12274.
- 75 Y.-X. Tan, Y.-P. He and J. Zhan, Pore partition effect on gas sorption properties of an anionic metal-organic framework with exposed  $Cu^{2+}$  coordination sites, *Chem. Commun.*, 2011, 47, 10647–10649.
- 76 S.-J. Liu, C. Cao, F. Yang, M.-H. Yu, S.-L. Yao, T.-F. Zheng, W.-W. He, H.-Xi. Zhao, T.-L. Hu and X.-H. Bu, High Proton Conduction in Two CoII and MnII Anionic Metal–Organic Frameworks Derived from 1,3,5-Benzenetricarboxylic Acid  $\{[M_2Cl_2(BTC)_{4/3}](Me_2NH_2)^+_2 \cdot 4/3H_2O\}_n$  ( $M = Co$  (1) and  $Mn$  (2)), *Cryst. Growth Des.*, 2016, 16, 6776–6780.
- 77 Y.-N. Gong, S.-Y. Zhang, P. Xiong, Y.-R. Xie, Z.-Y. Du and D.-C. Zhong, A two-fold interpenetrating porous metal-organic framework with a large solvent-accessible volume and selective sensing of nitroaromatic explosives, *J. Coord. Chem.*, 2016, 69, 996–1004.
- 78 J.-W. Zhang, M.-C. Hu, S.-N. Li, Y.-C. Jiang and Q.-G. Zhai, Ligand Torsion Triggered Two Robust Fe-Tetratopic Carboxylate Frameworks with Enhanced Gas Uptake and Separation Performance, *Chem. – Eur. J.*, 2017, 23, 6693–6700.
- 79 L. Senior and A. Linden, Coordination polymers incorporating Bi(III) and 2,4,6-pyridine tricarboxylic acid and its derivatives: Synthesis, structure and topology, *Polyhedron*, 2020, 184, 114564.
- 80 H. Chen, Z. Zhang, T. Hu and X. Zhang, An  $NH_2$ -modified  $\{Eu(III)\}$ -organic framework for the efficient chemical fixation of  $CO_2$  and highly sensitive sensing of 2,4,6-trinitrophenol, *Inorg. Chem. Front.*, 2021, 8, 4376–4385.
- 81 F. M. Amombo Noa, M. Abrahamsson, E. Ahlberg, O. Cheung, C. R. Göb, C. J. McKenzie and L. Öhrström, A unified topology approach to dot-, rod- and sheet-MOFs, *Chem*, 2021, 7, 2491–2512.
- 82 P. Thuéry, E. Rivière and J. M. Harrowfield, Uranyl- and Uranyl-3d-Block-Cation Complexes with 1,3-adamantanedicarboxylate: Crystal Structures, Luminescence and Magnetic Properties, *Inorg. Chem.*, 2015, 54, 2838–2850.
- 83 P. Thuéry and J. M. Harrowfield, Solvent effects in solvo-hydrothermal synthesis of uranyl ion complexes with 1,3-adamantanediacetate, *CrystEngComm*, 2015, 17, 4006–4018.
- 84 P. Thuéry and J. M. Harrowfield, Two-dimensional assemblies in f-element ion ( $UO_2^{2+}$ ,  $Yb^{3+}$ ) complexes with two cyclohexyl-based polycarboxylates, *Polyhedron*, 2015, 98, 5–11.
- 85 P. Thuéry and J. M. Harrowfield, Modulation of the Structure and Properties of Uranyl Ion Coordination Polymers Derived from 1,3,5-Benzenetriacetate by Incorporation of Ag(I) or Pb(II), *Inorg. Chem.*, 2016, 55, 6799–6816.
- 86 P. Thuéry, Y. Atoini and J. Harrowfield, Uranyl–Organic Coordination Polymers with trans-1,2-, trans-1,4- and cis-1,4-Cyclohexanedicarboxylates: Effects of Bulky  $PPh_4^+$  and  $PPh_3Me^+$  Counterions, *Cryst. Growth Des.*, 2018, 18, 2609–2619.
- 87 P. Thuéry, Y. Atoini and J. Harrowfield, Closed Uranyl-Dicarboxylate Oligomers: A Tetranuclear Metallatrilcycle with Uranyl Bridgeheads and 1,3-Adamantanedicarboxylate Linkers, *Inorg. Chem.*, 2018, 57, 7932–7939.
- 88 P. Thuéry, Y. Atoini and J. Harrowfield, Chiral Discrete and Polymeric Uranyl Ion Complexes with (1R,3S)-(+)-Camphorate Ligands: Counterion-Dependent Formation of a Hexanuclear Cage, *Inorg. Chem.*, 2019, 58, 870–880.



- 89 P. Thuéry, Y. Atoini and J. Harrowfield, Structure-directing effects of coordinating solvents, ammonium and phosphonium counterions in uranyl ion complexes with 1,2-, 1,3- and 1,4- phenylenediacetates, *Inorg. Chem.*, 2020, **59**, 2503–2518.
- 90 P. Thuéry and J. Harrowfield, 2,5-Thiophenedicarboxylate: an Interpenetration-Inducing Ligand in Uranyl Chemistry, *Inorg. Chem.*, 2021, **60**, 9074–9083.
- 91 P. Thuéry and J. Harrowfield, Contrasting Networks and Entanglements in Uranyl Ion Complexes with Adipic and trans,trans-Muconic Acids, *Inorg. Chem.*, 2022, **61**, 2790–2803.
- 92 P. Thuéry and J. Harrowfield, (R,R)-Tartrate as a polytopic ligand for  $\text{UO}_2^{2+}$ : mono- and dimeric coordination polymers including di- and tetranuclear subunits, *Polyhedron*, 2023, **235**, 116346.
- 93 L. A. Borkowski and C. L. Cahill, Topological Evolution in Uranyl Dicarboxylates: Synthesis and Structures of One-Dimensional  $\text{UO}_2(\text{C}_6\text{H}_8\text{O}_4)(\text{H}_2\text{O})_2$  and Three-Dimensional  $\text{UO}_2(\text{C}_6\text{H}_8\text{O}_4)$ , *Inorg. Chem.*, 2003, **42**, 7041–7045.
- 94 P. F. S. Cartwright, E. J. Newman and D. W. Wilson, Precipitation from homogeneous solution. A Review, *Analyst*, 1967, **92**, 663–679.
- 95 J.-F. Qian, W.-J. Tian, S. Yang, Z.-H. Sun, L. Chen, M.-J. Wei, Z. Wu, M.-Y. He, Z.-H. Zhang and L. Mei, Auxiliary-Ligand Dependent Adaptive Regulation of Uranyl Coordination in Mixed-Ligand Uranyl Compounds of Flexible Benzenetetracarboxylic Acid, *Inorg. Chem.*, 2020, **59**, 17659–17670.
- 96 J. Harrowfield, Y. Atoini and P. Thuéry, Plumbing the uncertainties of solvothermal synthesis involving uranyl ion carboxylate complexes, *CrystEngComm*, 2022, **24**, 1475–1484.
- 97 P. Thuéry and J. Harrowfield, Uranyl Ion Complexes with all-cis-1,3,5- Cyclohexanetricarboxylate: Unexpected Framework and Nanotubular Assemblies, *Cryst. Growth Des.*, 2014, **14**, 4214–4225.
- 98 P. Thuéry and J. Harrowfield, Structural Consequences of 1,4-Cyclohexanedicarboxylate Cis/Trans Isomerism in Uranyl Ion Complexes: From Molecular Species to 2D and 3D Entangled Nets, *Inorg. Chem.*, 2017, **56**, 13464–13481.
- 99 Z. Weng, Z.-H. Zhang, T. Olds, M. Sterniczuk and P. C. Burns, Copper(I) and Copper(II) Uranyl Heterometallic Hybrid Materials, *Inorg. Chem.*, 2014, **53**, 7993–7998.
- 100 E. H. Gamage, J. K. Clark, M. Yazbak, H.-P. Cheng, M. Shatruck and K. Kovnir, Solvothermal Synthesis of  $[\text{Cr}_7\text{S}_8(\text{en})_8\text{Cl}_2]\text{Cl}_3 \cdot 2\text{H}_2\text{O}$  with Magnetically Frustrated  $[\text{Cr}_7\text{S}_8]^{5+}$  Double-Cubes, *Chem. – Eur. J.*, 2022, **28**, e202103761.
- 101 S.-X. Wang, M. Chrzanowski, W.-Y. Gao, L. Vojtas, Y.-S. Chen, M. J. Zaworotko and S. Ma, Vertex-directed self-assembly of a high-symmetry supramolecular building block using a custom-designed porphyrin, *Chem. Sci.*, 2012, **3**, 2823–2827.
- 102 M. B. Andrews and C. L. Cahill, In situ oxalate formation during hydrothermal synthesis of uranyl hybrid materials, *CrystEngComm*, 2011, **13**, 7068–7078.
- 103 D. E. Felton, T. A. Kohlgruber, Z. D. Tucker, E. M. Gulotty, B. L. Ashfeld and P. C. Burns, Utilising ionic liquids as bifunctional reagents for the ionothermal synthesis of uranyl compounds, *Cryst. Growth Des.*, 2023, **23**, 8311–8318.
- 104 P. Thuéry, Y. Atoini and J. Harrowfield, Crown Ethers and their Alkali Metal Ion Complexes as Assembler Groups in Uranyl–Organic Coordination Polymers with cis-1,3-, cis-1,2- and trans-1,2-Cyclohexanedicarboxylates, *Cryst. Growth Des.*, 2018, **18**, 3167–3177.
- 105 P. Thuéry, Y. Atoini and J. Harrowfield, Triple-armed aliphatic tricarboxylic acids as sources of ligands for uranyl ion: influence of bridgehead functionalization, *CrystEngComm*, 2023, **25**, 3904–3915.
- 106 A. R. Katritzky, D. A. Nichols, M. Siskin, R. Muragan and M. Balasubramanian, Reactions in High-Temperature Aqueous Media, *Chem. Rev.*, 2001, **101**, 837–892.
- 107 H. Kaur, N. Devi, S. Singh Siwal, W. F. Alsanie, M. K. Thakur and V. K. Thakur, Metal–Organic Framework-Based Materials for Wastewater Treatment: Superior Adsorbent Materials for the Removal of Hazardous Pollutants, *ACS Omega*, 2023, **8**, 9004–9030.
- 108 Z. Ni and R. I. Masel, Rapid Production of Metal–Organic Frameworks by Microwave-Assisted Solvothermal Synthesis, *J. Am. Chem. Soc.*, 2006, **128**, 12394–12395.
- 109 H. M. L. Robert, F. Kundrat, E. Bermudez-Ureña, H. Rigneault, S. Monneret, R. Quidant, J. Polleux and G. Baffou, Light-Assisted Solvothermal Chemistry using Plasmonic Nanoparticles, *ACS Omega*, 2016, **1**, 2–8.
- 110 D. Sud and G. Kaur, A comprehensive review on synthetic approaches for metal-organic frameworks: From traditional solvothermal to greener protocols, *Polyhedron*, 2021, **193**, 114897.
- 111 Z. Kovács, C. Molnár, U. L. Štangar, V.-M. Cristea, Z. Pap, K. Bernadi and L. Baia, Optimization Method of the Solvothermal Parameters Using Box-Behnken Experimental Design - The Case Study of ZnO Structural and Catalytic Tailoring, *Nanomaterials*, 2021, **11**, 1334.
- 112 Z.-X. Xu, Y. Xiao, Y. Kang, L. Zhang and J. Zhang, Homochiral Cluster–Organic Frameworks Constructed from Enantiopure Lactate Derivatives, *Cryst. Growth Des.*, 2015, **15**, 4676–4686.
- 113 H. Kohlmann, Looking into the Black Box of Solid-State Synthesis, *Eur. J. Inorg. Chem.*, 2019, 4174–4180.
- 114 Y. Huang, B. Yan and M. Shao, Solvothermal synthesis, crystal structure and characterizations of three quaternary lanthanide homophthalate coordination polymers, *Solid State Sci.*, 2008, **10**, 1132–1138.
- 115 H. M. Felmy, K. T. Bennett and S. B. Clark, The impact of mixed solvents on the complexation thermodynamics of Eu(III) by simple carboxylate and amino carboxylate ligands, *J. Chem. Thermodyn.*, 2017, **114**, 83–92.
- 116 L. Rao, G. Tian, P. Di Bernardo and P.-L. Zanonato, Hydrolysis of Plutonium(VI) at Variable Temperatures (283–343 K), *Chem. – Eur. J.*, 2011, **17**, 10985–10990.



- 117 P.-L. Zanonato, P. Di Bernardo, A. Bismondo, G. Lui, X. Chen and L. Rao, Hydrolysis of Uranium(VI) at Variable Temperatures (10–85 °C), *J. Am. Chem. Soc.*, 2004, **126**, 5515–5522.
- 118 X.-M. Chen and M.-L. Tong, Solvothermal in Situ Metal/Ligand Reactions: A New Bridge between Coordination Chemistry and Synthetic Organic Chemistry, *Acc. Chem. Res.*, 2007, **40**, 162–170.
- 119 H. D. Burrows and T. J. Kemp, The Photochemistry of the Uranyl Ion, *Chem. Soc. Rev.*, 1974, **3**, 139–165.
- 120 P. Thuéry and J. Harrowfield, Stepwise Introduction of Flexibility into Aromatic Dicarboxylates Forming Uranyl Ion Coordination Polymers: a Comparison of the Phthalate Relatives 2-Carboxyphenylacetate and 1,2-Phenylenediacetate, *Eur. J. Inorg. Chem.*, 2021, 2182–2192.
- 121 L. Carlucci, G. Ciani, J. M. Garcia-Ruiz, M. Moret, D. M. Proserpio and S. Rizzato, Crystallisation Behaviour of Coordination Polymers. 1. Kinetic and Thermodynamic Features of 1,3-Bis(4-pyridyl)propane/MCl<sub>2</sub> Systems, *Cryst. Growth Des.*, 2009, **9**, 5024–5034.
- 122 S. L. James, Tackling a difficult question: how do crystals of coordination polymers form?, *IUCrJ*, 2015, **1**, 263–264.
- 123 J. Hengsteler, K. A. Kanen, L. Khasanova and D. Momotenko, Beginner's Guide to Micro- and Nanoscale Electrochemical Additive Manufacturing, *Annu. Rev. Anal. Chem.*, 2023, **16**, 71–91.
- 124 M. J. Van Vleet, T. Wang, X. Li and J. R. Schmidt, In Situ, Time-Resolved and Mechanistic Studies of Metal-Organic Framework Nucleation and Growth, *Chem. Rev.*, 2018, **118**, 3681–3721.

