

Faraday Discussions

Accepted Manuscript



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

This article can be cited before page numbers have been issued, to do this please use: R. Stuckert, F. Pohl, N. Shkodich, O. Prymak, N. Koch, U. Schürmann, M. Farle, L. Kienle, S. Barcikowski and C. Rehbock, *Faraday Discuss.*, 2025, DOI: 10.1039/D5FD00087D.

ARTICLE

Amorphization of Laser-fabricated Ignoble High-Entropy Alloy Nanoparticles and its Impact on Surface Composition and Electrochemistry

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Robert Stuckert,^a Felix Pohl,^b Natalia Shkodich,^c Oleg Prymak,^d Nico Koch,^a Ulrich Schürmann,^b Michael Farle,^c Lorenz Kienle,^b Stephan Barcikowski,^a and Christoph Rehbock^{*a}

High-entropy alloy nanoparticles (HEA NPs) constitute an interesting material class with a high potential as heterogeneous catalysts due to their exceptional compositional and structural tunability and the complex interplay of different element-specific surface sites. Laser ablation in liquids (LAL) is a kinetically controlled synthesis method that allows the generation of colloidal HEA NPs. With CrMnFeCoNi-NPs, a facile control of the NP phase structure, switching between crystalline and amorphous by applied laser pulse duration, has been previously reported, attributed to the different particle solidification times and carbon incorporation pathways. However, neither the replacement of the oxygen-affine Mn by the sp²-carbon coupling element Cu, nor the transferability of the pulsed laser fabrication process from bulk target to micropowder feedstock processing has been studied. In the present work, we use scanning transmission electron microscopy, equipped with energy-dispersive X-ray spectroscopy (STEM-EDX), high-resolution transmission electron microscopy (HRTEM), selected area electron diffraction (SAED), and X-ray diffraction (XRD) to demonstrate the transferability of internal phase structure tunability to the CrFeCoNiCu alloy and confirm ns- and ps-pulsed LAL yielding amorphous and crystalline HEA NPs with diameters of 10–40 nm, respectively. Furthermore, we examine the generation of CrMnFeCoNi and CrFeCoNiCu nanoparticles by scalable, fully continuous ns-pulsed microparticle laser fragmentation in liquid (MP-LFL) using a high-power UV-laser and find the emergence of amorphous phase structures only in the Cu-containing nanoparticles, a phenomenon we attribute to copper-catalyzed carbon incorporation into the HEA NPs. These studies are complemented by a detailed characterization of the surface electrochemistry of the HEA NPs by alkaline cyclic voltammetry (CV) and elemental compositions in surface near volumes, quantified by X-ray photoelectron spectroscopy (XPS). We elucidate that primarily the chemical composition (Mn vs. Cu) and only to a lower extent, the phase structure (amorphous vs. crystalline) determine surface potential, electrochemical stability upon multiple CV cycling, and surface element distribution of the particles. Finally, the activity of the HEA NPs in the oxygen evolution reaction (OER) is evaluated by linear sweep voltammetry (LSV), where we find amorphous CrMnFeCoNi HEA NPs to be more active (lower overpotential, higher current density) than their crystalline counterparts, motivating future application-focused work and transfer to other material systems and relevant reactions.

Introduction

High-entropy alloy nanoparticles (HEA NPs), also named compositionally complex alloy (CCA) NPs or compositionally complex solid solutions (CCSS) NPs¹ constitute a relatively new class of nanomaterials with high applicability in heterogeneous catalysis^{2,3}, showing increased activities in both nitrogen-

converting reactions⁴, electrocatalytic water-splitting reactions^{5,6}, and more³, resulting from synergistic interplay between multiple elements. HEA NPs were reported to form simple crystalline face-centered (fcc)⁷, body-centered cubic (bcc)⁸, and hexagonal close-packed (hcp)⁹ structures, while amorphous metallic glass HEA NPs have been reported as well.^{10,11} However, how the phase structure (amorphous vs crystalline) in HEA NPs affects electrocatalytic performance has not been addressed in detail yet, though several studies have reported an activity boost in amorphous materials compared to their crystalline counterparts, valid for different material systems and catalyzed reactions.^{12–15}

Synthesis of HEA NPs has been frequently reported for noble and ignoble alloy systems, while the latter gained special interest due to lower costs, carbon footprint, and higher availability.¹⁶ Synthesis strategies like carbothermal shock synthesis¹⁷, chemical reduction methods¹⁸, fast-moving bed

^a Technical Chemistry I and Center for Nanointegration Duisburg-Essen (CENIDE), University of Duisburg-Essen, 45141 Essen, Germany.


^b Institute for Material Science, Synthesis and Real Structure, Faculty of Engineering, Christian-Albrechts University of Kiel, 24143 Kiel, Germany.

^c Faculty of Physics and Center for Nanointegration Duisburg-Essen (CENIDE), University of Duisburg-Essen, 47057 Duisburg, Germany.

^d Inorganic Chemistry and Center for Nanointegration Duisburg-Essen (CENIDE), 45141 Essen, Germany.

Supplementary Information available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x





pyrolysis¹⁹, solvothermal methods²⁰, and arc-discharge⁸ were reported to yield crystalline fcc, or bcc-type HEA NPs, while FeCoNiCrMo_x HEA NPs via inert gas condensation¹¹, CrMnFeCoNi HEA NPs via direct current sputtering¹⁰, CoFeNiLaPt HEA NPs by electrodeposition²¹, as well as high-entropy oxide NPs²² and high-entropy phosphide NPs²³ were shown to form amorphous structures. Although the aforementioned synthesis techniques give access to HEA NPs with uniformly mixed elements and an impressive number of individual elements^{17,24} they often lack flexibility, as they are restricted to the carriers they were generated on or lack the flexibility of fabricating colloidal HEA NPs.²⁵ Fabrication of HEA NPs in the colloidal state allows their deposition on different support materials providing supported catalysts with different loadings while keeping the particle size constant.²⁶ Nanoparticle generation by laser synthesis and processing of colloids (LSPC)²⁷ yields colloidal nanoparticles without the need for additional stabilizing additives, and was shown to scale with laser power²⁸ to gain energy-specific mass productivities of 5–10 µg/J for LAL^{29,30} and up to 18 µg/J for LFL³¹, enabling multiple grams per hour productivity.²⁹ The high flexibility of the used liquid³² provides a high variety of synthesis conditions, and NP size and mass loading on the support can be freely tuned²⁶ making LSPC, particularly laser ablation in liquids (LAL) and laser fragmentation in liquids (LFL), an advantageous synthesis strategy. An emerging field in LSPC is the fragmentation of microparticles into nanoscale particles (microparticle laser fragmentation in liquid, MP-LFL) for both organic^{33–35} and

inorganic^{31,36,37} materials down to nanocluster-sized particles (< 3 nm)^{31,38}, that can be operated continuously. Synthesis of colloidal HEA NPs via LAL has been reported in a few studies, where crystalline CrMnFeCoNi HEA NPs with uniformly mixed elements were synthesized via LAL in ethanol^{1,39}, though minor oxide-driven segregations of Mn were reported by Tahir et al., who laser-fabricated CrMnFeCoNi HEA NPs in ethanol as well.⁴⁰ Johny et al. compared the catalytic activity of quinary CrMnFeCoNi and senary CrMnFeCoNiMo HEA NPs via ns-pulsed laser ablation in acetonitrile, observing the formation of mainly amorphous HEA NPs with only minor contributions of fcc phases. The authors stated that the amorphous structure is stabilized by the formation of graphitic carbon shells that impede the crystallization of the metallic matrix.⁴¹ As these studies utilized a bulk alloy target as starting material, it is unclear if different ablation dynamics of LAL and MP-LFL (where photomechanical effects may prominently contribute³¹ due to the curved ablation surface) affect the yielded HEA nanoparticle composition and structure. Further, colloidal HEA NP generation via MP-LFL has not been reported before, although alloy micropowders in a well-defined composition, fabricated by high-energy ball milling⁴², is an attractive feedstock material for MP-LFL, promising possible scale-up optimization. In previous experiments, we could show a structural directionality of LAL pulse duration on the internal phase structure of CrMnFeCoNi HEA NPs, yielding amorphous particles by ns-pulses and crystalline particles, at comparable sizes, by ps-pulses – a phenomenon we linked to differences of carbon



incorporation into the particles due to pulse-specific differences in particle cooling history.⁴³ This work addresses whether pulse-duration-driven amorphization rules may be transferable from CrMnFeCoNi to CrFeCoNiCu. Furthermore, we investigate whether such amorphous HEA NPs can be obtained from a fully continuous, scalable MP-LFL process, using a ns-pulsed high-power UV laser, differentiating how process (LAL vs. MP-LFL) and material (Mn vs. Cu) specific input variables affect HEA NP formation mechanisms. This is complemented by a detailed analysis of the HEA NPs' surface chemistry and composition (using cyclic voltammetry (CV) and X-ray photoelectron spectroscopy (XPS)), the structural and compositional analysis (by BET, XRD, HRTEM), and by the activity of the corresponding HEA NPs in the oxygen evolution reaction (OER). The study design is summarized in Figure 1.

Results and Discussion

Volume sensitive characterization of CrFeCoNiCu NPs from laser ablation in ethanol – Material dependency of pulse-duration-driven amorphization rules

Firstly, we investigated how our previously proposed pulse duration-controlled amorphization mechanism in CrMnFeCoNi NPs, where ps-LAL yielded crystalline HEA NPs and ns-LAL amorphous HEA NPs⁴³, is transferable to the related CrFeCoNiCu material system. LAL of CrFeCoNiCu bulk targets in ethanol leads to brownish-colored colloids with mass concentrations between 100–200 mg/L for both ps- and ns-LAL in ethanol, determined by differential weighing of the targets before and after ablation. The produced NPs are almost equimolar alloys, with the composition (determined via large area TEM-EDX measurements) of Cr₂₁Fe₂₂Co₂₂Ni₂₂Cu₁₃ for ps-LAL and Cr₂₁Fe₂₀Co₂₀Ni₂₀Cu₁₉ for ns-LAL (Supporting Information, Tables S1 and S2), which resembles the average composition of the bulk target of Cr₂₂Fe₂₂Co₁₉Ni₂₁Cu₁₇ as determined by XRF and SEM-EDX (Supporting Information, Section S2).

The number-weighted mean particle diameters from TEM evaluation for ps- and ns-LAL-synthesized HEA NPs are $d = 18 \pm 9$ nm and $d = 26 \pm 13$ nm, respectively (Supporting Information, Figure S1). Elemental maps of individual NPs (Figure 2a and 2b) show homogeneous distributions of Cr, Fe, Co, Ni, and Cu, though minor segregation can be correlated with enrichment of copper and a depletion of chromium or vice versa (red arrows in Figure 2a and 2b). This aligns with segregation trends in bulk⁴⁴, microscale⁴², or nanoscale⁴⁵ HEAs, and reflects the negligible miscibility of bulk Cu and Cr⁴⁶, though de-mixing may also be driven by Cr-oxide species. Similar segregation is observed in arc-melted CrFeCoNiCu bulk targets (Supporting Information, Figure S2), though overall elemental distributions in HEA NPs remains largely uniform and resembles the bulk target's surface. Interestingly, pulse duration-driven structural heterogeneity, as reported earlier for CrMnFeCoNi HEA NPs^{1,39,41,43} occurs analogously in CrFeCoNiCu, as indicated by XRD (Figure 2c). Ps-LAL yields highly crystalline NPs with distinct reflections matching a fcc structure and two different lattice

parameters ($a_1 = 0.3588$ nm, CS = 35 nm and $a_2 = 0.3602$ nm, CS = 13 nm), resembling the found lattice constants in the bulk target ($a_1 = 0.3584$ nm, $a_2 = 3.607$ nm, Supporting Information, Section S1, Figure S2 and Section S2, Figure S3) and an asymmetry in reflections, arising from the presence of the two different lattice parameters. As these two different lattice constants with equivalent values are found in the bulk phase as well as in the NPs, we can assume that contributions of particle diameter to the lattice constant values are negligible. The presence of different lattice parameters in ps-LAL-generated CrFeCoNiCu HEA NPs is likely due to Cr-Cu compositional variations, verified by single particle EDX analysis (Tables S3 and S4, Supporting Information), and can be attributed to the limited mutual solubility between Cr and Cu under equilibrium conditions, despite the rapid quenching during LAL. This immiscibility can initiate nanoscale phase separation which would lead to these different lattice parameters. In the single particle compositions, we found the standard deviations of the Cu and Cr content in individual particles to be 3–4 times and 2 times higher, respectively, than those of Fe, Co, and Ni. Similar phase distinctions have been observed before by Shkodich et al., who reported lattice parameters of 0.3608 nm for Cu-rich/Cr-depleted and 0.3572 nm for Cr-rich/Cu-depleted regions in CrFeCoNiCu HEA microparticles after annealing⁴², so it is conceivable that the observed differences in the lattice parameters in our observed HEA NPs also arise from Cr/Cu segregation. Moreover, note that the smaller lattice constant ($a_1 = 0.3588$ nm) is linked to larger crystallite sizes (CS = 35 nm). Even though we cannot fully exclude a potential impact of lattice strain on peak broadening, this data highlights a crystallite size that is larger than the mean particle diameter of $d = 18 \pm 9$ nm, determined from TEM (Supporting Information, Figure S1). As crystallites cannot be larger than the actual particle diameter, we can assume that the crystal phase with the lattice parameter a_1 is primarily located in larger HEA NPs, which do not represent the majority of the particles in the sample but may still have a pronounced contribution in a volume-sensitive technique like XRD. Also note that in Figure 2c, red line, a peak at a diffraction angle of $2\theta = 45^\circ$ and CS = 25 nm (via anisotropic refinement) was detected. Identification of this peak was impossible due to its low intensity, and it is unclear what led to the formation of this unknown phase. However, the signal's low intensity and their total absence in the XRD pattern of the ps-LAL-generated HEA NPs (Figure 2c, black line) suggest that this phase is not reproducibly formed in the majority of the sample and may be attributed to an unknown contamination of the sample.

Contrarily, the CrFeCoNiCu NPs synthesized via ns-LAL show significantly weaker reflections, which suggests that mainly amorphous NPs may be present. Additionally, reflections with low intensities, resembling metallic fcc structures, can be observed. However, the small peak intensity of the crystalline fcc structure (Figure 2c, red line) suggests that a small portion of HEA NPs forms with a crystalline structure. Considering that individual particles may experience deviating cooling rates, e.g., by the different predicted particle formation channels during ps-LAL of silver in water⁴⁷, we assume that a small portion of



HEA NPs form without the incorporation of carbon after cooldown and thus are able to form metallic fcc structures. This is in line with our previous observations on CrMnFeCoNi HEA NPs, where minor crystalline fractions were also reported after ns-LAL.⁴³

However, note that weaker reflections may also be an effect of very small coherently scattering domains, e.g., in very small, monocrystalline NPs. Thus, additional SAED (Figure 2d) and HRTEM analysis (Figure 2e) confirm the trends observed via XRD. It validates the formation of predominantly amorphous samples via ns-LAL (Figure 2d and 2e, left) and crystalline ones by ps-LAL (Figure 2d and 2e, right), flanked by similarity in mean particle size between the samples, which rules out that the weaker reflection intensity in the XRD pattern of Figure 2c is a particle size-dependent phenomenon. The crystalline NPs from ps-LAL, analyzed by SAED, have d-values of 0.209 nm (111), 0.182 nm (200), 0.128 nm (220), and 0.109 nm (311) for the metallic fcc structure, agreeing well with former observed d-spacings determined for CrFeCoNiCu HEA NPs via a pyrolytic

reduction reaction by Chen et al.⁴⁸, while minor reflections resulting from possible oxide species can also be detected (0.223 nm and 0.291 nm, possibly from FeCr_2O_4 and Cr_2O_3 species [ICSD 171121 and ICSD 185888]).

To sum up, we show that by utilizing laser ablation in an organic liquid, the applicability of the pulse duration-dependent phase formation observed for CrMnFeCoNi HEA NPs can be expanded to the CrFeCoNiCu HEA system. As discussed in our previous work⁴³, we attribute the prevalence of the amorphous phases to incorporation of carbon into the NPs, verified by STEM-EDX and EELS measurements, where we could observe the presence of carbon inside a nanoparticle's core and differentiate the observed carbon species from graphitic carbon species in the particle's carbon shell. In ns-LAL the heating duration of the ablation plume is significantly longer than in ps-LAL, which makes the diffusion of active carbon species that form during laser-based methods^{32,36} into the NP more probable. Upon cooldown with high cooling rates ranging from up to 10^{12} - 10^{13} K/s^{30,47}, crystallization is hindered as carbon is integrated into




Figure 2. STEM-EDX characterization of CrFeCoNiCu HEA NPs via ps-LAL (a) and ns-LAL (b) with EDX maps of Cr, Fe, Co, Ni, and Cu, all data originating from K-shell signals. Additionally, structural heterogeneity of the HEA NPs is displayed in two distinct X-ray diffraction patterns of crystalline dried colloids via ps-LAL (black) and amorphous dried colloids by ns-LAL (red) (c), SAED data of particle ensembles with similar mean particle diameters (shown by insets of particle size distributions) with amorphous HEA NPs via ns-LAL (left) and crystalline HEA NPs via ps-LAL (right) (d). HRTEM images of exemplary HEA NPs with FFT-insets support the observation of pulse length-dependent structural difference in the synthesized HEA NPs, highlighting an amorphous HEA NP without reflections via ns-LAL and a crystalline HEA NP with a (111) reflection ($d_{111} = 0.209$ nm) by ps-LAL (e). The overall observations state that the postulated pulse duration-dependent amorphization mechanism reported previously for CrMnFeCoNi52 can be extended to the CrFeCoNiCu system during laser ablation in ethanol.



the forming NPs, and consequently, the metastable amorphous structure of the HEA NPs can be stabilized. Contrarily, in ps-LAL, the heating time of the plume is shorter, and thus a diffusion of carbon species into the plume and the liquid metal droplets is less likely. After the cooling process, fewer or no carbon species are suspected to be within the solidifying NPs. Only in the absence of carbon, the thermodynamically favored crystalline fcc structure forms.⁴³

Volume sensitive characterization of CrMnFeCoNi and CrFeCoNiCu NPs from LFL in ethanol – Transferring amorphization rules from LAL to LFL

After extending the applicability of amorphous vs. crystalline phase control via LAL, we further aimed to elaborate on how the pulse duration effect and postulated mechanism can be applied to other laser-based NP synthesis methods. In detail, we address whether ns-LFL may yield amorphous HEA metallic glass NPs. For this, we conducted microparticle LFL (MP-LFL), using a high-power UV laser with ns pulses ($\tau = 20$ ns) to produce HEA NPs and chose ethanol as the liquid medium to ensure comparability between our nanoparticles generated by LAL and MP-LFL.

As a starting material, CrMnFeCoNi and CrFeCoNiCu HEA MP powders were utilized for HEA NP fabrication (details of fabrication in experimental section, characterization in Supporting Information, Section S3). The educt HEA MPs derived from HEBM before MP-LFL were plate-shaped with a maximum planar length of 20 μm (exemplary SEM image shown

for CrMnFeCoNi HEA MPs and $A = 0.3603$ nm, $CS = 9.5 \pm 0.6$ nm for CrFeCoNiCu HEA MPs (Figure 3a). MP-LFL of these HEA MPs yielded HEA NPs with mean diameters of 10 ± 4 nm (PDI = 0.17) for CrMnFeCoNi and 8 ± 3 nm (PDI = 0.14) for CrFeCoNiCu. Large area TEM-EDX measurements determined the compositions to be $\text{Cr}_{18}\text{Mn}_{31}\text{Fe}_{23}\text{Co}_{14}\text{Ni}_{14}$ for the Mn-containing alloy and $\text{Cr}_{20}\text{Fe}_{26}\text{Co}_{16}\text{Ni}_{18}\text{Cu}_{20}$ for the Cu-containing alloy, respectively (compare Supporting Information, Tables S5 and S6). All elements in CrMnFeCoNi NPs were evenly distributed, except for Mn, which was less integrated into the NPs and yielding spatially more scattered signals (Figure 3c). Considering the increased amount in the large area EDX value, this observation could be attributed to its vapor pressure, which is the highest of all involved elements⁴⁹. Hence, it is conceivable that Mn, which evaporated during the synthesis process, is less integrated into the forming NPs and rather deposits as manganese oxide precipitates, as can be seen by the Mn signal in the STEM-EDX images of Figure 3c (EDX spectra of whole area and individual HEA NP in the Supporting Information, Section S4, Figure S5). This would explain the increased large-area Mn values (Supporting Information, Table S5) despite a less localized signal strength within detected NPs in the EDX maps. Nonetheless, EDX spectra show Mn peaks discernible from noise even in the diffuse areas of the map, verifying the presence of manganese (Supporting Information, Figure S5). In CrFeCoNiCu NPs via MP-LFL, copper tends to segregate from the other elements, which leads to the formation of some NPs that mainly contain CrFeCoNi next to NPs dominated by copper (Figure 3d), especially in NPs that resemble the size of the determined mean




Figure 3. MP-LFL, conducted in ethanol for CrMnFeCoNi and CrFeCoNiCu MPs at a fluence of 1.8 J/cm², synthesizing HEA NPs via MP-LFL. Exemplary SEM image (a) and X-ray diffraction pattern (b) of the crystalline educt CrMnFeCoNi and CrFeCoNiCu MPs, showing a uniform fcc structure. TEM- and SAED images with corresponding particle size distribution are complemented by exemplary STEM-EDX maps of HEA NPs products generated via MP-LFL for CrMnFeCoNi (c) and CrFeCoNiCu (d), shows how composition sets partial segregation (Cr-Cu in Cu-containing HEA NPs) and structural development (crystalline Mn-containing HEA NPs and amorphous Cu-containing HEA NPs).

in Figure 3a). Their crystal structure was determined (via XRD) to be fcc with refined values of $A = 0.3591$ nm, $CS = 14 \pm 2$ nm

particle diameter of the samples ($d = 10 \pm 4$ nm). Contrarily, in larger particles ($d \sim 25$ nm), copper segregates within a particle



rather than in between particles (compare Supporting Information, Figure S6), agreeing with the previously observed segregations in CrFeCoNiCu NPs via LAL (Figure 2a and 2b). During MP-LFL, we observed material-dependent structural heterogeneity when analyzing the crystal structure of the product HEA NPs via MP-LFL, as shown in the SAED analyses (Figures 3c and 3d). While CrFeCoNiCu HEA NPs via MP-LFL form amorphous structures as their analogs from LAL, CrMnFeCoNi NPs by MP-LFL form crystalline structures, assigned to a metallic fcc structure ($A = 0.361$ nm; $d_{111} = 0.207$ nm, $d_{200} = 0.182$ nm). Additional reflections can be derived from crystalline oxide species. This abundance of reflections cannot be related to differences in particle size distributions, as they are comparable between samples (inset Figure 3c and 3d). Consequently, the HEA element system strongly affects the generation of amorphous HEA NPs via MP-LFL.

The change from LAL to MP-LFL led to the occurrence of two different phase structures (crystalline CrMnFeCoNi NPs and amorphous CrFeCoNiCu NPs). In MP-LFL, the processes that dictate the size reduction of particles can be described by a photomechanical^{31,34} mechanism (more dominant when ps-/fs-pulses are applied), which is favored when the pulse duration is substantially shorter than thermal and acoustic relaxation times⁵⁰, and when brittle materials such as oxides³¹ or organic MPs³³ are used (where the inner stress by the internal pressure wave exceeds their strength). In this study, we utilize more ductile metallic MPs and laser pulses with $\tau = 20$ ns, which makes dominant photomechanical contributions to the fragmentation mechanism less likely, and the photothermal⁵¹ effects, involving sequential heating, melting, and evaporation processes⁵², are more probable. The prevalence of photothermal processes suggests that carbon incorporation could analogously occur during the melting-evaporation process with consequent condensation of the particles. Due to the radical-forming decomposition of solvent molecules during irradiation with high-power pulsed lasers^{32,53}, radical carbon species can diffuse into the inorganic precursors (atom clusters and alloy droplets) of the emerging HEA NPs to stabilize an amorphous structure upon cooling. However, the structural heterogeneity between Cu and Mn-containing HEA NPs suggests that our postulation about the carbon diffusion-driven mechanism cannot be directly transferred from the LAL to the herein used MP-LFL process.

In LFL, cooling and solidification times are generally shorter than in LAL, though a direct comparison to literature data is limited, as the materials, educt particle sizes, and pulse durations we used differed from those in the literature.^{52,54} Particle formation during NP-LFL has been predicted to set in after 200 – 800 ps^{52,54}, whereas in LAL it is on the ns scale.^{30,47} At high fluence LFL of NPs, the fragments created by phase explosion are not trapped in the vapor bubble but are directly injected into the cold solvent, quickly cooling the created NPs.^{52,54} Consequently, it can be expected that due to faster cooling less carbon can be integrated during the formation process after LFL compared to LAL. Also, in LFL, vapor bubbles (that may contain the reactive carbon species like radicals created from the solvent molecule) have lifetimes orders of magnitude shorter

than during LAL.⁵² This could hint towards a less efficient carbon incorporation due to a deficient availability of carbon. Moreover, emerging NPs via MP-LFL are substantially smaller than those in LAL^{31,55}, making carbon incorporation even less likely, as this may also point towards faster particle growth quenching.

However, as particle formation pathways for MP-LFL of CrMnFeCoNi and CrFeCoNiCu will most likely be similar, a difference in the material composition (**Mn** vs **Cu**) must be the basis of the different structural development of the HEA NPs. As carbon may be less efficiently incorporated into the NPs from MP-LFL, chemical effects like material affinity between carbon and the individual metals may be structure-determining instead. Hence, substituting **Mn** by **Cu** may lead to an altered interaction between the metal droplets/clusters and the surrounding carbon species during MP-LFL. Laser-generated Cu NPs were shown to catalyze the formation of C-C bonds and sp²-carbon, resulting in C-encapsulated Cu NPs. Hence, the catalytic activity of the copper atoms may be the driving force behind this observation.^{32,56,57} Contrary, after laser-based fabrication of Mn NPs in organic solvents, such structures were not observed⁵⁸, despite the higher affinity of Mn towards C in bulk and its molten state.⁵⁹ Thus, it is probable that the mentioned differences in the composition between the two HEA systems and the role of **Mn** or **Cu** in ruling the formation and incorporation of reactive carbon species (formed in situ from the organic solvent molecule) set the amorphization of HEA NPs via MP-LFL. In a simplified picture, we see two determinants for the final NP structure created by MP-LFL: i) MP-LFL seems to set conditions with fast particle solidification kinetics, leading to less intensive reactions of the forming HEA NPs with their surrounding organic liquid and the reactive species created thereof. This results in weaker amorphization tendencies during MP-LFL compared to LAL of the Cantor HEA.⁴³ ii) Due to i) material-dependent differences in the reactivity between NPs and the reactive carbon species, in this case, the faster incorporation of carbon due to Cu catalysis, becomes the dominant rate-limiting and structure-determining step during particle formation. Consequently, carbon species are more quickly incorporated in the presence of Cu, hindering crystallization during the rapid cooling of HEA NPs.

The generation of HEA NPs by MP-LFL constitutes an important step towards the scale-up of HEA-NP productivity, especially when high-power UV lasers (e.g. the 400 W Trumpf TruMicro 7420 as in this study) and fully continuous flow-through reactor setups are used. Spellauge et al. reported power-specific productivities of 18 mg/(h*W) for IrO₂ using MP-LFL.³¹ Since maximal productivity scales with material density²⁸, we can benchmark against their results and anticipate comparable power-specific productivities, exceeding the values reported for LAL (~ 1 mg/(h*W)).^{39,43} Consequently, utilizing such a high-power laser system, productivities of 7 g/h or more become possible for the generation of HEA NPs via MP-LFL.

Surface sensitive characterization of CrFeCoNiCu and CrMnFeCoNi NPs from LAL in ethanol – Impact of amorphization on



electrochemical potentials and elemental composition in surface-near volumes

To gain insight into structural and compositional changes on the nanoparticles' surfaces of CrMnFeCoNi and CrFeCoNiCu HEA NPs obtained from ps- and ns-pulsed LAL, we conducted cyclic voltammetry (CV) measurements. A detailed characterization of the CrMnFeCoNi HEA NPs can be found in our previous work⁴³ and is further displayed in Section S5 of the supporting material. The central aim was to determine whether or to what extent differences in the NP's core phase structure (amorphous vs. crystalline) and the core elemental composition (Mn vs. Cu) translate into changes in the surface electrochemical potentials. Furthermore, we aimed to elucidate the chemical stability of the surface stressed by multiple CV cycling. Thus, we carried out 100 cycles of CV in a potential window of 0 – 1.5 V vs. RHE and focused on the structural information at the surface in the untreated state (after synthesis), after the 10th cycle, and after the 100th cycle of electrochemical treatment. Note that the designation of distinct anodic/cathodic peaks in a multi-element system can be challenging due to synergistic effects resulting in peak shifts towards more positive and negative potentials.⁶⁰

Figure 4 displays cyclic voltammograms of crystalline and amorphous HEA NPs of CrMnFeCoNi (Figure 4a and 4b) and CrFeCoNiCu (Figure 4c and 4d), respectively. In both cases, the

CrMnFeCoNi HEA NPs show a distinct decrease in activity throughout cycling (Figure 4a and 4b). The current density of the cathodic peak (located at 0.73 V after synthesis) decreases while a simultaneous peak shift can be observed, especially for the crystalline CrMnFeCoNi HEA NPs (Figure 4a, shift from 0.73 V (after synthesis) to 0.47 V (after 100th cycles)). This decrease in currents in high-potential regions with consecutive electrochemical treatments hints towards an electrochemical deactivation of the HEA NP surface. The deactivation of the CrMnFeCoNi HEA was stated very recently by Luan et al.⁶¹ where Mn-rich surfaces lead to deactivation and thus may also be the reason for the decrease in activity in our study. During cycling, a cathodic current appears at 1.35 V, which can be assigned to the reduction of Ni(OH)₂ species to NiOOH.⁶² This peak becomes more prominent in the cyclic voltammogram of the 100th cycle, where the anodic currents at 1.45 V with corresponding reduction at 1.38 V hint towards a NiOOH/Ni(OH)₂ transition (anodic peaks highlighted with blue arrows in Figure 4a-4d). The differences in electrochemical behavior between the surface after synthesis, after 10 cycles, and after 100 cycles of CV indicate that the structural composition of the HEA-NP surface changes with electrochemical cycling. Thus, we suspect that during CV, Ni has either moved to the nanoparticles' surface (either by diffusion or by solvation of the upper layers⁶¹) or was activated through an interplay with other elemental species. Interestingly, the




Figure 4. Cyclic voltammograms of crystalline and amorphous HEA NPs in a potential window of 0 – 1.5 V vs RHE in 1 M KOH with sweep rates of 20 mV/s. (a) Crystalline CrMnFeCoNi NPs, (b) amorphous CrMnFeCoNi NPs, (c) crystalline CrFeCoNiCu NPs, and (d) amorphous CrFeCoNiCu NPs. Insets display highlighted regions in cyclic voltammograms to display differences in electrochemical behavior of the HEA NPs. Blue arrows indicate the anodic current of NiOOH/Ni(OH)₂ transition.



appearance of the $\text{NiOOH}/\text{Ni}(\text{OH})_2$ transition in amorphous CrMnFeCoNi HEA NPs (Figure 4b) happened already at the 10th cycle of CV, which coincides with the anodic and cathodic currents mentioned above. This suggests that the supposed movement of Ni from the core to the surface has lower activation barriers than in crystalline CrMnFeCoNi NPs. However, the 100th cycle still displays the cathodic current, whereas the anodic current cannot be observed anymore, suggesting inactivation of the previously detected Ni-species or depletion of Ni in general. This was shown to appear when inactive $\gamma\text{-NiOOH}$ dominates over the more active $\beta\text{-NiOOH}$ ⁶³ species on the material's surface.⁶⁴

In CrFeCoNiCu HEA NPs (Figure 4c and 4d), new anodic and cathodic peaks appear upon substitution of Mn by Cu in the quinary alloy, particularly pronounced in the low potential regions (0 – 0.9 V vs. RHE). These currents can thus be assigned to oxidation/reduction processes of copper species and the formation of Cu_2O and $\text{Cu}(\text{OH})_2$ on the surface of the material.⁶⁵ However, the decrease in the anodic (0.60 – 0.90 V vs RHE) and cathodic (0 – 0.60 V vs RHE) current densities throughout cycling depicts that the oxidation process is not fully reversible. Also, note that the broad anodic region in the previously discussed CrMnFeCoNi HEA NPs (starting at ~ 0.9 V vs RHE) does not appear in the cyclic voltammograms of CrFeCoNiCu HEA NPs, strengthening our statement about the possible Mn-species that appear in that potential region. Contrary to the CrMnFeCoNi HEA NPs in Figures 4a and 4b, the CrFeCoNiCu HEA NPs undergo an activation towards the 10th cycle in CV. This may be attributed to the presence of Ni-species at the NPs surface. In Figures 4c and 4d, distinct anodic and cathodic peaks are observable at 1.44 V vs RHE (anodic peak) and 1.33 V vs RHE (cathodic peak), whereas in crystalline CrFeCoNiCu HEA NPs, this peak appears significantly smaller (shoulder at 1.44 V) than in amorphous CrFeCoNiCu HEA NPs. Nonetheless, whether $\gamma\text{-NiOOH}$ (less active in OER) or $\beta\text{-NiOOH}$ (more active in OER) is present at that state cannot be determined based on this data. Comparing the cyclic voltammograms of CrMnFeCoNi and CrFeCoNiCu HEA NPs concerning the pulse duration-dependent crystal structures, we can hypothesize that a distinct deactivation of the HEA nanoparticles surface is linked to the presence of Mn in the alloy, probably attributed to the formation of inactive Mn-oxide species as shown by Luan et al.⁶¹ Moreover, CrFeCoNiCu HEA NPs show activation towards 10th cycle in CV, possibly linked to the activation of Ni-species, as in both crystalline and amorphous CrFeCoNiCu HEA NPs $\text{NiOOH}/\text{Ni}(\text{OH})_2$ transitions can be observed. Also note that the anodic and respective cathodic peaks of $\text{NiOOH}/\text{Ni}(\text{OH})_2$ in amorphous CrFeCoNiCu HEA NPs (Figure 4d) are more dominant than in the crystalline counterpart (Figure 4c). Comparing this with the presence of the same transition species in the 10th CV cycle in amorphous CrMnFeCoNi HEA NPs (Figure 4b) versus the absence in the crystalline counterpart (Figure 4a, 10th cycle) suggests that the amorphous structure favors nickel's outward diffusion to the surface from the particles' core. The favored diffusion may be one reason that amorphous structures are favored in OER/catalysis.^{66,67}

Further, we analyzed the observed surface changes (after 10 cycles, and 100 cycles) in comparison to the initial (after synthesis) state via XPS (see details in experimental section) to expand our view about the already gained surface information based on electrochemical readouts. To better understand the observations on surface electrochemistry (Figure 4), we focus on how surface composition (from signals emerging in the 3p region of the metallic photoelectrons) and anodic/cathodic peaks in CV correlate (XPS spectra and tables with relative metal values are shown in Supporting Information, Section S6).

Figure 5 displays the XPS-derived changes in surface compositions of HEA NPs before and after electrochemical treatment. For CrMnFeCoNi HEA NPs (Figure 5a and 5b), we observe a pronounced enrichment of Mn in the surface near volume, which confirms our hypothesis of a Mn-induced electrochemical deactivation of the surface. Moreover, the statement that the outward diffusion of Ni-species from the particle cores to the surface is faster for the amorphous CrMnFeCoNi HEA NPs than for the crystalline counterpart, can be strengthened by the observation of the presence of Ni at the HEA NPs surfaces, which appears to be higher than in the amorphous NPs in the 10th cycle (Figure 5b), but lower in the 100th cycle, compared to the crystalline CrMnFeCoNi HEA NPs (Figure 5a). Note that here we refer to the relative changes after 10th and 100th cycles of CV, and that generally the Ni content is lower compared to the value before CV was conducted, most likely linked to dissolution processes upon contact with the alkaline media.⁶¹ For CrFeCoNiCu , the activation in the 10th cycle of HEA NPs may be linked to the significantly higher proportion of Cr and Co with additional Ni at the surface (Figure 5c and 5d). Contrarily, in CrMnFeCoNi HEA NPs, the relative




Figure 5. Radar charts of compositional changes, derived from XPS data (see Section S6 in the supporting information), before and after cyclic voltammetry in 1 M KOH, displaying compositions [%] of the surface after synthesis, after 10 cycles of CV, and after 100 cycles of CV. (a) Crystalline CrMnFeCoNi NPs, (b) amorphous CrMnFeCoNi NPs, (c) Crystalline CrFeCoNiCu NPs, and (d) amorphous CrFeCoNiCu NPs. Note that scales of a, b and c, d differ to support proper visibility of compositional changes.






Figure 6. OER activity of amorphous/crystalline CrMnFeCoNi and CrFeCoNiCu HEA NPs, showing extracted current densities at 1.7 V vs. RHE (a) and overpotentials at 10 $\text{mA}/\text{cm}^2_{\text{geo}}$ (c) from linear sweep voltammetry experiments. (b) Impedance of HEA NPs with different states of nanoparticle surface (after synthesis, after 10 CV cycles, and 50 cycles) and (d) Comparison of OER current densities extracted at 1.7 V vs. RHE: Crystalline and amorphous Mn-containing HEA NPs (C-Mn-HEA and A-Mn-HEA) compared to crystalline and amorphous Cu-containing HEA NPs (C-Cu-HEA and A-Cu-HEA) as well as reference values of on CB supported HEA NPs reported by Waag et al.³⁹ (crystalline CrMnFeCoNi HEA NPs via ps-LAL in ethanol) and Johny et al.⁴¹ (amorphous CrMnFeCoNi HEA NPs via ns-LAL in acetonitrile).

proportion of Cr and Co is (close to) zero. Co was shown to stabilize the more active β -NiOOH species⁶⁴, which could be the reason for higher activities in the high-potential region. However, whether Cr-(oxide) species at the surface may or may not play a role in the activation cannot be discerned based on this data. Also note that the deactivation towards the 100th cycle in CrFeCoNiCu HEA NPs (Figure 5c and 5d) may be linked to the oxidation of Co to CoO_2 , which was shown to correlate with the formation of the less active γ -NiOOH.⁶⁴ However, as the Co-proportion decreases towards the 100th cycle (Figure 5c and 5d), the deactivation may also be a result of lacking Co that could otherwise stabilize β -NiOOH. Interestingly, we do not see any evidence of an electronegativity-driven activation of surface species, which is frequently discussed in the literature on CrMnFeCoNi.^{5,68} Here, we do not observe any of the reported core-level shifts in our XPS spectra, where only oxidation-driven shifts could be observed (Supporting Information, Section S6).

In summary, we could assign anodic/cathodic currents in the cyclic voltammograms of CrMnFeCoNi/ CrFeCoNiCu amorphous (ns-LAL) and crystalline (ps-LAL) HEA NPs to be linked to the presence of certain species at the nanoparticle surfaces and

found them to be the reason for the activation (combination of Co- and Ni-species in CrFeCoNiCu HEA NPs) or deactivation (Mn-oxide species in CrMnFeCoNi HEA NPs). Furthermore, we may conclude that the morphology (crystalline vs. amorphous cores) has only a minute impact on the electrochemistry and surface composition, but is predominantly ruled by compositional differences replacing Mn with Cu.

Influence of electrochemically induced surface changes in crystalline and amorphous HEA NPs on the oxygen evolution reaction

Finally, we examined how the composition (Cu vs. Mn containing alloy) and the internal phase structure (crystalline vs. amorphous) influence the anodic electrocatalytic water splitting activity using the oxygen evolution reaction (OER) as a model electrochemical process. Finally, we correlate these findings with the surface compositions determined in the last chapter (summarized in Figure 7). To this end, we conducted CV with a consecutive linear sweep voltammetry (LSV) to understand how the NPs with different surface compositions



(after synthesis, and after 10, 50, and 100 cycles of CV) perform at the OER.

Figures 6a and 6b present LSV data in the 0–1.8 V vs. RHE range, showing current densities (CD) at 1.7 V vs. RHE (a) and overpotentials (OP) at 10 mA cm⁻²_{geo} (b). Initially, CrFeCoNiCu HEA NPs exhibit the highest OER activity (highest CD, lowest OP), whereas CrMnFeCoNi NPs show the lowest. However, this trend reverses following electrochemical surface restructuring via cyclic voltammetry (CV) over 100 cycles. A direct correlation between CD loss and OP increase is observed for both systems. Among all compositions, Mn-containing HEA NPs demonstrate the highest stability, with CD reductions of 51% (amorphous) and 61% (crystalline) at 1.7 V vs. RHE. In contrast, Cu-containing HEA NPs, despite exhibiting superior initial performance, display the most pronounced activity losses with 78% and 92% for crystalline and amorphous nanoparticles, respectively.

Notably, CrFeCoNiCu NPs show peak CD at the 10th CV cycle (Figure 5c,d), whereas the LSV measurements reveal a continuous decline in activity from the as-synthesized state to post-CV treatment. This observation suggests that redox-active surface intermediates discussed in the last chapter do not significantly contribute to OER catalysis under steady-state conditions. Prior studies on CrMnFeCoNi bulk electrodes by Luan et al.⁶¹ proposed a transient NiFe-(oxy)hydroxide phase on top of Cr oxides as the active species, ultimately suppressed by Mn enrichment and catalyst deactivation. In our NP-based system, analogous behavior was not observed. Instead, Mn surface enrichment was shown to correlate directly with activity decrease (Figures 5a,b, Figure 7). It is conceivable that the active species postulated could not be stabilized on a nanoscopic scale or that dissolution processes were faster in NPs due to a higher specific surface area, making potential active intermediate species non-observable.

In the case of CrFeCoNiCu NPs, a more substantial activity decline is attributed to the enrichment of catalytically less active Cr oxides in the surface-near region, which was reported to passivate the surface and impede outward diffusion of more active species⁶¹, as supported by XPS data (Figures 5c,d). Finally, the superior performance of amorphous over crystalline CrMnFeCoNi NPs (Figure 6a,b,) is consistent with previous reports^{12–15,67,69}, linking enhanced catalytic activity in amorphous materials to structural disorder and a higher density of coordinatively unsaturated sites, despite comparable surface compositions (Figures 5a and 5b, Figure 7).

Additionally, we conducted electrochemical impedance spectroscopy (EIS, raw data displayed in Supporting Information, Section S8) to observe possible changes in the resistance of the investigated HEA NPs (Figure 6c), in conjunction with vacuum volumetry (based on BET adsorption) to determine the samples' specific surface area (SSA) (Supporting Information, Section S9). In short, three out of four HEA NP samples exhibit a modest increase in impedance (reduction in conductivity) during CV cycling, as well as an overall comparable measured SSA among samples. In these samples, we consider the impact of impedance on OER activity minimal. However, a stronger increase in impedance was observed for amorphous CrFeCoNiCu HEA NPs, which is also

linked to a lower SSA, probably attributed to particle agglomeration. For this sample, we assume that high

View Article Online

DOI: 10.1039/D5FD00087D




Figure 7. Links between OER activity and surface composition. Top row: Qualitative comparison of current density, overpotential and conductivity of crystalline and amorphous Mn- and Cu-containing HEA NPs, displaying states before (left) and after (right) the OER. Bottom row: Semi-quantitative evaluation of the surface composition of crystalline (cryst.) and amorphous (am.) Mn- and Cu-containing HEA NPs, displaying states before (left) and after (right) the OER. Note that each surface-localized sphere color-coded by atom type, represents 4-5% of the total surface composition according to Table S5 (Supporting Information).

impedance and low SSA substantially contribute to the massive loss in OER activity (Figures 6a-6c,7). Unfortunately, this pronounced increase in resistance makes it difficult to determine to what extent the structurally altered surface of CrFeCoNiCu HEA NPs influences the OER activity.

We also compare the OER performance of the here-examined HEA NPs to laser-generated crystalline CrMnFeCoNi HEA NPs previously studied by Waag et al.³⁹ and Johny et al.⁴¹ (Figure 5d). In the literature, Waag et al. reported a CD of 0.51 A/mg_{NP} at 1.7 V vs. RHE for crystalline CrMnFeCoNi HEA NPs, while Johny et al. reported increased activities of 0.98 A/mg_{NP} at 1.7 V vs. RHE for amorphous CrMnFeCoNi HEA NPs. However, note that the authors in Ref. 39 and 41 conducted the experiments using carbon black as supporting material (CB), which is known to boost catalytic activity due to the increase of the SSA of used nanoparticles⁷⁰ and was furthermore shown to increase sensitivity in charge transfer towards the GCE⁷¹, so comparability is limited. Comparing this to the initial values in our study (Crystalline CrMnFeCoNi NPs: 0.34 A/mg_{NP}, Amorphous CrMnFeCoNi NPs: 0.44 A/mg_{NP}, Crystalline CrFeCoNiCu NPs: 0.64 A/mg_{NP}, Amorphous CrFeCoNiCu NPs: 0.90 A/mg_{NP}; (all values recalculated from Figure 5a) we can state that:

- 1) We could reproduce the OER activity values that Waag et al.³⁹ reported in 2019 with minor deviations (0.51 A/mg_{NP} vs. 0.34 A/mg_{NP}), which is likely attributed to the supporting on CB, increasing the OER activity in Ref. 39. Additionally, we expanded this work and showed the activity change after 100 cycles of CV (8.5 mA/cm²_{geo}; 0.13 A/mg_{NP}).
- 2) Amorphous CrMnFeCoNi HEA NPs show enhanced OER activities compared to their crystalline



counterpart with initial activities of $28.6 \text{ mA/cm}^2_{\text{geo}}$ ($0.44 \text{ A/mg}_{\text{NP}}$) and an activity of 14.0 mA/cm^2 ($0.22 \text{ A/mg}_{\text{NP}}$) after 100 cycles of electrochemical cycling. This agrees with prior investigations by Johny et al.⁴¹, though deviations occur analogously due to the supporting on CB in Ref. 41.

- 3) Though amorphous **CrFeCoNiCu** depict a very high activity in the initial state ($58.0 \text{ mA/cm}^2_{\text{geo}}$; $0.90 \text{ A/mg}_{\text{NP}}$), the activity decreases rapidly to $4.4 \text{ mA/cm}^2_{\text{geo}}$ ($0.07 \text{ A/mg}_{\text{NP}}$) (associated with increase in impedance), leaving crystalline **CrFeCoNiCu** HEA NPs as the superior counterpart with an initial activity of $41.0 \text{ mA/cm}^2_{\text{geo}}$ ($0.64 \text{ A/mg}_{\text{NP}}$) and $9.0 \text{ mA/cm}^2_{\text{geo}}$ ($0.14 \text{ A/mg}_{\text{NP}}$) after 100 cycles of CV.

Conclusions

We studied LSPC as a green and scalable technique to fabricate ignoble HEA NPs in ethanol. Previous LAL studies on **CrMnFeCoNi** highlighted a pulse-duration-driven mechanism controlling the particles' internal phase structure with ns-pulses and ps-pulses yielding amorphous and crystalline HEA NPs, respectively. We dedicate this phenomenon to the incorporation of carbon from the solvent's reactive species (created in situ by the pulsed laser process) into the forming NPs, stabilizing a metastable amorphous structure during cooldown of the alloy NP droplets. During nanosecond-LAL, the ablation plume is heated longer compared to picosecond-pulsed LAL, so the time to i) form reactive carbon species, in particular molecular carbon radicals as well as C-C coupling, and ii) carbon to diffuse into the NPs is extended, favoring amorphization.⁴³ One aim of this study was to investigate the transferability of this concept to other HEA systems, replacing Mn with Cu in the Cantor-based HEA alloy NPs. Our work confirms the transferability of the pulse-duration controlled amorphization rules to **CrFeCoNiCu**. Based on these findings, we may conclude that LAL constitutes a universally applicable route towards amorphous metallic glass or crystalline ignoble HEA NPs, switchable simply by laser pulse duration. However, further studies need to be conducted with other HEA compositions, verifying the universality of this approach and particularly the interplay between the carbon affinity of the individual HEA constituents and their activity in catalyzing solvent reactions in situ and carbon shell formation kinetics.

In a complementary, more scalable approach, we produced HEA NPs via MP-LFL, using a high-power ns-pulsed UV laser and **CrMnFeCoNi** and **CrFeCoNiCu** microparticles as starting material. Here, we verified the suitability of MP-LFL to generate HEA NPs, which may be beneficial for future upscaling approaches, as MP-LFL yields productivities higher than LAL³¹ and also works in a fully continuous mode, while LAL demands target replacements at some point. Moreover, HEA MP fabrication via HEBM is well established and scalable, and thus can provide starting material for MP-LFL in high quantities and with homogeneous distribution of all elements used. Interestingly, MP-LFL yielded amorphous **CrFeCoNiCu** HEA NPs while their **Mn**-containing counterparts were crystalline. Thus,

we conclude that the particle formation pathways in LAL and MP-LFL are fundamentally different and depend on the feedstock material. Based on previous findings from large-scale molecular dynamic simulations of the NP-LFL process, we hypothesize that particle solidification pathways during MP-LFL are faster than during LAL, in that regard, similar to NP-LFL^{52,54}, which impairs carbon incorporation and amorphization. Here, chemical features, e.g. the catalytic activity of Cu, favoring carbon shell formation, prevail. Based on these findings, we propose that the amorphization during LSPC is driven by both the kinetics and *in situ* reaction chemistry, including solidification times (setting the timescale for the structure-determining element carbon to diffuse into the particle) and chemical activity, specifically C-C bond coupling and formation of carbon shells through decomposed radical species after laser irradiation, as has been shown for Cu.⁵⁶ A more detailed structural analysis quantifying carbon contents in different regions of the particles, e.g., by atom probe tomography, may be a suitable follow-up approach for verifying further mechanistic processes as well as expanding the HEA compositional space of the MP-LFL study, as well as the organic solvent (with different C:H:O ratio⁷² or different radical forming tendencies^{36,73}).

Electrochemical characterization via CV and LSV of the oxygen evolution reaction in conjunction with XPS analysis enabled a correlation of electrochemical activity with surface composition in HEA NPs, both for the crystalline and amorphous variants (Figure 7). Hence, a compositional as well as a structural vector could be assessed. We observed that electrochemical treatment induced compositional shifts: **CrMnFeCoNi** NPs developed Mn-rich surfaces (with Co and Ni), correlating with a gradual decline in activity, while **CrFeCoNiCu** NPs exhibited surfaces enriched in Cr, Co, and Cu. Pronounced $\text{NiOOH}/\text{Ni}(\text{OH})_2$ redox peaks emerged at the 10th CV cycle in amorphous HEA NPs, suggesting lower activation barriers for outward Ni diffusion than in crystalline counterparts, where Ni signatures appeared only at later stages. These findings indicate that particle composition, specifically Mn versus Cu, mainly governs surface elemental distribution, while differences in structural phase have a secondary influence, as displayed in Figure 7, where surface compositions and also changes thereof are mostly driven by the presence of Cu or Mn, respectively. This also translates into electrochemical performances in CV with redox potentials mainly driven by composition and, to a lesser extent, by the internal phase structure. OER measurements further revealed that amorphous **CrMnFeCoNi** NPs demonstrated improved activity and durability over 100 CV cycles, outperforming both their crystalline analogs and **CrFeCoNiCu** NPs. This underscores the relevance of electrochemical restructuring in assessing catalyst stability. Another aspect frequently discussed in the context of HEA NPs is the impact of deviating particle size distributions on the electrochemical measurements. Here, our study highlights that in the studied HEA NPs from LSPC, different particle diameters did not show compositional differences on a single particle level (Tables S3, S4). Furthermore, deviations in the TEM-derived size distributions did not translate into significant differences in



specific surface areas (Table S8), verifying that particle size effects are negligible when comparing the electrochemical performances of the herein-studied HEA nanomaterials.

We conclude that compositional tuning, especially the substitution of Mn with Cu, has the most significant impact on electrochemical behavior, while amorphization, controlled by laser pulse duration, offers an additional degree of freedom in tailoring HEA catalysts. This dual-level design approach may enhance the performance of ignoble HEA electrocatalysts.

In a nutshell we can conclude that LSPC is a scalable method for the generation of ignoble HEA NPs with internal phase structures switchable by pulse duration (ns vs. ps in LAL) and material composition (Mn vs. Cu in MP-LFL) based on a mechanism ruled by the interplay of particle solidification and carbon incorporation kinetics. Finally, we could deduce a structure-functionality correlation between the elemental composition in surface near volumes and the electrochemical potential of the HEA NPs in correlation with overall composition, and to a lesser extent, the internal phase structure of the particles, verifying their applicability in electrocatalysis.

Experimental

Preparation of ablation targets and microparticle powders for LAL and LFL

Ablation targets for LAL NP synthesis with nominal compositions of $\text{Cr}_{20}\text{Mn}_{20}\text{Fe}_{20}\text{Co}_{20}\text{Ni}_{20}$ and $\text{Cr}_{20}\text{Fe}_{20}\text{Co}_{20}\text{Ni}_{20}\text{Cu}_{20}$ were fabricated by weighing and heat-treating metal granules of Cr, Mn, Fe, Co, Ni, and Cu (Evochem, purity 99.95 – 99.99 %) using an arc-melting oven (AM-200, Bühler) in an argon atmosphere for melting and sintering (at 10–14 V, 50–200 A). The inert atmosphere was used to avoid oxidation of the ignoble metals. The sintered targets were remelted three times to ensure homogeneity and uniform phase formation.

HEA microparticle (HEA MP) powders were produced by high-energy ball milling (HEBM). Elemental powders of Cr, Mn, Fe, Co, Ni, Cu (purity 99.0 – 99.9 %, grain size 10 – 160 μm) were used as the educt material for HEA MPs. HEBM was performed in a water-cooled planetary ball mill (Activator-2S) using stainless-steel cylindrical containers and balls (diameter = 7 mm) with a ball to powder weight ratio of 20:1. The process was carried out at rotation speeds (main disk/jars) of 700 rpm/1400 rpm for 120 min in dry conditions (Ar atmosphere, 4 bars, to prevent oxidation) with additional 15 min in isopropanol. Finally, the powder was sieved for size separation, and the grains with a size below 20 μm were used for further processing.

HEA nanoparticle synthesis by bulk laser ablation and microparticle laser fragmentation

Surfactant-free HEA nanoparticles via LAL were synthesized in p.a. grade ethanol (VWR, purity $\geq 99.8\%$, with additional de-watering and degassing steps) to minimize oxidation of the forming nanoparticles. Before the ablation, the bulk target was additionally polished with sandpaper to ensure it was free of surface oxides. The ablation was conducted in a self-designed

stirred batch reactor with a volume of 30 mL using an Nd:YAG laser (Ekspla, Atlantic Series, 10 ps, 1064 nm, 100 kHz, 0.15 mJ, $\lambda = 1064\text{ nm}$) for ps-LAL and a nanosecond-pulsed laser (Rofin, Powerline E20, 10 ns, 1064 nm, 10 kHz, 0.50 mJ, $\lambda = 1064\text{ nm}$) for ns-LAL. The nominal incident laser fluence was 0.1 J/cm² for ps-LAL and 7 J/cm² for ns-LAL. Note that in our earlier study, we showed that laser fluence does not affect the crystal structure of the HEA NPs.⁴³ The laser beam was moved on the target with a galvanometric scanner (100 mm focal length) in a spiral pattern.

Laser fragmentation in liquid was conducted to synthesize HEA NPs from HEA microparticle (size $\leq 20\text{ }\mu\text{m}$) suspensions in ethanol (concentration = 2 g/L). During synthesis, the suspension was stored in a sonication bath to avoid microparticle sedimentation and ensure an evenly distributed suspension. With a peristaltic pump (ISMATEC ISM1097B), set at 115 mL/min, the suspended HEA microparticles were transported to an Eppendorf pipette tip (diameter of 1 mm at exit), creating a circular-shaped fluid stream with a diameter of 1 mm. A high-power nanosecond-pulsed UV laser (Trumpf, TruMicro 7420, 20 ns, 10 kHz, $\lambda = 343\text{ nm}$) at a pulse energy of 20 mJ (maximum output 40 mJ at 400 W) combined with a focusing lens was utilized to focus the laser beam perpendicularly onto the liquid stream below the circular tip exit to set a fluence of 1.8 J/cm² with each unit of volume being irradiated by about 5 pulses. The synthesis step was repeated four times, exposing the irradiated microparticles to a maximum of 20 pulses. The liquid stream after LFL contained a mixture of product nanoparticles and educt microparticles, which were gravimetrically separated, and characterization was conducted on the supernatants that contain the HEA NPs.

Bulk-sensitive material characterization methods

Target characterization was done using X-ray powder diffraction (XRD, Bruker D8 Advance) with Cu K α radiation ($\lambda = 1.54\text{ }\text{\AA}$). The measurements covered a 2θ range from 5° to 130° with a step size of 0.01° and a counting time of 1.2 s to verify the crystal structure. Additionally, scanning electron microscopy combined with X-ray energy-dispersive spectroscopy (SEM-EDX, Philips XL30 equipped with an EDAX-system) and X-ray fluorescence spectroscopy (XRF, S8 Tiger, Bruker) were employed to verify the overall compositions and elemental distributions.

The global crystal structure of the fabricated HEA NPs was analyzed via XRD by drop-casting and drying concentrated colloidal HEA NPs of similar masses on silicon single-crystal sample holders, minimizing scattering effects. These measurements were performed using the same diffractometer (Bruker D8 Advance) within a 2θ range of 30° to 90° with a step size of 0.02° and a counting time of 8 s. Qualitative phase identification was conducted with the Bruker software Diffrac Suite EVA V7.1, employing the face-centered cubic Ni phase pattern (#70-1849) from the ICDD database. Lattice parameters and average crystallite size were determined through quantitative Rietveld refinement using Bruker's TOPAS 7.0



software, following instrumental calibration with a microcrystalline LaB_6 standard (SRM 660b, NIST, $a = 4.15689 \text{ \AA}$). Crystal structures of HEA microparticle powders were characterized by X-ray diffraction (Malvern Panalytical X'Pert MPD PW3040) with $\text{Cu K}\alpha$ radiation and within a 2θ range of 10 to 120° . Refinements were performed utilizing Maul Software⁷⁴ to determine phases, lattice parameters, and crystallite sizes (CS). For the calculation of average crystallite sizes from diffraction peak broadening in bulk and HEA NPs (using Bruker D8 Advance) the Scherrer equation was used, and instrumental peak broadening was taken into consideration by utilizing lanthanum hexaboride (LaB_6 ; NIST; National Institute of Standards and Technology; reference compound) as an internal standard. For HEA microparticles (Malvern Panalytical X'Pert MPD PW3040), crystallite sizes were determined using MAUD with the Popa model, which accounts for anisotropic broadening. This model is essential for HEBM powders due to significant strain and anisotropy. A Si standard was used to separate instrumental effects, and microstrain was excluded to isolate size-related broadening. Microstructural and compositional analyses were carried out using SEM (Thermo Scientific Phenom Pharos G2 FEG-SEM and Zeiss LEO 1530), operated in both secondary electron (SE) and backscattered electron (BSE) modes, as well as energy-dispersive X-ray spectroscopy (EDX; Oxford Instruments XMAX, 80 mm^2). Transmission electron microscopy (TEM) analysis, selected area electron diffraction (SAED, d -value determination errors within $\pm 0.001 \text{ nm}$ range), and high-resolution TEM (HRTEM) analysis were performed using a Tecnai F30 STwin G² (300 kV acceleration voltage) equipped with a Si(Li) detector (EDAX system) and a JEOL JEM 2100 (200 kV acceleration voltage). Elemental mapping was conducted at a probed-corrected JEOL JEM-ARM200F NEOARM STEM operated at 200 kV (cold-FEG) using EDX with a dual silicon drift detector system with 100 mm^2 active area each. All samples for (S)TEM analysis were prepared by drop-casting the NP colloid on copper grids with a lacey carbon film (Plano GmbH) or silicon nitride films (TED Pella Inc. 35 nm , $70 \times 70 \text{ }\mu\text{m}$ aperture). After drop-casting, all samples were dried in the atmosphere using an infrared lamp (Philips Infrared PAP38E, 150 W) for 10 min and stored under vacuum to avoid further contamination and oxidation.

Surface-sensitive material characterization methods

Electrochemical properties of HEA NPs were investigated by utilizing a three-electrode setup, consisting of a glassy carbon working electrode (GCE, geometric area (geo) = 0.196 cm^2) coated with the HEA NPs via drop casting, a platinum wire as the counter electrode, and an Ag/AgCl reference electrode with a potentiostat (VersaSTAT, 3F, AMETEK Scientific Instruments). For all measurements (conducted at room temperature), the working electrode was coated with $12.6 \text{ }\mu\text{g}$ of HEA NPs, and 1 M KOH ($\text{pH} = 14$) was used as the electrolyte. Before each experimental series, the electrolyte was degassed with nitrogen for 30 min and additionally for 5 min between individual measurements. Cyclic voltammetry (CV) was performed in a potential window of 0 to 1.5 V vs. Reversible Hydrogen

Electrode (RHE) with sweep rates of 20 mV/s for the selected (after synthesis, 10^{th} , 100^{th}) cycles and with 200 mV/s for the cycles in between. Oxygen Evolution Reaction (OER) was performed by rotating the working electrode at 1600 rpm , and sweep rates of 20 mV/s were utilized, reaching a maximum potential of 1.8 V vs. RHE, and the activity of HEA NPs was evaluated by extracting current densities at 1.7 V vs. RHE and overpotentials at $10 \text{ mA/cm}^2_{\text{geo}}$. Electrochemical impedance spectroscopy (EIS) measurements were conducted at 1.6 V vs. RHE and frequencies between 0.1 Hz and 100 kHz . Impedance values were determined via fitting the Nyquist plot ECLab software. The model circuit for fitting is displayed in the supplementary information (Section S9).

X-ray photoelectron spectroscopy (XPS) measurements were conducted with a VersaProbe IITM from Ulvac-Phi using the $\text{Al-K}\alpha$ line at 1486.6 eV and a spot size of $100 \text{ }\mu\text{m}$ with an energy resolution of 0.5 eV . A dual-beam charge neutralization was applied and a hemispherical analyzer (at an angle of 45° between sample surface and analyzer) was used for the measurements. All high-resolution spectra were corrected according to the binding energy of graphitic carbon (284.8 eV), determined during deconvolution of the $\text{C } 1\text{s}$ spectrum of each sample. Peak deconvolution was performed using the CasaXPS software, applying a Shirley-type background and Lorentzian asymmetric curves for fitting. Quantification of relative compositional values of all metals was done by analyzing their respective 3p spectra. A meaningful analysis of the 2p region was impossible as there is an overlap with element-specific Auger lines, a drawback previously reported when analyzing ignoble HEA bulk materials⁷⁵ and even more critical during analysis of NPs, where signal intensities are generally lower. Vacuum volumetry based on Brunauer-Emmett-Teller (BET) isotherms was performed on a NOVA 800 (Anton Paar), utilizing nitrogen physisorption for determining the specific surface area (SSA) of high-entropy alloy nanoparticles. All measurements were conducted at 200°C and the SSA was determined using the BET model with a 7-point adsorption isotherm at relative pressures of 0.05 to 0.20 p/p_0 .

Author contributions

Robert Stuckert: Investigation, Methodology, Visualization, Formal Analysis, Writing – original draft. Felix Pohl: Investigation, Formal Analysis, Writing – review & editing. Natalia Shkodich: Investigation, Resources, Formal Analysis, Writing – review & editing. Oleg Prymak: Investigation, Formal Analysis. Nico Koch: Investigation, Writing – review & editing. Ulrich Schürmann: Supervision, Funding acquisition, Writing – review & editing. Michael Farle: Funding Acquisition, Writing – review & editing. Lorenz Kienle: Funding Acquisition, Supervision, Writing – review & editing. Stephan Barcikowski: Funding Acquisition, Writing – review & editing, Project administration. Christoph Rehbock: Visualization, Supervision, Project Administration, Writing – original draft.



Conflicts of interest

There are no conflicts to declare.

Data availability

The data that support the findings of this study are available from the corresponding author, C.R., upon reasonable request.

Acknowledgements

The authors thank the Deutsche Forschungsgemeinschaft (DFG) for financial support within the project Nr. 277627168 and DGF large scientific instrument (Nr. 491146928). N.F.Sh. and M.F. are grateful for the financial support from the DFG within CRC/Tr270, projects A04 (Project ID 405553726), and project FA209/27-1. Support by the Interdisciplinary Center for Analytic on the Nanoscale (ICAN) of the University of Duisburg-Essen (DFG RIsources reference: RI_00313), a DFG-registered core facility (Project Nos. 233512597 and 324659309), is gratefully acknowledged. R.S. thanks Tobias Bessel for conducting BET measurements and Florian de Kock for bulk target sintering. R.S. acknowledges Varatharaja Nallathambi and Jan Söder for fruitful scientific discussions.

References

References

- 1 T. Löffler, F. Waag, B. Gökce, A. Ludwig, S. Barcikowski and W. Schuhmann, *ACS Catal.*, 2021, **11**, 1014–1023.
- 2 a) W. Al Zoubi, R. A. K. Putri, M. R. Abukhadra and Y. G. Ko, *Nano Energy*, 2023, **110**, 108362, <https://www.sciencedirect.com/science/article/pii/S2211285523001994>; b) T. G. Ritter, S. Pappu and R. Shahbazian-Yassar, *Adv Energy and Sustain Res*, 2024, **5**.
- 3 X. Huang, G. Yang, S. Li, H. Wang, Y. Cao, F. Peng and H. Yu, *Journal of Energy Chemistry*, 2022, **68**, 721–751, <https://www.sciencedirect.com/science/article/pii/S2095495621006884>.
- 4 a) P. Xie, Y. Yao, Z. Huang, Z. Liu, J. Zhang, T. Li, G. Wang, R. Shahbazian-yassar, L. Hu and C. Wang, *Nat Commun*, 2019, **10**, 4011, <https://www.nature.com/articles/s41467-019-11848-9>; b) D. Zhang, H. Zhao, X. Wu, Y. Deng, Z. Wang, Y. Han, H. Li, Y. Shi, X. Chen, S. Li, J. Lai, B. Huang and L. Wang, *Advanced Functional Materials*, 2021, **31**, 2006939, <https://advanced.onlinelibrary.wiley.com/doi/full/10.1002/adfm.202006939>;
- 5 H. Zhu, S. Sun, J. Hao, Z. Zhuang, S. Zhang, T. Wang, Q. Kang, S. Lu, X. Wang, F. Lai, T. Liu, G. Gao, M. Du and D. Wang, *Energy Environ. Sci.*, 2023, **16**, 619–628, <https://pubs.rsc.org/en/content/articlelanding/2023/ee/d2ee03185j>.
- 6 a) Y. Yu, F. Xia, C. Wang, J. Wu, X. Fu, D. Ma, B. Lin, J. Wang, Q. Yue and Y. Kang, *Nano Res.*, 2022, **15**, 7868–7876, <https://link.springer.com/article/10.1007/s12274-022-4432-1>; b) X. Li, J. Cao, G. Chen, J. Xie, C. Gu, X. Li, F. C. Walsh, Y. Wang and W. Hu, *ACS nano*, 2025, **19**, 7851–7863;
- 7 a) Y. Feng, H. Yao, Z. Sun, Y. Liao, J. Wang, R. Zhao and Y. Li, *ACS applied materials & interfaces*, 2024, **16**, 41027–41035; b) G. R. Dey, C. R. McCormick, S. S. Soliman, A. J. Darling and R. E. Schaak, *ACS nano*, 2023, **17**, 5943–5955; c) R. Nandan, G. Raj and K. K. Nanda, *ACS applied materials & interfaces*, 2022, **14**, 16108–16116;
- 8 A. Mao, P. Ding, F. Quan, T. Zhang, X. Ran, Y. Li, X. Jin and X. Gu, *Journal of Alloys and Compounds*, 2018, **735**, 1167–1175, <https://www.sciencedirect.com/science/article/pii/S0925838817340148>.
- 9 T.-H. Hu, C.-Y. Wu, Z. Y. He, Y. Chen, L.-C. Hsu, C.-W. Pao, J.-T. Lin, C.-W. Chang, S.-C. Lin, R. Osmundsen, L. Casalena, K. H. Lin, S. Zhou and T.-H. Yang, *Advanced Science*, 2025, **12**, e2409023, <https://advanced.onlinelibrary.wiley.com/doi/full/10.1002/advs.202409023>.
- 10 A. Garzón-Manjón, H. Meyer, D. Grochla, T. Löffler, W. Schuhmann, A. Ludwig and C. Scheu, *Nanomaterials*, 2018, **8**, 903, <https://www.mdpi.com/2079-4991/8/11/903>.
- 11 X. Zhou, H. Zhu, S. Fu, S. Lan, H. Hahn, J. Zeng and T. Feng, *Small*, 2024, e2405596, <https://onlinelibrary.wiley.com/doi/full/10.1002/sml.202405596>.
- 12 Y. Pei, G. Zhou, N. Luan, B. Zong, M. Qiao and F. F. Tao, *Chem. Soc. Rev.*, 2012, **41**, 8140–8162, <https://pubs.rsc.org/en/content/articlehtml/2021/xx/c2cs35182j>.
- 13 G. Shi, T. Tano, D. A. Tryk, M. Yamaguchi, A. Iiyama, M. Uchida, K. Iida, C. Arata, S. Watanabe and K. Kakinuma, *ACS Catal.*, 2022, **12**, 14209–14219.
- 14 A. Indra, P. W. Menezes, N. R. Sahraie, A. Bergmann, C. Das, M. Tallarida, D. Schmeißer, P. Strasser and M. Driess, *Journal of the American Chemical Society*, 2014, **136**, 17530–17536.
- 15 Z. Jia, Q. Wang, L. Sun, Q. Wang, L.-C. Zhang, G. Wu, J.-H. Luan, Z.-B. Jiao, A. Wang, S.-X. Liang, M. Gu and J. Lu, *Advanced Functional Materials*, 2019, **29**, 1807857, <https://advanced.onlinelibrary.wiley.com/doi/full/10.1002/adfm.201807857>.
- 16 L. Han, W. Mu, S. Wei, P. K. Liaw and D. Raabe, *Science advances*, 2024, **10**, eads3926.
- 17 Y. Yao, Z. Huang, P. Xie, S. D. Lacey, R. J. Jacob, H. Xie, F. Chen, A. Nie, T. Pu, M. Rehwoldt, D. Yu, M. R. Zachariah, C. Wang, R. Shahbazian-yassar, J. Li and L. Hu, *American Association for the Advancement of Science*, 2018, <https://www.science.org/doi/full/10.1126/science.aan5412>.
- 18 N. Kar, M. McCoy, J. Wolfe, S. L. A. Bueno, I. H. Shafei and S. E. Skrabalak, *Nat. Synth*, 2024, **3**, 175–184, <https://www.nature.com/articles/s44160-023-00409-0>.
- 19 S. Gao, S. Hao, Z. Huang, Y. Yuan, S. Han, L. Lei, X. Zhang, R. Shahbazian-yassar and J. Lu, *Nat Commun*, 2020, **11**, 2016, <https://www.nature.com/articles/s41467-020-15934-1>.



- 20 D. Wu, K. Kusada, T. Yamamoto, T. Toriyama, S. Matsumura, S. Kawaguchi, Y. Kubota and H. Kitagawa, *Journal of the American Chemical Society*, 2020, **142**, 13833–13838.
- 21 M. W. Glasscott, A. D. Pendergast, S. Goines, A. R. Bishop, A. T. Hoang, C. Renault and J. E. Dick, *Nat Commun*, 2019, **10**, 2650, <https://www.nature.com/articles/s41467-019-10303-z>.
- 22 W. Rong, Y. Chen, R. Dang, K. Huang, J. Xia, B. Zhang, J. Liu, H. Meng, Q. Cao and J. Wu, *Journal of Alloys and Compounds*, 2024, **971**, 172786, <https://www.sciencedirect.com/science/article/pii/S0925838823040896>.
- 23 Y. Wei, X. Liu, R. Yao, J. Qian, Y. Yin, de Li and Y. Chen, *Journal of Alloys and Compounds*, 2023, **938**, 168610, <https://www.sciencedirect.com/science/article/pii/S0925838822050010>.
- 24 Y. Liao, Y. Li, R. Zhao, J. Zhang, L. Zhao, L. Ji, Z. Zhang, X. Liu, G. Qin and X. Zhang, *Nat Sci Rev*, 2022, **9**, nwac041, <https://academic.oup.com/nsr/article/9/6/nwac041/6542465>.
- 25 a) M. Lau, A. Ziefuss, T. Komossa and S. Barcikowski, *Phys. Chem. Chem. Phys.*, 2015, **17**, 29311–29318, <https://pubs.rsc.org/en/content/articlelanding/2015/cp/c5cp04296h>; b) S. Kohsowski, R. Streubel, I. Radev, V. Peinecke, S. Barcikowski, G. Marzun and S. Reichenberger, *Applied Surface Science*, 2019, **467–468**, 486–492, <https://www.sciencedirect.com/science/article/pii/S016943321832899X>;
- 26 S. Reichenberger, G. Marzun, M. Muhler and S. Barcikowski, *ChemCatChem*, 2019, **11**, 4489–4518, <https://chemistry-europe.onlinelibrary.wiley.com/doi/full/10.1002/cctc.201900666>.
- 27 a) D. Zhang, J. Liu, P. Li, Z. Tian and C. Liang, *ChemNanoMat*, 2017, **3**, 512–533, <https://aces.onlinelibrary.wiley.com/doi/full/10.1002/cnm.a.201700079>; b) R. C. Forsythe, C. P. Cox, M. K. Wilsey and A. M. Müller, *Chemical reviews*, 2021, **121**, 7568–7637; c) A. A. Manshina, I. I. Tumkin, E. M. Khairullina, M. Mizoshiri, A. Ostendorf, S. A. Kulinich, S. Makarov, A. A. Kuchmizhak and E. L. Gurevich, *Advanced Functional Materials*, 2024, **34**, 2405457, <https://onlinelibrary.wiley.com/doi/full/10.1002/adfm.202405457>; d) D. Zhang, B. Gökce and S. Barcikowski, *Chemical reviews*, 2017, **117**, 3990–4103;
- 28 R. Streubel, S. Barcikowski and B. Gökce, *Opt. Lett.*, 2016, **41**, 1486–1489.
- 29 F. Waag, R. Streubel, B. Gökce and S. Barcikowski, *Appl Nanosci*, 2021, **11**, 1303–1312, <https://link.springer.com/article/10.1007/s13204-021-01693-y>.
- 30 C. Chen and L. V. Zhigilei, *Appl Phys A*, 2023, **129**, 1–35, <https://link.springer.com/article/10.1007/s00339-023-06525-0>.
- 31 M. Spellauge, M. Tack, R. Streubel, M. Miertz, K. S. Exner, S. Reichenberger, S. Barcikowski, H. P. Huber and A. R. Ziefuss, *Small*, 2023, **19**, e2206485, DOI: 10.1039/D5FD00087D [View Article Online](https://doi.org/10.1039/D5FD00087D)
- 32 T. Fromme, S. Reichenberger, K. M. Tibbetts and S. Barcikowski, *Beilstein J. Nanotechnol.*, 2024, **15**, 638–663, <https://www.beilstein-journals.org/bjnano/articles/15/54>.
- 33 T. Friedenauer, K. Buck, M. Eberwein, A.-L. Bunte, C. Rehbock and S. Barcikowski, *Particle & Particle Systems Characterization*, 2023, **40**, 2300034, <https://onlinelibrary.wiley.com/doi/full/10.1002/ppsc.202300034>.
- 34 T. Friedenauer, M. Spellauge, A. Sommereyns, C. Rehbock, H. P. Huber and S. Barcikowski, *J. Phys. Chem. C*, 2025, **129**, 6803–6816.
- 35 P. Wagener and S. Barcikowski, *Appl Phys A*, 2010, **101**, 435–439, <https://link.springer.com/article/10.1007/s00339-010-5814-x>.
- 36 T. Fromme, R. Müller, L. Krenz, L. K. Tintrop, I. Sanjuán, T. C. Schmidt, K. M. Tibbetts, C. Andronescu, S. Reichenberger and S. Barcikowski, *J. Phys. Chem. C*, 2025, **129**, 2953–2965.
- 37 M. Lau and S. Barcikowski, *Applied Surface Science*, 2015, **348**, 22–29, <https://www.sciencedirect.com/science/article/pii/S0169433214015815>.
- 38 A. R. Ziefuß, S. Reichenberger, C. Rehbock, I. Chakraborty, M. Gharib, W. J. Parak and S. Barcikowski, *J. Phys. Chem. C*, 2018, **122**, 22125–22136.
- 39 F. Waag, Y. Li, A. R. Ziefuß, E. Bertin, M. Kamp, V. Duppel, G. Marzun, L. Kienle, S. Barcikowski and B. Gökce, *RSC Advances*, 2019, **9**, 18547–18558, <https://pubs.rsc.org/en/content/articlehtml/2021/xx/c9ra03254a>.
- 40 S. Tahir, N. Shkodich, B. Eggert, J. Lill, O. Gatsa, M. Flimelová, E. Adabifiroozjaei, N. M. Bulgakova, L. Molina-Luna, H. Wende, M. Farle, A. V. Bulgakov, C. Doñate-Buendía and B. Gökce, *ChemNanoMat*, 2024, **10**, e202400064, <https://aces.onlinelibrary.wiley.com/doi/full/10.1002/cnm.a.202400064>.
- 41 J. Johnny, Y. Li, M. Kamp, O. Prymak, S.-X. Liang, T. Krekeler, M. Ritter, L. Kienle, C. Rehbock, S. Barcikowski and S. Reichenberger, *Nano Res.*, 2022, **15**, 4807–4819, <https://link.springer.com/article/10.1007/s12274-021-3804-2>.
- 42 N. F. Shkodich, I. D. Kovalev, K. V. Kuskov, D. Kovalev, Y. Vergunova, Y. Scheck, S. G. Vadchenko, O. Politano, F. Baras and A. S. Rogachev, *Journal of Alloys and Compounds*, 2022, **893**, 161839, <https://www.sciencedirect.com/science/article/pii/S0925838821032485>.
- 43 R. Stuckert, F. Pohl, O. Prymak, U. Schürmann, C. Rehbock, L. Kienle and S. Barcikowski, *Beilstein J. Nanotechnol.*, 2025, accepted.
- 44 A. S. Rogachev, D. Kovalev, Y. Vergunova, S. G. Vadchenko, D. O. Moskovskikh, N. Yurchenko, E. S. Panina, C. Zhang, O.



- V. Boyarchenko, Y. Morozov, A. Sheardy, M. Zhukovsky and A. S. Mukasyan, *Journal of Alloys and Compounds*, 2024, **1002**, 175401, <https://www.sciencedirect.com/science/article/pii/S0925838824019881>.
- 45 K. S. Kim, M. Couillard, Z. Tang, H. Shin, D. Poitras, C. Cheng, O. Naboka, D. Ruth, M. Plunkett, L. Chen, L. Gaburici, T. Lacelle, M. Nganbe and Y. Zou, *Nat Commun*, 2024, **15**, 1450, <https://www.nature.com/articles/s41467-024-45731-z>.
- 46 D. J. Chakrabarti and D. E. Laughlin, *Bulletin of Alloy Phase Diagrams*, 1984, **5**, 59–68, <https://link.springer.com/article/10.1007/BF02868727>.
- 47 C.-Y. Shih, M. V. Shugaev, C. Wu and L. V. Zhigilei, *Physical chemistry chemical physics : PCCP*, 2020, **22**, 7077–7099, <https://pubs.rsc.org/en/content/articlehtml/2020/cp/d0cp00608d>.
- 48 Q. Chen, L. Shi, G. Xu, M. Hu, M. Peng and Z. Yao, *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 2025, **709**, 136106, <https://www.sciencedirect.com/science/article/pii/S092777572500007X>.
- 49 *www.webelements.com*, available at: www.webelements.com.
- 50 G. Paltauf and H. Schmidt-Kloiber, *Appl Phys A*, 1999, **68**, 525–531, <https://link.springer.com/article/10.1007/s003390050935>.
- 51 a) A. Pyatenko, H. Wang, N. Koshizaki and T. Tsuji, *Laser & Photonics Reviews*, 2013, **7**, 596–604, <https://onlinelibrary.wiley.com/doi/full/10.1002/lpor.201300013>; b) A. Takami, H. Kurita and S. Koda, *J. Phys. Chem. B*, 1999, **103**, 1226–1232;
- 52 H. Huang and L. V. Zhigilei, *J. Phys. Chem. C*, 2021, **125**, 13413–13432.
- 53 T. Fromme, L. K. Tintrop, S. Reichenberger, T. C. Schmidt and S. Barcikowski, *ChemPhysChem*, 2023, **24**, e202300089, <https://chemistry-europe.onlinelibrary.wiley.com/doi/full/10.1002/cphc.202300089>.
- 54 H. Huang and L. V. Zhigilei, *Sci. China Phys. Mech. Astron.*, 2022, **65**, 1–16, <https://link.springer.com/article/10.1007/s11433-021-1881-8>.
- 55 M. Tack, M. Usama, N. Kazamer, K. S. Exner, M. Brodmann, S. Barcikowski and S. Reichenberger, *ACS Appl. Energy Mater.*, 2024, **7**, 4057–4067.
- 56 N. G. Simpson and K. M. Tibbetts, *J. Phys. Chem. C*, 2025, **129**, 5383–5392.
- 57 G. Marzun, H. Bönemann, C. Lehmann, B. Spliethoff, C. Weidenthaler and S. Barcikowski, *ChemPhysChem*, 2017, **18**, 1175–1184, <https://chemistry-europe.onlinelibrary.wiley.com/doi/full/10.1002/cphc.201601315>.
- 58 a) T. Simao, D. M. Chevrier, J. Jakobi, A. Korinek, G. Goupil, M. Lau, S. Garbarino, P. Zhang, S. Barcikowski, M.-A. Fortin and D. Guay, *J. Phys. Chem. C*, 2016, **120**, 22635–22645; b) D. Zhang, Z. Ma, M. Spasova, A. E. Yelsukova, S. Lu, M. Farle, U. Wiedwald and B. Gökce, *Part. Part. Syst. Charact.*, 2017, **34**, 1600225;
- 59 a) J. R. Anderson, *Doctoral Dissertation*, 1946, <https://dspace.mit.edu/bitstream/handle/1721.1/82742/27002020-mit.pdf>; b) R. B. McLellan, *Scripta Metallurgica*, 1969, **3**, 389–391, <https://www.sciencedirect.com/science/article/pii/0036974869902622>;
- 60 a) C.-C. Hu and Y.-R. Wu, *Materials Chemistry and Physics*, 2003, **82**, 588–596, <https://www.sciencedirect.com/science/article/pii/S025405840300316X>; b) J. Haenen, W. Visscher and E. Barendrecht, *Electrochimica Acta*, 1986, **31**, 1541–1551, <https://www.sciencedirect.com/science/article/pii/0013468686870736>;
- 61 C. Luan, D. Escalera-López, U. Hagemann, A. Kostka, G. Laplanche, D. Wu, S. Cherevko and T. Li, *ACS Catal.*, 2024, **14**, 12704–12716.
- 62 a) G. Marzun, A. Levish, V. Mackert, T. Kallio, S. Barcikowski and P. Wagener, *Journal of Colloid and Interface Science*, 2017, **489**, 57–67, <https://www.sciencedirect.com/science/article/pii/S0021979716306695>; b) K. Lian, S. J. Thorpe and D. W. Kirk, *Electrochimica Acta*, 1992, **37**, 2029–2041, <https://www.sciencedirect.com/science/article/pii/001346869287119K>; c) D. E. Pissinis, L. E. Sereno and J. M. Marioli, *OJPC*, 2012, **02**, 23–33;
- 63 L. Dai, C. Fang, F. Yao, X. Zhang, X. Xu, S. Han, J. Deng, J. Zhu and J. Sun, *Applied Surface Science*, 2023, **623**, 156991, <https://www.sciencedirect.com/science/article/pii/S0169433223006682>.
- 64 K. M. Cole, *Amorphous Ni-Based Alloys as Alkaline Oxygen Evolution Electrocatalysts*, Dissertation, 2022.
- 65 A. M. Zaky and F. H. Assaf, *British Corrosion Journal*, 2002, **37**, 48–55.
- 66 J. Kang, F. Li, Z. Xu, X. Chen, M. Sun, Y. Li, X. Yang and L. Guo, *JACS Au*, 2023, **3**, 2660–2676, <https://pmc.ncbi.nlm.nih.gov/articles/PMC10598560/>.
- 67 S.-X. Liang, L.-C. Zhang, S. Reichenberger and S. Barcikowski, *Physical chemistry chemical physics : PCCP*, 2021, **23**, 11121–11154, <https://pubs.rsc.org/en/content/articlehtml/2021/cp/d1cp00701g>.
- 68 X. Xu, Y. Guo, B. P. Bloom, J. Wei, H. Li, H. Li, Y. Du, Z. Zeng, L. Li and D. H. Waldeck, *ACS nano*, 2020, **14**, 17704–17712.
- 69 D. Guan, W. Zhou and Z. Shao, *Small Science*, 2021, **1**, 2100030, <https://onlinelibrary.wiley.com/doi/full/10.1002/ssmc.202100030>.
- 70 J. Chantaramethakul, C. Hussakan, Y. Yenmankhong, P. Chandeang, R. Techapiesancharoenkij, W. Hirunpinoyopas, Kasmui, C. Kurniawan and G. Panomsuwan, *RSC Adv.*, 2024, **14**, 31648–31654, <https://pubs.rsc.org/en/content/articlelanding/2024/ra/d4ra04809a>.



- 71 a) M. Ławrywianiec, J. Smajdor, B. Paczosa-Bator and R. Piech, *Anal. Methods*, 2017, **9**, 6662–6668, <https://pubs.rsc.org/en/content/articlelanding/2017/ay/c7ay02140b>; b) J. Smajdor, R. Piech, M. Pięk and B. Paczosa-Bator, *Journal of Electroanalytical Chemistry*, 2017, **799**, 278–284, <https://www.sciencedirect.com/science/article/pii/S1572665717304411>;
- 72 D. Amans, M. Diouf, J. Lam, G. Ledoux and C. Dujardin, *Journal of Colloid and Interface Science*, 2017, **489**, 114–125, <https://www.sciencedirect.com/science/article/pii/S0021979716305720>.
- 73 S. Harris, E. Kaplan, M. Aftel and K. M. Tibbetts, *J. Phys. Chem. B*, 2024, **128**, 10481–10491.
- 74 L. Lutterotti, *Universita di Trento 38050 Trento, Italy*, 2006, 1–18.
- 75 L. Wang, D. Mercier, S. Zanna, A. Seyeux, M. Laurent-Brocq, L. Perrière, I. Guillot and P. Marcus, *Corrosion Science*, 2020, **167**, 108507, <https://www.sciencedirect.com/science/article/pii/S0010938X19327829>.

View Article Online
DOI: 10.1039/D5FD00087D



Data Availability Statement

View Article Online
DOI: 10.1039/D5FD00087D

Amorphization of Laser-fabricated Ignoble High-Entropy Alloy Nanoparticles and its Impact on Surface Composition and Electrochemistry

Robert Stuckert,^a Felix Pohl,^b Natalia Shkodich,^c Oleg Prymak,^d Nico Koch,^a Ulrich Schürmann,^b Michael Farle,^c Lorenz Kienle,^b Stephan Barcikowski,^a and Christoph Rehbock^{*a}

^a Technical Chemistry I and Center for Nanointegration Duisburg-Essen (CENIDE), University of Duisburg-Essen, 45141 Essen, Germany.

^b Institute for Material Science, Synthesis and Real Structure, Faculty of Engineering, Christian-Albrechts University of Kiel, 24143 Kiel, Germany.

^c Faculty of Physics and Center for Nanointegration Duisburg-Essen (CENIDE), University of Duisburg-Essen, 47057 Duisburg, Germany.

^d Inorganic Chemistry and Center for Nanointegration Duisburg-Essen (CENIDE), 45141 Essen, Germany.

The raw data that support the findings of this study are available from the corresponding author, Christoph Rehbock upon reasonable request.

