



Cite this: *RSC Appl. Interfaces*, 2025, 2, 837

Comment on the “Reaction intermediates recognized by in situ FTIR spectroscopy in CO₂ hydrogenation over the Cu/ZnO/SPP-zeolite catalyst” by X. Liu *et al.*, *RSC Appl. Interfaces*, 2025, 2, 114

Received 23rd January 2025,
Accepted 28th March 2025

Frederic C. Meunier

DOI: 10.1039/d5lf00014a

Gaseous CO₂ exhibits hundreds of bands in the mid-IR region due to transitions between excited states and isotopologues. The intensity of these bands are orders of magnitude lower than that of the main features and are often misinterpreted as bands of adsorbates.

rs.c.li/RSCApplInter

Liu *et al.*¹ assigned in situ FTIR bands at *ca.* 2075 cm⁻¹ and 2060 cm⁻¹ to the stretching vibrations of different carbonyls that bonded to Cu metal surfaces (Cu-C=O) (Fig. 1). This assignment is incorrect, as these bands are merely those of gaseous CO₂ (Fig. 2), which is present in the IR cell. The difference of wavenumber (± 2 cm⁻¹) is due to the error on

band position at the resolution used. This recurring misinterpretation has already been discussed elsewhere.² The authors should thus revise data interpretation and conclusions of their paper in the light of this comment.

CuZn-SPP-E catalyst exposed to flowing CO₂ (A) and then to CO₂ + 3H₂ (B) at 150 °C.




Fig. 1 Reproduction of figure 4 from (ref. 1) describing the in situ FTIR spectra of the reduced.



Comment




Fig. 2 Gas-phase CO₂ spectrum (reproduced with permission from (ref. 2)).

Data availability

Data will be made available on request to the corresponding author.

Conflicts of interest

There are no conflicts to declare.

References

- 1 X. Liu, *et al.*, *RSC Appl. Interfaces*, 2025, 2, 114–121.
- 2 F. C. Meunier and C. Scarfiello, *Appl. Catal., B*, 2023, 330, 122610, DOI: [10.1016/j.apcatb.2023.122610](https://doi.org/10.1016/j.apcatb.2023.122610).

