


 Cite this: *RSC Adv.*, 2025, **15**, 18324

## A floatable $\text{TiO}_2$ –Ag photocatalyst enables effective antibiotic degradation and pathogen growth control†

Minh Thi Nguyen, <sup>a</sup> Phuong Thu Ha, <sup>b</sup> Thi Thu Huong Le, <sup>c</sup> Huong Giang Bui, <sup>a</sup> Ke Son Phan, <sup>b</sup> Nhat Huy Chu, <sup>a</sup> Thi Thu Trang Mai, <sup>b</sup> Thuy Dieu Thi Ung, <sup>b</sup> Anh Tuyet Thi Le <sup>a</sup> and Phuong Ha Hoang <sup>\*a</sup>

This study explores the powerful capabilities of a floatable photocatalyst,  $\text{TiO}_2$ –Ag immobilized on expanded clay (EC), for photocatalytic antibiotic degradation and pathogen inhibition in aquaculture systems. The porous and floatable nature of EC makes it an ideal carrier for enhancing photocatalytic activity, enabling the easy recovery and reusability of  $\text{TiO}_2$ –Ag. The synthesis of  $\text{TiO}_2$ –Ag/EC is optimized by adjusting  $\text{TiO}_2$ –Ag concentration, integration time, and stirring speed, with a peak Ti content of  $2584.51 \pm 49.52$  ppm achieved under specific conditions (35 000 ppm  $\text{TiO}_2$ –Ag, 12 hours integration, 100 rpm stirring). Remarkably, within 2 hours of sunlight exposure,  $\text{TiO}_2$ –Ag/EC (10% w/v) reduced the pathogenic density of *Vibrio harveyi*, *Vibrio parahaemolyticus*, and *Escherichia coli* from  $10^6$  CFU mL<sup>-1</sup> to under 100 CFU mL<sup>-1</sup>, maintaining antibacterial efficacy even after seven cycles. Beyond pathogen control,  $\text{TiO}_2$ –Ag/EC degraded over 92% of tetracycline and oxytetracycline at pH 7–9 and achieved up to 95.7% rifampicin removal at pH 5, within 4 hours of sunlight exposure. The degraded antibiotic solution lost its bactericidal activity, suggesting the safety of the formed byproducts for the environment. Notably, at the  $\text{TiO}_2$ –Ag/EC addition ratio of 2.5% w/v, equivalent to a Ti concentration of approximately 62.5 ppm, the material reached a maximum COD removal efficiency of  $82.7 \pm 2.0\%$  after 40 hours of illumination. These results highlight the potential of  $\text{TiO}_2$ –Ag/EC as a sustainable solution for eliminating antibiotic residues, organic matter, and controlling disease spread in aquaculture environments.

Received 4th April 2025  
 Accepted 21st May 2025

DOI: 10.1039/d5ra02333e

rsc.li/rsc-advances

## Introduction

The rapid expansion of high-density shrimp farming has given rise to significant environmental challenges, particularly in the form of pathogenic bacteria and antibiotic residues. Shrimp feed typically contains 33–45% protein, however, only a fraction of nitrogen (24–37%) and phosphorus (13–28%) are utilized by the shrimp.<sup>1</sup> The accumulation of excess organic nutrients not only pollutes the water but also creates a favorable environment for disease outbreaks, undermining shrimp growth and survival rates. Traditionally, various types of synthetic antibiotics have been widely used to control pathogens. However, up to 75% of the antibiotics fed to aquatic animals are excreted into the water, causing a high risk of the emergence of antibiotic-

resistant bacteria and human health.<sup>2</sup> A study by Pesi *et al.* showed that up to 90% of aquatic bacteria have developed the resistance to at least one antibiotic. Among them, antibiotic-resistant genes are commonly found in *Escherichia coli*, *Aeromonas*, and *Vibrio* genus.<sup>3</sup> These ongoing challenges highlight the urgent need for effective treatment solutions that can manage pathogen spread and reduce antibiotic residues in the environment, thereby preserving water quality and ensuring the sustainability of aquaculture.

Antibiotics degrade through several processes, including photodegradation, hydrolysis, and biodegradation, with their effectiveness largely influenced by environmental factors such as pH, temperature, and chemical composition.<sup>4</sup> Biological methods are favored due to their low cost and environmental benefits, but modern antibiotics have complex chemical structures that can hinder bacterial growth and disrupt microbial metabolism. This challenge complicates bacterial-based degradation methods and raises concerns about the development of antibiotic-resistant genes.<sup>5</sup> While physical filtration membranes can adsorb antibiotics, they suffer from frequent clogging, which increases maintenance costs and limits their widespread application.<sup>6</sup>

<sup>a</sup>Institute of Biology, Vietnam Academy of Science and Technology, 18 Hoang Quoc Viet Road, Cau Giay District, Hanoi 100000, Vietnam. E-mail: hph@ibt.ac.vn

<sup>b</sup>Institute of Materials Science, Vietnam Academy of Science and Technology, 18 Hoang Quoc Viet Road, Cau Giay District, Hanoi 100000, Vietnam

<sup>c</sup>Vietnam National University of Agriculture, Trau Quy, Gia Lam District, Hanoi 100000, Vietnam

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d5ra02333e>



Chemical methods using photocatalysts like  $\text{TiO}_2$ –Ag nanoparticles have gained attention for their ability to degrade pollutants effectively. Photocatalysis offers distinct advantages, including the use of light energy to generate reactive oxygen species (ROS) that can break down pollutants under normal temperature and pressure conditions, converting organic contaminants into harmless byproducts like  $\text{CO}_2$  and  $\text{H}_2\text{O}$ .<sup>7</sup> ROS can also penetrate bacterial cells, damaging vital components such as proteins, DNA, and lipids, leading to cell death. These properties make photocatalysis a promising approach for addressing antibiotic pollution and controlling pathogenic bacteria in the environment.<sup>8</sup> However, a major challenge is the recovery of photocatalytic particles after use. These powder nanoparticles often aggregate or remain suspended in the solution, reducing their active surface area, limiting pollutant interactions, and decreasing light absorption efficiency. Furthermore, the lack of established regulations surrounding the management of photocatalytic materials raises concerns about secondary pollution from nano-sized particles.<sup>9</sup>

Therefore, in the last few years, attention has been paid to designing the floatable photocatalyst to enable the easy recovery and reusability of the material. In contrast to powder material, floatable photocatalysts owe their unique advantage of direct sunlight irradiation without the attenuation caused by water, hence, enhancing photocatalytic performance.<sup>10</sup> In previous research, the expanded clay (EC) carriers were successfully fabricated by pyrolyzing a mixture of clay and rice husk at  $1200^\circ\text{C}$ , followed by rapid cooling. This process results in a rigid, porous structure that efficiently integrates and protects the  $\text{TiO}_2$ –Ag photocatalyst. The floatable nature of expanded clay enhances light exposure and maximizes oxygen involvement in the photocatalytic degradation process at the water/air interface. Preliminary results show that  $\text{TiO}_2$ –Ag immobilized on expanded clay can inhibit *Vibrio parahaemolyticus* by up to 99% within 2 hours of halogen lamp illumination.<sup>11</sup> Building on these findings, the present study will optimize the integration of  $\text{TiO}_2$ –Ag onto expanded clay and evaluate its ability to inhibit a range of pathogenic bacteria and degrade commonly used antibiotics in aquaculture environments. The photocatalytic performance of  $\text{TiO}_2$ –Ag/EC will be assessed under natural sunlight to provide a realistic evaluation of its efficiency in the wastewater treatment process. Ultimately, this research aims to confirm the potential practical significance of  $\text{TiO}_2$ –Ag/EC composites as a sustainable solution for tackling pollution and disease in aquaculture systems.

## Experimental

### Materials

The pathogenic bacteria, *Escherichia coli*, *Vibrio harveyi*, and *Vibrio parahaemolyticus*, and the probiotic *Lactobacillus acidophilus* were provided by the Key Laboratory of Bioprocess and Biochemical Synthesis Engineering, Institute of Biology, VAST. All the chemicals used in this study, including tetracycline (99%) and oxytetracycline hydrochloride (95%) were purchased from Sigma-Aldrich (St. Louis, MO, USA), while the Rifampicin (95%) was purchased from bioWorld (Dublin, Ohio, US). The de

Man–Rogosa–Sharpe (MRS) and Luria–Bertani medium (LB, Sigma-Aldrich, UK) were used to culture the *E. coli* and *L. acidophilus* bacteria, respectively. The pathogens, *V. harveyi* and *V. parahaemolyticus*, were activated in the thiosulfate citrate bile salts sucrose agar plate (TCBS, Sigma-Aldrich, UK), then were aerobically inoculated in LB medium until reaching a desired bacterial density. The MRS medium contains ( $\text{g L}^{-1}$ ): peptone (10), meat extract (10), yeast extract (5), glucose (20),  $\text{K}_2\text{HPO}_4$  (2),  $\text{NH}_4\text{Cl}$  (2),  $\text{CH}_3\text{COONa}$  (5),  $\text{MgSO}_4$  (0.2),  $\text{C}_6\text{H}_{17}\text{N}_3\text{O}_7$  (5), tween (80–100  $\mu\text{l}$ ), pH-6.5.

In the current study, the photocatalytic activity of the  $\text{TiO}_2$ –Ag/EC was assessed under the natural sunlight irritation at the Institute of Biology (VAST), which is located at  $21^\circ 02' 57.2''\text{N}$   $105^\circ 48' 06.8''\text{E}$ . The experiments were conducted during the time of July to September with the measured light density ranging from 70 to 100 klux, and temperature of 30 to 35 °C.

### Optimizing the immobilization of $\text{TiO}_2$ –Ag into expanded clay carrier

The expanded clay material (EC) and  $\text{TiO}_2$ –Ag photocatalyst were prepared using the method outlined in a previous study by Hoang *et al.*<sup>11</sup> The properties of the EC carrier, including surface areas, pore volume, and pore size, were examined using  $\text{N}_2$  physisorption isotherms at 77 K (Tristar-3030 system, Micromeritics-USA). The EC material was then rinsed with water and dried at 60 °C for 5 hours to eliminate dirt and impurities. Subsequently,  $\text{TiO}_2$ –Ag particles were dispersed in a 0.05% alginate solution with varying titanium concentrations (20 000, 25 000, 30 000, or 35 000 ppm). EC was then added to glass beakers containing the prepared  $\text{TiO}_2$ –Ag solutions at a mass ratio of 1 : 2 (w/v). During the integration process of  $\text{TiO}_2$ –Ag onto EC, the beakers were magnetically stirred at 100 rpm. After 6, 12, or 18 hours, the EC material was separated from the solution by filtration and subsequently dried at 60 °C for another 5 hours. The titanium and silver content integrated into the EC material ( $\text{TiO}_2$ –Ag/EC) was analyzed by the inductively coupled plasma mass spectrometry (ICP-MS, ICP Mass Spectrometer, Nexion 2000, PerkinElmer, USA) and the energy-dispersive X-ray spectroscopy (EDX) analyses (Hitachi S-4800 FE-SEM equipped with a Bruker Quantax EDS syste). Based on the results, a comparison was made to determine the optimal initial concentration of the  $\text{TiO}_2$ –Ag solution and the integration time to achieve the highest integration efficiency.

### Measurement of hydrogen peroxide formation by the $\text{TiO}_2$ –Ag/EC material

The  $\text{TiO}_2$ –Ag/EC (3 g) material was added to a 50 mL beaker containing 30 mL of deionized water (HI70346, Hanna Instruments, USA). The beakers were irradiated under sunlight for 4 hours. At the end of each hour, a sample was collected to measure the concentration of hydrogen peroxide formed at 230 nm using a quartz cuvette (UV-1601 Spectrophotometer, SHIMADZU, Japan).<sup>12</sup> The negative control consisted of beakers without any added material. After the first cycle, the material was collected and air-dried at room temperature for approximately 24 hours before being reused in subsequent tests. The



experiment was conducted in triplicate and repeated for a total of 10 cycles.

### Anti-pathogen activity of $\text{TiO}_2\text{-Ag/EC}$ material

The antibacterial activity of the  $\text{TiO}_2\text{-Ag}$  integrated EC material ( $\text{TiO}_2\text{-Ag/EC}$ ) was evaluated against several pathogenic bacteria, including *Vibrio harveyi*, *Vibrio parahaemolyticus*, and *Escherichia coli*. The biomass of these bacterial strains was separately dissolved in a sterile saline solution (0.9% NaCl) to achieve a bacterial density of  $10^6 \text{ CFU mL}^{-1}$ .  $\text{TiO}_2\text{-Ag/EC}$  particles were then added to each transparent glass vial containing 5 mL of the prepared bacterial solutions. For comparison, an experimental vial containing EC material without  $\text{TiO}_2\text{-Ag}$  integration served as the negative control. After 2 hours of exposure to sunlight, samples were collected to measure the remaining bacterial density in the vials, allowing us to determine the antibacterial effectiveness of the  $\text{TiO}_2\text{-Ag/EC}$  material. The antibacterial effectiveness ( $A$ ) was calculated using the following formula, where  $N_0$  and  $N_t$  represent the bacterial densities before and after treatment with  $\text{TiO}_2\text{-Ag/EC}$ , respectively.

$$A = \log N_0 - \log N_t = \log(N_0/N_t)$$

Following each experiment, the  $\text{TiO}_2\text{-Ag/EC}$  material was gently rinsed with water and left to air dry at room temperature for approximately 24 hours before being reused in subsequent tests. The experiment was repeated over seven cycles using the same method to assess the stability of the material's antibacterial activity.

### Antibiotic degradation ability of $\text{TiO}_2\text{-Ag/EC}$ material

The photocatalytic degradation capability of the  $\text{TiO}_2\text{-Ag/EC}$  material was assessed using three types of antibiotics: tetracycline (TET), oxytetracycline (OTC), and rifampicin (RIF). Reaction solutions were prepared for each antibiotic at varying concentrations (10, 20, and 30 ppm) and pH values (3, 5, 7, and 9). To initiate the experiment, three grams of the  $\text{TiO}_2\text{-Ag/EC}$  material were added to 30 mL of the antibiotic solution and stirred gently in the dark for 30 minutes to reach an equilibrium adsorption state. After this period, the mixture was exposed to sunlight for 4 hours. During the experiment, samples were taken at 1, 2, 3, and 4 hours to measure the remaining concentrations of TET, OTC, and RIF. The concentrations were determined using optical methods at specific UV wavelengths: 354 nm for TET,<sup>13</sup> 352 nm for OTC,<sup>14</sup> and 335 nm for RIF.<sup>15</sup> In the negative control, EC material without  $\text{TiO}_2\text{-Ag}$  was included in the reaction solution. The degradation efficiency of the antibiotics ( $H$ ) was calculated using the following formula:

$$H (\%) = ((C_0 - C_t)/C_0) \times 100\%$$

where  $C_0$  represents the initial concentration of the antibiotic, and  $C_t$  is the remaining concentration of the antibiotic in the reaction vial at time  $t$ .

The stability of the  $\text{TiO}_2\text{-Ag/EC}$  material for degrading the antibiotic tetracycline was evaluated at an initial concentration

of 10 ppm and a pH of 7. After the first cycle, the material was collected and air-dried at room temperature for approximately 24 hours before being reused in subsequent tests. The experiment was conducted in triplicate and repeated for a total of 10 cycles.

### Kinetic study on the antibiotics photocatalysis degradation process

Furthermore, the degradation kinetics of each tested antibiotic were analyzed using a pseudo-first-order (PFO) kinetic model, expressed by the equation:

$$\ln(C_0/C_t) = kt$$

where  $k$  denotes the reaction rate constant for antibiotic degradation.

### Toxicity of photo-catalytically degraded antibiotic solutions on bacterial growth

In this study, the effect of photocatalytically degraded antibiotic solutions on bacterial growth was examined. The biomass of the probiotic *Lactobacillus acidophilus* and the pathogen *Vibrio parahaemolyticus* was prepared at a concentration of  $10^5 \text{ CFU mL}^{-1}$  and added (2% v/v) to Eppendorf tubes containing 100  $\mu\text{L}$  of the appropriate growth media for each bacterial strain, specifically MRS and LB. Then, antibiotic solutions of tetracycline (TET), oxytetracycline (OTC), and rifampicin (RIF) (10 ppm, pH 7) after degradation by  $\text{TiO}_2\text{-Ag/EC}$ , labeled as  $\text{TET}_{\text{TA}}$ ,  $\text{OTC}_{\text{TA}}$ , and  $\text{RIF}_{\text{TA}}$ , were diluted using MRS or LB medium and added to each bacterial tube at different antibiotic concentrations: 0, 5, 10, 15, 20, 25, and 30% (v/v).

Additionally, control groups were established where the bacterial tubes were supplemented with either: (1) antibiotic solutions that were photodegraded under light using a material that did not contain  $\text{TiO}_2\text{-Ag}$ , labeled as  $\text{TET}_{\text{EC}}$ ,  $\text{OTC}_{\text{EC}}$ , and  $\text{RIF}_{\text{EC}}$ , or (2) the original TET, OTC, and RIF solutions at a concentration of 10 ppm, pH 7. These were included for comparison with the effects observed from the  $\text{TET}_{\text{TA}}$ ,  $\text{OTC}_{\text{TA}}$ , and  $\text{RIF}_{\text{TA}}$  solutions on bacterial growth. The tubes without any added antibiotics served as the negative control.

The experimental model is illustrated in Fig. S1.<sup>†</sup> After 24 hours of incubation at 35 °C, samples were collected to measure the optical density (OD) of the bacterial solutions at 600 nm. The experimental tubes containing antibiotics that exhibited significantly different ( $p < 0.05$ ) lower  $\text{OD}_{600}$  values compared to the negative control were determined to have reached the minimum inhibitory concentration necessary to inhibit bacterial growth.

### COD removal capacity of $\text{TiO}_2\text{-Ag/EC}$ material

A stock solution with a chemical oxygen demand (COD) concentration of 250 mg  $\text{L}^{-1}$  was prepared by adding shrimp feed (Tomboy, Skretting Vietnam) to distilled water at a 0.07% w/v ratio, followed by sterilization.<sup>16</sup> This stock solution was used to simulate aquaculture environments with varying organic contamination levels (25, 50, and 100 mg  $\text{L}^{-1}$ ).  $\text{TiO}_2\text{-Ag/EC}$  material was added to the stock solution at a 1:100 weight ratio and stirred for 30 minutes in the dark. The mixture was then exposed to sunlight for 4 hours. The remaining COD concentration was measured at 600 nm using a spectrophotometer.



EC material was then added to each COD solution at a 10% w/v concentration. The samples were exposed to sunlight for 8 hours daily, from 8:30 AM to 4:30 PM. After each 8 hours exposure period, samples were collected to measure the remaining COD concentration in the environment, following the method outlined by LaPara *et al.*<sup>17</sup> The efficiency of COD removal was calculated using the following equation:

$$\text{Degradation efficiency (\%)} = ((C_0 - C_t)/C_0) \times 100\%$$

where  $C_0$  is the initial COD concentration at the beginning of the experiment, and  $C_t$  is the remaining COD concentration in the reactor at time  $t$ .

To assess the impact of the  $\text{TiO}_2\text{-Ag}/\text{EC}$  material addition ratio on treatment efficiency, six transparent glass beakers were prepared, each containing 1 liter of a solution with a COD concentration of  $100 \text{ mg L}^{-1}$ . Different ratios of  $\text{TiO}_2\text{-Ag}/\text{EC}$  material (0.5%, 1%, 2.5%, 5%, and 7.5% w/v) were added to each beaker, and the photocatalytic degradation process was carried out under sunlight. Samples were collected to measure the remaining COD, ammonia, and nitrite concentrations in the environment after each 8 hours exposure period. Based on the obtained results, the appropriate concentration of photocatalytic material addition was selected to achieve high COD degradation efficiency.

## Results and discussion

### Optimizing the immobilization of $\text{TiO}_2\text{-Ag}$ on expanded clay carrier

In this study, the synthesized  $\text{TiO}_2\text{-Ag}$  were uniformly dispersed in the alginate polymer solution. During this synthesis process, the long chains of the alginate polymer envelop the nanoparticles, which not only enhances the stability of the material system but also plays a vital role in the subsequent integration of  $\text{TiO}_2\text{-Ag}$  onto the EC carrier.

When the EC is introduced into the prepared nanoparticle solution, the stirring during the integration process causes the alginate chains, which are bound to the  $\text{TiO}_2\text{-Ag}$  nanoparticles,

to continue surrounding the EC (Fig. 1a). The Brunauer–Emmett–Teller analysis indicated that the original EC has a total surface area of  $2.41 \text{ m}^2 \text{ g}^{-1}$ , displaying moderate mesoporosity with an average pore diameter ranging from 8 to 18 nm, along with minimal microporosity. These properties suggest that the outer porous structure of the EC offers optimal docking sites for the nanoparticles, facilitating efficient integration (Fig. S2†). As the  $\text{TiO}_2\text{-Ag}$  solution concentration increased from 20 000 ppm to 35 000 ppm, and the integration time extended from 6 to 12 to 18 hours, more nanoparticles were incorporated into the EC's surface pores. The integration efficiency peaked at a  $\text{TiO}_2\text{-Ag}$  concentration of 35 000 ppm, with the Ti density on the EC reaching its maximum of  $2503.95 \pm 35.80 \text{ ppm}$  after 12 hours. No further increase in Ti content was observed when the integration time was extended to 18 hours (Fig. 1b and Table 1). Additionally, the EDX results clearly demonstrate that the original EC carrier contains a low Ti content of  $0.51 \pm 0.11\%$  and does not include any silver. In contrast, the Ti content in the fabricated  $\text{TiO}_2\text{-Ag}/\text{EC}$  significantly increases to  $17.22 \pm 1.80\%$ , while the Ag content rises to  $0.75 \pm 0.12\%$ . Furthermore, the immobilization of  $\text{TiO}_2\text{-Ag}$  nanoparticles enhances the total surface area of  $\text{TiO}_2\text{-Ag}/\text{EC}$  to  $3.17 \text{ m}^2 \text{ g}^{-1}$  (Fig. S2 and S3†). The distribution of  $\text{TiO}_2\text{-Ag}$  nanoparticles on the EC carrier can be observed in the FESEM images at various magnifications (Fig. 2).

In similar research, Kaur *et al.* optimized the integration of  $\text{TiO}_2$  onto clay beads for the degradation of the fungicide carbendazim.<sup>18</sup> Though the exact Ti content integrated into the support was not specified, the authors found that an initial  $\text{TiO}_2$  concentration of 20 000 ppm, with two integration steps over 24 hours, resulted in the thickest  $\text{TiO}_2$  layer. However, no further increase in  $\text{TiO}_2$  thickness occurred after repeating the integration. In contrast, the present study found that the integration of  $\text{TiO}_2\text{-Ag}$  reached saturation much more quickly, after just one 12 hours integration step with an initial  $\text{TiO}_2\text{-Ag}$  concentration of 35 000 ppm. The difference may arise from the uniform dispersion of  $\text{TiO}_2\text{-Ag}$  within the alginate and the continuous stirring that occurred during the integration process in this study, contrasting with the static condition of




Fig. 1 Integration mechanism of  $\text{TiO}_2\text{-Ag}$  onto an expanded clay carrier (a) and impact of integration time and concentration on the immobilization of  $\text{TiO}_2\text{-Ag}$  on the EC carrier (b).



Table 1 Variation in Ti and Ag concentrations immobilized on EC under varying time and  $\text{TiO}_2$ –Ag concentration conditions

			Ti (ppm)	Ag (ppm)
Original EC			38.94 $\pm$ 5.32	—
Ti content in $\text{TiO}_2$ –Ag	Time	Sample	Ti content on EC (ppm)	Ag content on EC (ppm)
20 000 ppm	6 h	$\text{TiO}_2$ –Ag/EC <sub>6–20k</sub>	524.32 $\pm$ 63.21	154.47 $\pm$ 24.74
	12 h	$\text{TiO}_2$ –Ag/EC <sub>12–20k</sub>	597.26 $\pm$ 20.40	132.63 $\pm$ 37.65
	18 h	$\text{TiO}_2$ –Ag/EC <sub>18–20k</sub>	755.85 $\pm$ 28.53	133.66 $\pm$ 8.12
25 000 ppm	6 h	$\text{TiO}_2$ –Ag/EC <sub>6–25k</sub>	685.36 $\pm$ 10.06	306.71 $\pm$ 63.58
	12 h	$\text{TiO}_2$ –Ag/EC <sub>12–25k</sub>	814.33 $\pm$ 30.11	116.71 $\pm$ 2.76
	18 h	$\text{TiO}_2$ –Ag/EC <sub>18–25k</sub>	864.63 $\pm$ 6.79	226.00 $\pm$ 39.93
30 000 ppm	6 h	$\text{TiO}_2$ –Ag/EC <sub>6–30k</sub>	631.09 $\pm$ 89.44	354.75 $\pm$ 34.21
	12 h	$\text{TiO}_2$ –Ag/EC <sub>12–30k</sub>	957.00 $\pm$ 52.95	405.17 $\pm$ 52.73
	18 h	$\text{TiO}_2$ –Ag/EC <sub>18–30k</sub>	1198.60 $\pm$ 42.39	350.73 $\pm$ 34.85
35 000 ppm	6 h	$\text{TiO}_2$ –Ag/EC <sub>6–35k</sub>	1691.25 $\pm$ 19.02	793.5 $\pm$ 92.62
	12 h	$\text{TiO}_2$ –Ag/EC <sub>12–35k</sub>	2503.95 $\pm$ 35.80	961.62 $\pm$ 54.55
	18 h	$\text{TiO}_2$ –Ag/EC <sub>18–35k</sub>	2584.51 $\pm$ 49.52	332.45 $\pm$ 23.85

the  $\text{TiO}_2$  nanoparticles during the integration process described by Kaur *et al.*<sup>18</sup> This study investigated a novel strategy for improving  $\text{TiO}_2$ –Ag nanoparticles' immobilization efficiency. The approach emphasizes two principal factors. First, alginate chains function as an effective matrix for coating the porous surface of the EC carrier, facilitated by water flow induced through mechanical stirring. However, careful optimization of stirring speed is required to prevent excessive shear stress, which may lead to detachment of the immobilized  $\text{TiO}_2$ –Ag nanoparticles from the carrier surface. Overall, the results demonstrate that the immobilization efficiency is governed by multiple parameters, including the physicochemical properties and concentration of  $\text{TiO}_2$ –Ag, as well as the morphological characteristics of the EC carrier.


Previously, various methods have been employed in previous research to integrate photocatalytic substances into materials, including high-temperature treatment, sol-spray coating, electrodeposition, chemical vapor deposition (CVD), and dip-coating.<sup>19</sup> Electrodeposition, for example, allows for the formation of photocatalytic layers with controllable thicknesses tailored to specific structures.<sup>20</sup> Dunlop *et al.* used electrodeposition to coat semiconductor materials with  $\text{TiO}_2$  under an electric current and subsequently heated them at 500 °C to enhance stability.<sup>21</sup> Similarly, thermal treatment is a common

method for integrating  $\text{TiO}_2$  onto carriers, with annealing temperatures around 400 °C promoting the transformation of  $\text{TiO}_2$  from anatase to rutile, a more stable form.<sup>22</sup> However, these techniques, though efficient, are impractical for aquaculture applications due to the significant costs and sophisticated equipment required.

#### Hydrogen peroxide formation by the $\text{TiO}_2$ –Ag/EC photocatalytic activity

$\text{TiO}_2$ –Ag nanoparticles exhibit enhanced reactive oxygen species (ROS) formation activity under visible light compared to  $\text{TiO}_2$  alone, primarily due to the localized surface plasmon resonance effect of the silver nanoparticles.<sup>23</sup> One of the major ROS compounds generated by  $\text{TiO}_2$ –Ag is hydrogen peroxide ( $\text{H}_2\text{O}_2$ ). During sunlight irradiation, electrons from the conduction band can reduce  $\text{O}_2$  to produce  $\text{H}_2\text{O}_2$ . However, to date, the resultant product concentrations have been limited in study.

In this research,  $\text{TiO}_2$ –Ag immobilized on electrospun composite (EC) material was tested for its  $\text{H}_2\text{O}_2$  production ability. The results, presented in Fig. S4,† showed that  $\text{H}_2\text{O}_2$  concentration increased with irradiation time, reaching a peak value of approximately 280 mM after 4 hours. The material demonstrated highly stable  $\text{H}_2\text{O}_2$  production, maintaining

Fig. 2 FESEM images of  $\text{TiO}_2$ –Ag nanoparticles integrated on EC materials at magnifications of 5 k (a), 10 k (b), and 25 k (c).

a concentration of  $266.22 \pm 13.42$  mM even after being continuously tested for 10 cycles. These results provide evidence of the photocatalytic activity of the  $\text{TiO}_2\text{-Ag/EC}$  material.

### Antibacterial activity of $\text{TiO}_2\text{-Ag/EC}$

The prolonged overuse of antibiotics for disease prevention and treatment presents significant risks to both environmental and human health. A comprehensive review of studies published from 2002 to 2023 by Suyamud *et al.* identified three pathogenic bacterial genera, including *Escherichia coli*, *Aeromonas*, and *Vibrio* as the common carriers of antibiotic resistance genes within aquaculture systems.<sup>3</sup> In recent years, photocatalytic materials have gained significant attention for their promising ability to eliminate pathogenic bacteria. Typically,  $\text{TiO}_2$  materials require UV light to excite electrons from the valence band to the conduction band, generating highly reactive oxygen species (ROS) radicals. However, in this study, Ag-modified  $\text{TiO}_2$  nanoparticles were employed to enhance the visible light absorption ability of the material. After two hours of sunlight exposure, the  $\text{TiO}_2\text{-Ag/EC}$  material successfully inactivated *V. parahaemolyticus*, *V. harveyi*, and *E. coli* pathogens, reducing their concentrations from approximately  $10^6$  CFU mL<sup>-1</sup> to 7, 68, and 12 CFU mL<sup>-1</sup>, respectively. These reductions correspond to antibacterial efficiencies of 6.0, 5.1, and 5.8 log reductions ( $N_0/N_t$ ), as shown in Fig. 3. A study by Zhang *et al.* also examined the use of  $\text{TiO}_2\text{-Ag}$  integrated into a ceramic carrier to inhibit *E. coli* pathogens. However, after a 2 hours irritation, the material achieved only a 2–3 log reduction in bacterial count, which is significantly lower than the effectiveness of the  $\text{TiO}_2\text{-Ag/EC}$  material (Table 2).

To enhance the reuse of  $\text{TiO}_2\text{-Ag/EC}$ , the materials were gently rinsed with distilled water and air-dried in the dark at room temperature before undergoing further testing. The results showed that after four cycles of reuse, the  $\text{TiO}_2\text{-Ag/EC}$  material retained substantial antibacterial activity, achieving an efficiency of over a 4 log reduction ( $N_0/N_t$ ) against *V. parahaemolyticus* and *V. harveyi* (Fig. 3). Although the antibacterial efficiency gradually decreased from 5.1–6.0 log reductions to 2.5–3.2 log reductions ( $N_0/N_t$ ) at the 7th reuse, the material remained highly effective at eliminating pathogenic bacteria. It reduced bacterial concentrations from  $10^6$  CFU mL<sup>-1</sup> to approximately  $10^3$  CFU mL<sup>-1</sup> within just 2 hours of treatment. The antibacterial performance of  $\text{TiO}_2\text{-Ag/EC}$  is comparable to other materials, such as  $\text{TiO}_2\text{/Ag/Ni}$  films,<sup>23</sup> Mn- and Co-doped  $\text{TiO}_2$ ,<sup>28</sup> and  $\text{TiO}_2$  nanoparticles encapsulated in cellulose acetate films,<sup>26</sup> as previously reported (Table 2).

Additionally, Joost *et al.* have suggested that during photocatalysis, reactive oxygen species (ROS) disrupt bacterial cell integrity, leading to the leakage of intracellular components. While titanium dioxide ( $\text{TiO}_2$ ) can kill bacteria within 20 minutes, electron microscopy reveals that cell debris may persist on the surface even after 60 minutes of treatment.<sup>29</sup> These residual debris can hinder light absorption and block the active sites of the photocatalyst, thereby diminishing its efficacy upon reuse.<sup>29,30</sup> Therefore, after bacterial inactivation by  $\text{TiO}_2$ , prolonging the reaction time is essential to ensure complete degradation of the cell components. Besides, methods such as heating, ultrasonic treatment, or the use of basic solutions can effectively eliminate accumulated impurities, thus regenerating the surface of the photocatalyst for future applications.<sup>31</sup> Cao *et al.* reported that heating  $\text{TiO}_2$  to 420 °C was required to




Fig. 3 Pathogen inhibition ability of  $\text{TiO}_2\text{-Ag/EC}$  against *V. harveyi* (a), *V. parahaemolyticus* (b), *E. coli* (c), and  $\text{TiO}_2\text{-Ag/EC}$  antibacterial efficacy (d).

Table 2 Comparison of antibacterial efficacy of  $\text{TiO}_2-\text{Ag}/\text{EC}$  with the synthesized photocatalyst agents in other studies

Photocatalyst agent	Light source	Initial pathogen density (CFU mL <sup>-1</sup> )	Irritation time	Pathogen strain	Antibacterial activity log(N <sub>0</sub> /N <sub>t</sub> )	Reference
TiO <sub>2</sub> -Ag/EC	Natural sunlight	7.7 × 10 <sup>6</sup> 8.9 × 10 <sup>6</sup> 8.0 × 10 <sup>6</sup> 7.8 × 10 <sup>6</sup> 7.2 × 10 <sup>6</sup> 8.2 × 10 <sup>6</sup> 1 × 10 <sup>6</sup>	1st 7th 1st 7th 1st 7th 120 min	<i>V. harveyi</i> <i>V. parahaemolyticus</i> <i>E. coli</i> <i>E. coli</i> <i>S. aureus</i> <i>Salmonella</i> <i>Shigella</i>	6.0 log 3.2 log 5.1 log 2.9 log 5.8 log 2.5 log 2-3 log	The presence study
Ag/TiO <sub>2</sub> -functionalized ceramic tiles	UV-A lamp (1000 W; $\lambda \geq 420$ nm)	10 <sup>5</sup>	18 h	<i>E. coli</i> <i>S. aureus</i>	2-3 log	Zhang <i>et al.</i> <sup>22</sup>
Face masks coated with 2% TiO <sub>2</sub>	Natural sunlight	10 <sup>7</sup>	180 min	<i>E. coli</i>	2.67 log	Ahmed <i>et al.</i> <sup>24</sup>
Plastic cutting board coated with TiO <sub>2</sub>	UV-A lamp ( $\lambda_{\text{max}} \sim 356$ nm)	1 × 10 <sup>7</sup>	360 min	<i>E. coli</i>	5.2 log	Yemmireddy <i>et al.</i> <sup>25</sup>
TiO <sub>2</sub> -embedded cellulose acetate film	UV-A lamp ( $\lambda_{\text{max}} \sim 356$ nm)	7.2 × 10 <sup>4</sup> 1 × 10 <sup>7</sup> 1.5 × 10 <sup>8</sup>	10 min 30 min 60 min	<i>P. fluorescens</i> <i>E. coli</i> <i>K. pneumoniae</i>	2.48 log 5.17 log 6 log	Xie <i>et al.</i> <sup>26</sup>
TiO <sub>2</sub> /Ag/Ni film 2 wt% Ni/TiO <sub>2</sub> mesh Mn- and Co-doped TiO <sub>2</sub>	UV-A lamp					Skorb <i>et al.</i> <sup>23</sup>
	Xenon (with 5% of UV-A and 0.1% of UV-B light)					Jeong <i>et al.</i> <sup>27</sup>
	Natural sunlight					Venieri <i>et al.</i> <sup>28</sup>
						3 log

remove all organic compounds adsorbed during the toluene degradation process.<sup>32</sup> In contrast, the present study demonstrated that simple water rinsing was sufficient to preserve the antibacterial activity of TiO<sub>2</sub>-Ag/EC after seven uses, emphasizing the ease of use of the material for preventing pathogen spread in aquaculture systems.

### Antibiotics photodegradation activity of TiO<sub>2</sub>-Ag/EC

The excessive accumulation of antibiotics in the environment has led to the emergence of antibiotic-resistant genes and bacteria. Thus, this study assessed the TiO<sub>2</sub>-Ag/EC material not only for its capacity to inhibit pathogenic bacteria but also for its effectiveness in degrading several widely used antibiotics in aquaculture, including tetracycline (TET), oxytetracycline (OTC), and rifampicin (RIF). During the treatment process, the TiO<sub>2</sub>-Ag/EC material was introduced to an antibiotic solution and allowed to remain static in the dark for 30 minutes to achieve adsorption equilibrium, followed by exposure to natural sunlight for photocatalytic degradation. The environmental pH and initial antibiotic concentrations were identified as critical factors influencing degradation efficiency. Thus, the degradation process was evaluated at four pH levels (3, 5, 7, and 9) and three antibiotic concentrations (10, 20, and 30 ppm).

TiO<sub>2</sub>-Ag typically exhibits an isoelectric point (pH<sub>pzc</sub>) of 6.6. Hence, at pH levels below this threshold, the material possesses a positive surface charge, whereas at pH values above 6.6, it acquires a negative charge.<sup>33</sup> Tetracycline (TET) and

oxytetracycline (OTC) are classified as amphoteric substances, possessing the capability to both donate and accept protons. Moreover, the two antibiotics display similar pK<sub>a</sub> values: pK<sub>a1</sub> ranges from 3.27 to 3.30, pK<sub>a2</sub> from 7.32 to 7.68, and pK<sub>a3</sub> from 9.11 to 9.69.<sup>34</sup> At pH levels either below 3 or above 9, TET, OTC, and TiO<sub>2</sub>-Ag all exhibit the same charge, which leads to electrostatic repulsion and consequently limits the degradation processes. According to Sun *et al.* reactive oxygen species (ROS) have short lifespans and are easily decomposed as they move away from the photocatalyst surface.<sup>35</sup> Therefore, it is crucial to maintain close binding of pollutants to the TiO<sub>2</sub>-Ag/EC surface to accelerate the photocatalytic reaction rate.

As the pH increases from 3 to 7, the positive charge on TiO<sub>2</sub>-Ag decreases, while TET and OTC become neutral, reducing electrostatic repulsion and significantly enhancing degradation efficiency. For example, at pH 3, degradation efficiency for TET and OTC was 86.9–89.6%, which increased to 92.3–95.1% at pH 7, with an initial antibiotic concentration of 10 ppm. At pH levels of 7–9, the antibiotic compounds and TiO<sub>2</sub>-Ag carry negative charges, however, the charge density of both components may still be low, allowing degradation efficiency to remain high, reaching 94.6% for TET and 97.8% for OTC (Fig. 4 and 5).

In the photocatalytic degradation process of TET and OTC, it is suggested that the reactive oxygen species (ROS) produced by TiO<sub>2</sub>-Ag initiate oxidative reactions such as hydroxylation, quinonization, decarbonylation, demethylation, and dehydrogenation. These reactions lead to the cleavage of carbon–carbon (C–




Fig. 4 Photodegradation of tetracycline (TET) by TiO<sub>2</sub>-Ag/EC material at various environmental pH and initial antibiotics concentrations.






Fig. 5 Photodegradation of oxytetracycline (OTC) by  $\text{TiO}_2$ –Ag/EC material at various environmental pH and initial antibiotics concentrations.

C) and carbon–nitrogen (C–N) bonds, disruption of the fused, linearly connected ring structures of the antibiotics, and ultimately resulting in mineralization of antibiotics into harmless end products like carbon dioxide ( $\text{CO}_2$ ), ammonium ( $\text{NH}_4^+$ ), and water ( $\text{H}_2\text{O}$ ).<sup>36</sup>

In case of the rifampicin (RIF), the ROS initially cleave the carbon atom bonded to the amino group, triggering demethylation. This process breaks the tetrahydrofuran ring, resulting in mineralization into  $\text{CO}_2$  and  $\text{H}_2\text{O}$ .<sup>37</sup> The RIF has the two  $pK_a$  values of 1.7 and 7.9.<sup>38</sup> As the pH shifts from 3 to 5, RIF becomes neutral, while the positive charge on  $\text{TiO}_2$ –Ag decreases, enhancing the binding of RIF to the photocatalyst and resulting in a degradation efficiency of 95.7%. However, RIF degradation is inhibited at higher pH values. At pH 7, 76.7% of the initial RIF concentration (10 ppm) was degraded after 4 hours, while this decreased to 69.9% at pH 9 (Fig. 6).

Simultaneously with the photocatalytic process, antibiotics can directly absorb photons, which alters their chemical structures and contributes to their degradation.<sup>39</sup> Compounds with alternating saturated and unsaturated bonds, such as TET, OTC, and RIF, are more likely to undergo direct photon absorption.<sup>40</sup> The results showed that the photolysis process could degrade 53.7% to 63.6% of TET and OTC at an initial concentration of 10 ppm (Fig. 4 and 5). However, as the antibiotic concentration increased to 20 or 30 ppm, the photolysis efficiency dropped below 50%. Rifampicin is more resistant to degradation in the absence of  $\text{TiO}_2$ –Ag/EC. At a concentration of 10 ppm (pH 7), only 15.7% of the initial RIF was removed after 4

hours of photolysis, while the addition of  $\text{TiO}_2$ –Ag/EC increased the degradation efficiency to 76.7% (Fig. 6). The obtained results consistent with findings from Dai *et al.*, which reported lower photolysis efficiency for TET degradation compared to photocatalytic treatments.<sup>41</sup> Research by Zambrano *et al.* further emphasizes the effectiveness of  $\text{TiO}_2$  in antibiotic degradation, revealing that several antibiotics, including tetracycline, ciprofloxacin, sulfadiazine, and sulfamethoxazole, take 100 to 240 hours to degrade under UV-C exposure, while  $\text{TiO}_2$  enhanced the degradation efficiency to 99–100% in just 3.5 to 15.6 hours.<sup>42</sup> These findings proved the critical role of  $\text{TiO}_2$ –Ag/EC in improving the efficiency of antibiotic degradation, highlighting its potential for addressing residual antibiotics in the environment.

To evaluate the stability and reusability of the  $\text{TiO}_2$ –Ag/EC catalyst, we conducted repeated cycles of tetracycline (TET) degradation under identical conditions, initial concentration of 10 ppm at neutral pH (7.0), for up to 10 cycles. As shown in Fig. S5,† the catalyst maintained over 80% removal efficiency for the first six cycles. However, a noticeable decline was observed, with efficiency dropping to below 40% by the 10th cycle.

Interestingly, this decrease in activity does not appear to be associated with the relatively stable concentrations of  $\text{H}_2\text{O}_2$  produced by  $\text{TiO}_2$ –Ag/EC in deionized water, as illustrated in Fig. S4.† This suggests that the diminished photocatalytic efficiency may be more related to surface fouling, likely caused by the adsorption of intermediate degradation products rather than to catalyst leaching.






Fig. 6 Photodegradation of rifampicin (RIF) by  $\text{TiO}_2\text{-Ag/EC}$  material at various environmental pH and initial antibiotics concentrations.

Although we did not directly measure  $\text{TiO}_2\text{-Ag}$  leaching in this study, the immobilized nature of the  $\text{TiO}_2\text{-Ag}$  on the EC carrier and the consistent ROS generation imply minimal catalyst loss. For practical applications, it is recommended further enhancing catalyst stability by applying a chitosan coating to the  $\text{TiO}_2\text{-Ag/EC}$  material. Chitosan is poorly soluble at neutral pH, such as that found in aquaculture environments, and could help prevent the detachment of  $\text{TiO}_2\text{-Ag}$  without compromising photocatalytic activity.<sup>43</sup>

#### Kinetic study on the antibiotics photocatalysis degradation process

To further investigate the degradation of these antibiotics by  $\text{TiO}_2\text{-Ag/EC}$ , the kinetics of the process using the pseudo-first-order (PFO) kinetic model was also analyzed. The  $R^2$  values for all models ranged from 0.87 to 0.99, showing a good fit for

the experimental data. The degradation rate constants ( $k$ ) for TET, OTC, and RIF at a concentration of 20 ppm under different pH conditions are shown in Fig. S2<sup>†</sup> and Table 3. Specifically, the rate constants for TET and OTC increased from  $5.45 \times 10^{-3}$  and  $5.53 \times 10^{-3}$  at pH 3 to their highest values of  $10.83 \times 10^{-3}$  and  $8.31 \times 10^{-3}$  at pH 9, which correlates with the increased degradation efficiency that was observed under basic conditions. In contrast, RIF degradation was most efficient in mildly acidic conditions, pH 5, with the highest rate constant of  $9.23 \times 10^{-3}$ .

#### Impact of degraded antibiotic solutions on the growth of bacteria

The addition of probiotics, particularly *Lactobacillus* species, to aquaculture environments or feeds is commonly used to enhance digestion, growth performance, and overall productivity. However, the growth of *Lactobacillus* is sensitive to environmental factors, as it is a non-spore-forming bacterium.<sup>44</sup> Therefore, this study aimed to evaluate the effectiveness of photocatalytic and photolysis processes in reducing the toxicity of residual antibiotics on the growth of *Lactobacillus acidophilus*.

Tetracycline (TET) and oxytetracycline (OTC), both members of the tetracycline antibiotic group, have chemical structures with multiple binding sites for metal ions, such as the  $\beta$ -diketone system (C11, C12), enol group (C1, C3), and carboxamide group (C2).<sup>45</sup> These antibiotics form complexes with

Table 3 The rate constant ( $k$ ) and  $R^2$  value for antibiotic degradation using  $\text{TiO}_2\text{-Ag/EC}$  material under sunlight

	Oxytetracycline		Tetracycline		Rifampicin	
	$k$	$R^2$	$k$	$R^2$	$k$	$R^2$
pH 3	$5.45 \times 10^{-3}$	0.99	$5.53 \times 10^{-3}$	0.95	$4.92 \times 10^{-3}$	0.97
pH 5	$5.71 \times 10^{-3}$	0.98	$6.24 \times 10^{-3}$	0.98	$9.23 \times 10^{-3}$	0.87
pH 7	$6.40 \times 10^{-3}$	0.90	$7.30 \times 10^{-3}$	0.99	$4.58 \times 10^{-3}$	0.92
pH 9	$10.83 \times 10^{-3}$	0.99	$8.31 \times 10^{-3}$	0.98	$3.45 \times 10^{-3}$	0.95



<i>L. acidophilus</i>		<i>V. parahaemolyticus</i>						
		Antibiotic concentrations						
		0	5%	10%	15%	20%	25%	30%
<b>TET</b>		0.964	0.054	0.048	0.040	0.064	0.048	0.077
<b>TET<sub>EC</sub></b>		1.083	0.666	0.069	0.065	0.040	0.045	0.063
<b>TET<sub>TA</sub></b>		1.055	1.129	1.139	1.065	1.179	1.054	1.107
<b>OTC</b>		1.178	0.044	0.057	0.070	0.073	0.067	0.059
<b>OTC<sub>EC</sub></b>		1.143	0.718	0.305	0.069	0.065	0.040	0.056
<b>OTC<sub>TA</sub></b>		0.989	1.140	1.137	1.239	1.088	1.086	1.141
<b>RIF</b>		1.231	0.046	0.065	0.063	0.070	0.058	0.058
<b>RIF<sub>EC</sub></b>		1.145	0.079	0.067	0.073	0.068	0.056	0.066
<b>RIF<sub>TA</sub></b>		1.204	1.213	1.078	1.145	1.051	1.117	1.118

Fig. 7 Effects of original antibiotics (TET, OTC, and RIF), photolyzed antibiotics (TET<sub>EC</sub>, OTC<sub>EC</sub>, and RIF<sub>EC</sub>), and photocatalytically degraded antibiotics by TiO<sub>2</sub>–Ag/EC materials (TET<sub>TA</sub>, OTC<sub>TA</sub>, and RIF<sub>TA</sub>) on the growth of *L. acidophilus* (left) and *V. parahaemolyticus* (right).

magnesium ions ( $Mg^{2+}$ ), which inhibit protein synthesis in the 30S ribosomal subunit, contributing to their antibacterial effectiveness. In this study, the growth of *L. acidophilus* was completely inhibited at antibiotic concentrations of 5% (0.5 mg  $mL^{-1}$ ) for both TET and OTC. An increase to 10% concentration also resulted in the inactivation of *V. parahaemolyticus* bacteria. Nevertheless, after 4 hours of photocatalytic treatment using TiO<sub>2</sub>–Ag/EC material, over 92% of the TET and OTC content was

degraded. As a result, the treated antibiotic solutions, TET<sub>TA</sub> and OTC<sub>TA</sub>, lost their ability to inhibit the growth of *L. acidophilus* and *V. parahaemolyticus* at the tested concentrations. At the 30% supplementation level, the growth of bacterial strains in TET<sub>TA</sub> and OTC<sub>TA</sub> was comparable to those in the negative control, which contained no antibiotics (Fig. 7).

Yuan *et al.* proposed that reactive oxygen species (ROS) generated during photocatalysis can break the chemical bonds




Fig. 8 Dependence of the COD removal activity of TiO<sub>2</sub>–Ag/EC on initial COD concentrations: 25 mg  $L^{-1}$  (a), 50 mg  $L^{-1}$  (b), and 100 mg  $L^{-1}$  (c).



in oxytetracycline (OTC), converting it into harmless byproducts such as 1,4-benzenedicarboxylic acid, 4-oxopentanoic acid, and glycerin.<sup>46</sup> Nevertheless, the intermediate products formed during the photolysis of OTC may have altered functional groups but retained a tetra-phenyl structure, allowing them to penetrate bacterial membranes, including those of luminescent bacterial strains.<sup>47</sup> Furthermore, in the present study, the photolysis of antibiotics in the presence of EC without TiO<sub>2</sub>-Ag resulted in only partial degradation of TET and OTC, with efficiencies of 57.5% and 64.0%, respectively (Fig. 4 and 5). As a result, at TET<sub>EC</sub> and OTC<sub>EC</sub> concentrations of 15%, the growth of both bacterial strains was effectively inhibited. Similar results were observed with the antibiotic rifampicin (RIF), where *L. acidophilus* was completely inhibited at a concentration of 5% RIF<sub>EC</sub> but grew normally in the presence of 30% RIF<sub>TA</sub> (Fig. 7).

### COD removal

In addition to the concerns regarding the spread of pathogens and antibiotic residues, the accumulation and subsequent decomposition of excess feed contribute to an increasing concentration of organic matter in the waterbody, which can

lead to the deterioration of water quality in the aquaculture environment. The findings presented in Fig. 8 demonstrate that the TiO<sub>2</sub>-Ag/EC material (10% w/v) can effectively reduce the initial chemical oxygen demand (COD) concentration of 25 mg L<sup>-1</sup> by 92.9 ± 0.7% after 32 hours of sunlight exposure. Notably, the removal efficiency remained high, exceeding 86% after 40 hours of treatment when COD concentrations increased to 50 mg L<sup>-1</sup> and 100 mg L<sup>-1</sup>. It is worth mentioning that while photolysis of organic compounds occurred under sunlight, the efficiency of this process was relatively lower, at approximately 25.5% across all three tested COD concentrations.

To evaluate the impact of TiO<sub>2</sub>-Ag/EC concentration on COD removal efficiency, varying concentrations of TiO<sub>2</sub>-Ag/EC, ranging from 0.5% to 10% w/v, were introduced to a 100 mg L<sup>-1</sup> COD solution. As illustrated in Fig. 9, an increase in TiO<sub>2</sub>-Ag/EC concentration from 0.5% to 2.5% w/v resulted in a reduction of the remaining COD from 33.6 ± 5.5 mg L<sup>-1</sup> to 18.4 ± 3.1 mg L<sup>-1</sup>, achieving a maximum COD removal efficiency of 82.7 ± 2.0% after 40 hours of illumination. Munien *et al.* revealed that UV illumination with a TiO<sub>2</sub> concentration of 600 ppm can achieve a COD removal rate of 25.88% in domestic wastewater.<sup>48</sup> Additionally, Orojolou *et al.* found a significantly higher COD removal efficiency of 94.5% in industrial




Fig. 9 Effects of various concentrations of TiO<sub>2</sub>-Ag/EC additions: 0.5% (a), 1% (b), 2.5% (c), 5% (d), and 7.5% (e) w/v on COD removal efficiency.



wastewater at an increased  $\text{TiO}_2$  concentration of 2000 ppm.<sup>49</sup> In contrast, the  $\text{TiO}_2\text{-Ag/EC}$  composite was synthesized with an integrated Ti content of approximately 2500 ppm, hence, an addition ratio of 2.5% w/v  $\text{TiO}_2\text{-Ag/EC}$  corresponds to a photocatalyst concentration of about 62.5 ppm. Nevertheless, the floatable properties of  $\text{TiO}_2\text{-Ag/EC}$  enhance light absorption and oxygen interaction, thereby improving photocatalytic activity. As a result, this material can achieve a COD removal efficiency exceeding 80% when applied to an initial COD concentration of  $100 \text{ mg L}^{-1}$  over a treatment period of 40 hours.

However, as the  $\text{TiO}_2\text{-Ag/EC}$  concentration increased to 5% and 7.5% w/v, the efficiency subsequently decreased to  $65.2 \pm 6.7\%$ . A similar phenomenon was reported by Zhang *et al.*, where the rise in the concentration of the photocatalyst KBNNO ( $[\text{KNbO}_3]_{0.9} \text{-} [\text{BaNi}_{0.5}\text{Nb}_{0.5}\text{O}_3\text{-}\delta]_{0.1}$ ) from 1800 to 2000  $\text{mg L}^{-1}$  did not significantly enhance the removal efficiency of methyl blue dye.<sup>50</sup> This phenomenon can be explained by the fact that at lower photocatalyst densities, the number of photons absorbed and converted into reactive oxygen species (ROS) radicals is limited, resulting in lower degradation efficiency. Conversely, when the photocatalyst concentration exceeds a certain threshold, the nanoparticles may shadow one another, which reduces light absorption and overall photocatalytic activity. Therefore, it is essential to identify the minimum concentration of material needed to achieve effective treatment efficiency for each treatment model to reduce investment costs.

In addition to the COD decomposition process, the formation of inorganic compounds such as  $\text{NH}_4^+$  and  $\text{NO}_2^-$  was observed, with their concentrations increasing over time (Fig. 9). The reactor containing 2.5% w/v  $\text{TiO}_2\text{-Ag/EC}$  demonstrated the most effective performance in degrading organic compounds, resulting in high concentrations of  $\text{NH}_4^+$  and  $\text{NO}_2^-$ , measured at  $18.7 \pm 1.2 \text{ mgN L}^{-1}$  and  $7.9 \pm 0.2 \text{ mgN L}^{-1}$ , respectively. Therefore, a combination of multiple strategies is essential for effectively addressing the nitrogen pollution generated during the degradation of organic compounds in aquaculture systems.

## Conclusions

The present study demonstrates the effectiveness of the floatable photocatalyst material,  $\text{TiO}_2\text{-Ag/EC}$ , in addressing environmental issues commonly encountered in aquaculture systems. The integration of the photocatalyst within the EC materials is influenced by both the characteristics and concentration of  $\text{TiO}_2\text{-Ag}$ , as well as the structural features of the material itself. The  $\text{TiO}_2\text{-Ag/EC}$  (10% w/v) material can eliminate pathogenic bacteria such as *Vibrio harveyi*, *Vibrio parahaemolyticus*, and *Escherichia coli* within just 2 hours of sunlight exposure. Moreover, the antibacterial activity of the  $\text{TiO}_2\text{-Ag/EC}$  material remains effective even after seven uses. In addition to its antibacterial properties,  $\text{TiO}_2\text{-Ag/EC}$  has demonstrated the ability to degrade three types of antibiotics: tetracycline, oxytetracycline, and rifampicin. The degradation efficiency varies based on pH conditions and the initial concentrations of the antibiotics. Notably, the floatable

properties of  $\text{TiO}_2\text{-Ag/EC}$  enhance light absorption and oxygen interaction, thereby improving photocatalytic activity. With an additional ratio of 2.5% w/v,  $\text{TiO}_2\text{-Ag/EC}$  achieves a COD removal efficiency exceeding 80% when applied to an initial COD concentration of  $100 \text{ mg L}^{-1}$  over a treatment period of 40 hours. These findings suggest that the  $\text{TiO}_2\text{-Ag/EC}$  material has significant practical potential for improving water quality in the aquaculture system.

## Data availability

The data supporting this article have been included as part of the ESI.<sup>†</sup>

## Author contributions

Phuong Ha Hoang, Minh Thi Nguyen: investigation; formal analysis; writing – original draft. Ke Son Phan, Huong Giang Bui, Anh Tuyet Thi Le: methodology; writing – review & editing. Thi Thu Huong Le, Nhat Huy Chu, Thu Trang Thi Mai, Dieu Thuy Thi Ung: conceptualization; methodology, writing – review & editing. Phuong Ha Hoang, Phuong Thu Ha: conceptualization; writing – review & editing; funding acquisition; supervision.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work financially supported by The National Office of Intellectual Property of Vietnam (Grant No. SHTT.TW 07-2022) to Phuong Ha Hoang. Minh Thi Nguyen was funded by Vingroup JSC and supported by the Master, PhD Scholarship Programme of Vingroup Innovation Foundation (VINIF), Institute of Big Data, code VINIF.2023.TS067.

## Notes and references

- 1 J. Wang, D. Luo and J. Liu, *J. World Aquacult. Soc.*, 2023, **54**, 1337–1353.
- 2 E. S. Okeke, K. I. Chukwudzie, R. Nyaruaba, R. E. Ita, A. Oladipo, O. Ejemerodoghene, E. O. Atakpa, C. V. Agu and C. O. Okoye, *Environ. Sci. Pollut. Res. Int.*, 2022, **29**, 69241.
- 3 B. Suyamud, Y. Chen, D. T. T. Quyen, Z. Dong, C. Zhao and J. Hu, *Sci. Total Environ.*, 2024, **907**, 167942.
- 4 S. Zheng, Y. Wang, C. Chen, X. Zhou, Y. Liu, J. Yang, Q. Geng, G. Chen, Y. Ding and F. Yang, *Int. J. Environ. Res. Publ. Health*, 2022, **19**, 10919.
- 5 M. F. Warsito, *IOP Conf. Ser. Earth Environ. Sci.*, 2022, **1017**, 012026.
- 6 N. Nasrollahi, V. Vatanpour and A. Khataee, *Sci. Total Environ.*, 2022, **838**, 156010.



7 P. P. Singh, G. Pandey, Y. Murti, J. Gairola, S. Mahajan, H. Kandhari, S. Tivari and V. Srivastava, *RSC Adv.*, 2024, **14**, 20492–20515.

8 M. Fasnacht and N. Polacek, *Front. Mol. Biosci.*, 2021, **8**, 671037.

9 S. Thakur, A. Ojha, S. K. Kansal, N. K. Gupta, H. C. Swart, J. Cho, A. Kuznetsov, S. Sun and J. Prakash, *Adv. Powder Mater.*, 2024, **3**, 100233.

10 X. Liu, J. Pan, H. Huang, X. Zhang, N. Sun, C. Gu, Y. Zhuang and L. Wang, *Chem. Eng. J.*, 2023, **476**, 146868.

11 P. H. Hoang, M. T. Nguyen, K. S. Phan, H. G. Bui, T. T. H. Le, N. H. Chu, N. A. Ho, Q. H. Pham, X. K. Tran and P. T. Ha, *RSC Adv.*, 2024, **14**, 1984–1994.

12 C. J. Aul, M. W. Crofton, J. D. Mertens and E. L. Petersen, *Proc. Combust. Inst.*, 2011, **33**, 709–716.

13 N. Soni, N. Soni, R. Maheshwari, S. Thakkar, D. Sharma, R. K. Tekade, N. Sreeharsha and M. Tekade, *The Future of Pharmaceutical Product Development and Research*, 2020, pp. 413–446.

14 Y. Luo, Z. Liu, M. Ye, Y. Zhou, R. Su, S. Huang, Y. Chen and X. Dai, *Water*, 2024, **16**, 2586.

15 T. Sano, T. Ishii, K. Hotta and Y. Mano, *ACS Omega*, 2023, **8**, 36261–36268.

16 N. Zainol, K. A. Samad, C. A. Ilyana Che Jazlan and N. A. Razahazizi, *Heliyon*, 2022, **8**, e09217.

17 T. M. LaPara, J. E. Alleman, P. G. Pope, T. M. LaPara, J. E. Alleman and P. G. Pope, *Waste Manag.*, 2000, **20**, 295–298.

18 T. Kaur, A. Sraw, R. K. Wanchoo and A. P. Toor, *Sol. Energy*, 2018, **162**, 45–56.

19 A. H. Navidpour, B. Xu, M. B. Ahmed and J. L. Zhou, *Mater. Sci. Semicond. Process.*, 2024, **179**, 108518.

20 S. Karuppuchamy, K. Nonomura, T. Yoshida, T. Sugiura and H. Minoura, *Solid State Ionics*, 2002, **151**, 19–27.

21 P. S. M. Dunlop, T. A. McMurray, J. W. J. Hamilton and J. A. Byrne, *J. Photochem. Photobiol. A*, 2008, **196**, 113–119.

22 Y. Zhang, X. Zhao, S. Fu, X. Lv, Q. He, Y. Li, F. Ji and X. Xu, *Ceram. Int.*, 2022, **48**, 4897–4903.

23 E. V. Skorb, L. I. Antonouskaya, N. A. Belyasova, D. G. Shchukin, H. Möhwald and D. V. Sviridov, *Appl. Catal., B*, 2008, **84**, 94–99.

24 O. B. Ahmed and T. Alamro, *Sci. Rep.*, 2022, **12**, 18739.

25 V. K. Yemmireddy and Y. C. Hung, *Food Control*, 2017, **77**, 88–95.

26 J. Xie and Y. C. Hung, *Food Control*, 2019, **106**, 106690.

27 E. Jeong, H. Y. Park, J. Lee, H. E. Kim, C. Lee, E. J. Kim and S. W. Hong, *Environ. Res.*, 2021, **194**, 110657.

28 D. Venieri, I. Gounaki, M. Bikouvaraki, V. Binas, A. Zachopoulos, G. Kiriakidis and D. Mantzavinos, *J. Environ. Manage.*, 2017, **195**, 140–147.

29 U. Joost, K. Juganson, M. Visnapuu, M. Mortimer, A. Kahru, E. Nõmmiste, U. Joost, V. Kisand and A. Ivask, *J. Photochem. Photobiol., B*, 2015, **142**, 178–185.

30 M. Kook, H. Kaur, D. Danilian, M. Rosenberg, V. Kisand and A. Ivask, *J. Coat. Technol. Res.*, 2024, **21**, 1005–1016.

31 X. J. Yan, Y. Tang, C. Ma, Y. Liu and J. Xu, *Desalin. Water Treat.*, 2018, **124**, 160–176.

32 L. Cao, Z. Gao, S. L. Suib, T. N. Obee, S. O. Hay and J. D. Freihaut, *J. Catal.*, 2000, **196**, 253–261.

33 E. Jeong, H. Y. Park, J. Lee, H. E. Kim, C. Lee, E. J. Kim and S. W. Hong, *Environ. Res.*, 2021, **194**, 110657.

34 Y. Chen, H. Li, Z. Wang, T. Tao and C. Hu, *J. Environ. Sci.*, 2011, **23**, 1634–1639.

35 X. Sun, K. Xu, A. Chatzitakis and T. Norby, *J. Environ. Chem. Eng.*, 2021, **9**, 104809.

36 Y. Zhang, Q. Chen, H. Qin, J. Huang and Y. Yu, *Int. J. Environ. Res. Publ. Health*, 2022, **19**, 15550.

37 M. Raaja Rajeshwari, M. K. Okla, S. Kokilavani, M. A. Abdel-Maksoud, I. A. Saleh, H. A. Abu-Harirah, T. N. AlRamadneh and S. S. Khan, *Chemosphere*, 2023, **339**, 139529.

38 M. Motie, L. Pleno de Gouveia, T. Sopík, R. Vícha, D. Skoda, J. Císař, R. Khalili, E. Domincová Bergerová, L. Münster, H. Fei, V. Sedlářík and P. Sáha, *Molecules*, 2021, **26**, 2067.

39 T. Liu, L. Wang, C. Sun, X. Liu, R. Miao and Y. Lv, *Chem. Eng. J.*, 2019, **358**, 1296–1304.

40 A. Gürses, M. Açıkyıldız, K. Güneş and M. S. Gürses, *Dyes and pigments: their structure and properties*, in *Dyes and Pigments*, Springer, Cham, 2016, pp. 13–29.

41 Y. Dai, M. Liu, J. Li, S. Yang, Y. Sun, Q. Sun, W. Wang, L. Lu, K. Zhang, J. Xu, W. Zheng, Z. Hu, Y. Yang, Y. Gao and Z. Liu, *Sep. Sci. Technol.*, 2020, **55**, 1005–1021.

42 J. Zambrano, P. A. García-Encina, J. J. Jiménez, R. López-Serna and R. Irusta-Mata, *J. Water Proc. Eng.*, 2022, **48**, 102841.

43 I. Aranaz, A. R. Alcántara, M. C. Civera, C. Arias, B. Elorza, A. H. Caballero, N. Acosta, H. Velasco, D. Mecerreyres, R. Antonio, B. Gimeno, A. María Díez-Pascual, V. C. Moreno and A. Serra, *Polymers*, 2021, **13**, 3256.

44 Y. C. Wang, H. Y. Lin and P. S. Chang, *Aquac Rep.*, 2023, **30**, 101615.

45 J. P. White and C. R. Cantor, *J. Mol. Biol.*, 1971, **58**, 397–400.

46 F. Yuan, C. Hu, X. Hu, D. Wei, Y. Chen and J. Qu, *J. Hazard. Mater.*, 2011, **185**, 1256–1263.

47 G. H. Lu, Y. H. Zhao, S. G. Yang and X. J. Cheng, *Bull. Environ. Contam. Toxicol.*, 2002, **69**, 111–116.

48 C. Munien, E. Kweinor Tetteh, T. Govender, S. Jairajh, L. L. Mguni and S. Rathilal, *Appl. Sci.*, 2023, **13**, 4766.

49 S. Heydari Orojou, S. Rastegarzadeh and B. Zargar, *Sci. Rep.*, 2022, (12), 1–15.

50 D. Zhang, S. Lv and Z. Luo, *RSC Adv.*, 2020, **10**, 1275–1280.

