

Cite this: *RSC Adv.*, 2025, **15**, 41061

Emerging nanotechnology approaches for sustainable water treatment and heavy metals removal: a comprehensive review

Erfan Burhan Hussein, ^{*a} Farouk Abdullah Rasheed, ^a Ahmed Salih Mohammed ^b and Kawan F. Kayani ^c

Water pollution is a significant worldwide concern, caused mainly by industrialization, urban development, and inadequate waste management, leading to the release of harmful pollutants, especially heavy metals, into water bodies. These pollutants provide significant risks to ecological and public health owing to their toxicity, persistence, and bioaccumulative properties. Traditional water and wastewater treatment methods often inadequately remove these persistent pollutants due to challenges in selectivity, efficiency, and flexibility. Nanotechnology has grown as an effective and innovative method for eliminating pollutants, providing improved materials with distinctive physicochemical characteristics, including large surface area, increased reactivity, and functional tunability. The study systematically examines the utilization of nanotechnology in water and wastewater treatment, focusing on the adsorption-based elimination of heavy metal ions. The article begins with a summary of conventional treatment techniques and their limitations, then addresses adsorption principles, including physisorption and chemisorption processes. The review classifies and critically evaluates various types of nanoadsorbents, such as carbon-based nanocomposites, zeolites, metal and metal oxide nanoparticles, silica nanomaterials, polymer-based materials, metal-organic frameworks, and layered double hydroxides, emphasizing their efficacy under different operational conditions. Furthermore, essential nanomaterial characterization methods are introduced to assess structure-function relationships. This study provides an essential overview for academics and practitioners seeking to develop efficient, sustainable, and cost-effective nanomaterials for advanced water treatment systems by including current advancements and comparative data.

Received 12th September 2025
Accepted 10th October 2025

DOI: 10.1039/d5ra06914a
rsc.li/rsc-advances

1. Introduction

Water is the fundamental component necessary for every living thing on the planet and a valuable resource for the development of human society.¹ Ensuring the consistent and dependable availability of uncontaminated and accessible water is widely recognized as an essential purpose of humanistic efforts and continues to be a significant worldwide obstacle. Even though water covers over 71 percent of the Earth's surface, the amount of clean water accessible for utilization remains extremely limited, and the need for water is rising due to the expansion of industrial activity and growing populations.² Fig. 1 depicts the

global distribution of water. The primary concern associated with rising water consumption is providing potable water to the necessary fields. In addition to its domestic applications for consumption and use in cooking, pure water is also a crucial resource for various emerging businesses, including food, pharmaceuticals, electronics, and medical areas. However, the accessible freshwater reservoir faces complexity due to diminishing quantities caused by global warming, population growth, and stricter health regulations. Research by the World Health Organization (WHO) reveals that 2.1 billion people lack access to potable water sources, and over 700 million people do not have access to the essential daily demand for potable water. Moreover, approximately 4 billion individuals globally experience water shortages for at least one month yearly.²⁻⁵ Overall, eighty percent of health issues globally can be traced back to a contaminated water supply, directly or indirectly. Additionally, nineteen percent of all human deaths can be attributed to diseases associated with pathogenic microbes present in water.⁶ Furthermore, an alarming number of two million individuals die of diarrheal diseases annually as a direct consequence of the absence of any enhanced sanitary system, and each day,

^aDepartment of Water Resources Engineering, College of Engineering, University of Sulaimani, Sulaymaniyah, 46001, Kurdistan Region, Iraq. E-mail: erfan.hussein@univsul.edu.iq; farouk.rasheed@univsul.edu.iq

^bDepartment of Civil Engineering, College of Engineering, American University of Iraq, Sulaimani (AUIS), Sulaymaniyah 46001, Kurdistan Region, Iraq. E-mail: ahmed.salih@auis.edu.krd

^cDepartment of Chemistry, College of Science, University of Sulaimani, Sulaymaniyah 46001, Kurdistan Region, Iraq. E-mail: kawan.nasraldin@univsul.edu.iq






Fig. 1 Global distribution of water on the Earth's surface.^{19,20}

approximately 5000–6000 children lose their lives as a result of diarrhea, a water-based issue. Therefore, an uninterrupted provision of purified water is crucial for our everyday consumption. According to WHO guidelines, drinking water should have undetectable levels of fecal and total coliforms in any 100 mL water sample. The paper, plastic, and metal sectors also rely on providing uncontaminated water for their manufacturing processes. Therefore, individuals can reduce water consumption by gaining a deeper awareness of how water is used and recycled in the production of goods.^{4,7–9} Polluted water not only has adverse effects on the lives of people but also has harmful effects on biodiversity and ecosystems.¹⁰ It is crucial to implement new regulations for water usage in response to the growing strain on water resources, the unpredictable availability of clean water, and the impact of global climate change. The many demands placed on water systems necessitate the utilization or reutilization of alternate water sources, such as saltwater, stormwater, brine water, and recycled household water, particularly in regions with a history of water scarcity.^{11,12}

In addition to these global statistics, several practical cases further illustrate the severity of water pollution. For instance, the Flint water crisis in the United States highlighted the devastating health consequences of lead-contaminated drinking water on local communities.¹³ Chronic exposure to heavy metals such as arsenic, lead, and cadmium through contaminated water has been strongly associated with gastrointestinal disorders and increased cancer risks, particularly rectal and colorectal cancers.¹⁴ In Bangladesh, high levels of naturally occurring arsenic in groundwater continue to affect millions of people, with epidemiological data linking this exposure to gastrointestinal cancers and other severe health effects.^{14–17} Similarly, in China, long-term exposure to contaminated water containing nitrates, polycyclic aromatic hydrocarbons, and heavy metals has been associated with elevated incidences of digestive system cancers.^{14,18} These practical examples underscore the urgent need for effective and sustainable treatment strategies to mitigate the health and environmental impacts of water pollution.

As a result of the environmental concerns caused by water contamination, many scientists have focused their attention on developing innovative methods for treating wastewater,²¹ and

governments, non-governmental organizations, and environmentalists have established strict regulations and standards to promote environmental conservation and the principles of reuse, reduce, and recycle.²² Various methods have been created so far to reduce the release of wastewater and lessen the risks associated with contaminants. These methods include coagulation/flocculation, membrane filtration, adsorption, oxidation, chemical precipitation, and biological treatment.^{23,24} Wastewater treatment often incurs substantial expenses due to the necessity of efficiently eliminating the contaminants in the wastewater to render the water safe and appropriate for reuse. Nevertheless, the planning and development of these wastewater treatment methods primarily focus on investigating effluents and treatment standards, disregarding their potential effects on the entire treatment process and sustainability.²⁵ Current treatments do not eliminate contaminants; instead, they either concentrate them or transform them into other forms.²⁶

The progress in nanotechnology presents several possibilities for developing cost-effective and eco-friendly water supply methods. Nanomaterials are anticipated to possess diverse characteristics that provide cost-efficient and highly efficient methods for treating wastewater and water. These techniques would depend less on complex infrastructure for wastewater treatment and could be used with other water treatment processes such as adsorption, coagulation, membrane technology, and photocatalysis.^{11,27} Nanotechnology-based approaches for water and wastewater treatment have emerged as promising solutions to overcome key challenges in conventional treatment techniques. These advanced technologies provide innovative and efficient mechanisms for pollutant removal, enabling the cost-effective utilization of alternative water sources to enhance water availability. The increasing quantity of scientific articles in this field demonstrates the growing interest and recognition of nanotechnology's potential in addressing complex water pollution issues (as shown in Fig. 2). Alongside advances in synthesis, comprehensive characterization of nanomaterials is essential to validate their unique physiochemical properties and ensure their suitability for water and wastewater treatment applications. Different techniques provide complementary insights: microscopy-based methods (e.g., SEM, TEM, AFM) reveal particle size,






Fig. 2 Quantity of published research on nanomaterials in wastewater treatment (Scopus Database).³⁸




Fig. 3 Representative characterization techniques used for nanomaterials.

morphology, and crystal structure; spectroscopy methods (*e.g.*, FTIR, UV-Vis, XPS) identify surface functional groups and electronic state; diffraction and scattering methods (*e.g.*, XRD, SAXS) confirm crystallinity and phase composition; while surface and stability analyses (*e.g.*, BET, zeta potential, DLS) quantify porosity, surface area, dispersion behavior, and colloidal stability.^{28–31} Fig. 3 illustrates the main characterization techniques commonly employed in nanomaterial research and the properties they reveal. Including these techniques at the early stage of material evaluation is crucial, as particle size, morphology, surface chemistry, and stability directly govern adsorption performance, regeneration potential, and environmental safety.

This article provides a comprehensive review of recent advancements in nanotechnologies applications for water and wastewater treatment. It highlights the potential of nanomaterials to overcome the limitations of conventional treatment methods by offering enhanced efficiency, selectivity, and reusability. A detailed comparison between traditional techniques and nanotechnology-based approaches is presented to emphasize the superiority of nanoscale materials in pollutant removal. The review further examines the synthesis, structural properties, and performance of various nanoparticles and nanocomposites, particular focusing on their mechanisms of decontamination. Special attention is given to nanoadsorbents for the removal of heavy metals, with discussions on adsorption processes and the influence of key operational parameters such as solution pH, temperature, contact time, initial metal ion concentration, and adsorbent dosage. Overall, this study underscores the significance of nanotechnology as

a sustainable and efficient alternative for water purification. Moreover, recent evidence demonstrating the continued rise in industrial effluent discharge and associated heavy metal pollution highlights the urgent need to develop advanced and cost-effective treatment strategies.^{32–34} Numerous research groups have investigated diverse methods for treating heavy metal-contaminated wastewater using a wide range of materials.^{35–37} This review consolidates the most recent progress in employing nanomaterials for heavy metal removal, emphasizing their superior adsorption capacity, regeneration potential, and environmental compatibility compared to conventional adsorbents. The article elaborates on the fundamental principles of nanotechnology, interaction mechanisms between nanomaterials and heavy metal ions, and the types and performance of different nanomaterials utilized for remediation. Furthermore, it identifies knowledge gaps and future perspectives for optimizing nanomaterial design, improving recyclability, and ensuring environmental safety. To the best of our knowledge, this review provides one of the most comprehensive and up-to-date analyses of nanomaterial-based approaches for heavy metal removal, serving as a valuable reference for both researchers and practitioners in developing sustainable water treatment technologies.

2. Strategies applied for wastewater treatment and water decontamination

Water contamination harms the ecosystem and can also be a source of air pollution, severely impacting human health: water pollution damages both the economic development and

Table 1 Various types of water pollution, including their origins and impacts^{39,40,48}

Types	Origins	Impacts
Organic	Pest control substances include insecticides, herbicides, and detergents	Issues with aquatic life Diarrhea, kidney damage, colon inflammation, hemolytic uremic syndrome, illnesses such as typhoid fever and salmonellosis, and Legionnaires' disease
Inorganic	Trace substances, metallic compounds, inorganic salts, heavy metals, and acidic minerals	Aquatic plant and animal concerns as well as problems with public health For example, heavy metals enhance the body's vulnerability to infections, alter the production and use of neurotransmitters inside the body, and produce reactive oxygen species, which may lead to oxidative stress
Nutrients	Fertilizers and plant detritus	Eutrophication is influenced
Contaminated water and sewage	Residential wastewater	Impact on the process of eutrophication
Industrial	Pollution originating from municipal areas	Induced water and air contamination
Agricultural	Water-soluble compounds containing nitrate and phosphorus ions	The fast development of algae leads to the depletion of water oxygen levels, resulting in fish death
Macroscopic	Oceanic waste	The accumulation of plastic waste causes environmental contamination
Radioactive	Multiple isotopes	Certain types of cancer, congenital abnormalities, and hereditary conditions
Suspended solids and sediments	Earth cultivation, destruction, and excavation operations	The process of fish reproduction is adversely affected, hurting the aquatic ecosystem, including insects and fish
Pathogens	Microorganisms such as bacteria and viruses	Water-related illnesses



Table 2 Some regular water and wastewater treatment methods, their relative performances and limitations

Strategies	Performance and drawbacks	Ref.
Bioremediation	Biological treatment is a commonly used technique for removing organic pollutants from water, although it is ineffective in eradicating halogenated organics and some organic halides. Furthermore, it is inefficient in eliminating endocrine-disrupting drugs and primary care pharmacist practitioners. When used in conjunction with filtration, it may be very successful in eradicating harmful materials. Nevertheless, it relies on microorganisms and may be affected by water content, loading rate, medium type, temperature, and aeration level. Over time, the performance of the technology might be diminished due to fouling and filter clogging	45, 49 and 50
Coagulation/ precipitation	Chemical precipitation is a simple and effective process for eliminating harmful materials from the environment, but it is expensive due to the large quantities of chemicals required. Though not employed for organic pollutants, coagulation may remove colors from wastewater. After coagulation and flocculation, sedimentation or filtration may remove toxic and inorganic components from sewage. The high cost of chemical reagents makes coagulation and precipitation costly. The system must be carefully regulated and inspected to ensure the correct amounts of chemicals are introduced to clean the system without excess chemicals. Multiple metal species may complicate treatment owing to amphoteric compounds; optimizing one species' elimination might inhibit another. The effluent typically needs pH modification after treatment, increasing treatment costs. Coagulation and precipitation create a lot of waste, which is dangerous and expensive to treat due to the poisonous elements	40, 45, 49, 50 and 51
Chemical oxidation	Chemical oxidation is a technique used to address organic contaminants; however, it is not as efficient when dealing with hazardous components, inorganic pollutants, dissolved minerals, and salts. The inefficiency is often caused by the low concentrations of contaminants in the effluent. Chlorine is a toxic substance that is both corrosive and poisonous and generates harmful byproducts. Ozone is costly because of its elevated toxicity and the pollutants it produces. The manufacture and shipment of concentrated hydrogen peroxide can incur significant energy expenses. Wet oxidation necessitates elevated pressures and temperatures, leading to substantial costs. Chemical oxidation poses risks and necessitates cautious management of reactive chemicals and sludges. Chemical synthesis requires a significant amount of energy and necessitates frequent replacement of electrodes due to corrosion.	40, 45 and 50
Photocatalysis	Electrochemical oxidation is not practical in removing persistent contaminants from highly concentrated effluent Utilizing several photolysis methods, such as UV photolysis or TiO_2 -catalyzed UV photolysis, may be very efficient in breaking down a wide range of halogenated chemical compounds, some non-halogenated organic compounds, heavy metals, and particular personal care products. Photolysis alone may struggle to destroy volatile organic compounds at low concentrations, necessitating additional treatment methods. The effectiveness of photolysis is typically limited by the transparency of the water being purified, since UV light has to be capable of passing through it. The substantial energy consumption of UV photolysis may result in a significant life-cycle effect. UV lights need regular cleaning, and their replacement results in higher labor expenses. Photocatalysis is often ineffective over extended periods due to water chemistry factors, such as the presence of co-contaminants and hardness	40, 45, 47, 50 and 52
Filtration and membrane filtration	Various filtering methods are very efficient in eliminating most pollutants from wastewater. Filtration operates by capturing impurities inside the small openings of the filter, making it a very size-dependent method of elimination. Conventional filtering techniques are often insufficient for eliminating heavy metal ions, emerging pollutants, and other dissolved ions from water. However, membrane filtration, ultrafiltration, and reverse osmosis are all relatively efficient in addressing these issues Water movement across the membrane depends on applying pressure to push the fluid over the membrane, which may demand substantial energy inputs. In membrane filtration, particular circumstances must be maintained to avoid fouling, which is a typical problem in filtering. Backwashing is often necessary to prevent blockages, and the membrane is typically cleaned with strong chemicals to prepare it for regeneration. Reverse osmosis also necessitates	40, 45, 47, 49, 50 and 51



Table 2 (Contd.)

Strategies	Performance and drawbacks	Ref.
Adsorption	<p>adding minerals to the water and modifying the pH level, which incur additional expenses</p> <p>Most adsorption techniques use a carbonaceous substance to ensnare pollution particles inside its porous framework. Although the basic components for activated carbon may be cheap, using non-sustainable energy sources to generate high-quality activated carbon has been shown to affect the ecosystem substantially</p> <p>Reactivation of the carbon substance is necessary for activated carbon remediation to eliminate the adsorbed organic molecules. Alternative adsorption media are sometimes costly to manufacture and have a limited lifetime for reactivation, which is similarly costly. While some cheaper alternatives have been discovered, they often lack the same level of efficiency and frequently experience pore blockage. Adsorption eliminates the pollutant without altering it, producing a hazardous waste stream that must be managed. If the adsorbent is not reactivated on-site, it must be treated as hazardous waste, necessitating particular disposal methods and incurring additional expenses</p>	40, 45, 47, 49, 51 and 53
Fenton/photo-Fenton	<p>The Fenton treatment employs an iron catalyst and hydrogen peroxide to oxidize pollutants in wastewater. Integrating UV irradiation into the procedure may augment the rate of oxidant generation, thereby increasing the treatment's efficiency. Fenton and photography Fenton reactions are effective for degrading a wide range of compounds, including halogenated organics, insecticides, herbicides, non-halogenated organics, colors, and particular personal care products. Fenton and photography: the Fenton processes encounter similar constraints as hydrogen peroxide oxidation and UV photolysis: hydrogen peroxide production incurs substantial costs due to the energy required, and powering the UV lamps also demands considerable energy expenditure.</p> <p>Handling Fenton reagents involves dealing with very reactive substances</p>	45 and 49
Ion exchange	<p>Ion exchange primarily utilizes synthetic materials, namely ion exchangers, as sorbents to selectively adsorb precious ions. In the biological sector, the primary ion exchange method is the application of ion exchange resin. This resin extensively extracts organic acids, amino acids, antibiotics, and other tiny compounds. The ion exchange process has many benefits, including cost-effectiveness, minimal equipment requirements, straightforward operation, and little or no reliance on organic solvents. However, some limitations are associated with it, including a lengthy manufacturing cycle, occasional subpar product quality, and significant pH fluctuations throughout the operation. In addition, it is not always feasible to locate the appropriate resin</p>	51
Boiling	<p>In communities today, this practice is widespread. Boiling drinking water kills bacteria and viruses, but not chemical contaminants. Pathogens and biodegradable contaminants may be decontaminated using this approach. Filtering filthy or impure water before boiling improves its quality. Many creatures die in water boiling at around 100 °C. When water is warmed to 70–75 °C, microorganisms are unlikely to live longer than thirty minutes. One of the easiest water purification procedures without extra equipment is boiling. Water becomes less hard and salty when boiled. Along with its benefits, this technology has significant drawbacks, such as the need for fuel and the difficulty of purifying massive amounts of water</p>	7
Solar disinfection	<p>Solar disinfection is a common and cost-effective home approach. This technique is quite time-consuming since it involves exposing water held in transparent plastic or glass containers, or obvious plastic bags, to direct sunlight for extended periods to destroy the pathogenic microorganisms contained in the water. Occasionally, when the situation is overcast or during the winter, it may take several days for the water to be thoroughly disinfected using this method. The ability of this approach is determined by the intensity of the sun, the absorption of light, the initial concentration of bacteria, and the turbidity of the water. Although this procedure is cost-effective, its time requirements make it less desirable</p>	7



social standing of affected cultures or nations.³⁹ Water becomes contaminated when undesirable substances seep into water resources, making them unsafe for drinking and other uses.⁴⁰ Before 2015, only about 20% of wastewater worldwide received proper treatment. A 2016 United Nations report states that nearly 70% of industrial wastewater in poor countries is discharged into the environment without proper disposal.⁴¹ In many underdeveloped nations, wastewater is still released into water bodies without adequate treatment.²² Table 1 shows the different types of water contaminants, their sources, and the harmful effects they cause. Throughout history, people have used science-based techniques to purify polluted water, both in the past and the present day.⁷ Ongoing progress aims to develop new ways to treat wastewater to meet the demand for clean water.⁴² However, effectively treating wastewater, including contaminants, remains challenging with current methods.⁴³ The study outlines various wastewater treatment techniques, which typically include biological, chemical, and physical methods organized into stages called preliminary, primary, secondary, and tertiary treatment.^{44,45} Each approach has specific advantages and limitations. Industrial applications often avoid methods that are costly to install and operate, time-consuming, produce limited output, or generate harmful byproducts, as shown in Table 2.⁴⁶ Since it is responsibility of water providers to deliver and pure water, treatment methods must be characterized by long-term durability, reliability, accuracy, safety, and affordability.^{40,47} As a result, discovering an alternative treatment technique that can completely decompose or eliminate pollutants is essential.²⁶

3. Adsorption

Adsorption is an efficient, environmentally sustainable, and extensively used technique for eliminating contaminants from water and wastewater. This method has attracted considerable interest owing to its straightforwardness, economic efficiency, and adaptability in mitigating diverse pollutants, such as pesticides, heavy metals, pharmaceuticals, and dyes.^{54,55} Adsorption basically consists of the transferring of contaminants, termed adsorbates, from a liquid or gaseous phase to the surface of a solid substance defined as the adsorbent (solute). This transfer happens as a consequence of physical or chemical interactions between the adsorbates and the adsorbents, leading to the deposition of pollutants on the surface of the adsorbents.⁵⁶

The principle of adsorption has a substantial historical background. Preliminary research conducted by C. W. Scheele in 1773 illustrated the uptake of gases by charcoal, whilst Lowitz (1785) used charcoal to decolorize solutions of tartaric acid. Subsequently, Heinrich Kayser (1881) used the word “adsorption” to characterize the surface phenomena of material accumulation.⁵⁶ These essential investigations established the basis for the extensive use of adsorption in water remediation applications. By the 20th century, practical applications, such as the removal of heavy metals by activated carbon with efficiencies over 99.9%, emphasized its promise for eliminating both organic and inorganic contaminants.⁵⁷ Fig. 4 demonstrates that




Fig. 4 Increasing annual percentage of adsorption-related publications.⁷³

articles related to adsorption are becoming more prevalent every year.

Adsorption is classified into two main categories: physical adsorption (physisorption) and chemical adsorption (chemisorption). Physisorption is regulated by weak van der Waals forces and hydrogen bonding, often resulting in the formation of monolayers or multilayers on the adsorbent surface. This reversible process needs minimum activation energy and is frequently preferred at low temperatures^{58,59}. Chemisorption, by contrast, consists of intense chemical bonds, including covalent or ionic interactions, resulting in the establishment of a monolayer on the adsorbent. Chemisorption is often irreversible, highly selective, and characterized by a greater heat of adsorption, generally between 40 and 125 kJ mol^{-1} .^{60,61} In optimal circumstances, physisorption and chemisorption may take place either simultaneously or in an ordered process. For instance, an adsorbate might first be physically adsorbed onto the surface and later establish chemical bonds.^{56,62} The distinction between physical and chemical adsorption is illustrated in Table 3. Covalent bonding and surface functionalization play pivotal roles in chemical adsorption processes. Functional groups such as carboxyl ($-\text{COOH}$), amino ($-\text{NH}_2$), hydroxyl ($-\text{OH}$), and thiol ($-\text{SH}$) can form strong coordinate or covalent bonds with heavy metal ions, producing stable inner-sphere complexes that enhance adsorption selectivity and capacity. These groups act as electron donors to the vacant d-orbitals of metal ions, resulting in robust metal-ligand interactions. Furthermore, surface functionalization strategies significantly increase the density and accessibility of active sites while improving structural stability and regeneration potential.^{63,64}

The effectiveness of adsorption depends on various parameters such as the surface area, pore structure, and functional groups of the adsorbent, as well as the physicochemical characteristics of the adsorbate. External factors like pH, temperature, ionic strength, and contact time are also crucial^{57,65}. For instance, cationic dyes typically rely on electrostatic attractions for adsorption, although hydrophobic or hydrogen bonding interactions may dominate in different systems.⁵⁶ Surface modifications and adjustments, including functionalization



Table 3 A comparison of physical and chemical adsorption processes

Physical adsorption	Chemical adsorption
<p>Physical adsorption is mainly influenced by weak intermolecular forces, including van der Waals forces, hydrogen bonding, and electrostatic interactions. It is a non-specific process, indicating that it could happen with various adsorbate–adsorbent combinations. Essential properties associated with this process consist of:</p> <ul style="list-style-type: none"> • Small binding energy: the binding energy associated with physisorption is comparatively low, often between 5–40 kJ mol^{−1}, representing small attractive forces.^{56,62} The binding energy has been reported as around 10–300 meV (ref. 58) • Reversibility: owing to the small interaction forces, physisorption is often reversible, facilitating the straightforward desorption of the adsorbate from the adsorbent surface (regeneration or reactivation)⁷⁴ • Multilayer generation: may lead to the development of monolayers or multilayers of adsorbate molecules on the adsorbent surface⁵⁹ • Non-activated technique: the method is characterized by low activation energy requirements, providing rapid operation⁷⁵ • Temperature sensitivity: physisorption is generally enhanced at lower temperature levels. A rise in temperature often results in a reduction in adsorption capacity because the weak nature of the binding forces⁶⁵ • Mechanism of interaction: consist of van der Waals forces, hydrogen bonding, ion exchange, dipole–dipole interactions, π–π interactions, and hydrophobic hydration^{56,57} 	<p>Chemical adsorption refers to the establishment of strong chemical bonds—either covalent or ionic—between the adsorbate and the adsorbent surface. This method is much more specific and selective than physisorption. The primary characteristics consist of:</p> <ul style="list-style-type: none"> • Strong binding energy: distinguished by strong binding energies, often between 40 and 124 kJ mol^{−1}, indicating powerful interactions. The energy scale may vary from 1 to 10 eV, based upon the nature of the chemical bond established^{58,62} • Irreversible: due to strong bond formed, chemisorption is often irreversible. Desorption of chemisorbed species requires the rupture of these bonds, which makes it energetically challenging^{70,74} • Monolayer generation: in contrast to physisorption, chemisorption is restricted to a monolayer owing to the specificity of chemical bonding⁵⁹ • Activated technique: chemisorption needs activation energy, resulting in a slower method relative to physisorption⁷⁵ • Temperature independence: chemisorption could happen throughout an extensive range of temperatures, as its rate potentially improving with temperature due to the need of energy to activate⁶¹ • Mechanism of interaction: the method includes transferring electrons or sharing, resulting in the creation of covalent or ionic bonds. The surface functional groups of the adsorbent substantially affect the chemisorption process^{54,60}

with specific chemical groups, can enhance the selectivity and adsorption capacity of adsorbents.⁶⁶

Generally, traditional adsorbents like activated carbon, zeolites, and silica gel have been widely used due to their high adsorption efficiency and stability. However, their high costs and regeneration challenges have spurred interest in alternate adsorbents derived from agricultural and industrial waste. Materials such as chitin, nutshells, rice husks, and fly ash offer sustainable and cost-effective options.^{61,67}

Recently, nanoparticles have gained attention as innovative adsorbents because of their large surface areas, customizable surface chemistries, and rapid adsorption kinetics.⁶⁸ Their performance and selectivity can be further enhanced by modifications such as the adding of functional groups or surfactants.⁶⁵

The adsorption process generally proceeds through three stages; transportation of the adsorbate from the bulk solution to the surface of adsorbent, adsorption onto the surface, and diffusion inside the pores of the adsorbent.^{54,57} The stages are governed by diffusion, mass transfer, and thermodynamic principles aimed at minimizing the system's free energy. Interactions involved in adsorption include van der Waals forces, electrostatic attractions, hydrogen bonding, and chemical bonds, depending on the characteristics of the individual adsorbent and adsorbate. Fig. 5 illustrates these interactions, showing the sequential nature of the adsorption process.⁵⁷

A key advantage of adsorption is its environmental sustainability. Unlike traditional technologies that produce hazardous byproducts or sludge, adsorption is a process that does not generate secondary pollution.⁶⁹ Additionally, many adsorbents




Fig. 5 Schematic illustration of the adsorption technique and its mechanics. Adapted from ref. 57 with permission from Elsevier, copyright 2024.





Fig. 6 Progression of events in the area of nanotechnology across time.⁷⁸

can be reactivated or regenerated through desorption, allowing multiple reuse cycles and reducing operational costs.⁷⁰ This feature enhances the feasibility of adsorption for large-scale applications, especially in decentralized or resource-limited settings.



In conclusion, adsorption is a fundamental method for treating water and wastewater. Its ability to effectively remove a variety of pollutants, combined with its cost-effectiveness and eco-friendliness, underscores its importance in addressing global water pollution. Ongoing improvements in adsorbent materials and optimization techniques are expected to enhance the efficiency and sustainability of adsorption systems, ensuring their continued role in sustainable water management.^{71,72}

4. Nanotechnology

The term "Nano" originates from the Greek word "nanos," which refers to "dwarf." A nanometer is a unit of length equivalent to one billionth (10^{-9}) of a meter, about the length of

10 hydrogen atoms. The width of an average human hair is around 80 000 nanometers. Nobel Laureate Professor Richard Feynman introduced the principle of nanotechnology in his renowned 1959 speech titled "There is plenty of room at the bottom".⁷⁶ Nanotechnology integrates engineering capabilities with science at the atomic and molecular scale.⁷⁷ Fig. 6 shows the progression of nanotechnology, with notable research advancements beginning around 2010 and a sharp increase from 2015 forward.

Nanotechnology is the application of phenomena at the nanoscale size, which is the discipline of nanoscience in general. Nano-materials are the finest elements created by mankind, measuring only a few nanometers in dimension.⁷⁹ According to the European Commission, a nanomaterial is a microscopic particle, originating naturally, produced incidentally, or deliberately fabricated. These particles can exist individually (unbound) or together in agglomerates. For a material to qualify as a nanomaterial, it must contain at least half of its particles within the size range of 1–100 nanometers.⁸⁰ A wide range of nano-materials have been created, including

Fig. 7 Various categories of nanomaterials based on architectural configuration.^{90,83-88}Fig. 8 Schematic illustration of the wide-ranging applications of nanotechnology across various fields.^{82,83}

nanotubes, nanowires, particles, films, colloids, and quantum dots.⁵² Nanomaterials could be categorized based on their architectural configuration, which influences their properties and applications, as demonstrated in Fig. 7. This innovative subject incorporates knowledge and principles from multiple fields, such as physics, biology, chemistry, and biotechnology.⁸¹ Nanomaterials possess extraordinary characteristics due to their very minuscule dimensions, which provide an extensive range of potential applications in several areas.⁸² Fig. 8 illustrates the potential applications of nanotechnology in several fields.

Substances have distinct and highly modified characteristics when scaled down to the nanoscale (as shown in Fig. 9), making them suitable for a diverse array of uses in the remediation of wastewater.⁸³ The characteristics and functions of materials may change when they are modified from a large scale to a nanostructured scale.⁹⁰ The dimensions, while particular characteristics vary about the bulk of the equivalent material, are shown in Fig. 10.

4.1 Application of nanotechnology in wastewater

Nanotechnology has emerged as a significant field in environmental remediation, providing novel approaches for handling essential issues in wastewater treatment.⁹⁸ Presently, several

sectors worldwide, including paper and pulp, textiles, petroleum and natural gas, and pharmaceuticals, utilize substantial quantities of water and therefore generate heavily polluted wastewater.⁹⁹ The use of nanoparticles may provide prospects for the effective remediation of heavily polluted wastewater.¹⁰⁰ The hardest pollutants to remove from wastewater exist in the nanoscale region, namely between 1 and 100 nanometers. Therefore, nano-based methods are particularly appropriate for addressing these pollutants. Nanotechnologies provide significant benefits for water decontamination due to their small size and the exceptional physicochemical characteristics of nanoparticles.⁶ Their increased surface area-to-volume ratio and surface reactive properties create a high density of active sites for contaminant interaction, facilitating exceptional adsorption efficiency. Nanomaterials demonstrate significant efficacy in eliminating pollutants from aqueous environments.¹⁰¹

The diminutive dimensions and distinctive surface properties of nanomaterials enhance their interactions with pollutants *via* mechanisms including van der Waals forces, hydrogen bonding, and electrostatic interactions. Moreover, techniques for surface functionalization enable the customization of nanomaterials for the targeted adsorption of particular pollutants. Functionalized nanomaterials have been effectively utilized to target heavy metals, dyes, and pharmaceuticals, showcasing their versatility and adaptability in various




Fig. 9 Exploring the characteristics of materials at the nanoscale.^{76,91,92}






Fig. 10 Nanoparticles experience alterations in chemical, physical, and mechanical characteristics at certain dimension thresholds, distinguishing them from larger particles and bulk materials.⁹³⁻⁹⁷ The units used for measurement are nanometers, and the picture is not drawn to scale. The change may occur gradually, as indicated by the melting temperature, or rapidly, as observed in catalytic activity. Surface or quantum effects could cause the difference.

wastewater treatment contexts.^{58,102} Furthermore, specific nanomaterials like titanium dioxide and zinc oxide demonstrate photocatalytic characteristics, producing reactive oxygen species when exposed to light, which facilitates the degradation of pollutants. This multiple capability significantly improves their capacity for comprehensive wastewater treatment.¹⁰¹

Many efficient, environmentally friendly, and economical nanomaterials can be used to treat water and wastewater. These nanomaterials have distinct physical, chemical, and biological properties, giving them unique capabilities for decontaminating industrial effluents, drinking water, surface water, and ground water. The materials may be classified as organic, inorganic, carbon-based, or composites.^{52,103} Implementing nanotechnology in the purification and reusing of household

water presents potential solutions to issues associated with deteriorating water quality in network distribution, less reliance on critical infrastructure, and the utilization of alternative water sources for farming and portable purposes while subsidizing energy use. This approach is particularly relevant for developing countries facing challenges related to decreasing quality of water and increasing demand for purer water to ensure food safety, healthcare, and compliance with environmental regulations.¹¹

Governments and commercial businesses throughout the world, especially in China, Japan, the United States of America, and Germany, have initiated some programs and attempts to further the development of nanotechnology.⁴⁰ Many experts have been conducting different research and experiments on the potential applications of nanotechnology in water and wastewater remediation. However, there has been little advancement in comparison to the implementation of nanotechnology in areas like medicine and electronics.⁴⁵ Research using nanomaterials for water and wastewater treatment began in the early 2000s, but was mostly focused on laboratory and pilot-scale experiments. China and Iran were recognized as the leading nations in terms of the number of publications on this scientific subject.⁹⁹ As shown in Fig. 11, the 2020 market research of nanotechnology indicates that the Asia-Pacific region is the most appealing market for nanotechnology, due to significant demand for prospective nanomaterials.¹⁰⁴

Nanomaterials exist in several forms, such as nanoparticles, nanotubes, nanofibers, and nanosheets, each specialized for particular functions. Carbon nanotubes coated with titanium dioxide have been modified to improve adsorption effectiveness owing to their increased surface area and better reactivity. Smaller hematite nanoparticles have enhanced adsorption capabilities for metal ions at reduced pH levels, highlighting the influence of particle size and shape in adsorption efficacy.^{57,98} Advanced synthesis methods, including sol-gel techniques and molecular self-assembly, have enhanced the performance and scalability of nanomaterials for industrial applications.⁵⁷

Nanomaterials, such as nanoparticles, nanotubes, and nanomembranes, are capable of detecting and removing various biological and chemical particles, including toxic elements of heavy metals, dyes, organic substances, bacteria,




Fig. 11 Global nanotechnology market study report (2020), illustrating the statistics of the utilization of nanotechnology-based products worldwide.¹⁰⁴



viruses, antibiotics, micronutrients, and algae.^{105,106} Previous research has consistently demonstrated that nanomaterials possess essential abilities and suitability for use in water and wastewater treatment. Specifically, they have been proven effective in membrane techniques, adsorption, catalytic oxidation, disinfection, and detection and monitoring. Unfortunately, the majority of the established nanomaterials were still in the laboratory investigation phase or were only serving as a demonstration of feasibility. A specific type of nanotechnology widely accessible through injection is zero-valent iron nanoparticles.^{41,107} The United States commonly utilizes zero-valent iron nanoparticles for groundwater remediation. Due to the lower costs of nanomaterials, they are economically sustainable for water and wastewater treatment, making them a more acceptable option. Nevertheless, basic treatment limitations are associated with directly employing free nanoparticles in water and wastewater treatment operations. Nanoparticles tend to accumulate together in fluidized systems or fixed beds, which leads to a significant decrease in activities and a decrease in pressure.¹⁰⁸ Additionally, except for magnetic nanoparticles, separating the majority of exhausted nanoparticles from the purified water for subsequent reuse remains a difficult effort.^{109,110} Furthermore, much is still to learn about how nanomaterials behave and what happens during water and wastewater treatment. Understanding the effects of nanomaterials on the environment and human health is crucial, as it poses a significant challenge to the widespread use of nanotechnology.^{111,112}

To prevent or reduce the possible negative impact caused by nanotechnology, creating a substance or instrument that may decrease the escape or movement of nanoparticles while still protecting their strong reactive properties can be preferable. The efficiency and potential of nanocomposite progress have been established. Nanocomposites are often produced by incorporating nanoparticles onto different types of supporting substances, such as polymers or membranes.¹⁰⁷ Several nanocomposites that were documented had exceptional efficacy in purifying water, were capable of being reused, had a reasonable cost, and were suitable with current infrastructure.^{108,113} Recent improvements in the integration of nanomaterials with other substances have enhanced their adsorption effectiveness and decreased manufacturing costs, hence increasing their accessibility for large-scale applications.¹¹⁴

In the last ten years, nanoremediation has been extensively used for the treatment of polluted locations, displaying considerable benefits compared to traditional treatment techniques. Reports from the USEPA and environmental nanotechnology sources demonstrate that nanoremediation has resulted in an estimated 80% reduction in operating expenses and a significant drop in the duration necessary for site decontamination. The worldwide investment in nano-enabled technologies has significantly escalated from 432 million dollars in 1997 to 4.1 billion dollars in 2005, illustrating the increasing importance of nanotechnology across several fields. The market for nanotechnology-based products is growing quickly, with around 3 to 4 innovative products launched weekly. In 2015, the Asian nanotechnology industry was valued

at around 14 741.6 million dollars, with forecasts predicting an increase to 55 056 million dollars by 2022, propelled by a compound annual growth rate of 20.7%. Market assessments from 2020 indicate that the Asia-Pacific area is the most appealing market for nanotechnology, driven by the rising demand for sophisticated nanomaterials (Fig. 11).¹⁰⁴ The application of nanoparticles in water and wastewater treatment has shown notable increase. A study investigating *via* Scopus revealed 1990 papers relating to "nanomaterials in wastewater treatment", indicating a growing scientific interest in this area of research.³⁸

Nanotechnology's significant applications in wastewater treatment can be broadly categorized into three distinct groups according to the characteristics of its nanomaterials: nanomembranes, nanoadsorbents, and nanocatalysts.^{52,68} Nanomembranes are a crucial category of nanomaterials employed in wastewater treatment operations. Nanomembranes may be categorized into several types based on their porosity, structure, and application method.^{115,116} In this innovation, the pressure-driven use of wastewater has been demonstrated to be optimal for enhancing the desired water quality. Nano-filtration is widely used in industries for wastewater treatment due to its small pore sizes, cost-effectiveness, excellent effectiveness, and ease of use.⁵² Nanomembranes could be created using various nanomaterials, including nanometal particles and nano-carbon tubes, among others.¹¹⁷ The advantages of this technology are high-quality purified water, efficient disinfection, and minimal plant area requirements, the primary drivers behind its development. Furthermore, in comparison with alternative remediation methods, it is very affordable, effective, and straightforward in construction.^{118,119} The water has undergone advanced filtration procedures, offering superior-grade potable water. Enhanced purifying techniques include microfiltration, ultrafiltration, nanofiltration, reverse osmosis, and advanced oxidation. These membranes integrate adsorption, size-selective filtration, and catalytic functionality to efficiently eliminate pollutants like pharmaceuticals, heavy metals, and salts.¹²⁰ Fig. 12 illustrates the efficacy of several filtering methods in eliminating various pollutants often found in water.

The next category of nanomaterials is adsorption. Current research in nano-adsorption technology has examined chiefly the efficiency of using nano-adsorbent materials to eliminate contaminants from wastewater.⁵² Chemically active components with a high adsorption capacity could be employed to generate nanoadsorbents that attach to the outside of nanomaterials.¹²³ Their increased porosity, modifiable surface chemistry, and active surface sites render them very efficient in adsorbing a diverse array of pollutants, including trace metals and polar organic molecules.⁶² Various materials are used to produce nanoadsorbents, such as activated carbon, metal oxides, clay materials, silica, and modified materials in the form of composites.¹¹⁷ Nanoadsorbents have two primary characteristics: inherent surface and outside functionality. Their outside structure, visible size, and inner composition also influence their chemical, physical, and material characteristics. In an aqueous environment, the factors that impact the adsorption technique include a large surface area, strong adsorption






Fig. 12 The effectiveness of various methods of filtration in removing contaminants.^{7,85,121,122}

activity, considerable chemical activity, atom arrangement on the surface, minimal inner diffusion resistance, and considerable surface binding energy.^{52,124} The most extensively investigated approach for eliminating contaminants from water and wastewater is the utilization of engineered nano adsorbents.⁹⁹

Nanocatalysts are the final classification of nanomaterials. Researchers are interested in developing wastewater treatment innovations, particularly in using inorganic nanomaterials like metal oxides and semiconductors. Their elevated surface area-to-volume ratio improves catalytic efficiency, allowing for the breakdown of contaminants by mechanisms like reducing activation energy and promoting selective chemical reactions. A variety of nanocatalysts are used to break down pollutants in wastewater. These include electrocatalysts, Fenton-based catalysts, photocatalysts, and catalysts with antimicrobial characteristics. These catalysts contribute to enhancing the oxidation process of organic contaminants and have antimicrobial effects.^{68,79,125-127} Table 4 provides a concise overview of the practical considerations regarding using nanomaterials to eliminate environmental pollutants, allowing for a brief evaluation.

A significant benefit of nanomaterials is their capacity for regeneration and reuse, which improves sustainability and lowers operating expenses. The capacity to recover and reutilize nanoadsorbents, for example, corresponds with sustainable practices and mitigates issues related to resource consumption and waste production.¹²⁸ The progress in nanotechnology presents several possibilities for developing cost-effective and eco-friendly water supply methods. Nanomaterials are

anticipated to possess diverse characteristics that provide cost-efficient and highly efficient methods for treating wastewater and water. These techniques would depend less on complex infrastructure for wastewater treatment and could be used with other water treatment processes such as adsorption, coagulation, membrane technology, and photocatalysis.^{11,27} Nanotechnology-based water and wastewater treatments show great potential in addressing the primary obstacles in water treatment and offer innovative treatment capabilities that can facilitate the cost-effective utilization of other water sources to enhance the water supply.

5. Characterization techniques

Nanomaterials often exhibit distinct features compared to their larger counterparts, primarily due to their increased surface-to-volume ratio, significantly enhancing molecular-level reactivity. This results in unique electrical, optical, and chemical properties, and can affect their mechanical characteristics. Comprehensive characterization of nanoparticles is essential to understand and control their manufacturing processes fully. This includes analyzing agglomeration, spatial reasoning, geometric proportions, Brownian motion, intercalation, and dispersion, as well as particle size, crystal size, porosity, solubility, surface properties, water sorption, and surface morphology.^{141,142} Detailed and precise characterization of nanomaterials is vital to explore their enhanced properties, which allow overcoming limitations of conventional technologies. The methodologies for nanoparticle characterization are



Table 4 The practical considerations regarding the use of nanomaterials for effectively eliminating pollutants from the water and wastewater

Nanomaterials	Contaminants	Advantages	Disadvantages	References
Nano-membrane	Salts Organic Contaminants Inorganic Contaminants Microbes	Flexible design Non-toxic Environmentally sustainable Excellent water quality Reduced establishment area Cost-effective without losing efficiency compared to other new and traditional methods	Significant energy requirements Membrane fouling and clogging Extensive utilization of pressure Expensive Expensive maintenance costs The performance technique is relatively slow	22, 40, 129 and 130
Titanium dioxide (TiO ₂) based	Heavy metals Dyes Pesticides Microbes	Cost-effective Simple to prepare Non-toxic Biocompatibility Strong chemical and corrosion resistance	Low absorption capacity for both visible and ultraviolet radiation The challenge of extracting TiO ₂ particles	131
Dendrimer	Hormones and other endocrine-disrupting compounds Organic contaminants	Strong adhesion with little formation of sediment Regenerative	Tend to clump together and form larger particles	40
Iron-based	Heavy metals Organic contaminants Heavy metals Dichlorinations Dyes Anion and oxyanion	Simple separation Inexpensive Abundant in nature Uncomplicated preparation Safe for handling Characteristics of superparamagnetic	Generation of sludge Challenging removal of sludge Health concern Challenging to recover	40, 132 and 133
Micelle	Organic Contaminants Dyes Pharmaceuticals Pesticides	Groundwater purification High adsorption efficiency On-site remediation Remarkable attraction towards hydrophobic	Expensive	40 and 134
Bimetallic	Personal care products Organic contaminants Inorganic metals Heavy metals Pharmaceuticals Dichlorinations Dyes Pathogenic microorganisms and biotoxins Radiouclides	Enhanced reactivity	Generation of sludge Difficult for recovery Challenging removal of sludge	22, 40, 135 and 136



Table 4 (Contd.)

Nanomaterials	Contaminants	Advantages	Disadvantages	References
Nano-clay	Dyes Anion Heavy metals Pharmaceuticals Organic contaminants	Non-toxic Cost-effective Abundant in nature Enhanced ion-exchange capacity Increased efficiency of adsorption Swelling potential Excellent thermal characteristics Biodegradable Low aggregation Durability	Impermeable Generation of sludge	40, 137 and 138
Magnetic	Organic Contaminants Pharmaceuticals Pathogenic microorganisms and biotoxins	No generation of sludge A significant level of reusability and ability to regenerate	Adverse environmental impacts and human health effects	40, 78 and 139
Carbon nano-tube	Dyes Heavy metals Personal care products Organic	Excellent chemical durability	Adverse environmental impacts and human health effects Lesser adsorption efficacy Production expenses Generation of sludge Difficult for recovery	22, 40 and 140



Table 5 Some methodologies that can be used to characterize nanoparticles

Analysis method	Their roles in nanoparticle analysis	Ref.
X-ray diffractometry (XRD)	XRD is a technique used to analyze the crystalline structure of nanoparticles, providing information on crystallinity and chemical compound resolution. When a single-colored beam is aimed at the crystal, it generates distinct diffraction patterns, which are then analyzed using Bragg's equation to determine the features of crystalline or polycrystalline materials. The measurements are expressed in angstroms and are the main factor in determining a crystal's characteristic size and unit dimensions	31, 141, 142 and 147
Ultraviolet-visible spectrophotometer (UV-vis)	UV-vis absorption spectroscopy is helpful in studying the absorbance bands and band gap of nanoparticles, particularly noble metals. It is used to validate nanoparticle formation and monitor stability. UV-visible spectroscopy is used to measure the optical properties of nanoparticle solutions, validate their synthesis, and assess their stability. It is a quick, sensitive, and user-friendly technique that can evaluate both solid and liquid samples, providing insights into optical properties, size, concentration, agglomeration state, and NP shape	146
Fourier transform infrared spectroscopy (FT-IR)	An FT-IR spectrophotometer is used to identify functional groups in synthesized nanoparticles, which are crucial for adsorption characteristics. It analyzes chemical functional groups between 400 and 4000 cm^{-1} in the spectral band, including carboxyl, hydroxyl, and amine groups. FT-IR spectroscopy is a rapid, cost-effective technique that requires minimal sample preparation. This technology collects detailed information with great precision over a broad spectrum, enabling the examination of the chemical composition of metal nanoparticles on surfaces and detecting organic, inorganic, and polymeric substances using infrared radiation	147, 148, 149 and 150
Scanning electron microscope (SEM)	SEM is a crucial analytical technique that uses electrons to generate micro-images, allowing for the detection and characterization of nanoparticles with varying sizes and shapes. It is particularly effective for determining the morphological structure and dimensions of nanoparticles	141, 147, 149 and 151
Transmission electron microscopy (TEM)	TEM is a microscopic method to obtain detailed information on a material's surface features, structure, dimensions, composition, and crystallography. It involves the passage of an electron stream through a thin specimen, resulting in the interaction of electrons with the object and the formation of an image. TEM pictures precisely detail nanoparticles' specific dimensions, dispersion, and external structure. TEM provides higher-resolution pictures than a light microscope and is used for studying the structure and presence of nanoparticles	141, 142 and 148
Energy dispersive X-ray (EDX or EDS)	EDX is a crucial instrument in nanotechnology for determining the elemental composition of samples. It is an analytical technique used to chemically characterize or analyze the elemental composition of nanoparticles, providing data on chemical composition, phase identification, and purity. EDX is used to analyze nanoparticles to determine their elemental compositions, abundance,	147 and 152



Table 5 (Contd.)

Analysis method	Their roles in nanoparticle analysis	Ref.
Thermogravimetric analysis (TGA)	and purity. It is sensitive to surface chemistry and can detect elements in a very thin layer close to the surface. EDX can obtain compositional data on quasi-bulk specimens, and analyze single particles, morphologies, or isolated spots on filters or deposits. It is also compatible with applications like TEM and SEM. TGA is a method for assessing a sample's chemical and physical characteristics by quantifying the reduction in mass as the temperature increases. It is often used in qualitative analysis to ascertain nanoparticle composition, evaluate additive impact, and gauge nanoparticle stability under oxidative and thermal conditions	149, 153 and 154
X-ray photoelectron spectroscopy (XPS)	TGA can also be used to conduct dehydration studies and study the reduction in material mass caused by oxidation, decay, or volatilization. This analysis generates a plot showing the relationship between temperature and mass. X-ray photoelectron spectroscopy (XPS) is a widely used for analyzing materials' elemental composition and chemical state. It determines electron binding energy by examining the kinetic energy of emitted photoelectrons and their corresponding wavelength in incoming X-rays. Plotting the intensity of photoelectrons against binding energy helps identify the chemical composition of materials and the oxidation states of each element. The variation in binding energy for an atom with the same oxidation state may indicate distinct local coordination environments. XPS is highly sensitive, allowing accurate analysis of components in small quantities, making it a popular method for measuring doped materials	155
Vibrating sample magnetometry (VSM)	Vibrating sample magnetometry (VSM) is a widely used technique for measuring hysteresis loops at room temperature, quantifying magnetic characteristics of substances based on magnetic field, temperature, and duration. It helps identify whether nanoparticles exhibit paramagnetism or diamagnetism, determining their classification as ferromagnetic or diamagnetic. A material's level of attraction to a magnet or magnetic field determines its classification, with paramagnetic materials not strongly attracted to a magnet, and diamagnetic materials repelling against a magnet after being magnetized	149, 153 and 156
Dynamic light scattering (DLS)	DLS is a technique used to study nanoparticle size distribution and polydisperse nature in suspension. It calculates the hydrodynamic radius of a particle undergoing Brownian motion, which is crucial for understanding its functioning. When a particle in a solution is exposed to a laser beam, it scatters light with different intensities, and the Stokes-Einstein connection equation is used to analyze these fluctuations. DLS provides reliable measurements of particle sizes ranging from 20 to 200 nm. DLS is widely used in industry and research laboratories to analyze particle size distribution profiles of nanoparticles in solutions and colloidal suspensions. Its fast and sensitive detection capabilities allow for real-time determination of nanoparticle size	141, 146 and 157

crucial for verifying the existence of nanoscale particles and assessing their quality.⁸¹ These approaches involve microscopy for visualizing samples and spectroscopy for analyzing their composition and structure. Characterization provides information on morphology, crystal structure, chemistry, electronic structure, mechanical, thermal, and electrical properties.¹⁴³ Characterizing nanoparticles also helps determine their potential toxicity, stability, and dispersion behavior.¹⁴⁴ Table 5 presents various methodologies for nanoparticle characterization, while Fig. 13 displays parameters and their corresponding characterization methodologies.

Characterizing nanoparticles is challenging due to their small size and the complexity of their interactions. No single method is ideal for all situations; the choice of method depends on the type of sample, desired information, time constraints, and economic feasibility. Therefore, a combination of methods is often used to achieve comprehensive characterization. Comparing results from different techniques can also enhance accuracy, as each method has varied sensitivity, advantages, and limitations.¹⁴⁵

6. Heavy metals removal

There is a growing trend of heavy metals being released into the environment, particularly in developing nations. Unlike organic pollutants, heavy metals are not broken down by biological processes and tend to build up in living organisms. Many heavy metal ions are recognized for their toxicity or ability to cause cancer.¹⁶⁰ The atomic masses of heavy metals range from 63.5 to 200.6, and their specific gravities are more than 5.0.¹⁶¹ These elements are naturally present in the Earth's crust. Heavy metal contamination occurs due to natural phenomena and civilization. In addition to natural sources, human activities are the primary cause of heavy metal contamination. Fig. 14 provides a comprehensive summary of the primary sources of heavy metals.

The extensive use of heavy metals such as cadmium, arsenic, selenium, lead, and mercury significantly impacts the hydro-sphere, biosphere, lithosphere, and atmosphere.¹⁶³ The main heavy metals detected in industrial wastewater and their common industrial manufacturing origins are presented in




Fig. 13 Several parameters and their corresponding methods of characterization (Magnetic S. = magnetic susceptibility; Electron D. = electron diffraction).^{31,145,147,158,159}






Fig. 14 Graphical representation of heavy metal contamination sources.¹⁶²

Fig. 15. Several heavy metals serve as essential trace elements, functioning as micronutrients for people, flora, and fauna in small quantities. However, these heavy metals may lead to short-term and long-term toxicities when present in greater quantities. Since the 1970s, authorities have increasingly focused on addressing the contamination of heavy metals and have developed laws to regulate and mitigate its impact. The

European Union, formerly known as the European Community, requires the collection and remediation of municipal wastewater. Since the 1990s, it has been prohibited to dispose of this effluent directly into water bodies. The European law mandates that waste management initiatives adhere to the following priority orders: prevention, reuse, recycling, alternative forms of recovery (such as energy recovery), and disposal.¹⁶⁴ The United States Environmental Protection Agency (USEPA) and the WHO have established recommendations for the maximum allowable levels of hazardous heavy metals in drinking water and industrial effluent. These regulations outline the potential adverse health effects when these regulations are exceeded. Table 6 displays the dangerous heavy metals and the maximum allowable levels for their presence in drinking water and industrial effluent, according to regulations issued by the USEPA and WHO standards. The toxic impact of heavy metals escalates with increased concentrations; hazardous heavy metals may be very harmful to humans if ingested in amounts that exceed the maximum contamination level permitted in drinking water.^{165,166} In addition to impacting people and animals, it is important to ensure that the concentration of heavy metals in plants remains below the permitted level. If this limit is surpassed, there may be severe repercussions. Hence, it is essential to remediate wastewater polluted with these hazardous metals before releasing it into the environment or reusing it in industrial processes.⁹³

Surface water contamination with heavy metals is a widespread environmental issue worldwide. The quantities of heavy metals in Nigeria's Niger River water in 2004 were measured at 50 parts per billion (ppb) for cadmium, 30 ppb for lead, 2080 ppb for chromium, and 780 ppb for nickel. In 2013, the Korotoa River water in Bangladesh had a concentration of 11 ppb of cadmium, 35 ppb of lead, 83 ppb of chromium, and




Fig. 15 Most common heavy metals observed in industrial wastewater and their primary manufacturing origins.¹⁷⁴



46 ppb of arsenic. The excessive buildup, biomagnification, and toxicity of heavy metals in surface water have raised serious concerns among governments and the public.¹⁶⁴ Water heavy metal concentrations above the standards set by WHO and USEPA have been observed to be lower in industrialized nations such as Europe and North America, whereas they were higher in developing countries like Asia, Africa, and South America.¹⁶⁴

Several techniques are available for eliminating these heavy metals, including precipitation, filtration, adsorption, oxidation or lessening, reverse osmosis, ion exchange, and electrochemical remediation. However, these approaches lose effectiveness when heavy metals exceed 100 milligrams per liter. Many heavy metal salts exhibit water solubility and readily dissolve in wastewater, rendering them incapable of being extracted by physically separated techniques.^{165,167} Innovative methods such as nanotechnology have emerged over the past few years to address the deficiency in reusing heavy metals from wastewater for environmental purposes. Nanotechnology has been significant in the advancement of wastewater remediation and the preservation of the ecosystem. In the present situation, using nanomaterials has become essential for improving several industrial settings and processes, including catalysis, healthcare, and sensing. This eventually leads to decreased wastewater production and its handling.^{168,169} Recently, more advanced nanoadsorbents have been developed to enhance the adsorption process. On the other hand, advanced technologies like photocatalysis have shown their effectiveness and potential in eliminating heavy metals.^{170,171} Significant progress has been achieved in many nanomembrane methods, including ultrafiltration, nanofiltration, and reverse osmosis.^{172,173}

7. Adsorption for heavy metals removal

Adsorption is a surface phenomenon characterized by the attachment of heavy metal ions or molecules to an adsorbent. The process typically occurs in two stages: (1) the initial interaction between the adsorbent and the heavy metal-contaminated aqueous solution, and (2) the subsequent separation of the heavy metal-loaded adsorbent from the treated effluent. Adsorption is conducted through two primary methods: batch and column experiments. In batch adsorption, the adsorbent is dispersed in contaminated water with continuous agitation to establish equilibrium between the solid and liquid phases. Column adsorption consists of the continuous flow of contaminated water through a packed bed of adsorbent, a method frequently utilized in industrial applications owing to its operational efficiency and scalability. The physicochemical characteristics of the adsorbent and the existing operational conditions largely determine the efficacy of the adsorption process. An effective adsorbent must possess a high specific surface area, numerous active binding sites, structural stability, and selectivity for the target metal ion, regardless of competing contaminants. Furthermore, effective adsorbents must be economically viable, non-toxic, environmentally sustainable,

and able to undergo repeated regeneration and reuse with minimal performance degradation.¹⁷⁴

Nanoadsorbents utilize nanoscale dimensions along with modified surface chemistry, resulting in a considerably higher surface-to-volume ratio, enhanced density of active binding sites, and distinct physicochemical properties that can be modified for particular applications.¹⁸⁰ Researchers have investigated various nanomaterials for the adsorption of heavy metals, including carbon-based, zeolites, polymer-based, metal-based, silica, metal-organic frameworks (MOFs), and layered double hydroxides.^{174,180} The main adsorption mechanisms for these nanoadsorbents consist of surface complexation, ion exchange, electrostatic attraction, precipitation, and chelation, all of which may be affected by surface functionalization, particle morphology, and pore structure. Nanoscale engineering enables precise alterations in particle size, shape, and surface chemistry, thereby optimizing adsorption kinetics and capacity for specific heavy metals.^{176,180} Recent studies indicate that nanoadsorbents exhibit enhanced adsorption capacities, accelerated kinetics, and improved recyclability relative to traditional adsorbents, positioning them as a promising option for water and wastewater treatment. Table 7 provides a comprehensive overview of nanomaterials studied for heavy metal removal, and Fig. 16–21 display the characterization techniques utilized in recent research.

A comparative analysis of the nanoadsorbents listed in Table 7 reveals significant variability in adsorption performance. For instance, innovative electrospun polyvinyl alcohol nano zeolite nanocomposite nanofibers achieved an exceptionally high adsorption capacity of 838.7 mg g^{-1} for nickel(II) at 45°C and pH 5, outperforming traditional materials like carbon nanotubes, which showed a 96.03% removal efficiency. Similarly, magnetite nanorods demonstrated consistent high uptake across multiple metal ions, suggesting their versatility and robustness. However, materials like granular ferric oxide required much higher dosages (8000 mg L^{-1}) for moderate removal efficiency (66.99%), indicating lower cost-effectiveness. The structure-activity relationship is evident when comparing materials with high BET surface areas and functionalized surfaces. For example, copper oxide nanoparticles (Fig. 16) exhibited a BET surface area of $84.327 \text{ m}^2 \text{ g}^{-1}$, contributing to their high adsorption capacity of 15.625 mg g^{-1} for chromium(VI). Similarly, sulfonated magnetic graphene oxide composites exhibited enhanced adsorption due to the presence of sulfonic functional groups, despite a lower dosage. Zeta potential analysis (Fig. 20) further supports the role of surface charge in metal ion affinity, with materials exhibiting more negative zeta potentials at optimal pH showing better adsorption performance. While high-performance nanoadsorbents like maghemite nanoparticles functionalized with homopolymers show promising uptake values (e.g., 260.5 mg g^{-1} for silver(I)), their synthesis complexity and potential environmental risks (e.g., nanoparticle leaching) pose scalability challenges. Materials requiring extreme pH conditions (e.g., pH 2 for arsenic removal) may not be viable for large-scale systems. Moreover, regeneration efficiency varies widely; some polymer-based adsorbents retain performance over multiple cycles, while others degrade rapidly.



Table 6 Acceptable limits for toxic heavy metals and their adverse impact^{93,160,163,165,170,175-179}

Heavy metals	Drinking water		WHO for wastewater (ppb)	Negative effects
	USEPA (ppb)	WHO (ppb)		
Chromium	100	<50	50	Diarrhea, headache, and nausea. It impacts human physiology, bioaccumulates in the food chain, and leads to significant health issues, ranging from minor irritation of the skin to the development of lung cancer
Lead	15	<10	10	Damage to the central nervous system, the kidney, the liver, the reproduction system, fundamental cell processes, and the brain's functioning
Nickel	100	20-70	20	Toxic effects include anemia, insomnia, dizziness, headaches, irritation, muscular weakness, hallucinations, and renal damage. Conditions such as weight loss, eczema, and hair loss. Severe respiratory and renal issues, as well as liver and kidney damage, may lead to cancer in individuals; gastrointestinal discomfort, lung scarring, and skin inflammation
Copper	1300	<2000	1000	Damage to the liver and kidneys. Liver cirrhosis in individuals. Stomachache, anemia, vomiting, nausea, and headache in children. Overconsumption of copper may lead to severe toxicological issues, including symptoms such as vomiting, cramping, convulsions, and sometimes even death
Cadmium	5	3-5	3	Disorders affecting the muscles and skeletal system; irritate the respiratory system. Prolonged exposure to cadmium leads to renal failure, and excessive exposure may be fatal
Mercury	2	<6	50	Neurological effects include tiredness, headaches, tremors, hearing and cognitive impairment, and hallucinations
Zinc	5000	<3000	2000-5000	High mercury levels result in the deterioration of respiratory and renal function, which is accompanied by symptoms such as chest discomfort and difficulty breathing
Arsenic	10	<10	N/A	Diarrhea, vomiting, jaundice (yellowing of the mucous membranes), hematuria (presence of blood in the urine), anemia, renal failure, and hepatic failure. Abdominal pain and dermatological discomfort. Addiction may result in symptoms such as nausea and vomiting, reduced hematopoiesis, arrhythmia, and vascular damage. The individual has been diagnosed with cancer in the liver, kidneys, lungs, and bladder, as well as a skin lesion and visceral malignancies causing dermatitis

Engineering integration remains a bottleneck, especially for materials requiring long contact times or high dosages.

7.1 Carbon-based nanoadsorbents

Carbon-based nanomaterials have been shown to be very efficient adsorbents for the removal of heavy metals from polluted water, owing to their extremely high specific surface area, adjustable surface chemistry, mechanical strength, and strong adsorption affinity.^{212,213} Their nanoscale size provides a high density of active sites that may interact with heavy metal ions, including Pb^{2+} , Cr^{6+} , Cd^{2+} , Cu^{2+} , Hg^{2+} , and Ni^{2+} , *via* electrostatic attraction, ion exchange, surface complexation, and π - π interactions.^{212,214} In comparison to traditional adsorbents, carbon nanostructures provide enhanced performance due to their distinctive shape, elevated reactivity, and simple functionalization.²¹³

Carbon nanotubes (CNTs), graphene-based materials, fullerenes, and activated carbon are extensively researched. CNTs may be categorized as single-walled CNTs or multi-walled CNTs cylindrical hollow structures composed of rolled graphene sheets, may demonstrate theoretical specific surface areas of $2600 \text{ m}^2 \text{ g}^{-1}$; however, aggregation in aqueous environments can reduce this value.^{174,214} Functionalization with oxygen-containing ($-\text{OH}$, $-\text{COOH}$, $-\text{CO}$) or nitrogen ($-\text{NH}_2$) groups enhances dispersibility, stability, and metal-binding affinity. For instance, functionalized multi-walled CNTs demonstrated over 90% removal efficiency for Pb^{2+} and Cd^{2+} , while oxygenated single-walled CNTs reached over 95% removal of Hg^{2+} and As^{3+} . The reported adsorption capabilities for multi-walled CNTs are 88.62 mg g^{-1} for Cd^{2+} and 90.90 mg g^{-1} for Zn^{2+} under optimum situations.^{212,214} Graphene and its derivatives, especially graphene oxide, received considerable attention owing to their two-dimensional architecture, extensive surface area, and many oxygenated functional groups that enhance dispersion and adsorption in aqueous solutions.^{180,215} Graphene oxide interacts with heavy metal ions mostly *via* complexation at oxide binding sites, exhibiting capacities of 243.9 mg g^{-1} for Zn^{2+} (ref. 214) and 406.6 mg g^{-1} for Pb^{2+} .²¹⁵ Reduced graphene oxide provides significant adsorption capabilities while providing enhanced conductivity and stability. Fullerenes (e.g., C_{60} , C_{70}) are spherical carbon allotropes characterized by strong electron affinity, hydrophobic surfaces, and substantial surface-to-volume ratios, facilitating the adsorption of organic and inorganic pollutants. Research indicates the efficient adsorption of Cu^{2+} and other heavy metals, often according to the Langmuir isotherm, with improved efficacy when integrated into composites with activated carbon, lignin, or zeolites.^{215,216} Activated carbon is among the most prevalent carbon-based adsorbents, attributed to its highly developed porous architecture, extensive surface area, and comparatively inexpensive production cost from biomass. Activated carbon produced from eucalyptus bark, chicken litter, or rubberwood sawdust has adsorption capabilities that surpass those of most commercial coal-based activated carbons. Eucalyptus bark-derived activated carbon attained 0.45 mmol g^{-1} for Cu^{2+} and 0.53 mmol g^{-1} for

Pb^{2+} , while rubberwood sawdust-derived activated carbon obtained 44 mg g^{-1} for Cr^{6+} at pH 2.²¹⁵

In addition to pure carbon nanomaterials, carbon-based nanocomposites have developed as a promising category of adsorbents that combine carbon structures with functional nanoparticles, polymers, or metal oxides to improve adsorption capacity, selectivity, and regeneration potential. This encompasses composites of activated carbon, CNTs, graphene, or biochar combined with metal nanoparticles like zero-valent iron, silver, titanium dioxide, or manganese oxides. The combination enhances performance by offering additional reactive sites, promoting redox transformations, and increasing selectivity *via* functional groups such as $-\text{COOH}$, $-\text{OH}$, and $-\text{SO}_3\text{H}$. Zero-valent iron-carbon composites can transform $\text{Cr}(\text{vi})$ to the less hazardous $\text{Cr}(\text{iii})$, which subsequently precipitates from the solution.²¹² Numerous studies have proven the superior performance of these composites. Polyethyleneimine-functionalized multi-walled CNTs obtained 99% $\text{Cr}(\text{vi})$ removal (adsorption capacity of 40 mg g^{-1}) after 60 minutes at $\text{pH} < 4$ and maintained 80% efficiency after five reuse cycles. Polydopamine and polyethyleneimine-functionalized CNTs showed a copper ion (Cu^{2+}) adsorption capacity of 70.9 mg g^{-1} , while poly(amidoamine) dendrimer-modified CNTs attained remarkable capacities of 4870 mg g^{-1} for lead ions (Pb^{2+}) and 3333 mg g^{-1} for copper ions (Cu^{2+}) *via* metal-amine coordination.²¹⁴ CNT-based hybrids including TiO_2 and MnO_2 have capacities of 137 mg g^{-1} and 78.74 mg g^{-1} for Pb^{2+} , respectively.²¹⁵ Graphene oxide composites have improved performance; for instance, montmorillonite/graphene composites achieved 247.85 mg g^{-1} for Pb^{2+} .¹⁸⁰ Biochar-based composites, typically produced from biomass pyrolysis, provide a sustainable and economical option. The integration of iron or manganese oxides into biochar enhances heavy metal adsorption and promotes the reduction of hazardous metal species, making them suitable for extensive purposes. Chitosan–carbon nanocomposites have shown efficacy, attaining 54.6% heavy metal removal while being cost-effective and scalable.²¹²

Carbon-based adsorbents and their nanocomposites provide a diverse and high-performance alternative for heavy metal remediation in water. Although CNTs and graphene have exceptional adsorption capabilities, composites that include functional nanoparticles or polymers may further improve efficiency, selectivity, and regeneration potential. Outstanding issues include the prevention of nanoparticle leaching, the enhancement of large-scale recovery, and the reduction of manufacturing expenses. Continuous progress in economical synthesis, environmentally friendly functionalization, and hybrid material design is anticipated to enhance their utilization in sustainable water treatment systems.^{180,212,216}

7.2 Zeolite

Zeolites are crystalline microporous aluminosilicate characterized by a three-dimensional framework of SiO_4 and AlO_4 tetrahedra linked by shared oxygen atoms.^{217,218} The isomorphic substitution of Si^{4+} by Al^{4+} generates a net negative charge on the framework, which is balanced by exchangeable cations (e.g.,



Table 7 Experimental parameters and removal efficiency for the elimination of heavy metal ions using different nanoabsorbents^a

Adsorbent	Dose, milligrams per liter	Heavy metals	Initial concentration, milligrams per liter	Time, minute	pH	Temperature, °C	Adsorption capacity	
							% Milligrams per gram	Ref.
Magnetic nanoparticles coated mixed fungal biomass	700	Chromium(vi)	50	60	2	30	FT-IR, SEM, EDX	99.425 78 and 150
Copper(II) oxide nanoparticles	1600	Chromium(vi)	20	10	3	25	XRD, RS, FE-SEM, EDX, TEM, HR-TEM, BET, FT-IR, AAS, SAED	15.625 180 and 181
Magnetic multiwall carbon nanotubes	1000	Chromium(vi)	2	600	3	30	TEM, XRD	100 52 and 182
Chitosan-alginate nanoparticles	200	Mercury(II)	4	90	5	30	FT-IR, TEM, ZPA, SD, SEM, EDX	217.39 183
Zinc sulfide nanocrystals	2000	Mercury(II)	297.5	5	1-6	22.4-34.6	TEM, XRD, EDX, HR-TEM	99.99 52 and 184
Nickel oxide nanocatalyst	1000	Lead(II)	5	120	5.8	25	XRD, DTA, TGA, BET, FT-IR	100 175 and 185
Silicon dioxide/graphene composite	300	Lead(II)	20	60	6	25	UV-vis, FT-IR, XPS, XRD, SEM, BET	98.82 186 and 187
Copper ferrite nanoparticles	0.02	Lead(II)	10	120	4.5	25	BET, XRD, SEM, SQUID, ZFA	17.83 180 and 188
Carbon nanotubes	40	Lead(II)	540	80	5	25	EDX	96.03 176 and 189
Granular ferric oxide	8000	Arsenic(III)	30	49.99	5	25	SEM, FT-IR, pH _{pcz} (ZPA)	66.99 175 and 190
Magnetic nanoparticles coated with zeolite	500	Arsenic(III)	20	15	2.5	25 ± 1	TEM, EDX, FT-IR, XRD	95.6 191
Nano zero-valent iron	1000	Arsenic(III)	1	10	7	N/A	XRD, SEM	99.9 192
Magnetic	2000	Zinc(II)	10	90	5.5	25	SEM, EDX, XRD, FT-IR, VSM	95 156
Magnetic tubular carbon nanofibers	500	Copper(II)	50	10	6	30	FT-IR, TGA, XRD, BET, BJH, XPS, VSM, SEM, EDX, HR-TEM, AAS, HR-EDX	99.9 ± 0.1 78 and 193
Functionalized multiwalled carbon nanotubes	10	Copper(II)	20	60	3	25	FT-IR, XRD, SEM, TEM	93 118.41 175 and 194



Table 7 (Contd.)

Adsorbent	Dose, milligrams per liter	Heavy metals	Initial concentration, milligrams per liter	Time, minute	pH	Temperature, °C	Characterization	Adsorption capacity	
								%	Milligrams per gram
									Ref.
Carbon nanotube/calcium alginate composites	500	Copper(II)	5–40	120	5	20	SEM, BET, FT-IR	83.3	195
Mesoporous magnetite nanoparticles functionalized with amines	1000/3	Copper(II)	5	30	7	25	TEM, HR-TEM, XRD, RS, BET, BJH, VSM, FT-IR, SAED	~85	180 and 196
Sulfonated magnetic graphene oxide composite	18 ± 6.4	Copper(II)	73.71	180	4.68	50	TEM, EDX, PS, BET, TG-DTA, FT-IR, RS	62.73	186 and 197
Modified multiwalled carbon nanotubes	1200	Nickel(II)	50	0.6	6	N/A	RS, SEM, EDX, FT-IR, TGA	65	198
Multiwalled carbon nanotubes	500	Nickel(II)	10–80	900	7	25	BJH, BET, FT-IR	93.4	176 and 199
Maghemitite nanoparticles coated bacteria	N/A	Cadmium(II)	10	120	4	30	AAS, SEM, EDX	84.2	78 and 200
Hybrid polymeric nanocomposite	400	Cadmium(II) Zinc(II) Lead(II) Iron(II) Lead(II) Zinc(II) Nickel(II) Cadmium(II) Copper(II) Cadmium(II) Nickel(II) Cobalt(II)	25	1440	7	25	FT-IR, TGA, XRD, SEM, EDX, BET	72.36	45.22 and 52 and 201
Magnetite nanorods	1000	Iron(II) Lead(II) Zinc(II) Nickel(II) Cadmium(II) Copper(II) Cadmium(II) Nickel(II) Cobalt(II) Chromium(VI) Lead(II) Mercury(II)	50	60	5.5	25	SEM, TEM, XRD, BET	79.6	49.72 and 180 and 202
Milled goethite nanocrystalline	400	Zinc(II)	50	720	7 ± 0.2	25	XRD, TEM, VSM	99.88	127.01 and 112.86
Magnetic cobalt ferrite-reduced graphene oxide nanocomposites	160	Zinc(II)	100	120	5.5	30	XRD, BET, ZPA	99.45	99.89 and 99.75
Zinc oxide nanoparticles	140	Cadmium(II) Mercury(II) Lead(II)	20	80	5.3	25	XRD, SEM, EDX	87.5	107.27
Zinc(II)	5	60	4.6	25				89	132 and 203
Zinc(II)	0.5	Cadmium(II) Mercury(II) Lead(II)	35	5	25		UV-vis, FT-IR, SEM, XRD, VSM, AAS	91.5	41 and 205
Magnetic graphene oxide	16	Chromium(VI) Copper(II) Zinc(II) Nickel(II)	25	25				71.4	175 and 206



Table 7 (Contd.)

Adsorbent	Dose, milligrams per liter	Heavy metals	Initial concentration, milligrams per liter	Time, minute	pH	Temperature, °C	Characterization	Adsorption capacity		
								%	Milligrams per gram	Ref.
Innovative nanoadsorbent composed of electrospun polyvinyl alcohol nano zeolite nanocomposite nanofibers	500	Nickel(II) Cadmium(II)	10	60	5	45	FT-IR, SEM, BET, BJH, ICP-AES	90	838.7 342.8	180 and 207
Maghemic nanoparticles functionalized with homopolymers of a novel mercaptoethylamino monomer	1500	Cadmium(II) Mercury(II) Lead(II) Silver(I)	20	100	6	25	FT-IR, XRD, BET, TEM, pHpzC	91.5	91.5	180 and 208
Magnetic nanoparticles – hyperbranched polyglycerol	30	Nickel, aluminum, and copper Arsenic(V)	48	130	9	20	SV, TEM, DLS, XPS, XRD, FT-IR, VSM, ICP-AES	94	78 and 209	
Carbonate-based mesoporous magnetic	2000	Chromium(VI) Lead(II)	10	9	2	25	UV-vis, ICP-MS, UHR-FESEM, BET, BJH, XRD, FT-IR, XPS, FE- SEM, STEM, EDX	99.99	184.1 251.6	180 and 210
2,4-Dinitrophenylhydrazine-modified nano-alumina	1200	Lead(II) Cadmium(II) Nickel(II) Cobalt(II) Manganese(II) Chromium(III)	50	90	5	25 ± 1	FT-IR, SEM, EDX, BET, XRD, AAS	97.25 74.17 36.26 53.29 10.98 91.76	41 and 1041.9	

^a AAS = Atomic Absorption Spectrometry; BET = Brunauer-Emmett-Teller; BJH = Barrett-Joyner-Halenda; DLS = Dynamic Light Scattering; DTA = Differential Thermal Analysis; EDX = Energy Dispersive X-ray; FE-SEM = Field Emission Scanning Electron Microscopy; FT-IR = Fourier Transform Infrared Spectroscopy; HR-EDX = High-Resolution Energy Dispersive X-ray; HR-TEM = High-Resolution Transmission Electron Microscopy; ICP-AES = Inductively Coupled Plasma Atomic Emission Spectroscopy; ICP-MS = Inductively Coupled Plasma Mass Spectrometry; pHpzC = point of zero charge; PS = Particles Size; RS = Raman Spectroscopy; SAED = Selected Area Electron Diffraction; SD = Size Distribution; SEM = Scanning Electron Microscope; STEM = Scanning Transmission Electron Microscopy; SV = Settling Velocity; SQUID = Superconducting Quantum Interference Device; TEM = Transmission Electron Microscopy; TGA = Thermogravimetric Analysis; TG-DTA = thermogravimetric-differential thermal analysis; UHR-FESEM = Superconducting Quantum Interference Device; Effect Scanning Electron Microscope; UV-vis = ultraviolet-visible spectrophotometer; VSM = Vibrating-Sample Magnetometry; XPS = X-ray Photoelectron Spectroscopy; XRD = X-ray Diffraction; ZPA = Zeta Potential Analyzer.




Fig. 16 Characterization of copper oxide nanoparticles using (a) FE-SEM, (b) EDX, (c) TEM micrograph with inset displaying the SAED pattern, (d) HR-TEM, (e) XRD, (f) RS, (g) FT-IR, and (h) BET. Adapted from ref. 181 with permission from Elsevier, copyright 2016.

Na^+ , K^+ , Ca^{2+}) located within the well-defined channels and cages. This unique structure underpins their high cation exchange capacity (CEC), molecular sieving ability, and

reversible dehydration, making them highly effective adsorbents.^{62,215,217} Naturally occurring zeolites such as clinoptilolite and chabazite are widely used in water treatment due to their

abundance, low cost, ecological sustainability, and inherent selectivity for heavy metals like Pb^{2+} , Cd^{2+} , and Cu^{2+} .²¹⁵⁻²¹⁷

The primary mechanism for heavy metal removal is ion exchange, in which aqueous metal ions replace charge-balancing cations in the zeolite framework. This process is complemented by surface complexation and physical adsorption within the porous network.^{213,215,219} The adsorption capacity is strongly influenced by the Si/Al ratio, which determines hydrophobicity, acidity, and stability. Low-silica zeolites (Si/Al < 2) are hydrophilic, while high-silica zeolites (Si/Al > 5) exhibit greater thermal stability and resistance to chemical attack.²¹⁷ However, structural stability remains a limitation; the aluminosilicate framework is susceptible to dealumination under acidic conditions, leading to crystalline collapse, loss of porosity, and permanent reduction in adsorption capacity.²¹⁹

This acid sensitivity can limit their use in treating acidic waste streams without pre-neutralization. Furthermore, the presence of mineral impurities in natural zeolites can reduce their effective surface area and cation exchange capacity, while their performance is also highly dependent on solution pH, which affects both surface charge and metal speciation.^{219,220}

To overcome these limitations and enhance performance, several modification strategies have been developed. Chemical treatments with acidic, bases, or salt solutions (e.g., NaCl) can remove impurities, alter the Si/Al ratio, and enhance ion-exchange capacity.²¹⁹ Nano-structuring zeolites increases the surface-area-to-volume ratio, reduces diffusion path lengths, and improves adsorption kinetics and capacity for heavy metals.^{62,180,215} NaX nanosized zeolite has been extensively used for the removal of Cd^{2+} , exhibiting enhanced efficacy relative to




Fig. 17 Physicochemical properties of chitosan-alginate nanoparticles: (a and b) hydrodynamic size distribution and (c and d) zeta potential before and after adsorption. Adapted from ref. 183 with permission from Elsevier, copyright 2016.




Fig. 18 Thermal characterization of zinc sulfide nanocrystals: TGA and DTA. Adapted from ref. 185 with permission from Elsevier, copyright 2015.






Fig. 19 UV-Vis spectra and surface textural properties of silicon dioxide/graphene composite: using various techniques: (a) and (b) UV-Vis absorbance of graphene oxide and silicon dioxide/graphene composite showing a blueshift upon composite formation and (c) BET analysis and pore size distribution (BJH) for silicon dioxide/graphene composite. Adapted from ref. 187 with permission from Elsevier, copyright 2012.

bulk zeolite.²¹⁵ Functionalization with nanoparticles or specific groups significantly improve adsorption performance.^{212,213} Magnetic zeolite nanocomposites (e.g., Fe-zeolite) integrate the substantial adsorption capacity of zeolites with the magnetic separation properties of iron oxide, facilitating the effective elimination of Pb^{2+} , Cd^{2+} , and As^{3+} . Manganese-zeolite composites enhance redox characteristics, enabling the reduction of poisonous Cr^{6+} to less dangerous Cr^{3+} , subsequently followed by adsorption. Copper-zeolite composites enhance surface reactivity and form stable complexes with Hg^{2+} , and Pb^{2+} .²¹² Ag-modified zeolites release Ag^+ ions, providing anti-bacterial characteristics while maintaining heavy metal adsorption capability.⁶²

Regeneration is essential for sustainable application of zeolites. Chemical regeneration with dilute acids or salts may replenish ion-exchange sites while maintaining structural integrity, enabling repeated application over several adsorption-desorption cycles. However, acid regeneration must be carefully controlled to avoid structural degradation through dealumination.^{212,219} When properly regenerated, zeolites retain




Fig. 20 Surface and magnetic properties of copper ferrite nanoparticles: (a) pH-dependent zeta potential analysis, and (b) magnetization curves (VSM). Adapted from ref. 188 with permission from Elsevier, copyright 2017.




Fig. 21 Effect on settling velocity of magnetic nanoparticles grafted on hyperbranched polyglycerol, demonstrating their pH-responsive colloidal stability and aggregation behavior in aqueous media. Adapted from ref. 209 with permission from Elsevier, copyright 2020.

high efficiencies across multiple cycles, making them suitable for continuous industrial applications. Under optimized conditions, natural zeolites have achieved up to 99% removal of Cu^{2+} at neutral pH, underscoring their practical potential for cost-effective and sustainable water purification.^{212,216}

7.3 Metal-based nanoparticles

Metal-based nanoparticles have shown to be very efficient materials for eliminating of heavy metals and other pollutants



from water and wastewater owing to their elevated surface-to-volume ratio, increased reactivity, and adjustable surface chemistry.²¹² Their small particle size provides many active sites for adsorption, ion exchange, and catalytic processes, while their physicochemical characteristics may be modified using synthesis methods such as chemical reduction, green synthesis, and surface functionalization.^{212,213} Iron-based and silver nanoparticles are the most thoroughly researched and used in the treatment of water and wastewater for the removal of heavy metals. The adsorption mechanisms of metal-based nanoparticles are primarily governed by the physicochemical properties of the metal oxide, the nature of surface functional groups, and the specific characteristics of the target ions. Typical removal pathways include adsorption, ion exchange, surface complexation with hydroxyl or oxygenated groups, co-precipitation, redox reactions, and electrostatic attraction. In semiconductor oxides such as TiO_2 , ZnO , and CeO_2 , photocatalytic reduction and oxidation can also contribute significantly to metal ion immobilization. For instance, MgO , Al_2O_3 , and TiO_2 nanoparticles exhibit adsorption capacities of approximately 594.9, 114.6, and 49.4 mg g⁻¹ for Cd^{2+} , Cu^{2+} , Ni^{2+} , and Pb^{2+} in multicomponent systems, with MgO acting mainly through precipitation and adsorption, whereas TiO_2 and Al_2O_3 primarily operate *via* surface adsorption and complexation mechanisms.²²¹

Nanoscale zero-valent iron (nZVI) has been extensively studied for its efficacy in eliminating harmful heavy metals, include Cr(vi), Cd(II), Cu(II), Hg(II), Ni(II), and Pb(II), from polluted water. Their removal methods including adsorption, electrostatic attraction, redox transformations, co-precipitation, and surface complexation.²¹² nZVI generally displays a core-shell structure, including a zero-valent iron core surrounded by an oxide shell that contains Fe(II) and Fe(III) species. The metallic core functions as an effective reducing agent, capable of converting more hazardous species (e.g., Cr(vi)) into less dangerous forms (e.g., Cr(III)), while the oxide shell offers reactive sites for adsorption.²¹³ Research has shown the remarkable efficacy of iron-based nanoadsorbents in both batch and continuous systems, as well as *in situ* groundwater remediation. Biochar-supported nZVI has improved adsorption capability and dispersion, while green-synthesized iron nanoparticles derived from tea extract have effectively treated acid mine drainage *via* adsorption, reduction, and co-precipitation.²¹² Moreover, iron oxide nanoparticles, including magnetite (Fe_3O_4), maghemite ($\gamma\text{-Fe}_3\text{O}_4$), hematite ($\alpha\text{-Fe}_3\text{O}_4$), goethite ($\alpha\text{-FeOOH}$), and amorphous hydrous iron oxides, have been widely used for the removal of heavy metals owing to their cost-effectiveness, magnetic recoverability, and environmental compatibility.^{214,216} Surface modification is crucial for improving the dispersion, stability, and selectivity of iron nanoparticles. Functional groups such as $-\text{NH}_2$ and $-\text{COOH}$ may enhance their chelation capacity and adsorption efficacy. For instance, $-\text{NH}_2$ -functionalized Fe_3O_4 nanoparticles eliminated 97.94% of Cr(vi) and 98.56% of Ni(II) from 1 ppm tap water, exhibiting maximal adsorption capacities of 222.12 and 232.15 mg g⁻¹, respectively. Also, $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{NH}_2$ composites attained maximum removal of Zn(II) from industrial pickling

waste, exhibiting an adsorption capacity of 169.5 mg g⁻¹.²¹⁴ In a separate investigation, $\text{Fe}_3\text{O}_4@\text{SiO}_2@\text{carboxyl-PAMAM}$ nanocomposites exhibited adsorption capacities of 117.0, 119.16, and 115.82 mg g⁻¹ for Pb(II), Cu(II), and Cd(II), respectively, achieving removal efficiencies above 96%.²²² The magnetic properties of these materials enable straightforward separation and reutilization, enhancing their economic and environmental sustainability.⁶²

Silver nanoparticles (Ag NPs) represent a significant category of metal-based nanoparticles, offering dual advantages in water purification: adsorption of heavy metals and antibacterial properties.^{212,213} Ag NPs have significant bactericidal characteristics *via* the production of Ag^+ ions, which interfere with cellular activities in microorganisms, making them effective for the simultaneous elimination of infections and chemical pollutants.²¹² Their small dimensions and elevated surface area promote effective binding of hazardous metal ions, including Hg(II), Cu(II), Cd(II), and Pb(II).^{213,216} Multiple studies have shown the efficacy of Ag NPs in eliminating harmful metals from water and wastewater. Silver nanoparticles developed from microalgae and cyanobacteria extracts have shown efficient removal of iron and manganese ions.²¹² In a research study, Ag NPs exhibited a maximum Cu(II) adsorption capacity of 25.25 mg g⁻¹, while another investigation revealed a Cd(II) capacity of 19.6 mg g⁻¹. Nanocomposites based on Ag NPs have been produced to improve performance; for instance, Ag NPs combined with quartz using a sol-gel process eliminated almost 96% of Hg(II) after 60 minutes at pH 6, conforming to the Langmuir isotherm and pseudo-second-order kinetics.²¹⁶ In addition to adsorption, Ag NPs have been integrated into multifunctional membranes for simultaneous pollutant elimination and antibacterial efficacy. A bio-nanomembrane consisting of graphene oxide, natural rosin, Ag NPs, and a chitosan/PVA matrix demonstrated enhanced tensile strength, antibacterial characteristics, and heavy metal adsorption capabilities.²¹² Although Ag NPs are often considered low in toxicity relative to several other metals, concerns over their possible environmental discharge and accumulation persist, hence requiring regulated application and recovery techniques.⁶²

In conclusion, metal-based nanoparticles, specifically iron and silver nanostructures, exhibit elevated adsorption capabilities, adjustable reactivity, and multifunctionality for eliminating of heavy metals and related contaminants from water and wastewater. Iron-based nanoparticles demonstrate superiority in redox-mediated detoxification and magnetic recoverability, whereas Ag NPs provide combination antibacterial and adsorption properties. Ongoing progress in surface functionalization, composite development, and eco-friendly synthesis is anticipated to enhance their efficacy, durability, and sustainability in practical water treatment applications.^{212-214,216,222}

7.4 Silica nanomaterials

Silica nanoparticles (SiO_2) are esteemed for their non-toxic nature, extensive surface area, exceptional chemical and thermal stability, mechanical strength, and easy surface functionalization, rendering them viable options for eliminating of



heavy metals from aqueous environments.^{212,214,216,223} Their three-dimensional porous structure promotes fast mass transfer, while the plentiful surface silanol (Si-OH) groups serve as active adsorption sites, facilitating chelation and complexation with metal ions.^{214,216} The qualities have been further used in the formation of silica/metal nanocomposites, which integrate the adsorption, ion-exchange, and redox characteristics of metal nanoparticles with the structural stability and dispersibility afforded by the silica matrix.²¹² Silica/metal nanocomposites have significant efficacy in the removal of diverse hazardous metal ions. Iron-silica nanocomposites successfully eliminate arsenic (As³⁺) and lead (Pb²⁺), with iron component offering reactive adsorption and reduction sites, while the silica framework enhances nanoparticle dispersion and inhibits agglomeration. Manganese-silica nanocomposites may similarly decrease hazardous chromium (Cr⁶⁺) to less detrimental Cr³⁺ state, subsequently followed by adsorption. Copper-silica nanocomposites have a strong affinity for mercury (Hg²⁺) and cadmium (Cd²⁺) by active adsorption and surface complexation.²¹² The addition of silica improves the reactivity and durability of these composites while preventing metal nanoparticles against leaching, particularly in low pH environments.²¹⁶

The dominant mechanisms governing metal uptake typically include precipitation, electrostatic attraction, cation exchange, and surface complexation. Precipitation occurs through the formation of insoluble hydroxides or silicates on or within the silica surface, while electrostatic attraction depends on pH relative to the point of zero charge (pHpzc), where negatively charged silica surfaces favor cation adsorption. Cation exchange involves the replacement of surface-bound alkali or alkaline earth metals (e.g., Na⁺, Ca²⁺) with target metal ions, and surface complexation results from the coordination of metal ions with oxygenated functional groups such as hydroxyl or carboxyl groups. Among these, precipitation and electrostatic attraction are often predominant in fabricated nano SiO₂ systems, while surface complexation becomes significant in functionalized or hybrid silica materials.²²⁴ Surface functionalization of silica nanoparticles provides an efficient approach to enhance the adsorption capacity for heavy metals. Amin (-NH₂), thiol (-SH), phosphonate, carboxyl (-COOH), poly(ethylene glycol), and long-chain alkyl groups have been grafted onto silica surfaces to provide particular binding sites and decrease aggregation in aqueous solutions.²¹⁴ Ethylenediaminetetraacetic acid (EDTA)-functionalized silica adsorbents had a remarkable Pb²⁺ removal capability of 1.51 mol Pb²⁺ per mol adsorbent, exceeding previous functionalized variations due to their elevated metal ion affinity and geometric flexibility.²¹⁶ These functional modifications substantially improve adsorption capacity by enhancing the quantity and strength of binding sites.

Experimental investigations have validated the superior efficacy of silica nanoparticles in the removal of heavy metals. Bar silica nanoparticles attained a 99.5% removal of Zn²⁺ from electrically enhanced membrane bioreactor effluents in 4 hours at pH 8.2, exhibiting an adsorption capability of 9.1 mg g⁻¹ as per the Langmuir model. In another instance, mesoporous silica-calcium phosphate nanocomposites, synthesized by

a one-spot technique, exhibited a surface area of 314.56 m² g⁻¹ and a particle size of around 20 nm, successfully eliminating 99.65% of Cd²⁺ within 30 minutes at pH 6, reaching an adsorption capacity of 125.63 mg g⁻¹. The composite maintained around 80% of its removal effectiveness after three adsorption-desorption cycles, demonstrating excellent reusability.²¹⁴ Notwithstanding their superior adsorption characteristics, silica nanoparticles have an affinity to agglomerate in aqueous environments, therefore reducing their effective surface area and limiting large-scale utilization.²¹⁴ This problem may be minimized by integrating silica into nanocomposite structures or implementing surface modifications to enhance dispersion stability. Silica nanoparticles and their composites provide a diverse and highly adaptable platform for the efficient elimination of hazardous heavy metals from water. Further study into functionalization techniques, composite fabrication, and regeneration processes is expected to improve their efficacy and facilitate their implementation in sustainable wastewater treatment systems.^{212,214,216}

7.5 Polymer-based nanoadsorbents

Polymer-based nanoadsorbents have developed as a diverse and efficient category of materials for the elimination of heavy metals and other pollutants from water and wastewater. These nanocomposites combine the benefits of a polymer matrix, such as mechanical stability, flexibility, and adjustable surface chemistry, with the increased reactivity and extensive surface area of nanoparticles, resulting in synergistic adsorption performance that individual components cannot achieve.²¹² Commonly utilized nanoparticles encompass titanium dioxide (TiO₂), zinc oxide (ZnO), silver (Ag), magnetite (Fe₃O₄), and various metal or metal oxide nanomaterials, which provides numerous active sites for adsorption, catalytic activity, and in certain instances, photocatalytic degradation, while the polymer matrix ensures structural integrity and promotes the dispersion of nanoparticles.^{212,216}

Synthetic and natural polymers have been extensively investigated in polymer-based nanocomposites. Synthetic polymers, including polystyrene (PS), polyaniline (PANI), polyethylene, and polyvinyl alcohol (PVA), are widely recognized for their chemical resilience, processability, and adjustable functionalization capabilities.²¹⁶ Natural polymers, especially biopolymers like chitosan, cellulose, and alginate, have become popular due to their biocompatibility, biodegradability, and the presence of many functional groups that may bind metal ions. Chitosan, obtained from the deacetylation of chitin (a byproduct of shellfish processing), has amino groups capable of chelating metal ions *via* coordination, ion exchange, and electrostatic attraction. Chitosan's pH sensitivity and restricted mechanical strength are often mitigated by chemical modification or the integration of nanoparticles. Chitosan/magnetite nanocomposites efficiently eliminate Pb²⁺, Cd²⁺, and Cr(vi), offering the benefit of magnetic recovery, while chitosan/silver nanocomposites integrate heavy metal removal with antibacterial properties.^{180,212} Cellulose-based nanocomposites, using renewable resources and hydroxyl functionalities, have been



modified with iron oxide or silver nanoparticles to improve mechanical characteristics and adsorption efficacy for As^{3+} , Hg^{2+} , Pb^{2+} , and microbiological pollutants.^{212,216}

Polymer-based nanocomposites including dendrimer-based adsorbents, characterized by highly branched, monodisperse macromolecules including many terminal functional groups. These dendrimers can chelate heavy metals *via* the outer branches and absorb organic contaminants *via* hydrophobic cavities. Research demonstrated that dendrimer-assisted ultrafiltration effectively eliminated Cu^{2+} ions from aqueous solution, underscoring its potential in integrated treatment techniques. Despite their extraordinary efficacy, dendrimers undergo obstacles in large-scale implementation owing to their complicated and expensive manufacturing.⁶² Additional polymer nanocomposite systems are clay/polymer/metal hybrids, whereby layered clays like montmorillonite or kaolinite are intercalated with nanoparticles (e.g., Fe, Zn, TiO_2). These composites use clay's high cation exchange capacity and surface area, in combination with nanoparticles reactivity, to eliminate heavy metals *via* adsorption, ion exchange, reduction, and complexation. Iron-clay nanocomposites have been reported to decrease Cr(vi) to Cr(III) while adsorbing Pb^{2+} and As^{3+} , while Zn-clay composites have a strong affinity for Cd^{2+} and Pb^{2+} .²¹²

Polymer-based nanoadsorbents function *via* many processes, such as surface complexation, ion exchange, electrostatic attraction, chelation, and, in some instances, photocatalytic degradation when photoactive nanoparticles are included.^{180,212} Their adsorption performance is affected by variables like pH, contact duration, nanoparticle loading, polymer modification, and the existence of competing ions. These materials have shown superior performance in both batch and continuous flow systems, often reaching high removal efficiencies for Pb^{2+} , Hg^{2+} , Cd^{2+} , and As^{3+} .^{212,216} Furthermore, their regenerative capability *via* simple desorption techniques increases their cost-effectiveness and sustainability. Nano chitosan synthesized by polymerization with malonic acid had a maximal Pb^{2+} adsorption capacity of 32.2 mg g^{-1} at pH 6, conforming to the Langmuir isotherm and pseudo-second-order kinetics, while maintaining efficiency throughout several cycles.²¹⁶ Polymer-based nanoadsorbents provide a viable platform for enhanced water remediation, integrating the functionality of customized polymer matrices with the high reactivity of nanomaterials. Current research aims to develop "smart" polymer nanocomposites that may react to environmental stimuli, increase selectivity for target pollutants, and improve reusability, thereby facilitating their use in sustainable heavy metal removal methods.^{180,212,216}

7.6 MOF nanocomposites

Metal-organic frameworks (MOFs) are an innovative class of porous crystalline materials constructed from metal ions or clusters coordinated with organic ligands. They form extensive two- or three-dimensional networks characterized by exceptionally high surface area (typically $1000\text{--}10\,000 \text{ m}^2 \text{ g}^{-1}$), high porosity, tunable pore architectures.^{174,225,226} This versatility allows precise manipulation of pore geometry, surface

functionality, and chemical environments, enabling selective adsorption of heavy metal ions through mechanisms such as coordination bonding, electrostatic interactions, surface complexation, and π - π interactions.^{174,212} MOFs can be classified as cationic, neutral, anionic, and bioMOFs, with charged frameworks incorporating counter-ions within pore channels to maintain electroneutrality. A wide range of metals, including Cu(II), Al(III), Mg(II), Ca(II), Fe(III), Cd(II), Co(II), Zn(II), Zr(IV), Ti(IV), and lanthanides, have been employed as framework nodes, coordinated with organic linkers such as carboxylates, phosphonates, sulfonates, or amines. To date, over 20 000 MOF structures have been synthesized and investigated for applications in gas storage, catalysis, and environmental remediation.¹⁷⁴

While pristine MOFs demonstrate remarkable heavy metal removal capacity, their performance can be further enhanced by developing MOF-based nanocomposites with functional nanoparticles or polymers. For example, ZnO/MOF composites synergistically integrate the increased porosity and surface area of MOFs with photocatalytic and antibacterial properties of ZnO nanoparticles, facilitating simultaneous adsorption and elimination of metal-laden contaminants. ZnO/MOF nanocomposites exhibit rapid and effective adsorption of Cd^{2+} , Pb^{2+} , and Hg^{2+} ions, exceeding the performance of the individual constituents. Similarly, CuO/MOF composites utilize the reactive characteristics of CuO nanoparticles to enhance heavy metal binding and facilitate catalytic removal.²¹² Magnetic MOF nanocomposites have attracted particular attention for their efficient removal easy recovery of heavy metal-laden adsorbents. For instance, a polyacrylic acid-capped Fe_3O_4 -Cu-MOF hybrid demonstrated outstanding selectivity for Pb^{2+} , with an adsorption capacity of 610 mg g^{-1} and 93% removal efficiency in aqueous systems.¹⁷⁴ The incorporation of metal nanoparticles into MOF not only enhances structural stability and prevents aggregation, but also introduces additional active binding sites, collectively improving adsorption efficacy.²¹² MOFs and MOF-derived nanocomposites have been successfully employed to remove hazardous metals including As(III), As(V), Cr(VI), Cd(II), Ni(II), Pb(II), and Hg(II).^{174,212} Compared with conventional adsorbents such as activated carbon, zeolites, and metal oxides, they offer superior adsorption capacities, higher tunability, and better selectivity under competitive multi-ion conditions. Several pilot-scale studies highlight their potential: ethylenediamine-functionalized Zr-based MOFs achieved adsorption capacities up to 243.9 mg g^{-1} for Pb^{2+} , Cu^{2+} , and Cd^{2+} , while polypyrrole/aluminum fumarate MOF composites demonstrated nearly complete Pb^{2+} removal across a broad pH range.^{174,225,227} These findings underscore MOF-based nanocomposites as promising next-generation adsorbents for water treatment.

Despite these advances, several challenges hinder the transition of MOFs from laboratory demonstrations to large-scale applications. Economic feasibility is a primary concern, as MOF synthesis often requires costly high-purity linkers and metal precursors, along with energy-intensive solvothermal processes, making them more expensive than traditional adsorbents. To overcome this, researchers are exploring greener



and scalable synthesis methods such as mechanochemical, microwave-assisted, and solvent-free routes, which can lower and reduce environmental impact.²²⁵ Structural stability in real wastewater systems presents another barrier. While some frameworks exhibit good hydrothermal stability, many MOFs degrade under strongly acidic or alkaline conditions, potentially leading to framework collapse and release of toxic metal nodes (e.g., Cd, Cr, Co, Ag) or harmful organic linkers (e.g. 4,4'-bipyridine, pyrazine) during. The presence of competing ions and natural organic matter further reduces efficiency and lifespan. Addressing these issues requires the use of robust frameworks with strong metal-ligand bonds (e.g., Zr-based MOFs) and the development of hybrid composites that improve structural integrity.^{174,225} Process engineering considerations also limit practical applications. Fine MOF powders, though effective in batch adsorption, are unsuitable for continuous-flow systems due to high pressure drops and potential material loss. Thus, MOFs must be formulated into pellets, granules, or membranes, but these processes often reduce accessible active sites. In addition, regeneration efficiency varies widely among frameworks, and large-scale production still requires substantial solvent and energy input, raising sustainability concerns.^{225–229} Nevertheless, research progress is steadily bridging the gap between laboratory innovation and industrial application. The development of more stable and cost-effective MOFs, combined with greener synthesis methods and improved

formulation strategies, suggests a promising future for these materials in sustainable water treatment. Furthermore, integration with complementary technologies could further enhance their applicability.^{174,212,225,227}

7.7 Layered double hydroxide-based adsorbents

Layered double hydroxides (LDHs) are two-dimensional anionic clays composed of positively charged brucite-like layers of divalent and trivalent metal cations, intercalated with water molecules and exchangeable anions. Their lamellar architecture provides adjustable interlayer spacing, high surface area, and significant anion exchange capacity, making them especially effective for adsorption of heavy metal cations. LDHs can be synthesized by cost-effective methods including co-precipitation, hydrothermal treatment, ion exchange, urea hydrolysis, or structure reconstruction, offering flexibility in composition and crystallinity.^{230–232} Pristine LDHs already display respectable adsorption capacities, but surface modification, composite formation, intercalation with functional ligands, defect engineering, and hybridization with materials such as biochar, graphene oxide, carbon nanomaterials, Fe_3O_4 , or polymers significantly enhance their efficacy. For example, an LDH/biochar composite using orange peel biochar exhibited a $\text{Cu}(\text{II})$ adsorption capacity of $\sim 68 \text{ mg g}^{-1}$, outperforming CNT-modified LDHs ($\sim 44 \text{ mg g}^{-1}$) and unmodified ZnFe-LDHs ($\sim 25 \text{ mg g}^{-1}$), primarily due to greater surface area and

Table 8 Comparative performance of representative nanoadsorbents for heavy metal removal

Adsorbent	Heavy metal	Adsorption capacity (mg g^{-1})	pH	T (K)	Regeneration cycles	Kinetic parameters	Ref.
Ag–Fe MOF	$\text{Cd}(\text{II})$	265 – Langmuir	7	298	5	PSO – $K_2 = 0.000870$	234
	$\text{Cu}(\text{II})$	213 – Langmuir	5			PSO – $K_2 = 0.002220$	
CoMnMOF-74	As	531 – Langmuir	11	298	4	PSO – $K_2 = 0.01058$	235
	$\text{Pb}(\text{II})$	229.2 – Langmuir	6	303	4	PSO – $K_2 = 0.000166$	
Polyaspartic acid-LDH	$\text{Hg}(\text{II})$	208.6 – Langmuir	4			PSO – $K_2 = 0.000133$	232
	$\text{Ni}(\text{II})$	13.2 – Langmuir	5.5	298	4	PSO – $K_2 = 0.033$	
Fe ₃ O ₄ /cyclodextrin polymer	$\text{Cd}(\text{II})$	27.70 – Langmuir				PSO – $K_2 = 0.016$	236
	$\text{Pb}(\text{II})$	64.50 – Langmuir				PSO – $K_2 = 0.003$	
Polypyrrole–polyethyleneimine	$\text{Pb}(\text{II})$	75.60 – Langmuir	10	323	5	PSO – $K_2 = 0.031$	237
	$\text{Pb}(\text{II})$	91.34 – Freundlich	6	318	NR	NR	
Surfactant/nano zeolite	$\text{Cu}(\text{II})$	85.71 – Freundlich				NR	238
	$\text{Cd}(\text{II})$	78.27 – Langmuir				NR	
Magnetic nano zeolite	$\text{Ni}(\text{II})$	76.18 – Freundlich				NR	239
	$\text{Zn}(\text{II})$	67.41 – Freundlich				NR	
Graphene oxide–starch	$\text{Fe}(\text{II})$	63.45 – Freundlich				NR	240
	$\text{Cu}(\text{II})$	59.9 – Langmuir	7	298	NR	PSO – $K_2 = 0.000179$	
Activated carbon	$\text{Cd}(\text{II})$	188.6 – Langmuir				PSO – $K_2 = 0.000072$	241
	$\text{Pb}(\text{II})$	476.1 – Langmuir				PSO – $K_2 = 0.000024$	
nZVI	$\text{Cu}(\text{II})$	542.01 – Freundlich	8	283	3	PSO – $K_2 = 0.0.0206$	242
	$\text{Ni}(\text{II})$	19.19 – Langmuir	12	313	NR	PSO – $K_2 = 0.0.00265$	
Silver nanoparticles and magnetic nanoparticles/nanocomposites	$\text{Cr}(\text{VI})$	47.42 – Langmuir	2	310	NR	PSO – $K_2 = 0.0.000152$	243
	$\text{Cu}(\text{II})$	78.38 – Freundlich	5	303	6	PSO – $K_2 = 0.0.0000103$	
Nano SiO ₂	$\text{Pb}(\text{II})$	23.75 – Langmuir	5	298	3	PSO – $K_2 = 0.0387$	243
	$\text{Ni}(\text{II})$	12.38 – Langmuir	6			PSO – $K_2 = 0.0051$	
Silver nanoparticles and magnetic nanoparticles/nanocomposites	$\text{Cu}(\text{II})$	18.57 – Langmuir				PSO – $K_2 = 0.0094$	243
	$\text{Cd}(\text{II})$	8.71 – Langmuir				PSO – $K_2 = 0.0039$	
Nano SiO ₂	$\text{Pb}(\text{II})$	117.74 – Freundlich	5	298	6	PSO – $K_2 = 0.015$	224
	$\text{Cr}(\text{VI})$	51.42 – Freundlich	2			PSO – $K_2 = 0.008$	



abundance of binding sites. In another study, CaAl-LDHs achieved particularly high capacities ($\sim 592 \text{ mg g}^{-1}$ for Cd(II)) under optimized conditions, highlighting the potential of functionalized LDHs for heavy metal removal in highly contaminated waters. The adsorption mechanism in LDHs involves ion exchange (replacement of interlayer anions by heavy metal ions), electrostatic attraction, surface complexation and, in some cases, chelation with functional ligands. Defects in the LDH layers, such as oxygen vacancies, and substitution of metal cations (e.g., replacing M^{2+} or M^{3+} with metals of different ionic sizes) can influence the chemical reactivity and significantly enhance ion exchange and binding efficiency. Intercalation of anions and functional molecules into interlayer gallery, surface functionalization, and defect engineering are effective strategies to introduce binding affinity, expand adsorption sites, and improve adsorption kinetics.^{174,230}

Despite these advances, LDH-based adsorbents face important limitations when considering practical, large-scale applications. Key challenges include structural instability under extreme pH conditions (strongly acidic or alkaline), loss of crystallinity, aggregation of particles, and decreased performance in the presence of competing ions or natural organic matter. Additionally, functional ligands or intercalated anions can leach out or degrade over repeated cycles, reducing long-term stability. Synthesis methods involving surfactants or sacrificial templates may introduce toxicity or require multi-step, energy-intensive processes. The trade-off between material performance (capacity, rate) and synthesis complexity or cost remains a critical issue.^{230,233} To improve applicability, recent studies suggest multiple strategies: designing defect-rich LDHs with robust metal–cation frameworks, using benign intercalated anions or environmentally safe ligands, hybridizing LDHs with stable supports (e.g., biochar, polymer matrices) to prevent aggregation and facilitate separation, and optimizing regeneration protocols (e.g., mild acids, bases, or

chelating agents) to preserve structural integrity. Some hybrid LDH composites have shown excellent regeneration capability, maintaining a high proportion of their adsorption capacity after several cycles.^{174,231,232} Overall, LDHs remain one of the most promising adsorbent families for heavy metal removal due to their tunable structure, abundant binding sites, and versatility. Nonetheless, future research must rigorously address their stability, regeneration efficiency, scale-up synthesis, and performance under real wastewater conditions to bridge the gap between lab-scale demonstrations and sustainable industrial applications.

A comparative summary of adsorption capacities, optimum operating conditions, regeneration cycles, and kinetic parameters of representative nanoadsorbents is presented in Table 8, highlighting the relative performance of different material categories.

8. Recycling and regeneration of nanoadsorbents

The economic feasibility and environmental sustainability of nanoadsorbent-based water treatment technologies are fundamentally determined by their ability to be regenerated and reused effectively. Reusability is defined as the capacity of an adsorbent to retain its structural integrity and adsorption efficiency after several adsorption–desorption cycles, thus minimizing material waste and operational costs while enhancing environmental compatibility.^{62,244–249} Despite the promising adsorption capabilities and surface functionalities exhibited by various nanoadsorbents, their large-scale application remains hindered by challenges associated with recyclability, structural deterioration, and declining performance upon repeated use. One of the foremost operational challenges in nanoadsorbent recycling is the efficient separation and recovery of nanosized particles from treated effluents. The extremely small particle




Fig. 22 End-of-life management of nanomaterials, highlighting environmental impacts and challenges associated with landfilling, incineration, and recycling.²⁴⁸




Fig. 23 Main issues and prospective pathways for the utilization of nanoparticles in the removal of heavy metal ions from water and wastewater.²¹²

size and high dispersibility of nanomaterials complicate conventional recovery methods such as filtration or sedimentation, which often fail to achieve quantitative recovery.^{62,244}

Incorporating membrane-assisted or hybrid separation systems can improve recovery but adds substantial complexity and cost. Moreover, incomplete recovery may lead to the unintended



release of residual nanomaterials into water bodies, raising significant ecotoxicological and health concerns.^{244,248} Magnetic nanoadsorbents have emerged as a promising strategy to overcome these limitations, enabling rapid and energy-efficient recovery under an external magnetic field.^{245,249} For example, Fe_3O_4 -based nanocomposites and $\text{Fe}@\text{Au}$ -graphene oxide hybrids have shown efficient magnetic separation and stable adsorption performance over multiple cycles, highlighting the potential of magnetically assisted recycling.²⁴⁵ However, their long-term stability under varying pH, salinity, and redox conditions remains a key concern, as environmental fluctuations can alter magnetic and surface properties, leading to performance degradation.^{246,249}

Another critical issue in the regeneration of nanoadsorbents is the progressive decline in adsorption capacity with successive reuse cycles. This reduction is primarily attributed to irreversible surface fouling, pore blockage by organic or inorganic matter, and loss of active sites or functional groups during regeneration.^{246,249} For nanofibrous and porous materials, repeated exposure to wastewater can also induce shrinkage, deformation, and microstructural weakening, compromising both mechanical stability and adsorption efficiency.²⁴⁴ The extent of performance deterioration is strongly influenced by the regeneration technique employed, necessitating optimization of the regeneration method to balance desorption efficiency, structural preservation, and environmental safety.

Chemical regeneration using acids, bases, or chelating agents remains the most common approach due to its simplicity and high adsorption efficiency. However, the choice and concentration of regenerants critically determine the degree of adsorbent preservation. For instance, Fe/Cu nanoparticles exhibited higher $\text{As}(\text{III})$ desorption efficiency under alkaline conditions, while acidic eluents were more effective for $\text{As}(\text{V})$. Similarly, EDTA-functionalized Fe_3O_4 nanoparticles achieved up to 98% regeneration efficiency using 0.5 M HCl, maintaining performance across 30 reuse cycles.²⁴⁵ Despite such successes, aggressive chemical treatments can lead to dissolution of active components, leaching of metals, or destruction of surface functionalities. Thermal and electrochemical regeneration methods provide alternative routes, though each has inherent drawbacks; thermal treatments can induce sintering and surface area loss, while electrochemical methods require high energy input and specialized electrodes.²⁴⁸ Regardless of the regeneration method, managing the fate of desorbed pollutants remains a major environmental concern, as inadequate handling can lead to secondary contamination.^{248,250} Therefore, the development of closed-loop regeneration systems capable of capturing and neutralizing desorbed contaminants is essential for safe and sustainable implementation.

Beyond the regeneration process itself, the environmental and lifecycle implications of nanoadsorbent recycling must be critically considered. The high reactivity and small size that make nanomaterials effective adsorbents also enhance their mobility and persistence in ecosystems if released inadvertently. Leaching of nanoparticles or transformation under variable environmental conditions can lead to

bioaccumulation, toxicity, and disruption of microbial communities. To mitigate such risks, encapsulation within inert matrices, surface functionalization to reduce reactivity, and integration into composite systems have been proposed. End-of-life management further presents challenges: landfilling risks nanoparticle leaching; incineration may release toxic emissions; and recycling requires energy-intensive processes that must be optimized to remain economically viable.^{248,250} Fig. 22 illustrates the key environmental and operational challenges associated with various end-of-life management routes for nanomaterials, including landfilling, incineration, and recycling. Therefore, recycling technologies should be designed within the framework of circular economy principles, emphasizing material recovery, safe disposal, and minimal environmental footprint.

From a regulatory and practical perspective, the standardization of nanoadsorbent recycling practices remains insufficient, with inconsistent safety and performance guidelines across jurisdictions.^{249,251} Establishing harmonized international standards for recyclability, regeneration protocols, and environmental compliance will be critical to support broader adsorption and commercialization. Future research should prioritize green regeneration technologies, such as low-energy electrochemical systems, solvent-free desorption, and biodegradable nanocomposites, which minimize both cost and environmental burden.^{246,247,249} Moreover, the exploration of alternative reuse pathways for spent nanoadsorbents, such as their utilization in catalysis, soil conditioning, or as additives in cementitious materials, offers sustainable solutions that extend their functional lifespan while reducing waste generation.²⁵⁰ Overall, while the regeneration and reuse of nanoadsorbents hold significant promise for enhancing the sustainability and cost-effectiveness of water purification technologies, numerous technical, environmental, and regulatory challenges must be addressed before large-scale implementation. Achieving this goal requires interdisciplinary collaboration that bridges materials science, environmental engineering, toxicology, and policy development to ensure that next-generation nano-adsorbents are both highly efficient and environmentally responsible throughout their entire life cycle.²⁴⁴⁻²⁴⁹

9. Conclusions

Water pollution, especially from heavy metals, continues to be a significant worldwide concern owing to the persistence, non-biodegradability, and bioaccumulative characteristics of these contaminants. Rapid industrialization, urban growth, and human activities have considerably affected the contamination of water resources, promoting the need for effective, sustainable, and economical treatment approaches. Conventional water treatment techniques, while widely utilized, often inadequately address the complex chemical behavior and low concentrations of heavy metals in aquatic environments. This has promoted considerable interest in adsorption approaches using nanomaterials because of their exceptional surface characteristics, adjustable functionality, and improved reactivity.



Nanotechnology offers an innovative method for environmental remediation. Engineered nanomaterials, including carbon-based nanoadsorbents, zeolites, metal and metal oxide nanoparticles, polymer-based nanocomposites, metal-organic frameworks (MOFs), and layered double hydroxides (LDHs), exhibit exceptional adsorption capacities and selectivity for a variety of heavy metal ions. Their enhanced surface area-to-volume ratio, adjustable structure, and capacity for functionalization make them very efficient in targeting particular pollutants, even at trace concentrations.

Nonetheless, despite these benefits, several obstacles prevent the widespread utilization of nanoadsorbents. This involves the scalability of synthesis, economic viability, long-term stability, regeneration and reusability, toxicity of nanomaterials, and environmental fate issues. Fig. 23 demonstrates the principal obstacles currently limiting the extensive use of nanomaterials in water and wastewater treatment and provides prospective research pathways to address these issues. This encompasses the development of economical and environmentally friendly synthesis processes, enhancement of regeneration methods, optimization of adsorption selectivity across diverse environmental conditions, and execution of thorough toxicity evaluations.

Furthermore, extensive pilot and industrial studies are critically required to validate laboratory findings, assess economic feasibility, and evaluate environmental effects in real-world situations. The advancement of real-time performance assessment tools and intelligent monitoring systems combined with Internet of Things (IoT) technology might significantly improve the operation efficiency and traceability of nanomaterial-based water treatment systems.²¹²

Despite their remarkable potential for environmental remediation, several challenges hinder the large-scale application of nanomaterials. Nanoparticle leakage poses significant environmental risks, as released particles may accumulate in ecosystems, interact with microorganisms, and induce oxidative stress or toxicity. Ensuring nanoparticle stability, recovery, and safe disposal is therefore essential. Another major concern is regeneration efficiency; many nanomaterials lose adsorption capacity after repeated use due to surface fouling, oxidation, or structural degradation. Developing durable and easily regenerable materials, such as magnetically separable or composite nanostructures, can help mitigate this issue. Furthermore, comprehensive life cycle analysis (LCA) is required to evaluate the overall sustainability of nanomaterials, taking into account their synthesis, operational performance, and disposal impacts. Finally, high production and regeneration costs remain a major barrier to commercialization, emphasizing the need for scalable, low-cost, and green synthesis strategies. Addressing these challenges is crucial to achieving safe, efficient, and economically viable nanomaterial-based water treatment technologies.

Author contributions

E. B. Hussein: conceptualization; methodology; data curation; formal analysis; investigation; resources; writing – original draft; writing – review & editing; visualization; project

administration. A. S. Mohammed: formal analysis; investigation; writing – review & editing; visualization. F. A. Rasheed: formal analysis; investigation; writing – review & editing; visualization. K. F. Kayani: formal analysis; investigation; writing – review & editing; visualization.

Conflicts of interest

There are no conflicts to declare.

Data availability

No primary research results, software or code have been included and no new data were generated or analysed as part of this review. Data sharing is not applicable to this article as it is a review of previously published literature, and all supporting data are available in the cited references.

References

- 1 K. F. Kayani and S. J. Mohammed, Heavy metal pollution in aquatic environments and removal using highly efficient bimetallic metal-organic framework adsorbents, *RSC Adv.*, 2025, **15**(43), 35756–35769, DOI: [10.1039/d5ra06296a](https://doi.org/10.1039/d5ra06296a).
- 2 K. P. Mehta, R. Sharma, S. Haldar and A. Kumar, Advancement in treatment of wastewater with nano technology, *Mater. Today Proc.*, 2023, **80**, 3358–3362, DOI: [10.1016/j.matpr.2021.07.253](https://doi.org/10.1016/j.matpr.2021.07.253).
- 3 P. D. Dongare, *et al.*, Nanophotonics-enabled solar membrane distillation for off-grid water purification, *Proc. Natl. Acad. Sci. U. S. A.*, 2017, **114**(27), 6936–6941, DOI: [10.1073/pnas.1701835114](https://doi.org/10.1073/pnas.1701835114).
- 4 R. K. Thines, N. M. Mubarak, S. Nizamuddin, J. N. Sahu, E. C. Abdullah, and P. Ganesan, *Application Potential of Carbon Nanomaterials in Water and Wastewater Treatment: A Review*, Taiwan Institute of Chemical Engineers, 2017, DOI: [10.1016/j.jtice.2017.01.018](https://doi.org/10.1016/j.jtice.2017.01.018).
- 5 World Health Organization (WHO) and United Nations Children's Fund (UNICEF), Progress on household drinking water, sanitation and hygiene 2000–2024: special focus on inequalities, 2025, available: <https://www.who.int/publications/m/item/progress-on-household-drinking-water-sanitation-and-hygiene-2000-2024-special-focus-on-inequalities>, accessed: Sep. 30, 2025.
- 6 E. I. Epelle, P. U. Okoye, S. Roddy, B. Gunes, and J. A. Okolie, *Advances in the Applications of Nanomaterials for Wastewater Treatment*, MDPI, 2022, DOI: [10.3390/environments9110141](https://doi.org/10.3390/environments9110141).
- 7 P. Punia, *et al.*, *Recent Advances in Synthesis, Characterization, and Applications of Nanoparticles for Contaminated Water Treatment-A Review*, Elsevier Ltd, 2021, DOI: [10.1016/j.ceramint.2020.09.050](https://doi.org/10.1016/j.ceramint.2020.09.050).
- 8 G. Hutton, L. Haller and J. Bartram, Global cost-benefit analysis of water supply and sanitation interventions, *J. Water Health*, 2007, **5**(4), 481–501, DOI: [10.2166/wh.2007.009](https://doi.org/10.2166/wh.2007.009).

9 N. J. Ashbolt, Microbial contamination of drinking water and disease outcomes in developing regions, *Toxicology*, 2004, 229–238, DOI: [10.1016/j.tox.2004.01.030](https://doi.org/10.1016/j.tox.2004.01.030).

10 S. Cheriyamundath and S. L. Vavilala, Nanotechnology-based wastewater treatment, *Water Environ. J.*, 2021, 35(1), 123–132, DOI: [10.1111/wej.12610](https://doi.org/10.1111/wej.12610).

11 L. Madhura, S. Singh, S. Kanchi, M. Sabela, K. Bisetty and Inamuddin, Nanotechnology-based water quality management for wastewater treatment, *Environ. Chem. Lett.*, 2019, 17(1), 65–121, DOI: [10.1007/s10311-018-0778-8](https://doi.org/10.1007/s10311-018-0778-8).

12 WHO/UNICEF Joint Water Supply and Sanitation Monitoring Programme, World Health Organization and UNICEF, *Progress on Drinking Water and Sanitation*, 2012 update, UNICEF, 2012.

13 J. S. Carrera and K. Key, Troubling heroes: Reframing the environmental justice contributions of the Flint water crisis, *Wiley Interdiscip. Rev.: Water.*, 2021, 8(4), 1–18, DOI: [10.1002/wat.21524](https://doi.org/10.1002/wat.21524).

14 Y. Li, Z. Piao, X. Ge, J. Feng, D. Sun and J. Zhang, Environmental pollutants and rectal cancer: The impact of water contamination, *Ecotoxicol. Environ. Saf.*, 2025, 294, 118072, DOI: [10.1016/j.ecoenv.2025.118072](https://doi.org/10.1016/j.ecoenv.2025.118072).

15 M. M. Rahman, F. A. D. M. Opo and A. M. Asiri, Comprehensive Studies of Different Cancer Diseases among Less-Developed Countries, *Healthcare*, 2022, 10(424), 1–11, DOI: [10.3390/healthcare10030424](https://doi.org/10.3390/healthcare10030424).

16 M. E. Huq, *et al.*, Arsenic in a groundwater environment in Bangladesh: Occurrence and mobilization, *J. Environ. Manage.*, 2020, 262, 110318, DOI: [10.1016/j.jenvman.2020.110318](https://doi.org/10.1016/j.jenvman.2020.110318).

17 M. Das, Arsenic contamination and cancer risk in Bangladesh, *Lancet Oncol.*, 2024, 25(5), 538, DOI: [10.1016/S1470-2045\(24\)00156-6](https://doi.org/10.1016/S1470-2045(24)00156-6).

18 K. Chen, *et al.*, Association of soil arsenic and nickel exposure with cancer mortality rates, a town-scale ecological study in Suzhou, China, *Environ. Sci. Pollut. Res.*, 2015, 22(7), 5395–5404, DOI: [10.1007/s11356-014-3790-y](https://doi.org/10.1007/s11356-014-3790-y).

19 A. M. Elgarahy, K. Z. Elwakeel, A. Akhdhar, and M. F. Hamza, *Recent Advances in Greenly Synthesized Nanoengineered Materials for Water/Wastewater Remediation: An Overview*, Springer Science and Business Media, Deutschland GmbH, 2021, DOI: [10.1007/s41204-021-00104-5](https://doi.org/10.1007/s41204-021-00104-5).

20 P. A. Dhakras, *2011 International Conference on Nanoscience, Engineering and Technology*, IEEE, Chennai, India, 2011, DOI: [10.1109/ICONSET.2011.6167965](https://doi.org/10.1109/ICONSET.2011.6167965).

21 M. Y. Nassar, E. I. Ali and E. S. Zakaria, Tunable auto-combustion preparation of TiO₂ nanostructures as efficient adsorbents for the removal of an anionic textile dye, *RSC Adv.*, 2017, 7(13), 8034–8050, DOI: [10.1039/c6ra27924d](https://doi.org/10.1039/c6ra27924d).

22 B. D. Deshpande, P. S. Agrawal, M. K. N. Yenkie, and S. J. Dhoble, *Prospective of Nanotechnology in Degradation of Waste Water: A New Challenges*, Elsevier B.V., 2020, DOI: [10.1016/j.nanoso.2020.100442](https://doi.org/10.1016/j.nanoso.2020.100442).

23 Z. Xu, *et al.*, Development of a novel mixed titanium, silver oxide polyacrylonitrile nanofiber as a superior adsorbent and its application for MB removal in wastewater treatment, *J. Braz. Chem. Soc.*, 2018, 29(3), 560–570, DOI: [10.21577/0103-5053.20170168](https://doi.org/10.21577/0103-5053.20170168).

24 H. He, *et al.*, Novel starfish-like inorganic/organic heterojunction for Cr(VI) photocatalytic reduction in neutral solution, *Colloids Surf. A Physicochem. Eng. Asp.*, 2023, 667, 131357, DOI: [10.1016/J.COLSURFA.2023.131357](https://doi.org/10.1016/J.COLSURFA.2023.131357).

25 A. H. Khan, *et al.*, Application of advanced oxidation processes followed by different treatment technologies for hospital wastewater treatment, *J. Clean. Prod.*, 2020, 269, 122411, DOI: [10.1016/j.jclepro.2020.122411](https://doi.org/10.1016/j.jclepro.2020.122411).

26 N. Yahya, *et al.*, A review of integrated photocatalyst adsorbents for wastewater treatment, *J. Environ. Chem. Eng.*, 2018, 6(6), 7411–7425, DOI: [10.1016/j.jece.2018.06.051](https://doi.org/10.1016/j.jece.2018.06.051).

27 X. Qu, P. J. J. Alvarez and Q. Li, Applications of nanotechnology in water and wastewater treatment, *Water Res.*, 2013, 47(12), 3931–3946, DOI: [10.1016/j.watres.2012.09.058](https://doi.org/10.1016/j.watres.2012.09.058).

28 J. K. Patra and K. H. Baek, Green Nanobiotechnology: Factors Affecting Synthesis and Characterization Techniques, *J. Nanomater.*, 2014, 1(417305), 1–12, DOI: [10.1155/2014/417305](https://doi.org/10.1155/2014/417305).

29 P. Jagadeesh, S. M. Rangappa and S. Siengchin, Advanced characterization techniques for nanostructured materials in biomedical applications, *Adv. Ind. Eng. Polym. Res.*, 2024, 7(1), 122–143, DOI: [10.1016/j.aiepr.2023.03.002](https://doi.org/10.1016/j.aiepr.2023.03.002).

30 X. Zheng, P. Zhang, Z. Fu, S. Meng, L. Dai and H. Yang, Applications of nanomaterials in tissue engineering, *RSC Adv.*, 2021, 11(31), 19041–19058, DOI: [10.1039/d1ra01849c](https://doi.org/10.1039/d1ra01849c).

31 S. Moudrikoudis, R. M. Pallares and N. T. K. Thanh, Characterization techniques for nanoparticles: Comparison and complementarity upon studying nanoparticle properties, *Nanoscale*, 2018, 10(27), 12871–12934, DOI: [10.1039/c8nr02278j](https://doi.org/10.1039/c8nr02278j).

32 H. He, Z. Luo and C. Yu, Multifunctional ZnWO₄ nanoparticles for photocatalytic removal of pollutants and disinfection of bacteria, *J. Photochem. Photobiol. A: Chem.*, 2020, 401(112735), 1, DOI: [10.1016/j.jphotochem.2020.112735](https://doi.org/10.1016/j.jphotochem.2020.112735).

33 H. He, Z. Luo and C. Yu, Embellish zinc tungstate nanorods with silver chloride nanoparticles for enhanced photocatalytic, antibacterial and antifouling performance, *Colloids Surf. A Physicochem. Eng. Asp.*, 2021, 613, 126099, DOI: [10.1016/J.COLSURFA.2020.126099](https://doi.org/10.1016/J.COLSURFA.2020.126099).

34 S. Xie, *et al.*, Optimizing electronic structure through lattice engineering for enhanced photocatalytic reduction of Cr(VI), *Inorg. Chem. Commun.*, 2025, 173, 113845, DOI: [10.1016/J.ICONCHE.2024.113845](https://doi.org/10.1016/J.ICONCHE.2024.113845).

35 H. Qin, T. Hu, Y. Zhai, N. Lu and J. Aliyeva, The improved methods of heavy metals removal by biosorbents: A review, *Environ. Pollut.*, 2020, 258, 113777, DOI: [10.1016/J.JENPOL.2019.113777](https://doi.org/10.1016/J.JENPOL.2019.113777).

36 S. Srivastava, S. B. Agrawal and M. K. Mondal, A review on progress of heavy metal removal using adsorbents of



microbial and plant origin, *Environ. Sci. Pollut. Res.*, 2015, 22(20), 15386–15415, DOI: [10.1007/s11356-015-5278-9](https://doi.org/10.1007/s11356-015-5278-9).

37 M. I. Inyang, *et al.*, A review of biochar as a low-cost adsorbent for aqueous heavy metal removal, *Crit. Rev. Environ. Sci. Technol.*, 2016, **46**(4), 406–433, DOI: [10.1080/10643389.2015.1096880](https://doi.org/10.1080/10643389.2015.1096880).

38 M. A. Makhesana, K. M. Patel and A. Nyabadza, Applicability of nanomaterials in water and waste-water treatment: A state-of-the-art review and future perspectives, *Mater. Today Proc.*, 2024, DOI: [10.1016/j.matpr.2024.01.037](https://doi.org/10.1016/j.matpr.2024.01.037).

39 A. A. Yaqoob, T. Parveen, K. Umar, and M. N. M. Ibrahim, *Role of Nanomaterials in the Treatment of Wastewater: A Review*, MDPI AG, 2020, DOI: [10.3390/w12020495](https://doi.org/10.3390/w12020495).

40 S. Khan, M. Naushad, A. Al-Gheethi, and J. Iqbal, *Engineered Nanoparticles for Removal of Pollutants from Wastewater: Current Status and Future Prospects of Nanotechnology for Remediation Strategies*, Elsevier Ltd, 2021, DOI: [10.1016/j.jece.2021.106160](https://doi.org/10.1016/j.jece.2021.106160).

41 Y. Zhang, *et al.*, Nanomaterials-enabled water and wastewater treatment, *NanoImpact*, 2016, 3–4, 22–39, DOI: [10.1016/j.impact.2016.09.004](https://doi.org/10.1016/j.impact.2016.09.004).

42 S. N. Ahmed and W. Haider, Heterogeneous photocatalysis and its potential applications in water and wastewater treatment: A review, *Nanotechnology*, 2018, **29**(34), 342001, DOI: [10.1088/1361-6528/aac6ea](https://doi.org/10.1088/1361-6528/aac6ea).

43 C. H. Nguyen and R. S. Juang, Efficient removal of cationic dyes from water by a combined adsorption-photocatalysis process using platinum-doped titanate nanomaterials, *J. Taiwan Inst. Chem. Eng.*, 2019, **99**, 166–179, DOI: [10.1016/j.jtice.2019.03.017](https://doi.org/10.1016/j.jtice.2019.03.017).

44 C. O. Nnaji, J. Jeevanandam, Y. S. Chan, M. K. Danquah, S. Pan, and A. Barhoum, Engineered nanomaterials for wastewater treatment: Current and future trends, in *Fundamentals of Nanoparticles: Classifications, Synthesis Methods, Properties and Characterization*, Elsevier, 2018, pp. 129–168, DOI: [10.1016/B978-0-323-51255-8.00006-9](https://doi.org/10.1016/B978-0-323-51255-8.00006-9).

45 A. S. Adeleye, J. R. Conway, K. Garner, Y. Huang, Y. Su, and A. A. Keller, Engineered nanomaterials for water treatment and remediation: Costs, benefits, and applicability, 2015, [Online], available: <https://www.sciencedirect.com/science/article/pii/S1385894715015181>.

46 J. K. H. Wong, H. K. Tan, S. Y. Lau, P. S. Yap and M. K. Danquah, Potential and challenges of enzyme incorporated nanotechnology in dye wastewater treatment: A review, *J. Environ. Chem. Eng.*, 2019, **7**, 103261, DOI: [10.1016/j.jece.2019.103261](https://doi.org/10.1016/j.jece.2019.103261).

47 M. T. Amin, A. A. Alazba, and U. Manzoor, *A Review of Removal of Pollutants from Water/Wastewater Using Different Types of Nanomaterials*, Hindawi Publishing Corporation, 2014, DOI: [10.1155/2014/825910](https://doi.org/10.1155/2014/825910).

48 H. Pérez, O. J. Q. García, M. A. Amezcuá-Allieri and R. R. Vázquez, Nanotechnology as an efficient and effective alternative for wastewater treatment: An overview, *Water Sci. Technol.*, 2023, **87**(12), 2971–3001, DOI: [10.2166/wst.2023.179](https://doi.org/10.2166/wst.2023.179).

49 R. Rashid, I. Shafiq, P. Akhter, M. J. Iqbal and M. Hussain, A state-of-the-art review on wastewater treatment techniques: the effectiveness of adsorption method, *Environ. Sci. Pollut. Res.*, 2021, **28**(8), 9050–9066, DOI: [10.1007/s11356-021-12395-x](https://doi.org/10.1007/s11356-021-12395-x)/Published.

50 N. A. Khan, *et al.*, Applications of nanotechnology in water and wastewater treatment: A review, *Asian J. Water Environ. Pollut.*, 2019, **16**(4), 81–86, DOI: [10.3233/AJW190051](https://doi.org/10.3233/AJW190051).

51 P. Pandey, F. Khan, S. Agarwal, and M. Singh, *Nano Adsorbents in Wastewater Treatment: A New Paradigm in Wastewater Management*, AMG Transcend Association, 2023, DOI: [10.33263/LIANBS124.125](https://doi.org/10.33263/LIANBS124.125).

52 M. Anjum, R. Miidad, M. Waqas, F. Gehany, and M. A. Barakat, *Remediation of Wastewater Using Various Nano-Materials*, Elsevier B.V., 2019, DOI: [10.1016/j.arabjc.2016.10.004](https://doi.org/10.1016/j.arabjc.2016.10.004).

53 H. Chen and L. Wang, Posttreatment Strategies for Biomass Conversion, in *Technologies for Biochemical Conversion of Biomass*, ed. H. Chen and L. Wang, Academic Press, Oxford, 2017, ch. 8, pp. 197–217, DOI: [10.1016/B978-0-12-802417-1.00008-9](https://doi.org/10.1016/B978-0-12-802417-1.00008-9).

54 M. E. Ali, M. E. Hoque, S. K. Safdar Hossain, and M. C. Biswas, *Nanoadsorbents for Wastewater Treatment: Next Generation Biotechnological Solution*, Springer, 2020, DOI: [10.1007/s13762-020-02755-4](https://doi.org/10.1007/s13762-020-02755-4).

55 V. Gadore, S. R. Mishra, N. Yadav, G. Yadav and M. Ahmaruzzaman, Advances in zeolite-based materials for dye removal: Current trends and future prospects, *Inorg. Chem. Commun.*, 2024, **166**, 112606, DOI: [10.1016/j.inoche.2024.112606](https://doi.org/10.1016/j.inoche.2024.112606).

56 U. Yunusa, B. Usman, M. B. Ibrahim and M. Bashir Ibrahim, Cationic dyes removal from wastewater by adsorptive method: A systematic in-depth review Algerian Journal of Chemical Engineering Cationic dyes removal from wastewater by adsorptive method: A systematic in-depth review, *Alg. Journ. Che. Eng.*, 2021, **02**, 6–40, DOI: [10.5281/zenodo.5101197](https://doi.org/10.5281/zenodo.5101197).

57 F. Anoob, S. Arachchi, H. M. Azamathulla, N. Al-mahbashi and U. Rathnayake, Nanoadsorbents as an effective wastewater treatment candidate for pharmaceutical contaminants; towards sustainable policy development, *Case Stud. Chem. Environ. Eng.*, 2024, **9**, 100639, DOI: [10.1016/j.cscee.2024.100639](https://doi.org/10.1016/j.cscee.2024.100639).

58 T. A. Saleh, *Materials, Nanomaterials, Nanocomposites, and Methods Used for the Treatment and Removal of Hazardous Pollutants from Wastewater: Treatment Technologies for Water Recycling and Sustainability*, Elsevier B.V., 2024, DOI: [10.1016/j.nanoso.2024.101231](https://doi.org/10.1016/j.nanoso.2024.101231).

59 S. Y. Lee, *et al.*, A state-of-the-art review of metal oxide nanoflowers for wastewater treatment: Dye removal, *Environ. Res.*, 2024, **259**(119448), 1–24, DOI: [10.1016/j.envres.2024.119448](https://doi.org/10.1016/j.envres.2024.119448).

60 A. Mary Elias, G. Meda and K. Tanzil, Recent Progress in Sustainable Treatment Technologies for the Removal of Emerging Contaminants from Wastewater: A Review on Occurrence, Global Status and Impact on Biota, *Rev.*



Environ. Contam. Toxicol., 2024, **262**(1), 16, DOI: [10.1007/s44169-024-00067-z](https://doi.org/10.1007/s44169-024-00067-z).

61 M. Akhtar, M. Sarfraz and M. Ahmad, Use of low-cost adsorbent for waste water treatment: Recent progress, new trend and future perspectives, *Desalination Water Treat.*, 2025, **321**, 100914, DOI: [10.1016/j.dwt.2024.100914](https://doi.org/10.1016/j.dwt.2024.100914).

62 M. E. A. El-sayed, Nanoadsorbents for water and wastewater remediation, *Sci. Total Environ.*, 2020, **739**(139903), 1–12, DOI: [10.1016/j.scitotenv.2020.139903](https://doi.org/10.1016/j.scitotenv.2020.139903).

63 S. Zhang, S. Malik, N. Ali, A. Khan, M. Bilal and K. Rasool, Covalent and Non-covalent Functionalized Nanomaterials for Environmental Restoration, *Top. Curr. Chem.*, 2022, **380**(5), 1, DOI: [10.1007/s41061-022-00397-3](https://doi.org/10.1007/s41061-022-00397-3).

64 B. Liu, H. Sun, X. Tang and X. T. Su, Functional group influence on uranyl ion adsorption by L-cysteine-grafted graphene oxide: A theoretical study, *Ecotoxicol. Environ. Saf.*, 2025, **294**(118091), 1–11, DOI: [10.1016/j.ecoenv.2025.118091](https://doi.org/10.1016/j.ecoenv.2025.118091).

65 J. Kumar, M. Choudhary, P. K. Dikshit and S. Kumar, Recent advancements in utilizing plant-based approaches for water and wastewater treatment technologies, *Clean. Water*, 2024, **2**, 100030, DOI: [10.1016/j.clwat.2024.100030](https://doi.org/10.1016/j.clwat.2024.100030).

66 M. M. Selim, A. Tounsi, H. Gomaa, N. Hu, and M. Shenashen, *Addressing Emerging Contaminants in Wastewater: Insights from Adsorption Isotherms and Adsorbents: A Comprehensive Review*, Elsevier B.V., 2024, DOI: [10.1016/j.aej.2024.05.022](https://doi.org/10.1016/j.aej.2024.05.022).

67 H. Badamasi, *et al.*, A review of recent advances in green and sustainable technologies for removing 4-nitrophenol from the water and wastewater, *Sustain. Chem. Pharm.*, 2025, **43**, 101867, DOI: [10.1016/j.scp.2024.101867](https://doi.org/10.1016/j.scp.2024.101867).

68 S. Alkhair, N. Zouari, M. Ibrahim Ahmad Ibrahim, and M. A. Al-Ghouti, *Efficacy of Adsorption Processes Employing Green Nanoparticles for Bisphenol A Decontamination in Water: A Review*, Elsevier B.V., 2024, DOI: [10.1016/j.enemm.2024.100963](https://doi.org/10.1016/j.enemm.2024.100963).

69 A. Sharma, N. Kumar, A. Mudhoo, and V. K. Garg, *Phytobiomass-based Nanoadsorbents for Sequestration of Aquatic Emerging Contaminants: An Overview*, Elsevier Ltd, 2023, DOI: [10.1016/j.jece.2023.109506](https://doi.org/10.1016/j.jece.2023.109506).

70 J. Odoom, O. T. Iorhemen, and J. Li, Advances in adsorption for oily wastewater treatment: eco-friendly adsorbents and analytical insights, *Joint Center on Global Change and Earth System Science of the University of Maryland and Beijing Normal University*, 2024, DOI: [10.1007/s40974-024-00332-w](https://doi.org/10.1007/s40974-024-00332-w).

71 C. Sophia A and E. C. Lima, Removal of emerging contaminants from the environment by adsorption, *Ecotoxicol. Environ. Saf.*, 2018, **150**, 1–17, DOI: [10.1016/j.ecoenv.2017.12.026](https://doi.org/10.1016/j.ecoenv.2017.12.026).

72 M. R. Letsoalo, *et al.*, *Efficient Detection and Treatment of Pharmaceutical Contaminants to Produce Clean Water for Better Health and Environmental*, Elsevier Ltd, 2023, DOI: [10.1016/j.jclepro.2022.135798](https://doi.org/10.1016/j.jclepro.2022.135798).

73 S. J. Olusegun, *et al.*, *Iron-based Materials for the Adsorption and Photocatalytic Degradation of Pharmaceutical Drugs: A Comprehensive Review of the Mechanism Pathway*, Elsevier Ltd, 2023, DOI: [10.1016/j.jwpe.2022.103457](https://doi.org/10.1016/j.jwpe.2022.103457).

74 M. T. Yagub, T. K. Sen, S. Afrose, and H. M. Ang, *Dye and its Removal from Aqueous Solution by Adsorption: A Review*, Elsevier, 2014, DOI: [10.1016/j.cis.2014.04.002](https://doi.org/10.1016/j.cis.2014.04.002).

75 V. Katheresan, J. Kansedo and S. Y. Lau, Efficiency of various recent wastewater dye removal methods: A review, *J. Environ. Chem. Eng.*, 2018, **6**(4), 4676–4697, DOI: [10.1016/j.jece.2018.06.060](https://doi.org/10.1016/j.jece.2018.06.060).

76 T. Ahmed, S. Imdad, K. Yaldrum, N. M. Butt, and A. Pervez, *Emerging Nanotechnology-Based Methods for Water Purification: A Review*, Taylor and Francis Inc., 2014, DOI: [10.1080/19443994.2013.801789](https://doi.org/10.1080/19443994.2013.801789).

77 M. C. Roco, *National Nanotechnology Initiative-Past, Present, Future, Handbook on Nanoscience, Engineering and Technology*, 2007, vol. 2, pp. 3–4.

78 S. Shukla, R. Khan, and A. Daverey, *Synthesis and Characterization of Magnetic Nanoparticles, and Their Applications in Wastewater Treatment: A Review*, Elsevier B.V., 2021, DOI: [10.1016/j.eti.2021.101924](https://doi.org/10.1016/j.eti.2021.101924).

79 S. Chaturvedi, P. N. Dave and N. K. Shah, Applications of nano-catalyst in new era, *J. Saudi Chem. Soc.*, 2012, **16**(3), 307–325, DOI: [10.1016/j.jscs.2011.01.015](https://doi.org/10.1016/j.jscs.2011.01.015).

80 H. Saleem and S. J. Zaidi, *Developments in the Application of Nanomaterials for Water Treatment and Their Impact on the Environment*, MDPI AG, 2020, DOI: [10.3390/nano10091764](https://doi.org/10.3390/nano10091764).

81 S. Mohan Bhagyaraj, O. S. Oluwafemi, and O. S. Oluwafemi, Nanotechnology: The Science of the Invisible, in *Synthesis of Inorganic Nanomaterials: Advances and Key Technologies*, Elsevier, 2018, pp. 1–18, DOI: [10.1016/B978-0-08-101975-7.00001-4](https://doi.org/10.1016/B978-0-08-101975-7.00001-4).

82 K. Pathakoti, M. Manubolu and H. M. Hwang, Nanostructures: Current uses and future applications in food science, *J. Food Drug Anal.*, 2017, **25**(2), 245–253, DOI: [10.1016/j.jfda.2017.02.004](https://doi.org/10.1016/j.jfda.2017.02.004).

83 M. I. Sohail, *et al.*, Environmental application of nanomaterials: A promise to sustainable future, *Compr. Anal. Chem.*, 2019, **87**, 1–54, DOI: [10.1016/bs.coac.2019.10.002](https://doi.org/10.1016/bs.coac.2019.10.002).

84 M. Madeła, E. Neczaj and A. Grosser, Fate of Engineered Nanoparticles in Wastewater Treatment Plant, *Environ. Prot. Eng.*, 2016, **19**(4), 577–587, DOI: [10.17512/ios.2016.4.11](https://doi.org/10.17512/ios.2016.4.11).

85 A. Roy and J. Bhattacharya, *Nanotechnology in Industrial Wastewater Treatment*, IWA Publishing, 2015.

86 S. K. Brar, M. Verma, R. D. Tyagi and R. Y. Surampalli, Engineered nanoparticles in wastewater and wastewater sludge - Evidence and impacts, *Waste Manag.*, 2010, 504–520, DOI: [10.1016/j.wasman.2009.10.012](https://doi.org/10.1016/j.wasman.2009.10.012).

87 K. Khalid, *et al.*, Advanced in developmental organic and inorganic nanomaterial: a review, *Bioengineered*, 2020, **11**(1), 328–355, DOI: [10.1080/21655979.2020.1736240](https://doi.org/10.1080/21655979.2020.1736240).

88 E.-A. Moustafa, A. Noah, K. Beshay, L. Sultan, M. Essam and O. Nouh, Investigating the Effect of Various Nanomaterials on the Wettability of Sandstone Reservoir, *World J. Eng. Technol.*, 2015, **03**(03), 116–126, DOI: [10.4236/wjet.2015.33013](https://doi.org/10.4236/wjet.2015.33013).



89 K. Jain, A. S. Patel, V. P. Pardhi and S. J. S. Flora, Nanotechnology in wastewater management: A new paradigm towards wastewater treatment, *Molecules*, 2021, 26(6), 1797, DOI: [10.3390/molecules26061797](https://doi.org/10.3390/molecules26061797).

90 M. Jiang, Y. Qi, H. Liu and Y. Chen, The Role of Nanomaterials and Nanotechnologies in Wastewater Treatment: a Bibliometric Analysis, *Nanoscale Res. Lett.*, 2018, 233(1), 1–13, DOI: [10.1186/s11671-018-2649-4](https://doi.org/10.1186/s11671-018-2649-4).

91 N. Baig, I. Kammakakam, W. Falath and I. Kammakakam, Nanomaterials: A review of synthesis methods, properties, recent progress, and challenges, *Mater. Adv.*, 2021, 2(6), 1821–1871, DOI: [10.1039/doma00807a](https://doi.org/10.1039/doma00807a).

92 I. Khan, K. Saeed and I. Khan, Nanoparticles: Properties, applications and toxicities, *Arab. J. Chem.*, 2019, 12(7), 908–931, DOI: [10.1016/j.arabjc.2017.05.011](https://doi.org/10.1016/j.arabjc.2017.05.011).

93 O. V. Kharissova, L. M. T. Martínez, and B. I. Kharisov, *Handbook of Nanomaterials and Nanocomposites for Energy and Environmental Applications*, Springer Nature, Cham, 2021, pp. 489–511, DOI: [10.1007/978-3-030-11155-7](https://doi.org/10.1007/978-3-030-11155-7).

94 S. Thota and D. C. Crans, *Metal Nanoparticles*, Wiley, 2018, DOI: [10.1002/9783527807093](https://doi.org/10.1002/9783527807093).

95 C. Buzea and I. Pacheco, Nanomaterials and their classification, *Adv. Struct. Mater.*, 2017, 62, 3–45, DOI: [10.1007/978-81-322-3655-9_1](https://doi.org/10.1007/978-81-322-3655-9_1).

96 S. Prabha, G. Arya, R. Chandra, B. Ahmed and S. Nimesh, Effect of size on biological properties of nanoparticles employed in gene delivery, *Artif. Cells, Nanomed. Biotechnol.*, 2016, 44(1), 83–91, DOI: [10.3109/21691401.2014.913054](https://doi.org/10.3109/21691401.2014.913054).

97 W. P. Halperin, Quantum size effects in metal particles, *Rev. Mod. Phys.*, 1986, 533–606, DOI: [10.1103/RevModPhys.58.533](https://doi.org/10.1103/RevModPhys.58.533).

98 J. A. Naser, Z. W. Ahmed and E. H. Ali, Nanomaterials usage as adsorbents for the pollutants removal from wastewater: A review, *Mater. Today: Proc.*, 2021, 2590–2595, DOI: [10.1016/j.matpr.2020.12.584](https://doi.org/10.1016/j.matpr.2020.12.584).

99 M. Davarazar, M. Kamali and I. Lopes, Engineered nanomaterials for (waste)water treatment - A scientometric assessment and sustainability aspects, *NanoImpact*, 2021, 22, 100316, DOI: [10.1016/j.impact.2021.100316](https://doi.org/10.1016/j.impact.2021.100316).

100 M. Kamali, K. M. Persson, M. E. Costa and I. Capela, Sustainability criteria for assessing nanotechnology applicability in industrial wastewater treatment: Current status and future outlook, *Environ. Int.*, 2019, 125, 261–276, DOI: [10.1016/j.envint.2019.01.055](https://doi.org/10.1016/j.envint.2019.01.055).

101 Z. Ciğeroğlu, N. El Messaoudi, Z. M. Şenol, G. Başkan, J. Georgin and S. Gubernat, Clay-based nanomaterials and their adsorptive removal efficiency for dyes and antibiotics: A review, *Mater. Today Sustain.*, 2024, 26(100735), 1–26, DOI: [10.1016/j.mtsust.2024.100735](https://doi.org/10.1016/j.mtsust.2024.100735).

102 R. Neha, *et al.*, Nano-adsorbents an effective candidate for removal of toxic pharmaceutical compounds from aqueous environment: A critical review on emerging trends, *Chemosphere*, 2021, 272, 129852, DOI: [10.1016/j.chemosphere.2021.129852](https://doi.org/10.1016/j.chemosphere.2021.129852).

103 B. Barik, P. S. Nayak, and P. Dash, Nanomaterials in wastewater treatments, in *Nanotechnology in the Beverage Industry: Fundamentals and Applications*, Elsevier, 2020, pp. 185–206, DOI: [10.1016/B978-0-12-819941-1.00007-9](https://doi.org/10.1016/B978-0-12-819941-1.00007-9).

104 A. S. Ganie, *et al.*, Nanoremediation technologies for sustainable remediation of contaminated environments: Recent advances and challenges, *Chemosphere*, 2021, 275, 130065, DOI: [10.1016/j.chemosphere.2021.130065](https://doi.org/10.1016/j.chemosphere.2021.130065).

105 S. Khan, Z. Dan, Y. Mengling, Y. Yang, H. Haiyan and J. Hao, Isotherms, kinetics and thermodynamic studies of adsorption of Ni and Cu by modification of Al₂O₃ nanoparticles with natural organic matter, *Fullerenes, Nanotub. Carbon Nanostruct.*, 2018, 26(3), 158–167, DOI: [10.1080/1536383X.2017.1422490](https://doi.org/10.1080/1536383X.2017.1422490).

106 B. Bethi, S. H. Sonawane, B. A. Bhanvase and S. P. Gumfekar, Nanomaterials-based advanced oxidation processes for wastewater treatment: A review, *Chem. Eng. Process. Process Intensif.*, 2016, 109, 178–189, DOI: [10.1016/j.cep.2016.08.016](https://doi.org/10.1016/j.cep.2016.08.016).

107 S. J. Tesh and T. B. Scott, Nano-composites for water remediation: A review, *Adv. Mater.*, 2014, 26(35), 6056–6068, DOI: [10.1002/adma.201401376](https://doi.org/10.1002/adma.201401376).

108 G. Lofrano, *et al.*, Polymer functionalized nanocomposites for metals removal from water and wastewater: An overview, *Water Res.*, 2016, 92, 22–37, DOI: [10.1016/j.watres.2016.01.033](https://doi.org/10.1016/j.watres.2016.01.033).

109 Y. A. J. Al-Hamadani, *et al.*, Stabilization and dispersion of carbon nanomaterials in aqueous solutions: A review, *Sep. Purif. Technol.*, 2015, 156, 861–874, DOI: [10.1016/j.seppur.2015.11.002](https://doi.org/10.1016/j.seppur.2015.11.002).

110 X. Qu, J. Brame, Q. Li and P. J. J. Alvarez, Nanotechnology for a safe and sustainable water supply: Enabling integrated water treatment and reuse, *Acc. Chem. Res.*, 2013, 46(3), 834–843, DOI: [10.1021/ar300029v](https://doi.org/10.1021/ar300029v).

111 A. L. Dale, E. A. Casman, G. V. Lowry, J. R. Lead, E. Viparelli and M. Baalousha, Modeling nanomaterial environmental fate in aquatic systems, *Environ. Sci. Technol.*, 2015, 49(5), 2587–2593, DOI: [10.1021/es505076w](https://doi.org/10.1021/es505076w).

112 R. S. Varma, Greener approach to nanomaterials and their sustainable applications, *Curr. Opin. Chem. Eng.*, 2012, 1(2), 123–128, DOI: [10.1016/j.coche.2011.12.002](https://doi.org/10.1016/j.coche.2011.12.002).

113 J. Yin and B. Deng, Polymer-matrix nanocomposite membranes for water treatment, *J. Membr. Sci.*, 2015, 479, 256–275, DOI: [10.1016/j.memsci.2014.11.019](https://doi.org/10.1016/j.memsci.2014.11.019).

114 N. Komby Abdulla, *et al.*, MnO₂ decoration onto the guava leaves: A sustainable and cost-effective material for methylene blue dye removal, *Helijon*, 2024, 10(14), DOI: [10.1016/j.helijon.2024.e34267](https://doi.org/10.1016/j.helijon.2024.e34267).

115 N. Singh, A. Malik, and A. A. Hashmi, *Nanotechnology and its Application in Wastewater Treatment*, 2021, pp. 307–332.

116 A. Baruah, V. Chaudhary, R. Malik, and V. K. Tomer, Nanotechnology Based Solutions for Wastewater Treatment, in *Nanotechnology in Water and Wastewater Treatment: Theory and Applications*, Elsevier, 2019, pp. 337–368, DOI: [10.1016/B978-0-12-813902-8.00017-4](https://doi.org/10.1016/B978-0-12-813902-8.00017-4).

117 I. J. El Saliby, H. K. Shon, J. Kandasamy, and S. Vigneswaran, Nanotechnology For Wastewater



Treatment: In Brief, *Encyclopedia of Life Support System (EOLSS)*, 2008, vol. 15, p. 15.

118 J. Guo, Q. Zhang, Z. Cai and K. Zhao, Preparation and dye filtration property of electrospun polyhydroxybutyrate-calcium alginate/carbon nanotubes composite nanofibrous filtration membrane, *Sep. Purif. Technol.*, 2016, **161**, 69–79, DOI: [10.1016/j.seppur.2016.01.036](https://doi.org/10.1016/j.seppur.2016.01.036).

119 J. H. Jang, *et al.*, Correlation between particle deposition and the size ratio of particles to patterns in nano- and micro-patterned membrane filtration systems, *Sep. Purif. Technol.*, 2015, **156**, 608–616, DOI: [10.1016/j.seppur.2015.10.056](https://doi.org/10.1016/j.seppur.2015.10.056).

120 N. Narwal, *et al.*, Emerging micropollutants in aquatic ecosystems and nanotechnology-based removal alternatives: A review, *Chemosphere*, 2023, **341**, 139945, DOI: [10.1016/j.chemosphere.2023.139945](https://doi.org/10.1016/j.chemosphere.2023.139945).

121 H. A. Alalwan, A. H. Alminshid, M. M. Mohammed, M. F. Mohammed and M. H. Shadhar, Reviewing of Using Nanomaterials for Wastewater Treatment, *Pollution*, 2022, **8**(3), 995–1013, DOI: [10.22059/POLL.2022.337436.1329](https://doi.org/10.22059/POLL.2022.337436.1329).

122 V. Kugarajah, *et al.*, *Future Applications of Electrospun Nanofibers in Pressure Driven Water Treatment: A Brief Review and Research Update*, Elsevier Ltd, 2021, DOI: [10.1016/j.jece.2021.105107](https://doi.org/10.1016/j.jece.2021.105107).

123 G. Z. Kyzas and K. A. Matis, *Nanoadsorbents for Pollutants Removal: A Review*, Elsevier, 2015, DOI: [10.1016/j.molliq.2015.01.004](https://doi.org/10.1016/j.molliq.2015.01.004).

124 M. Khajeh, S. Laurent and K. Dastafkan, Nanoadsorbents: Classification, preparation, and applications (with emphasis on aqueous media), *Chem. Rev.*, 2013, **113**(10), 7728–7768, DOI: [10.1021/cr400086v](https://doi.org/10.1021/cr400086v).

125 A. K. Dutta, S. K. Maji and B. Adhikary, γ -Fe₂O₃ nanoparticles: An easily recoverable effective photocatalyst for the degradation of rose bengal and methylene blue dyes in the waste-water treatment plant, *Mater. Res. Bull.*, 2014, **49**(1), 28–34, DOI: [10.1016/j.materresbull.2013.08.024](https://doi.org/10.1016/j.materresbull.2013.08.024).

126 M. Kurian and D. S. Nair, Heterogeneous Fenton behavior of nano nickel zinc ferrite catalysts in the degradation of 4-chlorophenol from water under neutral conditions, *J. Water Proc. Eng.*, 2015, **8**, e37–e49, DOI: [10.1016/j.jwpe.2014.10.011](https://doi.org/10.1016/j.jwpe.2014.10.011).

127 H. Ma, H. Wang and C. Na, Microwave-assisted optimization of platinum-nickel nanoalloys for catalytic water treatment, *Appl. Catal., B*, 2015, **163**, 198–204, DOI: [10.1016/j.apcatb.2014.07.062](https://doi.org/10.1016/j.apcatb.2014.07.062).

128 A. Sharma, *et al.*, Cutting edge technology for wastewater treatment using smart nanomaterials: recent trends and futuristic advancements, *Environ. Sci. Pollut. Res.*, 2024, **31**, 58263–58293, DOI: [10.1007/s11356-024-34977-1](https://doi.org/10.1007/s11356-024-34977-1).

129 M. Singh and A. Kumar, A Comprehensive Review: Nanomembranes and Nanosorbents for Water Treatment, *International Journal of Research and Innovation in Applied Science*, 2022, **7**(9), 1–6.

130 I. Singh and P. K. Mishra, Nano-membrane Filtration a Novel Application of Nanotechnology for Waste Water Treatment, *Mater. Today: Proc.*, 2020, **29**, 327–332. [Online]. Available: <https://www.sciencedirect.com/>.

131 K. P. Gopinath, N. V. Madhav, A. Krishnan, R. Malolan and G. Rangarajan, Present applications of titanium dioxide for the photocatalytic removal of pollutants from water: A review, *J. Environ. Manage.*, 2020, **270**, 110906, DOI: [10.1016/j.jenvman.2020.110906](https://doi.org/10.1016/j.jenvman.2020.110906).

132 T. A. Aragaw, F. M. Bogale and B. A. Aragaw, Iron-based nanoparticles in wastewater treatment: A review on synthesis methods, applications, and removal mechanisms, *J. Saudi Chem. Soc.*, 2021, **25**(8), 1–28, DOI: [10.1016/j.jscs.2021.101280](https://doi.org/10.1016/j.jscs.2021.101280).

133 P. Xu, *et al.*, Use of iron oxide nanomaterials in wastewater treatment: A review, *Sci. Total Environ.*, 2012, **424**, 1–10, DOI: [10.1016/j.scitotenv.2012.02.023](https://doi.org/10.1016/j.scitotenv.2012.02.023).

134 A. Shah, *et al.*, Micelles as Soil and Water Decontamination Agents, *Chem. Rev.*, 2016, **116**(10), 6042–6074, DOI: [10.1016/j.acs.chemrev.6b00132](https://doi.org/10.1016/j.acs.chemrev.6b00132).

135 B. K. Allam, N. Musa, A. Debnath, U. L. Usman and S. Banerjee, Recent developments and application of bimetallic based materials in water purification, *Environ. Chall.*, 2021, **5**, 100405, DOI: [10.1016/j.envc.2021.100405](https://doi.org/10.1016/j.envc.2021.100405).

136 J. Scaria, P. V. Nidheesh and M. S. Kumar, Synthesis and applications of various bimetallic nanomaterials in water and wastewater treatment, *J. Environ. Manage.*, 2020, **259**, 110011, DOI: [10.1016/j.jenvman.2019.110011](https://doi.org/10.1016/j.jenvman.2019.110011).

137 Z. Bartul, *Advances in Nanotechnology*, Nova Science, 2022.

138 A. Awasthi, P. Jadhao and K. Kumari, Clay nano-adsorbent: structures, applications and mechanism for water treatment, *SN Appl. Sci.*, 2019, **1**(9), 1076, DOI: [10.1007/s42452-019-0858-9](https://doi.org/10.1007/s42452-019-0858-9).

139 A. Ali, *et al.*, Review on Recent Progress in Magnetic Nanoparticles: Synthesis, Characterization, and Diverse Applications, *Front. Chem.*, 2021, **9**, 629054, DOI: [10.3389/fchem.2021.629054](https://doi.org/10.3389/fchem.2021.629054).

140 J. H. Chung, N. Hasyimah and N. Hussein, Application of Carbon Nanotubes (CNTs) for Remediation of Emerging Pollutants - A Review, *Trop. Aquat. Soil Pollut.*, 2021, **2**(1), 13–26, DOI: [10.53623/tasp.v2i1.27](https://doi.org/10.53623/tasp.v2i1.27).

141 N. Hossain, M. A. Islam, and M. A. Chowdhury, *Synthesis and Characterization of Plant Extracted Silver Nanoparticles and Advances in Dental Implant Applications*, Elsevier Ltd, 2022, DOI: [10.1016/j.heliyon.2022.e12313](https://doi.org/10.1016/j.heliyon.2022.e12313).

142 W. M. Shume, H. C. A. Murthy, and E. A. Zereffa, *A Review on Synthesis and Characterization of Ag₂O Nanoparticles for Photocatalytic Applications*, Hindawi Limited, 2020, DOI: [10.1155/2020/5039479](https://doi.org/10.1155/2020/5039479).

143 S. Dawadi, *et al.*, Current Research on Silver Nanoparticles: Synthesis, Characterization, and Applications, *J. Nanomater.*, 2021, **2021**, 6687290, DOI: [10.1155/2021/6687290](https://doi.org/10.1155/2021/6687290).

144 S. Rani and R. Kumar, Nanoparticle-Incorporated Soy Protein Isolate Films, in *Nanotechnology in the Life Sciences*, Springer Science and Business Media B.V., 2020, pp. 19–37, DOI: [10.1007/978-3-030-31938-0_2](https://doi.org/10.1007/978-3-030-31938-0_2).

145 M. A. Hassaan, A. El Nemr, and S. Ragab, Green Synthesis and Application of Metal and Metal Oxide Nanoparticles,



in *Handbook of Nanomaterials and Nanocomposites for Energy and Environmental Applications: Volumes 1–4*, Springer International Publishing, 2021, vol. 2, pp. 831–858, DOI: [10.1007/978-3-030-36268-3_125](https://doi.org/10.1007/978-3-030-36268-3_125).

146 K. C. Hembram, R. Kumar, L. Kandha, P. K. Parhi, C. N. Kundu, and B. K. Bindhani, *Therapeutic Prospective of Plant-Induced Silver Nanoparticles: Application as Antimicrobial and Anticancer Agent*, Taylor and Francis Ltd, 2018, DOI: [10.1080/21691401.2018.1489262](https://doi.org/10.1080/21691401.2018.1489262).

147 S. P. Singh, *et al.*, Recent Trends and Advancement Toward Phyto-mediated Fabrication of Noble Metallic Nanomaterials: Focus on Silver, Gold, Platinum, and Palladium, in *Nanotechnology in the Life Sciences*, Springer Science and Business Media B.V., 2020, pp. 87–105, DOI: [10.1007/978-3-030-34544-0_6](https://doi.org/10.1007/978-3-030-34544-0_6).

148 K. A. Altammar, *A Review on Nanoparticles: Characteristics, Synthesis, Applications, and Challenges*, Frontiers Media S.A., 2023, DOI: [10.3389/fmibc.2023.1155622](https://doi.org/10.3389/fmibc.2023.1155622).

149 A. Gul, N. G. Khaligh, and N. M. Julkapli, *Surface Modification of Carbon-Based Nanoadsorbents for the Advanced Wastewater Treatment*, Elsevier B.V., 2021, DOI: [10.1016/j.molstruc.2021.130148](https://doi.org/10.1016/j.molstruc.2021.130148).

150 A. Saravanan, *et al.*, Adsorption characteristics of magnetic nanoparticles coated mixed fungal biomass for toxic Cr(VI) ions in aquatic environment, *Chemosphere*, 2021, **267**, 129226, DOI: [10.1016/j.chemosphere.2020.129226](https://doi.org/10.1016/j.chemosphere.2020.129226).

151 M. A. R. Khan, *et al.*, *A Review on Gold Nanoparticles: Biological Synthesis, Characterizations, and Analytical Applications*, Elsevier B.V., 2022, DOI: [10.1016/j.rechem.2022.100478](https://doi.org/10.1016/j.rechem.2022.100478).

152 A. F. Ismail, K. C. Khulbe, and T. Matsuura, RO Membrane Characterization, in *Reverse Osmosis*, Elsevier, 2019, pp. 57–90, DOI: [10.1016/b978-0-12-811468-1.00003-7](https://doi.org/10.1016/b978-0-12-811468-1.00003-7).

153 M. F. Al-Hakkani, G. A. Gouda, and S. H. A. Hassan, *A Review of Green Methods for Phyto-Fabrication of Hematite (α -Fe₂O₃) Nanoparticles and Their Characterization, Properties, and Applications*, Elsevier Ltd, 2021, DOI: [10.1016/j.heliyon.2020.e05806](https://doi.org/10.1016/j.heliyon.2020.e05806).

154 J. M. Rami, C. D. Patel, C. M. Patel and M. V. Patel, Thermogravimetric analysis (TGA) of some synthesized metal oxide nanoparticles, *Mater. Today: Proc.*, 2020, **655–659**, DOI: [10.1016/j.matpr.2020.12.554](https://doi.org/10.1016/j.matpr.2020.12.554).

155 J. Zheng, Y. Lyu, B. Wu, and S. Wang, *Defect Engineering of the Protection Layer for Photoelectrochemical Devices*, Elsevier B.V., 2020, DOI: [10.1016/j.enchem.2020.100039](https://doi.org/10.1016/j.enchem.2020.100039).

156 D. S. Shirasath and V. S. Shirivastava, Adsorptive removal of heavy metals by magnetic nanoadsorbent: an equilibrium and thermodynamic study, *Appl. Nanosci.*, 2015, **5**(8), 927–935, DOI: [10.1007/s13204-014-0390-6](https://doi.org/10.1007/s13204-014-0390-6).

157 S. Ghoteckar, T. Pagar, S. Pansambal and R. Oza, Suresh Ghoteckar *et. al./Ad.*, *Adv. J. Chem. Sect. B*, 2020, **2020**(3), 128–143, DOI: [10.33945/SAMI/AJCB.2020.3.5](https://doi.org/10.33945/SAMI/AJCB.2020.3.5).

158 N. Joudeh and D. Linke, Nanoparticle classification, physicochemical properties, characterization, and applications: a comprehensive review for biologists, *J. Nanobiotechnol.*, 2022, **20**(1), 262, DOI: [10.1186/s12951-022-01477-8](https://doi.org/10.1186/s12951-022-01477-8).

159 T. Anukiruthika, S. Priyanka, J. A. Moses, and C. Anandharamakrishnan, Characterisation of green nanomaterials, in *Advanced Structured Materials*, Springer, 2020, vol. 126, pp. 43–79, DOI: [10.1007/978-981-15-3560-4_3](https://doi.org/10.1007/978-981-15-3560-4_3).

160 F. Fu and Q. Wang, *Removal of Heavy Metal Ions from Wastewaters: A Review*, Academic Press, 2011, DOI: [10.1016/j.jenvman.2010.11.011](https://doi.org/10.1016/j.jenvman.2010.11.011).

161 N. K. Srivastava and C. B. Majumder, Novel biofiltration methods for the treatment of heavy metals from industrial wastewater, *J. Hazard. Mater.*, 2008, **151**(1), 1–8, DOI: [10.1016/j.jhazmat.2007.09.101](https://doi.org/10.1016/j.jhazmat.2007.09.101).

162 E. Odumbe, S. Murunga, and J. Ndiiri, Heavy Metals in Wastewater Effluent: Causes, Effects, and Removal Technologies, *Trace Metals in the Environment*, IntechOpen, 2023, DOI: [10.5772/intechopen.1001452](https://doi.org/10.5772/intechopen.1001452).

163 R. Kumar, R. Kumar, and G. Kaur, *New Frontiers of Nanomaterials in Environmental Science*, Springer, Singapore, 2021, DOI: [10.1007/978-981-15-9239-3](https://doi.org/10.1007/978-981-15-9239-3).

164 Q. Zhou, *et al.*, Total concentrations and sources of heavy metal pollution in global river and lake water bodies from 1972 to 2017, *Glob. Ecol. Conserv.*, 2020, **22**, e00925, DOI: [10.1016/j.gecco.2020.e00925](https://doi.org/10.1016/j.gecco.2020.e00925).

165 D. Thangadurai, J. Sangeetha, and R. Prasad, *Nanotechnology for Food, Agriculture, and Environment*, Berlin/Heidelberg, Germany, 2020, [Online], available: <http://www.springer.com/series/15921>.

166 S. Babel and T. Agustiono Kurniawan, Low-cost adsorbents for heavy metals uptake from contaminated water: a review, *J. Hazard. Mater.*, 2003, **97**, 219–243.

167 S. S. Ahluwalia and D. Goyal, Microbial and plant derived biomass for removal of heavy metals from wastewater, *Bioresour. Technol.*, 2007, **98**(12), 2243–2257, DOI: [10.1016/j.biortech.2005.12.006](https://doi.org/10.1016/j.biortech.2005.12.006).

168 H. Lu, J. Wang, M. Stoller, T. Wang, Y. Bao and H. Hao, An Overview of Nanomaterials for Water and Wastewater Treatment, *Adv. Mater. Sci. Eng.*, 2016, **2016**(1), 4964828, DOI: [10.1155/2016/4964828](https://doi.org/10.1155/2016/4964828).

169 X. Wang, Nanomaterials as Sorbents to Remove Heavy Metal Ions in Wastewater Treatment, *J. Environ. Anal. Toxicol.*, 2012, **02**(07), 154–158, DOI: [10.4172/2161-0525.1000154](https://doi.org/10.4172/2161-0525.1000154).

170 M. A. Barakat, New trends in removing heavy metals from industrial wastewater, *Arab. J. Chem.*, 2011, **4**(4), 361–377, DOI: [10.1016/j.arabjc.2010.07.019](https://doi.org/10.1016/j.arabjc.2010.07.019).

171 P. Kajitvichyanukul, J. Ananpattarakachai, and S. Pongpom, Sol-gel preparation and properties study of TiO₂ thin film for photocatalytic reduction of chromium(VI) in photocatalysis process, in *Science and Technology of Advanced Materials*, 2005, pp. 352–358, DOI: [10.1016/j.stam.2005.02.014](https://doi.org/10.1016/j.stam.2005.02.014).

172 Y. H. Cai, X. J. Yang and A. I. Schäfer, Removal of naturally occurring strontium by nanofiltration/reverse osmosis from groundwater, *Membranes*, 2020, **10**(11), 1–23, DOI: [10.3390/membranes10110321](https://doi.org/10.3390/membranes10110321).

173 J. Tian, H. Chang, S. Gao and R. Zhang, How to fabricate a negatively charged NF membrane for heavy metal



removal via the interfacial polymerization between PIP and TMC?, *Desalination*, 2020, **491**, 114499, DOI: [10.1016/j.desal.2020.114499](https://doi.org/10.1016/j.desal.2020.114499).

174 W. A. Al-Amrani and S. A. Onaizi, Adsorptive removal of heavy metals from wastewater using emerging nanostructured materials: A state-of-the-art review, *Sep. Purif. Technol.*, 2024, **343**, 127018, DOI: [10.1016/j.seppur.2024.127018](https://doi.org/10.1016/j.seppur.2024.127018).

175 N. R. Nik-Abdul-Ghani, M. S. Jami and M. Z. Alam, The role of nanoadsorbents and nanocomposite adsorbents in the removal of heavy metals from wastewater: A review and prospect, *Pollution*, 2021, **7**(1), 153–179, DOI: [10.22059/poll.2020.307069.859](https://doi.org/10.22059/poll.2020.307069.859).

176 R. Shrestha, *et al.*, *Technological Trends in Heavy Metals Removal from Industrial Wastewater: A Review*, Elsevier Ltd, 2021, DOI: [10.1016/j.jece.2021.105688](https://doi.org/10.1016/j.jece.2021.105688).

177 R. Soni, A. K. Pal, P. Tripathi, J. A. Lal, K. Kesari and V. Tripathi, An overview of nanoscale materials on the removal of wastewater contaminants, *Appl. Water Sci.*, 2020, **10**(8), 189, DOI: [10.1007/s13201-020-01275-3](https://doi.org/10.1007/s13201-020-01275-3).

178 L. Liu, X. B. Luo, L. Ding, and S. L. Luo, Application of Nanotechnology in the Removal of Heavy Metal From Water, in *Nanomaterials for the Removal of Pollutants and Resource Reutilization*, Elsevier, 2018, pp. 83–147, DOI: [10.1016/B978-0-12-814837-2.00004-4](https://doi.org/10.1016/B978-0-12-814837-2.00004-4).

179 S. Kumar, W. Ahlawat, G. Bhanjana, S. Heydarifard, M. M. Nazhad and N. Dilbaghi, Nanotechnology-based water treatment strategies, *J. Nanosci. Nanotechnol.*, 2014, **14**(2), 1838–1858, DOI: [10.1166/jnn.2014.9050](https://doi.org/10.1166/jnn.2014.9050).

180 S. Wadhawan, A. Jain, J. Nayyar and S. K. Mehta, Role of nanomaterials as adsorbents in heavy metal ion removal from waste water: A review, *J. Water Proc. Eng.*, 2020, **33**, 101038, DOI: [10.1016/j.jwpe.2019.101038](https://doi.org/10.1016/j.jwpe.2019.101038).

181 V. K. Gupta, R. Chandra, I. Tyagi and M. Verma, Removal of hexavalent chromium ions using CuO nanoparticles for water purification applications, *J. Colloid Interface Sci.*, 2016, **478**, 54–62, DOI: [10.1016/j.jcis.2016.05.064](https://doi.org/10.1016/j.jcis.2016.05.064).

182 Z. nan Huang, X. ling Wang and D. suo Yang, Adsorption of Cr(VI) in wastewater using magnetic multi-wall carbon nanotubes, *Water Sci. Eng.*, 2015, **8**(3), 226–232, DOI: [10.1016/j.wse.2015.01.009](https://doi.org/10.1016/j.wse.2015.01.009).

183 R. Dubey, J. Bajpai and A. K. Bajpai, Chitosan-alginate nanoparticles (CANPs) as potential nanosorbent for removal of Hg (II) ions, *Environ. Nanotechnol. Monit. Manag.*, 2016, **6**, 32–44, DOI: [10.1016/j.enmm.2016.06.008](https://doi.org/10.1016/j.enmm.2016.06.008).

184 Z. Qu, *et al.*, Ultraeffective ZnS nanocrystals sorbent for mercury(II) removal based on size-dependent cation exchange, *ACS Appl. Mater. Interfaces*, 2014, **6**(20), 18026–18032, DOI: [10.1021/am504896w](https://doi.org/10.1021/am504896w).

185 A. M. Mahmoud, F. A. Ibrahim, S. A. Shaban and N. A. Youssef, Adsorption of heavy metal ion from aqueous solution by nickel oxide nano catalyst prepared by different methods, *Egypt. J. Pet.*, 2015, **24**(1), 27–35, DOI: [10.1016/j.ejpe.2015.02.003](https://doi.org/10.1016/j.ejpe.2015.02.003).

186 C. Santhosh, V. Velmurugan, G. Jacob, S. K. Jeong, A. N. Grace, and A. Bhatnagar, *Role of Nanomaterials in Water Treatment Applications: A Review*, Elsevier B.V., 2016, DOI: [10.1016/j.cej.2016.08.053](https://doi.org/10.1016/j.cej.2016.08.053).

187 L. Hao, H. Song, L. Zhang, X. Wan, Y. Tang and Y. Lv, SiO₂/graphene composite for highly selective adsorption of Pb(II) ion, *J. Colloid Interface Sci.*, 2012, **369**(1), 381–387, DOI: [10.1016/j.jcis.2011.12.023](https://doi.org/10.1016/j.jcis.2011.12.023).

188 Y. J. Tu, C. F. You, M. H. Chen and Y. P. Duan, Efficient removal/recovery of Pb onto environmentally friendly fabricated copper ferrite nanoparticles, *J. Taiwan Inst. Chem. Eng.*, 2017, **71**, 197–205, DOI: [10.1016/j.jtice.2016.12.006](https://doi.org/10.1016/j.jtice.2016.12.006).

189 N. A. Kabbashi, M. A. Atieh, A. Al-Mamun, M. E. Mirghami, M. D. Z. Alam and N. Yahya, Kinetic adsorption of application of carbon nanotubes for Pb(II) removal from aqueous solution, *J. Environ. Sci.*, 2009, **21**(4), 539–544, DOI: [10.1016/S1001-0742\(08\)62305-0](https://doi.org/10.1016/S1001-0742(08)62305-0).

190 F. S. Tabatabaei, *et al.*, Modeling and optimization of arsenic (III) removal from aqueous solutions by GFO using response surface methodology, *Pollution*, 2020, **6**(3), 543–553, DOI: [10.22059/POLL.2020.296452.739](https://doi.org/10.22059/POLL.2020.296452.739).

191 T. M. Salem Attia, X. L. Hu and D. Q. Yin, Synthesised magnetic nanoparticles coated zeolite (MNCZ) for the removal of arsenic (As) from aqueous solution, *J. Exp. Nanosci.*, 2014, **9**(6), 551–560, DOI: [10.1080/17458080.2012.677549](https://doi.org/10.1080/17458080.2012.677549).

192 A. R. Rahmani, H. R. Ghaffari and M. T. Samadi, A Comparative Study On Arsenic (Iii) Removal From Aqueous Solution Using Nano And Micro Sized Zero-Valent Iron, *J. Environ. Health Sci. Eng.*, 2011, **8**(2), 175–180.

193 M. Ahmad, J. Wang, J. Xu, Q. Zhang and B. Zhang, Magnetic tubular carbon nanofibers as efficient Cu(II) ion adsorbent from wastewater, *J. Clean. Prod.*, 2020, **252**, 119825, DOI: [10.1016/j.jclepro.2019.119825](https://doi.org/10.1016/j.jclepro.2019.119825).

194 V. K. Gupta, S. Agarwal, A. K. Bharti and H. Sadegh, Adsorption mechanism of functionalized multi-walled carbon nanotubes for advanced Cu (II) removal, *J. Mol. Liq.*, 2017, **230**, 667–673, DOI: [10.1016/j.molliq.2017.01.083](https://doi.org/10.1016/j.molliq.2017.01.083).

195 Y. Li, *et al.*, Removal of copper from aqueous solution by carbon nanotube/calcium alginate composites, *J. Hazard. Mater.*, 2010, **177**(1–3), 876–880, DOI: [10.1016/j.jhazmat.2009.12.114](https://doi.org/10.1016/j.jhazmat.2009.12.114).

196 J. Gao, *et al.*, Single step synthesis of amine-functionalized mesoporous magnetite nanoparticles and their application for copper ions removal from aqueous solution, *J. Colloid Interface Sci.*, 2016, **481**, 220–228, DOI: [10.1016/j.jcis.2016.07.057](https://doi.org/10.1016/j.jcis.2016.07.057).

197 X. J. Hu, *et al.*, Removal of Cu(II) ions from aqueous solution using sulfonated magnetic graphene oxide composite, *Sep. Purif. Technol.*, 2013, **108**, 189–195, DOI: [10.1016/j.seppur.2013.02.011](https://doi.org/10.1016/j.seppur.2013.02.011).

198 E. M. Elsehly, *et al.*, Characterization of functionalized multiwalled carbon nanotubes and application as an effective filter for heavy metal removal from aqueous solutions, *Chin. J. Chem. Eng.*, 2016, **24**(12), 1695–1702, DOI: [10.1016/j.cjche.2016.05.017](https://doi.org/10.1016/j.cjche.2016.05.017).



199 C. Lu, C. Liu and G. P. Rao, Comparisons of sorbent cost for the removal of Ni^{2+} from aqueous solution by carbon nanotubes and granular activated carbon, *J. Hazard. Mater.*, 2008, **151**(1), 239–246, DOI: [10.1016/j.jhazmat.2007.05.078](https://doi.org/10.1016/j.jhazmat.2007.05.078).

200 C. P. Devatha and S. S, Novel application of maghemite nanoparticles coated bacteria for the removal of cadmium from aqueous solution, *J. Environ. Manage.*, 2020, **258**, 110038, DOI: [10.1016/j.jenvman.2019.110038](https://doi.org/10.1016/j.jenvman.2019.110038).

201 I. H. Alsohaimi, S. M. Wabaidur, M. Kumar, M. A. Khan, Z. A. Alothman and M. A. Abdalla, Synthesis, characterization of PMDA/TMSPEDA hybrid nanocomposite and its applications as an adsorbent for the removal of bivalent heavy metals ions, *Chem. Eng. J.*, 2015, **270**, 9–21, DOI: [10.1016/j.cej.2015.02.008](https://doi.org/10.1016/j.cej.2015.02.008).

202 H. Karami, Heavy metal removal from water by magnetite nanorods, *Chem. Eng. J.*, 2013, **219**, 209–216, DOI: [10.1016/j.cej.2013.01.022](https://doi.org/10.1016/j.cej.2013.01.022).

203 L. Khezami, M. Ould M'hamed, O. M. Lemine, M. Bououdina and A. Bessadok-Jemai, Milled goethite nanocrystalline for selective and fast uptake of cadmium ions from aqueous solution, *Desalination Water Treat.*, 2016, **57**(14), 6531–6539, DOI: [10.1080/19443994.2015.1010231](https://doi.org/10.1080/19443994.2015.1010231).

204 Y. Zhang, *et al.*, Adsorption of $\text{Pb}(\text{II})$ and $\text{Hg}(\text{II})$ from aqueous solution using magnetic CoFe_2O_4 -reduced graphene oxide, *J. Mol. Liq.*, 2014, **191**, 177–182, DOI: [10.1016/j.molliq.2013.12.015](https://doi.org/10.1016/j.molliq.2013.12.015).

205 T. Sheela, Y. A. Nayaka, R. Viswanatha, S. Basavanna and T. G. Venkatesha, Kinetics and thermodynamics studies on the adsorption of $\text{Zn}(\text{II})$, $\text{Cd}(\text{II})$ and $\text{Hg}(\text{II})$ from aqueous solution using zinc oxide nanoparticles, *Powder Technol.*, 2012, **217**, 163–170, DOI: [10.1016/j.powtec.2011.10.023](https://doi.org/10.1016/j.powtec.2011.10.023).

206 Q. U. Ain, M. U. Farooq and M. I. Jalees, Application of Magnetic Graphene Oxide for Water Purification: Heavy Metals Removal and Disinfection, *J. Water Proc. Eng.*, 2020, **33**, 101044, DOI: [10.1016/j.jwpe.2019.101044](https://doi.org/10.1016/j.jwpe.2019.101044).

207 L. R. Rad, A. Momeni, B. F. Ghazani, M. Irani, M. Mahmoudi and B. Noghreh, Removal of Ni^{2+} and Cd^{2+} ions from aqueous solutions using electrospun PVA/zeolite nanofibrous adsorbent, *Chem. Eng. J.*, 2014, **256**, 119–127, DOI: [10.1016/j.cej.2014.06.066](https://doi.org/10.1016/j.cej.2014.06.066).

208 T. Madrakian, A. Afkhami, B. Zadpour and M. Ahmadi, New synthetic mercaptoethylamino homopolymer-modified maghemite nanoparticles for effective removal of some heavy metal ions from aqueous solution, *J. Ind. Eng. Chem.*, 2015, **21**, 1160–1166, DOI: [10.1016/j.jiec.2014.05.029](https://doi.org/10.1016/j.jiec.2014.05.029).

209 F. Almomani, R. Bhosale, M. Khrasheh, A. kumar and T. Almomani, Heavy metal ions removal from industrial wastewater using magnetic nanoparticles (MNP), *Appl. Surf. Sci.*, 2020, **506**, 144924, DOI: [10.1016/j.apsusc.2019.144924](https://doi.org/10.1016/j.apsusc.2019.144924).

210 M. S. Islam, W. S. Choi, B. Nam, C. Yoon and H. J. Lee, Needle-like iron oxide@ CaCO_3 adsorbents for ultrafast removal of anionic and cationic heavy metal ions, *Chem. Eng. J.*, 2017, **307**, 208–219, DOI: [10.1016/j.cej.2016.08.079](https://doi.org/10.1016/j.cej.2016.08.079).

211 A. Afkhami, M. Saber-Tehrani and H. Bagheri, Simultaneous removal of heavy-metal ions in wastewater samples using nano-alumina modified with 2,4-dinitrophenylhydrazine, *J. Hazard. Mater.*, 2010, **181**(1–3), 836–844, DOI: [10.1016/j.jhazmat.2010.05.089](https://doi.org/10.1016/j.jhazmat.2010.05.089).

212 N. A. S. Feisal, N. H. Kamaludin, M. A. Ahmad and T. N. B. Tengku Ibrahim, A comprehensive review of nanomaterials for efficient heavy metal ions removal in water treatment, *J. Water Proc. Eng.*, 2024, **64**, 105566, DOI: [10.1016/j.jwpe.2024.105566](https://doi.org/10.1016/j.jwpe.2024.105566).

213 H. Sable, V. Kumar, V. Singh, S. Rustagi, S. Chahal and V. Chaudhary, Strategically engineering advanced nanomaterials for heavy-metal remediation from wastewater, *Coord. Chem. Rev.*, 2024, **518**, 216079, DOI: [10.1016/j.ccr.2024.216079](https://doi.org/10.1016/j.ccr.2024.216079).

214 A. Jawed, V. Saxena and L. M. Pandey, Engineered nanomaterials and their surface functionalization for the removal of heavy metals: A review, *J. Water Proc. Eng.*, 2020, **33**, 101009, DOI: [10.1016/j.jwpe.2019.101009](https://doi.org/10.1016/j.jwpe.2019.101009).

215 A. E. Burakov, *et al.*, Adsorption of heavy metals on conventional and nanostructured materials for wastewater treatment purposes: A review, *Ecotoxicol. Environ. Saf.*, 2018, **148**, 702–712, DOI: [10.1016/j.ecoenv.2017.11.034](https://doi.org/10.1016/j.ecoenv.2017.11.034).

216 R. Janani, B. Gurunathan, K. Sivakumar, S. Varjani, H. H. Ngo and E. Gnansounou, Advancements in heavy metals removal from effluents employing nano-adsorbents: Way towards cleaner production, *Environ. Res.*, 2022, **203**, 111815, DOI: [10.1016/j.envres.2021.111815](https://doi.org/10.1016/j.envres.2021.111815).

217 E. Pérez-Botella, S. Valencia and F. Rey, Zeolites in Adsorption Processes: State of the Art and Future Prospects, *Chem. Rev.*, 2022, **122**(24), 17647–17695, DOI: [10.1021/acs.chemrev.2c00140](https://doi.org/10.1021/acs.chemrev.2c00140).

218 M. K. de Pietre and J. C. C. Freitas, Fundamental studies on zeolite-adsorbate interactions: designing a better aluminosilicate adsorbent for pollutants' removal, *Environ. Earth Sci.*, 2022, **81**(1), 17, DOI: [10.1007/s12665-021-10130-w](https://doi.org/10.1007/s12665-021-10130-w).

219 M. Senila and O. Cadar, Modification of natural zeolites and their applications for heavy metal removal from polluted environments: Challenges, recent advances, and perspectives, *Heliyon*, 2024, **10**(3), 1–17, DOI: [10.1016/j.heliyon.2024.e25303](https://doi.org/10.1016/j.heliyon.2024.e25303).

220 E. I. Ugwu, A. Othmani and C. C. Nnaji, A review on zeolites as cost-effective adsorbents for removal of heavy metals from aqueous environment, *Int. J. Environ. Sci. Technol.*, 2022, **19**(8), 8061–8084, DOI: [10.1007/s13762-021-03560-3](https://doi.org/10.1007/s13762-021-03560-3).

221 M. De Silva, G. Cao and K. C. Tam, Nanomaterials for the removal and detection of heavy metals: a review, *Environ. Sci. Nano*, 2025, **12**(4), 2154–2176, DOI: [10.1039/d4en01041h](https://doi.org/10.1039/d4en01041h).

222 B. Natarajan, P. Kannan, J. A. Rather and R. A. Sheikh, Recent developments in metal nanoparticles functionalized nanocomposite adsorbents for heavy



metals removal from wastewaters, *J. Taiwan Inst. Chem. Eng.*, 2023, **147**, 104942, DOI: [10.1016/j.jtice.2023.104942](https://doi.org/10.1016/j.jtice.2023.104942).

223 S. Singh, D. Kapoor, S. Khasnabis, J. Singh and P. C. Ramamurthy, Mechanism and kinetics of adsorption and removal of heavy metals from wastewater using nanomaterials, *Environ. Chem. Lett.*, 2021, **19**(3), 2351–2381, DOI: [10.1007/s10311-021-01196-w](https://doi.org/10.1007/s10311-021-01196-w).

224 N. Meky, E. Salama, M. F. Soliman, S. G. Naeem, M. Ossman and M. Elsayed, Synthesis of Nano-silica Oxide for Heavy Metal Decontamination from Aqueous Solutions, *Water Air Soil Pollut.*, 2024, **235**(2), 1–23, DOI: [10.1007/s11270-024-06944-6](https://doi.org/10.1007/s11270-024-06944-6).

225 M. N. Abonyi, C. C. Obi and J. T. Nwabanne, Degradation of organic pollutants in wastewater using MOF-based catalysts: A review, *Next Mater.*, 2025, **8**, 100696, DOI: [10.1016/j.nxmate.2025.100696](https://doi.org/10.1016/j.nxmate.2025.100696).

226 A. Kumar, M. Rachamalla, and A. Adarsh, Case Studies (Success Stories) on the Application of Metal-Organic Frameworks (MOFs) in Wastewater Treatment and Their Implementations; Review, in *Metal Organic Frameworks for Wastewater Contaminant Removal*, Wiley-VCH GmbH, 2023, pp. 151–176, DOI: [10.1002/9783527841523.ch7](https://doi.org/10.1002/9783527841523.ch7).

227 H. Kaur, N. Devi, S. S. Siwal, W. F. Alsanie, M. K. Thakur and V. K. Thakur, Metal-Organic Framework-Based Materials for Wastewater Treatment: Superior Adsorbent Materials for the Removal of Hazardous Pollutants, *ACS Omega*, 2023, **8**(10), 9004–9030, DOI: [10.1021/acsomega.2c07719](https://doi.org/10.1021/acsomega.2c07719).

228 D. Li, A. Yadav, H. Zhou, K. Roy, P. Thanasekaran and C. Lee, Advances and Applications of Metal-Organic Frameworks (MOFs) in Emerging Technologies: A Comprehensive Review, *Glob. Chall.*, 2024, **8**(2), 1–32, DOI: [10.1002/gch2.202300244](https://doi.org/10.1002/gch2.202300244).

229 P. Wu, *et al.*, Opportunities and Challenges of Metal-Organic Framework Micro/Nano Reactors for Cascade Reactions, *JACS Au*, 2023, **3**(9), 2413–2435, DOI: [10.1021/jacsau.3c00344](https://doi.org/10.1021/jacsau.3c00344).

230 W. Liu, Y. Liu, Z. Yuan and C. Lu, Recent advances in the detection and removal of heavy metal ions using functionalized layered double hydroxides: a review, *Ind. Chem. Mater.*, 2023, **1**(1), 79–92, DOI: [10.1039/d2im00024e](https://doi.org/10.1039/d2im00024e).

231 F. Lyu, H. Yu, T. Hou, L. Yan, X. Zhang and B. Du, Efficient and fast removal of Pb²⁺ and Cd²⁺ from an aqueous solution using a chitosan/Mg-Al-layered double hydroxide nanocomposite, *J. Colloid Interface Sci.*, 2019, **539**, 184–193, DOI: [10.1016/j.jcis.2018.12.049](https://doi.org/10.1016/j.jcis.2018.12.049).

232 R. Bi, D. Yin, S. Zhang, R. Zhang and F. Chen, Efficient removal of Pb(II) and Hg(II) with eco-friendly polyaspartic acid/layered double hydroxide by host-guest interaction, *Appl. Clay Sci.*, 2022, **225**(106536), 1, DOI: [10.1016/j.clay.2022.106536](https://doi.org/10.1016/j.clay.2022.106536).

233 M. Mubarak, *et al.*, One-pot synthesis of layered double hydroxide hollow nanospheres with ultrafast removal efficiency for heavy metal ions and organic contaminants, *Chemosphere*, 2018, **201**, 676–686, DOI: [10.1016/j.chemosphere.2018.03.046](https://doi.org/10.1016/j.chemosphere.2018.03.046).

234 W. S. Abo El-Yazeed, Y. G. Abou El-Reash, L. A. Elatwy and A. I. Ahmed, Novel bimetallic Ag-Fe MOF for exceptional Cd and Cu removal and 3,4-dihydropyrimidinone synthesis, *J. Taiwan Inst. Chem. Eng.*, 2020, **114**, 199–210, DOI: [10.1016/j.jtice.2020.09.028](https://doi.org/10.1016/j.jtice.2020.09.028).

235 J. Feng, G. Zhi, X. Qi and M. Geng, Efficient Adsorption of Arsenic from Smelting Wastewater by CoMn-MOF-74 Bimetallic Composites, *Sustainability*, 2025, **17**(7), 1–18, DOI: [10.3390/su17073060](https://doi.org/10.3390/su17073060).

236 A. Z. M. Badruddoza, Z. B. Z. Shawon, W. J. D. Tay, K. Hidajat and M. S. Uddin, Fe 3O 4/cyclodextrin polymer nanocomposites for selective heavy metals removal from industrial wastewater, *Carbohydr. Polym.*, 2013, **91**(1), 322–332, DOI: [10.1016/j.carbpol.2012.08.030](https://doi.org/10.1016/j.carbpol.2012.08.030).

237 A. H. Birniwa, *et al.*, Polymer-Based Nano-Adsorbent for the Removal of Lead Ions: Kinetics Studies and Optimization by Response Surface Methodology, *Separations*, 2022, **9**(11), 1, DOI: [10.3390/separations9110356](https://doi.org/10.3390/separations9110356).

238 M. R. Mirbaloochzehi, A. Rezvani, A. Samimi and M. Shayesteh, Application of a Novel Surfactant-Modified Natural Nano-Zeolite for Removal of Heavy Metals from Drinking Water, *Adv. J. Chem. A*, 2020, **3**, 612–620, DOI: [10.33945/SAMI/AJCA.2020.5.6](https://doi.org/10.33945/SAMI/AJCA.2020.5.6).

239 X. Zhang, *et al.*, Synthesis of a novel magnetic nano-zeolite and its application as an efficient heavy metal adsorbent, *Mater. Res. Express*, 2020, **7**(8), 1–17, DOI: [10.1088/2053-1591/abab43](https://doi.org/10.1088/2053-1591/abab43).

240 C. Bulin, *et al.*, Graphene oxide-starch composite as an efficient adsorbent for removing Cu(II): removal performance and adsorption mechanism, *Res. Chem. Intermed.*, 2021, **47**(9), 3825–3852, DOI: [10.1007/s11164-021-04487-7](https://doi.org/10.1007/s11164-021-04487-7).

241 M. Kamel, A. M. Bastawesy and R. A. Hefny, Optimized Removal of Cr (VI) and Ni (II) From Wastewater Using Corncob-Derived Activated Carbon, *Water Air Soil Pollut.*, 2025, **236**(2), 1–22, DOI: [10.1007/s11270-024-07711-3](https://doi.org/10.1007/s11270-024-07711-3).

242 R. M. Amin, R. K. Mahmoud, Y. Gadelhak and F. I. Abo El-Ela, Gamma irradiated green synthesized zero valent iron nanoparticles as promising antibacterial agents and heavy metal nano-adsorbents, *Environ. Nanotechnol. Monit. Manag.*, 2021, **16**(100461), 1–13, DOI: [10.1016/j.jenmm.2021.100461](https://doi.org/10.1016/j.jenmm.2021.100461).

243 M. ŞAhıN, M. Atasoy, Y. Arslan and D. Yıldız, Removal of Ni(II), Cu(II), Pb(II), and Cd(II) from Aqueous Phases by Silver Nanoparticles and Magnetic Nanoparticles/Nanocomposites, *ACS Omega*, 2023, **8**(38), 34834–34843, DOI: [10.1021/acsomega.3c04054](https://doi.org/10.1021/acsomega.3c04054).

244 A. K. Mitra and S. Nayak, Sustainable Nanomaterials in Wastewater Remediation, in *Nanomaterials in Wastewater Research: Progress and Challenges*, ed. N. Agarwal, M. P. Shah, S. Vijendra Singh, and S. Neetu, Springer Nature, 2025, ch. 7, pp. 159–188, DOI: [10.1007/978-981-96-3908-3_7](https://doi.org/10.1007/978-981-96-3908-3_7).

245 P. K. Patel, H. K. Singh, and A. Singh, Waste Water Remediation and Nanoadsorbents, in *Nanomaterials in Wastewater Research: Progress and Challenges*, ed. N. Agarwal, M. P. Shah, S. Vijendra Singh, and S. Neetu,



Springer Nature, 2025, ch. 10, pp. 235–257, DOI: [10.1007/978-981-96-3908-3_10](https://doi.org/10.1007/978-981-96-3908-3_10).

246 M. Bharti, S. Kumar, and M. K. Purkait, A Sustainable Approach to Wastewater Remediation Using Nano-adsorbents, in *Nanomaterials in Wastewater Research: Progress and Challenges*, ed. N. Agarwal, M. P. Shah, S. Vijendra Singh, and S. Neetu, Springer Nature, 2025, ch. 11, pp. 259–283, DOI: [10.1007/978-981-96-3908-3_11](https://doi.org/10.1007/978-981-96-3908-3_11).

247 S. Dullah, *et al.*, Current Perspectives of Nanomaterials in Wastewater Treatment for Sustainable Environment, in *Nanomaterials in Wastewater Research: Progress and Challenges*, ed. N. Agarwal, M. P. Shah, S. Vijendra Singh, and S. Neetu, Springer Nature, 2025, ch. 17, pp. 399–415, DOI: [10.1007/978-981-96-3908-3_17](https://doi.org/10.1007/978-981-96-3908-3_17).

248 B. S. Ramadan, Y. G. Wibowo, D. Anwar and A. T. Maryani, A Review of Life Cycle Assessment of Nanomaterials-Based Adsorbent for Environmental Remediation, *Glob. Nest J.*, 2024, **26**(7), 6216, DOI: [10.30955/gnj.006216](https://doi.org/10.30955/gnj.006216).

249 S. Satyam and S. Patra, Innovations and challenges in adsorption-based wastewater remediation: A comprehensive review, *Helijon*, 2024, **10**(9), 1–24, DOI: [10.1016/j.heliyon.2024.e29573](https://doi.org/10.1016/j.heliyon.2024.e29573).

250 A. M. Badran, U. Utra, N. S. Yussof and M. J. K. Bashir, Advancements in Adsorption Techniques for Sustainable Water Purification: A Focus on Lead Removal, *Separations*, 2023, **10**(565), 1–26, DOI: [10.3390/separations10110565](https://doi.org/10.3390/separations10110565).

251 C. A. Robbins, *et al.*, Beyond treatment technology: Understanding motivations and barriers for wastewater treatment and reuse in unconventional energy production, *Resour. Conserv. Recycl.*, 2022, **177**, 106011, DOI: [10.1016/j.resconrec.2021.106011](https://doi.org/10.1016/j.resconrec.2021.106011).