View Article Online

Journal of Materials Chemistry C

Materials for optical, magnetic and electronic devices

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: T. Oka, T. Maeda, D. Sakamaki, H. Fujiwara, N. Suzuki, S. Kodama, S. Yagi, L. Mauri and K. Kamada, *J. Mater. Chem. C*, 2025, DOI: 10.1039/D5TC00973A.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the Information for Authors.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/materials-c

ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Croconaine Dyes with Intermediate Diradical Character Exhibiting Intense One- and Two-Photon Absorption in the Short-Wavelength Infrared Region

Taishi Oka,^a Takeshi Maeda,*^a Daisuke Sakamaki,^b Hideki Fujiwara,*^b Naoya Suzuki,^a

Shintaro Kodama,^a Shigeyuki Yagi,^a Luca Mauri^{c,d} and Kenji Kamada^{*c}

Intense one-photon absorption (OPA) and two-photon absorption (TPA) in the short-wavelength infrared (SWIR) region are achieved with chalcogenopyrylium-based croconaine dyes with intermediate diradical character by the synergistic effects of an enhanced degree of diradical character through substitution with heavy chalcogen atoms (O, S, and Se) and the extension of π -conjugation via the incorporation of phenyl groups. X-Ray crystal structure analysis, temperature-dependent ¹H-NMR, and ESR spectra revealed the intermediate diradical character of the croconaine dyes, with the contribution of the diradical form increasing with the atomic number of the chalcogen elements, in the order O < S < Se. As the atomic number of the chalcogen elements, in garticular, demonstrate strong OPA in the SWIR region, with absorption maxima at 1046 nm and 1096 nm, respectively. Furthermore, TPA spectra measured using the Z-scan technique reveal that dyes containing O, S, and Se exhibit large TPA cross sections of 1008 GM at 1255 nm, 1011 GM at 1395 nm, and 1177 GM at 1445 nm, respectively. The absorption bands shift to lower energy regions, similar to the OPA bands, with the cross section increasing with the atomic number of the diradical character of croconaine dyes using the z-scan technique reveal that dyes containing the atomic number of the chalcogen element. These results indicate that chalcogen atoms not only play a crucial role in modulating the intermediate diradical character of croconaine dyes but also significantly influence their OPA and TPA properties.

Introduction

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Access Article. Published on 07 May 2025. Downloaded on 5/9/2025 4:26:39 PM

Short-wavelength infrared (SWIR) radiation, with wavelengths longer than 1000 nm, exhibits high penetration through a wide range of materials, making it ideal for nondestructive testing in industrial and agricultural applications.¹⁻² Its limited scattering and absorption in biological tissues further enhance its potential for deep-tissue imaging and photodynamic therapy.³⁻⁵ These advantageous properties of SWIR also simulate developing materials that efficiently absorb this radiation. While inorganic semiconductors such as InGaAs are effective at absorbing SWIR radiation⁶⁻⁸, they contain rare and toxic elements, emphasizing the need for more sustainable and non-toxic alternatives.

Organic materials offer a promising alternative for SWIR absorption, as their structural diversity enables precise tuning of the orbital energy levels involved in electronic transitions.⁹⁻¹¹

SWIR-absorbing organic molecules typically feature an extended π -electron system that links strong electron donors and acceptors.¹²⁻¹⁴ This arrangement promotes resonance, where electron push-pull effects between donors and acceptors reduce bond alternation and suppress Peierls distortion, also known as the pseudo Jahn-Teller effect.¹⁵⁻¹⁶ Molecules with intermediate diradical character, referred to as diradicaloids, serve as effective SWIR absorbers, with closed-shell and openshell resonance structures that reflect their degree of openshell character (Fig. 1A).¹⁷⁻²⁰ This property is quantified by the diradical character (y_0) , where a value of 1 indicates a fully openshell state, and 0 indicates a fully closed-shell state and $1-y_0$ means its bond order.²¹ Following the pioneering work of Chichibabin²² and Müller,²³ researchers have developed a diverse range of diradicaloids with both Kekulé and non-Kekulé structures.²⁴⁻²⁹ Recently, compounds such as polymers³²⁻³³ diketopyrrolopyrroles³⁰⁻³¹ and certain previously considered closed-shell—have exhibited intermediate diradical character, broadening the potential of organic materials for SWIR absorption.

In diradicaloids, the π bonds can be considered partially dissociated due to the contribution of the diradical forms, making the electron density along the π -conjugated system more susceptible to distortion under electromagnetic fields induced by high-intensity laser irradiation. As a result, they exhibit intense two-photon absorption (TPA), which is a third-

^{a.} Department of Applied Chemistry, Graduate School of Engineering, Osaka Metropolitan University, Naka-ku, Sakai, Osaka 599-8531, Japan

^b Department of Chemistry, Graduate School of Science, Osaka Metropolitan University, Sumiyoshi-ku, Osaka 558-8585, Japan

^c Nanomaterials Research Institute (NMRI), National Institute of Advanced Industrial Science and Technology (AIST) Ikeda, Osaka 563-8577, Japan

^{d.} Chemistry Department, Università degli Studi di Milano, UdR dell'INSTM, Via Golgi 19, Milano 20133, Italy

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

nal of Materials Chemistry C Accepted

Journal Name

nonlinear optical (NLO) process involving the order simultaneous absorption of two photons through a virtual state in response to laser irradiation (Fig. 1B).³⁴⁻³⁶ As an illustration of the substantial influence of intermediate diradical character on TPA properties, Kamada et al. demonstrated that the TPA crosssection of a bis(acridine) dimer, which exhibits intermediate diradical character in its oxidized state, is over two orders of magnitude higher than that of the corresponding dimer in its lower oxidation state, which possesses a closed-shell electronic

ARTICLE



Fig. 1 (A) Correlation between orbital interactions and electronic structure: The closed-shell electronic structure resulting from orbital interactions (left, diradical character $y_0 = 0$), the open-shell electronic state without orbital interactions (right, $y_0 = 1$), and the intermediate state between the closed-shell and open-shell configurations (center, $0 < y_0 < 1$). (B) Three-state model of the TPA process, consisting of the ground state, virtual state, and excited state, where the one-photon transition is forbidden and the two-photon transition is allowed in symmetric molecular systems. (C) TPA cross-section ($\sigma^{(2)}$), with the maximum absorption wavelength for TPA in parentheses, for the bis(acridine) dimer (left) and its oxidized state with intermediate diradical character (right). (D) Structures and TPA properties bisphenalenyl derivatives (left) benzo-thia-fused of and [n]thienoacenequinodimethane (right).

configuration (Fig. 1C).³⁷ Similarly, bisphenalenyliand then zoa thia-fused [n]thienoacenequinodimethaneliderivatives, which also exhibit intermediate diradical character, show large TPA cross-sections (Fig. 1D).38-39

For closed-shell molecules, it is well-established both extending π-conjugated systems and incorporating donoracceptor structures can enhance the TPA cross section.^{36,40} In addition to these two axes of molecular design, which form a 2D-plane containing closed-shell molecules, the diradical character can be the third axis of the degrees of freedom, which expanded the dimensionality of the molecular design (Fig. 2A). With this third axis, further enhancement of TPA can be expected. This strategy is expected to promote the development of TPA materials for applications such as threedimensional laser microfabrication⁴¹⁻⁴⁴, 3D fluorescent imaging⁴⁴⁻⁴⁵, and photodynamic therapy.⁴⁵⁻⁴⁹

We previously demonstrated that croconaine dyes, featuring a five-membered oxocarbon ring and a (thio)pyrylium skeleton (CR1a and CR1b) exhibited intermediate diradical character ($y_0 = 0.63$, 0.70 respectively) and showed strong TPA in the SWIR region ($\sigma^{(2)}$ = 750 GM at 1290 nm as the maximum of **CR1b**)(Fig. 2B).⁵⁰ This is the first report on the intermediate diradical character and TPA properties of croconaine dyes to our best knowledge. This report suggests that croconaine dyes have potential as excellent TPA materials, similar to polymethine dyes such as cyanine dyes, which exhibit relatively intense TPA.⁵¹⁻⁵³ In contrast to polymethine dyes, croconaine dyes exhibit an additional axis of diradical character, in addition to



Fig. 2 (A) Design axes of molecular TPA materials: donor-acceptor substitution, π extension, and diradical character. (B) Structures of croconaine dyes comprising phenyl-substituted chalcogenopyrylium components (CR2a-c).

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Open Access Article. Published on 07 May 2025. Downloaded on 5/9/2025 4:26:39 PM.

Journal Name

the extension of the π -conjugated system and the modulation of the donor and acceptor strengths in the chromophore. These properties can be fine-tuned by replacing the oxygen atom in the pyrylium skeleton with a heavier heteroatom, such as sulfur in a thiopyrylium skeleton.^{50,54-56} As illustrated in Fig. 2A with blue/red arrows, tuning of the degree of intermediate diradical character by replacing heavy atom and expansion of the π conjugation have possibility of further enhancement of the TPA properties. These factors also enable the fine-tuning of the transition energy associated with TPA.

In this study, we synthesized croconaine dyes by replacing chalcogen atom in the chalcogenopyrylium ring from O to S, to Se for wider tuning diradical charter, enhancing both onephoton absorption (OPA) and TPA in the SWIR region (Fig. 2C). Additionally, we functionalized the chalcogenopyrylium core by introducing phenyl groups at the 2,5-positions to extend the πconjugation, aiming to achieve a further red shift in both OPA and TPA. We investigated the effects of both the substitutions of chalcogen elements and phenyl groups on the intermediate diradical character, as well as the combined impact of the intermediate diradical character and the extended π conjugated system on the OPA and TPA behaviors.

Results and discussion

Synthesis and Diradical Character

Croconaine dyes with oxygen (CR2a), sulfur (CR2b), and selenium (CR2c) as chalcogen atoms were synthesized by condensation of croconic acid with the corresponding chalcogenopyrylium perchlorates (see Supplementary Information). In solution, these dyes exhibited no evidence of degradation under conditions of complete darkness. (Fig. S1). Thermal gravimetric analysis of the solid-state samples revealed that the dyes possess high thermal stability (Fig. S2). These stability data validate the reliability of the subsequent measurements. The diradical character y_0 for the optimized structures of CR2a-c, obtained at the CAM-UB3LYP/6-31G(d,p) level, was calculated using spin-projected unrestricted Hartree-Fock (PUHF) theory with a 6-31G(d,p) basis set.⁵⁷ The resulting values for **CR2a**, **CR2b**, and **CR2c** were $y_0 = 0.69$, 0.81, and 0.82, respectively.

X-Ray Structures

A single crystal of CR2c was successfully obtained through the solvent diffusion method with a 1,1,2,2-tetrachloroethanehexane system. The X-Ray crystal structures of CR2c are shown Fig. 3, with detailed data provided in the Supplementary Information. CR2c has a structure in which the central cyclopentenedione and the selenopyrylium components are coplanar in a *cisoid* configuration. The four phenyl groups on the selenopyrylium are oriented at a dihedral angle of approximately 20° and 32° relative to the molecular plane (Fig. 3A). CR2c forms a dimer with a nearest-neighbor distance of 3.18 Å, and the dimers stack with a separation of 3.36 Å (Fig. 3B). Thus, the high planarity of **CR2c** promotes $\pi-\pi$ stacking interactions in the crystal, leading to dimer formation and resulting in the dense packing of the dimers.

As mentioned earlier, molecules with intermediate diradical character exhibit both closed-shell and open-shell contributions, and the relative contribution of each resonance structure, with its distinct electron configuration, influences the bond lengths.³⁷ CR2c is expected to have multiple resonance structures due to its extended π -electron system (Fig. S4). These structures can be classified into two zwitterionic forms, α and β , in closed-shell configurations, and two diradical forms, where unpaired electrons are delocalized over the central fivemembered ring (γ) or the selenopyrylium ring (δ , Fig. 3C). Now,



Fig. 3 (A) A single crystal X-Ray structure of CR2c at 100 K, showing C-C bond lengths (in Å) and dihedral angles along the phenyl groups. Solvent molecules were omitted for clarity. (B) Its packing structure (top and side views) with nearest-neighbor distances highlighted in red. (C) Resonance structures of CR2a-c.

ARTICLE

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

pen Access Article. Published on 07 May 2025. Downloaded on 5/9/2025 4:26:39 PM.

Journal Name

View Article Online

Table 1. Differences in average bond lengths (ΔD = ave.(a , d) – ave.(b , c)) from X-Ray and optimized structoresion CR2 b ^a TC00973.									
	Closed-shell singlet ^b / Å	X-Ray	Open-shell singlet ^c / Å	Open-shell triplet ^c / Å					
ave. (<i>a, d</i>)	1.403	1.412	1.415	1.421					
ave. (<i>b, c</i>)	1.390	1.396	1.380	1.374					
ΔD	+ 0.013	+ 0.016	+ 0.035	+0.047					

^aave.(*a*, *b*) represents the average bond length of bonds *a* and *b*. ^bCalculated at CAM-RB3LYP/6-31G(d,p) levels. ^cCalculated at CAM-UB3LYP/6-31G(d,p) levels

we focus on the outer bonds (a, d) and the inner bonds (b, c) connecting the central five-membered ring and the selenopyrylium ring, and quantify the bond length difference, ΔD = ave. (a, d) – ave. (b, c) (Fig. 3A, Table 1).

In the two closed-shell zwitterionic forms (α , β), bonds α and d(or b and c) are assigned as a pair of a double bond and a single bond, resulting in ΔD being zero. The diradical form γ , however, exhibits a negative ΔD value, as the inner bonds (b, c) are single bond and the outer bonds (a, d) are double bond. In the δ form, a positive ΔD value is observed in this bond length analysis. Actually, the X-Ray structure of CR2c confirms a positive ΔD value, suggesting that the δ form, where the unpaired electron is delocalized on the selenopyrylium ring, has a greater contribution among the four resonance forms. Additionally, we compared the ΔD values of the DFT-optimized structures of the closed-shell singlet and open-shell triplet states with those obtained from the X-Ray data. The value from the X-Ray structure (+0.016) was found to lie between those of the closedshell singlet (+0.013) and open-shell triplet states (+0.047), further supporting the intermediate diradical character of CR2c.

The spin density distributions of the croconaine dyes were calculated at the unrestricted CAM-B3LYP/6-31G level to investigate their spin delocalization (Fig. 4). The calculations revealed that spins are delocalized over the entire molecule, including the phenyl groups attached to the pyrylium moieties. Moreover, NICS(1)_{zz} values were calculated to evaluate the aromaticity of each ring.⁵⁸ The peripheral phenyl rings showed NICS(1)_{zz} values below -10, confirming that they are aromatic, while the central cyclopentenetrione and chalcogenopyrylium rings exhibited values between -1.9 and -1.6, indicating reduced aromaticity (as shown in Fig. 4C).

NMR and ESR studies

The ¹H NMR spectra of these dyes displayed characteristics of molecules with intermediate diradical character. As a representative case, variable temperature (VT)-¹H NMR spectra of **CR2c** in CDCl₃ are shown in Fig. 5. Although sharp signals for protons at aromatic groups were observed at 213 K, they gradually broadened as the temperature increased, and completely disappeared at 313 K. The observed temperature dependence of ¹H NMR is typical of diradicaloids, which have a contribution of thermally populated triplet species. The similar temperature dependence of the ¹H NMR spectra was observed for **CR2a** and **CR2b** (Fig. S5-6). However, the temperature at which the signal disappeared varied among the compounds. **CR2a** showed the signal disappearance at 333 K, whereas **CR2b** and **CR2c** exhibited it at 313 K. This difference is likely due to the varying triplet energy levels, suggesting that **CR2b** and **CR2c** are thermally excited to their triplet states at lower temperatures than **CR2a**.

Furthermore, the electron spin resonance (ESR) spectra of each dye were recorded to confirm the presence of unpaired



Fig. 4 Mulliken spin density maps of open-shell singlet states for **CR2a** (A), **CR2b** (B) and **CR2c** (C), calculated at the CAM-UBLYP/6-31G(d,p) level of theory with an isovalue of 0.002 (green: up spin; blue: down spin). The calculation for **CR2c** was performed using the X-Ray structure, while **CR2a-b** were based on DFT-optimized structures. NICS(1)_{sz} values for the selenopyrylium rings, phenyl groups, and five-membered ring, calculated at the GAIO UB3LYP/6-31G level, are shown in red.



Fig. 5 Variable temperature ¹H-NMR spectra (CDCl₃, 213–313 K) of CR2c along with a diagram illustrating thermal excitation from singlet to triplet states

electrons arising from thermally populated triplet states (Fig. 6A). In 1,1,2,2-tetrachloroethane at 303 K, CR2c displayed a broad ESR signal at g = 2.003. Unlike the behavior observed in the ¹H NMR spectra, the ESR signal intensified with increasing temperature, indicating the presence of unpaired electrons from a thermally populated triplet state. In the solid state, CR2c exhibited a more complex ESR signal than in solution (Fig. 6B). X-Ray crystal structure analysis revealed intermolecular interactions in the crystalline state for CR2c. These interactions are thought to influence electron spin coupling in the solid state,



Fig. 6 ESR spectra of the solution sample in 1,1,2,2-tetrachloroethane (A, q = 2.003) and the solid sample (B, g = 2.001) of **CR2c**. Temperature- $I_{ESR}T$ plots based on ESR data of the solution samples of CR2a (red), CR2b (green), and CR2c (blue) (C). The lines are the fitted plots by using the Bleaney-Bowers equation.

leading to the observed changes in the ESR signal. $_{\rm View \ Article \ Online}$ A similar trend was observed for the solutions of CR2a 374d CR2b, which also exhibited the increase in the ESR intensities upon heating (Fig. S8). The plots of ESR signal intensity (I_{ESR}) multiplied by temperature (T) as a function of temperature are shown in Fig. 6C. For all three dyes, *I*_{ESR}*T* increased with an increase in temperature. To estimate the energy difference between the singlet and thermally accessible triplet states (ΔE_{s-} $_{\rm T}$), the data were fitted to the Bleaney–Bowers equation (see Supplementary Information).⁵⁹ The curve-fitting analysis yielded ΔE_{S-T} values of 0.169, 0.164, and 0.148 eV for **CR2a**, CR2b, and CR2c, respectively. These results show a trend where the ΔE_{S-T} decreases as the atomic number of the chalcogens increases. The relatively small ΔE_{S-T} values suggest weak electron-electron interactions within the molecule, accompanied by a substantial contribution from the diradical form. Thus, the contribution of diradical forms increases in the order of CR2a, CR2b, and CR2c, which is consistent with the trend observed in the diradical character y_0 obtained from quantum chemical calculations.

One-Photon Absorption and Fluorescence Properties

The OPA and fluorescence emission spectra of CR2a-c in CHCl₃ are shown in Fig. 7. Detailed data, including absorption and emission maxima as well as molar extinction coefficients, are provided in Table 2. CR2a and CR2b exhibit absorption maxima at 955 nm and 1047 nm, respectively, with corresponding molar extinction coefficients of 3.3 × 10⁵ and 1.8 × 10⁵ M⁻¹ cm⁻¹. These OPA bands are red-shifted by approximately 100 nm (360 cm⁻¹ for CR2a and 477 cm⁻¹ for CR2b) compared to those of the tert-butyl-substituted chalcogenopyrylium analogues,⁴⁹ mainly due to the π conjugation extension by the substitution of *tert*-butyl groups with phenyl groups. The OPA maximum of CR2c, which contains a selenopyrylium moiety, was red-shifted by 49 nm (427 cm⁻¹) relative to CR2b, reaching 1096 nm. TD-DFT calculations for CR2a-c reveal that the absorption maxima of these dyes correspond to S₀–S₁ transitions, with the dominant contribution arising from the electronic transitions between the HOMOs and LUMOs (see Supplementary Information, Table S3).



Fig. 7 Normalized electronic absorption spectra (solid line) and emission spectra (dot line) (CHCl₃, r. t., conc. 5×10^{-6} M) of CR2a (red), CR2b (green), and CR2c (blue).

C ACCEDTEO

mistr

Materials Che

Vanus

ACCED

Journal Name

ARTICLE

Table 2. Differences in average bond lengths (ΔD = ave.(a, d) – ave.(b, c)) from X-Ray and optimized structures of **CR2c**.^a

Dye	λ _{οΡΑ} ^α / nm	ε ^b / 10 ⁵ M ⁻¹ cm ⁻ 1	λ _{ΡL} ° / nm	Stokes shift / cm ⁻¹	λ_{TPA}^{d} D	View Agricle Online OI: 10.1039/D5TC00973A / GM
CR2a	955	3.30	989	360	1255	1008 ± 136
CR2b	1047	1.83	1102	477	1395	1011 ± 202
CR2c	1096	1.64	N.D.	N.D.	1445	1177 ± 193

^aOPA maxima in CHCl₃ (conc. 5 × 10⁻⁶ M). ^bMolar absorption coefficient. ^cEmission maxima in CHCl₃ (conc. 5 × 10⁻⁶ M, excitation at 430 nm). ^dTPA maxima in CHCl₃ (conc. 0.44 mM for CR2a, 0.49 mM for CR2b, and 0.47 mM for CR2c) obtained by Z-scan technique. "TPA cross section ($\sigma^{(2)}$) was expressed in the Göppert-Mayer (GM) unit defined as 1 GM = 10^{-50} cm⁴ s molecule⁻¹ photon⁻¹.

These results demonstrate that the extension of π -conjugation through the phenyl substitution, coupled with the orbital expansion by the heavy chalcogen elements, contributes to the observed red-shift and enables SWIR absorption in these dyes. Fabian et al. predicted a correlation between diradical character and transition energy, describing that an increase in diradical contribution leads to a decrease in transition energy. Consistent with this prediction, the diradical character increases in the order CR2a < CR2b < CR2c, while their transition energies decrease in the reverse order CR2a > CR2b > CR2c.

According to the energy band gap law, organic compounds with transition energies in the SWIR region are expected to show weak fluorescence.⁶⁰ As anticipated, CR2c, which has the lowest transition energy, exhibited negligible fluorescence at r. t.

In contrast. CR2a and CR2b exhibited fluorescence in the SWIR region with maxima (λ_{em}) at 989 nm and 1102 nm, respectively, although their quantum yields were too low to evaluate. Thus, it remains difficult to achieve substantial SWIR emission in this class of dyes.

Two-Photon Absorption Properties

From the above studies, it was shown that the croconaine dyes in this work exhibit intermediate diradical character, and the relative degree of their diradical contributions has been clarified. Based on this, we investigated the correlation between diradical character and TPA properties. The TPA properties of CR2a-c were examined using the femtosecond Zscan technique (see ESI). Representative Z-scan traces are presented in Fig. 8. The excitation intensity dependence proved the nonlinear absorption signal (dip in the trace) originated from TPA process (Fig. S9-11). By scanning the wavelength, their TPA spectra were obtained. All dyes exhibited a distinct,



Fig 8. Open-aperture Z-scan traces, the normalized transmittance $T_{\rm N}$ curves against the sample position z, of (a) CR2a, (b) CR2b, and (c) CR2c in CHCl₃ (0.44, 0.49, and 0.47 mM) at 1255, 1395, and 1454 nm (red square) with theoretical fits (grey curves, see ESI) and blank solvent (green cross) at different excitation intensity I_0 of 190, 153, and 158 GW cm⁻², respectively.

intense TPA band in the SWIR region (Fig. 9, Table 2), with TPA maxima observed at 1255, 1395, and 1445 nm for CR2a, CR2b, and CR2c, respectively. This trend in TPA transition energies



Fig. 9 TPA spectra in the cross section $\sigma^{(2)}$ (symbols, left and bottom axes) of CR2a (A), CR2b (B) and CR2c (C) in CHCl₃ together with the corresponding OPA spectra (black dashed line, right and top axes). λ_{TPA} comes at the same horizontal position of 2 × λ_{OPA} . resulting in the same transition energies for TPA and OPA comes at the same horizontal position. Open symbols and the filled symbols with error bars mean that the $\sigma^{\scriptscriptstyle(2)}$ data were obtained by the different measurement procedures (wavelength scan and power scan, respectively; see the ESI⁺ for details.).

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence

Open Access Article. Published on 07 May 2025. Downloaded on 5/9/2025 4:26:39 PM

Journal Name

aligns with the order observed for OPA transitions, showing an inverse correlation with diradical character. It is also noted here that the TPA transition energies differ from those of the OPA maxima, which shows Laporte's symmetry selection rule holds.³⁶ In other words, these dyes are virtually centrosymmetric on the π -conjugation backbone.

The OPA and TPA spectra of CR2a-c were simulated by DFT calculations at the CAM-B3LYP/6-31G(d,p) level (see Supplementary Information). Although the transition energies were slightly overestimated for OPA and significantly overestimated for TPA, the relative spectral positions of OPA and TPA bands matched well with experimental values (Fig. S12). The simulations suggest that the OPA and TPA transitions correspond to the $S_1 \leftarrow S_0$ and $S_4 \leftarrow S_0$ states, respectively, which supports observed fact that the transition energies of the TPA maxima differed from those of the OPA maxima. In the simulation, the relatively weak second OPA band appears on the shorter wavelength side of the TPA band assigned to the $S_4 \leftarrow S_0$ transition. In the experimental spectrum of each dye, the substantial TPA is also observed on the shorter wavelength side of the strong $S_4 \leftarrow S_0$ TPA band, likely due to resonant enhancement by the OPA.61-62

The peak $\sigma^{(2)}$ of **CR2a**, **CR2b**, and **CR2c** of the band were determined to be 1008 \pm 136, 1011 \pm 202, and 1177 \pm 193 GM, respectively (where 1 GM = 10^{-50} cm⁴ s molecule⁻¹ photon⁻¹). These are significant values in the SWIR region as this size of molecule. To compare with the benchmarks, Fig 10 shows the reported $\sigma^{(2)}$ scaled by molecular weight (M.w.) for structurally similar oxocarbon analogues (squaraine dyes SQ1b and a previously repored croconaine dye with shorter conjugation CR1b, See Fig. S14 for their structures) is plotted against the TPA peak wavelength. Clearly, it is shown that CR2a-c have the highest class values of $\sigma^{(2)}/M.w.$ in the SWIR region, compared to the closed-shell squaraine dye. This finding suggests that these croconaine dyes possess unusually large $\sigma^{(2)}$, likely due to their extended conjugation and strong donor-acceptor interactions. Furthermore, the intermediate diradical character of these dyes contribute to the observed enhancement of $\sigma^{(2)}$.



Fig. 10 Plot of the maximum TPA wavelength versus TPA cross section for each dye divided by molecular weight for squaraine and croconaine dyes (detail showed in Fig. S14, Table S5).

Conclusions

DOI: 10.1039/D5TC00973A This study highlights the relationships between intermediate diradical characters and the OPA and TPA properties of croconaine dyes with phenyl-substituted chalcogenopyrylium components (O, S, and Se) in the shortwavelength infrared (SWIR) region. X-Ray crystallography revealed that the phenyl groups are not completely orthogonal to the chalcogenopyrylium ring, which likely contributes to the expansion of the π -conjugated system. Bond length analysis based on X-Ray data, along with VT ESR and NMR measurements, indicated that these croconaine dyes exhibit intermediate diradical character. The contribution of the diradical forms increased as the chalcogen atoms became heavier (O < S < Se). Due to the extended π -conjugation and intermediate diradical character, these dyes exhibit strong OPA in the SWIR region The enhanced diradical character, driven by heavier chalcogen atoms, lowers the transition energy for both OPA and TPA, while also increasing the TPA cross section. These findings suggest that, besides adjusting the extent of π conjugation, the third axis of diradical character can be finetuned to optimize the OPA and TPA properties of croconaine dyes, making these dyes more effective for SWIR-based applications.

Author Contributions

T.O. and T.M. designed experiments, conducted synthesis of compounds, analysed data, and wrote the manuscript. D. S. and H. F. conducted X-ray crystallographic analysis, collected ESR spectra, and analysed data of ESR. N. S., S.K. and S. Y. conducted characterization of compounds. L. M. and K. K. collected and analysed OPA/TPA spectra. All authors reviewed the manuscript and agreed to its publication.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by JSPS KAKENHI Grant Numbers 24K01573, ENEOS Tonengeneral Research/Development Encouragement & Scholarship Foundation, Iketani Science and Technology Foundation, and JST, the establishment of university fellowships towards the creation of science technology innovation, Grant Number JPMJFS2138.

Notes and references

+ Electronic supplementary information (ESI) available: Synthetic procedures, experimental details. CCDC-2407572 (CR2c). For ESI and crystallographic data in CIF or other electronic format see DOI: https://doi.org/10.1039/ x0xx00000x.

ARTICLE

View Article Online

ITV C Accepted Man

S

Materials

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Access Article. Published on 07 May 2025. Downloaded on 5/9/2025 4:26:39 PM

- 1 Z.-Y. Yang, Y.-F. Zhao, Y.-Y. Zhou, J.-W. Qiao, Y.-C. Chuang, M. S. Molokeev, Z.-G. Xia, *Adv. Funct. Mater.*, 2022, **32**, 12.
- 2 J. Qiao, G. Zhou, Y. Zhou, Q. Zhang, Z. Xia, *Nat. Commun.*, 2019, **10**, 5267.
- 3 R. X. Wang, Y. Ou, Y. Chen, T.-B. Ren, L. Yuan, X. B. Zhang, J. Am. Chem. Soc., 2024, **146**, 11669–11678.
- 4 C. Y. Li, G. C. Chen, Y. J. Zhang, F. Wu, Q. B. Wang, J. Am. Chem. Soc., 2020, 142, 14789.
- 5 J. Huang, K. Pu, Angew. Chem. Int. Ed., 2020, 59, 11717.
- 6 T. Sheikh, W. J. Mir, A. Alofi, M. Skoroterski, R. Zhou, S. Nematulloev, M. N. Hedhili, M. B. Hassine, M. S. Khan, K. E. Yorov, B. E. Hasanov, H. Liao, Y. Yang, A. Shamim, M. Abulikemu, O. F. Mohammed, O. M. Bakr, J. Am. Chem. Soc., 2024, 146, 29094–29103.
- 7 H. Jalali, L. De Trizio, L. Manna, F. Di Stasio, Chem. Soc. Rev., 2022, 51, 9861–9881.
- 8 X. Guan, X. Yu, D. Periyanagounder, M. R. Benzigar, J. K. Huang, C. H. Lin, J. Kim, S. Singh, L. Hu, G. Liu, D. Li, J. H. He, F. Yan, Q. J. Wang, T. Wu, *Adv. Opt. Mater.*, 2021, **9**, 2001708.
- 9 L. M. Obloy, S. Jockusch, A. N. Tarnovsky, *Phys. Chem. Chem. Phys.*, 2024, **26**, 24261–24278.
- A. L. Antaris, H. Chen, K. Cheng, Y. Sun, G. Hong, C. Qu, S. Diao, Z. Deng, X. Hu, B. Zhang, X. Zhang, O. K. Yaghi, Z. R. Alamparambil, X. Hong, Z. Cheng, H. Dai, *Nat. Mater.*, 2016, 15, 235–242.
- Q. Yang, Z. Ma, H. Wang, B. Zhou, S. Zhu, Y. Zhong, J. Wang, H. Wan, A. Antaris, R. Ma, X. Zhang, J. Yang, X. Zhang, H. Sun, W. Liu, Y. Liang, H. Dai, *Adv. Mater.*, 2017, **29**, 1605497.
- 12 A. Ji, H. Lou, C. Qu, W. Lu, Y. Hao, J. Li, Y. Wu, T. Chang, H. Chen, Z. Cheng, *Nat. Commun.*, 2022, **13**, 3815.
- 13 Q. Wu, Z. Kang, Q. Gong, X. Guo, H. Wang, D. Wang, L. Jiao, E. Hao, *Org. Lett.*, 2020, **22**, 7513.
- S. Zhu, R. Tian, A. L. Antaris, X. Chen, H. Dai, *Adv. Mater.*, 2019, 31, 1900321.
- 15 D.-H. Li, B. D. Smith, J. Org. Chem. 2022, 87, 5893–5903.
- 16 Y. Ni, J. Wu, Tetrahedron Lett. **2016**, **57**, 5426–5434.
- 17 M. Abe, *Chem. Rev.*, 2013, **113**, 7011–7088.
- 18 T. Kubo, *Chem. Lett.*, 2015, **44**, 111–122.
- 19 N. Nakano, *Chem. Rec.*, 2017, **17**, 27–62.
- 20 T. Y. Gopalakrishna, W. Zeng, X. Lu, J. Wu, *Chem. Commun.*, 2018, **54**, 2186–2199.
- 21 K. Yamaguchi, *Chem. Phys. Lett.*, 1975, **33**, 330–335.
- 22 A. E. Tschitschibabin, Chem. Ber., 1907, 40, 1810–1819.
- 23 E. Müller, H. Pfanz, Ber. Dtsch. Chem. Ges. B, 1941, 74, 1051– 1074.
- 24 T. Kubo, A. Shimizu, M. Sakamoto, M. Uruichi, K. Yakushi, M. Nakano, D. Shiomi, K. Sato, T. Takui, Y. Morita, K. Nakasuji, *Angew. Chem., Int. Ed.*, 2005, **44**, 6564–6568.
- 25 A. Shimizu, R. Kishi, M. Nakano, D. Shiomi, K. Sato, T. Takui, I. Hisaki, M. Miyata, Y. Tobe, *Angew. Chem., Int. Ed.*, 2013, **52**, 6076–6079.
- 26 A. Arikawa, A. Shimizu, D. Shiomi, K. Sato, R. Shintani, *J. Am. Chem. Soc.*, 2021, **143**, 19599–19605.
- 27 A. Konishi, M. Yasuda, Chem. Lett., 2021, 50, 195-212.
- 28 H. Hayashi, J. E. Barker, A. Cárdenas Valdivia, R. Kishi, S. N. MacMillan, C. J. Gómez-García, H. Miyauchi, Y. Nakamura, M. Nakano, S.-i. Kato, M. M. Haley, J. Casado, *J. Am. Chem. Soc.*, 2020, **142**, 20444–20455.
- 29 Q. Wang, P. Hu, T. Tanaka, T. Y. Gopalakrishna, T. S. Herng, H. Phan, W. Zeng, J. Ding, A. Osuka, C. Chi, J. Siegel, J. Wu, *Chem. Sci.*, 2018, **9**, 5100–5105.
- 30 Z. Chen, W. Li, M. A. Sabuj, Y. Li, W. Zhu, M. Zeng, C. S. Sarap, M. M. Huda, X. Qiao, X. Peng, D. Ma, Y. Ma, N. Rai, F. Huang, *Nat. Commun.*, 2021, **12**, 5889.
- 31 W. Wang, L. Ge, G. Xue, F. Miao, P. Chen, H. Chen, Y. Lin, Y. Ni, J. Xiong, Y. Hu, J. Wu, Y. Zheng, *Chem. Commun.*, 2020, 56, 1405–1408.

- 32 H. Cai, H. Tang, T. Wang, C. Xu, J. Xie, M. Fu, X. Luo, Z. Hu, Y. Zhang, Y. Deng, G. Li, C. Liu, F. Huang, Di Cap, Aggew Company, Int. Ed., 2024, 63, e202402375.
- 33 L. Huang, N. Eedugurala, A. Benasco, S. Zhang, K. S. Mayer, D. J. Adams, B. Fowler, M. M. Lockart, M. Saghayezhian, H. Tahir, E. R. King, S. Morgan, M. K. Bowman, X. Gu, J. D. Azoulay, *Adv. Funct. Mater.* 2020, **30**, 1909805.
- 34 X. Shi, P. M. Burrezo, S. Lee, W. Zhang, B. Zheng, G. Dai, J. Chang, J. T. López Navarrete, K.-W. Huang, D. Kim, J. Casado, C. Chi, *Chem. Sci.*, 2014, 5, 4490.
- 35 S. Pascal, S. David, C. Andraud, O. Maury, *Chem. Soc. Rev.*, 2021, **50**, 6613–6658.
- 36 M. Pawlicki, H. A. Collins, R. G. Denning, H. L. Anderson, Angew. Chem. Int. Ed., 2009, 48, 3244–3266.
- K. Kamada, S. Fuku-en, S. Minamide, K. Ohta, R. Kishi, M. Nakano, H. Matsuzaki, H. Okamoto, H. Higashikawa, K. Inoue, S. Kojima, Y. Yamamoto, J. Am. Chem. Soc., 2013, 135, 232–241.
- K. Kamada, K. Ohta, T. Kubo, A. Shimizu, Y. Morita, K. Nakasuji, R. Kishi, S. Ohta, S. Furukawa, H. Takahashi, M. Nakano, Angew. Chem. Int. Ed., 2007, 46, 3544–3546.
- 39 X. Shi, E. Quintero, S. Lee, L. Jing, T. S. Herng, B. Zheng, K.-W. Huang, J. T. López Navarrete, J. Ding, D. Kim, J. Casado, C. Chi, *Chem. Sci.*, 2016, **7**, 3036–3046.
- 40 E. A. Yildiz, G. Sevinç, S. Tekin, A. Karatay, M. Hayvalı, A. Elmali, Dyes Pigms. 2021, **193**, 109522.
- 41 S. Maruo, O. Nakamura, S. Kawata, Opt. Lett., 1997, 22, 132.
- 42 B. H. Cumpston, S. P. Ananthavel, S. Barlow, D. L. Dyer, J. E. Ehrlich, L. L. Erskine, A. A. Heikal, S. M. Kuebler, I. Y. S. Lee, D. McCord-Maughon, J. Qin, H. Rockel, M. Rumi, X.-L. Wu, S. R. Marder, J. W. Perry, *Nature*, 1999, **398**, 51.
- 43 K. D. Belfield, K. J. Schafer, Y. Liu, J. Liu, X. Ren, E. W. V. Stryland, J. Phys. Org. Chem., 2000, **13**, 837.
- 44 S. Kawata, H.-B. Sun, T. Tanaka, K. Takada, Nature, 2001, 412, 697.
- 45 O. Varnavski, T. Goodson III, J. Am. Chem. Soc., 2020, 142, 12966–12975.
- 46 A. Diaspro, M. Robello, J. Photochem. Photobiol. B: Biol., 2000, 55, 1–8.
- 47 K. Ogawa, Y. Kobuke, Org. Biomol. Chem., 2009, 7, 2241.
- 48 J. P. Celli, B. Q. Spring, I. Rizvi, C. L. Evans, K. S. Samkoe, S. Verma, B. W. Pogue, T. Hasan, *Chem. Rev.*, 2010, **110**, 2795.
- 49 Y. Shen, A. J. Shuhendler, D. Ye, J.-J. Xu, H.-Y. Chen, *Chem. Soc. Rev.*, 2016, **45**, 6725.
- 50 T. Maeda, T. Oka, D. Sakamaki, H. Fujiwara, N. Suzuki, S. Yagi, T. Konishi, K. Kamada, *Chem. Sci.*, 2023, **14**, 1978.
- S. Webster, J. Fu, L. A. Padilha, O. V. Przhonska, D. J. Hagan, E. W. Van Stryland, M. V. Bondar, Y. L. Slominsky and A. D. Kachkovski, *Chem. Phys.*, 2008, **348**, 143-151.
- 52 Q. Bellier, N. S. Makarov, P.-A. Bouit, S. Rigaut, K. Kamada, P. Feneyrou, G. Berginc, O. Maury, J. W. Perry, C. Andraud, *Phys. Chem. Chem. Phys.*, 2012, **14**, 15299.
- 53 L. A. Padilha, S. Webster, O. V. Przhonska, H. Hu, D. Peceli, T. R. Ensley, M. V. Bondar, A. O. Gerasov, Y. P. Kovtun, M. P. Shandura, A. D. Kachkovski, D. J. Hagan and E. W. V. Stryland, *J. Phys. Chem. A*, 2010, **114**, 6493-6501.
- 54 T. Oka, T. Maeda, D. Sakamaki, N. Suzuki, S. Yagi, S. Kodama, H. Fujiwara, *Org. Chem. Front.* 2025, **12**, 42–47.
- 55 W. Wang, L. Ge, G. Xue, F. Miao, P. Chen, H. Chen, Y. Lin, Y. Ni, J. Xiong, Y. Hu, J. Wu, Y. Zheng, *Chem. Commun.*, 2020, **56**, 1405–1408.
- 56 L. Shen, Q. Wu, J. Lu, H. Zhao, H. Liu, Q. Meng, X. Li, *J. Mater. Chem. C*, 2022, **10**, 10404–10411.
- 57 D. López-Carballeira, D. Casanova, F. Ruipérez, ChemPhysChem, 2018, 19, 2224–2233.
- 58 H. Fallah-Bagher-Shaidaei, C. S. Wannere, C. Corminboeuf, R. Puchta, P. v. R. Schleyer, *Org. Lett.*, 2006, **8**, 863–866.

Journal Name

- 59 Bleaney, B.; Bowers, K. D., Anomalous paramagnetism of copper acetate, *Proc. R. Soc. London Ser. A*, 1952, **214**, 451–465.
- 61 K. Kamada, K. Ohta, Y. Iwase, K. Kondo, *Chem. Phys. Lett.* 2003, **372**, 386–393. DOI: 10.1039/D5TC00973A
- 60 C. Erker, T. Basché, J. Am. Chem. Soc., 2022, **144**, 14053– 14056.
- 62 J. M. Hales, D. J. Hagan, E. W. Van Stryland, K. J. Schafer, A. R. Morales, K. D. Belfield, P. Pacher, O. Kwon, E. Zojer, J. L. Bredas, J. Chem. Phys., 2004, **121**, 3152–3160.

This journal is © The Royal Society of Chemistry 20xx

Journal of Materials Chemistry C Accepted Manuscrip

View Article Online DOI: 10.1039/D5TC00973A

Data availability statement

Croconaine Dyes with Intermediate Diradical Character Exhibiting Intense One- and Two-Photon Absorption in the Short-Wavelength Infrared Region

Taishi Oka,^a Takeshi Maeda,^a* Daisuke Sakamaki,^b Hideki Fujiwara,^b* Naoya Suzuki,^a Shintaro Kodama,^a Shigeyuki Yagi,^a Luca Mauri,^{c,d} and Kenji Kamada^c*

All data associated with this article are available in the main text and Electronic Supplementary Information (ESI).