



Cite this: *Chem. Soc. Rev.*, 2026, 55, 3788

Photo-responsive chemical systems enabling multiscale structural ordering

Jianshuo Cheng, Mouwei Liu and Liangliang Zhu *

Beyond elemental composition and molecular structure, ordered multiscale architectures (self-assembled structure, crystal structure, phase structure, etc.) play a comparably important role in determining material functions, especially the optoelectronic properties. Light, a unique external stimulus with superior spatiotemporal resolution and non-invasive nature, provides unparalleled capabilities for dynamically constructing and manipulating such ordered structures. Since previous reviews on light-responsive materials have generally overlooked how light can govern multiscale structural ordering, this review comprehensively surveys the rapidly advancing field of photo-responsive chemical systems designed to achieve and control multiscale structural ordering. We begin by elucidating the fundamental photochemical and photophysical mechanisms at the molecular level, which serve as the primary triggers for molecular structural, configurational, or conformational transformations. Based on these events that initiate molecular perturbation, the core of the review critically examines several key light-mediated strategies for constructing and manipulating ordered hierarchical architectures, notably photo-triggered polymerization-induced self-assembly, liquid crystal-assisted phase structural amplification, photo-induced self-assembly mediated by host–guest interaction, and the emerging paradigm of photoexcitation-induced assembly (PEIA). We discuss how these strategies successfully translate molecular or nanoscale events into well-defined, macroscopic ordered states in real time and *in situ*. Finally, we provide a forward-looking perspective on the existing challenges and promising future research directions.

Received 3rd December 2025

DOI: 10.1039/d5cs00843c

rsc.li/chem-soc-rev

Key learning points

- (1) Fundamental principles and new mechanisms underlying photo-responsive materials.
- (2) Strategies for constructing and tuning ordered structures in photo-responsive systems.
- (3) Structure–property relationships: how different levels of structural ordering affect material performance.
- (4) Design guidelines and future directions for developing light-regulated materials with controllable structural ordering.

1. Introduction

1.1. Structural order across scales

Ordered structures are ubiquitous in nature across multiple scales, from the atomic to the macroscopic level, representing spontaneous organizational forms that enable matter to adapt to environmental constraints and achieve optimal functionality.^{1–6} This inherent orderliness not only reflects the physico-chemical principles of nature but also provides principles for structural design in materials science, biology, and engineering.^{7–11} At the microscopic scale, thermodynamic

driving forces (*e.g.*, energy minimization, entropic effects) prompt the periodic arrangement of atoms, molecules, or colloidal particles.^{12–15} For instance, minerals like diamond and quartz acquire high strength and anisotropy through long-range atomic ordering,^{16–18} while biological molecules such as the DNA double helix achieve ordered encoding of genetic information *via* hydrogen bonding and base pairing.^{19–23} Amphiphilic molecules like phospholipids spontaneously form lipid bilayers in aqueous phases, where the ordered hydrophobic–hydrophilic interface underpins the selective permeability of cell membranes.^{24–27} At the mesoscopic scale, natural systems often integrate structures across different scales through hierarchical ordering to balance conflicting properties.^{28–31} Examples include the structural colors of peacock feathers and butterfly wings, which arise from coherent light scattering

State Key Laboratory of Molecular Engineering of Polymers, Department of Macromolecular Science, Fudan University, Shanghai 200438, China.
E-mail: zhuliangliang@fudan.edu.cn



by periodic nanostructures rather than pigmental chemistry.^{24,32–34} On larger scales, space-filling and mechanical optimization drive the formation of regular geometric configurations, such as the hexagonal units in honeycombs, which maximize load-bearing efficiency with minimal material consumption, exhibiting strength significantly superior to foam materials.^{35–38} Across scales and systems, such ordered structures emerge as optimal solutions to the combined constraints of energy, information, and function. Their universality not only reveals the unity of natural laws but also provides the fundamental logic of “structure determines property” for the design of artificial materials.^{39–42}

Structural ordering is a universal principle for optimizing material properties.^{43–45} From atomic-scale crystalline arrangements (e.g., the sp^3 hybridized carbon network in diamond conferring ultra-high hardness) to mesoscale biomineralized structures (e.g., the nacreous layer in abalone shells, a composite of aragonite and organic matter, synergizing strength and toughness), and further to macroscopic structures like honeycombs achieving lightweight and high strength, ordering dictates material characteristics across mechanical, optical, and electrical properties.^{46–49} This structure–property relationship

offers crucial insights for material design. In materials science, *in situ* structural modulation refers to the real-time control of atomic/molecular order within a material under operational conditions *via* external stimuli (e.g., temperature, stress, electric/magnetic fields, chemical environment, light).^{50–52} Compared to traditional “synthesis-characterization-optimization” cycles, *in situ* modulation offers unique advantages such as dynamism, precision, and reversibility, serving as a key pathway for enhancing material order and optimizing performance.^{53,54}

1.2. Tools for engineering structural order

To bridge the molecular events and macroscopic material responses discussed herein, a suite of complementary characterization tools is essential. At the molecular and nanoscale, transient absorption spectroscopy and time-resolved photoluminescence capture the kinetics of photoexcitation and the initial conformational changes. For mesoscale order, which is critical for self-assembled and liquid crystalline architectures, scattering techniques like small-/wide-angle X-ray scattering (SAXS/WAXS) provide statistically averaged information on periodic structures, phase symmetry, and lattice parameters, while atomic force microscopy (AFM) offers direct, real-space visualization of surface morphology and domain organization. At the macroscopic scale, the overall optical anisotropy and phase transitions are directly visualized through polarized optical microscopy (POM).³ This multi-technique framework forms the foundation for the mechanistic insights presented in the following sections, and is capable of effectively interpreting the structural data that underpins the progress of the field.

1.3. Distinctive features and challenges of photo-responsive systems

Light-response stands out as a non-contact, high spatiotemporal resolution way for *in situ* modulation, demonstrating unique potential for dynamically manipulating ordered structures in materials.^{55–58} Unlike other external fields, like



Jianshuo Cheng

Jianshuo Cheng is currently a doctoral student at Fudan University under the supervision of Prof. Liangliang Zhu. She obtained a bachelor's degree from Shandong University in 2020. Her research interests mainly focus on organic luminescent functional materials.



Mouwei Liu

Mouwei Liu received her bachelor's degree in Polymer Science from Sichuan University. From 2020 to 2025, she pursued her PhD at Fudan University, where she was supervised by Prof. Liangliang Zhu. Currently, she is employed at Semiconductor Manufacturing International Corporation (SMIC).



Liangliang Zhu

Liangliang Zhu received his BSc in chemistry from Zhejiang University in 2005 and PhD in Applied Chemistry at the East China University of Science and Technology in 2011. From 2011 to 2013, he worked at Nanyang Technological University as a Research Fellow. In 2013, he joined Columbia University as a Postdoctoral Research Scientist. He became a professor at Fudan University in 2015. He has published over 190 scientific papers so far. His research interests mainly focus on self-assembled photofunctional and luminescent materials.



thermal, electric, magnetic, and so on, light control takes advantage of specific interactions between photon energy and matter (*e.g.*, electronic excitation, molecular structural changes, localized heating), enabling high selectivity, rapid response, and multi-dimensional manipulation, thus becoming a pivotal tool for designing smart materials and functional devices.^{59–62}

However, a significant challenge persists in most photo-responsive chemical systems, namely, producing, maintaining, and enhancing structural order during photo-induced transformations. Even when the initially ordered arrangements are achieved, multi-scale structures often collapse due to misalignment of molecules or defects upon irradiation, originating from insufficient photoreaction efficiency and interference from side reactions.⁶³ Addressing this requires precise molecular design, synergy of specific components or phases, and the development of novel photo-responsive mechanisms. In this way, structural orderliness is expected to evolve from molecule-scale photo-responsive moieties to larger scales under irradiation. This review aims to systematically summarize recent advances in this perspective, spanning chemical synthesis, material processing, and functional property control.

1.4. Scope and organization of this review

In this tutorial review, we first introduce the two primary types of photo-responsive behaviors (*i.e.*, photochemical and photophysical), explain their fundamental principles at the molecular and microscopic scales, and summarize representative molecular systems. These fundamental response modes provide the molecular moiety-level upon which light can perturb molecular structure, configuration, conformation, interactions, or assembly equilibria. Based on these behaviors, we then discuss four distinct photo-responsive strategies for achieving or tuning multi-level hierarchical ordered structures (including self-assembled or phase-ordered systems), each of which leverages photochemical or photophysical events in different ways to induce structural transitions across scales. These strategies focus on how irradiation drives transformations between hierarchical levels or enhances structural order through controlled photo-perturbations. Key points and underlying mechanisms are elucidated through representative examples. Subsequently, we present typical material properties based on photo-responsive structural ordering, such as creating optical patterns with tuning refractive index, modulation of photoluminescence and chiroptical properties, lithography, and so forth. Finally, we offer perspectives on future directions for photo-responsive ordered systems, aiming to bridge light-stimulus, self-assembly, and material processing to advance this frontier towards practical applications (see also the outline in Fig. 1).

To ensure conceptual clarity and pedagogical consistency throughout this Tutorial Review, we explicitly distinguish between photochemical processes, which involve ground-state chemical bond formation, cleavage, or isomerization, and photophysical processes, which primarily involve excited-state energy redistribution, conformational distortion, or intermolecular interaction modulation without permanent chemical transformation. In particular, the term photoexcitation-induced

assembly (PEIA) is used here to describe emerging phenomena driven by excited-state intermolecular interactions or conformational dynamics, rather than by covalent bond reorganization. These definitions are applied consistently across all sections to avoid terminological ambiguity and to facilitate comparison among different light-responsive strategies.

2. Photo-responsive principles: from molecular events to material responses

In this section, we aim to discuss fundamental principles and new mechanisms underlying photo-responsive materials. A clear understanding of photo-responsive behaviors requires examining how molecular systems evolve at the microscopic level upon photoirradiation. At this scale, light-mediated molecular control can be categorized into photochemical and photophysical processes (as shown in Fig. 2). The main criterion for distinguishing these two is whether it involves the breaking and reforming of chemical bonds. This section summarizes typical photo-responsive systems based on photochemical and photophysical processes, primarily analyzing molecular structural, configurational, or conformational changes during photo-responses from a theoretical and experimental standpoint, with the aim of providing a fundamental basis for enhancing material properties.

2.1. Photochemical behavior

Photochemistry, a widely studied photo-responsive behavior, involves chemical reaction processes driven by photons under light irradiation.^{64–66} Its core principle involves electronic state transitions in molecules following light absorption, opening new reaction pathways.^{67–70} Research in photochemistry dates back to the 19th-century exploration of photosensitivity and photolysis. By the mid-20th century, advancements in laser technology and spectroscopy gradually revealed photochemical reaction mechanisms, particularly the dynamics of photoexcited states and ultrafast processes, laying the foundation for modern photochemistry.^{68,69,71–73} The past several decades have witnessed significant developments in light-initiated chemical reactions, utilizing typical photo-responsive molecular moieties such as azobenzene, stilbene, diaryl ethylene, and spiropyrene.^{74–83}

A distinguishing feature of photochemical reactions is their non-thermodynamic driving force: photon energy can directly excite molecules into high-energy excited states, overcoming energy barriers limiting thermal processes and opening new reaction pathways.⁵⁹ Furthermore, photochemical processes offer high selectivity and controllability. By adjusting the wavelength, intensity, and polarization of the light source, spatial, temporal, and energy-resolved control of reactions can be achieved. These processes can even occur under mild conditions and frequently utilize visible light as the driver, offering the benefits of low energy consumption and environmental friendliness.⁸⁴






Fig. 1 Outline of this tutorial review. (a) Basic information of multiscale structural evolution in photo-responsive chemical systems. The length and time scales indicated here are approximate and refer to typical regimes in soft photo-responsive materials, rather than strict universal boundaries. (b) Integrative presentation of the relationship between the four strategies to be discussed next and the evolution of multi-scale structures. (c) The organization of this review began with introducing two primary types of photo-responsive behaviors (*i.e.*, photochemical and photophysical), followed by discussing four distinct photo-responsive strategies for achieving multi-level hierarchical ordered structures. Some typical material properties enabled by light-triggered structural ordering were showcased.






Fig. 2 Outline of photochemical and photophysical behaviors discussed in this review.

2.1.1. Photoisomerization. Photoisomerization is a typical photochemical reaction type, exemplified by azobenzene and its derivatives or analogues. Photoisomerization refers to the process by which a molecule undergoes a reversible change in its chemical structure or configuration upon photon absorption.^{85,86} Specifically, this process typically involves the conversion from one stable state (e.g., *trans*) to another (usually *cis*).⁷⁴ Notably, for azobenzene, this *trans*-to-*cis* conversion can proceed *via* two primary mechanisms on the excited-state potential energy surface: the traditional rotation pathway, which involves breaking of the N=N π -bond and rotation around the N-N σ -bond, and the inversion (or concerted inversion) pathway, where one nitrogen atom inverts through a linear or nearly linear transition state while maintaining partial N=N bond character.⁸⁷ Most photoisomerization processes are reversible, especially in *cis*-*trans* isomerization. By controlling light intensity, wavelength, or exposure duration, molecules can be switched between *cis* and *trans* configurations.⁸⁸ For instance, azobenzene derivatives transition from the *trans* to the *cis* isomer under UV light irradiation and revert to the *trans* isomer under visible light or thermal treatment. This change results from electronic transitions upon photoexcitation, leading to the excited double bond breaking and reforming after rotation of the single bond. The reversibility makes photoisomerization widely applicable in smart materials, optical switches, and photo-responsive systems.⁸⁹

Photo-isomerization can achieve reversible single-crystal configurational changes if the efficiency of photoisomerization can be significantly improved, and the degrees of freedom of molecules can be well designed. Li *et al.* studied the reversible single crystal-to-single crystal (SCSC) photo-isomerization in azobenzene (Fig. 3).⁹⁰ Using single-crystal X-ray diffraction techniques, the researchers demonstrated that under 365-nm light exposure (15 min, 112 mW cm⁻²), the large single crystals could undergo complete and reversible crystal transformation while maintaining long-range crystal order. The capture of the




Fig. 3 Photo-responsive systems enabling single crystal-to-single crystal conversion. (a) SCSC $E \rightleftharpoons Z$ isomerization. (b) Photographs of single crystals with reversible SCSC isomerization. (c) Related X-ray molecular structures.⁹⁰ Reproduced with permission.⁹⁰ Copyright © 2025 American Chemical Society.

two intermediate states revealed a three-step mechanism, including the initial configurational change, followed by an isomerization process accompanied by minor, coordinated molecular motions (specifically interlayer sliding and subtle distance adjustments). This work redefines the understanding of azo conversions in crystals and opens up new avenues for the development of photo-responsive crystal materials.

Photoisomerization can also regulate the mechanical properties of materials and establish the connection between molecules and macroscopic objects. Cao *et al.* demonstrated that azobenzene-based compounds exhibit photoswitchable mechanical strength, where light-induced structural changes alter their rupture forces, making them ideal photo-responsive






Fig. 4 Photo-responsive systems enabling material mechanical properties tuning. Structures of *cis* 4-AZB, *trans* 4-AZB, and SMFS measurement of the azobenzene derivative.⁹¹ Reproduced with permission.⁹¹ Copyright © 2023, Springer Nature Limited.

mechanical elements (Fig. 4).⁹¹ Using single-molecule force spectroscopy (SMFS) and theoretical calculations, they found that the *cis* and *trans* 4,4'-azobenzene isomers possess contrasting mechanical properties (600 pN for *trans* species and 200 pN for *cis* species). The different rupture forces of the two isomers were attributed to the pulling direction. These mechanical characteristics of azobenzene can be utilized to rationally control the macroscopic fracture behavior of polymer networks *via* light irradiation. These examples typically illustrate the photoisomerization portion in learning point (1).

2.1.2. Photogenerated radicals. Besides photoisomerization, another representative type of photochemical behavior involves photogenerated radicals. Photogenerated radicals are chemical species produced by light excitation, possessing unpaired electrons and thus exhibiting high reactivity. Radical generation typically occurs *via* bond cleavage or energy transfer processes in the excited state after a molecule absorbs light energy.⁹² When a molecule absorbs a photon with an appropriate wavelength, the electron transitions to a higher energy level to form an excited state. This state is typically high-energy, rendering internal chemical bonds unstable. In the excited state, the strength of a certain chemical bond weakens, making it more prone to cleavage. The generation of radicals often accompanies bond cleavage, producing two fragments with unpaired electrons.⁹³ Typical photolabile bonds include C–X (X = halogen), N–O, and S–S, while direct C–H or C–C homolysis usually requires high-energy UV photons or sensitized conditions. For example, C–H bond cleavage can generate a hydrogen radical ($\bullet\text{H}$) and an organic radical (*e.g.*, an alkyl or aryl radical).^{94,95} Radical photogeneration is a fast process, and radicals typically participate further in other reactions. Radical-involved reactions are a crucial type in organic chemistry.

In addition to radical-mediated synthesis, photogenerated radicals can also regulate the photoluminescent (PL) properties of materials. An *et al.* reported a dynamically tunable room-temperature phosphorescence (RTP) strategy based on the reversible transformation of radicals under external stimuli (Fig. 5).⁹⁶ RTP has been a focus of scientific research due to

its potential applications in optical materials, such as displays, memory devices, and bioimaging. However, achieving RTP often requires high molecular aggregation and strong intermolecular interactions, which aim to limit molecular flexibility and suppress non-radiative transitions in practical applications. Different from these traditional strategies, the researchers found that light irradiation can generate radicals in certain organic molecules (NDIA), which reversibly modulates the optical properties of the NDIA/PVA film. Specifically, light-induced radical generation can regulate RTP emission to become a radical emission, producing stronger PL signals under certain conditions within 90 s. The reversible transformation between the NDIA molecule and its anionic radical under light is related to excited-state bond weakening, where UV irradiation facilitates the cleavage of specific bonds, leading to radical formation and subsequent changes in emission properties. This example typically illustrates the photogenerated radicals portion in learning point (1).

2.2. Photophysical behavior

Although many important photochemical systems have been thoroughly studied, the self-assembly process always has limitations. Firstly, the conversion rate of photochemical reactions is relatively low. Secondly, the presence of side reactions in photochemical reactions can have adverse effects on molecular assembly, potentially leading to defects and impacting their performance. Thirdly, most of these systems switch between two stable states, requiring additional energy consumption.⁶³ In contrast to photochemical processes, photophysical processes involve a change only in the electronic states of molecules upon photon absorption, leading to conformational adjustments (*e.g.*, change in spatial orientation due to single-bond rotation) or electron redistribution, without breaking chemical bonds.^{97,98} Photoinduced electron transfer (PET) is one of the earliest studied photophysical processes, where light absorption usually causes electron transfer from an electron-rich donor to an electron-deficient acceptor following photoexcitation.⁹⁹ PET plays a vital role in many important






Fig. 5 Photo-responsive systems with photogenerated radical transformation for dynamically tuning RTP. (a) Related chemical structures and photoluminescence images. (b) PL spectra of the NDIA/PVA film upon UV irradiation. (c) Corresponding emission color trajectory in the CIE coordinate diagram. (d) Corresponding energy transfer processes.⁹⁶ Reproduced with permission.⁹⁶ Copyright © 2022, Science China Press and Springer-Verlag GmbH Germany, part of Springer Nature.

photo-responsive processes, particularly in designing photo-responsive materials, photoelectric devices, and light-mediated electrochemical processes, providing the foundation for efficient energy conversion and information transfer. For instance, Liu *et al.* investigated the key role of molecular conformational folding in PET (Fig. 6).¹⁰⁰ Their study revealed that conformational changes in naphthalimide-containing systems, particularly from an open to a folded state, can significantly enhance PET efficiency. Notably, although PET is generally classified as a photophysical process in the excited state without involving permanent chemical changes, it may also trigger subsequent photochemical reactions once the generated radical species proceed to further irreversible steps.

Besides PET, with advancements in photophysics, an increasing number of other photophysical mechanisms have been proposed, enriching the existing theories and strategies. For example, Tang *et al.* studied the mechanism of visualizing and regulating molecular motion *via* photoinduced

clusteroluminescence in the solid state.¹⁰¹ They discovered that certain organic molecules in the solid state exhibit dynamic molecular motions upon photoexcitation, leading to changes in luminescence properties. Specifically, light-induced relative motions within molecular clusters trigger significant changes in clusteroluminescence, allowing real-time monitoring of molecular-level motions (Fig. 7). Li *et al.* investigated the photoinduced phosphorescence effect through 365-nm irradiation for 5 min.¹⁰² Their study revealed that photoinduced phosphorescence can be attributed to reversible changes in crystal packing. By adjusting the molecular packing structure, the intensity and lifetime of resonance phosphorescence can be significantly enhanced or regulated (Fig. 8). These reports provide molecular mechanisms and design principles for precisely regulating small-molecule crystal forms through photophysical processes.

Recently, PEIA has been proposed as a novel photophysical behavior. By studying a class of persulfurated arene compounds,




Fig. 6 Photo-responsive systems with a conformation folding-activated PET.¹⁰⁰ Reproduced with permission.¹⁰⁰ Copyright © 2024 Chinese Chemical Society. This article is published under the terms of the Creative Commons Attribution-NonCommercial 3.0 Unported license (CC BY-NC 3.0, <https://creativecommons.org/licenses/by-nc/3.0/>).




Fig. 7 Photo-responsive systems with light-driven intermolecular motions in the solid state.¹⁰¹ Reproduced with permission.¹⁰¹ Copyright © 2019 American Chemical Society.






Fig. 8 Photo-responsive systems bearing photophysical processes that affect crystal stacking and phosphorescence activation. (a) The RTP spectral change of CS-CF₃ upon UV irradiation. (b)–(e) The corresponding change in UV-visible spectra, PL-decay curves, crystal structures, and a PL patterning.¹⁰² Reproduced under terms of the CC-BY license.¹⁰² Copyright © 2018, The Author(s), published by Springer Nature under a Creative Commons Attribution 4.0 International License (<http://creativecommons.org/licenses/by/4.0/>).

our group found that these compounds exhibited the ability to undergo aggregation upon photoirradiation, leading to the proposal of the PEIA effect.¹⁰³ Compared to studying more AIE phenomena, the main difference between the two lies in the causality. AIE causes luminescence through aggregation, while PEIA leads to assembly through light excitation. Compared to standard excited-state aggregation, the main difference between the two lies in the driving force. The driving force of standard

excited-state aggregation can be various methods such as electric and magnetic, while PEIA is driven by light, which gives PEIA advantages such as remote controllability and good biocompatibility. These molecules exhibit reversible aggregation upon photoexcitation (driven by their distinct excited-state conformation from the ground-state counterpart), and display flicker phosphorescence during the recovery process (Fig. 9). Accompanied by a long-lived dark state formed, the system has sufficient time to resist energy relaxation, ensuring that the molecules aggregate and exhibit PEIA. It is worth noting that most systems do not exhibit aggregation properties under light excitation due to their relatively rigid molecular conformations and short excited-state lifetimes. Currently, PEIA is mainly applicable to persulfurated arene systems. With the advancement of research, other photo-responsive skeletons have also emerged, demonstrating the universality of this strategy.¹⁰⁴ The above examples typically illustrate the photophysical portion in learning point (1).

3. Achieving or controlling multiscale order structures *via* photo-responsive processes

In this section, we turn to discuss strategies for constructing and tuning ordered structures in photo-responsive systems. The molecular-scale photochemical and photophysical events provide the fundamental “triggers” for structural change. However, the manifestation of these molecular perturbations at the mesoscopic and macroscopic scales relies on a critical amplification and organization process. To bridge this gap, photo-responsive strategies must effectively couple these primary molecular events (*e.g.*, isomerization, electron transfer, conformational switching) with defined intermolecular interactions or




Fig. 9 Photo-responsive systems rendering PEIA effect that can activate phosphorescence in solution. (a) Conformational change upon photoexcitation of the persulfurated arene. (b) Successive action of the photoactivation and self-recovery cycle with a flicker RTP effect of the main compound in aqueous media (ISC: intersystem crossing).¹⁰³ Reproduced with permission.¹⁰³ Copyright © 2019. Published under the PNAS license.



collective dynamics. This coupling can propagate and amplify local changes through mechanisms such as cooperative alignment in liquid crystals, templated growth in host-guest systems, or polymerization-induced confinement, thereby translating discrete molecular actions into long-range, multiscale structural order.

Before elaborating on the multi-scale orderliness, we first distinguish between the molecular, supramolecular, and macroscopic levels in order to better understand the process of multi-scale ordering. Molecular scale: orderliness is manifested in the spatial arrangement of atoms/molecules, chemical bonds, or coordination environments, as well as the resulting electronic states, molecular conformations, or dipole orientations.^{105,106} Supramolecular scale: orderliness stems from non-covalent interactions between molecules (such as hydrogen bonds, π - π stacking, hydrophobic interactions), forming assemblies with specific morphology, periodicity, or symmetry.^{107,108} Macroscopic scale: orderliness is reflected in the anisotropy of the material as a whole, regular surface morphology, macroscopic patterns, or functional structures at the device level.^{109,110}

Upon the fundamental photochemical and photophysical events originate at the molecular level, a pivotal challenge lies

in translating these photo-responsive molecular perturbations into controlled, long-range structural order from the microscopic to the macroscopic scale.¹¹¹ Through photochemical or photophysical response processes, as well as with the help of precise molecular design, synergy of specific components or phases, or enrolment of new photo-responsive mechanisms, the structural changes occurring at the molecular scale can drive larger-scale self-assembly or phase transitions, thereby enabling adjustments in material order across multiple hierarchical levels.^{63,112} This multi-level ordering transformation not only provides new ideas for designing high-performance optical functional materials but also expands their application potential in micropatterning, structural color tuning, chiroptical modulation, luminescence control, photoresist, and so forth. In this section, we will explore in detail several strategies that utilize photo-responsive approaches to construct and regulate multi-level ordered structures, and analyse their strengths, weaknesses, and applicable scenarios through concrete examples (Table 1). Concurrently, we will delve into the mechanisms behind these photo-responsive processes, revealing the fundamental principles and influencing factors.

Table 1 Systematic comparison of four light-responsive strategies for constructing ordered structures

Strategies	Photo-triggered polymerization-induced self-assembly	Liquid crystal-assisted structural amplification	Photo-induced ordered self-assembly mediated by host-guest interaction	Photoexcitation-induced assembly (PEIA)
Light-response type	Photochemical	Photochemical	Photochemical	Photophysical
Mechanism	Light-initiated polymerization drives <i>in situ</i> amphiphile formation, leading to spontaneous self-assembly <i>via</i> block incompatibility and phase separation	Photo-induced molecular changes are amplified through cooperative mesogen alignment and liquid crystalline phase transitions	Light modulates host-guest binding affinity, dynamically controlling supramolecular association and structural organization	Excited-state conformational distortion drives aggregation or non-equilibrium assembly, leading to ordered structural evolving
Molecular-level change	Photo-induced molecular structure change	Light-controlled orientation-induced collective reordering of liquid crystals	Light regulation of host-guest molecular recognition and encapsulation	Molecular excited-state conformational change
Primary driving force for ordering	Covalent bonds	Mesogenic cooperative orientation order	Changes in non-covalent interaction strength such as host-guest molecular recognition	Interactions between molecules driven by excited state conformations
Time scale	Seconds to hours, depending on polymerization kinetics and diffusion	Milliseconds to seconds for phase reorientation; longer if involving bulk relaxation	Milliseconds to minutes, depending on binding kinetics and diffusion	Ultrafast excitation (fs-ns) followed by assembly evolution (ns-min)
Reversibility	Generally irreversible due to covalent bond formation, except for dynamic covalent bonds	Typically reversible, depending on photoisomer stability and thermal back-relaxation	Highly reversible under appropriate binding equilibria	Potentially reversible but can be kinetically trapped.
Spatial resolution	Moderate to high; can be spatially patterned through localized light exposure, though diffusion may blur boundaries	High at the micro-scale; governed by liquid crystal elasticity and domain coupling	Moderate; limited by molecular diffusion and binding exchange rates	Mesoscale precision depends on diffusion and cooperative effects.
Advantages	Broadly applicable to various monomers and polymer systems; compatible with scalable synthesis	Effective in systems containing mesogenic units; particularly powerful in soft anisotropic materials	Versatile across diverse supramolecular chemistries; tunable <i>via</i> host-guest design	High photon utilization efficiency; suitable for large-scale and continuous morphology control
Limitations	Limited reversibility; structural precision depends on polymerization control; kinetic trapping and dispersity effects may arise	Requires mesogen incorporation; sensitive to temperature, alignment conditions, and phase stability.	Binding strength trade-off between stability and reversibility; may suffer from competitive interactions or environmental sensitivity	Requires chromophores with excited state conformational distortable and long lifetimes
Ordering product type	Nanocages, nanogels, nanova-cuoles, nanofibers, <i>etc.</i>	Liquid crystal orientation pattern	Supramolecular polymers, nanofibers, hydrogels	Structural changes of assemblies or block copolymer phases



3.1. Photo-triggered polymerization-induced self-assembly

Photo-triggered polymerization-induced self-assembly is a technique that utilizes light energy to initiate polymerization or photocrosslinking, and induce the self-assembly of leading polymers into ordered structures.¹¹³ It combines photo-responsiveness and polymerization reactions, thereby harnessing the controllability and non-invasiveness of light to regulate the assembly behavior of macromolecules or nanosystems. Photopolymerization-induced self-assembly is mainly applicable to block copolymers and surface-grafted polymer systems. The intensity, wavelength, and pattern of light irradiation directly determine the local initiation rate of polymerization. This in turn governs the gradual formation and *in situ* aggregation of the polymer blocks, allowing for the real-time, kinetically trapped fabrication of nanostructures with defined morphologies that are often inaccessible through traditional thermal equilibrium methods.

Chen *et al.* proposed a simple and robust one-pot method to synthesize stilbene-containing block copolymer (BCP) nanowires with uniform morphology, combining photodimerization and polymerization-induced hierarchical self-assembly.¹¹⁴ Although the photodimerization reaction proceeded successfully, it resulted in a decrease in the overall structural order of the assembly. This demonstrates the critical importance of designing the dimerizable moieties attached to the polymer backbone. Thus, Russell *et al.* designed and synthesized a deuterated polystyrene (d_8 -PS, easy to track by NMR) and poly(methyl methacrylate) (PMMA) diblock copolymer PS-*b*-PMMA di-BCP (Fig. 10a and b).¹¹⁵ They further investigated

the light-controlled ordering transition in PS-*b*-PMMA films *via* the photodimerization of an anthracene group. In this way, UV irradiation (365 nm, 35 mW cm⁻²) can regulate interactions between copolymer chains, transitioning the order state of the film (monitored by small-angle neutron scattering from 0.03796 Å to 0.03109 Å).

Photo-triggered polymerization-induced self-assembly can also be realized through photoinduced cyclization. Clever *et al.* demonstrated the reversible transformation of self-assembled structures controlled by the change in the geometry of photo-responsive molecules (Fig. 10c and d).¹¹⁶ They designed a photo-responsive self-assembly system where UV light regulates intramolecular cyclization, enabling reversible switching between triangular and octahedral shapes with a nonspherical morphology of 6.4 nm across. Such a light-induced geometric change drives the structural transformation from one regular morphology to another by altering intermolecular interactions. This study further shows that the light-induced geometric change can help achieve nanostructures with high tunability and dynamic response. These examples typically illustrate the photo-triggered polymerization-induced self-assembly strategy in learning point (2).

3.2. Liquid crystal-assisted structural amplification

The strategy of liquid crystal-assisted structural amplification is mainly applicable to small-molecule liquid crystal-doped systems. In liquid crystal (LC) environments, perturbations of photo-responsive molecules can readily induce ordered changes in the phase environment and amplify the molecular




Fig. 10 Photo-responsive systems enabling photo-triggered polymerization to construct ordered self-assembled structures. (a) PS-*b*-PMMA di-BCP with a anthracene-based dimerizable moiety and (b) corresponding small-angle neutron scattering profiles featured an ordered film morphology transfer.¹¹⁵ (c) Photoinduced cyclization enabling a switching between triangular and octahedral shapes of the molecular superstructure and (d) related TEM image featuring the yielded nanospheres.¹¹⁶ (a) and (b) Reproduced with permission.¹¹⁵ Copyright © 2011 American Chemical Society; (c) and (d) Reproduced with permission.¹¹⁶ Copyright © 2016 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim.



perturbation. LC molecules themselves possess anisotropy and long-range order characteristics. When photo-responsive moieties are embedded within an LC environment, light-induced changes in molecular configuration or dipole moment can disrupt the local orientational balance, thereby triggering the rearrangement of orientation domains within the LC phase. Due to the high fluidity and plasticity of LCs, this light-triggered perturbation diffuses successively along the orientation direction through molecular cooperative effects, manifesting as an evolution of ordered structures from local to global scales. The diffusion process achieves the translation of molecular-scale photo-responses to macroscopic-scale order regulation, providing a unique pathway for constructing light-controlled materials with multiscale order.^{117,118}

Katsonis *et al.* revealed how the ordered structure of LCs amplifies local molecular changes under light to produce macroscopic optical responses. They constructed a light-controlled chiral inversion cholesteric LC system, where a bisazo-photoactive dopant exhibits reversible three-state isomerization (EE, ZE, ZZ), with interconversion between configurations achievable *via* visible light irradiation and thermal relaxation (Fig. 11a). Throughout the process, the helix pitch can be regulated within the range of 2.2 μm to 30 μm .¹¹⁷ Cheng *et al.* investigated the inversion of circularly polarized

luminescence (CPL) signals in LCs.¹¹⁹ They introduced a photo-responsive achiral negative dichroism dye (KG) and a static achiral positive dichroism dye (NR) dopant with opposite dichroism to the CLC host, thus achieving the control of CPL chirality and intensity. By introducing a synergic dichroic modulation, the researchers achieved reversible CPL signal inversion in LC materials (Fig. 11b and c). Li *et al.* also studied chiral inversion in self-assembled helical superstructures based on a cyclic azobenzenophane (Fig. 11d).¹²⁰ Their work demonstrated how LC-assisted self-assembly can achieve chiral inversion *via* light regulation with high reversibility. Similarly, the process of photoisomerization is also accompanied by extensive regulation of cholesterol pitch between 100 μm and 400 μm . Kosa *et al.* proposed a method of photoinduced liquid crystallization on naphthopyran-based materials, studying how light irradiation induces the formation of LC phases and its impact on material structure. Their work revealed a more fundamental phenomenon of “photoinduced liquid crystallization”, where light can trigger the transformation of a non-LC system into a highly ordered LC phase, thus achieving spontaneous ordering driven by the light field.¹²¹ The phase transition process occurred in seconds above the clear point of the liquid crystal (31.8 $^{\circ}\text{C}$). This change reduces the system free energy in the ordered mesophase under isothermal conditions. POM images




Fig. 11 Mesogen-assisted photo-responsive systems enabling ordered phase structural regulation. (a) Photoisomerization of a bisazo-photoactive dopant, leading to a photoinduced chiral inversion in a photoactive cholesteric LC system.¹¹⁷ (b) CD and (c) CPL spectra of a liquid crystal system with an achiral negative dichroism dye (KG) and a static achiral dye (NR) as dopants, in its initial state and under light irradiation.¹¹⁹ (d) Schematic representation of light-driven reversible handedness inversion in LC-assisted self-organized helical superstructures based on a cyclic azobenzenophane.¹²⁰ (e) POM images visualizing the macroscopic process of light-controlled LC phase before, during, and after UV exposure on a naphthopyran-based material.¹²¹ (a) Reproduced with permission.¹¹⁷ Copyright © 2019 American Chemical Society. This publication is licensed under CC-BY-NC-ND. (b) and (c) Reproduced with permission.¹¹⁹ Copyright © 2024 Wiley-VCH GmbH. (d) Reproduced with permission.¹²⁰ Copyright © 2010 American Chemical Society. (e) Reproduced with permission.¹²¹ Copyright © 2012, Springer Nature Limited.



visually demonstrate the macroscopic manifestation of this light-controlled transition (Fig. 11e).

Light can further drive multi-morphological and superficial phase transitions within LC media. Evans *et al.* studied light-controlled phase transitions in arylazopyrazole-based liquid crystals, focusing on the transition from hexagonal to cubic phases under light irradiation (Fig. 12a–c).¹²² This transition is evidenced by the appearance of a new series of peaks with a ratio of $\sqrt{6}:\sqrt{8}:\sqrt{14}:\sqrt{16}:\sqrt{20}$ and a reduction in the intensity of the hexagonal peaks (Fig. 12a). Mechanically, this transition is driven by light-induced packing frustration: photoisomerization of the azopyrazole moieties introduces geometric mismatch. The system resolves this frustration by reorganizing into a cubic phase, which accommodates the varied molecular geometries with lower curvature elastic energy. The study showed that the ordered structures of LC materials can undergo peculiar phase transitions under light, thereby increasing the rate of CO₂ diffusion. Yu *et al.* studied the application of halogen bonding in block copolymer nanostructures, demonstrating how halogen bonds provide additional stability and control in LC molecular alignment (Fig. 12d).¹²³ Through linearly polarized light (LPL) irradiation, the researchers achieved efficient photoalignment and photoreorientation

of the nanostructures with a periodic distance of 21.7 nm. These examples typically illustrate the liquid crystal-assisted structural amplification strategy in learning point (2).

3.3. Photo-induced ordered self-assembly mediated by host-guest interaction

Host-guest interactions are a class of non-covalent forces based on molecular recognition, establishing selective binding between molecules through size matching, shape complementarity, and specific electrostatic, hydrogen bonding, or hydrophobic interactions. The host molecule typically possesses a regular cavity or channel structure (*e.g.*, cyclodextrins, cucurbiturils, cyclic oligomers) capable of partially or fully encapsulating the guest molecule, thereby significantly altering the guest orientation and local environment.^{124,125} Macrocyclic structures like cyclodextrins and calixarenes are rich in non-covalent bonds such as hydrogen bonds and electrostatic interactions, and can form host-guest assemblies with small molecules *via* size effects.^{126,127} This interaction not only stabilizes the assembly units at the molecular level but can also extend local molecular recognition to larger-scale ordered structures through the arrangement of guest molecules. In this process, host-guest recognition provides both precise and directional control for construction, and ensures dynamic reversibility, enabling the systems to undergo controllable structural rearrangements under external stimuli (*e.g.*, light, heat, solvent).¹²⁸ Beyond simple binding, host-guest systems can also achieve sophisticated cooperative effects. The light-triggered encapsulation or release of a guest can alter intermolecular forces (*e.g.*, π - π stacking, hydrophobic collapse) among the complexed units, thereby directing nanoscale morphology evolutions such as transitions between 1D fibers, 2D sheets, and 3D networks. Thus, host-guest recognition not only stabilizes assembly units but also translates finely tuned molecular responses into well-defined, higher-order architectures through synergistic non-covalent networks. This dual role makes host-guest chemistry a unique strategy for building adaptive, multi-scale ordered materials.

As shown in Fig. 13a and b, Liu *et al.* reported a photo-controlled chiral self-assembly system based on cucurbit[8]uril (CB[8]).¹²⁹ They present a multicomponent supramolecular heterodimer (Fig. 13a), which is constructed by photoswitchable DTE-bridged doubly charged bipyridinium (BP) salt (1), naphthalene (NP)-substituted chiral diphenylalanine (2), and cucurbit[8]uril (CB[8]). Diphenylalanine (l-Phe-l-Phe, FF) as a chiral source is introduced into the supramolecular system and provides the possibility of chiral transfer. Intermolecular hydrogen-bond interaction of FF and aromatic stacking effect of DTE supply a self-aggregated chance. These forces caused the formation of typical nanofibers with a diameter of 20–30 nm (Fig. 13b). Combining the ultra-stability of CB[8] complexes (the binding constant $\log K$ can reach over 10), the system realized the topological transformation from one-dimensional nanofibers to two-dimensional nanosheets (thickness: 7.8 nm), owing to the intervention of the rigid CB[8] host that blocked the hydrogen bonding between FFs. Photocontrollable




Fig. 12 Mesogen-assisted photo-responsive systems enabling the modulation of morphology and orientation. (a) and (b) After UV irradiation, the SAXS patterns reveal a phase change from hexagonal to cubic in an arylazopyrazole-based LC system. (c) Corresponding POM micrographs showing birefringent, hexagonal-to-isotropic cubic transition.¹²² (d) AFM images of a halogen bonding mediated LC BCP film and its orientations upon polarized light irradiation. Scale bar: 200 nm.¹²³ (a)–(c) Reproduced with permission.¹²² Copyright © 2024 The Authors. Published by American Chemical Society. This publication is licensed under CC-BY 4.0 (<https://creativecommons.org/licenses/by/4.0/>). (d) Reproduced with permission.¹²³ Copyright © 2020, American Chemical Society.






Fig. 13 Photo-responsive systems with host-guest interactions for synergistically regulating the ordered structure of assemblies. (a) Photo-controlled chiral transfer driven by CB[8] host-guest recognition and (b) corresponding nano-morphological changes and cartoon illustrations.¹²⁹ (c) Corresponding CD and absorption spectral changes.¹²⁹ (a)–(c) Reproduced with permission.¹²⁹ Copyright © 2023 The Authors. Published by American Chemical Society. This publication is licensed under CC-BY-NC-ND 4.0 (<https://creativecommons.org/licenses/by-nc-nd/4.0/>).

and reversible conversion between two-dimensional nanosheets and one-dimensional nanorods with chiral modulation within 16 min was followed, because the photocyclization effect of DTE changed the π - π stacking and cooperated with the host-guest interaction to reconstruct the self-assembled morphology. The entire process is also accompanied by changes in electronic transitions and chiral self-assembly, allowing absorption and circular dichroism (CD) spectra to track these dynamic changes (Fig. 13c).

Furthermore, Liu *et al.* constructed a controllable dimensionality transition system based on host-guest recognition between coumarin-diphenylalanine (CO-FF) and γ -cyclodextrin (γ -CD) (Fig. 14a and b).¹³⁰ They constructed stable supramolecular assemblies using CO-FF and γ -CD (binding constant: $7.01 \times 10^3 \text{ M}^{-1}$). Through the collaboration of host-guest interactions, one-dimensional nanofibers with an average width of several nanometers and a length of tens of micrometers were initially formed, due to the similar peptide properties as in the previous example and the inclusion of cyclodextrin that enhanced the amphiphilicity of the guest molecule. Such nanofibers were then converted into two-dimensional films with a lateral dimension of tens of micrometers and a thickness of 4.5 nm *via* photo-dimerization of the coumarin groups after 365-nm irradiation for 8 h. This is because the host-guest complexes after photodimerization can grow along two perpendicular directions, and the resultant two-dimensional structure was stabilized by the hydrogen bonds and π - π interactions among adjacent di-CO-FF- γ -CD units (Fig. 14a). In another photo-switchable self-assembly system involving adamantanyl-modified diphenylalanine

(Ada-FF) with azobenzene-bridged bis(β -CD) (H, Fig. 14a), high-constant complex (binding constant: $5.32 \times 10^4 \text{ M}^{-1}$) can be formed. On this basis, one-dimensional nanotubes (open-ended, curved tubular structures, formed by Ada-FF- β -CD-*cis*) and two-dimensional nanosheets (formed by Ada-FF- β -CD-*trans*), whose lengths and widths reached several micrometers with a height of approximately 7 nm, can be converted into each other through irradiation with different wavelengths of light.¹³¹ Typically, when the solution is exposed to ultraviolet light (365 nm) for 10 minutes, nearly all the two-dimensional nanosheets transform into one-dimensional nanotubes. Meanwhile, the resulting nanotubes can revert to their original two-dimensional nanosheets after being irradiated with visible light (450 nm) for 30 minutes (Fig. 14b). Here, the molecular length variation of H plays a crucial role (6.51 nm for the *trans*-species and 6.18 nm for the *cis*-one, accompanied by configurational bending, Fig. 14c). This, in turn, changes the self-assembly dynamics, achieving a morphological transition from two-dimensional to one-dimensional while weakening the rigidity of the system. These examples typically illustrate the strategy of photo-induced ordered self-assembly mediated by host-guest interaction in learning point (2).

3.4. PEIA

PEIA can occur *in situ* to regulate molecular motion and drive self-assembly change of the photo-responsive groups themselves, or cooperatively drive the self-assembly change of a second component like polymer chains, thereby controlling the orderliness of the entire system.⁶³ This strategy refers to






Fig. 14 Photo-responsive systems with host-guest interactions for synergistically regulating the ordered structure of assemblies. (a) A coumarin-diphenylalanine (CO-FF) based guest system and schematic illustration of their assemblies with γ -CD. (b) TEM images of CO-FF \subset γ -CD irradiated for (1) 0, (2) 4, and (3) 8 h, and (4) SEM image for 8 h at 365 nm.¹³⁰ (c) Ada-FF and H, and their assembly. (d) TEM images showed: (1) the one-dimensional structure of Ada-FF (scale = 0.2 μ m); (2) the two-dimensional structure of Ada-FF \subset H-trans (scale = 0.5 μ m); and (3) the one-dimensional structure of Ada-FF \subset H-cis (scale = 0.2 μ m).¹³¹ (a) and (b) Reproduced with permission.¹³⁰ Copyright © 2018 American Chemical Society. (c) and (d) Reproduced with permission.¹³¹ Copyright © 2017 Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim.

the dual regulation of both self-assembled structures and phase structures. This photophysical process does not alter molecular structures but utilizes excited-state conformational change to drive the assembly and phase structures of the entire system.

Building on the prior research, our group proposed a self-assembly strategy controlled by photoexcitation-mediated host-guest interactions to achieve a self-assembly transition from a linear nanostructure to a worm-like one (Fig. 15a).¹³² In detail, by introducing a unique photo-responsive group, persulfurated arene, into the host-guest system HB-CyD, we achieved a light-controlled transition from one ordered structure to another. Photoexcitation causes rearrangement of the host and the guest components, triggering a transformation in the self-assembled structure and enhancing the afterglow performance of the material. Based on a similar host-guest interaction, PEIA-caused 3D-to-2D exfoliation can also be attained on the ordered assembly of a persulfurated arene-based poly(pseudorotaxane) (PR) nanosheet (Fig. 15b).¹³³ Light exposure induces interlayer separation of the 3D PR structure, forming individual nanosheets. These nanosheets subsequently reorganize into bilayer nanosheets upon solvent evaporation.

Furthermore, by controlling molecular aggregation *via* photoexcitation, microphase separation in block copolymer materials can be regulated. Polystyrene-*b*-poly(L-lactide) (PS-*b*-PLLA) was chosen as the chiral BCP backbone, which could co-assemble with

a six-carboxylate-group modified hexathiobenzene compound (referred to as M-1) through hydrogen bonding. The helical microphase-separation characteristic of PS-*b*-(M-1)@PLLA in a film state was observable within different co-assembly ratios. Due to the application of PEIA, driven by the excited-state conformation of M-1, the helical pitch could be regulated *in situ*.¹³⁴ After the *in situ* irradiation for 20 s, the phase transitioned into an ordered helix, and the average pitch was approximately 25 nm. Through this PEIA-mediated phase control, we can also precisely adjust the phase volume ratio of the material (Fig. 15c).¹³⁵ A typical PEIA molecule, hexa-(aryltio) benzene with noncovalent sites modified on the periphery (M-2), was non-covalently linked to a block copolymer (BCP), PS-*b*-PA, to form a supramolecular BCP ensemble M-2@PS-*b*-PA. The molecular framework of M-2 exerted a distinct conformational difference between its ground state and excited state, thus driving the self-assembly of the BCP chain synergistically. The resulting system can access a full phase diagram across different irradiation periods, evolving from a lamellar structure to a gyroidal, cylindrical, and finally to a spherical one within 15 min. These examples typically illustrate the PEIA strategy in learning point (2).

3.5. Design considerations

The structural evolution of light-responsive systems is governed by the interplay between kinetic trapping and thermodynamic






Fig. 15 Photo-responsive systems rendering PEIA effect that can cause order-to-order structural transfer. (a) Cryo-TEM images of HB-CyD before and after UV irradiation and the corresponding structural transition diagram of HB-CyD assembly.¹³² (b) Cryo-TEM images of a persulfurated arene-based PR in pure water without light irradiation and after light irradiation with different periods.¹³³ (c) AFM images and Schematic diagram of the PEIA-induced BCP self-assembly.¹³⁵ (a) Reproduced with permission.¹³² This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence (<https://creativecommons.org/licenses/by-nc/3.0/>). (b) Reproduced with permission.¹³³ Copyright © 2022 American Chemical Society. (c) Reproduced with permission.¹³⁵ Copyright © 2022 Wiley-VCH GmbH.

regulation, and this balance varies significantly across the four strategies discussed in this review. In photo-triggered polymerization-induced self-assembly, covalent bond formation often drives rapid structural fixation, unless dynamic covalent chemistry is introduced. In contrast, liquid crystal-assisted amplification and host-guest mediated assembly more commonly operate under thermodynamic or quasi-equilibrium conditions, where reversible molecular reorganization enables adaptive structural reconfiguration. PEIA occupies an intermediate case: while the primary photoevent occurs on ultrafast timescales, the subsequent ordering process may involve either reversible excited-state interaction modulation or non-equilibrium structural evolution, depending on relaxation pathways and cooperative effects. Across all four strategies, several common limitations emerge. Photofatigue and chromophore degradation may gradually reduce responsiveness under repeated cycling. Competitive side reactions or environmental perturbations (*e.g.*, temperature, solvent polarity, oxygen) can alter interaction strength or phase stability. Diffusion-driven

blurring may limit spatial precision at larger length scales. Furthermore, the trade-off between structural robustness and reversibility remains a fundamental constraint in many systems.

4. Material properties enabled by light-triggered structural ordering

In this section, we will analyse structure-property relationships: how different levels of structural ordering affect material performance. Photo-responsive ordered materials have demonstrated broad application prospects in numerous fields due to their unique multi-structural changes and dynamic response characteristics.¹³⁶ By introducing photo-responsive ability into address multiscale ordered structures, scientists have achieved precise control over material properties, enabling applications in micropatterning techniques, chiroptical modulation, luminescence control, photoresist, and so forth. This section will



Tutorial Review

focus on several typical material properties, detailing how photo-responsive ordered materials play a unique role in these fields and analyzing their advantages and potential.

4.1. Refractive index modulation and optical patterning

Due to changes in the refractive index of liquid crystal systems during photo-responsive processes, these materials can display different structural colors, enabling various visual patterning effects.¹³⁷ In the process of photo-triggered structural ordering, light irradiation not only regulates molecular alignment but also significantly influences the material optical properties and structural manifestations. In recent years, refractive index modulation and optical patterning based on photo-responsive molecular materials have become research hotspots, with numerous studies focusing on exploring the effects of photo-triggered processes on materials such as liquid crystals and polymers.

Katayama *et al.* revealed structural changes induced by light near topological defects through studying photoinduced molecular orientation changes.¹³⁸ Using light-induced polarization/phase microscopy, they observed orientation changes of molecules around local topological defects, which can significantly alter the refractive index distribution. Osuji *et al.* studied the fast phase transition in liquid crystalline block co-oligomers (BCOs) under light irradiation.¹³⁹ They found that UV and visible light could effectively control the alignment of BCO, enabling rapid switching of optical properties. Particularly, the light-driven phase transition affects the material anisotropy, resulting in significantly different refractive index characteristics under different irradiation conditions. Although the above systems involve a structural transition from order to disorder, they provide a new idea for the application of the system of light-responsive order transition in tunable optical devices.

To further optimize the relevant strategies, Li *et al.* found that under UV irradiation, the selective reflection spectrum of a LC material based on a cyclic azobenzenophane undergoes significant changes, thereby modulating its reflection behavior (Fig. 16). The regulation range of reflection wavelength can range from 450 nm to 800 nm.¹²⁰ Evans *et al.* explored light-driven phase transition phenomena in liquid crystal materials, where UV light induces a transition from a hexagonal to a cubic phase (Fig. 12c).¹²² This phase transition not only alters the material order but also significantly changes its optical properties, particularly in terms of refractive index and light scattering modulation. These examples typically illustrate the refractive index modulation portion in learning point (3).

4.2. Chiroptical modulation

Chiral self-assembly systems based on photo-responsive materials show great potential for tuning chiroptical properties, particularly CPL.^{140,141} By introducing luminescent dyes into asymmetric systems, the system is likely to exhibit unique chiral luminescence, *i.e.*, the CPL characteristics. Furthermore, by controlling the configuration or conformation changes of




Fig. 16 Photo-responsive systems enabling selective reflection tuning of LC materials. Polarized optical photomicrographs of a planar aligned film based on a cyclic azobenzenophane at room temperature, showing reversible phase transitions occurring by light irradiation of the sample inside a 5 μm cell.¹²⁰ Reproduced with permission.¹²⁰ Copyright © 2010 American Chemical Society.

photo-responsive groups *via* light irradiation, the ordered structure and the chiroptical signal of the whole systems can be further regulated, achieving light-mediated tuning of CPL.

As mentioned above, many research groups on light-induced LC phase transitions have discovered the phenomenon of chiroptical modulation and flipping. For example, Cheng *et al.* employed a cholesterol-based liquid crystal system with photo-responsive groups and achieved CPL signal inversion by adjusting the light intensity and wavelength (Fig. 11b and c).¹¹⁹ In this case, light-induced molecular configurational change caused chiral inversion in the system, thereby inverting the sign and intensity of its CPL signal. Light-tunable CPL characteristics can also be realized through PEIA effects. Our research found that light irradiation can induce molecular aggregation with boosting π - π stacking interactions within persulfurated arenes, subsequently regulating the structure of microphase separation in the chiral block copolymer, PS-*b*-(M-1@PLLA).¹³⁴ This light-induced molecular aggregation allows the material to exhibit tunable CD and CPL responses under different lighting conditions. In this way, our study shows that light irradiation can not only regulate the order of molecular self-assembly but also affect the luminescence intensity and thus achieve an effective tuning of CPL from almost a silent level to a g_{lum} of 0.005 (Fig. 17). These examples typically illustrate the chiroptical modulation portion in learning point (3).

4.3. Modulation of photoluminescence properties

The modulation of PL properties is another important topic in photo-responsive materials research, especially concerning luminescence changes induced by the variations of ordered structures, with an application potential in smart light-emitting events. Through light-induced multiscale structural changes, not only can the fluorescence and RTP properties of materials be controlled, but also light-tunable afterglow (a long-lasting emission observable after ceasing excitation) can be achieved.¹⁴²⁻¹⁴⁵ This control over PL properties provides important pathways for designing novel optoelectronic devices and






Fig. 17 Photo-responsive systems enabling chiroptical amplification. (a) Schematic diagram of the *in situ* regulation of chirality and CPL by light irradiation in the PS-*b*-(M-1@PLLA) film. Corresponding (b) CD spectra and (c) CPL spectra before and after *in situ* photoirradiation for 20 s ($\lambda_{\text{ex}} = 365$ nm).¹³⁴ Reproduced with permission.¹³⁴ Copyright © 2022 American Chemical Society.

opens new avenues for applications of various smart optical materials.

Our group investigated the effect of light on the luminescence behavior of tetrakis-(aryltio)benzene by studying the impact of photoinduced molecular rearrangement on its crystal structure.¹⁴⁶ The PEIA strategy can effectively trigger molecular rearrangement, leading to changes of molecular arrangement in single crystals and consequently modulating its photoluminescence properties among yellow, blue, and violet luminescence. We also accessed fast light-regulated solid-state luminescent materials (phosphorescence activated within 20 s) with noticeable afterglow effect through the unsymmetric tetrakis-(aryltio)benzene-based single-luminophore engineering. With further continuous UV irradiation, macroscopic photo-mechanical behaviors such as directional cracking and bending could be observed in the crystalline state, clearly indicating the effect of PEIA in the solid state (Fig. 18).¹⁴⁷ These examples typically illustrate the photoluminescent modulation portion in learning point (3).

4.4. Photoresists and nanolithography

Photoresists and nanolithography technologies are widely used in micro-nano fabrication, particularly in the manufacturing of integrated circuits, optoelectronic devices, and ultra-high-density storage media. BCPs, as self-assembling polymeric

materials, can guide the formation of nanostructures through their ordered transitions.^{148–150} With light-mediated self-assembly control, precise lithographic patterning can be achieved. This light-responsive nanostructure generation approach also shows great potential in those high-tech fields, such as high-precision photomask fabrication and magnetic storage media.^{151,152}

Watkins *et al.* demonstrated the application potential of photo-responsive materials in nanolithography by studying the light-induced ordering process with BCPs (Fig. 19a).¹⁵³ They induced ordered alignment of polymer chains within a BCP film *via* UV irradiation (254 nm, 1 min) mediated by photoacid, forming highly regular nanostructures upon hydrogen bond remodeling between photoacid products and BCPs. Fig. 15 presents representative scanning force microscopy (SFM) images of both unexposed and exposed regions. The roughness of the unexposed area is attributed to crystallization (Fig. 19b and c). The UV-exposed area displays a fingerprint-like pattern, suggesting the formation of ordered cylindrical structures (Fig. 19d and e). Both height maps and phase maps reveal morphological features, clearly indicating that the photoinduced ordering process leads to the formation of topographical patterns. The self-assembly behavior of the photo-responsive BCPs allows control over material order at the nanoscale and points out some promising approaches for the development of




Fig. 18 Photoinduced RTP enhancement and directional cracking behaviour of unsymmetric tetrakis-(aryltio)benzene crystals. Optical micrographs of crystals before and after UV irradiation showing photoinduced RTP enhancement and crystal bending behavior.¹⁴⁷ Reproduced with permission.¹⁴⁷ Copyright © 2024 Wiley-VCH GmbH.






Fig. 19 Photo-responsive systems enabling well-ordered cylindrical nanomorphology through region-selective irradiation. (a) Schematic of the photoinduced ordering process of a photoacid-mediated BCP film; SFM images of unexposed and exposed regions of the film: (b) height image of the unexposed region (z range = 10 nm); (c) phase image of the unexposed region (z range = 22°); (d) height image of the exposed region (z range = 4 nm); (e) phase image of the exposed region (z range = 9°). Scale bars = 150 nm.¹⁵³ Reproduced with permission.¹⁵³ Copyright © 2011, American Chemical Society.

photoresists and nanolithography technology. This example typically illustrates the lithographic property portion in learning point (3).

5. Summary and outlooks

Here, we attempt to present design guidelines and future directions for developing light-regulated materials with controllable structural ordering. This review has summarized the latest research progress in photo-responsive chemical systems enabling multiscale structural ordering. It focuses on the fundamental principles and emerging mechanisms underlying photo-responsive materials, as well as strategies for constructing and dynamically tuning ordered structures under light stimuli. We further discuss how structural ordering across different length scales governs material performance, and provide a comparative analysis of current approaches for achieving hierarchical ordering. A thorough understanding and control of the light-responsive arrangements at different scales is largely driven by their technological application value. From using the molecular isomerization in liquid crystals to achieve soft robotics technology, to utilizing the phase transition in block copolymers to realize the next-generation nanolithography technology, these principles demonstrate that multi-scale arrangements are the key design parameters for achieving complex functions such as programmed movement, adaptive optics, and rewritable information storage.

5.1. Summary of actionable design principles

Several generalizable design principles can be extracted from the four strategies discussed in this review. First, effective multiscale ordering requires a transduction mechanism that amplifies photoresponsive molecular events into cooperative intermolecular interactions. Without such amplification,

structural reorganization remains localized. Second, the balance between kinetic trapping and thermodynamic equilibration fundamentally determines reversibility, spatial precision, and structural persistence. Third, spatial resolution is often limited not by the behaviors of the photoresponsive moieties but by diffusion and relaxation dynamics at larger length scales. Fourth, structural robustness and reversibility typically exhibit an intrinsic trade-off, requiring deliberate tuning of interaction strength, relaxation pathways, and environmental stability.

At the same time, certain design constraints are strategy-specific. Covalent bond-forming systems often favor structural permanence but sacrifice reversibility; liquid-crystalline systems rely on mesogenic alignment and are sensitive to temperature and phase stability; host-guest systems depend critically on binding equilibria and competitive interactions; and photophysical strategies such as PEIA require chromophores with appropriate excited-state lifetimes and conformational flexibility. Recognizing which principles are broadly applicable and which are mechanism-dependent is essential for rational material design. These points collectively reflect the design guidelines in learning point (4).

5.2. Future challenges

Despite significant breakthroughs, several issues and challenges remain to be addressed, particularly at the application level. Specifically, the following aspects are key focus for future research.

(1) **Incorporating long-wavelength-responsive chromophores for constructing long-range ordered structures and optimizing the transparency.** For biomedical usage, light penetration depth is often limited by tissue absorption, scattering, and other factors, which can disrupt the precise spatial control required for effective photo-regulation. The resulting challenge in delivering light, especially for deep-tissue optical therapy



and diagnosis, underscores a critical limitation. Here, structural ordering within photo-responsive materials offers a promising pathway. By enabling directed energy transfer and creating well-defined optical pathways, ordered structures may enhance the efficiency of light utilization at the target site. Future research could, therefore, focus on leveraging this principle to optimize the transparency and intrinsic light-harvesting capabilities of materials. For instance, developing more second- and third-window near-infrared (NIR-II/III) chromophores (e.g., donor-acceptor-donor-based dyes, conjugated polymers) that align their absorption with biological transparency windows. Alternatively, combining such hierarchically ordered systems with external optical enhancement technologies (e.g., optical fibers, waveguides, or photonic crystals) could synergistically overcome penetration barriers. Furthermore, the rational design of ordered materials with tissue-specific optical properties would allow for customized penetration depths, thereby greatly expanding their applicability across diverse biomedical scenarios.

(2) Employing artificial intelligence to predict and optimize the fatigue resistance and long-term stability of photo-responsive materials. The ordered structures of photo-responsive molecules may degrade under repeated light response cycles, especially under high-intensity or prolonged irradiation. The long-term stability and reproducibility of materials are crucial for maintaining effective performance in practical applications. For instance, in adaptive optics and neuromorphic devices, materials need to maintain stable structure and performance through repeated response and adjustment cycles. Future research should focus on developing more durable materials that can effectively recover their original ordered structure while enhancing their performance stability over multiple cycles. To accelerate the discovery of such durable systems, machine-learning-guided molecular dynamics simulations could be employed to predict fatigue behavior and screen for molecular motifs that resist irreversible degradation.

(3) Employing artificial intelligence to refine molecular design and structural control for further improvements in photo-response efficiency and sensitivity. Although existing photo-responsive materials have seen progress in response speed and efficiency, there is still room for improvement compared to practical application demands. Increasing the response speed of photo-responsive materials, enabling them to respond more quickly to external stimuli, is particularly important in applications requiring rapid switching or modulation, such as real-time sensing and dynamically adjustable optical systems. Researchers could further enhance the photo-response efficiency and sensitivity of materials by optimizing molecular design and control strategies, potentially assisted by AI-guided optimization.

In summary, the research and development of photo-responsive ordered systems are progressing rapidly. The above paragraphs typically elaborate on the future directions for developing light-regulated materials with controllable structural ordering in learning point (4). With deepening theoretical research and continuous technological innovation, it is

expected that photo-responsive materials will find practical applications in more fields, leading to transformative developments particularly in biomedicine, smart materials, and energy. In the future, we can anticipate the emergence of more efficient, stable, and easily scalable photo-responsive molecular materials, applied to a wider range of scenarios with practical needs.

Conflicts of interest

There are no conflicts to declare.

Data availability

No primary research results, software or code have been included and no new data were generated or analysed as part of this review.

Acknowledgements

This work is supported by the National Natural Science Foundation of China (22275038 and 22575058).

Notes and references

- H. Ma and J. Hao, *Chem. Soc. Rev.*, 2011, **40**, 5457–5471.
- J. S. Miller, *Chem. Soc. Rev.*, 2011, **40**, 3266–3296.
- H. K. Bisoyi and Q. Li, *Acc. Chem. Res.*, 2014, **47**, 3184–3195.
- Q. Zhang, Y. Sun, C. He, F. Shi and M. Cheng, *Adv. Sci.*, 2020, **7**, 2002025.
- T. Zhang, D. Wang and J. Liu, *Adv. Mater.*, 2024, **36**, 2408259.
- H. Yin, K. Xing, Y. Zhang, D. M. A. S. Dissanayake, Z. Lu, H. Zhao, Z. Zeng, J.-H. Yun, D.-C. Qi and Z. Yin, *Chem. Soc. Rev.*, 2021, **50**, 6423–6482.
- R. Y. Liu, K. T. Tan, Y. F. Gong, Y. Z. Chen, Z. E. Li, S. L. Xie, T. He, Z. Lu, H. Yang and D. L. Jiang, *Chem. Soc. Rev.*, 2021, **50**, 120–242.
- Z. G. Zhao, R. C. Fang, Q. F. Rong and M. J. Liu, *Adv. Mater.*, 2017, **29**, 1703045.
- L. Xiang, Q. Li, C. Li, Q. Yang, F. Xu and Y. Mai, *Adv. Mater.*, 2023, **35**, 2207684.
- G. Yang, H.-m Ding, Z. Kochovski, R. Hu, Y. Lu, Y.-q Ma, G. Chen and M. Jiang, *Angew. Chem., Int. Ed.*, 2017, **56**, 10691–10695.
- L. Shao, J. Ma, J. L. Prelesnik, Y. Zhou, M. Nguyen, M. Zhao, S. A. Jenekhe, S. V. Kalinin, A. L. Ferguson, J. Pfaendtner, C. J. Mundy, J. J. De Yoreo, F. Baneyx and C.-L. Chen, *Chem. Rev.*, 2022, **122**, 17397–17478.
- E. Potanina, C. Flindt, M. Moskalets and K. Brandner, *Phys. Rev. X*, 2021, **11**, 021013.
- T. Liu, Z. He, J.-L. Wang, S.-Z. Sheng, Z.-Y. Xian, J.-W. Liu and S.-H. Yu, *Angew. Chem., Int. Ed.*, 2025, **64**, e202503613.
- D. Guo, Y. Li, X. Zheng, F. Li, S. Chen, M. Li, Q. Yang, H. Li and Y. Song, *J. Am. Chem. Soc.*, 2018, **140**, 18–21.



- 15 Y. Yang, C.-C. Chen, M. C. Scott, C. Ophus, R. Xu, A. Pryor, L. Wu, F. Sun, W. Theis, J. Zhou, M. Eisenbach, P. R. C. Kent, R. F. Sabirianov, H. Zeng, P. Ercius and J. Miao, *Nature*, 2017, **542**, 75–79.
- 16 A. M. Nie, Z. S. Zhao, B. Xu and Y. J. Tian, *Nat. Mater.*, 2025, **24**, 1172–1185.
- 17 Y. Wang, J. Chen, Y. Zhong, S. Jeong, R. Li and X. Ye, *J. Am. Chem. Soc.*, 2022, **144**, 13538–13546.
- 18 Y. Ku, K. Xu, L. Yan, K. Zhang, D. Song, X. Li, S. Li, S. Cheng and C. Shan, *Carbon Energy*, 2024, **6**, e440.
- 19 F. Hong, F. Zhang, Y. Liu and H. Yan, *Chem. Rev.*, 2017, **117**, 12584–12640.
- 20 V. Kulikov, N. A. B. Johnson, A. J. Surman, M. Hutin, S. M. Kelly, M. Hezwani, D.-L. Long, G. Meyer and L. Cronin, *Angew. Chem., Int. Ed.*, 2017, **56**, 1141–1145.
- 21 F. Bošković, C. Maffeo, G. Patiño-Guillén, R. Tivony, A. Aksimentiev and U. F. Keyser, *ACS Nano*, 2024, **18**, 15013–15024.
- 22 S. I. S. Hendrikse, R. Contreras-Montoya, A. V. Ellis, P. Thordarson and J. W. Steed, *Chem. Soc. Rev.*, 2022, **51**, 28–42.
- 23 Q. Luo, C. Hou, Y. Bai, R. Wang and J. Liu, *Chem. Rev.*, 2016, **116**, 13571–13632.
- 24 M. Xie, M. G. N. Derks, E. H. W. Koch, C. B. van Boven, M. Janlad, B. Bagheri, Z. Xu, D. Kovryzhenko, C. A. van Walree, A. Sobota, M. Weingarth, J. Wong-Ekkabut, M. Karttunen, E. Breukink, J. A. Killian, A. F. P. Sonnen and J. H. Lorent, *J. Am. Chem. Soc.*, 2025, **147**, 9175–9189.
- 25 S. MuhammedNazaar, J. Yao, M. R. Necelis, Y. C. Park, Z. Shen, M. D. Bridges, R. Guo, N. Swope, M. S. Rhee, M. Kim, K. H. Kim, W. L. Hubbell, K. G. Fleming, L. Columbus, S.-G. Kang and H. Hong, *Sci. Adv.*, 2025, **11**, eadv9568.
- 26 L. Jin, N. P. Kamat, S. Jena and J. W. Szostak, *Small*, 2018, **14**, 1704077.
- 27 B. Kwon, M. Lee, A. J. Waring and M. Hong, *J. Am. Chem. Soc.*, 2018, **140**, 8246–8259.
- 28 X. Fu, J.-M. Park, R. Liang, Y. Xue and M. Zhong, *Prog. Polym. Sci.*, 2025, **170**, 102027.
- 29 A. Xin, Y. Su, S. Feng, M. Yan, K. Yu, Z. Feng, K. Hoon Lee, L. Sun and Q. Wang, *Adv. Mater.*, 2021, **33**, 2006946.
- 30 C. Yuan, W. Ji, R. Xing, J. Li, E. Gazit and X. Yan, *Nat. Rev. Chem.*, 2019, **3**, 567–588.
- 31 C. Zhang, G. Chu, Z. Ruan, N. Tang, C. Song, Q. Li, W. Zhou, J. Jin, H. Haick, Y. Chen and D. Cui, *ACS Nano*, 2022, **16**, 16584–16597.
- 32 P. Vukusic, J. R. Sambles and C. R. Lawrence, *Nature*, 2000, **404**, 457.
- 33 Z. Chen, F. Fu, Y. Yu, H. Wang, Y. Shang and Y. Zhao, *Adv. Mater.*, 2019, **31**, 1805431.
- 34 M. Kolle, P. M. Salgard-Cunha, M. R. J. Scherer, F. Huang, P. Vukusic, S. Mahajan, J. J. Baumberg and U. Steiner, *Nat. Nanotechnol.*, 2010, **5**, 511–515.
- 35 L. Zhang, S. Feih, S. Daynes, S. Chang, M. Y. Wang, J. Wei and W. F. Lu, *Addit. Manuf.*, 2018, **23**, 505–515.
- 36 K. Chen and L. Li, *Adv. Mater.*, 2019, **31**, 1901115.
- 37 L.-J. Chen and H.-B. Yang, *Acc. Chem. Res.*, 2018, **51**, 2699–2710.
- 38 K. L. Hvorecny, *Nat. Struct. Mol. Biol.*, 2024, **31**, 1147–1149.
- 39 H. J. Bae, S. Bae, J. Yoon, C. Park, K. Kim, S. Kwon and W. Park, *Sci. Adv.*, 2017, **3**, e1700071.
- 40 Y. Deng, S. Gao, J. Liu, U. Gohs, E. Mäder and G. Heinrich, *Mater. Horiz.*, 2017, **4**, 389–395.
- 41 G. Li, J. Fei, Y. Xu, Y. Li and J. Li, *Adv. Funct. Mater.*, 2018, **28**, 1706557.
- 42 Z. Wang, X. Rong, D. Zhao, X. Zhang, C. He and N. Zhao, *Mater. Horiz.*, 2025, **12**, 10478–10497.
- 43 K. Liu, H. Ding, S. Li, Y. Niu, Y. Zeng, J. Zhang, X. Du and Z. Gu, *Nat. Commun.*, 2022, **13**, 4563.
- 44 H.-T. Zhang, T. Zhang and X. Zhang, *Adv. Sci.*, 2023, **10**, 2300193.
- 45 C. Li, X. Qin, Z. Zhang, Y. Lv, S. Zhang, Y. Fan, S. Liang, B. Guo, Z. Li, Y. Liu and D. Luo, *Nano Today*, 2022, **42**, 101354.
- 46 T. Le, V. C. Epa, F. R. Burden and D. A. Winkler, *Chem. Rev.*, 2012, **112**, 2889–2919.
- 47 Y. Wang, I. C. Jenkins, J. T. McGinley, T. Sinno and J. C. Crocker, *Nat. Commun.*, 2017, **8**, 14173.
- 48 Y. Xiao, M. Zhou, M. Zeng and L. Fu, *Adv. Sci.*, 2019, **6**, 1801501.
- 49 D.-G. Kang, Y.-B. Kook, I.-S. Kim, M. Rim, H. Ko, C.-H. Hsu, C.-L. Wang, K.-H. Ryu, D.-Y. Kim and K.-U. Jeong, *Small*, 2025, **21**, 2404782.
- 50 T. Guo, L. Luo, L. Wang, F. Zhang, Y. Liu and J. Leng, *ACS Nano*, 2025, **19**, 18003–18036.
- 51 S. Chandrasekaran, Q. Wang, Q. Liu, H. Wang, D. Qiu, H. Lu, Y. Liu, C. Bowen and H. Huang, *Chem. Soc. Rev.*, 2025, **54**, 2275–2343.
- 52 Z. Meng, S. Miao, Y. Liu, Y. Li, Y. Ma, W. Luo and H. Huang, *Mater. Horiz.*, 2025, **12**, 8380–8408.
- 53 H. Yin, X. Yu, Y. Zhu, Z. Hou, J. Cunha, Z. Liang and Z. Yu, *Adv. Sci.*, 2025, **12**, e03340.
- 54 M. Li, H. Hu, B. Liu, X. Liu, Z.-G. Zheng, H. Tian and W.-H. Zhu, *J. Am. Chem. Soc.*, 2022, **144**, 20773–20784.
- 55 N. P. Nazirkar, V. Tran, P. Bassène, A. Ndiaye, J. Barringer, J. Jiang, W. Cha, R. Harder, J. Shi, M. N'Gom and E. Fohntung, *Adv. Mater.*, 2025, **37**, 2415231.
- 56 A. S. Gliozzi, M. Miniaci, A. Chiappone, A. Bergamini, B. Morin and E. Descrovi, *Nat. Commun.*, 2020, **11**, 2576.
- 57 C. Wang, M. P. O'Hagan, Z. Li, J. Zhang, X. Ma, H. Tian and I. Willner, *Chem. Soc. Rev.*, 2022, **51**, 720–760.
- 58 W. Xu, D. M. Sanchez, U. Raucci, H. Zhou, X. Dong, M. Hu, C. J. Bardeen, T. J. Martinez and R. C. Hayward, *Nat. Mater.*, 2023, **22**, 1152–1159.
- 59 O. P. Dimitriev, *Chem. Rev.*, 2022, **122**, 8487–8593.
- 60 Y. Deng, G. Long, Y. Zhang, W. Zhao, G. Zhou, B. L. Feringa and J. Chen, *Light:Sci. Appl.*, 2024, **13**, 63.
- 61 H. P. Lee and A. K. Gaharwar, *Adv. Sci.*, 2020, **7**, 2000863.
- 62 Y. Liu and P. Xing, *Adv. Mater.*, 2023, **35**, 2300968.
- 63 X. Jia and L. Zhu, *Acc. Chem. Res.*, 2023, **56**, 655–666.
- 64 J. Großkopf, T. Kratz, T. Rigotti and T. Bach, *Chem. Rev.*, 2022, **122**, 1626–1653.



- 65 A. P. Demchenko, V. I. Tomin and P.-T. Chou, *Chem. Rev.*, 2017, **117**, 13353–13381.
- 66 I. M. Irshadeen, S. L. Walden, M. Wegener, V. X. Truong, H. Frisch, J. P. Blinco and C. Barner-Kowollik, *J. Am. Chem. Soc.*, 2021, **143**, 21113–21126.
- 67 A. Fihey, A. Perrier, W. R. Browne and D. Jacquemin, *Chem. Soc. Rev.*, 2015, **44**, 3719–3759.
- 68 Y. Boeije and M. Olivucci, *Chem. Soc. Rev.*, 2023, **52**, 2643–2687.
- 69 L. Salem, *Science*, 1976, **191**, 822–830.
- 70 L. Huang and G. Han, *Nat. Rev. Chem.*, 2024, **8**, 238–255.
- 71 N. J. Turro and G. Schuster, *Science*, 1975, **187**, 303–312.
- 72 T. Kumpulainen, B. Lang, A. Rosspeintner and E. Vauthey, *Chem. Rev.*, 2017, **117**, 10826–10939.
- 73 J.-Y. Xu, X. Tong, P. Yu, G. E. Wenyua, T. McGrath, M. J. Fong, J. Wu and Z. M. Wang, *Adv. Sci.*, 2018, **5**, 1800221.
- 74 H.-B. Cheng, S. Zhang, J. Qi, X.-J. Liang and J. Yoon, *Adv. Mater.*, 2021, **33**, 2007290.
- 75 M. Zhu, W. Wang, C. Zhang, L. Zhu and S. Yang, *Adv. Fiber Mater.*, 2021, **3**, 172–179.
- 76 H. M. D. Bandara and S. C. Burdette, *Chem. Soc. Rev.*, 2012, **41**, 1809–1825.
- 77 C. Wang, M. D. J. Waters, P. Zhang, J. Suchan, V. Svoboda, T. T. Luu, C. Perry, Z. Yin, P. Slaviček and H. J. Wörner, *Nat. Chem.*, 2022, **14**, 1126–1132.
- 78 U. Raucci, H. Weir, C. Bannwarth, D. M. Sanchez and T. J. Martinez, *Nat. Commun.*, 2022, **13**, 2091.
- 79 F. D. Lewis, R. S. Kalgutkar and J.-S. Yang, *J. Am. Chem. Soc.*, 1999, **121**, 12045–12053.
- 80 M. Irie, T. Fukaminato, K. Matsuda and S. Kobatake, *Chem. Rev.*, 2014, **114**, 12174–12277.
- 81 S. Lin, K. G. Gutierrez-Cuevas, X. Zhang, J. Guo and Q. Li, *Adv. Funct. Mater.*, 2021, **31**, 2007957.
- 82 L. Hou, T. Leydecker, X. Zhang, W. Rekam, M. Herder, C. Cendra, S. Hecht, I. McCulloch, A. Salleo, E. Orgiu and P. Samorì, *J. Am. Chem. Soc.*, 2020, **142**, 11050–11059.
- 83 R. Klajn, *Chem. Soc. Rev.*, 2014, **43**, 148–184.
- 84 V. M. Lechner, M. Nappi, P. J. Deneny, S. Folliet, J. C. K. Chu and M. J. Gaunt, *Chem. Rev.*, 2022, **122**, 1752–1829.
- 85 J. Zhu, X.-W. Sun, X. Yang, S.-N. Yu, L. Liang, Y.-Z. Chen, X. Zheng, M. Yu, L. Yan, J. Tang, W. Zhao, X.-J. Yang and B. Wu, *Angew. Chem., Int. Ed.*, 2023, **62**, e202314510.
- 86 J. Gemen, J. R. Church, T.-P. Ruoko, N. Durandin, M. J. Białek, M. Weisfenfels, M. Feller, M. Kazes, M. Odaybat, V. A. Borin, R. Kalepu, Y. Diskin-Posner, D. Oron, M. J. Fuchter, A. Priimagi, I. Schapiro and R. Klajn, *Science*, 2023, **381**, 1357–1363.
- 87 C.-W. Chang, Y.-C. Lu, T.-T. Wang and E. W.-G. Diau, *J. Am. Chem. Soc.*, 2004, **126**, 10109–10118.
- 88 W.-J. Li, W.-T. Xu, X.-Q. Wang, Y. Jiang, Y. Zhu, D.-Y. Zhang, X.-Q. Xu, L.-R. Hu, W. Wang and H.-B. Yang, *J. Am. Chem. Soc.*, 2023, **145**, 14498–14509.
- 89 K. P. Xie, Z. Y. Ruan, B. H. Lyu, X. X. Chen, X. W. Zhang, G. Z. Huang, Y. C. Chen, Z. P. Ni and M. L. Tong, *Angew. Chem., Int. Ed.*, 2021, **60**, 27144–27150.
- 90 T. Dang, Y. He, X. Yu, Z.-Y. Zhang, L. Li and T. Li, *J. Am. Chem. Soc.*, 2025, **147**, 38677–38683.
- 91 Y. Li, B. Xue, J. Yang, J. Jiang, J. Liu, Y. Zhou, J. Zhang, M. Wu, Y. Yuan, Z. Zhu, Z. J. Wang, Y. Chen, Y. Harabuchi, T. Nakajima, W. Wang, S. Maeda, J. P. Gong and Y. Cao, *Nat. Chem.*, 2024, **16**, 446–455.
- 92 J. Wang, S. Shen, X. Li, J. Li and F. Dong, *Chem. Rev.*, 2025, **125**, 7811–7917.
- 93 Z. Huang, N. Luo, C. Zhang and F. Wang, *Nat. Rev. Chem.*, 2022, **6**, 197–214.
- 94 S. Crespi and M. Fagnoni, *Chem. Rev.*, 2020, **120**, 9790–9833.
- 95 C.-Y. Huang, J. Li and C.-J. Li, *Chem. Sci.*, 2022, **13**, 5465–5504.
- 96 X. Yao, H. Shi, X. Wang, H. Wang, Q. Li, Y. Li, J. Liang, J. Li, Y. He, H. Ma, W. Huang and Z. An, *Sci. China: Chem.*, 2022, **65**, 1538–1543.
- 97 Y. N. Hong, J. W. Y. Lam and B. Z. Tang, *Chem. Soc. Rev.*, 2011, **40**, 5361–5388.
- 98 M. Gao, R. Wu, Y. Zhang, Y. Meng, M. Fang, J. Yang and Z. Li, *J. Am. Chem. Soc.*, 2025, **147**, 2653–2663.
- 99 D. Escudero, *Acc. Chem. Res.*, 2016, **49**, 1816–1824.
- 100 S. Huang, A. Abedi Syed Ali, Z. Li, R. Huang, X. Yan, M. Izadyar, Q. Qiao, Y. Fang, Z. Xu and X. Liu, *CCS Chem.*, 2024, **6**, 2804–2813.
- 101 H. Zhang, L. Du, L. Wang, J. Liu, Q. Wan, R. T. K. Kwok, J. W. Y. Lam, D. L. Phillips and B. Z. Tang, *J. Phys. Chem. Lett.*, 2019, **10**, 7077–7085.
- 102 J. Yang, X. Zhen, B. Wang, X. Gao, Z. Ren, J. Wang, Y. Xie, J. Li, Q. Peng, K. Pu and Z. Li, *Nat. Commun.*, 2018, **9**, 840.
- 103 X. Jia, C. Shao, X. Bai, Q. Zhou, B. Wu, L. Wang, B. Yue, H. Zhu and L. Zhu, *Proc. Natl. Acad. Sci. U. S. A.*, 2019, **116**, 4816–4821.
- 104 S. Wu, Z. Li, G. V. Baryshnikov, M. Zhang, B. Jiang and L. Zhu, *Chem. Mater.*, 2026, **38**, 1325–1332.
- 105 G. Xu, A. Chen, F. Feng, Y. Wu and X. Wang, *ACS Nano*, 2024, **18**, 35347–35355.
- 106 Z. Li, C. Y. Gao, D. Su, C. Jia and X. Guo, *ACS Mater. Lett.*, 2021, **3**, 1484–1502.
- 107 S. Datta, H. Itabashi, T. Saito and S. Yagai, *Nat. Chem.*, 2025, **17**, 477–492.
- 108 C. S. Zehe, J. A. Hill, N. P. Funnell, K. Kreger, K. P. van der Zwan, A. L. Goodwin, H.-W. Schmidt and J. Senker, *Angew. Chem., Int. Ed.*, 2017, **56**, 4432–4437.
- 109 J. Neugebauer and T. Hickel, *WIREs Comput. Mol. Sci.*, 2013, **3**, 438–448.
- 110 P. J. Santos, P. A. Gabrys, L. Z. Zornberg, M. S. Lee and R. J. Macfarlane, *Nature*, 2021, **591**, 586–591.
- 111 M. D. Ward and P. R. Raithby, *Chem. Soc. Rev.*, 2013, **42**, 1619–1636.
- 112 H. K. Bisoyi and Q. Li, *Chem. Rev.*, 2016, **116**, 15089–15166.
- 113 Z.-X. Chang, R.-M. Zhu, C.-Y. Hong and W.-J. Zhang, *Sci. China: Chem.*, 2024, **67**, 390–397.
- 114 S. Guan and A. Chen, *ACS Macro Lett.*, 2020, **9**, 14–19.
- 115 W. Chen, J. Y. Wang, W. Zhao, L. Li, X. Wei, A. C. Balazs, K. Matyjaszewski and T. P. Russell, *J. Am. Chem. Soc.*, 2011, **133**, 17217–17224.



- 116 M. Han, Y. Luo, B. Damaschke, L. Gomez, X. Ribas, A. Jose, P. Peretzki, M. Seibt and G. H. Clever, *Angew. Chem., Int. Ed.*, 2016, **55**, 445–449.
- 117 A. Ryabchun, D. Yakovlev, A. Bobrovsky and N. Katsonis, *ACS Appl. Mater. Interfaces*, 2019, **11**, 10895–10904.
- 118 S. Pan, M. F. Ni, B. Mu, Q. Li, X. Y. Hu, C. Lin, D. Z. Chen and L. Y. Wang, *Adv. Funct. Mater.*, 2015, **25**, 3571–3580.
- 119 Y. Li, Y. Chen, J. Luo, Y. Quan and Y. Cheng, *Adv. Mater.*, 2024, **36**, e2312331.
- 120 M. Mathews, R. S. Zola, S. Hurley, D. K. Yang, T. J. White, T. J. Bunning and Q. Li, *J. Am. Chem. Soc.*, 2010, **132**, 18361–18366.
- 121 T. Kosa, L. Sukhomlinova, L. Su, B. Taheri, T. J. White and T. J. Bunning, *Nature*, 2012, **485**, 347–349.
- 122 B. E. Jones, J. L. Greenfield, N. Cowieson, M. J. Fuchter and R. C. Evans, *J. Am. Chem. Soc.*, 2024, **146**, 12315–12319.
- 123 Y. X. Chen, S. Huang, T. J. Wang and H. F. Yu, *Macromolecules*, 2020, **53**, 1486–1493.
- 124 B. V. K. J. Schmidt and C. Barner-Kowollik, *Angew. Chem., Int. Ed.*, 2017, **56**, 8350–8369.
- 125 X. Ma and H. Tian, *Acc. Chem. Res.*, 2014, **47**, 1971–1981.
- 126 X. J. Loh, *Mater. Horiz.*, 2014, **1**, 185–195.
- 127 X. K. Ma, W. Zhang, Z. X. Liu, H. Y. Zhang, B. Zhang and Y. Liu, *Adv. Mater.*, 2021, **33**, 2007476.
- 128 H. Yang, B. Yuan, X. Zhang and O. A. Scherman, *Acc. Chem. Res.*, 2014, **47**, 2106–2115.
- 129 G. Liu, C. Tian, X. Fan, X. Xue, L. Feng, C. Wang and Y. Liu, *JACS Au*, 2023, **3**, 2550–2556.
- 130 N. Cheng, Y. Chen, J. Yu, J. J. Li and Y. Liu, *ACS Appl. Mater. Interfaces*, 2018, **10**, 6810–6814.
- 131 H. L. Sun, Y. Chen, X. Han and Y. Liu, *Angew. Chem., Int. Ed.*, 2017, **56**, 7062–7065.
- 132 M. Liu, B. Wu, G. V. Baryshnikov, S. Shen, H. Sun, X. Gu, H. Agren, Y. Xu, Q. Zou, D. H. Qu and L. Zhu, *Chem. Sci.*, 2024, **15**, 12569–12579.
- 133 M. Liu, B. Wu, S. Shen, H. Sun, X. Gu, S. Li, Z. Tang, J. Cheng, X. Ma, M. Zhang, Y. Xu and L. Zhu, *ACS Macro Lett.*, 2025, **14**, 93–100.
- 134 B. Yue, X. Feng, C. Wang, M. Zhang, H. Lin, X. Jia and L. Zhu, *ACS Nano*, 2022, **16**, 16201–16210.
- 135 B. Yue, X. Jia, G. V. Baryshnikov, X. Jin, X. Feng, Y. Lu, M. Luo, M. Zhang, S. Shen, H. Agren and L. Zhu, *Angew. Chem., Int. Ed.*, 2022, **61**, e202209777.
- 136 F. Xu and B. L. Feringa, *Adv. Mater.*, 2023, **35**, 2204413.
- 137 P. Zhang, L. T. de Haan, M. G. Debije and A. P. H. J. Schenning, *Light:Sci. Appl.*, 2022, **11**, 248.
- 138 H. Sakanoue, W. Y. Sohn and K. Katayama, *ACS Omega*, 2019, **4**, 13936–13942.
- 139 C. Lee, D. Ndaya, R. Bosire, N. K. Kim, R. M. Kasi and C. O. Osuji, *J. Am. Chem. Soc.*, 2022, **144**, 390–399.
- 140 L. L. Zhu, X. Li, S. J. Wu, K. T. Nguyen, H. Yan, H. Ågren and Y. L. Zhao, *J. Am. Chem. Soc.*, 2013, **135**, 9174–9180.
- 141 S. E. Penty, G. R. F. Orton, D. J. Black, R. Pal, M. A. Zwijnenburg and T. A. Barendt, *J. Am. Chem. Soc.*, 2024, **146**, 5470–5479.
- 142 X. Chen, X. F. Hou, X. M. Chen and Q. Li, *Nat. Commun.*, 2024, **15**, 5401.
- 143 J. Huang, Y. Jiang, Q. Chen, H. Xie and S. Zhou, *Nat. Commun.*, 2023, **14**, 7131.
- 144 D.-X. Feng, Y. Mu, J. Li, S. De Han, J.-H. Li, H.-L. Sun, M. Pan, J.-X. Hu and G.-M. Wang, *Adv. Funct. Mater.*, 2023, **33**, 2305796.
- 145 M. Komura, H. Sotome, H. Miyasaka, T. Ogawa and Y. Tani, *Chem. Sci.*, 2023, **14**, 5302–5308.
- 146 S. Shen, G. Baryshnikov, B. B. Yue, B. Wu, X. P. Li, M. Zhang, H. Ågren and L. L. Zhu, *J. Mater. Chem. C*, 2021, **9**, 11707–11714.
- 147 H. Sun, Z. Yu, C. Li, M. Zhang, S. Shen, M. Li, M. Liu, Z. Li, D. Wu and L. Zhu, *Angew. Chem., Int. Ed.*, 2025, **64**, e202413827.
- 148 G. G. Yang, H. J. Choi, K. H. Han, J. H. Kim, C. W. Lee, E. I. Jung, H. M. Jin and S. O. Kim, *ACS Appl. Mater. Interfaces*, 2022, **14**, 12011–12037.
- 149 L. Yao and J. J. Watkins, *ACS Nano*, 2013, **7**, 1513–1523.
- 150 L. L. Zhu, H. Tran, F. L. Beyer, S. D. Walck, X. Li, H. Ågren, K. L. Killops and L. M. Campos, *J. Am. Chem. Soc.*, 2014, **136**, 13381–13387.
- 151 C. E. Kim, J. W. Shim, S. J. Ham and S. H. Kim, *ACS Omega*, 2025, **10**, 8579–8587.
- 152 W. C. Xu, C. W. Liu, S. F. Liang, D. C. Zhang, Y. Z. Liu and S. Wu, *Adv. Mater.*, 2022, **34**, 2202150.
- 153 V. K. Daga, E. L. Schwartz, C. M. Chandler, J. K. Lee, Y. Lin, C. K. Ober and J. J. Watkins, *Nano Lett.*, 2011, **11**, 1153–1160.

