


 Cite this: *RSC Adv.*, 2026, 16, 16895

Cutting-edge advancements in the synthesis, chemical structure, and applications of the lithium batteries and supercapacitors of metal–/covalent–organic frameworks

 Na Xiao,^a Yaqiong Wang,^c Kang Yang,^{ID *bc} Zhengjun Wang,^c Dian Zhao,^c Yulong Shi,^c Jufeng Qiao^c and Fang Qian^c

Metal organic frameworks (MOFs) and covalent organic frameworks (COFs) are novel classes of advanced porous materials with high crystallinity, which have garnered significant research attention due to their distinctive structures and properties. However, the insufficient structural stability and poor conductivity are the major bottlenecks restricting their widespread application in new energy storage and conversion devices. A large number of studies have shown that by selecting appropriate synthesis methods and making targeted improvements, the crystal structure, pore characteristics and interface interactions of MOFs/COFs can be precisely controlled, thereby enhancing the bonding strength of covalent/coordination bonds, reducing the resistance of charge transfer, and improving their structural stability and conductivity. This paper describes the progress in MOF/COF research from the aspects of synthesis and chemical structure, summarizes the latest achievements, and presents their milestone applications in lithium-ion batteries and supercapacitors. Finally, it discusses the challenges and future prospects of developing high-performance MOF/COF energy storage materials.

 Received 15th January 2026
 Accepted 11th February 2026

DOI: 10.1039/d6ra00378h

rsc.li/rsc-advances

1. Introduction

The rapid development of society has brought convenience to the lives of people, but it has also led to many problems.¹ The energy issue is among the most pressing concerns faced by humanity currently. Energy shortage has become an increasingly acute crisis, serving as a significant deterrent to global economic growth, and it could ultimately jeopardize human survival. Therefore, exploring and tapping new energy sources² and reducing the energy consumption³ in equipment operation are the primary strategies to address the current energy crisis.

In recent years, porous materials have attracted considerable attention in various electronic fields, including batteries⁴ and supercapacitors (SCs),⁵ due to their unique properties. Among them, metal–organic frameworks (MOFs) and covalent organic frameworks (COFs) have shown particularly outstanding performance. MOFs are organic–inorganic hybrid materials that combine the characteristics of organic and inorganic materials,⁶ giving them a larger pore size range and specific surface area (SSA) than the common porous materials such as

zeolites, aluminum phosphates, and activated carbon.⁷ COFs represent a new class of carbon-based porous nanomaterials characterized by their low density, high surface area, and tunable chemical composition.⁸ This enables researchers to create a variety of hybrid products by modifying their chemical composition and adjusting the covalent bonds.⁹ As a result, COFs offer considerable flexibility for designing complex products with diverse porosity.

The exceptional properties exhibited by MOFs/COFs have the potential to broaden their application across diverse scientific fields, particularly in the context of molecular catalysts for energy storage.^{10,11} Indeed, it is evident that both MOFs and COFs have been the focus of extensive research due to their considerable potential in energy storage systems. These materials can be utilized in a variety of ways, including their direct application as active catalytic materials.¹² Alternatively, they can be used as precursors for the synthesis of porous carbon or metal oxides as active catalytic materials.¹³ For example, in a study by Xu *et al.*,¹⁴ novel 1D metal–organic nickel hydroxide nanorods were synthesized by the hydrothermal method and employed as electrode materials for SCs. Nickel-based MOF (Ni-MOF) nanorods exhibit exceptional uniformity regarding size, and they demonstrate high specific capacitance (mass-specific capacitance C_g and surface capacitance C_s), remarkably high-rate capability, and outstanding cycle stability. After 1000 cycles at a current density of 1 A g^{−1}, the capacitance remains at

^aFaculty of Engineering, Huanghe Science and Technology University, Zhengzhou, 450000, China. E-mail: angongyangkang@163.com

^bSchool of Mechanical and Electrical Engineering, Linzhou College of Architectural Technology, Anyang 456550, China

^cSchool of Mechanical and Aviation Manufacturing Engineering, Anyang Institute of Technology, Anyang 455000, China


approximately 94.8%. The superior performance of the rod-like Ni-MOF is attributed to its large surface area, suitable pore size, active redox metal sites and rapid charge transport kinetics. In recent years, substantial research efforts have been dedicated toward the development of functionalized MOFs and COFs for diverse energy storage applications. The materials in question must satisfy several criteria including elevated SSA,^{15,16} considerable electrolyte chemical stability^{17,18} and adequate porosity.^{19,20} The emphasis on MOFs/COFs is mainly motivated by their characteristic porous structure, the benefits offered by the synthesis processes, and their potential applications.²¹ Consequently, there is a growing interest in exploring the potential of MOFs/COFs in energy-related applications.

Electrochemical energy storage systems are vital for advancing the global adoption of sustainable energy. Batteries and SCs are currently the most promising and environmentally friendly electrochemical energy storage systems, and they have been extensively studied in recent decades.^{22,23} Different types of batteries, including lithium batteries,²⁴ zinc-air batteries,²⁵ and nickel-cobalt batteries,²⁶ have been broadly employed as energy storage systems for portable devices. However, alongside the growing trend towards global energy sustainability, the demand for efficient and reliable clean energy is increasing.²⁷ The high energy density of batteries affords them the advantage of long-

term discharge. Nevertheless, after long-term use, batteries inevitably suffer voltage and power loss, rendering them less suitable for meeting the demands of some high-power-density applications in the market. The advent of SCs offers a way to overcome these limitations, as they deliver higher power densities and can realize fast charging. However, the energy density of SCs is low, and there is still room for improvement.²⁸ Electrode materials play a crucial role in determining the efficiency of electrochemical energy storage systems. Materials with high porosity, enhanced chemical stability, and numerous electrochemical active sites are considered advantageous for enhanced battery and SC applications.

Motivated by the above considerations, this paper will focus on the synthesis, chemical structure, and functions of MOF/COF materials in battery and SC applications, which may contribute to the rapid development of related applications, as shown in Fig. 1. Synthesis methods are introduced in the second part, including solvothermal, microwave-assisted, mechanochemical, hydrothermal, and sonochemical methods. Subsequently, the chemical architecture of MOFs/COFs is examined, which serves as a guiding factor for their performance. Then, prominent topics concerning MOFs/COFs in batteries and the SCs are discussed. The operational mechanism of MOFs/COFs, with their characteristic high surface area,




Fig. 1 Schematic demonstrating the synthesis, chemical structure and applications of MOF/COF materials in batteries and SCs.^{29–37} Reproduced from ref. 29 with permission from Elsevier, copyright 2020. Reproduced from ref. 30 with permission from the American Chemical Society, copyright 2023. Reproduced from ref. 31 with permission from Elsevier, copyright 2024. Reproduced from ref. 32 with permission from the American Chemical Society, copyright 2022. Reproduced from ref. 33 with permission from Wiley, copyright 2018. Reproduced from ref. 34 and 36 with permission from Elsevier, copyright 2023. Reproduced from ref. 35 with permission from Elsevier, copyright 2022. Reproduced from ref. 37 with permission from MDPI, copyright 2022.



finely tunable porosity, and rich active sites, is also systematically analyzed. Finally, the principal challenges and future outlooks for MOF/COF materials are discussed.

2. Synthesis methods

MOFs and COFs constitute two novel categories of porous coordination polymers. MOFs are 3D materials composed of secondary building blocks formed from metal ions/clusters and organic ligands, while COFs are highly porous 2D or 3D organic solids composed of light elements (that is, H, B, C, N, and O). MOFs and COFs are highly conjugated scaffolds with modifiable electronic characteristics, elevated surface area, superior light and thermal stability, simple and comparatively low-cost preparation, and structural versatility. These attributes considerably extend their applicability.³⁸ Recently, various synthetic methods have been explored to develop MOFs and COFs with more potentially advantageous characteristics. Several conventional synthesis methods are reviewed in this section and have proven successful in fabricating COFs/MOFs.²¹

The architecture and properties of MOFs/COFs are defined by the synthesis approach and conditions, such as temperature, reaction time, pressure, pH value, and solvent. Widely used synthetic strategies include solvothermal synthesis,^{31,39} microwave-assisted synthesis,^{40,41} sonochemical synthesis,^{42,43} mechanochemical methods,^{44,45} and hydrothermal synthesis,^{46,47} each of which has its own advantages and disadvantages. Table 1 summarizes the advantages and disadvantages (in terms of yield, time, cost, and crystallinity) of these five synthesis methods. Solvothermal synthesis offers high yield and is suitable for preparing materials with controllable morphology and pore structure, but it is time-consuming and costly. The other four methods, by contrast, involve lower costs. Microwave-assisted syntheses require extremely short times and produce materials with high crystallinity and uniform size, making the approach ideal for the rapid preparation of nanocrystals and small-batch, high-crystallinity samples. Mechanochemical syntheses, in contrast, offer very high yields, approaching 100%, but typically result in lower crystallinity; it is a fast process and ideal for solvent-free green synthesis. Hydrothermal syntheses offer high yields and superior

crystallinity with uniform porosity, although it is time-consuming, making it appropriate for growing single crystals, large grains, and high-crystallinity materials. The approach is also suitable for large-scale and low-cost manufacturing. Ultrasonic syntheses require short reaction times and deliver the product with medium crystallinity and high yields; this approach is suitable for the preparation of room-temperature nanomaterials. Diverse targeted functionalities can be achieved through the selection of proper synthesis strategies and customized parameters.

2.1. Solvothermal synthesis

Solvothermal synthesis represents a systematic method for preparing MOFs and associated composites. This technology offers excellent production potential, operates at low temperatures, and requires minimal pressure.^{58,59} In the solvothermal method, it is very important to select the appropriate solvent for a reaction. Notably, solvents such as *N,N*-dimethylformamide (DMF),⁶⁰ dimethyl sulfoxide (DMSO),⁶¹ toluene, and other organic solvents are commonly employed for the preparation of MOFs and MOF-COMs. Moreover, in addition to stimulating the development of new materials, these organic solvents can also be employed to direct the assembly of structures. DMF possesses an elevated boiling point and good solubility, and is the preferred organic solvent for the synthesis of MOFs and MOFs-COMs. In 2018, a metalloporphyrinic MOF (PCN-624) featuring perfluorophenylene functionalization was successfully prepared using DMF at 120 °C, with a reaction duration of 72 h.⁶² In 2019, Wu *et al.* employed the solvothermal method to improve the solubility of PCN-221(Fe_x) in different concentrations of Fe.⁶³ This resulted in the application of a photocatalyst designated MAPbI₃@PCN-221(Fe_x) for CO₂ reduction. Ravipati *et al.* fabricated single-crystal Ni-MOF *via* a straightforward solvothermal method and precipitated it onto nickel foam (NF).³⁰ The prepared Ni-MOF/NF electrode exhibited a specific current capacity of 8.8 A g⁻¹ (compared with Hg/HgO) at an onset potential of 0.51 V. This was achieved because NF can transfer electrons quickly and has high conductivity on the surface between the electrode and the electrolyte. The porous architecture of the catalyst and the existence of a large number of metal charges generated by point defects enhance the

Table 1 Comparison of the advantages and disadvantages (yield, time, cost, and crystallinity) of the five synthetic methods of MOFs/COFs

	Productivity	Time	Cost	Degree of crystallinity
Solvothermal synthesis	—	1–5 minutes	More than 50 US dollars per kilogram	Single crystal of 0.2 millimeters ⁴⁸
Microwave-assisted synthesis	More than 10 g	16 h	Costs are controllable	— ⁴⁹
	44% and 90%	25 s–4 h	Low cost	High crystallinity and uniform size ⁵⁰
Mechanochemical synthesis	96.37%	15 min–1 h	Low cost	24.29% and uniform size ⁵¹
	~100%	30–45 min	Low cost	High crystallinity ⁵²
Hydrothermal synthesis	—	40 and 80 min	Low cost	Good crystallinity ⁵³
	96%	24 h	Low cost	High crystallinity ⁵⁴
Sonochemical synthesis	84–96%	6 h	Low cost	High crystallinity and uniform porosity ⁵⁵
	—	~20 min	Low cost	High crystallinity ⁵⁶
	60–98%	5 min–2 h	Low cost	High crystallinity ⁵⁷



electrocatalytic performance of the catalyst. Solvothermal synthesis of MOF and its composites with different length, width and morphology has also been confirmed in multiple studies, with polyhedral PCN-250-Fe₃ crystals (with a diameter of about 13 nm),³⁰ octahedral UiO-68 and UiO-68-TZDC (10–20 μm size range),⁶⁴ octahedral Co-MOFs and Ni-MOFs mixture (~200 nm size),⁶⁵ new 2D Ni-MOF nanosheets (~100 nm size),⁶⁶ MIL-53(Fe) (~50 nm size),⁶⁷ and the octahedral MIL-100(Fe) (100–200 nm size range)⁶⁴ being good examples.

Analogous techniques are also used to prepare COFs. Similar to the standard method for synthesizing inorganic zeolites in an autoclave, 3 to 7 days are required to prepare COF materials in a sealed heating container (100–130 °C) by the solvothermal method.⁶⁸ The procedure involves placing the COF precursors in a heat-resistant glass tube, along with the necessary amount of solvent and, optionally, a catalyst. After degassing and sealing, the mixture is maintained at the desired temperature for a pre-determined reaction time. Following this, the mixture is cooled to room temperature, and the product is collected by filtration, followed by drying at elevated temperatures (100–130 °C) to yield the COF powder. Solvothermal synthesis is the primary

approach for generating new COFs. However, it is confronted with difficulties in controlling the shape and morphology. For instance, non-uniform solvent addition may lead to accelerated polymerization and uncontrolled phase separation. In response to these challenges, Su *et al.* proposed a two-step solvent feeding process for solvothermal molding of an imine-linked COF monomer with layered porosity.⁶⁹ This study demonstrates that the two-step solvent feeding strategy can be effectively integrated with the traditional solvothermal synthesis to enhance the solution processability of COFs.

In addition, the solvothermal method is also of great significance in industrial applications. Xu *et al.* synthesized two highly ordered ionic COFs (TABD-COFs and TAPB-COFs) by the solvothermal method; these COFs have many advantages, such as large adsorption capacity, good selectivity, good stability and clear pore structure.³¹ This makes it an exemplary material for extracting rare earths. Experimental investigations have substantiated that TABD-COFs and TAPB-COFs have highly ordered multilayer stacked crystal structures (Fig. 2a). Furthermore, their morphology and crystallinity can be tailored by changing the reaction conditions and the structure of the




Fig. 2 (a) Schematic of the synthesis of TABD-COFs and TAPB-COFs. PXRD patterns of TABD-COFs (b) and TAPB-COFs (c) obtained after treatment with different mixed solvents for 72 h; reproduced from ref. 31 with permission from Elsevier, copyright 2024.



precursors. Unfortunately, TABD has an amorphous nature, as shown in the PXRD diagram in Fig. 2b, which makes the synthesis of TABD-COFs and TAPB-COFs difficult under the current synthetic parameters. Nevertheless, the successful synthesis of TAPB-COFs demonstrates that the structure of the building blocks plays an important role in the construction of TABD-COFs and TAPB-COFs. The crystallinity of the TAPB-COFs is corroborated by PXRD pattern analysis (Fig. 2c). Therefore, this study shows that the morphology and crystallinity can be modulated by adjusting the reaction conditions of the solvothermal method and by curating appropriate precursors, so as to engineer functional materials with excellent properties. Despite advantages such as mild reaction conditions and meticulous control over product dimensions, solvothermal synthesis is hindered by a series of challenges, including prolonged reaction durations, substantial consumption of organic solvents (such as DMF and DMSO) with inherent toxicity, susceptibility of product morphology and crystallinity to external factors, and significant environmental burdens. These drawbacks collectively exacerbate the temporal and environmental remediation costs and hinder large-scale production, and the inconsistent product quality can potentially compromise the reliability of practical applications in high-performance energy storage devices.

2.2. Microwave-assisted synthesis

Microwave heating has been employed in the domain of organic chemistry for several decades, particularly for the large-scale synthesis of COFs and MOFs. This method has been shown to significantly accelerate reaction kinetics and facilitate rapid crystal nucleation and growth.⁷⁰ As early as 2006, Ni *et al.* utilized microwave-assisted heating technology to synthesize MOFs.⁷¹ The synthesis of MOFs, a process that previously required hours or days, can now be completed within a time frame of 30 seconds to 2 minutes. Nowadays, this synthesis method has demonstrated wide applicability, ranging from 30% to exceeding 90%. Furthermore, this method renders the growth process independent of the nucleation of walls or dust particles, thus enabling the synthesis of novel MOFs. Notably, the particle dimensions can be controlled by altering the precursor concentration. Moreover, Guo and his colleagues synthesized MOFs derived from rice-like Zn_2GeO_4 nanowire bundles by a microwave-assisted hydrothermal method.⁷² In comparison with the traditional hydrothermal/solvothermal technique, the microwave-heating method ensures uniform temperature across the entire reaction system. This method facilitates the preparation of a highly pure Zn_2GeO_4 phase, which is conducive to the synthesis of small-sized Zn_2GeO_4 crystals. This method is thus deemed to have substantial advantages over traditional hydrothermal/solvothermal methods.

In addition to the enhanced crystallinity and higher SSA, microwave synthesis has potential advantages including narrow particle size distribution, phase selectivity and easy morphology control.²¹ Wei and colleagues demonstrated a microwave-assisted synthesis of TpPa-COF with excellent crystallinity,

larger surface area, and augmented CO_2 adsorption capacity compared with solvothermal synthesis.⁷³ Similarly, Alsudairy *et al.* synthesized a high-performance COF adsorbent to capture hazardous radioactive iodine, thereby overcoming the limitations of traditional solvothermal methods.⁴¹ As a feasible method to develop multicomponent COFs, microwave-assisted technology has the advantages of reduced reaction time and the ability to accurately customize the pore environment and adjust adsorption characteristics. It also has considerable prospects in environmental remediation and a range of niche applications. Microwave-assisted synthesis suffers from limitations including non-uniform heating at scale (causing product heterogeneity), stringent reactor material demands, precursor instability, and poor particle size control. These issues can be mitigated by designing multi-mode microwave systems for uniform power distribution, screening suitable precursors with the addition of stabilizers, and integrating template or surface modification strategies.

2.3. Mechanochemical synthesis

Whilst microwave and solvothermal reactions offer a series of MOF and COF materials with high crystallinity, stringent reaction conditions are requisite, including an inert atmosphere, a sealed reaction container, optimal temperature, and the use of a crystallization solvent. Consequently, there is a pressing need to explore more streamlined synthesis methods to facilitate rapid commercialization.

Mechanochemistry has great potential for the synthesis of high-value materials and is used in key reaction steps in many industries.⁷⁴ The salient characteristic of this method is that it can be carried out in batch mode, mainly by using milling technology, or in continuous mode, for example, using screw extrusion.⁷⁵ In addition, this method can be executed under solventless conditions, which is highly environmentally friendly.⁷⁶ In synthetic chemistry, mechanochemistry has an extensive heritage. To date, it has been used in multicomponent (ternary and above) reactions to fabricate cocrystals with pharmaceutical activity, as well as in inorganic solid-state chemistry, polymer science, organic synthesis and numerous other domains. For example, in 2022, Negin Khosroshahi *et al.* prepared novel MOF-808 and $NiFe_2O_4$ nano-composites with various mass ratios through mechanochemistry and employed them for visible-light photocatalytic degradation of Meropenem and reduction of $Cr(VI)$.⁷⁷ In addition, Zhu *et al.* compared mechanochemically prepared (MOFs-5 (M)) and solvothermally (MOFs-5 (S)) prepared samples to develop efficient hydrogen storage media. The results demonstrate that across the pressure range of 0–10 MPa, the crystal structure inside MOFs-5 (M) is more regular and the distribution is more uniform, and the average size is only one-tenth that of MOFs-5 (S).⁷⁸ These examples unequivocally underscore that the mechanochemical synthesis of MOFs has significant commercial potential. Importantly, mechanochemical methods have been widely used to synthesize various MOFs, including HKUST-1, ZIF-8, UIO-66 and MOFs-5, which have larger SSAs.



An analogous method is applied to the synthesis of COFs. Brown *et al.* demonstrated the liquid-assisted mechanochemical synthesis of COF adsorbents for efficient iodine capture.⁷⁹ At room temperature, six types of imine-linked COFs with diverse pore sizes and functions were produced within one hour. Significantly, a representative COF exhibits exceptional crystallinity and a surface area of 1387 m² g⁻¹ within 1 minute of ball milling. The empirical results demonstrate that the mechanochemically synthesized COFs have an excellent iodine adsorption capacity, which is comparable with or higher than that of the solvothermally synthesized COFs and most reported COF adsorbent materials. In a similar vein, Hamzehpoor *et al.* reported an expeditious room-temperature mechanochemical synthesis of 2D and 3D boron-oxygen COFs.⁴⁵ The COFs obtained in this study exhibit substantial porosity and crystallinity, with COFs-102 being the first example of a 3D COFs prepared by mechanochemistry; its surface area is approximately 2500 m² g⁻¹. In comparison with the solvothermal method, the mechanochemical method enabled a reduction in the solvent volume by approximately 20 times and the reaction time by about 100 times. Furthermore, the target COFs can be isolated in quantitative amounts without the need for additional treatment, aside from vacuum drying. Despite its environmentally benign and efficient nature, mechanochemical synthesis suffers from poor control of product structure, low crystallinity, pronounced equipment wear, and precursor degradation, although these can be mitigated through precise grinding control, liquid-assisted processing, and modular continuous manufacturing.

2.4. Hydrothermal synthesis

The hydrothermal synthesis strategy is regarded as exceptionally beneficial for the large-scale fabrication of MOFs/COFs owing to its simplicity, cost-effectiveness and environmental sustainability. The use of water instead of organic solvents as a reaction medium for the synthesis of MOFs/COFs is an appealing option. Liang *et al.* synthesized three new MOFs based on flexible tetradentate imidazole ligands L1 and L2 by the hydrothermal method.⁴⁷ The results demonstrate that the three complexes exhibit enhanced thermal stability, with complexes 1 and 2 displaying robust solid-state fluorescence emission properties, indicating their potential as luminescent materials. Additionally, complex 1 exhibits an adsorption characteristic for C₆₀ molecules. Similarly, Yang *et al.* used the hydrothermal method to synthesize two polyimide-linked COFs, namely HATN-PD-COFs and HATN-TAB-COFs.⁴⁶ The constant-current intermittent titration technique and the theoretical calculation of density overtone collectively demonstrate that the HATN-PD-COFs has excellent high-rate performance (195 mA h g⁻¹) at an ultrahigh current density of 10 000 mA g⁻¹, and maintains a capacity retention of approximately 91% after 7000 cycles at 10 000 mA g⁻¹. Moreover, Zhang *et al.* also used a hydrothermal synthesis to prepare COFs (ZVCOFs) with high crystallinity from pre-designed zwitterionic building blocks.⁸⁰ In this context, the addition of water not only substantially lowers the activation energy barrier for the reaction, thus enhancing

the reversibility of the reaction but also promotes the hydration and orderly layered arrangement of ZVCOF, which, in turn, facilitates the crystallization. These examples undoubtedly demonstrate the important role of hydrothermal methods for the fabrication of high-quality MOFs/COFs. Hydrothermal synthesis, though simple and environmentally friendly, is constrained by narrow precursor applicability, insufficient ligand solubility, product agglomeration, and compromised structural stability, which can be ameliorated by adding co-solvents/surfactants, introducing templates, and developing low-pressure processes.

2.5. Sonochemical synthesis

The sonochemical approach is widely considered to be a highly efficient and environmentally benign synthesis route due to the fact that it is both rapid and environmentally friendly. In a recent study, Kaur *et al.* synthesized a 2D Zn(II) and Cd(II)-based organic framework (MOFs) by the sonochemical method.⁸¹ The effects of different irradiation times and precursor concentrations on the reproducibility of the morphology were studied. The outcomes of this study demonstrate that the synthesis of nanoparticles and spherical nanoparticles is feasible at low precursor concentrations, with the ultrasonic irradiation time playing a pivotal role in modulating the size of the resulting particles. These two kinds of MOFs have been used to selectively detect phenolic structural analogues, and have demonstrated efficacy. Similarly, Maleki *et al.*⁸² prepared water-stable MOFs/polymer composite-Tarbiat Modares University-10/poly pyrrole by a sonochemical method, and used it as an adsorbent to remove methyl red from polluted water, which achieved a good removal effect.

In 2012, Yang *et al.* for the first time obtained COFs-1 and COFs-5 crystals with excellent structural properties through ultrasonic chemical methods within 1 to 2 hours.⁸³ This method offers a significantly reduced synthesis time (from 3 days to 1 hour), and yields smaller crystals (50–250 nm). Notably, their physical and chemical properties are comparable with, or even superior to, those of carbon nanotubes (CNTs) prepared by the vacuum solvothermal method. Similarly, the COF (TFPPy-AD) prepared by Wei *et al.* via the sonochemical method was characterized by the expediency of the approach, taking a mere hour to produce, and by the absence of any toxic reagents in its synthesis.⁴² The characterization results indicate that the TFPPy-AD possesses features such as substantial pore size, elevated crystallinity, and favorable thermal stability. Furthermore, COFs synthesized via ultrasonic chemistry demonstrate high adsorption capacity and selectivity, and rapid adsorption kinetics for flavonoids, indicating their potential for application in the separation and purification of flavonoids in natural medicines.

While the examples presented underscore the feasibility of synthesizing COFs and MOFs using green methodologies, it remains challenging to expand this approach to encompass a broader range of COFs and MOFs beyond the exemplars mentioned. To mitigate issues such as limited scalability, structural distortion, and narrow applicability, the use of high-



power sonication systems, precise parameter tuning, and strategic precursor modifications can be considered.

3. Chemical structures

3.1. Structure and properties of MOFs

MOFs are novel crystalline porous materials assembled from metal ions and organic ligands. Their intrinsic chemical structure fundamentally dictates their performance. These core chemical structural features include secondary building units (SBUs, composed of metal ions or metal clusters, which determines the redox activity, coordination environment and structural stability of MOFs), organic ligands (which coordinate with SBUs through carboxyl and other functional groups to determine the pore size, specific surface area and topological structure of MOFs), and the pore chemical environment of the pores (which can regulate the polarity and hydrophilicity of the pores through ligand functionalization, thereby providing a chemical basis for selective adsorption, catalysis, *etc.*).^{84,85} The versatility of these chemical structure designs and the fine-tuning of pore structures make MOFs stand out as porous materials. Researchers can design and adjust the physicochemical attributes of MOFs from various organic building units, which remain unattainable in pure organic or inorganic systems.³² Chen *et al.* synthesized a hollow sea-urchin-shaped Ni-based MOF (NiPSC). Owing to the multi-center Ni-oxo SBU clusters and the large *d*-spacing distance, NiPSC demonstrated high specific capacity and excellent rate performance. The battery employing NiPSC as the positive electrode exhibited an 82.8% capacitance retention rate after 3000 cycles and achieved a maximum energy density of 28.81 W h kg⁻¹ at a power of 425 W kg⁻¹. This study demonstrates that incorporating multiple oxidation active sites and modulating the lattice spacing to tailor its internal structure can effectively improve the electrochemical performance of a material.⁸⁶ Grafting various functional groups (-NH₂, -NO₂ and -Br) onto the carboxylic acid ligands of the sheet-like Ni-*p*-phenylene dicarboxylic acid type metal-organic framework nanosheets (Ni-BDC NAs) can be used to precisely engineer the microenvironment of Ni-BDC NAs while having minimal destructive effects on their structure and morphology. The overpotential of the functionalized materials is substantially mitigated, the long-term stability and structural stability are augmented, and the charge transfer resistance is attenuated. Among them, the performance of Ni-BDC-Br NAs is the optimal, with an overpotential of only 200 mV at a current density of 10 mA cm⁻².⁸⁷ In addition, compared with traditional porous carriers such as metal oxides, zeolites and carbon, MOFs have achieved the ability to expand the base surface without altering the base's topological structure through chemical modification. Therefore, MOFs can be compounded with other materials to construct excellent functional materials with improved overall performance.⁸⁸

When MOFs are used as a functional material, to fully leverage their structural advantages and make up for the deficiencies of a single structure, their morphology can be regulated through composite strategies. Both the composite-forming

method used and the spatial structure between the MOF and matrix material have a great impact on its performance.⁸⁹ This section will introduce three typical composite-forming strategies: (1) MOFs embedded in nanopores, (2) MOFs fixed on the surface, and (3) MOFs coated into shells. In the first type, MOFs are embedded in nanopores. The stability of MOFs grown in nanospaces differs significantly from that of simple random mixtures. Nanopores effectively prevent the aggregation of MOFs. At the same time, porous materials increase the stability of the MOFs.⁹⁰ For example, Farzaneh Mahmoudi *et al.* used the reflux method to confine the crystallization of MIL-68(Al) within the mesoporous channels of SBA-15, thereby forming the MIL-68(Al)@SBA-15 composite material. This structure embeds the MOF into the confined spaces of the mesoholes, significantly enhancing its water resistance. Compared with composite materials obtained through simple physical mixing, the MOFs that form through restricted crystallization can maintain their structural integrity even after repeated use, which indicates the protective and enhancing effect of the porous carriers on the stability of the MOFs.⁹¹

The second approach is to fix MOFs on the surface. For example, Du and his team designed a layered self-assembled MOF network to provide continuous ion transport and mechanical support for composite polymer electrolytes.⁹² This unique structure is achieved by constructing ordered MOF nanocrystals along the 1D polyimide fibers, providing continuous linear channels for lithium ions at the micron scale. The 1D MOF fibers are connected to form an integral 3D network for continuous transmission of Li⁺ in composite electrolytes. At the same time, the sub-nanopores and Lewis acid sites in the MOF nanocrystals can act as ion sieves to selectively restrict the movement of larger anions and promote the transport of Li⁺. In addition, the strong bonding between the MOFs and polyimide, coupled with the robustness of the polyimide skeleton, endows the MOF network with high mechanical strength and flexibility. Therefore, the synthesized composite electrolytes provide the high ionic conductivity and mechanical strength required.

The third kind of composite is MOFs coated into shells. The core-shell structures of MOFs and inorganic NPs (NP@MOF) are considered to be one of the easiest and most effective methods for achieving multifunctional applications of MOFs and inorganic NPs.⁹³ The existence of a MOF shell structure not only greatly limits the aggregation and migration of NP nuclei, but also maintains their chemical stability. In addition, the MOF shell (offering structural adaptability, ordered crystal pores and multiple ligand sites) and NP core (with unique magnetic, electrical, optical and catalytic properties) can be effectively integrated.⁹⁴ Owing to their unique structure and diverse nature, NP@MOF core shell nanomaterials have great potential in sensing⁹⁵ and catalysis applications.⁹⁶

3.2. Structure and properties of COFs

The synthesis and characterization of the COF materials have developed rapidly in the field of chemical science, owing to their distinctive structures and considerable potential in a range of application areas.^{97,98} A comprehensive understanding of these



materials necessitates a detailed study of their structures. COFs are crystalline porous polymers which are formed from bottom to top from molecular building blocks with predesigned geometric shapes, linked *via* covalent bonds. They provide positional control of the building blocks in 2D and 3D space, thereby enabling the synthesis of rigid porous structures with high regularity while allowing fine-tuning of the chemical and physical properties of the network.³³ Notably, the success of connecting 2D and 3D atomic systems to build extended frame structures shifts the chemistry of COFs from structure to method, highlighting the possibility of potential applications.⁹⁸ Therefore, an in-depth study of the structure–performance relationship in COFs yields exceptional functional performance.

COFs are composed of multifunctional monomers bonded to one another *via* covalent bonds. In addition, the 2D structures are stacked layer-by-layer through weak interactions (such as hydrogen bonds and π – π stacking interactions). The result of this process is the formation of 1D channels. In recent years, the number of COF structures with different linkage types has exceeded 500, including borates, imines, triazines, hydrazones,

azines and olefins.⁹⁹ The preparation of 2D COFs typically involves the utilization of planar building blocks (Fig. 3a),¹⁰⁰ while 3D COFs are formed *via* the condensation of 3D precursors (Fig. 3b).¹⁰¹

To date, the majority of COFs have been found to possess a 2D structure. The key challenges associated with the construction of 3D COFs lie in the scarce availability of 3D building units and notable crystallization issues.¹⁰² It is important to note that enhancing the clarity and diversification of COF structures offers significant advantages, particularly in the study of structure–performance correlations. This is of considerable significance for the exploration and development of new COFs for a range of functional applications.^{16,103–105}

The flexibility and customization of the COF structure provide significant opportunities for the construction of functional COFs for a range of specific applications.^{106–108} In general, there are two approaches to adjusting the structures of COFs. The first approach is the bottom-up method, which prioritizes the design of monomers and directly synthesizes the target COFs.^{109,110} Reacting hexaazatriphenylene (HATp), as a rigid




Fig. 3 (a) Schematic of the construction of 2D-MC-COF, reproduced from ref. 100 with permission from the Nature Portfolio, copyright 2016. (b) Schematic of the synthesis of 3D-hea-COF, reproduced from ref. 101 with permission from the American Chemical Society, copyright 2021.



conjugated monomer, with aromatic diamine/dialdehyde monomers, forms conjugated networks of COFs with an ordered channel. The planar conjugated structure of the HATp monomer is linked by strong covalent bonds, making the MOF framework highly chemically stable and structurally rigid, with a longitudinal contraction rate of the pore channel of less than 2%. The high negative charge of the HATp framework enhances the affinity for metal ions (Li^+ , Na^+ , K^+ , and Zn^{2+}), forming stable ligands with metal ions, and inhibits ion aggregation and shuttling, and the rigid conjugated structure provides a continuous electron transmission path. Moreover, the ordered pore channels shorten the ion migration distance, which can improve the electron conduction efficiency. As a lithium-ion electrode material, the specific capacity reaches 280 mA h g^{-1} at a current density of 0.1 A g^{-1} .¹¹¹ The alternative approach involves post-synthesis modification.¹¹² This approach involves the introduction of new functional groups into the original COFs, with the objective of adjusting their surface or pore environment while maintaining the integrity of the original COF structure. After synthesis and modification, the potential application scope of the COF materials expands significantly. For instance, TTBT-COF was functionalized with triazine rings to be used as a separator for lithium-sulfur batteries. The highly conjugated and electronegative characteristics of the triazine rings endow COFs with strong polarity and electron transport capability. Moreover, while the high electronegativity of the triazine rings exerts electrostatic repulsion, preventing the migration of polysulfide anions, the conjugated structure enhances electron conduction and accelerates the kinetics of polysulfide redox reactions. The initial capacity at 1C current reaches 1022 mA h g^{-1} , and the average capacity decay rate per cycle is 0.057%.¹¹³

In a similar manner, the modification and practical application of COFs are influenced by their stability. In general, COFs exhibit favorable thermal stability and robust covalent bonds, with the capacity to preserve structural integrity at temperatures ranging from $250 \text{ }^\circ\text{C}$ to $450 \text{ }^\circ\text{C}$ under an inert gas.⁹⁹ Despite the challenges related to the chemical stability of COFs, significant advancements have been made in developing methodologies aimed at enhancing their structural stability.^{114,115} It is important to note that COFs exhibit highly ordered, versatile and permanent porosity, which renders them highly promising for a variety of applications.¹¹⁶ Furthermore, in addition to the pore size, the pore environment of the COFs can be adjusted with a high degree of accuracy.

Consequently, the structure of COFs plays an important role in their application in many fields. The advantages of such structural analyses include the following: (1) defining the structural characteristics of COFs can provide a theoretical basis for synthesizing COFs with specific functions. (2) Understanding the relationship between the structure and properties of COFs is helpful for predicting the properties of materials and for making targeted modifications. (3) In energy storage devices, such as batteries and SCs, exploring the COF structure can help guide the design of electrode materials with high ionic conductivity, good stability and high specific capacity. In addition, exploring their structure is helpful for discovering and

exploring new functions and application scenarios of COFs in the field of energy storage.

4. Application of energy storage batteries

Confronted with the dual challenges of the energy crisis and environmental protection, exploring novel solutions has become imperative. The growing prevalence of electric vehicles has led to a shift in the automotive landscape, with traditional fossil fuel vehicles gradually being replaced by their electric counterparts.¹¹⁷ In addition, batteries are widely explored as reliable electrochemical energy storage devices. However, current battery designs have defects such as low power density and short service life.^{118,119} Crystalline porous materials have attracted great interest in the field of energy storage, especially in the battery field, because orderly porous frameworks can provide fast ion transmission and storage paths without large volume changes.²⁹ Consequently, MOFs and COFs stand out from the wide range of functional materials, and they show great potential for battery applications.

4.1. Application of MOFs in energy storage batteries

MOFs are hybrid materials composed of different metal nodes and organic linkers, featuring ultra-high porosity, large SSA, and easy functionalization. They can provide superior electronic transfer and rapid mass transfer in various industrial applications, and have excellent electrochemical properties.¹²⁰ These characteristics make them promising candidates for developing lithium-based batteries (such as lithium-ion batteries, lithium sulfur (Li-S) batteries, and lithium oxygen batteries (LOB)) with excellent electrochemical properties.¹²¹


4.1.1 Lithium-ion batteries. The ultra-high porosity, multi-functionality, structural diversity and tunable chemical composition of MOFs offer great potential for their deployment as advanced electrode materials in rechargeable batteries.¹²² Lithium-ion batteries exhibit excellent electrical performance and safety profiles, and they have good cycle stability; thus, they are one of the most promising energy storage components in power equipment^{123,124} and can make a significant contribution to achieving “carbon neutrality”.¹²⁵

Lithium-ion batteries consist of an anode, a cathode, an electrolyte, a diaphragm and a shell.¹²⁶ In general, the working principle of lithium-ion batteries is that the cathode and anode exchange lithium ions in the electrolyte to store or release electrical energy. The working efficiency and capacity of a battery mainly depend on the cathode, anode and electrolyte.¹²⁷ The separator and electrolyte ensure the normal operation of the battery, while the positive and negative electrode materials determine the battery capacity.¹²⁸ The electrode materials serve as the primary factors governing the electrochemical performance of lithium-ion batteries. The inherent ultra-high porosity and large SSA of MOFs are conducive to the penetration of electrolytes and can effectively withstand the volume expansion that occurs during the storage of lithium ions. In addition, their designable components enable the




incorporation of electroactive sites, laying the foundation for the development of candidate electrode materials suitable for lithium-ion batteries.¹²⁹ Lithium-ion batteries achieve energy storage and release through the reversible insertion and extraction of lithium ions between the positive and negative electrodes. Taking the typical positive electrode material LiCoO₂ and the negative electrode material graphite as examples, the basic electrochemical reaction can be expressed as follows:


Cathode reaction:



and anode reaction:



The formation of the solid electrolyte interphase (SEI) on the anode during initial cycles can be expressed as:



The high porosity and controllable structure of MOFs can optimize the above electrochemical processes in multiple aspects: promoting the kinetics of lithium ion transport, adapting to the structural deformation during the cycling process, and potentially enhancing the intrinsic activity of the electrode materials through chemical modification. Therefore, MOFs and their derivatives have become important candidate systems for electrode materials in lithium-ion batteries. Table 2 shows the performance of MOF hybrid electrode materials in lithium-ion batteries developed in recent years.

At present, the negative electrode material used in most lithium-ion batteries on the market is graphite. However, the theoretical gravimetric capacity of conventional graphite anodes is 372 mA h g⁻¹.¹⁴³ This value cannot meet the power density and reliability requirements required for large-scale applications. Therefore, developing new types of batteries with high capacity, low charging potential and low production cost is an important and urgent task.¹²⁸ Owing to the ultra-high SSA of the catcher contacts, abundant lithium-ion storage active

sites, and tunable pores that enable lithium-ion migration, MOFs are considered one of the most promising candidates to replace graphite anodes in current lithium-ion batteries.¹⁴⁴ In experiments, the polycrystalline MOF-177 has been employed as an anode material for lithium-ion batteries, providing a high initial irreversible capacity of 400 mA h g⁻¹, which is a favorable performance. However, after only two cycles, the capacity attenuates rapidly to 105 mA h g⁻¹.¹⁴⁵

Long-life battery materials and battery design have always been the goals of research. However, due to their electrochemical properties, lithium-ion batteries are affected by the battery design (battery structure, electrode engineering, *etc.*), chemical composition (active materials, electrolytes, additives, *etc.*), mode of use, and operating conditions, and will experience irreversible ageing.¹⁴⁶ Yan *et al.* obtained Si@calbolt-ZIF-62-glass composites (SiZGC) by *in situ* growth of a MOF on the Si surface, followed by melting and quenching the MOF to a glassy state. The preparation is shown in Fig. 4f. Studies show that the disordered network structure of ZIF glass can provide additional channels for the diffusion and storage of Li⁺, thereby effectively enhancing the electrochemical performance of the anode in lithium-ion batteries. Additionally, the ZIF glass phase can mitigate volume variations and inhibit the agglomeration of silicon nanoparticles during the lithiation/delithiation process. After 500 cycles of the 10SiZGC-based anode, the specific capacity at a current density of 1 A g⁻¹ is 650 mA h g⁻¹.¹⁴⁴ Furthermore, the metal-organic framework (MOFs-199, namely, Cu₃(BTC)₂) is deposited on the surface of graphene oxide (GO) in a layer-by-layer (LBL) coating approach to fabricate the Cu₃(BTC)₂@GO composite anode material. Owing to the porous nature of the MOFs, at a current density of 100 mA g⁻¹, the composite delivers an initial charge/discharge capacity that reaches 1200/1420 mA h g⁻¹, with a coulombic efficiency of 85%. After 100 cycles, the reversible discharge capacity is 1296 mA h g⁻¹, the coulombic efficiency is 98.9%, and the capacity retention rate is 91%. When the current density increases from 100 mA g⁻¹ to 2000 mA g⁻¹, its specific capacity decreases from 1352 mA h g⁻¹ to 836 mA g⁻¹. When it

Table 2 Electrochemical properties of MOFs and their derivatives as the electrode materials for lithium-ion batteries

Materials	Current density (mA g ⁻¹)	Specific capacity (mA h g ⁻¹)	Cycles
MOF-SnO ₂ NP	—	1050.8	100 (ref. 130)
Si/CoMo@NCP	500	1013	100 (ref. 131)
Co-MOF 2	100	732	200 (ref. 132)
Fe ₂ O ₃ -Co ₃ O ₄ /NPC	2000	406	1000 (ref. 133)
PbSe/SC	100	717	100 (ref. 134)
Fe-HHTP	355	1142	220 (ref. 135)
ZIF-67@rGO	2000	1002	2500 (ref. 136)
NiMnCo-MOF	15	685	50 (ref. 137)
Co-ZnO/C and Co-Co ₃ O ₄ /C	37.2	898 and 784	100 (ref. 138)
FNO@NCNFs	1000	748.5	900 (ref. 139)
Fe-Tp	1000	743	500 (ref. 140)
Cu-IM/Co-MOF 250 and Cu-IM/Co-MOF	50	834 and 54.3	75 (ref. 141)
Co-CAT	200	404	100 (ref. 142)






Fig. 4 (a) Schematic of the synthesis of MOF-808/CNT interlayers, reproduced from ref. 148 with permission from Elsevier, copyright 2022. (b) Oxidation and restoration reactions occurring in Li-S batteries. (c) Voltage distribution at the carbon/sulfur (C/S) cathode. (d) The theoretical discharge capacity of each stage in a battery, reproduced from ref. 149 with permission from KeAi Communications Co., Ltd, copyright 2023. (e) Ce-ZrOF@CC function diagram of the middle layer, reproduced from ref. 150 with permission from Elsevier, copyright 2022. (f) Synthesis of SiZGC materials and the protective effect of the ZIF glass matrix, reproduced from ref. 144 with permission from Elsevier, copyright 2022.

is restored to 100 mA g^{-1} , the capacity recovery rate reaches 94%.¹⁴⁷

Although MOFs and their derivatives possess many advantages, they face a variety of critical challenges as electrode materials, which hinder their practical implementation. Low driven rate, poor cycling stability, and electrochemical instability constitute the primary obstacles for the practical application of MOF electrodes.¹⁵¹

4.1.2 Lithium-sulfur batteries. In comparison with lithium-ion batteries, Li-S batteries exhibit high theoretical rate capacity (1675 mA h g^{-1}) and theoretical energy density (2600 W h kg^{-1}), with the latter being nearly five times that of traditional lithium-ion batteries.^{152–154} In addition, as the cathode material for Li-S batteries, sulfur (S) is naturally abundant, low in cost, and environmentally friendly, laying a solid foundation for its large-scale application.¹⁵⁵ However, Li-

S batteries still suffer from critical unresolved challenges, such as low active-material utilization, poor cycling stability, the polysulfide shuttle effect, and sluggish reaction kinetics.²⁶ In recent years, various strategies to improve the working performance of Li-S batteries have been proposed in view of the excellent performance of MOFs, including developing new cathode bodies and electrolytes, modifying separators and anodes, and inserting intermediate layers.^{156–160} For instance, when sulfur is embedded in the pores of carbonized ZIF-8 as the cathode host, the ultrahigh micropore density inhibits the dissolution and shuttling of polysulfides. After 100 cycles, a reversible capacity of around 490 mA h g^{-1} can be achieved based on sulfur mass, and it also exhibits stable cycling performance and high coulombic efficiency.¹⁶¹ Of these four approaches, inserting an intermediate MOF-based layer





between the cathode and the separator has been proven to be a simple and effective method.^{34,162,163}

Zirconium-based MOFs (Zr-MOFs), such as MOFs-808, exhibit several key advantages, such as excellent hydrophilicity, high chemical stability and relatively large pore sizes, which are suitable for use as membrane-based interlayer materials.¹⁶⁴ Wang *et al.* successfully fabricated a continuous Zr-based MOFs-808 film (MOFs-808/CNT) *via* a CNT thin-film substrate.¹⁴⁸ The design of the MOFs-808/CNT interlayer is shown in Fig. 4a. A dense MOFs-808 film is prepared on a CNT film *via* an *in situ* hydrothermal method and employed as an ion-selective interlayer to inhibit the shuttle effect in Li-S batteries, effectively blocking the polysulfides while enabling rapid transport of lithium ions, providing long-lasting cycle stability for Li-S batteries. In addition, the excellent electrical conductivity of CNT films can remedy the poor electrical conductivity of MOFs-808 films, giving a rate capacity of 707.3 mA h g⁻¹ at 5 °C. Zhou *et al.* impregnated Zr-based MOFs-808 films with cerium (Ce) salts and carbonized them to fabricate ZrOF/carbon composites based on carbon fiber cloth (Ce-ZrOF@CC).¹⁵⁰ Synergistic effects between the materials reduce the cyclic decay rate of the Li-S batteries at 1C to only 0.025% and deliver a rate capacity of 744 mA h g⁻¹ at 5C. A working schematic of the Ce-ZrOF@CC intermediate layer is shown in Fig. 4e. When employed as the intermediate layer of Li-S batteries, Ce-ZrOF@CC provides sufficient active sites for effective capture of polysulfides and rapid transformation of LiPSs, which is expected to inhibit the shuttle effect and enhance the electrochemical performance of the battery.

In addition, MOFs are highly important catalysts for energy storage and energy conversion systems.¹⁶⁵ Research finds that introducing electrocatalysts into the matrix or interlayer materials can promote the slow conversion process, thereby enhancing the utilization rate of sulfur and battery performance.¹⁵⁰ In the chemistry of Li-S batteries, the redox reaction involves multi-step and multi-phase transformations of sulfur during discharge/charging (Fig. 4b). In the sulfur reduction reaction, S₈ is reduced stepwise to long-chain LiPSs at a voltage higher than 2.1 V. This process provides 25% of the theoretical capacity (418 mA h g⁻¹). In this process, the adsorption, activation and desorption of LiPS are the key factors governing the reaction kinetics. In the second stage, the conversion from Li₂S₄ to Li₂S₂ contributes an additional 25% of the theoretical capacity. Finally, the solid–solid conversion from Li₂S₂ to Li₂S is a rate-determining step that delivers the remaining 50% theoretical capacity (839 mA h g⁻¹), as shown in Fig. 4c and d. This reaction step is instructive for sulfur reduction in Li-S batteries.¹⁴⁹ Currently, a variety of dual-metal MOF catalysts are employed in battery systems; for example, NiCu-MOF catalysts¹⁶⁶ and NiFe-MOF catalysts.¹⁶⁷

4.1.3 Lithium–air batteries. In the pursuit of higher energy density, LOBs, also known as lithium air batteries, have garnered considerable attention due to their higher theoretical energy density (3500 W h kg⁻¹).¹⁶⁸ Owing to their excellent physicochemical and electrochemical properties, MOFs have promising prospects for their application in LOBs.¹⁶⁹ Based on the electrolyte type, they can be divided into four groups: proton

type, aprotic type, mixed type and all-solid type.¹⁷⁰ When these batteries are discharged, the reversible lithium dissolution/precipitation reaction occurs at the anode. The oxygen reduction/oxidation of the reaction products occurs on the positive pole.^{171,172} MOF-derived materials have large pore volumes, good pore structures and well-distributed catalysts, which are conducive to the regulation of quality transportation, oxygen-related redox reactions and the deposition of reaction products (such as Li₂O₂).^{121,129} The overall reaction of the battery is shown in reactions (4) and (5):



There remain key challenges for the development of LOBs, such as the design and synthesis of high-efficiency catalysts for Li₂O₂ decomposition, the selection of electrolytes, and the passivation of porous cathodes induced by reaction products.^{171,173} Using MOFs as the precursor and mSiO₂ as the template, cobalt-encapsulated catalysts (Co, N-CNF) confined within porous nitrogen-doped carbon nano-frameworks have been prepared. These catalysts retain their intrinsic structural features after MOF pyrolysis, inhibit the agglomeration of metal particles, and fully expose the catalytically active sites, thus enabling efficient catalytic decomposition of Li₂O₂. They effectively enhance the specific capacity of the battery (5288 mA h g⁻¹) and the cycling stability (no obvious voltage decay after 500 cycles).¹⁷⁴

Before LOBs can meet the requirements of actual applications, there are still numerous fundamental and technical challenges to be addressed, such as round-trip efficiency, energy density, and cycling durability. For the MOF materials, firstly, the deposition of reaction products and electrolyte decomposition byproducts may lead to blockage of the pores and active sites of the MOFs. Secondly, the active intermediates in the electrochemical process may induce structural damage to the MOFs. Finally, when used as a membrane, the functional active sites may be gradually occupied, leading to a decline in adsorption performance and thus a decrease in the electrochemical performance. In MOF-derived materials, the carbon component may be decomposed in the presence of Li₂O₂, resulting in poor cycling stability. Reducing surface defects and non-essential functional groups in the carbon matrix to enhance the structural stability may effectively mitigate the above issues and provide valuable insights for future research efforts. Gaining a better understanding of the basic chemical properties of LOB systems is of great significance for guiding the design and manufacture of effective MOF-derived materials.¹²¹

4.2. Application of COFs in lithium–sulfur batteries

COFs are a new class of porous organic crystal materials that are synthesized from molecular building blocks containing light elements (such as C, H, O, N, or B atoms) *via* reticular chemistry. They achieve ordered covalent connectivity at the molecular level *via* periodic covalent bonding that can be further



extended to form a porous framework structure in 2D or 3D space.^{175,176} Their unique properties, such as high porosity, diverse structural configurations, facile surface modifiability, large SSA, and good physical, chemical and thermal stability, have driven the vigorous development of COFs in the field of Li-S batteries.^{175,177} The excellent structural controllability of COFs affords critical support for tuning their physicochemical properties. Research shows that by choosing the appropriate connection motifs and building blocks, the backbone structures, pore sizes and pore geometry of COFs can be precisely designed.¹⁷⁸ As seen in Fig. 5a and b, a variety of methods have been developed using distinct building units that allow the fabrication of COFs with different topological structures. By the rational and independent customization of the pore structure and functional groups of COFs, well-defined active sites can be introduced on the large, permanent and accessible surfaces to

promote or catalyze the progress of target electrochemical reactions, providing a foundation for the rapid development of COFs in the field of electrode materials.¹⁷⁵

Traditional Li-S batteries have some inherent drawbacks that need to be addressed, including the poor conductivity of sulfur and Li_2S intermediates, sulfur volume expansion, the shuttle effect of the dissolution of polysulfide lithium intermediates on the electrolyte, and the electrochemical response issues during the slow reaction process of the electrolyte.¹⁸⁰⁻¹⁸⁵ As a typical type of porous material, COFs have been shown to effectively alleviate the performance bottlenecks of the aforementioned Li-S batteries.¹⁷⁸ Theoretically, COFs containing multiple flexible units exhibit better adaptability to the dynamic behavior of active sulfur in batteries. Compared with Li-S batteries based on traditional conductive materials, the permanent 1D channels of 2D COFs not only provide diffusion





Fig. 5 Basic topology of the COF design and constructed COFs: (a) 2D COFs and (b) 3D COFs, reproduced from ref. 175 with permission from Elsevier, copyright 2021. (c) Schematic diagram of the S/Co/Ti-NC@TpPa composite materials, reproduced from ref. 179 with permission from Elsevier, copyright 2023.


channels for the electrolyte and Li^+ , but also selectively block the shuttle effect of polysulfides.³⁵

To understand the mechanism by which COFs mitigate this shuttle effect, it is essential to consider the multi-step conversion reactions of sulfur in Li-S batteries. The discharge process involves the reduction of solid S_8 to soluble long-chain lithium polysulfides (Li_2S_n , where $4 \leq n \leq 8$), and ultimately to insoluble $\text{Li}_2\text{S}_2/\text{Li}_2\text{S}$. The key steps related to the shuttle effect can be summarized as follows:

Overall reaction:



and Shuttle effect:



In one study, Ge *et al.* employed large, flexible monomers (TPT-CHO) as nodes to synthesize two flexible COFs containing triazine ring organic macromolecules (semi-rigid/flexible COFs-TPT(OH) and flexible COFs-TPT) as the cathode host materials for Li-S batteries. The strong coordination between -OH and O atoms and Li^+ significantly inhibits the shuttle effect of polysulfides, and the highly efficient catalytic performance of COFs-TPT(OH)@S ensures no residual polysulfides remain at the end of discharge. Electrochemical tests show that COFs-TPT(OH)@S has the highest lithium-ion diffusion coefficient ($7.77 \times 10^{-7} \text{ cm}^2 \text{ s}^{-1}$) and the smallest charge transfer impedance (6.7Ω), and the reversible capacity after 1000 cycles at 0.5C is 732 mA h g^{-1} , with a per-cycle decay rate of only 0.045%.¹⁸⁰ In addition, the structural diversity of the COF building units provides abundant sites for the introduction of polar functional groups, thus enhancing the suppression of the shuttle effect.³⁵ For instance, Zhang *et al.* introduced F functional groups into COFs to fabricate the 4F-COFs/PP (polypropylene) composite separator. Negatively charged channels induced by the high electronegativity of F can effectively suppress the shuttling of polysulfide anions by generating electrostatic repulsion. Meanwhile, the ordered porous structure and the superior electrolyte wettability boost the lithium-ion migration efficiency, allowing the durability to exceed 2000 h at 1 mA cm^{-2} .¹⁸⁶

However, the application of COFs in Li-S batteries is hindered by their intrinsically low electrical conductivity and the scarcity of active sites capable of catalyzing polysulfide redox reactions.¹⁸⁷ Lin *et al.* proposed incorporating transition-metal-based porous carbon (PC) composites derived from MOFs into COFs. This advanced design strategy for the multifunctional core-shell sulfur cathode has an important impact on improving the polysulfide shuttle problem in sulfur batteries. This approach leverages the carbon/metal core inside the composite for sulfur sequestration and functions as a dedicated catalyst to accelerate the redox kinetics of sulfur species. In experimental tests, the S/Co/TiNC@TpPa battery (Fig. 5c) constructed from the core-shell structured Co/Ti-NC@TpPA composite shows excellent performance. In the experiments, the initial rate of the battery is as high as 1135 mA h g^{-1} at 0.2C, and after 500 cycles at 1C, the capacity decay rate per cycle is

0.05%. With a high sulfur load of 4.46 mg cm^{-2} , the area capacity of the battery reaches 3.6 mA h cm^{-2} .¹⁷⁹

In energy storage battery applications, the porous structures and functionalized designs of MOFs and COFs are used to adapt to specific energy storage mechanisms. Both share the common characteristics of high specific surface area and controllable channels, providing ion adsorption/intrusion sites, shortening the ion transmission path, and allowing the energy storage performance to be optimized through modification of the active sites. However, MOFs achieve energy storage through redox reactions of metal ions/clusters or the double-layer energy storage of derived materials, with the metal active sites determining the redox capacity. COFs rely on ion adsorption and transmission as well as redox reactions of functional groups, and the regularity of pore channel determines the ion migration rate. Additionally, in terms of material performance requirements, it is necessary to ensure that the electronic/ion conductivity is suitable for charge transmission, chemical/electrochemical/thermal stability is sufficient to ensure cycle life, and the pore size/specific surface area/pore volume is adapted to the common rules for ion migration and storage.

5. Applications of supercapacitors


As the global economy grows, the dwindling supplies of non-renewable fossil fuels such as petrol and diesel, as well as the environmental concerns associated with their use, continue to spur researchers to explore new energy storage systems.^{188,189} The growing need for reliable energy has led to a fervent search for cutting-edge materials that are designed to further change the way energy is stored.¹⁹⁰ In the past, humans predominantly relied on non-renewable resources (fossil energy) to generate the secondary energy (electricity) necessary for modern societal development.¹⁹¹ Hence, there is a pressing need to develop electrical energy storage systems with higher energy and power densities in order to meet the growing energy demand and mitigate greenhouse gas emissions.¹⁹² With the continuous advancement of modern science and technology, renewable energy sources such as wind power, nuclear power, and hydropower are gradually replacing fossil fuels for electricity generation.¹⁹³ Electricity generation is becoming increasingly environmentally friendly, with a diminished environmental impact. The transition toward electricity replacing fossil fuels is becoming an inevitable trend of the era.¹⁹⁴ Therefore, there is an increasingly urgent demand for eco-friendly and high-power energy storage systems.¹⁹⁵ SCs have garnered considerable attention from researchers due to their fast charging and discharging rates, high power density, and excellent rate performance.¹⁹⁶

SCs, also known as electrochemical capacitors, are a new type of energy storage device that exhibits characteristics between those of traditional capacitors and batteries, with unique properties distinct from traditional chemical power supplies.^{197,198} These advantages, including high power density, long cycle life and low maintenance costs, enable SCs to exhibit outstanding performance among numerous energy storage systems.¹⁹⁹⁻²⁰¹ They have a wide range of applications, including




smart electronic devices, portable electronic devices, automotive systems, energy grids and defense sectors.²⁰² There are three primary types of SCs: hybrid SCs, pseudocapacitors, and electric double-layer capacitors (EDLCs).^{203,204} The energy storage mechanisms of these three types of SCs are distinct, and can be represented by the following typical electrode reactions.

Electric double-layer capacitors (EDLCs), typically employing materials such as activated carbon in alkaline electrolytes (such as KOH), store charge *via* electrostatic adsorption/desorption of ions at the electrode–electrolyte interface without faradaic charge transfer.



and



Pseudocapacitors (such as RuO₂ and MnO₂):

Pseudocapacitors, exemplified by metal oxides like RuO₂ and MnO₂, rely on fast and reversible surface or near-surface faradaic redox reactions.


For RuO₂ in acidic electrolyte:



and for MnO₂ in neutral/alkaline electrolyte:



Hybrid SCs combine capacitive and battery-like charge storage mechanisms, often integrating a battery-type electrode with a capacitive electrode. A representative example is the lithium-ion capacitor (LIC), which couples a pre-lithiated graphite anode with an activated carbon cathode.



MOFs and COFs can be engineered to enhance these mechanisms by providing a high surface area for EDLC, introducing redox-active sites for pseudocapacitance, or serving as precursors for composite materials in hybrid systems.

In EDLCs, charge storage occurs through the electrostatic adsorption/desorption process at the electrode–electrolyte interface (EEI). The electrode surface undergoes a fast and reversible non-faradaic electrostatic adsorption process, resulting in high power density and low energy density.²⁰⁵ Hybrid SCs store charge through rapid and reversible faradaic reactions occurring at the electrode surface, which enables them to maintain high power density while also achieving higher energy density than EDLCs.²⁰⁶ Hybrid SCs are devices in which one electrode is an EDLC electrode, and the other is a battery electrode. Each of these electrodes utilizes different charge storage mechanisms: EDLC-type electrostatic adsorption and faradaic redox reactions. Pseudocapacitors exhibit excellent electrochemical performance, including high energy density,

high energy, and outstanding cycling stability.²⁰⁷ Moreover, due to their dependence on rapid redox reactions occurring at or near the electrode surface region, pseudocapacitors typically possess higher charge storage capacity compared with EDLCs.²⁰⁸ With their excellent cycle life and power density, these three types of SCs play an important role in the modern market's ongoing quest for efficient, reliable and sustainable energy storage.²⁰⁹ However, due to the limitations of energy density, the further application of SCs has been significantly limited. The performance of SCs is closely related to their electrode materials. Therefore, it is of great significance to explore and develop new electrode materials to improve their electrochemical properties.¹⁹² At present, electrode materials used in SCs are generally divided into three categories, namely, transition metal oxides, carbon materials,^{210–214} and conductive polymers (CPs).^{215–217}

In recent years, there has been a surge of interest in the fields of MOFs and COFs among researchers, with these novel materials emerging as pivotal components in enhancing SCs. This section aims to provide a comprehensive review of recent advancements in research and development of MOFs and COFs, and their derivatives, in the context of their application as electrode materials for SCs.

5.1. Applications of MOFs, MOF derivatives, and composite materials in SCs

MOFs are crystalline materials with unique properties, featuring a vast surface area conducive to molecular diffusion, precisely tunable and controllable porosity, and abundant active sites.²¹⁸ Derivatives of these materials retain the distinctive ordered structures and networked voids of MOFs, exhibiting high porosity, large specific surface area (SSA), and high energy storage capacity.^{219,220} MOFs and their derivatives offer novel approaches to overcoming the performance limitations of SC electrode materials.

5.1.1 Transition metal MOFs. MOFs containing transition metal ions, such as Ni, Co, V, Fe, and Zn, have emerged as key electrode materials for enhancing SC performance due to their tunable porous structures, abundant redox active sites, and synergistic effects among the components. K. Xia *et al.*²²¹ tuned the molar ratio of metal salt to ligand ($R_m : L$) to synthesize 2D coordination-unsaturated Ni-MOF hierarchical nanosheets. The internal electric field reduced the bandgap, thus enhancing conductivity. At 1 A g⁻¹, the specific capacity reached 746C g⁻¹, with a capacity retention of 89.7% after 10 000 cycles. A. H. Anwer *et al.*²²² used an ultrasonic-assisted hydrothermal method to synthesize the bimetallic, bi-ligand Co–V-MOF, exhibiting a C_g of 1711.1 F g⁻¹ at 1 A g⁻¹ and a retention rate of 92.21% after 10 000 cycles.

Combining transition metal MOFs with other materials or derivatizing them into metal selenides and oxides further enhances performance. A ternary Zn–Ni–Co–Se alloy combined with Ni–Co-LDH etched from MOFs was used to form a hierarchical structure on rGO-Ni foam, exhibiting a specific capacity of 387.2 mA h g⁻¹ at 1 A g⁻¹ and an assembled HSC with an energy density of 80.3 W h kg⁻¹;²²³ MOF-derived ZnCo₂O₄/ZnO



flower-like structures achieve a specific capacity of 803 F g^{-1} at 1 A g^{-1} , with 91.04% capacity retention after 10 000 HSCs cycles;²²⁴ MOF-derived $\text{CoFe}_2\text{O}_4@\text{NiMn}_2\text{O}_4$ composite electrodes reach an energy density of 90.3 W h kg^{-1} in HSCs;²²⁵ MOF-derived $\text{CoSe}_2\text{-Ni}_3\text{Se}_4$ nanosheets and MXene form a heterostructure *via in situ* growth on the substrate. The synergistic effect of the high conductivity of MXene and the active sites of $\text{CoSe}_2\text{-Ni}_3\text{Se}_4$ reduces the charge transfer resistance, significantly enhancing the electrochemical performance of the hybrid SCs.²²⁶ Furthermore, Ni-doped V-MOF nanosheet arrays grown *in situ* on Ni foam exhibit a specific capacity of 516.5 C g^{-1} at 1 A g^{-1} , retaining 85.6% capacity after 12 000 cycles.²²⁷ Thus, transition metal MOFs offer an effective pathway for high-performance SCs through structural and compositional tuning. Table 3 summarizes the key performance parameters of the aforementioned transition metal MOF composites for SC electrodes, enabling an intuitive comparison of their overall performance.

5.1.2 Bimetallic MOFs and their derivatives. In the study of transition metal MOFs, bimetallic systems hold promise for further enhancing the performance of MOF-based energy storage devices. Xu *et al.* combined the layered structure of MOFs, characterized by fewer electrolyte ion diffusion pathways and shorter electron transfer channels, with the unique properties of carbon cloth (CC) to fabricate a SC cathode material. This material is composed of a carbon cloth (CC) substrate onto which bilayer CoNi-MOF nanosheets and nanotubes are assembled. The CC/CoNi-MOF nanosheets/nanotubes exhibit unique nanostructures and morphologies, yielding electrode materials with high specific surface area, high capacity and outstanding rate performance. Fig. 6a illustrates the synthesis of hierarchical CC/CoNi-MOF, featuring ultrathin nanosheets and nanotubes, using $\text{Co}(\text{OH})_2$ as a template. This hierarchical nanostructure significantly increases the contact surface area between the electrode material and the electrolyte, which is crucial for enhancing the electrochemical performance of the electrode. Experiments reveal that the hybrid SCs based on CC/

CoNi-MOF and reduced graphene/CNTs exhibit a large areal capacitance of 846 mF cm^{-2} at 1 mA cm^{-2} (equivalent to 177.7 F g^{-1} at 0.21 g A g^{-1}). This provides insights for the synthesis of other high-performance energy storage electrodes based on MOFs.²³³ Amidst tensions arising from energy crises and environmental concerns, researchers continue to explore novel materials to further enhance the performance of energy storage systems.²³⁴

J. Khan *et al.* published research in 2024 on synthesizing bimetallic MOFs using Ni and Co as transition metals. The researchers employed a hydrothermal synthesis method to prepare the Ni-Co MOF nanorods as the anode materials. By utilizing EDTA (ethylenediaminetetraacetic acid, an organic ligand with multiple advantages) as the organic ligand, the hydrothermal approach further enhanced the storage capacity and stability of the SC electrodes.²³⁵ Fig. 6b illustrates the architecture of the Ni-Co-MOF device as the cathode component within the asymmetric structure of a hybrid SC, which facilitated its construction. The innovation of this approach lies in effectively enhancing the performance of the energy storage systems through structural optimization. To further evaluate the stability of this electrode material, the researchers conducted cyclic voltammetry tests, as shown in Fig. 6c. The cyclic voltammetry curves for this electrode assembly were obtained at scan rates ranging from 5 to 100 mV s^{-1} , revealing symmetrical responses across varying scan rates. These data are crucial for subsequent verification of the stability of the device.

The cyclic potential evaluation of the experimental device was conducted by monitoring 10 000 consecutive charge-discharge cycles at a current density of 10 A g^{-1} , as depicted in Fig. 6d. To validate the device's durability and reproducibility, the experimentally prepared hybrid structure was retested after being stored at room temperature for 40 days and 80 days. The experimental results are shown in Fig. 6e. As depicted, although the specific power and specific energy decrease after 40 and 80 days, the final stable electrochemical properties reach

Table 3 Important parameters of the MOF composites for SC electrode materials

Materials	Synthetic method	Cyclic stability (%); cycles	Specific capacitance (F g^{-1}); current density (A g^{-1})	Specific energy (W h kg^{-1})
Co-V-MOF	Ultrasonic-assisted <i>in situ</i> hydrothermal	92.21; 10 000	187.5; 5	70.65 (ref. 222)
ZNC-Se@NC-LDH@rGO-NF	Hydrothermal	92.4; 10 000	226; 1	80.3 (ref. 223)
Ni-MOFs	Hydrothermal	89.7; 10 000	~830; 1	53.1 (ref. 221)
MXene@CoSe ₂ /Ni ₃ Se ₄	—	80; 5000	283; 1	90 (ref. 226)
ZCO/ZnO	Hydrothermal	91.04; 10 000	161; 1	50.41 (ref. 224)
VNi-MOF NSAs/NF	One-step solvothermal	85.6; 12 000	~574.6; 1	43 (ref. 227)
CFO@NMO	Hydrothermal	88.4; 10 000	312.8; 0.5	90.3 (ref. 225)
Ni/Co-MOF-NPC	Solvothermal	98.8; 6000	681; 10	55.4 (ref. 228)
MOF525-NC1.35	Carbonization transformation	77; 10 000	200; 5	— ²²⁹
NGCA	High-temperature carbonization activation	93; 5000	244; 1	17.08 (ref. 230)
Ni-MOF/rGO	Hydrothermal synthesis	Increases by 49.34; 25 000	435.25; 1	76.96 (ref. 231)
Ni-MOF/CNF	Hydrothermal synthesis	88; 5000	742.2; 1	58.43 (ref. 232)






Fig. 6 (a) Schematic of the preparation of CC/CoNi-MOF, reproduced from ref. 233 with permission from Elsevier, copyright 2020. (b) Power schematic of hybrid SCs. (c) CV analysis plots at different scan rates with different potential windows. (d) Capacity retention for 10 000 cycles. (e) Analysis of the power and energy after 40 and 80 days, reproduced from ref. 235 with permission from Elsevier, copyright 2024.

71.43 W h kg⁻¹ and 70.33 W h kg⁻¹, respectively, demonstrating satisfactory performance.²³⁵

Based on the principle that vacancies in nanostructured metal oxides significantly enhance the specific capacitance of electrode materials,^{236,237} Wei *et al.* conducted an in-depth exploration of MOF derivatives for developing novel electrode materials. They synthesized oxygen-rich vacancy P-doped ZnCo₂O₄ nanosheets (abbreviated as ZCP/NC) derived from nitrogen-doped carbon-loaded MOFs. They reported a method derived from the synthesis of ZnCo-MOFs to construct P-doped ZnCo₂O₄ nanosheets, with oxygen-rich vacancies coated on the surface of the nitrogen-doped carbon, as shown in Fig. 7b. Electrochemical testing results revealed that, under 1 A g⁻¹

conditions, the maximum capacitance of the electrode material reached 1581.5 F g⁻¹. Furthermore, the experimentally prepared composite material and activated carbon exhibit outstanding stability. When assembled as pseudocapacitors in asymmetric electrodes, their retention rate approached 90.6% after 5000 cycles.²³⁸

5.1.3 Composites of MOFs with MXenes and CNTs. In recent years, MXene composites synthesized from MOFs have garnered significant attention due to their exceptional surface area and structural flexibility, sparking considerable interest in their use for the exploration of energy storage materials.²⁴⁰ Among these, the integration of MXenes with MOFs represents a new era of electrochemical synergy, effectively enhancing the






Fig. 7 (a) Production of ZIF-8 and ZIF-67-derived nano-PC and their advantages and disadvantages. Reproduced with permission from the American Chemical Society and reproduced from ref. 239 with permission from the Royal Society of Chemistry, copyright 2020. (b) Schematic of the synthetic procedure used to prepare P-doped ZnCo_2O_4 on N-doped carbon, reproduced from ref. 238 with permission from Elsevier, copyright 2021.

performance of SCs by increasing the surface area and providing more active sites for electrochemical reactions.²⁴¹ Despite the appeal of MOFs for energy-related applications, they still suffer from inherent challenges such as low conductivity and chemical sensitivity. These issues severely hinder their practical implementation and scalability. Recently, researchers discovered that the unique properties and structure of MXenes can potentially improve the conductivity and stability of pristine MOFs.²³ First, the high conductivity of MXene frameworks enables the formation of efficient conductive pathways that effectively shorten ion diffusion routes. Furthermore, MXenes possess abundant negatively charged surface groups, making them excellent substrates for supporting MOF growth. This not only prevents the agglomeration of MXenes and MOF nanoparticles but also increases the accessible surface area. Additionally, strong interfacial interactions between MXene and MOFs significantly enhance the structural integrity and stability. Based on this, MXene@MOF composites hold great

promise as functional materials for electrochemical applications. Furthermore, converting the MOFs into functional MOF-derived nanoparticles can optimize and enhance the electrochemical performance of MXene@MOF composites. It is noteworthy that the synergistic effects induced by the hybridization of MXene with MOFs or MOF-derived nanoparticles effectively address the inherent drawbacks of the individual components. Sani and his team investigated the preparation of MXene@MOF composites, particularly by utilizing MXene as a metal precursor for MOF synthesis. For the preparation of MOF/MXene composites, MXenes were added to a solution containing well-dissolved metal ions and organic ligands, with the composite formed by using the same synthesis methods used for pure MOFs. This approach includes room-temperature diffusion reactions, hydrothermal methods, and other technical approaches.²³ The research conducted by K. J. *et al.* aimed to explore electrode materials suitable for hybrid supercapacitors with different charge storage mechanisms. They



assembled carboxyl-functionalized graphene acid with amino-functionalized metal-organic framework UiO-66-NH₂ through amide bonds to prepare the GA@UiO-66-NH₂ hybrid material as the positive electrode, and Ti₃C₂T_x MXene as the negative electrode to construct an asymmetric supercapacitor. The energy density reached up to 73 W h kg⁻¹, and the power density reached up to 16 kW kg⁻¹. What is more remarkable is that, under a current density of 5.2 A g⁻¹, this design could still maintain 88% of the initial capacitance after 10 000 cycles, and achieved a 100% Coulomb efficiency.²⁴² These findings provide compelling evidence for the adoption of hybrid designs in fabricating more robust, high-power energy storage systems.

CNTs exhibit excellent electrical conductivity, large SSA, and high thermal stability, and they can be easily prepared at low cost. Given the precise properties required for SCs, CNTs have been extensively utilized in pseudocapacitors. Polypyrrole (PPy), polyaniline (PANI), and polythiophene (PTh) CNTs are commonly used in SC electrodes. Although these polymers offer relatively high theoretical specific capacitance values, their actual performance remains unsatisfactory. This is primarily due to the strong aggregation tendency of polymers, which causes a linear reduction in surface area. Consequently, the exposed surface area for interaction with the electrolyte decreases, leading to poor practical results. Research has revealed that composites of MOFs and CNTs can effectively overcome the inherent limitations of their parent materials. These composites eliminate the brittleness and agglomeration issues faced by CNTs while addressing the low conductivity problem associated with MOFs. TMOs derived from MOFs exhibit large SSAs and high conductivity. Since electrode materials undergo continuous expansion and contraction during SC charge-discharge cycles, the TMO-based electrodes typically exhibit poor cycling stability. This issue can be addressed by co-depositing mechanically stable CP (such as PANI) with TMO. He *et al.* designed the CuOx@mC@PANI@rGO composite, which was prepared *via* the *in situ* polymerization of aniline monomers. This composite exhibits an excellent C_g of 534.5 F g⁻¹ at a current density of 1 A g⁻¹.²⁴³

5.1.4 A new type of MOFs: ZIF. The zeolite imidazole framework (ZIF) is a novel MOF material that has emerged in recent years. By combining organic and inorganic components, this approach enables the fabrication of materials with distinct particle shapes, exceptional porosity, and tailored surface functionality. As shown in Fig. 7a, ZIFs can be selectively pyrolyzed under controlled conditions to generate PC or metal compounds with unique nanostructures. ZIFs can also be synthesized *via* simple coordination chemistry of organic and inorganic components, allowing precise regulation and control of surface area, pore volume, and porous architecture. Consequently, the diverse and unique structures derived from them hold significant application potential as electrode materials for SCs. Among these, ZIF-67 and ZIF-8 have garnered attention from scientists as electrode materials for SCs.²³⁹ Yao *et al.* developed a promising strategy to overcome the conductivity barrier in MOF materials. They enhanced faradaic processes at the electrode interface by wrapping PANI chains around MOF crystals, with these PANI chains electrochemically deposited

onto the MOF framework.²⁴⁴ MOF materials such as ZIF-67 and ZIF-8 have been successfully synthesized chemically. Compared with ZIF-67/POAP, SGO/ZIF-8/POAP, and pure graphene electrodes, the SGO/ZIF-67/POAP composite electrode exhibits a higher specific capacitance and maximum energy density. The SGO/ZIF-67/POAP composite electrode demonstrates superior capacitance values and maximum energy density relative to the ZIF-67/POAP, the SGO/ZIF-8/POAP, and the pure graphene electrodes. The C_g (specific capacitance) of the prepared electrodes is 825 and 670 F g⁻¹, respectively. After 103 charge-discharge cycles on these two types of nanocomposite materials, it was found that they only lost 10% of their initial capacitance, which indicates extremely high electrochemical cycle stability. Furthermore, the energy densities of the SGO/ZIF-67/POAP and SGO/ZIF-8/POAP electrodes are 114.58 W h kg⁻¹ and 111.77 W h kg⁻¹, respectively. Compared with the electrochemical performance of more commonly used composites (such as MOFs and GO) at different current densities, the SGO/ZIF-67/POAP and SGO/ZIF-8/POAP composites exhibit superior performance due to their high conductivity.²⁴⁵ Furthermore, to validate the potential of the experimental materials as electrode materials for energy storage systems, researchers conducted additional electrochemical experiments. The ternary nanocomposite electrode (SGO/ZIF-67/POAP) exhibits a C_g of 825 F g⁻¹ at a current density of 1 A g⁻¹. Remarkably, the prepared electrode maintained 90% of its initial capacitance after 1000 cycles.

Notably, although the MOFs and their derivatives have demonstrated significant improvements in energy density and other aspects when used as container electrode materials for SCs, further research is still needed on composite materials formed by combining these frameworks with other high-performance materials. Evaluating the synthesis and experimental properties of such composites to elucidate how their chemical structures and architectures influence charge storage behavior will effectively advance the development of next-generation high-performance, green, and sustainable energy storage systems.

5.2. Application of COFs and their composite materials in SCs

COFs are crystalline organic porous materials formed by ordered covalent bonds between structural units.²⁴⁶ Their high porosity, tunable framework architectures, and charge-transfer-adaptive channels make COFs key materials for SC electrodes.²⁴⁷ Based on the geometric symmetry, COFs can be broadly classified into 2D and 3D structures.²⁴⁸ The functional group design not only adjusts the dimensional architectures of COFs but also directly governs their electrochemical performance. Therefore, the targeted incorporation of functional groups can endow COF materials with unique performance characteristics.

For SCs, 2D COFs (with porous channel characteristics that mimic the ion transport behavior of CNTs) facilitate electrolyte wetting of electrode surfaces and efficient ion adsorption, thereby enhancing specific capacitance.²⁴⁹ Specifically, the highly ordered porous structure of the COFs serves as an



electron-conducting framework, providing an ideal ion-transport pathway at the EEI. Concurrently, their inherently large SSA offers an abundant number of ion-adsorption sites.²⁵⁰ These combined properties lay the foundation for enhanced SC performance.

To further validate the practical application potential of 2D COF-derived materials in SC electrodes, researchers have conducted in-depth studies *via* experimental approaches such as doping modification and structural optimization. Umezawa *et al.* provided key references for the preparation and performance evaluation of boron-doped COF-derived carbon materials. Umezawa *et al.* synthesized porous COFs with a $C_9H_4BO_2$ structure (designated COF-5) *via* the direct boron carbide method. Thermogravimetric analysis confirms its excellent thermal stability, with the thermal decomposition temperature of COF-5 fluctuating only slightly around 600 °C. To obtain boron-doped PC materials, the team calcined COF-5 at 1000 °C. The resulting carbon material was washed with water under a nitrogen atmosphere to yield boron-doped PC (WCCOF-5). WCCOF-5 was further pulverized to prepare PCCOF-5 nanoparticles suitable for SC electrode films, and their electrochemical performance was evaluated to validate their energy storage potential. At a current density of 40 mA g⁻¹, the pore characteristics and specific capacitance of PCCOF-5 and two commercial carbon materials, YP50F and MSP20, were tested, and the results show C_g values of approximately 82.9 F g⁻¹, 99.6 F g⁻¹, and 159.2 F g⁻¹ for the three materials, respectively. Notably, despite the significantly lower SSA of PCCOF-5 (approximately 689 m² g⁻¹) compared with YP50F (1670 m² g⁻¹), its C_g (82.9 F g⁻¹) was comparable with that of YP50F (99.6 F g⁻¹). This suggests that PCCOF-5 possesses an optimized pore structure better suited for electrolyte ion transport. Furthermore, at a current density of 40 mA cm⁻², PCCOF-5 exhibits the highest C_s among the three materials, at 15.3 μF cm⁻².²⁵¹

Currently, research is ongoing to identify highly efficient electrode materials for SCs and to synthesize materials with superior electrochemical performance. Carbon nanomaterials have emerged as representative electrode materials for SCs due to their high structural plasticity, large SSA, and excellent electrical conductivity. Furthermore, doping with heteroatoms such as boron, phosphorus, and sulfur can significantly enhance the properties of carbon nanomaterials. For instance, doping with heteroatoms such as carbon and nitrogen not only improves conductivity and capacitance but also enhances material wettability, outperforming pure carbon materials. Consequently, a key research direction involves deepening our understanding of the properties of existing energy storage material properties, overcoming the limitations of single materials, and constructing more efficient electrode material systems through rational combination strategies.

COFs, as suitable precursors for preparing carbon-based nanocomposite electrode materials for SCs, provide an effective pathway in this direction. Mewat *et al.* reported a COF-based composite system for SCs: triazine-based COF/GO nanocomposites were synthesized *via* both *ex situ* and *in situ* one-pot strategies. These composites were further converted into nitrogen-doped carbon (N-doped C)/reduced graphene oxide

(rGO) composites through a simple carbonization step. Performance testing revealed that devices using the *in situ* prepared N-doped C/rGO (N-doped C/rGO_In) as the electrode material achieved a specific power of up to 400 W kg⁻¹, a specific energy of 14.6 W h kg⁻¹, and a capacitance performance degradation of only 14% after 3500 cycles. To systematically validate material performance, the researchers evaluated COF/GO, pure COF, N-doped C, and N-doped C/rGO as the SC electrode materials. Electrochemical impedance spectroscopy (EIS) was used to assess the conductivity and characterize the electrochemical performance, confirming that carbonized COF/rGO composites exhibit optimal capacitive properties.²⁵²

To conclude, COFs have evolved into key precursors for SC electrode materials, owing to their tailorable framework structures, superior porosity, and derived functional properties. Through the carbonization modification of single-component COFs or their composites with carbon-based materials (such as GO), the energy density, power density, and cycling stability of devices can be significantly enhanced, providing key technological support for the development of high-performance energy storage devices.

MOFs and COFs, as two prominent classes of porous framework materials, exhibit notable similarities in their applications in supercapacitors. Regarding the energy storage mechanism, both leverage their high specific surface area and ordered pore channels to enable efficient electrical double-layer capacitance. Additionally, their specific capacitance can be enhanced through pseudocapacitance, which is further facilitated by the introduction of redox-active sites. In terms of essential material properties, both require high electrical conductivity, robust structural stability, and well-designed micro/mesoporous architectures. Common performance optimization strategies include heteroatom doping, compositing with conductive matrices, and transformation into carbonized derivatives, which synergistically improve electrical conductivity, active site density, and structural integrity. Despite their significant potential for enhancing energy density, both MOFs and COFs face shared challenges, such as scalable synthesis, long-term cycling stability, and electrode–electrolyte interface optimization. Future research should focus on integrating their complementary structural and performance advantages through rational design and composite engineering to advance the development of next-generation high-performance energy storage systems.

6. Conclusions and prospects

6.1. Conclusion

With the continuous progress of society and the rapid development of science and technology, the associated industries, as the economic lifeline of a country, have naturally developed rapidly. However, this progression is followed by energy consumption, environmental pollution and other problems, which pose a great threat to human living environments. For more than two decades, researchers have been committed to exploring high-performance, versatile materials. The rapid development of advanced MOF/COF materials has triggered



great interest, advances and breakthroughs in multifunctional applications. This is mainly due to their high SSA, active organic functional groups, and good pore structure and stability, which endow them with superior physical, chemical and biological properties. This review summarizes the synthesis and chemical structures of MOFs/COFs, as well as the latest progress in typical fields such as batteries and SCs, and highlights numerous important discoveries.

In terms of synthetic methods, solvothermal and hydrothermal syntheses feature mild reaction conditions, allowing precise control of crystal growth, and the products are formed with high crystallinity. Microwave-assisted synthesis can drastically reduce reaction times through the application of rapid and uniform heating, enhance the nucleation and growth kinetics of crystals, and offer a viable route for the efficient fabrication of high-performance materials. Mechanochemical synthesis does not require the use of solvents and can be solvent-free, rendering it more environmentally friendly, and it can also be used for efficient compounding with other materials. It has broad prospects in the preparation of low-cost materials. Ultrasonic chemical synthesis utilizes the ultrasonic cavitation effect to prepare nanoscale materials and synthesize special structures. In conclusion, each type of synthetic method has its own characteristics. For practical applications, the optimal synthetic method should be selected based on specific requirements of the application, such as research or production.

At the chemical structure level, the unique structures of MOFs and COFs are the core support for achieving high-performance energy storage. MOFs form 3D porous structures through the coordination of metal ions/clusters with organic ligands. Their regular pore systems provide an efficient path for ion transport, and the abundant metal active sites can directly participate in electrochemical reactions, significantly enhancing the energy storage capacity. COFs form 2D or 3D crystal porous structures through covalent bonds of light elements, featuring high stability, large SSA and uniform pore channels. These features not only increase the contact area between the electrode and the electrolyte, but also promote rapid ion diffusion, providing a structural guarantee for the optimization of energy storage performance.

In the field of batteries, these types of crystalline porous materials, with their ordered porous frameworks, can achieve rapid ion transport and storage without significant volume changes, providing a new solution to the problems of low power density and poor cycle stability of traditional batteries. MOFs exhibit excellent electrochemical efficacy in lithium-ion batteries, Li-S batteries and LOBs. Materials derived from MOFs can effectively mitigate the polysulfide shuttle effect of Li-S batteries and enhance the catalytic activity of LOBs through structural optimization. COFs, through the precise design of skeleton structure and functional groups, perform outstandingly in inhibiting polysulfide shuttling and optimizing ion transport kinetics, providing a new path for the development of high-energy-density batteries.

Within the realm of SCs, MOFs and their derivatives can substantially boost the specific capacitance and cycling stability

of electrodes by regulating the composition of transition metals and allowing the fabrication of composite structures (such as combining with MXene and CNTs). The porous channel characteristics of COFs can simulate the ion transport function of CNTs, promoting electrolyte wetting and ion adsorption. Their highly ordered porous structure not only provides a framework for electron transport but also offers abundant ion adsorption sites, effectively enhancing the specific capacitance and energy density of SCs.

In conclusion, MOFs and COFs, with their unique advantages such as high SSA, tailorable pore architectures, abundant active sites and structural designability, have irreplaceable application value in the field of energy storage.

6.2. Challenges and future prospects

6.2.1 Challenges. Although MOF/COF materials demonstrate great potential in numerous application fields, there are still some key issues to be addressed to further deepen our understanding of these materials and expand their application prospects. These problems include the following.

The bottleneck in the fabrication protocols makes it difficult for MOF/COF materials to balance large-scale production and economic efficiency. The commonly employed solvothermal and hydrothermal synthesis methods in the laboratory have long reaction cycles, high solvent consumption, and rely on high-pressure apparatus. When microwave-assisted synthesis is scaled up, it faces the problem of uneven heating, which leads to significant differences in product performance. Mechanochemical synthesis struggles to precisely control the particle size distribution and pore structure of the products, while sonochemical synthesis is limited by the reaction scale. Neither approach can directly meet the demands of industrial production. Meanwhile, the rare metal salts required by MOFs and the special organic ligands of COFs are expensive, and the synthesis cost is significantly higher than that of traditional carbon materials. Some synthetic solvents are also toxic or scarce, further increasing the cost of environmental remediation and the risk of interrupted raw material supply.

The insufficient adaptability to practical applications makes it difficult for MOF/COF materials to meet the actual service requirements of energy storage devices. Their porous structure is prone to adsorb solvent molecules in the electrolyte, can change the composition of the electrolyte in the channels, and can increase the resistance of ion diffusion. Furthermore, the material surface is prone to forming an unstable solid electrolyte interface (SEI) layer with the electrolyte. The metal sites of MOFs can also catalyze the repeated rupture and reconstruction of the film, exacerbating the increase in battery impedance. In terms of safety and thermal management, the high SSA endows the material with a robust adsorption capacity for electrolytes. At high temperatures, thermal runaway reactions are prone to occur. Some metal ions in MOFs may also catalyze the decomposition of the electrolyte to produce flammable substances, which limits their application in high-power scenarios. In addition, the MOFs/COFs in retired electrodes are mixed with various components such as binders and conductive agents,



rendering their separation and purification difficult. Current recovery methods predominantly rely on strong acid dissolution, which not only leads to high energy consumption and serious pollution, but also, if the waste liquid and residue produced during the synthesis process are not properly treated, can cause heavy metal and organic pollution, which is in conflict with the environmental protection requirements for clean energy storage.

6.2.2 Future prospects. In response to these challenges, relevant research has proposed numerous solutions, as follows.

Innovation in synthesis and fabrication processes: the synthetic process will develop in the direction of high efficiency, greenness and scalability. On the one hand, existing synthesis methods should be optimized by, for example, shortening the reaction cycle of solvothermal and hydrothermal synthesis through process integration and intelligent regulation of reaction parameters, improving the solvent recovery rate, and developing low-cost and environmentally friendly solvent systems to reduce the environmental footprint of the synthesis process. On the other hand, new synthetic technologies should be explored, such as continuous-flow synthesis and photo-assisted synthesis, to achieve batch preparation and performance homogenization of materials. In terms of cost control, low-cost precursors should be developed to replace rare metal salts and high-cost organic ligands, for instance, in the synthesis of covalent organic frameworks (COFs), low-cost organic ligands typified by tetrathiafulvalene (TTF) derivatives and aromatic amines derived from industrial by-products have demonstrated favorable application prospects. Compared with high-priced commercial organic ligands, these alternative ligands enable a 30–50% reduction in raw material costs, while retaining the exceptional structural regularity and functional properties inherent to COF materials.²⁵³ The application of industrial waste in material synthesis should also be explored to reduce raw material costs. Furthermore, ionothermal synthesis employs low-cost ionic liquids (ILs) as both solvents and templates. This approach enables the rapid fabrication of 3D COFs under ambient temperature and pressure, eliminating the need for expensive high-pressure reaction equipment and substantially reducing energy consumption.²⁵⁴ By optimizing the process to increase the synthetic yield, cost allocation under large-scale production can be achieved.

Application scenario expansion and system adaptation. In terms of application scenarios, MOF/COF materials will be deeply integrated in a diverse range of energy storage devices. In the field of batteries, dedicated MOF/COF-based electrode materials and intermediates will be developed to address the pain points of new types of batteries, such as Li–S batteries and LOBs, further enhancing the energy density and cycling stability of batteries. In the field of SCs, the focus will be on developing high-energy-density MOF/COF-based composite electrodes. By integrating them with CPs and transition metal oxides, the specific capacitance and cycling stability of the materials will be synergistically boosted. In terms of system adaptation, the collaborative design of materials and energy storage devices will be further advanced. In terms of interface optimization, the compatibility between the material and the electrolyte will be

improved and the interface impedance will be reduced through surface modification, functional coating and other methods. In terms of thermal management, MOF/COF composite materials will be developed with both energy storage and heat conduction functions to enhance the thermal stability and safety of devices.

Interdisciplinary integration and advancement of fundamental research. In the future, the innovative development of the MOF/COF materials will be driven through interdisciplinary integration. By leveraging computational chemistry and artificial intelligence technologies, the structure–performance relationship of materials can be accurately predicted, guiding the design and synthesis of function-oriented MOFs/COFs and shortening the R&D cycle. By integrating advanced characterization techniques (such as *in situ* transmission electron microscopy and synchrotron radiation X-ray diffraction), the structural evolution, ion transport and reaction mechanisms of materials during the charge–discharge cycles are revealed in-depth, providing theoretical support for performance optimization. Strengthening of cross-disciplinary cooperation between materials science, electrochemistry, engineering and other fields should solve technical problems throughout the entire chain, such as material synthesis, device assembly and system integration, promoting the translation of MOF/COF materials from laboratory research to large-scale commercial applications, and providing key material support for alleviating the energy crisis and advancing sustainable energy development.

Conflicts of interest

There are no conflicts of interest to declare.

Data availability

No primary research results, software or code have been included and no new data were generated or analysed as part of this review.

Acknowledgements

This investigation is supported by the Project for Natural Science Foundation of Henan Province (262300420053), Science and Technology Plan of Henan Province (252102221038 and 252102220073); the Henan postdoctoral Science Foundation (HN2025153), the Key Scientific Research Project Plan of Higher Education Institutions of Henan Province (25B460009); the Henan Province's New Key Discipline Machinery; the Henan Province's first-class undergraduate major-Mechanical Design, Manufacturing and Automation; the Henan Engineering Research Center of Acoustic Meta-materials; the Henan Province Private University Discipline Funding Project-Mechanical Design, Manufacturing and Automation; Henan Mechanical Engineering Master Teacher Studio (ZLG202320); and the Zhengzhou City Mechanical and Electronic Engineering Master Teacher Studio (ZZLG202401).



References

- B. K. Saikia, S. M. Benoy, M. Bora, D. Neog, D. Bhattacharjya, A. Rajbongshi and P. Saikia, Fabrication of pouch cell supercapacitors using abundant coal feedstock and their hybridization with Li-ion battery for e-rickshaw application, *J. Energy Storage*, 2024, **78**, 110312.
- L. Dai, M. Xie, J. Liu and H. Peng, A review of MOFs and their derivatives for lithium ion battery: Structural design, synthesis strategy and mechanism, *J. Ind. Eng. Chem.*, 2024, **130**, 125–140.
- R. Wang, F. Zhang, K. Yang, Y. Xiong, J. Tang, H. Chen, M. Duan, Z. Li, H. Zhang and B. Xiong, Review of two-dimensional nanomaterials in tribology: Recent developments, challenges and prospects, *Adv. Colloid Interface Sci.*, 2023, **321**, 103004.
- J. Zhang, Y. Liu, T. Wang, N. Fu and Z. Yang, Manganese-based MOF interconnected carbon nanotubes as a high-performance cathode for rechargeable aqueous zinc-ion batteries, *J. Energy Storage*, 2024, **76**, 109873.
- Y. Feng, L. Shen, C. Wang, H. Bao, N. Chen, X. Lin, R. Liu and X. Feng, Electrodeposition of NiMn-MOFs/carbon cloth for flexible all-solid-state supercapacitors electrode with ultra-long cycling stability, *Electrochim. Acta*, 2024, **485**, 144110.
- A. Kumar and R. Kataria, MOFs as versatile scaffolds to explore environmental contaminants based on their luminescence bustle, *Sci. Total Environ.*, 2024, **926**, 172129.
- G. M. Choi, M. Mandal, H. J. Jung, J. Panda, Y. J. Kwon, K. Zhang, E. Vivek, M. Shon, K. Ravi, K.-Y. Baek, H. T. Kwon, J.-G. Yeo and K. Y. Cho, Post-synthetic modifications (PSM)-induced defects in hybrid metal-organic frameworks (MOFs) to unleash potential in gas separation membrane applications, *J. Mater. Sci. Technol.*, 2024, **201**, 95–118.
- Y. Liu, P. Li, R. Cui, C. Qin, L. Wu, X. Zhang, B. Li, J. Ping, Y. Wang, J. Pan, Y. Ying, D. Li, D. Shi and L. Xu, Metal-organic frameworks (MOFs) and covalent organic frameworks (COFs)-based prototyping of integrated sensing devices for robust analysis, *TrAC, Trends Anal. Chem.*, 2024, **174**, 117678.
- S. Gharanli, R. E. Malekshah, M. Moharramnejad, A. Ehsani, M. Shahi, A. H. Joshaghani, A. h. Amini, J. Haribabu, E. S. Istifli and F. K. Tehrani, Recent progress in designing heterogeneous COFs with the photocatalytic performance, *Mol. Catal.*, 2024, **560**, 114127.
- R. Iqbal, G. Yasin, M. Hamza, S. Ibraheem, B. Ullah, A. Saleem, S. Ali, S. Hussain, T. Anh Nguyen, Y. Slimani and R. Pathak, State of the art two-dimensional covalent organic frameworks: Prospects from rational design and reactions to applications for advanced energy storage technologies, *Coord. Chem. Rev.*, 2021, **447**, 214152.
- M. Du, Q. Li, G. Zhang, F. Wang and H. Pang, Metal-Organic Framework-Based Sulfur-Loaded Materials, *Energy Environ. Mater.*, 2022, **5**(1), 215–230.
- M. Sajjad, R. Tao, K. Kang, S. Luo and L. Qiu, Phosphine-Based Porous Organic Polymer/rGO Aerogel Composites for High-Performance Asymmetric Supercapacitor, *ACS Appl. Energy Mater.*, 2021, **4**(1), 828–838.
- X. Song, S. Song, D. Wang and H. Zhang, Prussian blue analogs and their derived nanomaterials for electrochemical energy storage and electrocatalysis, *Small Methods*, 2021, **5**(4), 2001000.
- J. Xu, C. Yang, Y. Xue, C. Wang, J. Cao and Z. Chen, Facile synthesis of novel metal-organic nickel hydroxide nanorods for high performance supercapacitor, *Electrochim. Acta*, 2016, **211**, 595–602.
- J. Yan, T. Liu, X. Liu, Y. Yan and Y. Huang, Metal-organic framework-based materials for flexible supercapacitor application, *Coord. Chem. Rev.*, 2022, **452**, 214300.
- M. Sajjad and W. Lu, Covalent organic frameworks based nanomaterials: Design, synthesis, and current status for supercapacitor applications: A review, *J. Energy Storage*, 2021, **39**, 102618.
- M. Zhao and S. Tong, Recent Progress and Perspectives on Metal-Organic Framework-Based Electrode Materials for Metal-Ion Batteries and Supercapacitors, *Energy Fuels*, 2024, **38**(15), 13796–13818.
- R. Tao, T. Yang, Y. Wang, J. Zhang, Z. Wu and L. Qiu, Design strategies of covalent organic framework-based electrodes for supercapacitor application, *Chem. Commun.*, 2023, **59**(22), 3175–3192.
- D.-G. Wang, Z. Liang, S. Gao, C. Qu and R. Zou, Metal-organic framework-based materials for hybrid supercapacitor application, *Coord. Chem. Rev.*, 2020, **404**, 213093.
- D.-G. Wang, T. Qiu, W. Guo, Z. Liang, H. Tabassum, D. Xia and R. Zou, Covalent organic framework-based materials for energy applications, *Energy Environ. Sci.*, 2021, **14**(2), 688–728.
- R. Shah, S. Ali, F. Raziq, S. Ali, P. M. Ismail, S. Shah, R. Iqbal, X. Wu, W. He and X. Zu, Exploration of metal organic frameworks and covalent organic frameworks for energy-related applications, *Coord. Chem. Rev.*, 2023, **477**, 214968.
- H. Niu, N. Zhang, Y. Lu, Z. Zhang, M. Li, J. Liu, N. Zhang, W. Song, Y. Zhao and Z. Miao, Strategies toward the development of high-energy-density lithium batteries, *J. Energy Storage*, 2024, **88**, 111666.
- N. Kitchamsetti and J. S. Cho, A roadmap of recent advances in MXene@MOF hybrids, its derived composites: Synthesis, properties, and their utilization as an electrode for supercapacitors, rechargeable batteries and electrocatalysis, *J. Energy Storage*, 2024, **80**, 110293.
- L. Han, Y. Cao, C. Liao, Y. Kan and Y. Hu, Novel silica-coated cathode to realize internal-short-circuit proof, high-interface-stabilized, high-safety lithium batteries, *J. Power Sources*, 2024, **602**, 234273.
- J. Chen, J. Luo, Y. Xiang and Y. Yu, Light-assisted rechargeable zinc-air battery: Mechanism, progress, and prospects, *J. Energy Chem.*, 2024, **91**, 178–193.



- 26 X. Leng, J. Zeng, M. Yang, C. Li, S. V. P. Vattikuti, J. Chen, S. Li, J. Shim, T. Guo and T. J. Ko, Bimetallic Ni–Co MOF@PAN modified electrospun separator enhances high-performance lithium-sulfur batteries, *J. Energy Chem.*, 2023, **82**, 484–496.
- 27 A. Haruna, K. B. Dönmez, S. Hooshmand, E. Avcı, M. Qamar, S. A. Zaidi, F. Shahzad, T. S. Miller, B. K. Chakrabarti, C. A. Howard and M. K. Bayazit, Harmony of nanosystems: Graphitic carbon nitride/carbon nanomaterial hybrid architectures for energy storage in supercapacitors and batteries, *Carbon*, 2024, **226**, 119177.
- 28 Q. Pan, M. Yang, F. Song, Z. Xiong and X. He, Preparation of layered NiCo-MOF nanosheets for high-performance asymmetric supercapacitor electrode material, *Vacuum*, 2024, **225**, 113203.
- 29 C. Li, L. Liu, J. Kang, Y. Xiao, Y. Feng, F.-F. Cao and H. Zhang, Pristine MOF and COF materials for advanced batteries, *Energy Storage Mater.*, 2020, **31**, 115–134.
- 30 M. Ravipati, L. Durai and S. Badhulika, Single-pot solvothermal synthesis of single-crystalline nickel–metal organic framework nanosheets for direct iron fuel cell applications, *ACS Appl. Energy Mater.*, 2023, **6**(13), 6901–6909.
- 31 H. Xu, H. Sun, J. Zhang, H. Cao, G. Li and Z. Ni, Construction and ReO₄[–] adsorption of ionic covalent organic frameworks by solvothermal synthesis based on Zincke reaction, *Sep. Purif. Technol.*, 2024, **333**, 125895.
- 32 M. Gutiérrez, Y. Zhang and J.-C. Tan, Confinement of luminescent guests in metal–organic frameworks: understanding pathways from synthesis and multimodal characterization to potential applications of LG@ MOF systems, *Chem. Rev.*, 2022, **122**(11), 10438–10483.
- 33 M. S. Lohse and T. Bein, Covalent organic frameworks: structures, synthesis, and applications, *Adv. Funct. Mater.*, 2018, **28**(33), 1705553.
- 34 Y. Yang, S. Ma, M. Xia, Y. Guo, Y. Zhang, L. Liu, C. Zhou, G. Chen, X. Wang, Q. Wu, L. Yang and Z. Hu, Elaborately converting hierarchical NiCo-LDH to rod-like LDH-decorated MOF as interlayer for high-performance lithium–sulfur battery, *Mater. Today Phys.*, 2023, **35**, 101112.
- 35 B. Du, Y. Luo, Y. Yang, W. Xue, G. Liu and J. Li, COFs-confined multifunctional Sulfur-host design towards High-performance Lithium-sulfur batteries, *Chem. Eng. J.*, 2022, **442**, 135823.
- 36 A. D. Savariraj, C. J. Raj, R. Velayutham, H. M. Jang, P. Sivakumar, W.-J. Cho and B. C. Kim, Experimental and theoretical exploration of nickel ion-implanted metal-organic frameworks (ZIF-67) as free-standing electrodes for hybrid supercapacitors, *J. Power Sources*, 2023, **580**, 233467.
- 37 J. Xia, R. Wang, C. Qian, K. Sun, H. Liu, C. Guo, J. Li, F. Yu and W. Bao, Supercapacitors of Nanocrystalline Covalent Organic Frameworks—A Review, *Crystals*, 2022, **12**(10), 1350.
- 38 O. Yildirim, M. Bonomo, N. Barbero, C. Atzori, B. Civalleri, F. Bonino, G. Viscardi and C. Barolo, Application of metal-organic frameworks and covalent organic frameworks as (photo) active material in hybrid photovoltaic technologies, *Energies*, 2020, **13**(21), 5602.
- 39 A. Bhoite, V. Sawant and N. Tarwal, Solvothermal synthesis of Ni/Co-based metal-organic framework with nanosheets-like structure for high-performance supercapacitor, *Colloids Surf., A*, 2024, **702**, 134814.
- 40 M. M. Mahmoud, Microwave-assisted fast synthesis of MOF-801, *Next Mater.*, 2025, **6**, 100316.
- 41 Z. Alsudairy, Q. Zheng, N. Brown, R. Behera, C. Yang, M. H. Uddin, A. Saintlima, L. Middlebrooks, J. Li and C. Ingram, Microwave-assisted synthesis of mixed-linker covalent organic frameworks enabling tunable and ultrahigh iodine capture, *Chem. Eng. J.*, 2024, **485**, 149135.
- 42 X. Wei, M. Bi, Q. Lou, D. Di, B. Liu and D. Pei, Fast and facile sonochemical fabrication of covalent organic frameworks in water for the adsorption of flavonoids: Adsorption behaviors and mechanisms, *Colloids Surf., A*, 2024, **702**, 134731.
- 43 N. Abaszadeh, D. Afzali, G. Sargazi and A. Golpayegani, Sonochemical-assisted method for efficient synthesis of Cu-MOF and evaluating its antibacterial properties, *Heliyon*, 2024, **10**(10), e31024.
- 44 Y. Hou, M. Dong, F. Meng, J. He, X. Li, J. Sun, X. Wang, Z. Su and C. Sun, Enhanced stability and confinement effects of Cs₄PbBr₆ quantum dots via mechanochemical immobilization on MOF nodes, *J. Alloys Compd.*, 2024, **985**, 173880.
- 45 E. Hamzehpoor, F. Effaty, T. H. Borchers, R. S. Stein, A. Wahrhaftig-Lewis, X. Ottenwaelder, T. Frišćić and D. F. Perepichka, Mechanochemical Synthesis of Boroxine-linked Covalent Organic Frameworks, *Angew. Chem.*, 2024, **136**(51), e202404539.
- 46 X. Yang, L. Gong, Z. Liu, Q. Zhi, B. Yu, X. Chen, K. Wang, X. Li, D. Qi and J. Jiang, Hydrothermal synthesis of polyimide-linked covalent organic frameworks towards ultrafast and stable cathodic sodium storage, *Sci. China:Chem.*, 2024, **67**(4), 1300–1310.
- 47 Y. Liang, W.-G. Yuan, S.-F. Zhang, Z. He, J. Xue, X. Zhang, L.-H. Jing and D.-B. Qin, Hydrothermal synthesis and structural characterization of metal–organic frameworks based on new tetradentate ligands, *Dalton Trans.*, 2016, **45**(4), 1382–1390.
- 48 L. Peng, Y. Liu and D. Wei, Supercritical Solvothermal Synthesis of Single-Crystalline Covalent Organic Frameworks and Their Applications, *Acc. Mater. Res.*, 2025, **6**(8), 991–1005.
- 49 A. Laemont, G. Matthys, R. Lavendomme and P. Van Der Voort, Mild and Scalable Conditions for the Solvothermal Synthesis of Imine-Linked Covalent Organic Frameworks, *Angew. Chem., Int. Ed.*, 2024, **63**(51), e202412420.
- 50 J. Klinowski, F. A. Almeida Paz, P. Silva and J. Rocha, Microwave-Assisted Synthesis of Metal–Organic Frameworks, *Dalton Trans.*, 2011, **40**(2), 321–330.



- 51 M. Lyu, Z. Zhao, H. Li and X. Gao, Surfactant-mediated microwave synthesis of metal organic frameworks for efficient atmospheric water harvesting, *Chin. J. Chem. Eng.*, 2025, **86**, 150–163.
- 52 E. Hamzehpoor, F. Effaty, T. H. Borchers, R. S. Stein, A. Wahrhaftig-Lewis, X. Ottenwaelder, T. Frišćić and D. F. Perepichka, Mechanochemical Synthesis of Boroxine-linked Covalent Organic Frameworks, *Angew. Chem., Int. Ed.*, 2024, **63**(51), e202404539.
- 53 D. Bigdelifam and M. Hashemi, Mechanochemical Synthesis of Graphene Oxide/UiO-66-NH₂ Nanocomposites: Characterization and Fabrication of an Electrochemical Sensor for the Determination of Tetracycline Residues in Milk Samples, *ACS Omega*, 2025, **10**(16), 16184–16193.
- 54 C. Li, J. Florek, P. Guggenberger and F. Kleitz, Gram-scale green synthesis of a highly stable cationic covalent organic framework for efficient and selective removal of $\text{ReO}_4^-/^{99}\text{TcO}_4^-$, *J. Mater. Chem. A*, 2025, **13**(1), 214–219.
- 55 Z. Zheng, A. H. Alawadhi and O. M. Yaghi, Green synthesis and scale-up of MOFs for water harvesting from air, *Mol. Front. J.*, 2023, **7**, 20–39.
- 56 C. Sun, L. Karuppasamy, L. Gurusamy, H.-J. Yang, C.-H. Liu, J. Dong and J. J. Wu, Facile sonochemical synthesis of CdS/COF heterostructured nanocomposites and their enhanced photocatalytic degradation of Bisphenol-A, *Sep. Purif. Technol.*, 2021, **271**, 118873.
- 57 C. Vaitis, G. Sourkouni and C. Argiris, Chapter 11- Sonochemical synthesis of MOFs, in *Metal-Organic Frameworks for Biomedical Applications*, ed. M. Mozafari, Woodhead Publishing, 2020, pp. 223–244.
- 58 L. Zhang, Y. Song, W. Wu, R. Bradley, Y. Hu, Y. Liu and S. Guo, Fe₂Mo₃O₈ nanoparticles self-assembling 3D mesoporous hollow spheres toward superior lithium storage properties, *Front. Chem. Sci. Eng.*, 2021, **15**, 156–163.
- 59 C. Li, M. Luo, Z. Xia and S. Guo, High-index faceted noble metal nanostructures drive renewable energy electrocatalysis, *Nano Mater. Sci.*, 2020, **2**(4), 309–315.
- 60 T. Guo, K. Wang, G. Zhang and X. Wu, A novel $\alpha\text{-Fe}_2\text{O}_3$ @g-C₃N₄ catalyst: Synthesis derived from Fe-based MOF and its superior photo-Fenton performance, *Appl. Surf. Sci.*, 2019, **469**, 331–339.
- 61 P. B. So, H.-T. Chen and C.-H. Lin, De novo synthesis and particle size control of iron metal organic framework for diclofenac drug delivery, *Microporous Mesoporous Mater.*, 2020, **309**, 110495.
- 62 N. Huang, K. Wang, H. Drake, P. Cai, J. Pang, J. Li, S. Che, L. Huang, Q. Wang and H.-C. Zhou, Tailor-made pyrazolide-based metal-organic frameworks for selective catalysis, *J. Am. Chem. Soc.*, 2018, **140**(20), 6383–6390.
- 63 L. Y. Wu, Y. F. Mu, X. X. Guo, W. Zhang, Z. M. Zhang, M. Zhang and T. B. Lu, Encapsulating perovskite quantum dots in iron-based metal-organic frameworks (MOFs) for efficient photocatalytic CO₂ reduction, *Angew. Chem., Int. Ed.*, 2019, **58**(28), 9491–9495.
- 64 B. n. Lerma-Berlanga, C. R. Ganivet, N. Almora-Barrios, S. Tatay, Y. Peng, J. Albero, O. Fabelo, J. González-Platas, H. García and N. M. Padiál, Effect of linker distribution in the photocatalytic activity of multivariate mesoporous crystals, *J. Am. Chem. Soc.*, 2021, **143**(4), 1798–1806.
- 65 P. Karthik, A. M. Shaheer, A. Vinu and B. Neppolian, Amine functionalized metal-organic framework coordinated with transition metal ions: d-d transition enhanced optical absorption and role of transition metal sites on solar light driven H₂ production, *Small*, 2020, **16**(12), 1902990.
- 66 H. Jiang, S. Bu, Q. Gao, J. Long, P. Wang, C.-S. Lee and W. Zhang, Ultrathin two-dimensional nickel-organic framework nanosheets for efficient electrocatalytic urea oxidation, *Mater. Today Energy*, 2022, **27**, 101024.
- 67 Y. Gao, S. Li, Y. Li, L. Yao and H. Zhang, Accelerated photocatalytic degradation of organic pollutant over metal-organic framework MIL-53(Fe) under visible LED light mediated by persulfate, *Appl. Catal., B*, 2017, **202**, 165–174.
- 68 A. P. Cote, A. I. Benin, N. W. Ockwig, M. O’Keeffe, A. J. Matzger and O. M. Yaghi, Porous, crystalline, covalent organic frameworks, *Science*, 2005, **310**(5751), 1166–1170.
- 69 Y. Su, M. Qin, J. Kong, Q. Zhai, D. Yuan, Z. Liu and Y. Fang, Solvothermal Shaping of Imine-Linked Covalent Organic Frameworks by a Two-Step Solvent Feeding Process, *Adv. Funct. Mater.*, 2024, **34**(33), 2400433.
- 70 J. Klinowski, F. A. A. Paz, P. Silva and J. Rocha, Microwave-assisted synthesis of metal-organic frameworks, *Dalton Trans.*, 2011, **40**(2), 321–330.
- 71 Z. Ni and R. I. Masel, Rapid production of metal-organic frameworks via microwave-assisted solvothermal synthesis, *J. Am. Chem. Soc.*, 2006, **128**(38), 12394–12395.
- 72 C. Guo, S. Chen, J. Aslam, J. Li, L.-P. Lv, W. Sun, W. Cao and Y. Wang, Microwave-Assisted Metal-Organic Frameworks Derived Synthesis of Zn₂GeO₄ Nanowire Bundles for Lithium-Ion Batteries, *Nanomaterials*, 2023, **13**(8), 1432.
- 73 H. Wei, S. Chai, N. Hu, Z. Yang, L. Wei and L. Wang, The microwave-assisted solvothermal synthesis of a crystalline two-dimensional covalent organic framework with high CO₂ capacity, *Chem. Commun.*, 2015, **51**(61), 12178–12181.
- 74 A. B. Albadarin, C. B. Potter, M. T. Davis, J. Iqbal, S. Korde, S. Pagire, A. Paradkar and G. Walker, Development of stability-enhanced ternary solid dispersions via combinations of HPMCP and Soluplus processed by hot melt extrusion, *Int. J. Pharm.*, 2017, **532**(1), 603–611.
- 75 A. Metawea, R. Soto, M. Khraisheh, G. Walker and A. B. Albadarin, Application of Raman and chemometrics to the mechanochemical synthesis of 4,4'-bipyridine/cobalt based MOF using twin screw extrusion, *Powder Technol.*, 2024, **437**, 119558.
- 76 G. Kaur, A. Anthwal, P. Kandwal and D. Sud, Mechanochemical synthesis and theoretical investigations of Fe(II) based MOF containing 4,4'-bipyridine with ordained intercalated p-aminobenzoic acid: Application as fluoroprobe for detection of carbonyl group, *Inorg. Chim. Acta*, 2023, **545**, 121248.
- 77 N. Khosroshahi, M. Bakhtian and V. Safarifard, Mechanochemical synthesis of ferrite/MOF



- nanocomposite: Efficient photocatalyst for the removal of meropenem and hexavalent chromium from water, *J. Photochem. Photobiol., A*, 2022, **431**, 114033.
- 78 Z. W. Zhu and Q. R. Zheng, Investigation of cryo-adsorption hydrogen storage capacity of rapidly synthesized MOF-5 by mechanochemical method, *Int. J. Hydrogen Energy*, 2023, **48**(13), 5166–5174.
- 79 N. Brown, Z. Alsudairy, R. Behera, F. Akram, K. Chen, K. Smith-Petty, B. Motley, S. Williams, W. Huang and C. Ingram, Green mechanochemical synthesis of imine-linked covalent organic frameworks for high iodine capture, *Green Chem.*, 2023, **25**(16), 6287–6296.
- 80 Z. Zhang and Y. Xu, Hydrothermal synthesis of highly crystalline zwitterionic vinylene-linked covalent organic frameworks with exceptional photocatalytic properties, *J. Am. Chem. Soc.*, 2023, **145**(46), 25222–25232.
- 81 G. Kaur, P. Kandwal and D. Sud, Sonochemically synthesized Zn (II) and Cd (II) based metal-organic frameworks as fluoroprobes for sensing of 2,6-dichlorophenol, *J. Solid State Chem.*, 2023, **319**, 123833.
- 82 F. Maleki, S. Fathi and M. Safari, Sonochemical synthesis of cobalt (II) metal-organic framework (TMU-10)/polypyrrole nanocomposites with high adsorption capacity for dye removal from water, *Environ. Prog. Sustainable Energy*, 2024, **43**(2), e14311.
- 83 S.-T. Yang, J. Kim, H.-Y. Cho, S. Kim and W.-S. Ahn, Facile synthesis of covalent organic frameworks COF-1 and COF-5 by sonochemical method, *RSC Adv.*, 2012, **2**(27), 10179–10181.
- 84 V. F. Yusuf, N. I. Malek and S. K. Kailasa, Review on Metal-Organic Framework Classification, Synthetic Approaches, and Influencing Factors: Applications in Energy, Drug Delivery, and Wastewater Treatment, *ACS Omega*, 2022, **7**(49), 44507–44531.
- 85 F. Kong and W. Chen, Carbon Dioxide Capture and Conversion Using Metal-Organic Framework (MOF) Materials: A Comprehensive Review, *Nanomaterials*, 2024, **14**, 16.
- 86 T. Chen, S. Bian, X. Yang, W. Lu, K. Wang, Y. Guo, C. Zhang and Q. Zhang, A hollow urchin-like metal-organic framework with Ni-O-cluster SBUs as a promising electrode for an alkaline battery-supercapacitor device, *Inorg. Chem. Front.*, 2023, **10**(8), 2380–2386.
- 87 C. Lin, S. Wang, X. Zhang, B. Xiao, Y. Zeng, L. Huang, F. Luo, K. Liu, J. Tian, M. Li, M. Cao and Y. Qian, Unraveling the Role of Functional Groups of Terephthalate in Enhancing the Electrochemical Oxygen Evolution Reaction of Nickel-Organic Framework Nanoarrays, *Inorg. Chem.*, 2025, **64**(4), 2059–2071.
- 88 W. Liu, W. Que, R. Yin, J. Dai, D. Zheng, J. Feng, X. Xu, F. Wu, W. Shi, X. Liu and X. Cao, Ferrum-molybdenum dual incorporated cobalt oxides as efficient bifunctional anti-corrosion electrocatalyst for seawater splitting, *Appl. Catal., B*, 2023, **328**, 122488.
- 89 J. Feng, D. Zheng, R. Yin, X. Niu, X. Xu, S. Meng, S. Ma, W. Shi, F. Wu and W. Liu, A Wide-Temperature Adaptive Aqueous Zinc-Air Battery-Based on Cu-Co Dual Metal-Nitrogen-Carbon/Nanoparticle Electrocatalysts, *Small Struct.*, 2023, **4**(7), 2200340.
- 90 X. Li, X. Wang, A. Ito and N. M. Tsuji, A nanoscale metal organic frameworks-based vaccine synergises with PD-1 blockade to potentiate anti-tumour immunity, *Nat. Commun.*, 2020, **11**(1), 3858.
- 91 F. Mahmoudi and M. M. Amini, Confined crystallization of microporous metal-organic framework within mesoporous silica with enhanced hydrostability: Ultrafast removal of organic dyes from aqueous solutions by MIL-68(Al)@SBA-15 composite, *J. Water Proc. Eng.*, 2020, **35**, 101227.
- 92 L. Du, B. Zhang, W. Deng, Y. Cheng, L. Xu and L. Mai, Hierarchically self-assembled mof network enables continuous ion transport and high mechanical strength, *Adv. Energy Mater.*, 2022, **12**(24), 2200501.
- 93 Y. Liu, Z. Liu, D. Huang, M. Cheng, G. Zeng, C. Lai, C. Zhang, C. Zhou, W. Wang, D. Jiang, H. Wang and B. Shao, Metal or metal-containing nanoparticle@MOF nanocomposites as a promising type of photocatalyst, *Coord. Chem. Rev.*, 2019, **388**, 63–78.
- 94 D. Yuan, T. He, X. Guo, J. Huang, Y. He, Y. Wang, Y. Liu, X. Zhao, Z. Liu and Q. Zhang, Highly selective removal of thorium from acidic solutions achieved on phosphonic acid functionalized core-shell magnetic nanocomposite: Understanding adsorption and binding mechanisms, *Sep. Purif. Technol.*, 2025, **352**, 127586.
- 95 X. Lei, Y. Li, P. Guo, M. Qiu, R. Meng, S. Li, D. Zhang, N. Chen and X. Zhou, Hydroquinone colorimetric sensing based on core-shell structured CoFe₂O₄@N-GQDs@CeO₂ nanocomposites as oxidase mimics, *New J. Chem.*, 2024, **48**(16), 7323–7333.
- 96 A. Barzkar, A. Salimi Beni, S. Abaezadeh, S. Parang and F. salahshour, Benzothiazole/Palladium immobilize on magnetic core-shell nanostructure with carbon and TiO₂ shells as a novel and magnetically catalyst with high recoverability, *Results Chem.*, 2024, **8**, 101599.
- 97 K. Geng, T. He, R. Liu, S. Dalapati, K. T. Tan, Z. Li, S. Tao, Y. Gong, Q. Jiang and D. Jiang, Covalent organic frameworks: design, synthesis, and functions, *Chem. Rev.*, 2020, **120**(16), 8814–8933.
- 98 S. Kandambeth, K. Dey and R. Banerjee, Covalent organic frameworks: chemistry beyond the structure, *J. Am. Chem. Soc.*, 2018, **141**(5), 1807–1822.
- 99 Y.-N. Gong, X. Guan and H.-L. Jiang, Covalent organic frameworks for photocatalysis: Synthesis, structural features, fundamentals and performance, *Coord. Chem. Rev.*, 2023, **475**, 214889.
- 100 N. Huang, L. Zhai, D. E. Coupry, M. A. Addicoat, K. Okushita, K. Nishimura, T. Heine and D. Jiang, Multiple-component covalent organic frameworks, *Nat. Commun.*, 2016, **7**(1), 12325.
- 101 Z. Li, L. Sheng, C. Hsueh, X. Wang, H. Cui, H. Gao, Y. Wu, J. Wang, Y. Tang and H. Xu, Three-dimensional covalent organic frameworks with hea topology, *Chem. Mater.*, 2021, **33**(24), 9618–9623.
- 102 F. Chen, H. Zheng, Y. Yusran, H. Li, S. Qiu and Q. Fang, Exploring high-connectivity three-dimensional covalent



- organic frameworks: topologies, structures, and emerging applications, *Chem. Soc. Rev.*, 2025, **54**(1), 484–514.
- 103 L. Yang and N. Huang, Covalent organic frameworks for applications in lithium batteries, *J. Polym. Sci.*, 2022, **60**(15), 2225–2238.
- 104 S. J. Shin, J. W. Gittins, C. J. Balhatchet, A. Walsh and A. C. Forse, Metal–organic framework supercapacitors: challenges and opportunities, *Adv. Funct. Mater.*, 2024, **34**(43), 2308497.
- 105 R. C. K. Reddy, X. Lin, A. Zeb and C.-Y. Su, Metal–Organic Frameworks and Their Derivatives as Cathodes for Lithium-Ion Battery Applications: A Review, *Electrochem. Energy Rev.*, 2022, **5**(2), 312–347.
- 106 S. Qiao, H. Jin, A. Zuo and Y. Chen, Integration of Enzyme and Covalent Organic Frameworks: From Rational Design to Applications, *Acc. Chem. Res.*, 2023, **57**(1), 93–105.
- 107 Y. Song, Q. Sun, B. Aguila and S. Ma, Opportunities of covalent organic frameworks for advanced applications, *Adv. Sci.*, 2019, **6**(2), 1801410.
- 108 M. Shao, Y. Liu and Y. Guo, Customizable 2d covalent organic frameworks for optoelectronic applications, *Chin. J. Chem.*, 2023, **41**(10), 1260–1285.
- 109 F. Jin, E. Lin, T. Wang, S. Geng, T. Wang, W. Liu, F. Xiong, Z. Wang, Y. Chen and P. Cheng, Bottom-up synthesis of 8-connected three-dimensional covalent organic frameworks for highly efficient ethylene/ethane separation, *J. Am. Chem. Soc.*, 2022, **144**(12), 5643–5652.
- 110 H.-L. Qian, C.-X. Yang and X.-P. Yan, Bottom-up synthesis of chiral covalent organic frameworks and their bound capillaries for chiral separation, *Nat. Commun.*, 2016, **7**(1), 12104.
- 111 Z. Sun, Z. Li, J. Peng, X. Yan, H. Shang, Y. Jin, Q. Zhao, C. Li, S. Lyu and C. Chen, Advances in hexaazatriphenylene-based COFs for rechargeable batteries: from structural design to electrochemical performance, *Energy Environ. Sci.*, 2025, **18**, 5159–5189.
- 112 J. L. Segura, S. Royuela and M. M. Ramos, Post-synthetic modification of covalent organic frameworks, *Chem. Soc. Rev.*, 2019, **48**(14), 3903–3945.
- 113 N. Xu, Y. Hu, B. Sun, W. Xie, C. Yao, Y. Xu and J. Qi, Highly Electronegative Element-Rich COF Modified Separator Achieves High-Performance of Lithium–Sulfur Batteries, *ACS Appl. Polym. Mater.*, 2024, **6**(22), 13813–13818.
- 114 X. Huang, C. Sun and X. Feng, Crystallinity and stability of covalent organic frameworks, *Sci. China: Chem.*, 2020, **63**, 1367–1390.
- 115 X. Guan, H. Li, Y. Ma, M. Xue, Q. Fang, Y. Yan, V. Valtchev and S. Qiu, Chemically stable polyarylether-based covalent organic frameworks, *Nat. Chem.*, 2019, **11**(6), 587–594.
- 116 W. Wang, K. Cai, W. Zhou, F. Tao, Z. Li, Q. Lin, L. Wang, Z. Yu, J. Zhang and H. Zhou, Nanoporous Vinylene-Linked 2D Covalent Organic Frameworks for Visible-Light-Driven Aerobic Oxidation, *ACS Appl. Nano Mater.*, 2023, **6**(10), 8396–8403.
- 117 J. Sindha, J. Thakur and M. Khalid, The economic value of hybrid battery swapping stations with second life of batteries, *Clean. Energy Syst.*, 2023, **5**, 100066.
- 118 Y. Wu, M. Yang, S. Wang, S. Hou, Y. Zou, Y. Tao and C. Yang, Sulfur-rich polymer/Ketjen Black composites as lithium-sulfur battery cathode with high cycling stability, *J. Alloys Compd.*, 2023, **962**, 171177.
- 119 M. Zhong, L. Kong, K. Zhao, Y.-H. Zhang, N. Li and X.-H. Bu, Recent Progress of Nanoscale Metal-Organic Frameworks in Synthesis and Battery Applications, *Adv. Sci.*, 2021, **8**(4), 2001980.
- 120 J. Xu, M. Zhong, X. Chen, C. Wang and X. Lu, One-dimensional MOFs-based and their-derived fascinating electrocatalysts for water electrolysis, *Sep. Purif. Technol.*, 2023, **320**, 124184.
- 121 R. Zhao, Z. Liang, R. Zou and Q. Xu, Metal-Organic Frameworks for Batteries, *Joule*, 2018, **2**(11), 2235–2259.
- 122 X. Liu, F. Liu, X. Zhao and L.-Z. Fan, Constructing MOF-derived CoP-NC@MXene sandwich-like composite by in-situ intercalation for enhanced lithium and sodium storage, *J. Mater. Chem.*, 2022, **8**(1), 30–37.
- 123 F. M. N. U. Khan, M. G. Rasul, A. S. M. Sayem and N. K. Mandal, Design and optimization of lithium-ion battery as an efficient energy storage device for electric vehicles: A comprehensive review, *J. Energy Storage*, 2023, **71**, 108033.
- 124 T. Nshizirungu, M. Rana, M. I. H. Khan, Y. T. Jo and J.-H. Park, Innovative green approach for recovering Co₂O₃ nanoparticles and Li₂CO₃ from spent lithium-ion batteries, *J. Hazard. Mater. Adv.*, 2023, **9**, 100242.
- 125 J. Xiong, T.-X. Lei, D.-M. Fu, J.-W. Wu and T.-Y. Zhang, Data driven discovery of an analytic formula for the life prediction of Lithium-ion batteries, *Prog. Nat. Sci. Mater. Int.*, 2022, **32**(6), 793–799.
- 126 P. U. Nzereogu, A. D. Omah, F. I. Ezema, E. I. Iwuoha and A. C. Nwanya, Anode materials for lithium-ion batteries: A review, *Appl. Surf. Sci. Adv.*, 2022, **9**, 100233.
- 127 A. Kumar Prajapati and A. Bhatnagar, A review on anode materials for lithium/sodium-ion batteries, *J. Energy Chem.*, 2023, **83**, 509–540.
- 128 L. Li, Y. Deng, K. Hu, B. Xu, N. Wang, Z. Bai, X. Xu and J. Yang, Nanostructure designing and hybridizing of high-capacity silicon-based anode for lithium-ion batteries, *Prog. Nat. Sci. Mater. Int.*, 2023, **33**(1), 16–36.
- 129 Y. Jiang, H. Zhao, L. Yue, J. Liang, T. Li, Q. Liu, Y. Luo, X. Kong, S. Lu, X. Shi, K. Zhou and X. Sun, Recent advances in lithium-based batteries using metal organic frameworks as electrode materials, *Electrochem. Commun.*, 2021, **122**, 106881.
- 130 C. Liang, J. Guo, L. Yue, M. Wang, J. Liang, X. Wang, Y. Li and K. Yu, MOF-SnO₂ nanoparticles composited with biomass-derived carbon used as high-performance anodes for lithium-ion batteries, *Diamond Relat. Mater.*, 2023, **140**, 110488.
- 131 H. Ruan, L. Zhang, S. Li, K. Wang, W. Huang and S. Guo, Carbon polyhedra encapsulated Si derived from Co-Mo bimetal MOFs as anode materials for lithium-ion batteries, *J. Mater. Sci. Technol.*, 2023, **159**, 91–98.
- 132 N. Sammawipawekul, N. Kaesamut, T. Autthawong, A. Watwiangkham, S. Suthirakun, S. Wannapaiboon,



- N. Mahamai, T. Sarakonsri, Y. Chimupala and S. Yimklan, Isostructural dual-ligand-based MOFs with different metal centers in response to diverse capacity lithium-ion battery anode, *Chem. Eng. J.*, 2024, **482**, 148904.
- 133 M. Jin, G. Sun, J. Yuan, Y. Wang, J. Zhou, J. Li, X. Ni, X. Pan and E. Xie, Synergistic effect of $\text{Co}_3\text{O}_4/\text{Fe}_2\text{O}_3$ nanoparticles encapsulated with MOFs-derived nitrogen-doped porous carbon for high-performance lithium-ion battery, *J. Alloys Compd.*, 2022, **922**, 166231.
- 134 T. Lu, J. Zhao, J. Yuan, J. Xu and J. Jin, PbSe/sulfur-doped carbon nanocube composites prepared from Pb-MOF precursors as anode materials for lithium and sodium-ion batteries, *J. Alloys Compd.*, 2021, **874**, 159942.
- 135 I. Ciria-Ramos, A. R. Neale, L. J. Hardwick, E. J. Juarez-Perez, I. Gascon and M. Haro, Operando Raman and ex situ characterization of an iron-based conductive MOF as a negative electrode in Li-ion batteries, *Dalton Trans.*, 2025, **24**, 54.
- 136 M. Han, J. Ma, Y. Luo, S. Han and Y. Huang, ZIF-67 Clusters with Small-Size Particles Confined by a Graphene Framework as a Promising Lithium-Ion Battery Anode, *ACS Omega*, 2025, **10**(15), 15181–15190.
- 137 M. Cognet, T. Gutel, D. Peralta, J. Maynadié, J. Cambedouzou, M. Carboni and D. Meyer, A (NiMnCo)-Metal-Organic Framework (MOF) as active material for Lithium-ion battery electrodes, *Sci. Technol. Energy Transition*, 2023, **78**, 33.
- 138 Y. Yang, M. Li and X. Hu, Self-Assembled Carbon Metal-Organic Framework Oxides Derived from Two Calcination Temperatures as Anode Material for Lithium-Ion Batteries, *Molecules*, 2024, **29**, 3566.
- 139 F. Jia, F. Wang, J. Pan, C. Sun, R. Zhang, C. Jiao, C. Gao, J. Sang, Y. Xu and Q. Wang, Electrospun metal-organic framework materials derived bimetallic oxides as high-efficiency anodes for lithium-ion battery, *J. Alloys Compd.*, 2024, **1006**, 176201.
- 140 S. Gaber, A. K. Mohammed, B. H. Javaregowda, J. I. Martínez, P. P. Sánchez, F. Gándara, K. Krishnamoorthy and D. Shetty, MOFite: A High-Density Lithiophilic and Scalable Metal-Organic Framework Anode for Rechargeable Lithium-Ion Battery, *Angew. Chem., Int. Ed.*, 2024, **63**(44), e202409256.
- 141 X. Du, G. Xu, C. Zhu, T. Zhou, P. Shi and G. Gao, Copper/cobalt metal-organic framework composites for advanced anode material of lithium-ion battery, *J. Energy Storage*, 2024, **89**, 111863.
- 142 P. Mao, H. Fan, C. Liu, G. Lan, W. Huang, Z. Li, H. Mahmoud, R. Zheng, Z. Wang, H. Sun and Y. Liu, Conductive Co-based metal organic framework nanostructures for excellent potassium- and lithium-ion storage: kinetics and mechanism studies, *Sustain. Energy Fuels*, 2022, **6**(17), 4075–4084.
- 143 W. Zhai, N. Srikanth, L. B. Kong and K. Zhou, Carbon nanomaterials in tribology, *Carbon*, 2017, **119**, 150–171.
- 144 J. Yan, C. Gao, S. Qi, Z. Jiang, L. R. Jensen, H. Zhan, Y. Zhang and Y. Yue, Encapsulation of nano-Si into MOF glass to enhance lithium-ion battery anode performances, *Nano Energy*, 2022, **103**, 107779.
- 145 C. Gao, Z. Jiang, S. Qi, P. Wang, L. R. Jensen, M. Johansen, C. K. Christensen, Y. Zhang, D. B. Ravnsbæk and Y. Yue, Metal-Organic Framework Glass Anode with an Exceptional Cycling-Induced Capacity Enhancement for Lithium-Ion Batteries, *Adv. Mater.*, 2022, **34**(10), 2110048.
- 146 J. Zhu, W. Xu, M. Knapp, M. S. Dewi Darma, L. Mereacre, P. Su, W. Hua, X. Liu-Théato, H. Dai, X. Wei and H. Ehrenberg, A method to prolong lithium-ion battery life during the full life cycle, *Cell Rep. Phys. Sci.*, 2023, **4**(7), 101464.
- 147 R. A. Bajwa, U. Farooq, S. Ullah, M. Salman, S. Haider, S. Shahida, B. A. Farooqi and E. B. Elkaeed, Layer-By-Layer (LBL) hybrid MOF coating for graphene-based multilayer composite: Synthesis and application as anode for lithium ion batteries, *J. Saudi Chem. Soc.*, 2023, **27**(5), 101691.
- 148 X. Wang, Y. Wang, F. Wu, G. Jin, J. Li and Z. Zhang, Continuous zirconium-based MOF-808 membranes for polysulfide shuttle suppression in lithium-sulfur batteries, *Appl. Surf. Sci.*, 2022, **596**, 153628.
- 149 Z. Ye, Y. Jiang, L. Li, F. Wu and R. Chen, MOF-related electrocatalysts for sulfur reduction/evolution reactions: Composition modulation, structure design, and mechanism research, *eScience*, 2023, **3**(5), 100107.
- 150 C. Zhou, X. Wang, R. Zhao, L. Li, J. Li and F. Wu, MOF-808-derived Ce-doped ZrOF composite as an efficient polysulfide inhibitor for advanced lithium-sulfur batteries, *J. Alloys Compd.*, 2022, **924**, 166486.
- 151 X. Li, F. Cheng, S. Zhang and J. Chen, Shape-controlled synthesis and lithium-storage study of metal-organic frameworks $\text{Zn}_4\text{O}(1,3,5\text{-benzenetribenzoate})_2$, *J. Power Sources*, 2006, **160**(1), 542–547.
- 152 X. Liu, J. Q. Huang, Q. Zhang and L. Mai, Nanostructured Metal Oxides and Sulfides for Lithium-Sulfur Batteries, *Adv. Mater.*, 2017, **29**(20), 1601759.
- 153 Z. Xiong, G. Zhang, Y. Ding, J. You and S. Cheng, Thin-walled hollow MoS_2 microspheres as sulfur hosts for high-performance lithium sulfur batteries, *Int. J. Electrochem. Sci.*, 2023, **18**(8), 100215.
- 154 P. Balaji T, S. Choudhury and E. E. Marinero, Polymer-Based Solid-State Electrolytes For Lithium-Sulfur Batteries, *ACS Appl. Polym. Mater.*, 2025, **7**(13), 8352–8374.
- 155 W. Wang, H. Li, C. Ding, Z. Guo and G. Wang, Self-supporting cathodes with conductive composite interlayer for high performance bendable lithium-sulfur batteries, *J. Energy Storage*, 2023, **71**, 108072.
- 156 T. Wan, E. Wang, C. Wu, J. Li, Z. Zhang and G. Liu, MOF-derived micro-mesoporous TiO_2 -based composite as sulfur host for high-performance lithium-sulfur batteries, *Electrochim. Acta*, 2023, **439**, 141570.
- 157 H. Wu, Y. Yang, W. Jia, R. Xiao and H. Wang, Defect-engineered bilayer MOFs separator for high stability lithium-sulfur batteries, *J. Alloys Compd.*, 2021, **874**, 159917.



- 158 J. Liu, W. Gao, X. Zhang, J. Li, Q. Li, G. Li, Y. Zhang and Z. Chen, Rational construction of rich coordination-unsaturated Zr-BTB electrocatalyst towards advanced lithium-sulfur batteries, *Chem. Eng. J.*, 2023, **471**, 144238.
- 159 X. Wu, C. Zhou, C. Dong, C. Shen, B. Shuai, C. Li, Y. Li, Q. An, X. Xu and L. Mai, Polydopamine-assisted in-situ formation of dense MOF layer on polyolefin separator for synergistic enhancement of lithium-sulfur battery, *Nano Res.*, 2022, **15**(9), 8048–8055.
- 160 D. K. Kim, J. Byun, S. Moon, J. Choi, J. H. Chang and J. Suk, Molten salts approach of metal-organic framework-derived nitrogen-doped porous carbon as sulfur host for lithium-sulfur batteries, *Chem. Eng. J.*, 2022, **441**, 135945.
- 161 H. B. Wu, S. Wei, L. Zhang, R. Xu, H. H. Hng and X. W. Lou, Embedding Sulfur in MOF-Derived Microporous Carbon Polyhedrons for Lithium-Sulfur Batteries, *Chem.-Eur. J.*, 2013, **19**(33), 10804–10808.
- 162 Y. Xiao, Y. Xiang, S. Guo, J. Wang, Y. Ouyang, D. Li, Q. Zeng, W. Gong, L. Gan, Q. Zhang and S. Huang, An ultralight electroconductive metal-organic framework membrane for multistep catalytic conversion and molecular sieving in lithium-sulfur batteries, *Energy Storage Mater.*, 2022, **51**, 882–889.
- 163 Y. Wang, S. Cao, J. Zhao, X. Zhang, X. Du, J. Li and F. Wu, Conductive vanadium-based metal-organic framework nanosheets membranes as polysulfide inhibitors for lithium-sulfur batteries, *J. Alloys Compd.*, 2023, **960**, 170922.
- 164 A. E. Baumann, X. Han, M. M. Butala and V. S. Thoi, Lithium Thiophosphate Functionalized Zirconium MOFs for Li-S Batteries with Enhanced Rate Capabilities, *J. Am. Chem. Soc.*, 2019, **141**(44), 17891–17899.
- 165 A. C. Xu Zhang, M. Zhong, Z. Zhang, X. Zhang, Z. Zhou and X.-H. Bu, Metal-Organic Frameworks (MOFs) and MOF-Derived Materials for Energy Storage and Conversion, *Electrochem. Energy Rev.*, 2019, **2**(1), 29–104.
- 166 S. Gopi, A. M. Al-Mohaimed, W. A. Al-onazi, M. Soliman Elshikh and K. Yun, Metal organic framework-derived Ni-Cu bimetallic electrocatalyst for efficient oxygen evolution reaction, *J. King Saud Univ. Sci.*, 2021, **33**(3), 101379.
- 167 T. Lan, H. Du, Y. Li, K. Qu, J. Zhao, X. Zhang, Y. Dong, Y. Zhang, X. Zhang and D. Zhang, One-pot synthesis of NiFe-MOF/NiFe₂O₄ hollow spheres and their application as bifunctional ORR/OER electrocatalysts in Zn-air batteries, *J. Alloys Compd.*, 2023, **943**, 169144.
- 168 H. Mu, X. Zhuge, G. Ren, K. Luo, Z. Ding, Y. Ren, Z. Luo, M. Bayati, B. B. Xu and X. Liu, Dual functional mesoporous silica colloidal electrolyte for lithium-oxygen batteries, *Chem. Eng. J.*, 2023, **455**, 140761.
- 169 X. Zhang, L. Peng, Z. Zhai, H. Fong, Y. Liu and C. Li, A freestanding cathode with bimetallic MOF-based composites anchored on N-doped porous carbon nanofibers for lithium-oxygen batteries, *Electrochim. Acta*, 2021, **397**, 139251.
- 170 Q. Qiu, J. Long, P. Yao, J. Wang, X. Li, Z.-Z. Pan, Y. Zhao and Y. Li, Cathode electrocatalyst in aprotic lithium oxygen (Li-O₂) battery: A literature survey, *Catal. Today*, 2023, **420**, 114138.
- 171 T. L. Kulova, V. N. Fateev, E. A. Seregina and A. S. Grigoriev, A Brief Review of Post-Lithium-Ion Batteries, *Int. J. Electrochem. Sci.*, 2020, **15**(8), 7242–7259.
- 172 W. Dou, Z. Cheng, X. Zhang, J. Duan, Z. Sun, J. Lei, L. Zhu, M. Huang, J. Fan, R. Yuan, M. Zheng and Q. Dong, Intelligently tuning the electronic structure of solid catalyst for bidirectional electrode process in lithium-oxygen batteries, *Cell Rep. Phys. Sci.*, 2023, **4**(6), 101448.
- 173 H. Ouyang, S. Min, J. Yi, X. Liu, F. Ning, J. Qin, Y. Jiang, B. Zhao and J. Zhang, Tuning composite solid-state electrolyte interface to improve the electrochemical performance of lithium-oxygen battery, *Green Energy Environ.*, 2023, **8**(4), 1195–1204.
- 174 R. Liang, A. Hu, M. Li, Z. Ran, C. Shu and J. Long, Cobalt encapsulated within porous MOF-derived nitrogen-doped carbon as an efficient bifunctional electrocatalyst for aprotic lithium-oxygen battery, *J. Alloys Compd.*, 2019, **810**, 151877.
- 175 H. R. Abuzeid, A. F. M. El-Mahdy and S.-W. Kuo, Covalent organic frameworks: Design principles, synthetic strategies, and diverse applications, *Giant*, 2021, **6**, 100054.
- 176 X. Kong, S. Zhou, M. Strømme and C. Xu, Redox active covalent organic framework-based conductive nanofibers for flexible energy storage device, *Carbon*, 2021, **171**, 248–256.
- 177 Z. Su, J. Huang, R. Wang, Y. Zhang, L. Zeng, Y. Zhang and H. Fan, Multilayer structure covalent organic frameworks (COFs) linking by double functional groups for advanced K⁺ batteries, *J. Colloid Interface Sci.*, 2023, **639**, 7–13.
- 178 S. Jin, O. Allam, S. S. Jang and S. W. Lee, Covalent organic frameworks: Design and applications in electrochemical energy storage devices, *InfoMat*, 2022, **4**(6), e12277.
- 179 T. Lin, R. Qiao, Y. Luo, Z. Zhang, Y. Yang and J. Li, Covalent organic framework-based core-shell sulfur cathode design for enhanced polysulfide immobilization and redox kinetics in lithium-sulfur batteries, *J. Alloys Compd.*, 2023, **936**, 168184.
- 180 Y. Ge, J. Li, Y. Meng and D. Xiao, Tuning the structure characteristic of the flexible covalent organic framework (COF) meets a high performance for lithium-sulfur batteries, *Nano Energy*, 2023, **109**, 108297.
- 181 G.-H. Kim, Y.-J. Lee, J.-W. Park, A. Raza, M. B. Raza, D. Kim, M. Park and H. Choi, Enhanced performance of lithium-sulfur battery cathode via composition optimization using modified MWCNTs as a conductive material and poly (acrylic acid) as a binder, *Int. J. Electrochem. Sci.*, 2023, **18**(8), 100217.
- 182 J. R. Choi, E. Kim, B.-I. Park, I. Choi, B.-H. Park, S.-B. Lee, J. H. Lee and S. Yu, Meringue-derived hierarchically porous carbon as an efficient polysulfide regulator for lithium-sulfur batteries, *J. Ind. Eng. Chem.*, 2022, **115**, 355–364.
- 183 F. Zhao, J. Xue, W. Shao, H. Yu, W. Huang and J. Xiao, Toward high-sulfur-content, high-performance lithium-



- sulfur batteries: Review of materials and technologies, *J. Energy Chem.*, 2023, **80**, 625–657.
- 184 J. Wang, H. Wang, S. Jia, Q. Zhao, Q. Zheng, Y. Ma, T. Ma and X. Li, Recent advances in inhibiting shuttle effect of polysulfide in lithium-sulfur batteries, *J. Energy Storage*, 2023, **72**, 108372.
- 185 F. Sultanov, A. Mentbayeva, S. Kalybekkyzy, A. Zhaisanova, S.-T. Myung and Z. Bakenov, Advances of graphene-based aerogels and their modifications in lithium-sulfur batteries, *Carbon*, 2023, **201**, 679–702.
- 186 K. Zhang, X. Li, L. Ma, F. Chen, Z. Chen, Y. Yuan, Y. Zhao, J. Yang, J. Liu, K. Xie and K. P. Loh, Fluorinated Covalent Organic Framework-Based Nanofluidic Interface for Robust Lithium–Sulfur Batteries, *ACS Nano*, 2023, **17**(3), 2901–2911.
- 187 T. Lin, H. Wang, X. Du, D. Zhang, Z. Zhang and G. Liu, A COF-coated MOF framework polysulfide barrier design for enhanced performance in lithium-sulfur batteries, *Electrochim. Acta*, 2022, **412**, 140156.
- 188 S. Khokhar, P. Chand and H. Anand, Recent advancements in Ni-MOF template derived electrode materials for supercapacitor application: A mini review, *Results Chem.*, 2024, **7**, 101298.
- 189 L. Guo, P. Hu and H. Wei, Development of supercapacitor hybrid electric vehicle, *J. Energy Storage*, 2023, **65**, 107269.
- 190 V. J. Ariyamparambil and B. Kandasubramanian, A mini-review on the recent advancement of electrospun MOF-derived nanofibers for energy storage, *Chem. Eng. J. Adv.*, 2022, **11**, 100355.
- 191 D. Cai, B. Liu, D. Wang, Y. Liu, L. Wang, H. Li, Y. Wang, C. Wang, Q. Li and T. Wang, Enhanced performance of supercapacitors with ultrathin mesoporous NiMoO₄ nanosheets, *Electrochim. Acta*, 2014, **125**, 294–301.
- 192 M. Saleem, F. Ahmad, M. Fatima, A. Shahzad, M. S. Javed, S. Atiq, M. A. Khan, M. Danish, O. Munir, S. M. B. Arif, U. Faryad, M. J. Shabbir and D. Khan, Exploring new frontiers in supercapacitor electrodes through MOF advancements, *J. Energy Storage*, 2024, **76**, 109822.
- 193 B. Shabbir, K. Jabbar, S. Manzoor, M. F. Ashiq, K. F. Fawy and M. N. Ashiq, Solvothermally designed Pr-MOF/Fe₂O₃ based nanocomposites for efficient electrocatalytic water splitting, *Heliyon*, 2023, **9**(10), e20261.
- 194 S. Kumar, S. Sekar, A. K. Kaliamurthy and S. Lee, Bifunctional rGO-NiCo₂S₄ MOF hybrid with high electrochemical and catalytic activity for supercapacitor and nitroarene reduction, *J. Mater. Res. Technol.*, 2021, **12**, 2489–2501.
- 195 Q. Wang, B. Xiong and J. Pan, Preparation of high porous carbon using Al-based MOFs and influence of dimethylformamide on morphological and electrochemical supercapacitor performances, *Int. J. Electrochem. Sci.*, 2022, **17**(6), 220671.
- 196 X. X. Liu, Q. He, Y. Wang, J. Wang, Y. Xiang, D. J. Blackwood, R. Wu and J. S. Chen, MOF-reinforced Co₉S₈ self-supported nanowire arrays for highly durable and flexible supercapacitor, *Electrochim. Acta*, 2020, **346**, 136201.
- 197 T. Ramachandran, S. S. Sana, K. D. Kumar, Y. A. Kumar, H. H. Hegazy and S. C. Kim, Asymmetric supercapacitors: Unlocking the energy storage revolution, *J. Energy Storage*, 2023, **73**, 109096.
- 198 X. Fu, W. Guo, L. Chen, G. Wang, Y. Liu, T. Gu, F. Yu and X. Guo, Coal-derived N,O co-doped mesoporous carbon as electrode material for high performance aqueous electric-double layer capacitors and zinc-ion hybrid supercapacitors, *Electrochim. Acta*, 2023, **439**, 141576.
- 199 S. Ghosh, J. Majhi, S. Sharma, K. Priya and A. Bandyopadhyay, A review on the development of electron and ion conductive polymer hydrogels and their composites for flexible and smart supercapacitors, *J. Energy Storage*, 2023, **74**, 109423.
- 200 P. Siwach, L. Gaba, S. Dahiya, R. Punia, A. S. Maan, K. Singh and A. Ohlan, Recent progress in conjugated polymers composites with metal-organic frameworks as electrode materials for supercapacitors, *Appl. Surf. Sci. Adv.*, 2024, **19**, 100555.
- 201 M. Shariq, K. Alshehri, S. Mohammed Bouzgarrou, S. Kashif Ali, Y. Alqurashi, K. F. Hassan and R. E. Azooz, Progress in development of MXene-based nanocomposites for supercapacitor application-A review, *FlatChem*, 2024, **44**, 100609.
- 202 A. P. Khedulkar, V. D. Dang, A. Thamilselvan, R.-a. Doong and B. Pandit, Sustainable high-energy supercapacitors: Metal oxide-agricultural waste biochar composites paving the way for a greener future, *J. Energy Storage*, 2024, **77**, 109723.
- 203 W. Du, Y.-L. Bai, J. Xu, H. Zhao, L. Zhang, X. Li and J. Zhang, Advanced metal-organic frameworks (MOFs) and their derived electrode materials for supercapacitors, *J. Power Sources*, 2018, **402**, 281–295.
- 204 L. M. Da Silva, R. Cesar, C. M. R. Moreira, J. H. M. Santos, L. G. De Souza, B. M. Pires, R. Vicentini, W. Nunes and H. Zanin, Reviewing the fundamentals of supercapacitors and the difficulties involving the analysis of the electrochemical findings obtained for porous electrode materials, *Energy Storage Mater.*, 2020, **27**, 555–590.
- 205 A. A. Moya, Nonlinear charge-voltage relationships in electric double layer capacitors performing under constant load resistance, *J. Energy Storage*, 2023, **71**, 108136.
- 206 W. Wang, C. Yang, D. Han, S. Yu, W. Qi, R. Ling and G. Liu, Ni₃S₂/Ni₂O₃ heterojunction anchored on N-doped carbon nanosheet aerogels for dual-ion hybrid supercapacitors, *J. Colloid Interface Sci.*, 2024, **654**, 709–718.
- 207 S. Mahala, K. Khosravinia and A. Kiani, Unwanted degradation in pseudocapacitors: Challenges and opportunities, *J. Energy Storage*, 2023, **67**, 107558.
- 208 S. K. Lichhavi, A. K. Srivastava and S. K. Jha, Elucidation of intercalation-pseudocapacitor mechanism in Binder-free Bi₂S₃@Ni foam electrodes towards high-performance supercapattery, *Electrochim. Acta*, 2023, **456**, 142438.
- 209 D. Gao, Z. Luo, C. Liu and S. Fan, A survey of hybrid energy devices based on supercapacitors, *Green Energy Environ.*, 2023, **8**(4), 972–988.



- 210 P.-y. Hung, H. Zhang, H. Lin, Q. Guo, K.-t. Lau and B. Jia, Specializing liquid electrolytes and carbon-based materials in EDLCs for low-temperature applications, *J. Energy Chem.*, 2022, **68**, 580–602.
- 211 C. Jiang and Z. Zou, Waste polyurethane foam filler-derived mesoporous carbons as superior electrode materials for EDLCs and Zn-ion capacitors, *Diamond Relat. Mater.*, 2020, **101**, 107603.
- 212 Ö. Taş, Z. Kudaş and D. Ekinçi, Electrochemical performance of diazonium-generated carbon films for electrochemical double-layer capacitors (EDLCs), *Diamond Relat. Mater.*, 2023, **138**, 110227.
- 213 H. Wang, D. Pei, Y. Li, Z. Zhang, S. Wan, Z. Wang, M. Yu and H. Lu, Unveiling the influential factors and inhibition strategies of the electrodeposition behavior on the negative electrode in aqueous nickel-carbon supercapacitors, *J. Energy Storage*, 2024, **81**, 110297.
- 214 C. Zhu, J. Yan and X. Fang, N/O codoped carbons with enriched micropore for high-energy supercapacitor in a wide temperature range, *J. Energy Storage*, 2024, **84**, 110988.
- 215 J. Liu, D. Tang, W. Hou, D. Ding, S. Yao, Y. Liu, Y. Chen, W. Chi, Z. Zhang, M. Ouyang and C. Zhang, Conductive polymer electrode materials with excellent mechanical and electrochemical properties for flexible supercapacitor, *J. Energy Storage*, 2023, **74**, 109329.
- 216 T. Yu, S. Li, L. Zhang, F. Li, H. Pan and D. Zhang, Design and construction of conductive polymer PPy anchored NiCo bi-metal sulfide composite electrode materials for high-performance hybrid supercapacitor and electrochemical hydroquinone sensor, *J. Energy Storage*, 2024, **87**, 111427.
- 217 J. Wan, R. Hu, J. Li, S. Mi, J. Xian, Z. Xiao, Z. Liu, A. Mei, S. Xu, M. Fan, H. Jiang, Q. Zhang, H. Liu and W. Xu, A universal construction of robust interface between 2D conductive polymer and cellulose for textile supercapacitor, *Carbohydr. Polym.*, 2022, **284**, 119230.
- 218 Raissa, N. L. Wulan Septiani, S. Wustoni, F. Failamani, N. Wehbe, M. Eguchi, H. Nara, S. Inal, V. Suendo and B. Yulianto, Revealing the effect of cobalt content and ligand exchange in the bimetallic Ni–Co MOF for stable supercapacitors with high energy density, *J. Power Sources*, 2024, **603**, 234423.
- 219 B. Li, M. Ashrafizadeh and T. Jiao, Biomedical application of metal-organic frameworks (MOFs) in cancer therapy: Stimuli-responsive and biomimetic nanocomposites in targeted delivery, phototherapy and diagnosis, *Int. J. Biol. Macromol.*, 2024, **260**, 129391.
- 220 D. Wachholz Junior, B. M. Hryniewicz and L. Tatsuo Kubota, Advanced Hybrid materials in electrochemical sensors: Combining MOFs and conducting polymers for environmental monitoring, *Chemosphere*, 2024, **352**, 141479.
- 221 K. Xia, F. Yi, L. Zheng, A. Gao, D. Shu and J. Ling, 2D coordination unsaturated Ni-MOFs hierarchical nanosheets with internal electric fields for high-performance hybrid supercapacitors, *J. Electroanal. Chem.*, 2023, **939**, 117464.
- 222 A. H. Anwer, M. M. Zubair, F. Mashkooor, A. Benamor, I. Hasan, M. Shoeb and C. Jeong, Enhancing the electrochemical performance of hybrid supercapacitors with in-situ grown ultrasound-mediated heterostructure bi-metallic and dual-linker MOF nanoarchitecture by harnessing charge storage mechanisms, *J. Alloys Compd.*, 2024, **970**, 172512.
- 223 J. Acharya, B. Pant, G. P. Ojha, J. Yoo and M. Park, Revealing the potential of hierarchical heterostructure of tri-metallic selenide and MOFs etched layered hydroxide dodecahedron laminated with rGO-Ni foam for a hybrid supercapacitor applications, *J. Energy Storage*, 2023, **68**, 107841.
- 224 P. Sivakumar, L. Kulandaivel, J. Park, C. J. Raj, R. Manikandan and H. Jung, MOF-derived flower-like ZnCo₂O₄/ZnO nanoarchitecture as a high-performance battery-type redox-active electrode material for hybrid supercapacitor applications, *J. Alloys Compd.*, 2023, **952**, 170042.
- 225 N. Kitchamsetti and D. Kim, High performance hybrid supercapacitor based on hierarchical MOF derived CoFe₂O₄ and NiMn₂O₄ composite for efficient energy storage, *J. Alloys Compd.*, 2023, **959**, 170483.
- 226 Y. Yang, X. Huang, C. Sheng, Y. Pan, Y. Huang and X. Wang, In-situ formation of MOFs derivatives CoSe₂/Ni₃Se₄ nanosheets on MXene nanosheets for hybrid supercapacitor with enhanced electrochemical performance, *J. Alloys Compd.*, 2022, **920**, 165908.
- 227 Y. Xie, H. Zhang, K. Zhang, R. Liu, Y. Sun, X. Gao, H. Bai, F. Yao and H. Yue, In-situ Ni-doped V-MOF ultra-thin nanosheet arrays on Ni foam for high-performance hybrid supercapacitors, *Electrochim. Acta*, 2024, **477**, 143784.
- 228 P. Zhou, J. Wan, X. Wang, K. Xu, Y. Gong and L. Chen, Nickel and cobalt metal-organic-frameworks-derived hollow microspheres porous carbon assembled from nanorods and nanospheres for outstanding supercapacitors, *J. Colloid Interface Sci.*, 2020, **575**, 96–107.
- 229 Q. Li, Z. Dai, J. Wu, W. Liu, T. Di, R. Jiang, X. Zheng, W. Wang, X. Ji, P. Li, Z. Xu, X. Qu, Z. Xu and J. Zhou, Fabrication of ordered macro-microporous single-crystalline MOF and its derivative carbon material for supercapacitor, *Adv. Energy Mater.*, 2020, **10**(27), 1903750.
- 230 Y. Ping, S. Yang, J. Han, X. Li, H. Zhang, B. Xiong, P. Fang and C. He, N-self-doped graphitic carbon aerogels derived from metal-organic frameworks as supercapacitor electrode materials with high-performance, *Electrochim. Acta*, 2021, **380**, 138237.
- 231 X. Li, J. Li, Y. Zhang, P. J. C. Zhao, S. A. Physicochemical and E. Aspects, Synthesis of Ni-MOF derived NiO/rGO composites as novel electrode materials for high performance supercapacitors, *Colloids Surf., A*, 2021, **622**, 126653.
- 232 S. Shin and M. W. Shin, Nickel metal-organic framework (Ni-MOF) derived NiO/C@CNF composite for the



- application of high performance self-standing supercapacitor electrode, *Appl. Surf. Sci.*, 2021, **540**, 148295.
- 233 S. Xu, R. Liu, X. Shi, Y. Ma, M. Hong, X. Chen, T. Wang, F. Li, N. Hu and Z. Yang, A dual CoNi MOF nanosheet/nanotube assembled on carbon cloth for high performance hybrid supercapacitors, *Electrochim. Acta*, 2020, **342**, 136124.
- 234 K. Chhetri, T. Kim, D. Acharya, A. Muthurasu, B. Dahal, R. M. Bhattarai, P. C. Lohani, I. Pathak, S. Ji, T. H. Ko and H. Y. Kim, Hollow Carbon Nanofibers with Inside-outside Decoration of Bi-metallic MOF Derived Ni-Fe Phosphides as Electrode Materials for Asymmetric Supercapacitors, *Chem. Eng. J.*, 2022, **450**, 138363.
- 235 J. Khan, N. Shakeel, S. Alam, M. Z. Iqbal, Z. Ahmad and K. Yusuf, Exploring the potency of EDTA-based Ni-Co-MOF nanospheres for highly durable battery-supercapacitor hybrids, *Electrochim. Acta*, 2024, **486**, 143970.
- 236 J.-E. Zhou, Z. Xu, Y. Li, X. Lin, Y. Wu, A. Zeb and S. Zhang, Oxygen-deficient metal-organic framework derivatives for advanced energy storage: Multiscale design, application, and future development, *Coord. Chem. Rev.*, 2023, **494**, 215348.
- 237 B. Liu, S. Sun, R. Jia, H. Zhang, X. Zhu, C. Zhang, J. Xu, T. Zhai and H. Xia, Oxygen-Deficient Homo-Interface toward Exciting Boost of Pseudocapacitance, *Adv. Funct. Mater.*, 2020, **30**(14), 1909546.
- 238 X. Wei, H. Wu and L. Li, 3D N-doped carbon continuous network supported P-doped ZnCo₂O₄ nanosheets with rich oxygen vacancies for high-performance asymmetric pseudocapacitor, *J. Alloys Compd.*, 2021, **861**, 158544.
- 239 R. Ahmad, U. A. Khan, N. Iqbal and T. Noor, Zeolitic imidazolate framework (ZIF)-derived porous carbon materials for supercapacitors: an overview, *RSC Adv.*, 2020, **10**(71), 43733–43750.
- 240 Y. A. Kumar, G. R. Reddy, T. Ramachandran, D. K. Kulurumotlakatla, H. S. M. Abd-Rabboh, A. A. Abdel Hafez, S. S. Rao and S. W. Joo, Supercharging the future: MOF-2D MXenes supercapacitors for sustainable energy storage, *J. Energy Storage*, 2024, **80**, 110303.
- 241 C. Shi, M. Wan, Z. Hou, X. Qian, H. Che, Y. Qin, J. Jing, J. Li, F. Ren, B. Yu and N. Hong, Co-MOF@MXene hybrids flame retardants for enhancing the fire safety of thermoplastic polyurethanes, *Polym. Degrad. Stab.*, 2022, **204**, 110119.
- 242 K. Jayaramulu, M. Horn, A. Schneemann, H. Saini, A. Bakandritsos, V. Ranc, M. Petr, V. Stavila, C. Narayana, B. Scheibe, S. Kment, M. Otyepka, N. Motta, D. Dubal, R. Zbořil and R. A. Fischer, Covalent Graphene-MOF Hybrids for High-Performance Asymmetric Supercapacitors, *Adv. Mater.*, 2021, **33**, 2004560.
- 243 L. He, J. Liu, L. Yang, Y. Song, M. Wang, D. Peng, Z. Zhang and S. Fang, Copper metal-organic framework-derived CuOx-coated three-dimensional reduced graphene oxide and polyaniline composite: Excellent candidate free-standing electrodes for high-performance supercapacitors, *Electrochim. Acta*, 2018, **275**, 133–144.
- 244 M. Yao, X. Zhao, J. Zhang, W. Tan, J. Luo, J. Dong and Q. Zhang, Flexible all-solid-state supercapacitors of polyaniline nanowire arrays deposited on electrospun carbon nanofibers decorated with MOFs, *Nanotechnology*, 2019, **30**(8), 085404.
- 245 F. B. Ajdari, E. Kowsari and A. Ehsani, Ternary nanocomposites of conductive polymer/functionalized GO/MOFs: Synthesis, characterization and electrochemical performance as effective electrode materials in pseudocapacitors, *J. Solid State Chem.*, 2018, **265**, 155–166.
- 246 J. Xia, R. Wang, C. Qian, K. Sun, H. Liu, C. Guo, J. Li, F. Yu and W. Bao, Supercapacitors of Nanocrystalline Covalent Organic Frameworks—A Review, *Crystals*, 2022, **12**(10), 1350.
- 247 H. Shanavaz, N. Kannanugu, D. Kasai, K. Y. Kumar, M. S. Raghu, M. K. Prashanth, M. A. Khan, B.-H. Jeon and E. Linul, Covalent organic frameworks as promising materials: Review on synthetic strategies, topology and application towards supercapacitors, *J. Energy Storage*, 2023, **71**, 108006.
- 248 Y. Meng, Y. Luo, J.-L. Shi, H. Ding, X. Lang, W. Chen, A. Zheng, J. Sun and C. Wang, 2D and 3D Porphyrinic Covalent Organic Frameworks: The Influence of Dimensionality on Functionality, *Angew. Chem., Int. Ed.*, 2020, **59**(9), 3624–3629.
- 249 J. Li, X. Jing, Q. Li, S. Li, X. Gao, X. Feng and B. Wang, Bulk COFs and COF nanosheets for electrochemical energy storage and conversion, *Chem. Soc. Rev.*, 2020, **49**(11), 3565–3604.
- 250 S. O. Akinawo, Covalent organic frameworks: Design, synthesis, characterization, and applications, *ChemPhysMater*, 2024, **3**(1), 36–63.
- 251 S. Umezawa, T. Douura, K. Yoshikawa, Y. Takashima, M. Yoneda, K. Gotoh, V. Stolojan, S. R. P. Silva, Y. Hayashi and D. Tanaka, Supercapacitor electrode with high charge density based on boron-doped porous carbon derived from covalent organic frameworks, *Carbon*, 2021, **184**, 418–425.
- 252 M. Ibrahim, H. N. Abdelhamid, A. M. Abuelftooh, S. G. Mohamed, Z. Wen and X. Sun, Covalent organic frameworks (COFs)-derived nitrogen-doped carbon/reduced graphene oxide nanocomposite as electrodes materials for supercapacitors, *J. Energy Storage*, 2022, **55**, 105375.
- 253 Y. Yusran, Q. Fang and V. Valtchev, Electroactive Covalent Organic Frameworks: Design, Synthesis, and Applications, *Adv. Mater.*, 2020, **32**(44), 2002038.
- 254 X. Guan, Y. Ma, H. Li, Y. Yusran, M. Xue, Q. Fang, Y. Yan, V. Valtchev and S. Qiu, Fast, Ambient Temperature and Pressure Ionothermal Synthesis of Three-Dimensional Covalent Organic Frameworks, *J. Am. Chem. Soc.*, 2018, **140**(13), 4494–4498.

