

ChemComm

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

COMMUNICATION

A self-assembling induced emission system constructed by host-guest interaction of AIE-active building blocks

Cite this: DOI: 10.1039/x0xx00000x

Wei Bai,^a Zhaoyang Wang,^a Jiaqi Tong,^a Ju Mei,^{ab} Anjun Qin,^c Jing Zhi Sun^{*ad} and Ben Zhong Tang^{*abc}

Received 00th January 2012,
Accepted 00th January 2012

DOI: 10.1039/x0xx00000x


www.rsc.org/

Dibenzo[24]crown-8 (host) and benzylamine (guest) modified tetra-phenylethene are prepared and used to construct supramolecular polymer, which demonstrates the merits of reversible assembling-disassembling and tunable aggregation-induced emission by acid/base treatments.

Aggregation-induced emission (AIE) has attracted great attention in the research areas including chemo- and biosensors, photo-electronic materials, and stimuli-responsive elements.¹ Tetraphenylethene (TPE) is a typical AIE luminogen (AIE-gen). It emits faintly in dilute solution but becomes highly emissive in aggregate state. TPE has been widely used to construct AIE-active materials due to its good AIE performance and easy preparation.² As to the underlying mechanisms, the restriction of intramolecular rotation (RIR), among all the possible theories, is the best acceptable one and has been proven by different methods.^{1c,3} The RIR process is briefly described as following. In solution, the rotations of the phenyl groups of TPE (see the blue moiety in Scheme 1) are active. In kinetics, the rate of the intramolecular rotations are on femto-second level, which is faster than the irradiative decay rate of the excited state. As a result, the emission of the excited TPE molecules is quenched. In aggregate state, the intramolecular rotations are restricted, thus the non-irradiative channels are blocked and the emission can be observed. Based on the RIR mechanism, a series of novel AIE-active compounds have been designed and constructed, and their AIE characteristics together with other properties are studied.¹⁻³

Up to now, developing more AIE-active systems and opening wider application fields are the main topics. During the past decades, supramolecular chemistry is one of the hottest research areas. Supramolecular systems are constructed from secondary bonds (*i.e.* hydrogen bonds, coordinating bonds, π - π stacking, host-guest interactions, *etc.*), rather than covalent bonds, among the building blocks. This trait bestows supramolecular systems with unique advantages such as good degradability, stimuli-responsiveness and self-healing properties.^{4,5} Among a variety of supramolecular

systems, The host-guest recognition of crown-ether to different guest species, ranging from potassium ions to ammonium and paraquat derivatives has received considerable investigations.⁴ It is noted that all these processes are highly dynamic. Considering that the restriction and emancipation of the intramolecular rotations of an AIE molecule are also a dynamic process, the correlation between supramolecular system and AIE will be a significant attempt.⁵ Herein, we report our concept-proof work by using TPE as the AIE-gen and the host-guest interaction between dibenzo[24]crown-8 and benzylamino moieties as the driving force to construct a self-assembling induced emission system.



Scheme 1. Synthetic routes to TPE-DBA and TPE-DDBC.




Fig. 1 Fluorescence (FL) spectra of (A) TPE-DBA and (C) TPE-DDBC; and plots of peak FL intensity of (B) TPE-DBA and (D) TPE-DDBC in THF/water mixtures with different water fractions. Concentrations of TPE-DBA and TPE-DDBC: 10^{-5} M, λ_{ex} for TPE-DBA and TPE-DDBC: 360 nm.

Based on the above-mentioned idea, we designed and synthesized two TPE-derivatives, i.e. TPE-DDBC and TPE-DBA (Scheme 1 and inset of Fig. 1), which perform as the host and guest molecules due to their bearing dibenzo[24]crown-8 moieties and benzylamine groups, respectively. The details of syntheses can be found in electronic supplementary information (ESI). The target compound TPE-DBA including both of the *E/Z*- isomers was prepared from dialdehyde-functionalized TPE utilising a Schiff's base reaction followed by a reduction of imine groups in one pot in a yield of 68%. Dibenzo[24]-crown-8 was brominated by ceric ammonium nitrate with sodium bromide, and the product 2-bromo-dibenzo[24]crown-8 was undergone a Suzuki coupling reaction to attached onto TPE. Characterizations of two target compounds were described in ESI (Fig. S1-S9, Scheme S1 and S2).

The AIE activity of the building blocks of TPE-DBA and TPE-DDBC were examined and the results are shown in Fig. 1. For TPE-DBA, it shows no emission in dilute tetrahydrofuran (THF) solution when excited at a wavelength of 360 nm (λ_{ex}), which is close to the maximum of TPE-DBA's UV-vis absorption spectrum (Fig. S10). It keeps non-emissive in the THF/water mixture solvent with the water fraction (f_w , by volume) being up to 80%. When the f_w reaches to 90%, the system becomes highly emissive and the emission peak (λ_{em}) appears at around 485 nm. This λ_{em} is nearly identical to that of TPE itself,⁷ because the conjugation of TPE-DBA is no larger than TPE, thanks to the blocking role of the methylene group between TPE and the benzylamino group. In addition, the water fraction to induce the aggregation for TPE-DBA is higher than that for most AIE molecules,^{2,5,6} due to the enhancement of the hydrophilicity contributed from the secondary amino groups.

Since both of the building blocks own AIE characteristics, we expect the AIE trait will be inherited by the supramolecular system. The working scheme is illustrated as Fig. 2A. The secondary amines in TPE-DBA are protonated by adding acid into the solution (Scheme S3), and the protonated amines are capable to recognize the crown ethers thereby the ionic TPE-DBA and TPE-DDBC molecules interaction. The non-covalent interaction of the host will lock on the




Fig. 2 (A) An illustration of the reversible self-assembly and disassembly between TPE-DBA and TPE-DDBC via host-guest interaction. (B) FL spectra of TPE-DBA and TPE-DDBC in THF solution treated with HCl and NaOH solutions repeatedly. (C) Plots of the changes in peak intensity and wavelength in three acid/base treating cycles. Concentrations of HCl and NaOH: 1.0 M in H₂O; Concentrations of TPE-DBA and TPE-DDBC: 5×10^{-4} M in THF; λ_{ex} : 360 nm. Letters A, B and N stand for acid and base treatments and neutral THF solution. 1, 2 and 3 stand for the number of acid/base cycles.

rotations of guest benzylamine groups, which involve with the phenyl rotations of TPE units. According to the RIR mechanism, the FL from TPE-DBA will be turned on, as observed for boronic acid modified TPEs and β -cyclodextrin and TPE-containing metal organic frameworks.⁷ Meanwhile, the emission from the TPE moiety in TPE-DDBC can also be partially initiated, due to the damped intramolecular phenyl rotations caused by the formation of the supramolecular macro-molecules. The acidification induced assemblies will disassemble when treated with base, because deionized amines cannot be hosted by crown ethers and the restriction effect disappears accordingly.

Guided by this assumption, we monitored the FL changes upon repeatedly adding acid and base into THF solution containing TPE-DBA and TPE-DDBC in 1:1 mole ratio. The experimental data collected in a typical run are presented in Fig. 2B and 2C. In neutral THF solution, two compounds are unable to aggregate, so that no FL could be detected. When 10 μ L HCl aqueous solution was added into 5 mL THF solution, white precipitate appeared after sonicating for 10 min and the system emitted bright blue FL under 365-nm UV-light illumination (Fig. 3). Afterwards, the mixture was treated with 10 and 20 μ L NaOH solution to neutralize HCl and turned solution to basic, the FL was gone with the disappearance of precipitate. The FL "turn-on/turn-off" behaviours are reversible and can be repeated, as demonstrated in Fig. 2B.

The origin of the FL is ascribed to the formation of the insoluble assembly, which is induced by the host-guest interaction, but not to the insolubility of TPE-DBA and TPE-DDBC induced by water addition. In fact, f_w in the mixture is very small. Specifically, the volume of THF solution used in the experiment was 5 mL, while the volume of HCl solution or NaOH solution was only 10 ~ 20 μ L each time. As a result, after 3 cycles of treatments, the volume of water should be 100 ~ 110 μ L. Compared with the volume of THF, the water fraction is as low as 2% eventually. As indicated by the results in Fig. 1, such low water fraction cannot lead to the aggregation of TPE-DBA and TPE-DDBC. It is noted in Fig. 2B that the emission became stronger and the emission peak blue-shifted after every cycle. This "stepwise" FL amplification can be associated with the stepwise addition of water in the mixture, which leads the hydrophobic TPE moieties to tighter packing thus induced stronger

emission, according to the RIR mechanism. The blue-shift may be associated with the formation of higher ordered microstructure in the fluorescent precipitate. It has been proved that in crystal or in highly ordered structure, TPE moiety takes a more twisted conformation.^{5,6}

To get further understanding of the observed phenomenon, the microstructures formed in the supramolecular systems were checked with scanning electron microscope (SEM) technique. Fig. 3 exhibits the SEM images of samples taken from the TPE-DBA/TPE-DDBC mixtures treated with acid and base for the first three cycles. Without the protonation of the secondary amine groups, the self-assembling could not occur, and the precipitate obtained by solvent evaporation showed irregularly shaped morphology (Fig. 3A). Upon acidification, the host-guest recognition occurred and resulted in the formation of supramolecular polymers, which precipitated in the solution due to the rigid and hydrophobic TPE units and the increased molecular weight. The morphology is characterized by microscopic wires in diameter of about 100 nm (Fig. 3B). Several wires twisted together to make a bunch. Such string-like networks were often observed in the supramolecular organogels.⁸ Strong FL comes from the organized microstructures here. When the precipitate was treated with base, the micro-networks collapse, featureless morphology was observed again under the surveillance of SEM (Fig. 3C). Similar morphological changes took place in each acid/base treatment cycle (Fig. 3A-3F and S12-S17). A distinction is that the width of the microwires became larger (from ~100 nm to over 500 nm) as the treatment cycle increased. The microscopic morphology changes are responsible for the FL enhancement and blue-shift.




Fig. 3 SEM images of the morphologies (scale bar: 500 nm) for the microstructures formed in the mixture of TPE-DBA and TPE-DDBC (1:1, mole ratio, in THF) treated with HCl/NaOH solutions. Shown in the bottom row are the corresponding FL images. (A): neutral THF solution; (B), (D) and (F): treated with 1.0 M HCl; (C) and (E): treated with 1.0 M NaOH following steps (B) and (D), respectively.

In summary, we have demonstrated a novel self-assembling induced emission (SAIE) system. The host-guest interaction initiated the “polymerization” of the TPE-containing building blocks and the RIR process, and turned on the emission of the AIE-gen. The breaking of the non-covalent bonds eliminated the restriction and turned the emission off. The assembling/disassembling processes accompanied by FL turn-on/off are dynamic, reversible and tuneable by treating the system with acid/base. Yet, Cl⁻ can form a strongly-bonded counter-ion pair with a protonated secondary amine and PF₆⁻ or BF₄⁻ may be a better candidate of anion to manifest better host-guest interaction. As a concept-proof work, the existing results have offered sufficient evidences to support the SAIE idea. Host-guest interaction is only one of various supramolecular interactions and AIE-gens can be chemically modified to accommodate different situations, thus the present concept is helpful and useful to construct more supramolecular AIE systems and to fabricate novel chemo-/biosensors and stimuli-responsive materials with FL emission property.

This work was financially supported by 973 Program of China (2013CB834704), the Research Grants Council of Hong

Kong (604711, 602212 and HKUST2/CRF/10). J. Z. Sun thanks the support of Jiangsu Key Lab of Advanced Functional Polymer Design and Application (Soochow University).


Notes and references

- ^a MOE Key Laboratory of Macromolecular Synthesis and Functionalization, Department of Polymer Science and Engineering, Zhejiang University, Hangzhou 310027, China. Email: sunjz@zju.edu.cn.
^b Department of Chemistry, Institute for Advanced Study, Institute of Molecular Functional Materials, and State Key Laboratory of Molecular Neuroscience, The Hong Kong University of Science & Technology, Clear Water Bay, Kowloon, Hong Kong China. Email: tangbenz@ust.hk.
^c Guangdong Innovative Research Team, State Key Laboratory of Luminescent Materials and Devices, South China University of Technology, Guangzhou 510640, China.

Electronic Supplementary Information (ESI) available: Synthesis and characterization, materials, procedures of all experiments; additional absorption/emission spectra; SEM images. See DOI: 10.1039/c000000x/

- (a) Y. Hong, J. W. Y. Lam and B. Z. Tang, *Chem. Soc. Rev.*, 2011, **40**, 5361. (b) Z. Chi, X. Zhang, B. Xu, X. Zhou, C. Ma, Y. Zhang and J. Xu, *Chem. Soc. Rev.*, 2012, **41**, 3878. (c) J. Mei, Y. Hong, J. W. Y. Lam, A. Qin, Y. Tang and B. Z. Tang, *Adv. Mater.*, 2014, **26**, 5429.
- (a) J. Wang, J. Mei, R. Hu, J. Z. Sun, A. Qin and B. Z. Tang, *J. Am. Chem. Soc.*, 2012, **134**, 9956. (b) E. P. J. Parrott, N. Y. Tan, R. Hu, A. Zeitler, B. Z. Tang and E. Pickwell-MacPherson, *Mater. Horiz.*, 2014, **1**, 251.
- (a) L. Brunsveld, B. J. B. Folmer, E. W. Meijer and R. P. Sijbesma, *Chem. Rev.*, 2001, **101**, 4071. (b) T. Ogoshi and T. Yamagishi, *Chem. Commun.*, 2014, **50**, 4776.
- (a) B. Zheng, F. Wang, S. Dong and F. Huang, *Chem. Soc. Rev.*, 2012, **41**, 1621. (b) T. Kakuta, Y. Takashima and A. Harada, *Macromolecules*, 2013, **46**, 4575. (c) X. Yan, T. R. Cook, J. B. Pollock, P. Wei, Y. Zhang, Y. Yu, F. Huang and P. J. Stang, *J. Am. Chem. Soc.*, 2014, **136**, 4460.
- (a) X. Wang, J. Hu, T. Liu, G. Zhang and S. Liu, *J. Mater. Chem.*, 2012, **22**, 8622. (b) Z. Zhao, J. W. Y. Lam and B. Z. Tang, *Soft Matter*, 2013, **9**, 4564. (c) P. Wang, X. Yan and F. Huang, *Chem. Commun.*, 2014, **50**, 5017. (d) G. Liang, J. W. Y. Lam, W. Qin, J. Li, N. Xie and B. Z. Tang, *Chem. Commun.*, 2014, **50**, 1725.
- (a) Y. Dong, J. W. Y. Lam, A. Qin, J. Liu, Z. Li and B. Z. Tang, *Appl. Phys. Lett.*, 2007, **91**, 011111. (b) Q. Zhao, S. Zhang, Y. Liu, J. Mei, S. Chen, P. Lu, A. Qin, Y. Ma, J. Z. Sun and B. Z. Tang, *J. Mater. Chem.*, 2012, **22**, 7387. (c) Z. Zhao, J. W. Y. Lam and B. Z. Tang, *J. Mater. Chem.*, 2012, **22**, 23726. (d) J. Ma, T. Lin, X. Pan and W. Wang, *Chem. Mater.*, 2014, **26**, 4221.
- (a) Y. Liu, A. Qin, X. J. Chen, X. Y. Shen, L. Tong, R. Hu, J. Z. Sun and B. Z. Tang, *Chem. Eur. J.*, 2011, **17**, 14736. (b) N. B. Shustova, T. C. Ong, A. F. Cozzolino, V. K. Michaelis, R. G. Griffin, M. Dinca, *J. Am. Chem. Soc.*, 2012, **134**, 10561.
- (a) X. Yan, D. Xu, X. Chi, J. Chen, S. Dong, X. Dong, Y. Yu and F. Huang, *Adv. Mater.*, 2012, **24**, 362. (b) S. Dong, B. Zheng, D. Xu, X. Yan, M. Zhang and F. Huang, *Adv. Mater.*, 2012, **24**, 3191.

Table of content



Benzylamino- (guest) and dibenzo[24]crown-8 (host) modified tetraphenylethenes (AIE-gens) are prepared and used to construct supramolecular polymer exhibiting the merits of reversible assembling-disassembling and tunable aggregation-induced emission by acid/base treatments.