

# Dalton Transactions

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

*Accepted Manuscripts* are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

## ARTICLE

# Revised crystal structure and luminescent properties of gadolinium oxyfluoride $\text{Gd}_4\text{O}_3\text{F}_6$ doped with $\text{Eu}^{3+}$ ions

Cite this: DOI: 10.1039/x0xx00000x

Received 00th January 2012,

Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

Tomasz Grzyb,<sup>a</sup> Rafal J. Wiglusz,<sup>b</sup> Vitali Nagirnyi,<sup>c</sup> Aleksei Kotlov<sup>d</sup> and Stefan Lis<sup>a</sup>

The structure of gadolinium oxyfluoride nanoparticles was revised. Extensive studies including X-ray diffraction and Rietveld refinement as well as Fourier transform infrared spectroscopy and Raman spectroscopy confirmed the monoclinic  $P 1 2/c 1$  crystal structure of  $\text{Gd}_4\text{O}_3\text{F}_6$ . Morphological analysis using transmission electron microscopy showed nanocrystallinity of the materials prepared via the sol-gel Pechini's method. The luminescent properties of the prepared materials with different concentrations of  $\text{Eu}^{3+}$  ions were characterized by the emission spectroscopy. The phosphors obtained were investigated in the vacuum ultraviolet range using synchrotron radiation. The Judd–Ofelt parameters ( $\Omega_2$ ,  $\Omega_4$ ) and emission efficiencies  $\eta$  were calculated and discussed in detail.

## Introduction

The research in the area of rare earth oxyfluorides (REOF) is thriving not only through the rich structural varieties observed in the materials but also through the widely varying luminescence properties, that promise potential applications.<sup>1–15</sup> The structural properties of REOF were mostly investigated by Zachariassen in the 1950s.<sup>16</sup> It has been determined that as a result of solid state reaction between rare earth fluorides and their oxides at high temperature, oxyfluorides are formed. They crystallize in two different phases, tetragonal and rhombohedral. Unlike rhombohedral oxyfluorides, the ones with the tetragonal crystal structure suffer from instability and form usually nonstoichiometric compounds. Their general formula is  $\text{RE}_n\text{F}_{3-2n}$ ,  $0.7 < n < 1$ .<sup>16</sup> A high similarity between  $\text{F}^-$  and  $\text{O}^{2-}$  ionic radii is mainly responsible for the variations in the tetragonal phase. These ions can substitute for each other in the crystal structure. The crystallographic structure of YOF and LaOF can be obtained as a result of a tetragonal or rhombohedral deformation of the regular cubic elementary crystal cell of  $\text{CaF}_2$ . Further research has brought about a better understanding of other lanthanide oxyfluoride systems, giving detailed information about their crystallography.<sup>17–19</sup>

Besides tetragonal and rhombohedral also cubic form has been obtained as a result of phase transition from their rhombohedral forms at high temperature.<sup>20,21</sup> The main crystallographic space groups assigned to REOF are: tetragonal

$P_4/nmm$  and rhombohedral  $R\bar{3}m$ . In the tetragonal structure,  $\text{RE}^{3+}$  ions occupy sites with  $C_{4v}$  symmetry, whereas in the rhombohedral structure, the local symmetry of  $\text{RE}^{3+}$  is  $C_{3v}$ .<sup>2</sup>

The more accurate analysis of nonstoichiometric oxyfluorides has shown higher than expected complexity of these materials.<sup>22–24</sup> The oxyfluorides of the composition of  $\text{RE}(\text{O},\text{F})_{2+\delta}$ , where  $0.4 \geq \delta \geq 0$ , crystallize in a tetragonal form, however for  $\text{RE}_n\text{O}_{n-1}\text{F}_{n+2}$ , where  $5 \leq n \leq 9$ ,  $\text{RE} = \text{Y}, \text{Sm} - \text{Lu}$ , the orthorhombic crystal structure is more stable and probable.

The crystallographic data for gadolinium oxyfluoride are incomplete and this compound requires additional studies. Up to now, the tetragonal structure has been assigned to  $\text{Gd}_4\text{O}_3\text{F}_6$  only in one scientific article, however there no data have been given about its crystallographic space group.<sup>25</sup> As this compound, similarly as other rare earth oxyfluorides, could be used as a host for luminescent  $\text{Ln}^{3+}$  ions (where  $\text{Ln}^{3+} = \text{Eu}^{3+}, \text{Yb}^{3+}/\text{Er}^{3+}$ , etc.),<sup>13,15,11,9</sup> there is a need to know its structure and determine the crystallographic properties.

Tetragonal oxyfluorides of the formula  $\text{RE}_n\text{F}_{3-2n}$ ,  $0.7 < n < 1$ , contain fluorine  $\text{F}^-$  ions in the interstitial sites in a crystal structure derived from that of fluorite  $\text{CaF}_2$ .<sup>16</sup> Takashima et al. proposed a different crystal structure for the binary rare earth oxyfluorides,  $\text{RE}^{\text{I}}_2\text{RE}^{\text{II}}_2\text{O}_3\text{F}_6$ , where  $\text{RE}^{\text{I}} = \text{La}, \text{Nd}$ ,  $\text{RE}^{\text{II}} = \text{Y}, \text{Eu}, \text{Gd}$ . In the presented studies, concerning mainly the ionic conductivity of oxyfluorides, a monoclinic crystal system of  $P 2/c$  space group is reported.<sup>26–31</sup> The assignment of a tetragonal structure to binary rare earth

oxyfluorides results in a discrepancy in the positions of XRD reflections with the reference pattern. Also the shape of XRD peaks recorded, their intensity and the ratio between them are in disagreement with the theoretical pattern. Additionally, the presence of a weak peak at  $33.84^\circ 2\theta$  could not be attributed to any of crystallographic planes. A monoclinic structure could be considered as a slightly distorted tetragonal lattice derived from the fluorite structure. The refinement with the structural parameters of a monoclinic crystal system allowed us to solve the structure of the  $\text{Gd}_4\text{O}_3\text{F}_6$  material. The  $P2/c$  monoclinic crystal system was assigned as the most probable for this compound. The presented results show that the positions of ions in the  $\text{Gd}_4\text{O}_3\text{F}_6$  crystallographic lattice are very similar to those in the tetragonal structure. Hence, the  $\text{Gd}_4\text{O}_3\text{F}_6$  structure can be treated as pseudo-tetragonal.

Luminescence properties of lanthanide ions ( $\text{Ln}^{3+}$ ) are well known and widely studied because of their narrow line-width emission bands, large Stokes shifts, high quantum yields, long lifetimes and photostability.<sup>32–37</sup> The presence of (Gd,Eu)-F and (Gd,Eu)-O bonds in the  $\text{Eu}^{3+}$ -doped oxyfluorides can increase absorption in the vacuum ultraviolet (VUV) range. This property is useful for new, Hg-free sources of fluorescent light<sup>38,39</sup> Quantum cutting phenomena which are prone to occur in VUV absorbing phosphors is another advantage of these materials, enabling the emission quantum yield higher than 100%.<sup>40,41</sup> Also white LEDs (light emitting diodes) may be an area where luminescence of  $\text{Ln}^{3+}$  ions is important.<sup>42–44</sup>

The sol-gel method used for the synthesis of  $\text{Gd}_4\text{O}_3\text{F}_6$  and relatively low temperature of calcination of the prepared in this way precursors could be used for the production of phosphors.

## Experimental

### Synthesis

Gadolinium oxyfluorides,  $\text{Gd}_4\text{O}_3\text{F}_6$  and  $\text{Gd}_4\text{O}_3\text{F}_6:\text{Eu}^{3+}$ , were synthesized by the modified Pechini's method.<sup>45</sup> The starting materials were gadolinium and europium oxides,  $\text{Gd}_2\text{O}_3$  and  $\text{Eu}_2\text{O}_3$  (Stanford Materials 99.99%, United States), nitric acid  $\text{HNO}_3$  (POCh S.A., ultra-pure, Poland), ammonium fluoride  $\text{NH}_4\text{F}$  (POCh S.A., ACS grade 98+%, Poland), citric acid monohydrate (CHEMPUR, p.a. grade, Poland), and ethylene glycol (CHEMPUR, p.a. grade, Poland).

To synthesize pure matrix without dopant ions,  $\text{Gd}_4\text{O}_3\text{F}_6$ , the gadolinium oxide (0.9166 g) was dissolved in  $\text{HNO}_3$  and evaporated several times in order to remove excess amount of  $\text{HNO}_3$ . The beaker containing the obtained  $\text{Gd}(\text{NO}_3)_3$  was filled up to 100 ml by distilled water and 24 g of citric acid and then 4 ml of ethylene glycol were added. A large excess of citric acid was used to prevent precipitation of lanthanide fluorides (24 g of citric acid and 4 ml of ethylene glycol per 1 g of product). Upon intensive stirring, an aqueous solution of 0.35 g ammonium fluoride in 10 ml of water was slowly dropped into the solution (with 25% excess because of the stoichiometric amounts of  $\text{Gd}^{3+}$  ions). The solution was heated at  $80^\circ\text{C}$  for 24 hours in order to evaporate the water and to obtain a gel. The

prepared precursor was annealed at  $500 - 900^\circ\text{C}$  in the air atmosphere for 2 h. A similar procedure was used for the synthesis of  $\text{Eu}^{3+}$ -doped samples, based on the stoichiometric calculations which assumed replacement of  $\text{Gd}^{3+}$  by  $\text{Eu}^{3+}$  ions in the structure of  $\text{Gd}_4\text{O}_3\text{F}_6$ .

### Characterization

Thermogravimetric analysis (TG) and differential thermal gravimetry (DTG) were performed using a Haas DSC XP-10i calorimeter. The X-ray diffraction (XRD) patterns were collected in the  $2\theta$  range  $10 - 80^\circ$  with X'Pert PRO X-ray diffractometer (Cu,  $K\alpha_1$ :  $1.54060 \text{ \AA}$ ) (PANalytical). IR absorption spectrum was recorded between  $400 - 4000 \text{ cm}^{-1}$  on a Fourier transform infrared (FT-IR) spectrophotometer Bruker FT-IR IFS 66/s. The material was mixed with KBr and then pressed to discs. Raman spectra were taken using a LabRam HR 800 Horiba Yvon Jobin system equipped with a 9 mW HeNe laser emitting a 632.8 nm line. The  $\text{Gd}_4\text{O}_3\text{F}_6$  powders were investigated by transmission electron microscopy (TEM) using a Philips CM-20 SuperTwin microscope operating at 200 kV. Specimens for TEM were prepared by dispersing a small amount of the sample in methanol and putting a droplet of the suspension on a copper microscope grid covered with perforated carbon. Diffractograms were used in crystallographic data refinement with help of the Rietveld method.<sup>46</sup> The Maud 2.33 software was used to perform the Rietveld refinement of cell parameters and phase composition.<sup>47</sup> The quality of structural refinement was generally checked by R-values ( $R_w$ ,  $R_{\text{wnb}}$ ,  $R_{\text{all}}$ ,  $R_{\text{nb}}$ ), and these numbers are easy to detect as they are consistent with a monoclinic structure. However, other parameters with additional functions were applied to find a structural refinement with better quality and reliability.

The luminescence characteristics of the synthesized samples were studied with a Hitachi F-7000 fluorescence spectrophotometer at room and liquid nitrogen temperatures (300 and 77 K) with a 150 W xenon lamp as an excitation source. Excitation and emission spectra were corrected for the instrumental response. The luminescence decay curves of the prepared samples were measured on a Photon Technology Int. QuantaMasterTM 40 spectrophotometer equipped with an Optronic Inc. Opolette 355LD UVDM tunable laser a repetition rate 20 Hz as an excitation source and a Hamamatsu R928 photomultiplier as a detector. The curve fit for the decay data was performed with Origin 9.0 software. The fit with the time traces was at least  $R^2 = 0.998$  and the errors were not larger than  $\tau_{\text{err}} < 0.01 \text{ ms}$ .

The synchrotron radiation study of powder samples was performed at the SUPERLUMI station of HASYLAB, Hamburg, Germany. The setup has been described in detail elsewhere.<sup>48</sup> Luminescence spectra with resolution 1 nm were recorded with a SpectraPro308i (Acton) spectrograph equipped with a CCD camera. The second arm of the spectrograph equipped with a Hamamatsu photomultiplier R6358P was used for measuring the excitation spectra of different emission lines. In the latter case, the slits of the spectrograph were set to a

spectral interval of 10 nm. The excitation spectra were corrected for the spectral distribution of incident light.

## Results and discussion

### Structure and morphology


Gadolinium oxyfluoride,  $\text{Gd}_4\text{O}_3\text{F}_6$ , is a relatively less studied material as can be concluded, for example, from the lack of accurate crystallographic data for this compound. It has attracted undeservedly little attention of researches and only one example of its use as a matrix for up-converting  $\text{Yb}^{3+}$ ,  $\text{Tm}^{3+}$  and  $\text{Er}^{3+}$  ions could be found.<sup>11</sup> This material could be a good potential host for luminescent lanthanide ions like  $\text{Eu}^{3+}$  and  $\text{Tb}^{3+}$ . Relatively low phonon energies of  $\text{Gd}_4\text{O}_3\text{F}_6$  cause lower efficiency of the phonon relaxation from the  $^5\text{D}_1$  excited state of  $\text{Eu}^{3+}$  ions to the  $^5\text{D}_0$  state. A large energy gap ( $\sim 12\,000\text{ cm}^{-1}$ ) between the first excited state,  $^5\text{D}_0$ , and the highest ground state of  $\text{Eu}^{3+}$  ions,  $^7\text{F}_J$ , makes phonon relaxation between them very improbable.<sup>49</sup>

The synthesized  $\text{Gd}_4\text{O}_3\text{F}_6$  sample was analysed precisely by the Rietveld refinement in the isotropic approach in order to obtain the structural information about this compound.


**Table 1.** Atomic and crystal cell parameters for monoclinic  $\text{Gd}_4\text{O}_3\text{F}_6$ : cell dimensions ( $a$ ,  $b$  and  $c$ ), angles ( $\beta$ ) and volume ( $V$ ); atom site coordinates ( $x$ ,  $y$  and  $z$ ), isotropic atomic displacement parameter ( $B_{\text{iso}}$ ) and the goodness of fits between experimental and theoretical diffraction patterns values ( $R_w$ ,  $R_{\text{wnb}}$ ,  $R_{\text{all}}$  and  $R_{\text{nb}}$ ).

Sample	$\text{Gd}_4\text{O}_3\text{F}_6$					
Space group	Monoclinic $P1\ 2/c\ 1\ (13)$					
Formula units per cell	$Z = 1$					
Calculated cell parameters	$a = 3.9498(8)\ \text{\AA}$ $b = 11.2280(6)\ \text{\AA}$ $c = 5.5420(9)\ \text{\AA}$ $\beta = 134.56(3)^\circ$ $V = 175.12(517)\ \text{\AA}^3$					
$R_w$	3.29%					
$R_{\text{wnb}}$	2.06%					
$R_{\text{all}}$	2.26%					
$R_{\text{nb}}$	2.72%					
Selected contacts						
Gd – Gd	3.9498(8) $\text{\AA}$					
Gd – O	2.1445(1) $\text{\AA}$					
Gd – O/F	2.1469(4) $\text{\AA}$					
Gd – F	2.2718(3) $\text{\AA}$					
Gd – O – Gd	133.813(10) $^\circ$					
Gd – F – Gd	120.760(9) $^\circ$					
Atom	Wyckoff positions	x	y	z	$B_{\text{iso}}\ [\text{\AA}^2]$	
Gd1	2e	0	0.115(x)	0.25	0.135(5)	
Gd2	2e	0	0.615(x)	0.25	0.141(6)	
O1	2f	0.5	0.960(x)	0.75	1.021 (4)	
O2	2e	0	0.836(x)	0.25	1.023(2)	
O3	2e	0	0.306(x)	0.25	1.024(1)	
F1	2f	0.5	0.960(x)	0.75	1.025(5)	
F2	2f	0.5	0.285(x)	0.75	1.021(4)	
F3	2f	0.5	0.462(x)	0.75	1.022(3)	
F4	2f	0.5	0.789(x)	0.75	1.021(1)	

Table 1 shows the experimental and calculated results of the Rietveld analysis of gadolinium oxyfluoride. These results confirmed that the synthesized compound was monophasic. The crystal structure of  $\text{Gd}_4\text{O}_3\text{F}_6$  was determined to be monoclinic with space group  $P1\ 2/c\ 1$ .



**Fig. 1.** The Rietveld profile fit of X-ray diffraction data of  $\text{Gd}_4\text{O}_3\text{F}_6$  annealed at  $500^\circ\text{C}$  for 2 h.



**Fig. 2.** The structure of the monoclinic  $\text{Gd}_4\text{O}_3\text{F}_6$  phase with (a) unit cell and (b and c) the coordination environment of  $\text{Gd}^{3+}$  ions.

The Rietveld analysis could be applied to any of the compounds prepared within the compositional domain and occurring in a stable, single phase. However, our aim was to find a structural model suitable for all the chemical compositions within the stable structural domain with pure phases.

The structure of the new  $Gd_4O_3F_6$  compound was refined from powder XRD data in a tetralanthanide trioxyfluoride structure model.<sup>29</sup> The instrumental parameters used to describe the Rietveld profile were as follows: zero-point in  $2\theta$ , background parameters, three peak-shape parameters,  $U$ ,  $V$  and  $W$ , in the formula  $H^2 = U \tan^2 \theta + V \tan \theta + W$  to describe a Pseudo-Voigt peak with full width at half maximum,  $H$ , which increases with  $\theta$ . The structure parameters used were: a scale factor, the lattice constant, the positional coordinate and the occupancy factors (Table 1) of all atoms and the isotropic temperature factors.

Fig. 1 shows typical observed, calculated, and difference profiles for the synthesized  $Gd_4O_3F_6$ . In all cases, the agreement between the observed and calculated Rietveld profiles is excellent and the final  $R$  factors are satisfactory. This model fits the observed intensity provided that the structural parameters from Table 1 are taken.

In this structure, the cation sites, Gd1 and Gd2, are coordinated by oxygen and fluorine ions with CN = 9, while the occupancy of  $2f$  site by  $F^-$  and  $O^{2-}$  is 0.4 and 0.5, respectively (Fig. 2). In the  $Gd_4O_3F_6$  structure, the ionic arrangement was supposed to be highly ordered with two kinds of ion clusters,  $GdO_{0.5}F \cdot O_{0.5}$  and  $GdF_2 \cdot O_{0.5}$ .<sup>29</sup> The linkage of these clusters was estimated to be somewhat disordered. The disorder in the anion arrangement was caused by the disorder in the cation arrangement. Consequently, the occupancy of  $2e$  sites by oxygen ions remained at 0.5, whereas  $2f$  sites layered at  $y = 0$  plane were occupied partially by fluoride ions. Because the occupancy of  $2f$  sites by fluorine ions and oxygen ions is less than 1.0, then oxygen and fluorine ion conductivity could be considered in this material.<sup>50,28</sup>

The stoichiometric composition of rare earth oxyfluorides is strongly affected by the amount of fluorine ions in the sample. It is greatly important to maintain the required composition of the initial precursor for the synthesis of an appropriate material phase. The Pechini's method enables a full control of the  $F^-$  amount because the initial concentration can be easily changed with the quantity of  $NH_4F$  in the gel. In this way it is possible to obtain a rhombohedral as well as a pseudo-tetragonal form of gadolinium oxyfluoride.

Thermo-gravimetric analysis of powders purified from the reaction mixture was performed in air in order to identify the processes occurring during the thermal treatment (see Fig. 3). The mass loss up to  $550^\circ C$  was attributed to the decomposition of organic components. The  $Gd_4O_3F_6$  product is formed above  $550^\circ C$ . The intense peak around  $500^\circ C$  visible in the DTA curve is an effect of the exoenergetic decomposition of organic resin and simultaneous crystallization of  $Gd_4O_3F_6$  product. Temperature increase has a very small effect on the sample above  $600^\circ C$ , considering the lack of any larger peaks at these

temperatures. Finally, only about 4% of the gel precursor is transferred into the powder product.




Fig. 3. DTG/TG analysis of  $Gd_4O_3F_6$  gel precursor.

The phase composition of the samples prepared at temperatures from the range  $500 - 900^\circ C$  was calculated with the help of Rietveld refinement. Above  $500^\circ C$ , a phase transition to the rhombohedral GdOF form was observed. At temperatures higher than  $600^\circ C$  oxyfluorides decomposed into  $Gd_2O_3$  oxide. From Fig. 3, the optimal temperature for annealing the precursor gel can be found. Heating the gel at  $500^\circ C$  allows the formation of the product, and at the same time it is a temperature sufficient for the decomposition of organic contaminants. The product obtained at  $500^\circ C$  was used in further structural analysis including IR and Raman spectroscopy.




Fig. 4. TEM and SAED images of  $Gd_4O_3F_6$  prepared at  $500^\circ C$ .

In order to investigate the morphology and structure of the final products, TEM and SAED characterization was carried

out for the  $\text{Gd}_4\text{O}_3\text{F}_6$  sample heat treated at  $500^\circ\text{C}$  (Fig. 4). TEM images showed the nanocrystalline structure of powders, whereas the average nanocrystals size taken from TEM was  $26 \pm 8$  nm. The synthesis conditions and character of used sol-gel method result in formation of agglomerates. However, the agglomeration of individual crystallites is relatively weak and there are no sintered and melted forms visible in the TEM image. Selected area diffraction (SEAD) shows the polycrystalline properties of the powders prepared.

The number of expected IR and Raman peaks can be found from the described crystal structure of  $\text{Gd}_4\text{O}_3\text{F}_6$ . According to the factor group analysis, for the monoclinic  $\text{Gd}_4\text{O}_3\text{F}_6$ , 6 IR and 6 Raman peaks should be observed in the measured spectra. There are 16 atoms in the unit cell and therefore  $3N = 48$  degrees of freedom which are divided into 12 modes (IR active modes are labelled as IR, Raman modes as R):

$$\Gamma_{\text{opt}} = 2A_g(\text{R}) + 2A_u(\text{IR}) + 4B_g(\text{R}) + 4B_u(\text{IR}) \quad (1)$$

The FT-IR spectrum of the  $\text{Gd}_4\text{O}_3\text{F}_6$  sample is shown in Fig. 5. It demonstrates characteristic intense bands in the range of  $3000 - 3750 \text{ cm}^{-1}$  connected with the O-H stretching vibrations. The peaks near  $1530 \text{ cm}^{-1}$  and  $1380 \text{ cm}^{-1}$  can be assigned to the C-O absorption. These two bands could be connected with traces of organic impurities present in the sample or with absorption by  $\text{CO}_2$  and  $\text{H}_2\text{O}$  adsorbed at the powder surface. The C-O and O-H groups with high energy vibrations may be present in the samples because the character of a sol-gel process involves the decomposition processes of organic compounds forming a gel. The absorption peak at  $527 \text{ cm}^{-1}$  is ascribed to the vibration of the Gd-O bond. The  $\text{Gd}_4\text{O}_3\text{F}_6$  compound shows also absorption in the range below  $400 \text{ cm}^{-1}$  (showed as inset in Fig. 5). The absorption in this range is observed as a broad peak with the minimum of transmittance at  $367 \text{ cm}^{-1}$ . The broad shape of this absorption band can be attributed to the disordered arrangement of the ions in the crystal lattice of the  $\text{Gd}_4\text{O}_3\text{F}_6$  compound. There is also similarity in absorption bands in this range between the monoclinic and tetragonal or cubic REOF.<sup>51</sup>




Fig. 5. IR spectra of  $\text{Gd}_4\text{O}_3\text{F}_6$  nanomaterial.

The FT-IR spectra of the rhombohedral REOF are much more complex demonstrating at least two absorption bands in this region.<sup>52</sup> In the IR spectrum shown in the inset, the structure of absorption bands is complex due to the nanocrystalline character of the sample and a large number of IR peaks.

The Raman spectra of the  $\text{Gd}_4\text{O}_3\text{F}_6$  oxyfluoride are shown in Fig. 6. Six peaks at about  $127, 218, 340, 360, 415$  and  $460 \text{ cm}^{-1}$  can be observed. The lower energy peaks are connected with the movement of heavy Gd-Gd pairs ( $127$  and  $218 \text{ cm}^{-1}$ ).<sup>53</sup> The vibrations of the Gd-O group are visible as a peak at  $460 \text{ cm}^{-1}$ .<sup>52</sup>




Fig. 6. Raman spectrum of  $\text{Gd}_4\text{O}_3\text{F}_6$  nanocrystals.




Fig. 7. XRD patterns of  $\text{Gd}_4\text{O}_3\text{F}_6:\text{Eu}^{3+}$  nanophosphors prepared by sol-gel method and annealed at  $500^\circ\text{C}$  for 2 h.

Fig. 7 shows the XRD patterns of the nanosized  $\text{Gd}_4\text{O}_3\text{F}_6:\text{Eu}^{3+}$  crystals. The positions of all peaks are in good agreement with those in the pattern calculated for monoclinic  $\text{Gd}_4\text{O}_3\text{F}_6$  with  $P2_1/c$  space group. The single-phase product with no presence of any additional peaks from extraneous admixtures was obtained in the whole range of  $\text{Eu}^{3+}$  doping concentrations.

The structure of gadolinium offers two equivalent cationic sites Gd(I) and Gd(II) for possible substitution with RE<sup>3+</sup> ions. No preferential site substitution depending on the concentration of dopant and annealing temperature has been observed. Besides, in comparison with the cell parameters for 0.5% mol Eu<sup>3+</sup> ions doped Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub> ( $a = 3.9421(7)$  Å,  $b = 11.2169(6)$  Å,  $c = 5.5564(9)$  Å and  $\beta = 134.97(4)$ ,  $V = 173.81(731)$ ) an insignificant cell volume decrease with the substitution of Gd<sup>3+</sup> ions (ionic radius 1.107 Å in ninefold coordination) with the dopants (the ionic radius of Eu<sup>3+</sup> is 1.12 Å).<sup>54</sup>

### Luminescent properties


Figs. 8 – 10 illustrate the luminescent properties of Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub>:Eu<sup>3+</sup> materials. Excitation spectra (Fig. 8a) in the range of 200 – 500 nm indicate the possibility of efficient excitation impurity emission in the O<sup>2-</sup>→Eu<sup>3+</sup> charge transfer band (CT) with maximum at 250 nm. The presence of this band is a result of O<sup>2-</sup> ions in the structure.<sup>55</sup> The energy of O<sup>2-</sup>→Eu<sup>3+</sup> CT could be estimated by using the following equation given by Jørgensen:<sup>56</sup>

$$E_{CT} = [\chi(L) - \chi(M)](3 \cdot 10^4) \quad (2)$$

where  $E_{CT}$  denotes the position of CT band (in cm<sup>-1</sup>),  $\chi(L)$  and  $\chi(M)$  are the optical electronegativities of the anion and the central metal cation, respectively. For  $\chi(O) = 3.2$  and  $\chi(Eu) =$

1.75,<sup>57</sup> the calculated CT position should be 43 500 cm<sup>-1</sup> (around 230 nm). The measured positions of CT bands in the excitation spectra of obtained samples were at around 250 nm. The red shift of CT band resulted from the difference between bulk materials, for which equation (2) was derived, and nano-sized phosphors.<sup>58–61</sup>

The remaining narrow excitation bands with maxima above 270 nm are related to the  $f-f$  transitions of Gd<sup>3+</sup> and Eu<sup>3+</sup> ions. Their narrow character is a consequence of the shielding properties of the higher energetic  $5d$  and  $6s$  electron sublevels present in Ln<sup>3+</sup> ions. These properties influence the impact of the surrounding local environment and therefore  $f-f$  electronic transitions are relatively insensitive to the changes in ligands. These transitions are Laporte forbidden and due to that their intensities are low unlike that of the CT band, allowed by selection rules. The transition bands in the spectral range of 270 – 315 nm are connected with excitation of Gd<sup>3+</sup> ions and confirm the energy transfer (ET) between Gd<sup>3+</sup> and Eu<sup>3+</sup> ions.<sup>40</sup> The other peaks proved the direct excitation of Eu<sup>3+</sup> ions. As follows from the excitation spectra, Eu<sup>3+</sup> ions at lower concentrations can be effectively excited not only in CT but also in ET bands. However, with increasing Eu<sup>3+</sup> concentration, the ratio between CT and ET changes in favour of the former.



**Fig. 8.** Luminescence excitation (a) and emission (b) spectra of Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub>:Eu<sup>3+</sup> samples; (c) integrated luminescence intensity as a function of Eu<sup>3+</sup> ions concentration (dots represent integrated area under emission bands; the dotted line is nonlinear fit), (d) comparison of luminescence spectra of LaOF:Eu<sup>3+</sup> and Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub>:Eu<sup>3+</sup> samples measured in the same conditions.

## ARTICLE


The emission spectra obtained under excitation by 250 nm UV light are presented in Fig. 8b. All emission bands are due to the transitions from the  $^5D_0$  excited level to the  $^7F_J$  components of the ground state. The most intense emission line observed at 612 nm is connected with one of the components of  $^5D_0 \rightarrow ^7F_2$  transition. The sensitivity of transitions within the  $f$ -electron shell of  $RE^{3+}$  ions to crystal field is relatively low. However, some of  $f$ - $f$  transitions are prone to changes depending on the symmetry of local environment. In  $Eu^{3+}$  ion, the  $^5D_0 \rightarrow ^7F_2$  transition is sensitive to the  $Eu^{3+}$  local symmetry and becomes partially allowed when  $Eu^{3+}$  ions occupy sites of low symmetry (without an inversion symmetry). Its hypersensitivity is often used to track the structural changes in  $Eu^{3+}$  host and surrounding coordination.<sup>62</sup> In the  $Gd_4O_3F_6$  host material, the  $Eu^{3+}$  ions are located in low symmetry sites, replacing Gd1 or Gd2 ions (both  $C_{2v}$ ), that causes a relatively high intensity of the  $^5D_0 \rightarrow ^7F_2$  transition band.

The highest integral luminescence intensity was measured for the 10%-doped sample. The value between 5 – 10 % is typical of  $Eu^{3+}$  doped materials, whereas for higher doping the concentration quenching of the  $^5D_0$  excited state occurs.<sup>49</sup> This process can be attributed to the resonance energy transfer between neighbouring  $Eu^{3+}$  ions or by the transfer to the crystal defects and impurities. The energy resulting from the difference between  $^5D_0$  and  $^7F_J$  manifolds can be cooperatively transferred between three or four nearest  $Eu^{3+}$  ions.<sup>63</sup> The mechanism of interaction between  $Eu^{3+}$  ions depends on the critical distance between them.<sup>64</sup> The energy transfer between  $Eu^{3+}$  ions may occur via one of the following mechanisms: exchange interaction, radiation reabsorption and multipole–multipole interactions. The critical distance between donor and acceptor can be calculated using the equation proposed by Blasse.<sup>65</sup> In  $Gd_4O_3F_6$  host material, critical distance between  $Eu^{3+}$  ions was calculated to be 9.42 Å. For the distances greater than 5 Å multipole-multipole interactions are dominant and are the major cause of concentration quenching.

The interactions between  $Eu^{3+}$  ions, observed in the oxyfluoride host previously,<sup>13</sup> also affect the observed decays, which is discussed below. Phonon relaxation from  $^5D_0$  excited state to  $^7F_6$  level is impossible in the most cases due to a large energy gap between these states. This is particularly true for  $Gd_4O_3F_6$  due the low phonon energy in this matrix, which is confirmed by Raman spectroscopy (see Fig. 6).

A comparison of the luminescence properties of tetragonal  $LaOF:Eu^{3+}$  and monoclinic  $Gd_4O_3F_6:Eu^{3+}$ , prepared in the same way, shows their similarity but also important differences (see Fig. 8d). In the first instance, the shapes and widths of emission bands show that the number of different  $Eu^{3+}$  sites is higher in  $Gd_4O_3F_6:Eu^{3+}$ . The  $^5D_0 \rightarrow ^7F_0$  transition band is forbidden by the

selection rules of  $f$ - $f$  transitions, but it could be observed when  $Eu^{3+}$  ions occupy sites with  $C_s$ ,  $C_n$ , or  $C_{nv}$  symmetry through the  $J$ - $J_0$  mixing effect which is really achieved in both structures.<sup>66</sup> In  $LaOF:Eu^{3+}$  material, the intensity of  $^5D_0 \rightarrow ^7F_0$  line is higher that emphasizes the difference between these two materials. Also the shape of  $^5D_0 \rightarrow ^7F_0$  line in the luminescence spectra of  $Gd_4O_3F_6:Eu^{3+}$  suggests that it is composed of at least two single peaks connected with two different sites of  $Eu^{3+}$  in the proposed crystal structure. The remaining emission lines in the luminescence spectrum of  $Gd_4O_3F_6:Eu^{3+}$  material are broadened and more complex due to the stronger splitting of degenerated  $^7F_J$  states in  $C_{2v}$  symmetry than in  $C_{4v}$  in  $LaOF:Eu^{3+}$ ,<sup>67</sup> as the splitting is generally thinner in a site with lower-symmetry.



**Fig. 9.** Emission spectra of  $Gd_4O_3F_6:2\%Eu^{3+}$  sample measured at  $T = 7$  K with the use of different excitation wavelengths and the excitation spectrum of the 612 nm emission measured for  $Gd_4O_3F_6:2\%Eu^{3+}$  sample in the VUV and UV range.

Emission spectra of  $Gd_4O_3F_6:Eu^{3+}$  2% sample under excitation with different wavelengths selected from the UV-VUV range are presented in Fig. 9. The excitation spectrum measured for the 612 nm line in the UV-VUV range is presented in the inset as well. It clearly indicates that the emission of  $Eu^{3+}$  centres in the obtained material can be efficiently excited in VUV range. The intensity of the  $Eu^{3+}$  emission is high under excitation in the fundamental absorption region below 100 nm (host –  $Eu^{3+}$  energy transfer), while wide and intense bands observed in the excitation spectra between 150 and 200 nm can be associated with  $F^- \rightarrow Eu^{3+}$  and  $O^{2-} \rightarrow Gd^{3+}$  CT. The spectral range in which the  $F^- \rightarrow Eu^{3+}$  CT band can be observed, can be determined from Eq. 2. For  $\chi(F) = 3.9$  and  $\chi(Eu) = 1.75$ , the calculated CT position should be at  $64500\text{ cm}^{-1}$  (around 155 nm).<sup>68</sup> A similar position of CT band (around 150 nm) was experimentally obtained by Ptacek et al.

in the spectra of NaGdF<sub>4</sub> nanocrystals doped with Eu<sup>3+</sup> ions.<sup>69</sup> The calculated in the same way position of O<sup>2-</sup>→Gd<sup>3+</sup> CT should be around 145 nm (with the  $\chi(\text{Gd}) = 0.91$ ) and F<sup>-</sup>→Gd<sup>3+</sup> CT peak should be observed at around 89 700 cm<sup>-1</sup> (111 nm).<sup>70</sup> The energy of CT between O<sup>2-</sup> and Gd<sup>3+</sup> ions can be different depending on the host material. It was observed that O<sup>2-</sup>→Gd<sup>3+</sup> CT has higher energy when occurred in fluorides and the maximum of CT band can be found at 123 nm and 131 nm in YF<sub>3</sub> and LaF<sub>3</sub> matrices, respectively.<sup>71</sup> In materials containing O<sup>2-</sup> ions, such as borates, aluminates and silicates, the maximum of CT band can be found at lower energies than that predicted theoretically (155 – 184 nm).<sup>71,72</sup> The energies of CT are generally dependent on the surrounding environment and can be different in various host materials. In our system, the F<sup>-</sup>→Eu<sup>3+</sup> CT band is red-shifted with respect to the theoretical position. However, only the band with a maximum at 176 nm can be assigned to F<sup>-</sup>→Eu<sup>3+</sup> CT because of expected intensity higher than that of O<sup>2-</sup>→Gd<sup>3+</sup> CT. In the emission of Eu<sup>3+</sup> ions excited by the O<sup>2-</sup>→Gd<sup>3+</sup> CT, the radiative relaxation of Eu<sup>3+</sup> ions is preceded by the Gd<sup>3+</sup>→Eu<sup>3+</sup> energy transfer that decreases the efficiency of the whole process. The remaining excitation bands in the range from 200 to 330 nm are connected with O<sup>2-</sup>→Eu<sup>3+</sup> CT and Gd<sup>3+</sup>→Eu<sup>3+</sup> energy transfer similarly to those shown in Fig. 8a and discussed above.

The highest intensity of the Eu<sup>3+</sup> emission recorded upon excitation below 200 nm was recorded at 176 nm. The property of efficient excitation below 200 nm makes this compound a suitable phosphor for vacuum ultraviolet applications, such as plasma display panels and Hg-free fluorescent lamps.<sup>33,73</sup>

Luminescence decay curves recorded for Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub>:Eu<sup>3+</sup> materials at room temperature are presented in Fig. 10. The decays are relatively fast for the Eu<sup>3+</sup>-doped materials, however this is an advantage concerning their potential applications as red emitting phosphors. Average luminescence lifetimes were calculated by applying the following equation:<sup>74</sup>

$$\tau = \frac{\int_0^{\infty} tI(t)dt}{\int_0^{\infty} I(t)dt} \approx \frac{\int_0^{\text{max}} tI(t)dt}{\int_0^{\text{max}} I(t)dt} \quad (3)$$

where  $I(t)$  represents the luminescence intensity at time  $t$  corrected for the background and the integrals are evaluated in the range  $0 < t < t_{\text{max}}$ , where  $t_{\text{max}} \gg \tau$ .

The longest luminescence lifetime was calculated for the 1%-doped sample. Higher concentrations of Eu<sup>3+</sup> ions caused a decrease in lifetime, which resulted from the above-mentioned concentration quenching. All depicted curves show a short rise in their intensities after the laser pulse, especially visible for the samples with low Eu<sup>3+</sup> concentration. This phenomenon is caused by interactions between Eu<sup>3+</sup> ions, fully described elsewhere.<sup>13</sup> In short, Eu<sup>3+</sup> ions can exchange their energies after excitation in several ways. Energy transfer from the <sup>5</sup>D<sub>J</sub> ( $J > 0$ ) manifold to another Eu<sup>3+</sup> ion in the <sup>7</sup>F<sub>J</sub> ground state can occur, which affects the relaxation dynamics, or one of the excited Eu<sup>3+</sup> ions transfers its entire energy to another excited Eu<sup>3+</sup> ion in its <sup>5</sup>D<sub>0</sub> state, doubling its energy and therefore

pumping the emitting, <sup>5</sup>D<sub>0</sub> state after nonradiative relaxation from higher excited states.




Fig. 10. Luminescence decays of Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub>:Eu<sup>3+</sup> samples.

The emission spectra and luminescence decay curves measured at 300 K were used for the calculation of the Judd-Ofelt spectroscopic parameters by the method described earlier.<sup>75-77</sup> According to the Judd-Ofelt theory, intensity parameters contain contributions from the forced electric dipole and dynamic coupling mechanisms and provide information about the surrounding environment of Eu<sup>3+</sup> ions.<sup>77,76,78,79</sup> The calculated  $\Omega_2$  and  $\Omega_4$  parameters are sensitive to the character of Eu<sup>3+</sup> local environment. The changes in  $\Omega_2$  parameter bring information on the covalency of the Eu<sup>3+</sup> ion environment. Its value is high for all samples studied, which confirms highly polarized surrounding of Eu<sup>3+</sup> ions. This parameter is also connected with the average site symmetry and is high for the sites with low symmetry. The value of  $\Omega_2$  slightly increases with growing amount of Eu<sup>3+</sup> ions in the matrix. This could be a result of distortions appearing at the Eu<sup>3+</sup> site. The value of  $\Omega_4$  parameter could be gained by lowering the covalency of the chemical bond between the Eu<sup>3+</sup> ion and O<sup>2-</sup> ligand ions.<sup>80</sup> The electron density decreasing on ligands results in an increase in  $\Omega_4$ .

The calculated luminescence quantum efficiencies were high for the samples with Eu<sup>3+</sup> concentration up to 5%, which confirms the effectiveness of prepared materials as phosphors and good properties of Gd<sub>4</sub>O<sub>3</sub>F<sub>6</sub> as a host material. The decreased efficiency in the 10%-doped sample, was a result of the earlier mentioned cross-relaxation between Eu<sup>3+</sup> ions. According to Fig. 8c, the highest quantum efficiency should be expected for the 10%-doped sample, for which the most intense luminescence was observed. However, the method used for the calculations, includes also nonradiative processes, being inversely proportional to the luminescence lifetimes. Hence, from the calculated total decay rates (see Table 3) we can estimate that the absorption of light is the highest for the 10%-doped sample, however there are some quenching process (like concentration quenching) which are reflected in high nonradiative rate and therefore low quantum efficiency.

**Table 3.** Judd-Ofelt parameters and luminescence quantum yields calculated for the obtained oxyfluorides: radiative, nonradiative and total deactivation rates ( $A_{\text{rad}}$ ,  $A_{\text{nrad}}$  and  $A_{\text{tot}}$ ), Judd-Ofelt intensity parameters ( $\Omega_2$  and  $\Omega_4$ ) and quantum yields ( $\eta$ ).

Eu (%)	$A_{\text{rad}} (\text{s}^{-1})$	$A_{\text{nrad}} (\text{s}^{-1})$	$A_{\text{tot}} (\text{s}^{-1})$	$\Omega_2$ ( $10^{-20} \text{ cm}^2$ )	$\Omega_4$ ( $10^{-20} \text{ cm}^2$ )	$\eta$ (%)
0.5	553	56	609	43.7	17.8	91
1	496	84	580	41.0	11.1	85
2	524	77	600	42.8	13.5	87
5	573	5	577	45.2	19.2	99
10	582	222	804	48.2	14.8	72

## Conclusions

Gadolinium oxyfluoride  $\text{Gd}_4\text{O}_3\text{F}_6$  with a new monoclinic crystal structure was successfully prepared by a modified Pechini's method. The prepared materials crystallized as the monoclinic phase in the  $P12/c1$  (13) space group. In this crystal structure two types of clusters  $\text{GdO}_{0.5}\text{F}\cdot\text{O}_{0.5}$  and  $\text{GdF}_2\cdot\text{O}_{0.5}$  are located. Thermo-gravimetric analysis (TGA) was used to observe the transformation from an amorphous polymeric precursor to a crystalline powder, which provided information about optimal annealing conditions. X-ray diffraction (XRD) analysis, IR spectroscopy and Raman spectrum confirmed the monoclinic structure of the nanopowders obtained at  $500^\circ\text{C}$ . Crystal structure parameters were determined with the help of the Rietveld analysis and compared with the reference data. The transmission electron microscopy and EDX spectrum proved the formation of gadolinium oxyfluoride with the average grain size of 30 nm.

The nanophosphors were effectively excited by the radiation from the vacuum ultraviolet range with the wavelength  $\lambda_{\text{ex}} = 176 \text{ nm}$  and by the UV light, with the wavelength of  $\lambda_{\text{ex}} = 250 \text{ nm}$ . For the efficient excitation by VUV light, the  $\text{F}^- \rightarrow \text{Eu}^{3+}$  and  $\text{O}^{2-} \rightarrow \text{Gd}^{3+}$  CT processes are suggested to be responsible. The excitation band related to the  $\text{O}^{2-} \rightarrow \text{Eu}^{3+}$  CT allows the excitation in the UV range. The materials doped with  $\text{Eu}^{3+}$  ions showed intense red luminescence. The recorded emission spectra were used for calculation of the Judd-Ofelt intensity parameters indicating highly polarized local environment and low symmetry of sites occupied by  $\text{Eu}^{3+}$  ions. The most effective dopant concentration was estimated to be 10%. Although the decay times of the emission of  $\text{Eu}^{3+}$  ions were relatively short, ranging from 1.42 to 2.42 ms, the calculated luminescence quantum yields were high which makes the prepared materials interesting phosphors sensitive to the VUV and UV excitation.

## Acknowledgments

Funding for this research was provided by the National Science Centre (grant no. DEC-2011/03/D/ST5/05701). T.G. holds a scholarship from the Foundation for Polish Science for Young Scientists (FNP).

This work was supported in part by the European Community Research Infrastructure Action under the FP6 Structuring the European Research Area Programme (through the Integrated Infrastructure Initiative Integrating Activity on Synchrotron and Free Electron Laser Science) and by the Estonian Research Council—Institutional Research Funding IUT02-26.

## Notes and references

<sup>a</sup> Department of Rare Earth, Faculty of Chemistry, Adam Mickiewicz University, Umultowska 89b, 61-614 Poznan, Poland, e-mail: tgrzyb@amu.edu.pl

<sup>b</sup> Institute of Low Temperature and Structure Research, Polish Academy of Sciences, P.O. Box 1410, 50-950 Wroclaw, Poland, e-mail:

R.Wiglusz@int.pan.wroc.pl

<sup>c</sup> Institute of Physics, University of Tartu, Riia 142, 51014 Tartu, Estonia.

<sup>d</sup> HASYLAB at DESY, Gebaude 25b/309 Notkestr. 85, D-22607 Hamburg, Germany.

1. P. Berdowski, M. J. J. Lammers, and G. Blasse, *Chem. Phys. Lett.*, 1985, **113**, 387–390.
2. J. Holsa, *Acta Chem. Scand.*, 1991, **45**, 583–587.
3. J. Hölsä and E. Kestilä, *J. Alloy. Compd.*, 1995, **225**, 89–94.
4. J. Hölsä, E. Kestilä, P. Ylha, E. Antic-Fidancev, M. Lemaitre-Blaise, P. Porcher, P. Deren, and W. Strek, *J. Appl. Spectrosc.*, 1995, **62**, 697–705.
5. S. Fujihara, T. Kato, and T. Kimura, *J. Mater. Sci. Lett.*, 2001, **20**, 687–689.
6. J. Kyu Park, C.-H. Han, C. Hae Kim, H. D. Park, and S. Y. Choi, *J. Mater. Sci. Lett.*, 2003, **22**, 477–478.
7. E. Antic-Fidancev, J. Hölsä, J.-C. Krupa, and M. Lastusaari, *J. Alloy. Compd.*, 2004, **380**, 303–309.
8. D. Gao, H. Zheng, X. Zhang, Z. Fu, Z. Zhang, Y. Tian, and M. Cui, *Appl. Phys. Lett.*, 2011, **98**, 011907.
9. X. Zhang, D. Gao, and L. Li, *J. Appl. Phys.*, 2010, **107**, 123528.
10. E. He, H. Zheng, Z. Zhang, X. Zhang, L. Xu, Z. Fu, and Y. Lei, *J. Nanosci. Nanotechnol.*, 2010, **10**, 1908–1912.
11. T. Passuello, F. Piccinelli, M. Pedroni, M. Bettinelli, F. Mangiarini, R. Naccache, F. Vetrone, J. A. Capobianco, and A. Speghini, *Opt. Mater.*, 2011, **33**, 643–646.
12. T. Passuello, F. Piccinelli, M. Pedroni, S. Polizzi, F. Mangiarini, F. Vetrone, M. Bettinelli, and A. Speghini, *Opt. Mater.*, 2011, **33**, 1500–1505.
13. T. Grzyb and S. Lis, *Inorg. Chem.*, 2011, **50**, 8112–20.
14. M. Shang, G. Li, X. Kang, D. Yang, D. Geng, C. Peng, Z. Cheng, H. Lian, and J. Lin, *Dalt. Trans.*, 2012, **41**, 5571–80.
15. T. Grzyb, M. Węclawiak, and S. Lis, *J. Alloy. Compd.*, 2012, **539**, 82–89.
16. W. H. Zachariasen, *Acta Crystallogr.*, 1951, **4**, 231–236.
17. D. B. Shinn and H. A. Eick, *Inorg. Chem.*, 1969, **8**, 232–235.
18. A. Popov and G. Knudson, *J. Am. Chem. Soc.*, 1954, **76**, 3921–3922.
19. N. Baenziger, J. Holden, G. Knudson, and A. Popov, *J. Am. Chem. Soc.*, 1954, **76**, 4734–4735.
20. J. Müller and T. Petzel, *J. Alloy. Compd.*, 1995, **224**, 18–21.
21. J. W. Fergus, *J. Mater. Sci. Lett.*, 1997, **16**, 267–269.
22. A. W. Mann and D. J. M. Bevan, *J. Solid State Chem.*, 1972, **5**, 410–418.
23. J. Müller, *Thermochim. Acta*, 1997, **298**, 109–114.
24. S. Schmid, *Acta Crystallogr. B*, 1998, **54**, 391–398.
25. A. de Kozak, M. Samouël, and A. Chretien, *Rev. Chim. Miner.*, 1975, **10**, 259.
26. M. Takashima, S. Yonezawa, K. Horita, K. Ohwaki, and H. Takahashi, *J. Mater. Chem.*, 1996, **6**, 795.
27. M. Takashima, S. Yonezawa, J. H. Kim, and S. Nishibu, *J. Ind. Eng. Chem.*, 2004, **10**, 1230–1241.

28. M. Takashima, S. Yonezawaa, and M. Leblanc, *Solid State Ionics*, 2002, **154-155**, 547–553.
29. M. Takashima, S. Yonezawa, T. Tanioka, Y. Nakajima, and M. Leblanc, *Solid State Sci.*, 2000, **2**, 71–76.
30. M. Takashima, S. Yonezawa, and Y. Ukuma, *J. Fluor. Chem.*, 1998, **87**, 229–234.
31. M. Takashima and G. Kano, *Solid State Ionics*, 1987, **23**, 99–106.
32. J.-C. G. Bünzli and C. Piguet, *Chem. Soc. Rev.*, 2005, **34**, 1048–77.
33. Q. Y. Zhang and X. Y. Huang, *Prog. Mater. Sci.*, 2010, **55**, 353–427.
34. K. Binnemans, *Chem. Rev.*, 2009, **109**, 4283–374.
35. J.-C. G. Bünzli, *Acc. Chem. Res.*, 2006, **39**, 53–61.
36. T. Grzyb, M. Runowski, A. Szczeszak, and S. Lis, *J. Solid State Chem.*, 2013, **200**, 76–83.
37. A. Szczeszak, T. Grzyb, B. Barszcz, V. Nagirnyi, A. Kotlov, and S. Lis, *Inorg. Chem.*, 2013, **52**, 4934–4940.
38. S. Okamoto, R. Uchino, K. Kobayashi, and H. Yamamoto, *J. Appl. Phys.*, 2009, **106**, 013522.
39. J. Krupa and M. Queffelec, *J. Alloys Compd.*, 1997, **250**, 287–292.
40. R. T. Wegh, H. Donker, K. D. Oskam, and A. Meijerink, *Science (80- )*, 1999, **283**, 663–666.
41. J. Dexpert-Ghys, R. Mauricot, B. Caillier, P. Guillot, T. Beaudette, G. Jia, P. a. Tanner, and B.-M. Cheng, *J. Phys. Chem. C*, 2010, **114**, 6681–6689.
42. S. Dutta, S. Som, and S. K. Sharma, *Dalt. Trans.*, 2013, **42**, 9654.
43. A. K. Ambast, J. Goutam, S. Som, and S. K. Sharma, *Spectrochim. Acta Part A Mol. Biomol. Spectrosc.*, 2014, **122**, 93–99.
44. C. C. Lin and R.-S. Liu, *J. Phys. Chem. Lett.*, 2011, **2**, 1268–1277.
45. M. Pechini, 1967.
46. H. M. Rietveld, *J. Appl. Crystallor.*, 1969, **2**, 65–71.
47. L. Lutterotti and M. Bortolotti, *Compcomm. Newsl.*, 2003, **1**, 43–50.
48. G. Zimmerer, *Radiat. Meas.*, 2007, **42**, 859–864.
49. M. Weber, *Phys. Rev.*, 1968, **171**, 283–291.
50. K. T. Jacob, V. S. Saji, and Y. Waseda, *Int. J. Appl. Ceram. Technol.*, 2006, **3**, 312–321.
51. G. N. Kustova, K. F. Obzherina, and L. R. Batsanova, *J. Appl. Spectrosc.*, 1968, **9**, 947–950.
52. J. Hölsä, E. Säilynoja, H. Rahiala, and J. Valkonen, *Polyhedron*, 1997, **16**, 3421–3427.
53. J. Hölsä, *Spectrochim. Acta, Part A*, 1993, **49**, 465–470.
54. R. D. Shannon, *Acta Crystallogr. A*, 1976, **32**, 751–767.
55. P. Dorenbos, *J. Phys. Condens. Matter*, 2003, **15**, 8417–8434.
56. C. K. Jørgensen, *Electron Transfer Spectra*, John Wiley & Sons, Inc., 1970.
57. C. Liu, J. Liu, and K. Dou, *J. Phys. Chem. B*, 2006, **110**, 20277–81.
58. J. C. Boyer, F. Vetrone, J. A. Capobianco, A. Speghini, and M. Bettinelli, *J. Phys. Chem. B*, 2004, **108**, 20137–20143.
59. Z. Fu, S. Zhou, T. Pan, and S. Zhang, *J. Lumin.*, 2007, **124**, 213–216.
60. G. Hodes, *Adv. Mater.*, 2007, **19**, 639–655.
61. L. Liu, E. Ma, R. Li, G. Liu, and X. Chen, *Nanotechnology*, 2007, **18**, 015403.
62. K. Binnemans and C. Görrler-Walrand, *J. Rare Earths*, 1996, **14**, 173–180.
63. D. B. Pi, F. Wang, X. P. Fan, M. Q. Wang, and Y. Zhang, *Spectrochim. Acta, Part A*, 2005, **61**, 2455–2459.
64. S. Som and S. K. Sharma, *J. Phys. D. Appl. Phys.*, 2012, **45**, 415102.
65. G. Blasse, *Phys. Lett. A*, 1968, **28**, 444–445.
66. F. Fong, L. Vredevoe, and R. De Wames, *Phys. Rev.*, 1968, **170**, 412–417.
67. S. Cotton, *Lanthanide and Actinide Chemistry*, 2nd edn.
68. G. Blasse, *J. Phys. Chem. Solids*, 1989, **50**, 99.
69. P. Ptacek, H. Schäfer, O. Zerzouf, K. Kömpe, and M. Haase, *Cryst. Growth Des.*, 2010, **10**, 2434–2438.
70. F. Zhang, Y. Wang, and Y. Tao, *Phys. Procedia*, 2012, **29**, 55–61.
71. Y. H. Wang, T. Endo, X. Guo, Y. Murakami, and M. Ushirozawa, *J. Soc. Inf. Disp.*, 2004, **12**, 495.
72. Y. Wang, X. Guo, T. Endo, Y. Murakami, and M. Ushirozawa, *J. Solid State Chem.*, 2004, **177**, 2242–2248.
73. C. H. Kim, I. E. Kwon, C. H. Park, Y. J. Hwang, H. S. Bae, B. Y. Yu, and C. H. Pyun, *J. Alloy. Compd.*, 2000, **311**, 33–39.
74. J. R. Lakowicz, *Principles of Fluorescence Spectroscopy*, Springer, Baltimore, third., 2006.
75. C. Kodaira, *J. Lumin.*, 2003, **101**, 11–21.
76. G. S. Ofelt, *J. Chem. Phys.*, 1962, **37**, 511.
77. B. Judd, *Phys. Rev.*, 1962, **127**, 750–761.
78. C. K. Jørgensen and R. Reisfeld, *J. Less-Common Met.*, 1983, **93**, 107–112.
79. B. M. Walsh, *Adv. Spectrosc. Lasers Sens.*, 2006, 403–433.
80. S. Tanabe, T. Hanada, T. Ohyagi, and N. Soga, *Phys. Rev. B*, 1993, **48**, 10591–10594.

## Table of Contents

The crystal structure of gadolinium oxyfluoride was revised. Luminescent properties of the  $\text{Eu}^{3+}$ -doped materials were characterized by the luminescence spectroscopy.

