

FD Corrosion Chemistry

Journal:	<i>Faraday Discussions</i>
Manuscript ID:	FD-ART-12-2014-000256.R1
Article Type:	Paper
Date Submitted by the Author:	22-Jan-2015
Complete List of Authors:	Shrestha, Buddha; Max-Planck-Institute for Iron Research, Bashir, Asif; Max-Planck-Institute for Iron Research, Anka, Genesis; Max-Planck-Institute for Iron Research, Valtiner, Markus; Max-Planck-Institute for Iron Research, Renner, Frank; Hasselt University, Institute for Materials Research

Localized dealloying corrosion mediated by self-assembled monolayers used as an inhibitor system

B. R. Shrestha¹, A. Bashir¹, G. N. Ankah¹, M. Valtiner¹, F.U. Renner^{1,2*}

¹*Max-Planck-Institut für Eisenforschung GmbH, Max-Planck-Straße 1, D-40237 Düsseldorf, Germany*

²*Institute of Materials Research (IMO), Hasselt University, Wetenschapspark 1, B-3590 Diepenbeek, Belgium*

*corresponding author: frank.renner@uhasselt.be

Abstract

The structure and chemistry of thiol or selenol self-assembled organic monolayers have been frequently addressed due to the unique opportunities in functionalization of materials. Such organic films can also act as effective inhibition layers to mitigate oxidation or corrosion. Cu-Au alloy substrates covered by self-assembled-monolayers show a different dealloying mechanism compared to bare surfaces. The organic surface layer inhibits dealloying of noble metal alloys by a suppression of surface diffusion at lower potentials but at higher applied potentials dealloying proceeds in localized regions due to passivity breakdown. We present an in-situ atomic force microscopy study of a patterned thiol layer applied on Cu-Au alloy surfaces and further explore approaches to change the local composition of the surface layers by exchange of molecules. The pattern for the in-situ experiment has been applied by micro-contact printing. This allows the study of corrosion protection with its dependence on different molecule densities at different sites. Low-density thiol areas surrounding the high-density patterns are completely protected and initiation of dealloying proceeds only along the areas with lowest inhibitor concentration. Dealloying patterns are highly influenced and controlled by molecular thiol to selenol exchange and are also affected by introducing structural defects such as scratches or polishing defects.

Keywords: Dealloying, self-assembled monolayers, nanoporous gold, selective dissolution, surface cracks, electrochemical interface.

Introduction

Corrosion is a major problem in various technical fields from the oil, gas, and chemical industry¹ to biomedical implants^{2, 3} or infrastructures⁴. In particular, premature catastrophic failure of structural components can be initiated by corrosion and poses a considerable risk for the environment and human society. Several studies report on the huge economical loss caused by corrosion each year. Considerable effort has therefore been made to design and develop complex alloys which deliver good mechanical properties as well as excellent corrosion resistance. Unfortunately, such corrosion resistant alloys often contain large quantities of expensive elements such as Cr, Ni, or Mo. One further way to mitigate corrosion of materials in applications is the use of inhibitors and organic systems are today widespread. Especially the oil and gas industry is a large consumer of organic inhibitors¹. At the same time there is also a large research effort to find environmentally friendly inhibitors⁵. The effect of inhibitors varies often depending on (even slight) changes in the environment, temperature, or protected materials, even “from one oil well to another”¹. A better understanding of the underlying mechanisms of corrosion protection by organic inhibitors is therefore needed. A true mechanistic understanding on the atomic and molecular level is so far widely lacking. Thiol and selenols based films have been employed for oxidation and corrosion protection of copper⁶⁻¹⁰. The formation of self-assembled organic monolayer films (SAMs) based on various thiols and selenols has been widely studied due to the unique opportunities in functionalization of materials. In particular, with the wide and detailed knowledge of the structure and chemistry of such often highly ordered films on the molecular level, SAMs provide a promising model system for fundamental corrosion studies.

Molecular self-assembly of SAMs is controlled through a strong covalent bonding to a substrate and non-covalent interactions between the molecules such as van der Waals forces, or π - π interactions^{11, 12}. Common examples include the formation of liquid crystal phases, micelles, vesicles, and Langmuir films¹³. Most SAMs are based on thiol or lately selenol

molecules on Au, Ag, Pd, or Cu substrates¹¹⁻¹⁴. The large possible variety (Fig.1a) to combine the S- or Se-head group¹⁵⁻¹⁷ with different organic ends or chains enables many possibilities to control the structure of SAM films¹⁸. Recent research has concentrated on increasing the stability of the films by offering structural changes via exchange of molecules. For Au substrates selenols were found to be more stable than thiol-based molecules¹⁸. In general the stability of SAMs depends on the substrate symmetry and atomic distances in the surface plane as well as on the interplay with the chain interactions. The ability to form a well-ordered surface film thus depends often on the chosen chain length, an odd or even number of carbon atoms¹⁸ in the chain, or the existence of aromatic building blocks^{6, 19}. The presence of such SAMs plays an important role in dealloying.




Fig.1(a) Schematics showing the formation of organic SAM layer on metal substrate. (b) Schematics showing the formation of SAM patches during stamping and dealloying

Dealloying is one form of corrosion where less noble element/s (one or more) are selectively dissolved. The nobler element(s) accumulate and or diffuse on the surface leading to passivation. At lower overpotentials above the equilibrium potential of Cu, bare Cu₃Au(111) surfaces are covered by an ultrathin film of Au of about 3 monolayers (ML) which protects from further selective dissolution of Cu, as was described earlier^{20, 21}. At intermediate overpotentials 10 - 15 ML thick Au islands are formed, before the protective effect of the Au barrier layer breaks down at the so-called critical potential (E_c) and bulk nanoporous Au is

formed^{22, 23} due to uniform dealloying. But the uniform dealloying can be overruled by the application of SAMs²³⁻²⁶. We have recently started research on the effects of SAMs on alloys²³⁻²⁵ based on noble metal binary systems²⁷. Cu-Au alloy substrates covered by SAMs show a different dealloying mechanism compared to bare surfaces. The organic surface layer inhibits dealloying corrosion of noble metal alloys by a suppression of surface diffusion. After passivity breakdown at higher applied potentials dealloying proceeds in localized regions. With progressing dealloying the process results in the appearance of surface cracks which form due to an accumulation of local stress related to a volume shrinking of nanoporous gold during dealloying²⁸. Together with the high level of control over the structural quality of self-assembled organic films, the system is a promising inhibitor model for understanding localized dealloying corrosion on the molecular scale.

Moreover, laterally structured SAMs can be applied on surfaces employing micro-contact printing (μ CP) using simple polydimethylsiloxane (PDMS) stamps²⁹⁻³³. The process is sketched in Fig. 1b. This approach includes local chemical reactions³¹⁻³³ and possibly also local exchange of molecules in the monolayer.

Here we report initial results of a larger research effort where we want to employ the great opportunities offered by molecularly homogeneous and heterogeneous self-assembled organic films used as model inhibitor films towards dealloying and in particular localized corrosion. The use of patterned SAMs and their effect on dealloying is well suited for in-situ atomic force microscopy to reveal molecular and atomic scale mechanisms of corrosion and corrosion protection. We will further discuss first results of a controlled exchange of thiol and selenol molecules to further manipulate the internal structure of the self-assembled inhibitor monolayers and the respective effect on dealloying corrosion.

Experimental

Standard H_2SO_4 was bought from Sigma Aldrich and diluted to get the required 0.1M solution. Self-assembled monolayers (SAMs) were prepared from 1mM and 4 mM solutions of thiophenol and benzeneselenol in absolute ethanol. The solutions were obtained by dissolving the required amount of the chemicals bought from Sigma Aldrich (98% purity). All solutions were freshly prepared before each experiment.

Here we report the results of characterization by different techniques including in-situ electrochemical dealloying by Atomic Force Microscope (AFM), the exchange of organic molecules (benzeneselenol, thiophenol) by Quartz Crystal Microbalance Dissipation (QCMD) and ex-situ Scanning Electron Micrographs recorded after electrochemical dealloying.

(i) In-situ electrochemical dealloying by Atomic Force Microscope: $\text{Cu}_3\text{Au}(111)$ single-crystals with orientation misfit less than 0.1° and polycrystalline alloys were obtained from MaTecK GmbH (Germany). The surfaces were prepared by repeating cycles of sputtering and annealing in an UHV chamber. The self-assembled monolayers (SAMs) were printed on well-prepared Cu_3Au crystals by using a polydimethylsiloxane (PDMS) stamp with $3\ \mu\text{m} \times 3\ \mu\text{m}$ square patterns. Cu_3Au crystals were patterned by micro-contact printing (μCP), to yield a surface consisting of target molecules. The desired SAMs were fabricated from the stamp after exposing to the 1mM solutions of target molecules. In-situ AFM experiments on CuAu surfaces were carried out under potentiostatic conditions in 0.1M H_2SO_4 . A platinum wire was used as a counter electrode and a silver/silver-chloride (Ag/AgCl) micro-reference electrode was used as reference electrode. The reference electrode is homemade according to the protocol published by Hassel et al.³⁴. All potentials in this paper are referred against Ag/AgCl. Prior to AFM experiments, the tip was cleaned in conc. sulfuric acid for 2 minutes, thoroughly rinsed with deionized water and ethanol and dried in stream of nitrogen. In situ-

AFM experiments were performed using a JPK NanoWizard I AFM (JPK Instruments AG, Berlin, Germany). A syringe pump (Micromechatronics AG, Germany) was used for pumping electrolyte. For electrochemical control a VoltaLab 40 potentiostat/galvanostat (Radiometer Analytical, France) was used. IR-drop compensation was performed using the current-interrupt method compensating for 95% of the measured IR-drop.

(ii) Adsorption and or replacement of organic molecules experiment by QCMD: Gold quartz crystals used in the QCMD experiments were purchased from Q-sense. 4 mM solutions of thiophenol and benzeneselenol were used for this experiment. First ethanol was passed into the QCMD system (Q-Sense E1 from Biolin Scientific, Finland) to minimize the drift of the system. The data obtained in ethanol is used as a base line of zero as all the SAM solutions were prepared in ethanol. The drift in the experiments are less than 0.5 Hzhour^{-1} . Once the drift is satisfactory, the adsorption of thiophenol, benzeneselenol and exchange of thiophenol by benzeneselenol or vice-versa on polycrystalline gold quartz crystals were measured during the flow of the respective solution.

(iii) Scanning Electron Micrographs after electrochemical dealloying: Polycrystalline Cu_3Au alloys were obtained from MaTeck GmbH (Germany) in polished form. The samples were first dipped in 0.1M H_2SO_4 for 1 hour for chemical cleaning. Then thiophenol SAM was deposited onto the surface by exposing the sample in 4mM SAM solution, and an eventual exchange of the thiophenol SAM was done by benzeneselenol by exposing the surface onto the respective solution. One cycle of CV was performed from -0.2 V to 1.0 V vs. Ag/AgCl in 0.1 M H_2SO_4 at 10mVs^{-1} and finally SEM images were taken using a Zeiss Leo scanning electron microscope.




Fig. 2: Alloy corrosion studied with patterned inhibitor films by in-situ AFM. We show the initial surface roughening and the evolution of the structure up to +805 mV. a) Typical pattern without halo effect (ideal press). The used pattern has been hard pressed to obtain a low-density halo around the central patch. b) 100 mV c) 255 mV d) 355 mV e) 455 mV f) 555 mV g) 705 mV b) 805 mV.

Results and discussions

Localized and inhomogeneous corrosion, the likely pattern in any realistic application, are much less understood than the homogeneous case. The application of structured thiol SAMs by a pre-formed PDMS stamp is well established simple lithography method. We have applied hexadecanethiol (HDT) SAM patterns of $3\mu\text{m} \times 3\mu\text{m}$ separated by a gap of $2\mu\text{m}$ as an inhomogeneous film of a model inhibitor. Fig. 2 shows the sequence of AFM images obtained by following the potential-dependent initiation of the dealloying process on the surfaces protected by the patterned thiol inhibitor film by in-situ atomic force microscopy. Fig. 2a represents this used stamp with a typical regular SAM pattern on pure gold. For our experiment we have intentionally pressed the stamp slightly harder on the $\text{Cu}_3\text{Au}(111)$ surface in order to obtain a halo or additional ring of a less dense thiol phase around the central patch (compare Fig. 2b). For the experiments we have chosen to image an area including 4 patches of HDT SAM, two of these shows a macroscopic defect which stems from a presumed defect

in the used stamp. The defects allow us to better correlate the structural changes and changes in the surface morphology around the patterns.

The sequence of in-situ images (Figs. 2b – 2h) from initially 100 mV to 805 mV does not show the typical Au islands which form on bare $\text{Cu}_3\text{Au}(111)^{20,21}$. At 805 mV which is close to the critical potential of bare Cu_3Au surfaces dealloying clearly occurs in the central part in between the applied thiol patches (area indicated by a white circle). Yet, part of the surface where no thiol film or islands (in the AFM images) can be perceived is also still completely stable as revealed by the flat morphology showing the typical crystalline steps of intact well-prepared single-crystalline surfaces.




Fig. 3: Magnified view of the structure after stepping the potential to 100 mV, 255 mV, 355, 455, 505 mV, 605 mV, 705 mV and 805 mV respectively.

Fig. 3 shows a selection of enlarged sections focussing on the thiol SAM around the two macroscopic defects of the sequence shown in Fig. 2. The central part representing a dense thiol SAM does not show considerable changes of the local film morphology although it appears slightly rougher at higher applied potentials. In contrast, the halo shows major changes. At 100 mV the halo is formed by a smooth continuous film with a clear height contrast in comparison to the central dense SAM. This directly points to a possible lying-down thiol phase within the halo film. The white arrows in the upper row of Fig. 3 follow a

thiol island which appears to be stable over the experimental run. The surrounding of this discernible island has nevertheless considerably changed at 705 mV. The initial dense and continuous lying-down phase has developed into islands covering the area of the initial halo. An interesting detail is that this area of the initial halo appears at the end with a clear height difference of the underlying substrate towards the outer surface which appears slightly lower. The same processes are mirrored in the lower row where the lower white arrow points to a thiol island which initially grows but finally vanishes completely. Such phenomena of evolution and disappearance of islands generated from organothiolate³⁵ SAMs/Au(111) have previously been observed. Fig. 4 focusses on the image obtained at 805 mV and reveals a height difference of the surface below the thiol islands of the halo and the outer (Au-enriched) surface of exactly 2 monoatomic steps (about 0.48 nm, a double step on Au(111)). On the outer surface mono-atomic steps are present (about 0.24 nm step height). The higher resolution image also reveals that the formed thiol islands within the halo area have the same height as the initial SAM of the inner dense core of the applied pattern. Above the critical potential, at 805 mV, the area in between the thiol SAM undergoes dealloying leaving part of the surface in the vicinity of the halo region unaltered. Thus an area in the form of a second ring becomes evident around the printed central dense SAM where apparently thiol molecules again influence the stability of the surface and protect from dealloying attack.




Fig. 4: (a) High resolution atomic force micrograph showing the structure of Cu_3Au alloy surface after stepping and holding the potential at 805 mV.

Fig. 5 depicts the AFM images of Fig. 2 in phase mode. The phase signals along the images indicate a reason for the observed second or outer halo area. At lower potentials, only one homogeneous halo ring around the central part is visible (Fig. 5 a-c). But at higher potentials, another bright halo ring becomes visible (Fig. 5 d-h) due to diffusion of thiol from the initial halo. Thus, we interpret this region as a lower-density thiol phase. This emerging second ring (see white arrow) extends right to the middle area of the image where dealloying commences (white circle in Fig. 6h).




Fig. 5: Phase images of the structure after stepping the potential to 100 mV, 255 mV, 355, 455 mV, 505 mV, 605 mV, 705 mV and 805 mV respectively.

Fig. 6 and Fig. 7 focus on the area where dealloying is clearly visible at potentials of 805 mV or higher. The first contrasting and important feature to our previous study on bare Cu_3Au surfaces^{20,21} is no formation of Au islands. Au islands 10-15 ML thick are formed on Cu-Au alloys at intermediate potentials well below the critical potential. Above the critical potential finally a bulk nanoporous Au network is formed due to passivity breakdown of Au film. The suppression of the formation of Au islands was nevertheless observed in experiments where a continuous self-assembled thiol film was applied²³ and localized nanoporous etch pits appeared at the anodically shifted critical potential. The site of dealloying is given in this

experiment by the applied pattern of SAM and line profiles in the attacked regions clearly show the progression of dissolution (Fig. 6c and 6f). Initially at 805 mV, the observed bottom surface is about 1 nm lower than that of the surrounding area, and later at 905 mV, the pitted area is about 3 nm deep (Fig. 6c and 6f). To accumulate about 1 ML of Au, Cu from about 4 ML of Cu_3Au has to be removed by selective dissolution. In other words, a pit of 3 nm points to an accumulated Au thickness of about 1 nm, i.e. the dealloying process is still in an initial state. Full ligaments of a nanoporous structure are typically in the order of 10-40 nm.




Fig.6: High-resolution AFM images and height profiles along the indicated lines at 805 mV (a-c) and 905 mV (d-f).

The evolution of the morphology at the locally attacked sites during dealloying is also interesting to follow. Initial individual islands are first forming in low density before dealloying proceeds into the bulk. Fig.7 shows one sequence recorded from the inner part of an area undergoing dealloying. The receding bottom surface is initially following the original atomic steps of the well-prepared surface. With further dealloying the interface develops higher roughness and the islands cover the interface more densely. Here the island formation is at potentials close to E_c , the first step in the evolution of nanoporosity. The surface

morphology clearly resembles the island formation on bare Cu_3Au surfaces at much lower potentials and can be clearly distinguished from other alloys such as Cu-Pd ³⁶.




Fig. 7: High resolution atomic force micrograph showing the structure of inner region with visible dealloying while holding the potential at 805 mV at different times.

The in-situ AFM imaging was stopped at 905 mV and SEM images such as shown in Fig. 8a were taken. Dealloying processes have visibly taken place over a large sample area and it always occurs at the farthest site from the printed SAM patches. The dense central thiol SAM as well as the first halo around this central area is visible. Comparing SEM images with the in-situ AFM images it can be inferred that, a large part of the area in between the SAM patches and also their halo is clearly free of dealloying and the actual dealloying has taken place only at limited small area. Few of these potential dealloying sites are fully protected allowing no visible dealloying at all. Part of the on first sight thiol-free area was therefore apparently protected from massive Cu dissolution. We nevertheless note here that some limited number of spots have undergone more severe dealloying attack. These originate at sites where visibly one of the central thiol patches is missing, i.e. the printing process has not properly succeeded and dealloying has locally spread out over a larger region. Due to such flaws and their associated inhomogeneous current distribution, it is not possible to correlate the measured total current with the observed changes in morphology, in particular, the local

observation by AFM. Yet, since dissolution is a kinetically fast process, we can conclude that the applied potentials are homogeneous over the surface.




Fig. 8: (a) SEM image of Cu_3Au (111) surface after the in-situ AFM experiment up to 905 mV. (b) Images after dealloying of a Cu_3Au polycrystalline surface modified with a continuous self-assembled mixed aminobenzenethiol monolayer. (c) SEM images of a grain surface partly free of thiols after a potential step to 1.3 V for 15s and a CV.

When we compare dealloying from patterned thiol-modified (current study) with dealloying from homogeneously thiol-modified alloys (previous study²³) a few interesting aspects can be understood. With the printed pattern of SAM, we could control the site where dealloying corrosion initiates. In contrast, on homogeneously covered thiol-surfaces a stochastic distribution of dealloying sites has been described²³. For these sites, the separation is much larger as natural structural inhomogeneity as for example the typical domain size as exemplified for a surface initially modified by a mixed aminobenzenethiol film²⁴ in Fig. 8b. Still an open question therefore is the nature of the potential initiation site. Approaching this problem by pre-patterned inhomogeneous SAMs may well contribute to the molecular-level understanding of the inhibition effect. A further approach is represented in Fig. 8c where an initially continuous ethanethiol monolayer formed on Cu_3Au was partially removed by a short oxidative potential step. The effective removal of ethanethiol by such an oxidation step has been observed on Au by in-situ electrochemical surface-sensitive X-ray diffraction employing synchrotron light²⁵. This process results in an inhomogeneous dealloying process (Fig. 8c).

The driving force for these experiments has been to advance our understanding of the effect of structural inhomogeneity on the onset of dealloying for inhibitor-covered surfaces. Yet chemical or molecular inhomogeneity will potentially play a large role and provides further means to manipulate and control the stability of inhibitor-covered alloy surfaces.




Fig. 9: Plot showing the areal mass change with time during the adsorption or adsorption and exchange of respective molecules. Red line shows the adsorption of thiophenol molecule first and then replacement by benzeneselenol. Black line represents the curve obtained during adsorption of benzeneselenol and blue line shows the adsorption of benzeneselenol and potential exchange of with thiophenol.

Molecular inhomogeneity can be deliberately introduced by exchanging part of the applied SAM on the molecular level and can be simultaneously monitored by QCMD as the sensitivity of the technique is few ngcm⁻². Fig. 10 shows the areal mass change on gold quartz crystals during the adsorption and exchange of thiophenol by benzeneselenol or vice-versa. The base line shown till 300 seconds is the data obtained while ethanol was passed into the QCMD. Since all SAMs were assembled in ethanol, ethanol was referenced as base line. As shown in Fig. 9, after 300 seconds of passing ethanol, solutions containing SAMs were passed and their adsorption increases the areal mass in each case. In two other experiments another (thiophenol or benzeneselenol) molecule was passed after 600 seconds which either increased

(see red line) or did not show any effect (see blue line) on the areal mass. Some limited disturbance of the measurement system is caused during the process of solution change.




Fig. 10: SEM images after dealloying of a Cu_3Au polycrystalline surface modified first with a self-assembled thiophenol and exchanged with benzeneselenol monolayer. (a) - (d) SEM image of surface cracks after one CV from -0.2 to 1.0 V vs Ag/AgCl at 10 mVs^{-1} in $0.1 \text{ M H}_2\text{SO}_4$.

From Kaefer et al.³⁷ we derive 26.1 ngcm^{-2} and 10.16 ngcm^{-2} of benzeneselenol and thiophenol, respectively³⁷. Thus, we see in Figure 9 that a monolayer of benzeneselenol and thiophenol is formed when the respective SAMs are passed to the crystal (see black and red line) but when replacing the thiophenol SAM by benzeneselenol (see red line), we find that it is about 80% exchanged. When thiophenol was passed the areal mass decreased slightly, indicating that there is replacement of thiophenol SAMs by benzeneselenol as well. Here the value also decays towards a ratio of about 2.1, indicating a benzeneselenol area of $\sim 85\%$. Interestingly, the exchange from a full benzeneselenol appears to exhibit slower exchange kinetics, compared to exchanging thiophenol by benzeneselenol. Yet, both ways converge to coverage of approximately 80-85% benzeneselenol and 20-15% thiophenol.

Based on the exchange, we expect different thin-film properties, and as such a moderation of the dealloying process. These results on molecular exchange between have

been then applied to a polycrystalline Cu₃Au foil for a first test of respective changes in the behavior during dealloying corrosion. Fig. 10 shows the SEM recorded after the exchange of thiophenol SAM by benzeneselenol according to Fig. 9 (red curve). As seen in Fig. 9, the mass obtained during exchange of thiophenol with benzeneselenol is not same as when benzeneselenol alone is passed. So, we conclude that the exchange process did not replace thiophenol by 100%. The polished surface was then dealloyed by a potential sweep from -200 mV to 1 V and back with a rate of 10 mVs⁻¹. As a result, the alloy is non-homogeneously dealloyed as can be seen in Fig. 10 where the brighter regions represent the dealloyed regions. Round as well as slightly elongated dealloyed areas with typical dimensions of between 1 μm and maximum 20 μm can be distinguished. Some polishing lines are also visible but, in general, the dealloyed regions are rather independent of these defect lines. The larger dealloyed regions, however, often show cracks along the crossing polishing lines. Independent of the cracking behavior we can conclude that the exchange process did indeed significantly change the dealloying initiation as from comparison of Fig. 8(b) and Fig 10(b). With a homogeneous SAM dealloying occurs purely local, producing round areas in the beginning which later form cracks (Fig. 8b) but we see dealloying in more elongated and outspread forms indicating dealloying is not purely local anymore (Fig 10b). Routes to control the growth and behavior of organic molecules on metal surfaces are also important for functionalized interfaces, for example in sensor applications. Inhibition of corrosion is another economically important process where metal-organic interfaces play a crucial role. Most of today's inhibitors are organic in nature¹. Dealloying of Cu-Au alloys is due to clearly distinguished stages of surface evolution (ultrathin film – Au islands – nanoporosity) of the bare substrate and the localized nature of SAM-modified (inhibited) surfaces an in our view interesting model system. Here we addressed different aspects of control over a localized corrosion process on Cu-Au alloys. Printed structured patterns produce a local variation of different inhibitor densities and enable by a variation of the basic dimensions of the pattern to

address the important questions of inhibitors and mechanistic understanding of material's (surface) protection on the molecular level. Also a combination of approaches with molecular exchange, the second aspect presented here, is possible. We presented the manipulation of the internal structure of a given SAM by molecule exchange processes as a promising approach to address the molecular stability of an inhibitor monolayer film towards dealloying.

As reported for Cu and Au the surface mobility may be orders of magnitude higher in solution (in particular when halides are present) than in vacuum or dry atmospheres³⁸⁻⁴¹. Smaller structural defects should be removed by gentle chemical annealing in acidic electrolytes but larger polishing scratches will not be removed by this simple method (requires a number of sputter-annealing cycles in UHV). Using such a surface with still present scratches, however, allows in parallel to follow the effect of such macroscopic defects on the dealloying behavior. Although a slight increase of dealloying probability is visible, the density and size of the dealloyed sites are not largely influenced by these defects. But higher numbers of cracks are clearly visible along such polishing lines. Also, the cracks follow mostly the direction of the defect or polishing lines. Macroscopic structural defects thus do clearly influence the stability of our chosen model system Cu_3Au during dealloying.

Conclusion

The conclusions that are derived for the current study are as follows:-

- In-situ AFM studies of dealloying corrosion of surfaces modified with a micro-structured inhibitor pattern applied by μ -contact printing is a promising approach to study the effect of inhomogeneous organic molecular films.
- Even a small density of hexadecanethiol SAM molecules can suppress the typical Au island formation on $\text{Cu}_3\text{Au}(111)$ at intermediate potentials.
- This study also shows the potential dependent mobility of thiol islands. Diffusion of hexadecanethiol molecules can take place at elevated potentials.

- Only at higher potentials, dealloying initiates at the areas with the lowest concentration of thiol
- The local dealloying pattern is highly influenced and controlled by a molecular exchange of thiols to selenols and is also affected by introducing structural defects such as scratches or polishing defects (lines).

References

1. M. Finsgar and J. Jackson, *Corrosion Science*, 2014, 86, 17-41.
2. Y. Chen, Z. Xu, C. Smith and J. Sankar, *Acta Biomaterialia*, 2014, 10, 4561-4573.
3. R. A. Antunes and M. C. Lopes de Oliveira, *Acta Biomaterialia*, 2012, 8, 937-962.
4. H. H. Uhlig, ed. R. W. Revie, John Wiley & Sons, Inc., Third Edition edn., DOI: 10.1002/9780470872864.
5. E. E. Oguzie, C. B. Adindu, C. K. Enenebeaku, C. E. Ogukwe, M. A. Chidiebere and K. L. Oguzie, *Journal of Physical Chemistry C*, 2012, 116, 13603-13615.
6. J. Denayer, J. Delhalle and Z. Mekhalif, *Journal of Electroanalytical Chemistry*, 2009, 637, 43-49.
7. G. Fonder, J. Delhalle and Z. Mekhalif, *Applied Surface Science*, 2010, 256, 2968-2973.
8. P. E. Laibinis and G. M. Whitesides, *Journal of the American Chemical Society*, 1992, 114, 9022-9028.
9. G. K. Jennings, J. C. Munro, T. H. Yong and P. E. Laibinis, *Langmuir*, 1998, 14, 6130-6139.
10. S. Hosseinpour, M. Gothelid, C. Leygraf and C. M. Johnson, *Journal of the Electrochemical Society*, 2014, 161, C50-C56.
11. J. C. Love, L. A. Estroff, J. K. Kriebel, R. G. Nuzzo and G. M. Whitesides, *Chemical Reviews*, 2005, 105, 1103-1169.
12. F. Schreiber, *Progress in Surface Science*, 2000, 65, 151-256.
13. J. C. Love, D. B. Wolfe, R. Haasch, M. L. Chabinyc, K. E. Paul, G. M. Whitesides and R. G. Nuzzo, *Journal of the American Chemical Society*, 2003, 125, 2597-2609.
14. A. Bashir, D. Kaefer, J. Mueller, C. Woell, A. Terfort and G. Witte, *Angewandte Chemie-International Edition*, 2008, 47, 5250-5252.
15. J. V. B. J.A. Martínez, R.C. Milánc, J. Herrera, M.H. Farías, M.P. Hernández, , *Applied Physics Letters*, 2014, 320, 287-293.
16. C. Vericat, M. E. Vela, G. A. Andreasen, R. C. Salvarezza, F. Borgatti, R. Felici, T. L. Lee, F. Renner, J. Zegenhagen and J. A. Martin-Gago, *Physical Review Letters*, 2003, 90.
17. J. Jia, A. Bendounan, H. M. N. Kotresh, K. Chaouchi, F. Sirotti, S. Sampath and V. A. Esaulov, *Journal of Physical Chemistry C*, 2013, 117, 9835-9842.
18. K. Szlagowska-Kunstman, P. Cyganik, B. Schuepbach and A. Terfort, *Physical Chemistry Chemical Physics*, 2010, 12, 4400-4406.
19. W. Azzam, A. Bashir, A. Terfort, T. Strunskus and C. Woll, *Langmuir*, 2006, 22, 3647-3655.
20. F. U. Renner, A. Stierle, H. Dosch, D. M. Kolb, T. L. Lee and J. Zegenhagen, *Nature*, 2006, 439, 707-710.
21. F. U. Renner, A. Stierle, H. Dosch, D. M. Kolb, T. L. Lee and J. Zegenhagen, *Physical Review B*, 2008, 77.
22. J. Erlebacher, M. J. Aziz, A. Karma, N. Dimitrov and K. Sieradzki, *Nature*, 2001, 410, 450-453.
23. A. Pareek, S. Borodin, A. Bashir, G. N. Ankah, P. Keil, G. A. Eckstein, M. Rohwerder, M. Stratmann, Y. Gruender and F. U. Renner, *Journal of the American Chemical Society*, 2011, 133, 18264-18271.
24. A. Pareek, G. N. Ankah, S. Cherevko, P. Ebbinghaus, K. J. J. Mayrhofer, A. Erbe and F. U. Renner, *Rsc Advances*, 2013, 3, 6586-6595.
25. G. N. Ankah, A. Pareek, S. Cherevko, J. Zegenhagen and F. U. Renner, *Electrochimica Acta*, 2014, 140, 352-358.

26. F.U. Renner, G. N. Ankah, B.R. Shrestha, D. Ma, A. Bashir, M.J. Duarte, M. Nellesen, A. Khorashadizadeh, U. Biedermann, D. Raabe, M. Valtiner, *submitted*.
27. T. P. Moffat, F. R. F. Fan and A. J. Bard, *Journal of the Electrochemical Society*, 1991, 138, 3224-3235.
28. S. Parida, D. Kramer, C. A. Volkert, H. Roesner, J. Erlebacher and J. Weissmueller, *Physical Review Letters*, 2006, 97.
29. A. Kumar and G. M. Whitesides, *Applied Physics Letters*, 1993, 63, 2002-2004.
30. J. L. Wilbur, A. Kumar, H. A. Biebuyck, E. Kim and G. M. Whitesides, *Nanotechnology*, 1996, 7, 452-457.
31. J. Tien, A. Terfort and G. M. Whitesides, *Langmuir*, 1997, 13, 5349-5355.
32. L. Yan, C. Marzolin, A. Terfort and G. M. Whitesides, *Langmuir*, 1997, 13, 6704-6712.
33. L. Yan, X. M. Zhao and G. M. Whitesides, *Journal of the American Chemical Society*, 1998, 120, 6179-6180.
34. A. W. Hassel, K. Fushimi and M. Seo, *Electrochemistry Communications*, 1999, 1, 180-183.
35. W. Azzam, A. Bashir, P. U. Biedermann and M. Rohwerder, *Langmuir*, 2012, 28, 10192-10208.
36. G. N. Ankah, S. Meimandi and F. U. Renner, *Journal of the Electrochemical Society*, 2013, 160, C390-C395.
37. D. Kaefer, A. Bashir and G. Witte, *Journal of Physical Chemistry C*, 2007, 111, 10546-10551.
38. J. Wiechers, T. Twomey, D. M. Kolb and R. J. Behm, *Journal of Electroanalytical Chemistry*, 1988, 248, 451-460.
39. C. Alonso, R. C. Salvarezza, J. M. Vara and A. J. Arvia, *Electrochimica Acta*, 1990, 35, 1331-1336.
40. M. Giesen and D. M. Kolb, *Surface Science*, 2000, 468, 149-164.
41. M. Giesen, *Progress in Surface Science*, 2001, 68, 1-153.