

NJC

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/njc

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

ARTICLE TYPE

2-Diphenylaminothiophene as the donor of porphyrin sensitizers for dye-sensitized solar cells

Yueqiang Wang^a, Lu Xu^a, Xiaodong Wei^a, Xin Li^b, Hans Ågren^b, Wenjun Wu^a, and Yongshu Xie^{*a}

Received (in XXX, XXX) Xth XXXXXXXXXX 20XX, Accepted Xth XXXXXXXXXX 20XX

DOI: 10.1039/b000000x

Four novel D- π -A porphyrin dyes (YQ1–YQ4) with 2-diphenylaminothiophene attached at the *meso*-position as the electron donor have been synthesized and used as the sensitizers for dye sensitized solar cells (DSSCs). 4-Ethynylbenzoic acid and 2-cyanoacrylic acid were incorporated as the anchoring moieties in YQ1, and YQ2–YQ4, respectively. Due to the extended conjugation size, the absorption spectra of YQ2–YQ4 showed Soret band maxima in the range of 447–468 nm, which is red shifted as compared to that of 446 nm for YQ1. Furthermore, in comparison with most reported porphyrin dyes with similar structures, YQ1–YQ4 demonstrate obviously red-shifted absorption maxima and broadened Soret bands, indicating that these porphyrin dyes may be developed as promising DSSC sensitizers. The electrochemical studies and DFT calculations indicated that all the four dyes were capable of serving as DSSC sensitizers. Thus, DSSCs were fabricated based on these dyes. The cells based on YQ4 showed the power conversion efficiency of 5.00%, which is higher than those of 4.23% and 4.38% for YQ2 and YQ3, respectively. This observation may be attributed to the suppression of the dye aggregation by the hexyl group attached to the thienyl ring of YQ4. On the other hand, YQ2–YQ4 demonstrated lower efficiencies compared with YQ1, which may be ascribed to the floppy structures of the cyanoacrylic acid-based porphyrins that provide free space for charge recombination. As a result, the DSSCs based on YQ1 exhibited the highest efficiency of 6.01%. This work demonstrates that the introduction of 2-diphenylaminothiophene to a porphyrin framework can obviously red-shift and broaden the absorption bands of the porphyrin dyes, resulting in high solar cell efficiencies. Hence, the introduction of 2-diphenylaminothiophene as the electron donor may be promising for the design of efficient porphyrin-based DSSC sensitizers.

Introduction

Dye-sensitized solar cells (DSSCs) have been demonstrated to be promising in utilizing the solar energy.¹ In the past decade, many efforts have been devoted to the development of efficient DSSC sensitizers.² In this respect, many ruthenium-based sensitizers have been successfully developed.³ On the other hand, increasing interests have been focused on the development of new efficient organic sensitizers because of their advantages of low cost, high molar absorption coefficients, and facile modulation of the properties by the modification of the molecular structures.⁴ As is well known, the donor- π -acceptor (D- π -A) frameworks are the most commonly adopted for organic sensitizers.⁵ In this respect, we have reported various dyes incorporating indoline and isophorone units.⁶ Among the organic dyes, porphyrins have been considered to be promising sensitizers inspired by their important roles in the natural photosynthesis system.⁷ They have strongly absorbing Soret bands (400–450 nm) and moderately absorbing Q-bands (550–600 nm) from the visible to the near-IR region.⁸ Thus, numerous porphyrins have been synthesized and used as DSSC

sensitizers.⁹ In this respect, the highest efficiency of 13.0% achieved for DSSCs has been reported by Grätzel and co-workers for a porphyrin dye SM315, using 2,1,3-benzothiadiazole as an electron accepting unit, which is conjugated with the anchoring benzoic acid group.¹⁰

The electron rich thienyl group has been widely utilized in porphyrin-based sensitizers to enhance and red-shift the absorption of the dyes.¹² Based on our previous work on the porphyrin dyes utilizing triphenylamine and carbazole as the donors,¹¹ herein, 2-diphenylaminothiophene was introduced to the porphyrin framework as the donor, with the thienyl group used to increase the electron donating character. Thus, we synthesized a series of novel porphyrin sensitizers (YQ1–YQ4, Scheme 1).


The planar structural feature of the porphyrins may facilitate the formation of aggregates. Thus, the porphyrins were all enveloped with alkoxy chains to decrease the dye aggregation and to retard the charge recombination process.¹³ In addition, various acceptors were employed (Scheme 1) to further optimize the dye performance. Thus, YQ1–YQ4 were synthesized and utilized as sensitizers to fabricate DSSCs, and the results indicated that YQ1 exhibited the highest power conversion

efficiency of 6.01%, which is higher than those for our previously reported porphyrin dyes containing triphenylamine donors.^{11a}

Experimental Section

Materials and reagents

All reagents and solvents were obtained from commercial sources and used without further purification unless otherwise noted. THF was dried over 4 Å molecular sieves, and distilled under nitrogen from sodium benzophenone prior to use. Tetrabutylammonium hexafluorophosphate (TBAPF₆) was vacuum-dried for 48 h. The transparent FTO conducting glass (fluorine-doped SnO₂, transmission >90% in the visible range, sheet resistance 15Ω/square) and the TiO₂ paste was purchased from Geao Science and Educational Co. Ltd. The FTO conducting glass was washed with a detergent solution, deionized water, ethanol, and acetone successively under ultrasonication for 20 min prior to use. Dibromoporphyrin **1** and 3-hexyl-5-ethynylthiophene-2-carbaldehyde were prepared according to the reported procedures.^{13c, 14}



Scheme 1 Molecular structures of the porphyrin sensitizers.

Equipments and apparatus

¹H NMR and ¹³C NMR spectra were obtained using a Bruker AM 400 or 500 MHz spectrometer at 298 K with tetramethylsilane (TMS) as the internal standard. Matrix-assisted laser desorption/ionization time-of-flight mass spectrometry (MALDI-TOF-MS) was measured using a Shimadzu-Kratos model Axima CFR+ mass spectrometer with dithranol as the matrix. UV-Vis absorption spectra were recorded on a Varian Cary 100 spectrophotometer and fluorescence spectra were recorded on a Varian Cray Eclipse fluorescence spectrophotometer. The cyclic voltammograms of the dyes were obtained in acetonitrile with a Versastat II electrochemical workstation (Princeton Applied Research) using 0.1 M TBAPF₆ (Aldrich) as the supporting electrolyte, the sensitizer attached to a nanocrystalline TiO₂ film deposited on the conducting FTO glass as the working electrode, a platinum wire as the counter electrode, and a regular calomel electrode in saturated KCl solution as the reference electrode. The scan rate was 100 mV s⁻¹.

Photovoltaic measurements were performed by employing an AM 1.5 solar simulator equipped with a 300 W xenon lamp (model no. 91160, Oriel). The power of the simulated light was calibrated to 100 mW cm⁻² using a Newport Oriel PV reference cell system (model 91150 V). I–V curves were obtained by applying an external bias to the cell and measuring the generated photocurrent with a model 2400 source meter (Keithley Instruments, Inc. USA). The voltage step and delay time of the photocurrent were 10 mV and 40 ms, respectively. Action spectra of the incident monochromatic photon-to-electron conversion efficiency (IPCE) for the solar cells were obtained with a Newport-74125 system (Newport Instruments). The intensity of monochromatic light was measured with a Si detector (Newport-71640). The electrochemical impedance spectroscopy (EIS) measurements of all the DSSCs were performed using a Zahner IM6e Impedance Analyzer (ZAHNER-Elektrik GmbH & CoKG, Kronach, Germany), with the frequency range of 0.1 Hz–100 kHz and the alternative signal of 10 mV.

Fabrication of the solar cells

The procedure for preparation of TiO₂ electrodes and fabrication of the sealed cells for photovoltaic measurements were adapted from that reported by Grätzel and co-workers.¹⁵ A screen-printed double layer of TiO₂ particles was used as the photoelectrode. The detailed procedure was reported in our previous work.¹¹ The films were then immersed into a 0.2 mM solution of the dyes in a mixture of tetrahydrofuran (THF) and ethanol (EtOH) (volume ratio of 1:4) for 10 h at room temperature. The counter electrode was also prepared according to the procedure reported in our previous work.¹¹ Finally, the DSSCs were assembled, with the electrolyte solution containing 0.1 M LiI, 0.05 M I₂, 0.6 M 1-methyl-3-propyl-imidazolium iodide (PMII), and 0.5 M 4-tert-butylpyridine (TBP) in acetonitrile.

Syntheses of the dyes

The procedures for the syntheses of **3a–3d** are described in the Electronic Supplementary Information (ESI).

YQ1: A mixture of the porphyrin carboxylate **3a** (30 mg, 0.018 mmol) and LiOH·H₂O (30 mg, 0.72 mmol) in THF (30 mL) and H₂O (4 mL) was refluxed for 12 h under nitrogen. Then, the solvent was removed *in vacuo*. The residue was dissolved in THF and the precipitate was filtered off. The filtrate was concentrated *in vacuo* to afford the crude product, which was purified by column chromatography on silica gel to give the product as a green powder (25 mg, yield 85%). ¹H NMR (CDCl₃ : DMSO-*d*₆ = 1 : 2, 400 MHz, ppm): δ 0.27-0.35 (m, 8H), 0.52-0.56 (m, 16H), 0.66-0.81 (m, 20H), 0.84-1.12 (m, 40H), 1.13-1.20 (m, 8H), 3.85 (t, *J* = 6.4 Hz, 8H), 7.05-7.12 (m, 7H), 7.35-7.43 (m, 8H), 7.59 (d, *J* = 3.6 Hz, 1H, thieryl), 7.71 (t, *J* = 8.4 Hz, 2H, phenyl), 8.07 (d, *J* = 7.6 Hz, 2H, phenyl), 8.17 (d, *J* = 8.0 Hz, 2H, phenyl), 8.68 (d, *J* = 4.4 Hz, 2H, pyrrolic), 8.75 (d, *J* = 4.0 Hz, 2H, pyrrolic), 9.01 (d, *J* = 4.4 Hz, 2H, pyrrolic), 9.60 (d, *J* = 4.4 Hz, 2H, pyrrolic). MS (MALDI-TOF, *m/z*): [M] calcd for C₁₀₅H₁₃₁N₅O₆SZn, 1653.91; found, 1653.69. IR (KBr pellet, cm⁻¹): 2922(s), 2852(m), 2183(w), 2029(w), 1958(m), 1660(m), 1618(s), 1602(m), 1494(w), 1455(m), 1272(w), 1241(w), 1100(m), 994(m), 789(w).

YQ2: A mixture of **3b** (30 mg, 0.018 mmol) and cyanoacetic acid (6 mg, 0.073 mmol) in acetonitrile (10 mL) was heated to

reflux in the presence of piperidine (0.5 mL) for 10 h under nitrogen. After cooling, the mixture was diluted with CH_2Cl_2 (50 mL), washed with water and brine, dried over Na_2SO_4 , and evaporated under reduced pressure. The crude product was purified by column chromatography on silica gel to yield the product as a green powder (20 mg, yield 65 %). ^1H NMR (CDCl_3 : $\text{DMSO}-d_6 = 1 : 2$, 500 MHz, ppm): δ 0.43-0.49 (m, 8H), 0.60-0.67 (m, 16H), 0.77-0.84 (m, 20H), 0.87-1.12 (m, 40H), 1.14-1.21 (m, 8H), 3.84 (t, $J = 6.0$ Hz, 8H), 7.01 (d, $J = 8.5$ Hz, 2H, phenyl), 7.07-7.11 (m, 3H), 7.36-7.42 (m, 8H), 7.58 (d, $J = 2.5$ Hz, 1H, thienyl), 7.69 (t, $J = 8.0$ Hz, 2H, phenyl), 8.08 (d, $J = 8.0$ Hz, 2H, phenyl), 8.18 (d, $J = 8.5$ Hz, 2H, phenyl), 8.33 (s, 1H), 8.74 (d, $J = 4.5$ Hz, 2H, pyrrolic), 8.83 (d, $J = 5.0$ Hz, 2H, pyrrolic), 9.06 (d, $J = 4.5$ Hz, 2H, pyrrolic), 9.60 (d, $J = 5.0$ Hz, 2H, pyrrolic). MS (MALDI-TOF, m/z): [M] calcd for $\text{C}_{108}\text{H}_{132}\text{N}_6\text{O}_6\text{S}_2\text{Zn}$, 1704.92; found, 1705.46. IR (KBr pellet, cm^{-1}): 3357(br), 2922(s), 2851(s), 2180(w), 2027(w), 1959(m), 1723(m), 1658(m), 1632(s), 1467(m), 1410(m), 1181(w), 1139(w), 1175(w), 733(w).

YQ3: It was prepared according to the procedure same as that for **Y2**, except that **3c** (30 mg, 0.018 mmol) was used instead of **3b**. Yield: 21 mg, 68%. ^1H NMR (CDCl_3 : $\text{DMSO}-d_6 = 1 : 2$, 500 MHz, ppm): δ 0.23-0.30 (m, 8H), 0.39-0.50 (m, 16H), 0.67-0.78 (m, 20H), 0.85-1.06 (m, 40H), 1.08-1.14 (m, 8H), 3.80 (t, $J = 6.0$ Hz, 8H), 7.02 (d, $J = 8.5$ Hz, 2H, phenyl), 7.05-7.08 (m, 3H), 7.31-7.38 (m, 8H), 7.55 (d, $J = 3.5$ Hz, 1H, thienyl), 7.66 (t, $J = 8.5$ Hz, 2H, phenyl), 7.73 (d, $J = 4.0$ Hz, 1H, thienyl), 7.81 (d, $J = 4.0$ Hz, 1H, thienyl), 8.20 (s, 1H), 8.62 (d, $J = 4.5$ Hz, 2H, pyrrolic), 8.71 (d, $J = 4.5$ Hz, 2H, pyrrolic), 8.97 (d, $J = 4.5$ Hz, 2H, pyrrolic), 9.44 (d, $J = 4.5$ Hz, 2H, pyrrolic). MS (MALDI-TOF, m/z): [M] calcd for $\text{C}_{106}\text{H}_{130}\text{N}_6\text{O}_6\text{S}_2\text{Zn}$, 1710.88; found, 1710.92. IR (KBr pellet, cm^{-1}): 3358(br), 2922(s), 2851(s), 2179(w), 2030(w), 1958(m), 1659(s), 1632(s), 1468(w), 1455(s), 1410(w), 1178(w), 1099(w), 995(w), 790(w), 717(w).


YQ4: It was prepared according to the procedure same as that for **Y2**, except that **3d** (32 mg, 0.018 mmol) was used instead of **3b**. Yield: 21 mg, 64%. ^1H NMR (CDCl_3 : $\text{DMSO}-d_6 = 1 : 2$, 500

MHz, ppm): δ 0.37-0.45 (m, 8H), 0.51-0.64 (m, 16H), 0.74-0.86 (m, 20H), 0.88-1.12 (m, 43H), 1.16-1.22 (m, 8H), 1.65-1.70 (m, 4H), 2.00-2.07 (m, 4H), 3.26 (t, $J = 7.5$ Hz, 2H), 3.88 (t, $J = 5.5$ Hz, 8H), 7.05-7.14 (m, 7H), 7.34-7.45 (m, 8H), 7.62 (s, 1H, thienyl), 7.73 (t, $J = 8.0$ Hz, 2H, phenyl), 8.27 (s, 1H), 8.73 (d, $J = 5.0$ Hz, 2H, pyrrolic), 8.79 (d, $J = 5.0$ Hz, 2H, pyrrolic), 9.05 (d, $J = 4.5$ Hz, 2H, pyrrolic), 9.52 (d, $J = 4.5$ Hz, 2H, pyrrolic). MS (MALDI-TOF, m/z): [M] calcd for $\text{C}_{112}\text{H}_{142}\text{N}_6\text{O}_6\text{S}_2\text{Zn}$, 1794.97; found, 1794.97. IR (KBr pellet, cm^{-1}): 3359(br), 2922(s), 2852(s), 2166(w), 2030(w), 1956(m), 1659(w), 1632(w), 1588(m), 1493(w), 1455(s), 1393(w), 1374(w), 1289(w), 1247(w), 1181(w), 1100(s), 995(m), 790(m), 717(w).

Results and Discussion

Design and syntheses

As shown in **Scheme 1**, all the four porphyrins were designed on the basis of D- π -A frameworks. 2-Diphenylaminothiophene was introduced as the electron donor, and the porphyrin cores were wrapped with four dodecoyl chains at the phenyl *ortho*-positions with the purpose of suppressing the dye aggregation and preventing the approach of the electrolyte to the TiO_2 surface, and thus decreasing the I_3^- concentration in the vicinity of TiO_2 , resulting in the improved V_{oc} of the DSSCs.^{13c} In addition, to further investigate the effect of the acceptors on the cell performance, various acceptors were employed. Thus, dyes **YQ1–YQ4** were designed, and the synthetic routes are depicted in **Scheme 2**. The dibromoporphyrin **1**^{13c} was used to react with various ethynyl derivatives through Sonogashira coupling reactions to afford the intermediates **2a–2d**. 2-Diphenylaminothiophene was then attached to the meso-position via Stille coupling reactions in satisfactory yields. Finally, the target sensitizers were synthesized through hydrolysis or Knoevenagel condensation reactions. Consequently, dyes **YQ1–YQ4** were successfully synthesized in acceptable yields and fully characterized with NMR and HRMS (Fig. S1–S24).



Scheme 2 The synthetic routes for dyes **YQ1–YQ4**. Reaction conditions: (i) $\text{Pd}(\text{PPh}_3)_4$, CuI , TEA, THF, (ii) 2-diphenylamino-5-tributylstannylthiophene, $\text{Pd}(\text{PPh}_3)_4$, toluene, (iii) $\text{LiOH}\cdot\text{H}_2\text{O}$, THF, H_2O , (iv) cyanoacetic acid, piperidine, MeCN.




Fig. 1 (a) Absorption and (b) emission spectra of YQ1–YQ4 in THF.

Spectral properties


- Strong absorption characteristics are vital for efficient DSSC sensitizers. The UV-visible absorption spectra and steady-state fluorescence spectra of the dyes in THF are shown in Fig. 1, and the corresponding data are listed in Table 1.

Table 1 Absorption and emission data of the porphyrin dyes

Dyes	Absorption $\lambda_{\text{max}}/\text{nm}$ ($\epsilon/10^3 \text{ M}^{-1} \text{ cm}^{-1}$) ^a	Emission $\lambda_{\text{max}}/\text{nm}$ ^a
YQ1	446 (153), 575 (5.6), 632 (11.2)	644
YQ2	447 (59.7), 575 (4.1), 637 (9.1)	653
YQ3	468 (83.2), 578 (8.2), 653 (30.0)	673
YQ4	468 (64.0), 578 (6.0), 653 (23.0)	671

^aAbsorption and emission data were measured in THF. Excitation wavelengths/nm: 446 nm (YQ1), 447 nm (YQ2), 468 nm (YQ3), 468 nm (YQ4).

YQ1–YQ4 exhibit typical porphyrin absorption characteristics, with an intense Soret band in the range of 400–500 nm and less intense Q bands in the range of 550–720 nm. The Soret band for YQ1 is centred at 446 nm with the molar absorption coefficient of $1.53 \times 10^5 \text{ M}^{-1} \text{ cm}^{-1}$, and the corresponding bands are red shifted to 447, 468 and 468 nm for YQ2, YQ3 and YQ4, respectively. Meanwhile, the molar absorption coefficients are decreased to 0.64×10^5 – $0.83 \times 10^5 \text{ M}^{-1} \text{ cm}^{-1}$. Compared with YQ1, the Q bands for YQ2–YQ4 are also red shifted. These results indicate that YQ1 has stronger absorption in the short wavelength range. Whereas, YQ2–YQ4 have stronger absorption in the long wavelength range. In comparison with most reported porphyrin dyes with similar structures,¹⁶ all the four porphyrin dyes demonstrate obviously red-shifted absorption maxima and broadened Soret bands. For example, YQ1 shows similar Soret



Scheme 3 Molecular structures of reported porphyrin dyes CPZ^{16a}, DPZ1^{16a}, DPZ2^{16a}, LW2^{16b}, T3P^{16a, 16c}, and HT3P^{16c}.

- bands and an obvious red shift of the Q band in the long wavelength range, compared with the porphyrin dyes CPZ, DPZ1 and DPZ2 (Scheme 3)^{16a}, which have similar structures containing a carbazole or a methoxyphenyl unit as the donor.

Among the porphyrin dyes using 2-cyano-3-(5-ethynylthienyl) acrylic acid as the electron acceptor, **YQ3** and **YQ4** show 5 nm red shift of the Soret band compared to **LW2**^{16b} which contains N,N-dimethylaminophenyl unit as the electron donor. Compared with dyes **T3P** and **HT3P** which contain a triphenylamine unit as the donor,^{11a, 16c} **YQ1–YQ4** show broadened Soret bands. The red shift of the absorption peaks and broadened absorption may be attributed to the stronger electron-donating ability of the 2-diphenylaminothiophene unit compared with the other donors. Thus, the introduction of 2-diphenylaminothiophene may be promising for the fabrication of efficient DSSCs. For the fluorescence spectra in THF (Fig. 1b), the emission wavelength variation trend is similar to that of the absorption bands.




Fig. 2 Normalized UV-visible spectra of the porphyrins in THF and on the TiO₂ films (5 μm).

To better elucidate the absorption properties of the porphyrin dyes in DSSC devices, the absorption spectra of the porphyrin dyes on 5 μm transparent TiO₂ films were measured and shown in Fig. 2. Compared with the corresponding solution spectra, both the Soret and Q bands of the porphyrin/TiO₂ films were considerably broadened. The absorption bands are obviously blue-shifted for **YQ3** and **YQ4**, which may result from the deprotonation of the carboxylic acid group upon dye attachment to the TiO₂ surface,¹⁷ and/or the H-aggregation of the dye molecules on the TiO₂ films.¹⁸

Electrochemical behavior

To evaluate the possibility of electron transfer from the excited dye molecules to the conduction band (CB) of TiO₂, cyclic voltammetry measurements (Fig. 3) were performed on the porphyrin dyes adsorbed on the TiO₂ films in 0.1 M solution of tetra-n-butylammonium hexafluorophosphate in acetonitrile, and the corresponding data are listed in Table 2. It can be estimated from Fig. 3 that the first oxidation potentials for **YQ1–YQ4** dyes are 0.69, 0.69, 0.67 and 0.68 V, respectively, versus the normal hydrogen electrode (NHE). The energy gaps E_{0-0} are determined to be 1.95, 1.92, 1.88 and 1.88 V for **YQ1**, **YQ2**, **YQ3** and **YQ4**, respectively, through the intersection of the normalized absorption and emission spectra. Thus, the LUMO levels of these dyes (**YQ1–YQ4**) are calculated to be -1.26, -1.23, -1.21 and -1.20 V, respectively. The HOMO levels for these four dyes are

almost identical, which can be attributed to the similar electron-donating ability of the donors in the four dyes. On the other hand, the LUMO energy levels for **YQ2**, **YQ3** and **YQ4** are slightly lower than that of **YQ1**, which may be attributed to the difference in the acceptor moieties.




Fig. 3 The cyclic voltammetry curves of the dyes adsorbed to a nanocrystalline TiO₂ film deposited on conducting FTO glass.

To guarantee efficient electron injection from the LUMO of the porphyrin dyes into the CB of TiO₂, the LUMO levels must be higher than that of the conduction band edge of TiO₂. And the HOMO levels of the sensitizers must be lower than the redox potential of the electrolyte I⁻/I³⁻ couple to ensure efficient regeneration of the sensitizer cations following the photo-induced electron injection into the conduction band of TiO₂. As shown in Fig. 4, the LUMO levels of these dyes are more negative than the CB of TiO₂ (-0.5 V vs. NHE), indicating that electron injection from the excited states of the dyes into the CB of TiO₂ is energetically permitted. On the other hand, the HOMO levels of **YQ1–YQ4** are more positive than the iodine/iodide redox potential value (0.4 V vs. NHE), indicating that the oxidized dyes formed upon electron injection into the CB of TiO₂ thermodynamically could be regenerated by accepting electrons from the I⁻ ions.¹⁹ The HOMO levels of the four porphyrin dyes are almost identical, and the LUMO level of **YQ1** is slightly higher with respect to those of **YQ2–YQ4**, which results in a larger driving force for the electron injection process. Thus, it can be anticipated that **YQ1** sensitized solar cells will demonstrate higher efficiency than those of the other porphyrin dyes. This is in agreement with the photovoltaic performance results (*vide infra*).

Table 2 Electrochemical properties of the porphyrin dyes

Dyes	HOMO ^a /V (vs. NHE)	E_{0-0} ^b /V	LUMO ^c /V (vs. NHE)
YQ1	0.69	1.95	-1.26
YQ2	0.69	1.92	-1.23
YQ3	0.67	1.88	-1.21
YQ4	0.68	1.88	-1.20

^a HOMO levels were measured in acetonitrile using 0.1 M tetrabutylammonium hexafluorophosphate (TBAPF₆) as the electrolyte (working electrode: FTO/TiO₂/dye; reference electrode: SCE; calibrated with ferrocene/ferrocenium (Fc/Fc⁺) as an external reference. Counter electrode: Pt). ^b E_{0-0} was calculated from the wavelength at the intersection (λ_{inter}) of normalized absorption and emission spectra with the equation $E_{0-0} = 1240/\lambda_{inter}$. ^c The LUMO was calculated from the equation of LUMO = HOMO - E_{0-0} .




Fig. 5 Frontier molecular orbital profiles of YQ1–YQ4 calculated by DFT.




Fig. 4 Schematic energy-level diagram of YQ1–YQ4.

Theoretical calculations

To gain further insight into the electron distribution at the frontier molecular orbitals, we employed density functional theory (DFT) calculations to optimize the geometries of YQ1–YQ4. For the calculations, the long alkyl chains in these compounds were replaced by methyl groups to save computational time while preserving their steric effect. The hybrid B3LYP functional²⁰ was used together with a mixed basis set, *i.e.*, the Los Alamos effective core potential basis set (LANL2DZ)²¹ for zinc ion and the 6-31G* basis set²² for the other atoms, as implemented by the Gaussian 09 program package.²³ Fig. 5 shows the corresponding molecular orbitals. It is obvious that the HOMO orbitals of the dyes are delocalized through the 2-diphenylaminothiophene and the porphyrin frameworks while the LUMO orbitals are delocalized between the porphyrin frameworks and the anchoring carboxyl groups. Thus, the excitation of the electron from the HOMO to the LUMO can result in electron redistribution from the donor to the anchoring moiety and thus realize electron injection from the LUMO orbital to the conduction band of TiO₂. Therefore, it may be concluded that YQ1–YQ4 are suitable for using as DSSC sensitizers.

Photovoltaic performance

Solar cells were fabricated using YQ1–YQ4 as the sensitizers. To evaluate the photovoltaic performance, the incident photon-to-electron conversion efficiency (IPCE) was checked as a function of incident wavelength (Fig. 6). Because of the strong absorption

bands, these porphyrin dyes demonstrated moderate to high IPCE values in a large wavelength range of 400–800 nm. For YQ1, a broad peak around 450 nm and two well-separated peaks between 550 and 700 nm were observed, corresponding to the Soret and Q bands, respectively. For YQ2–YQ4, the IPCE spectra demonstrated similar characteristics. In good agreement with the absorption spectra, the onset wavelengths of photocurrent responses were red-shifted from 750 nm for YQ1 to 800 nm for YQ4. It is noteworthy that the high plateau of YQ1 (about 84.7%) is much higher than the other three dyes (from 62.5% to 66.0%). This may result in the highest current density for the cells based on YQ1 (*vide infra*) despite its relatively smaller IPCE values relative to YQ2–YQ4 in the NIR region. For YQ2–YQ4, their maximum IPCE values are almost identical, and their onset wavelength thresholds (Fig. 6) lie in the order of YQ2 < YQ3 < YQ4, which is in consistent with the relative magnitude sequence of J_{sc} as described below.




Fig. 6 IPCE action spectra for YQ1, YQ2, YQ3 and YQ4-based DSSCs.

The current density–voltage (J – V) curves of the DSSCs based on YQ1–YQ4 were measured under simulated AM1.5G irradiation (100 mW cm⁻²) and shown in Fig. 7, where J_{sc} , V_{oc} , FF , and the power conversion efficiency (η) can be obtained, and the corresponding data are listed in Table 3.




Fig. 7 Current–voltage characteristics of the DSSCs based on YQ1–YQ4.

Table 3 Photovoltaic parameters of porphyrin-based dye-sensitized solar cells under AM1.5 illumination (power $100 \text{ mW}\cdot\text{cm}^{-2}$) with an active area of 0.25 cm^2

Dyes	$J_{sc}/\text{mA cm}^{-2}$	V_{oc}/V	FF	η (%)
YQ1	14.27	0.68	0.62	6.01
YQ2	12.51	0.63	0.54	4.23
YQ3	12.76	0.58	0.59	4.38
YQ4	13.61	0.60	0.62	5.00
CPZ ^{16a}	7.34	0.57	0.71	2.93
DPZI ^{16a}	17.70	0.63	0.70	7.74
DPZ2 ^{16a}	9.11	0.53	0.70	3.40
LW2 ^{16b}	15.36	0.69	0.70	7.37
T3P ^{11a}	12.38	0.57	0.58	4.10
T3P ^{16c}	10.09	0.63	0.67	4.19
HT3P ^{16c}	7.83	0.62	0.70	3.40

The overall power conversion efficiencies lie in the range of 4.23–6.01%, exhibiting an order of $YQ2 \approx YQ3 < YQ4 < YQ1$. As described above, YQ1 and YQ2–YQ4 contain the 4-ethynylbenzoic acid and the cyanoacrylic acid moieties as the acceptors, respectively. The DSSCs based on YQ1 exhibited the highest η value of 6.01% ($J_{sc} = 14.27 \text{ mA cm}^{-2}$, $V_{oc} = 0.68 \text{ V}$, $FF = 0.62$). And the efficiencies obtained for YQ2–YQ4 are lower than that for YQ1, lying in the range of 4.23%–5.00%. These observations may be ascribed to the floppy structures of YQ2–YQ4 induced by the cyanoacrylic acid moieties which provide free space for charge recombination. This observation is similar to the results reported by Yeh and Wang *et al.*^{16b, 24} And compared with YQ3, the attachment of a hexyl group to the thienyl ring of YQ4 results in an improved voltage, which may be related to the suppression of the dye aggregation and the charge recombination processes.²⁵ In comparison with similar porphyrin dyes CPZ, DPZ2, T3P and HT3P (Scheme 3) containing carbazole or triphenylamine as the donors,^{11a, 16a, 16c} the DSSCs based on YQ1 show higher efficiencies. This observation may be ascribed to the strong electron-donating ability of 2-diphenylaminothiophene which can obviously red-shift and broaden the absorption bands as described above, and thus broaden the IPCE spectrum and enhance the current density. On the other hand, the DSSCs based on DPZI^{16a} show a higher efficiency of 7.74%, which may be attributed to the presence of the diketopyrrolopyrrole fragment, which filled the absorption gap between the Soret band and the Q bands, thus a higher current density of 17.70 mA cm^{-2} was obtained. LW2^{16b} also exhibits a higher efficiency of 7.37% compared with those observed for

YQ1–YQ4, which may be ascribed to the more red-shifted IPCE spectrum of LW2 in the near infrared region, resulting in a higher current density of 15.36 mA cm^{-2} . Based on the above observations, it can be concluded that the introduction of 2-diphenylaminothiophene as the donor may be promising for the design of porphyrin-based efficient DSSC sensitizers, and the cell efficiencies may be further improved by further optimizing the structures and extending the absorption spectra.¹⁶




Fig. 8 Electrochemical impedance spectra of DSSCs based on porphyrin dyes under dark. (a) Nyquist plots; (b) Bode phase plots.

Electrochemical impedance spectroscopy

To further understand the electron transport and recombination processes for the DSSCs based on dyes YQ1–YQ4, the electrochemical impedance spectroscopy (EIS) was measured in the dark within a frequency range of 0.1 Hz to 100 kHz. The Nyquist and Bode plots for the sensitized cells are shown in Fig. 8. In general, a typical EIS spectrum of a DSSC exhibits three components in the order of increasing frequency, which can be assigned to the Nernst diffusion within the electrolyte (in the mHz range), the charge transfer at the tin oxide/electrolyte interface (in the 10/100 Hz range), and the redox reaction at the Pt counter electrode (in the kHz range), respectively. In some cases, only two of the components can be observed, because the Nernst diffusion part within the electrolyte is overlapped by the intermediate-frequency counterpart, which is indicative of fast electron transport and long electron lifetime in the TiO_2 film.²⁶ As shown in the EIS Nyquist plots (Fig. 8a), the radii of the middle semicircles lie in the order of $YQ3 < YQ4 < YQ2 < YQ1$, indicating the sequence of charge transfer resistance. Thus, the sequence of charge recombination resistance at the surface lies in the order of $YQ3 < YQ4 < YQ2 < YQ1$.

Fig. 8b shows the EIS Bode plots, i.e., the phase angles of the

impedance vs. the frequencies, for the DSSCs. As is well known, the characteristic frequency of the peak in the intermediate frequency region is related to the charge recombination rate, and its reciprocal is proportional to the electron lifetime.²⁷ The peak maximum of the DSSC based on **YQ1** is shifted to a lower frequency relative to the other three dyes, indicative of the longest electron lifetime, and the electron lifetime values derived from the curve fitting are 27.0, 19.6, 10.7 and 14.3 ms, for **YQ1**, **YQ2**, **YQ3** and **YQ4**, respectively. Thus, the longest electron lifetime observed for **YQ1** indicates the effective suppression of the back reaction of the injected electron with the I₃⁻ in the electrolyte, resulting in the highest photovoltage. The EIS results are in good agreement with the photovoltaic performance (Fig. 7 and Table 3).

Conclusions

In summary, we synthesized porphyrin-based DSSC dyes **YQ1**–**YQ4** with 2-diphenylaminothiophene attached at the *meso*-position as the electron donor. 4-Ethynylbenzoic acid and 2-cyanoacrylic acid with various aromatic groups were incorporated as the anchoring moieties in **YQ1**, and **YQ2**–**YQ4**, respectively. In comparison with most reported porphyrin dyes with similar structures, **YQ1**–**YQ4** demonstrate obviously red-shifted absorption maxima and broadened Soret bands. **YQ4** shows better photovoltaic performance compared with **YQ2** and **YQ3**, which may be attributed to the suppression of the dye aggregation by the hexyl chain attached to the thienyl ring of **YQ4**. On the other hand, **YQ2**–**YQ4** demonstrate lower efficiencies compared with **YQ1**, which may be ascribed to the floppy structures of the cyanoacrylic acid-based porphyrins that provide free space for charge recombination. As a result, the DSSCs based on **YQ1** exhibited the highest efficiency of 6.01%. This work demonstrates that the introduction of 2-diphenylaminothiophene to a porphyrin framework can obviously red-shift and broaden the absorption bands of the porphyrin dyes, resulting in high solar cell efficiencies. Hence, the introduction of 2-diphenylaminothiophene as the electron donor may be promising for the design of efficient porphyrin-based DSSC sensitizers.

Acknowledgements

This work was financially supported by NSFC (21072060, 91227201), the Oriental Scholarship, NCET-11-0638, the Fundamental Research Funds for the Central Universities (WK1013002), and SRFDP (20100074110015).

Notes and references

⁴⁵ *Key Laboratory for Advanced Materials and Institute of Fine Chemicals, Shanghai Key Laboratory of Functional Materials Chemistry, East China University of Science and Technology, Shanghai, P. R. China. E-mail: yshxie@ecust.edu.cn; Fax: (+86) 21-6425-2758. Tel: (+86) 21-6425-0772.*

⁵⁰ *Department of Theoretical Chemistry and Biology, School of Biotechnology KTH Royal Institute of Technology, Stockholm, Sweden*
 † Electronic Supplementary Information (ESI) available: ¹H NMR, and MALDI-TOF spectra of intermediates and target porphyrins (Fig. S1 to S24). For ESI See DOI: 10.1039/b000000x/

⁵⁵ 1 B. O'Regan, M. Grätzel, *Nature*, 1991, **353**, 737.

- 2 (a) L. L. Li and E. W. G. Diau, *Chem. Soc. Rev.*, 2013, **42**, 291; (b) S. Zhang, X. Yang, Y. Numata and L. Y. Han, *Energy Environ. Sci.*, 2013, **6**, 1443.
- 60 3 Q. J. Yu, Y. H. Wang, Z. H. Yi, N. N. Zu, J. Zhang, M. Zhang and P. Wang, *ACS Nano*, 2010, **4**, 6032.
- 4 (a) J. H. Delcamp, Y. Shi, J. Yum, T. Sajoto, E. Dell'Orto, S. Barlow, M. K. Nazeeruddin, S. R. Marder and M. Grätzel, *Chem. Eur. J.*, 2013, **19**, 1819; (b) J. H. Delcamp, A. Yella, T. W. Holcombe, M. K. Nazeeruddin and M. Grätzel, *Angew. Chem., Int. Ed.*, 2013, **52**, 376; (c) Q. Li, J. Shi, H. Li, S. Li, C. Zhong, F. Guo, M. Peng, J. L. Hua, J. Qin and Z. Li, *J. Mater. Chem.*, 2012, **22**, 6689; (d) J. Liu, Y. Numata, C. J. Qin, A. Islam, X. D. Yang and L. Y. Han, *Chem. Commun.*, 2013, **49**, 7587; (e) Q. Y. Feng, X. W. Jia, G. Zhou and Z. S. Wang, *Chem. Commun.*, 2013, **49**, 7445; (f) C. Chen, X. C. Yang, M. Cheng, F. G. Zhang, J. H. Zhao and L. C. Sun, *RSC Adv.*, 2013, **3**, 12688.
- 5 (a) K. Pei, Y. Wu, W. Wu, Q. Zhang, B. Chen, H. Tian and W. H. Zhu, *Chem. Eur. J.*, 2012, **18**, 8190; (b) S. H. Aaron, B. K. Chandra, B. G. Chandra, R. S. Lindsey and D. S. Francis, *ACS Appl. Mater. Interfaces*, 2013, **5**, 5314; (c) M. Katono, T. Bessho, M. Wielopolski, M. Marszalek, J. Moser, R. H. Baker, S. M. Zakeeruddin and M. Grätzel, *J. Phys. Chem. C*, 2012, **116**, 16876; (d) J. Liu, X. Yang, J. Zhao and L. Sun, *RSC Adv.*, 2013, **3**, 15734; (e) X. Ren, S. Jiang, M. Cha, G. Zhou, and Z. S. Wang, *Chem. Mater.*, 2012, **24**, 3493; (f) J. Shi, J. Chen, Z. Chai, H. Wang, R. Tang, K. Fan, M. Wu, H. Han, J. Qin, T. Peng, Q. Li and Z. Li, *J. Mater. Chem.*, 2012, **22**, 18830.
- 6 (a) B. Liu, W. H. Zhu, Q. Zhang, W. J. Wu, M. Xu, Z. J. Ning, Y. S. Xie and H. Tian, *Chem. Commun.*, 2009, 1766; (b) W. Q. Li, Y. Z. Wu, X. Li, Y. S. Xie and W. H. Zhu, *Energy Environ. Sci.*, 2011, **4**, 1830.
- 85 7. J. Deisenhofer and J. R. Norris, *The Photosynthetic Reaction*, Academic Press, New York, 1993.
- 8 (a) S. H. Kang, I. T. Choi, M. S. Kang, Y. K. Eom, M. J. Ju, J. Y. Hong, H. S. Kang and H. K. Kim, *J. Mater. Chem. A*, 2013, **1**, 3977; (b) J. Warnan, L. Favereau, F. Meslin, M. Severac, E. Blart, Y. Pellegrin, D. Jacquemin and F. Odobel, *ChemSusChem* 2012, **5**, 1568; (c) J. Luo, M. Xu, R. Li, K. Huang, C. Jiang, Q. Qi, W. Zeng, J. Zhang, C. Chi, P. Wang and J. S. Wu, *J. Am. Chem. Soc.*, 2014, **136**, 265.
- 9 (a) C. Lee, H. Lu, C. Lan, Y. Huang, Y. Liang, W. Yen, Y. Liu, Y. Lin, E. W. G. Diau, and C. Y. Yeh, *Chem. Eur. J.*, 2009, **15**, 1403; (b) J. Lu, X. Xu, Z. Li, K. Cao, J. Cui, Y. Zhang, Y. Shen, Y. Li, J. Zhu, S. Dai, W. Chen, Y. Cheng and M. Wang, *Chem. Asian J.*, 2013, **8**, 956; (c) A. Yella, H. W. Lee, H. N. Tsao, C. Y. Yi, A. K. Chandiran, M. K. Nazeeruddin, E. W. G. Diau, C. Y. Yeh, S. M. Zakeeruddin and M. Grätzel, *Science*, 2011, **334**, 629.
- 100 10 S. Mathew, A. Yella, P. Gao, R. H. Baker, B. F. E. Curchod, N. A. Astani, I. Tavernelli, U. Rothlisberger, M. K. Nazeeruddin and M. Grätzel, *Nature chem.*, 2014, **6**, 242.
- 11 (a) B. Liu, W. H. Zhu, Y. Q. Wang, W. J. Wu, X. Li, B. Chen, Y. T. Long and Y. S. Xie, *J. Mater. Chem.*, 2012, **22**, 7434; (b) Y. Q. Wang, X. Li, B. Liu, W. J. Wu, W. H. Zhu and Y. S. Xie, *RSC Adv.*, 2013, **3**, 14780.
- 12 (a) R. Ambre, K. Chen, C. Yao, L. Luo, E. W. G. Diau and C. H. Hung, *J. Phys. Chem. C*, 2012, **116**, 11907; (b) Y. Liu, N. Xiang, X. Feng, P. Shen, W. Zhou, C. Weng, B. Zhao and S. Tan, *Chem. Commun.*, 2009, 2499.
- 110 13 (a) C. Y. Lee, J. T. Hupp, *Langmuir*, 2010, **26**, 3760; (b) C. Y. Lee, C. X. She, N. C. Jeong and J. T. Hupp, *Chem. Commun.*, 2010, **46**, 6090; (c) C. L. Wang, C. M. Lan, S. H. Hong, Y. F. Wang, T. Y. Pan, C. W. Chang, H. H. Kuo, M. Y. Kuo, E. W. G. Diau and C. Y. Lin, *Energy Environ. Sci.*, 2012, **5**, 6933; (d) Y. C. Chang, C. L. Wang, T. Y. Pan, S. H. Hong, C. M. Lan, H. H. Kuo, C. F. Lo, H. Y. Hsu, C. Y. Lin and E. W. G. Diau, *Chem. Commun.*, 2011, **47**, 8910.
- 14 (a) M. Lee, M. S. Kang, M. Shin, J. Park, D. S. Chung, C. E. Park, S. Kwon, Y. Kim, *J. Polym. Sci., Part A: Polym. Chem.*, 2010, **48**, 3942; (b) J. L. Song, P. Amaladass, S. H. Wen, K. K. Pasunooti, A. Li, Y. L. Yu, X. Wang, W. Deng and X. W. Liu, *New J. Chem.*, 2011, **35**, 127.
- 15 S. Ito, T. N. Murakami, P. Comte, P. Liska, C. Grätzel, M. K. Nazeeruddin and M. Grätzel, *Thin Solid Films*, 2008, **516**, 4613.
- 125 16 (a) L. Favereau, J. Warnan, F. B. Anne, Y. Pellegrin, E. Blart, D. Jacquemin, and F. Odobel, *J. Mater. Chem. A*, 2013, **1**, 7572; (b) J. Lu, X. Xu, K. Cao, J. Cui, Y. Zhang, Y. Shen, X. Shi, L. Liao, Y. Cheng and M. Wang, *J. Mater. Chem. A*, 2013, **1**, 10008; (c) A. Aljarilla, J. N.

- Clifford, L. Pelleja, A. Moncho, S. Arrechea, P. Cruz, F. Langa and E. Palomares, *J. Mater. Chem. A*, 2013, **1**, 13640.
- 17 (a) M. K. Nazeeruddin, P. Pechy, T. Renouard, S. M. Zakeeruddin, R. Humphry-Baker, P. Comte, P. Liska, C. Le, E. Costa, V. Shklover, L. Spiccia, G. B. Deacon, C. A. Bignozzi and M. Grätzel, *J. Am. Chem. Soc.*, 2001, **123**, 1613; (b) Z. S. Wang and H. Sugihara, *Langmuir*, 2006, **22**, 9718.
- 18 E. G. McRae and M. Kasha, *J. Chem. Phys.*, 1958, **28**, 721.
- 19 (a) D. P. Hagberg, J. H. Yum, H. Lee, F. De Angelis, T. Marinado, K. M. Karlsson, R. Humphry-Baker, L. C. Sun, A. Hagfeldt, M. Grätzel and M. K. Nazeeruddin, *J. Am. Chem. Soc.*, 2008, **130**, 6259; (b) A. Hagfeldt and M. Grätzel, *Chem. Rev.*, 1995, **95**, 49.
- 20 (a) A. D. Becke, *J. Chem. Phys.*, 1993, **98**, 5648; (b) P. J. Stephens, F. J. Devlin, C. F. Chabalowski and M. J. Frisch, *J. Phys. Chem.*, 1994, **98**, 11623.
- 21 P. J. Hay, W. R. Wadt, *J. Chem. Phys.*, 1985, **82**, 270.
- 22 W. J. Hehre, R. Ditchfield and J. A. Pople, *J. Chem. Phys.*, 1972, **56**, 2257.
- 23 M. J. Frisch, G. W. Trucks, H. B. Schlegel, G. E. Scuseria, M. A. Robb, J. R. Cheeseman, G. Scalmani, V. Barone, B. Mennucci and G. A. Petersson, *et al. Gaussian 09, Revision A.2, Gaussian, Inc.*, Wallingford CT, 2009.
- 24 N. M. Reddy, T. Y. Pan, Y. C. Rajan, B. C. Guo, C. M. Lan, E. W. G. Diau and C. Y. Yeh, *Phys. Chem. Chem. Phys.*, 2013, **15**, 8409.
- 25 Y. Wu, M. Marszalek, S. M. Zakeeruddin, Q. Zhang, H. Tian, Michael Grätzel and W. H. Zhu, *Energy Environ. Sci.*, 2012, **5**, 8261.
- 26 (a) Q. Wang, J. E. Moser and M. Grätzel, *J. Phys. Chem. B.*, 2005, **109**, 14945; (b) F. Fabregat-Santiago, J. Bisquert, G. Garcia-Belmonte, G. Boschloo and A. Hagfeldt, *Energy Mater. Sol. Cells*, 2005, **87**, 117; (c) D. B. Kuang, S. Uchida, R. Humphry-Baker, S. M. Zakeeruddin and M. Grätzel, *Angew. Chem., Int. Ed.*, 2008, **47**, 1923; (d) R. Kern, R. Sastrawan, J. Ferber, R. Stangl and J. Luther, *J. Electrochim. Acta.*, 2002, **47**, 4213.
- 27 (a) J. Bisquert, *Phys. Chem. Chem. Phys.*, 2003, **5**, 5360; (b) J. Bisquert, A. Zaban, M. Greenshtein and I. Mora-Sero, *J. Am. Chem. Soc.*, 2004, **126**, 13550.