

RSC Advances



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. This *Accepted Manuscript* will be replaced by the edited, formatted and paginated article as soon as this is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

ARTICLE

Activation of giant silicalite-1 monocrystals combining rapid thermal processing and ozone calcination

Cite this: DOI: 10.1039/x0xx00000x

Marta Navarro,^{a,b} Ester Mateo,^c Beatriz Diosdado,^d Michael Tsapatsis^e and Joaquín Coronas^{a*}

Received 00th January 2012,

Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

A rapid thermal processing (RTP) technique combined with ozone/oxygen calcination was applied to activate and heal the structure of a 1.1 mm² section of a silicalite-1 giant monocrystal. Crystallinity was monitored by single crystal X-ray diffraction and high sensitive thermogravimetry (TGA) was performed to prove the complete removal of the structure directing agent.

Introduction

Silicalite-1, a pure silica zeolite with an MFI type structure, has attracted considerable attention due to its particular framework. It contains two intersecting channels, one sinusoidal and parallel to (100) with elliptical cross sections (0.55 x 0.51 nm in size), and the other straight, circular in section (0.56 x 0.53 nm) and parallel to (010).¹ This particular channel system plays an important role in diffusion processes,² membrane permeation properties³ and even crystal growth habit.⁴ The orientation or preferential growth of the MFI crystals along the *b* axis, i.e. the (010) direction, promotes a better performance in membrane separations, increasing the flux and selectivity to specific molecules.³ Large silicalite-1 monocrystals could be sectioned perpendicularly to the *b* axis, yielding to lamellas free of intergrowth defects. With the advantage of porosity-morphology control, such lamellas, as zeolites or microporous materials in general,^{5, 6} could serve as effective self-supported membranes,⁷ fillers in mixed matrix membranes,⁸ sensors⁹ and other microdevices.¹⁰

For such samples to be accessible for guest molecules of interest and useful as separation membranes,⁶ it is important to remove the occluded template or organic structure directing agent (OSDA) molecules while retaining the inorganic framework.¹¹ Tetrapropylammonium hydroxide (TPAOH) has been used as an OSDA, although other organic templates can be used to synthesize large silicalite-1 crystals.¹² During calcination at high temperatures, mechanical tensions are produced in the zeolite framework and in consequence cracks usually arise; in addition, carbon residues are formed along the diffusion paths. All these issues become crucial when the performance of large crystals is considered. Herein we demonstrate how a rapid thermal processing (RTP)¹³ technique heals the structure of up to 1.1 mm² sections of silicalite-1 giant monocrystals. Furthermore, oxygen/ozone mixtures were used for the complete removal of the OSDA under mild temperature conditions (350 °C). Single crystal diffraction was applied to study the effect of combining both methodologies in the zeolite

structure,^{12, 14} and high sensitive thermogravimetry (TGA) able to register the weight loss of a single crystal (ca 300 µg) was performed to confirm OSDA removal. Finally, even though both RTP treatment and ozone calcination have previously been reported,¹³⁻¹⁵ this is the first time that OSDA was completely removed from giant silicalite-1 crystals providing evidence of structure and crystallinity preservation.

Experimental

Synthesis and sectioning of giant silicalite-1 crystals

Synthesis of giant zeolite crystals was carried out following the methodology already published.¹² This method is based on slowing down the dissolution of the silica source using low surface area materials of silicon, such as two quartz glass tubes, following the so-called BMD ("bulk material dissolution") technique.¹⁶ Prior to the addition of reactants, a thorough cleaning process was achieved in the teflon liners and silica tubes. Then, 25.35 g of tetrapropylammonium hydroxide solution (TPAOH 1 M, Aldrich) was used as the structure directing agent and afterwards 1.68 g of HF (48 wt% in water, Aldrich) was added as a nucleation suppressing agent. The molar composition of the gel was 24TPAOH:38HF:1000H₂O, and the hydrothermal synthesis was carried out at 200 °C for 10 days. Crystals were recovered by handpicking, washed thoroughly with distilled water and dried at 70 °C overnight.

For sectioning the silicalite-1 crystals, a vertical diamond wire saw (Well, 3242 model) was used, equipped with two micrometers for accurate positioning of the sample and for setting the depth of a slice. The crystal was mounted on an alumina support in the desired position and glued with Quickstick 135 mounting wax to avoid any deviation while cutting.

Calcination treatments

For RTP treatment, silicalite-1 samples were placed over a quartz reactor to heat them up to 700 °C within a 25 s, using an infrared heating chamber (Research Inc., model *E4-10*), supplied with a cabinet temperature controller (model *915*). The maximum temperature was held for 2 min, and then the sample was cooled down using a water cooling system (Research Inc., model *C100-1*). The thermal treatment was performed in oxygen atmosphere (1.2 L·min⁻¹).

For ozone calcination, a single crystal is placed in a quartz reactor and calcined in a cross-flow system using an O₂/O₃ mixture, feeding O₂ (20 mL·min⁻¹) through a O₃ generator (Neosyt NEO 500), giving an ozone production of approximately 0.3 mL·min⁻¹ (1.5 %). The temperature was maintained at 350 °C for 12 h with heating and cooling rates of 0.2 and 1 °C·min⁻¹, respectively. Pure oxygen calcination was not carried out due to crack formation.¹⁴ The effect of calcination conditions and gas atmospheres used on template removal was studied by using a TA Instruments Thermogravimetric Analyzer TGA-Q5000 IR with a resolution of 0.01 µg. With this equipment, calcination analyses were carried out in air (50 mL (STP)·min⁻¹) at 600 °C for 8 h, with heating and cooling rates of 0.5 and 1 °C·min⁻¹, respectively.

Characterization

Optical microscopy (Olympus Bx41 TRF) was routinely employed to observe, measure and classify the handpicked specimens. Single crystal X-ray data were acquired on a Xcalibur, Sapphire-3 diffractometer equipped with a graphite monochromator (Mo_{Kα} radiation, $\lambda = 0.71073$ Å) and analysed using the CrysAlisPro package. [CrysAlisPro, Agilent Technologies, Version 1.171.37.31 (release 14-01-2014 CrysAlis171.NET) (compiled Jan 14 2014, 18:38:05)]. Data collection commences indexing the spots from several image frames. The software automatically does “peak hunting” and finds a unit cell. The same variables (default settings) and background are used for analysing every sample. Orthogonal projections of the Ewald sphere were presented from the original unit cell calculated by the software. Then, monocristallinity percentages were obtained comparing both the unit cell defined for silicalite-1¹⁷ and that calculated by the software.

Morphology, size and quality of the samples were determined using scanning electron microscopy (SEM) using an Inspect F50 field emission gun scanning electron microscope, operated at 5 and 10 kV. 3D images of the silicalite-1 slide were obtained with a SENSOFAR PLµ 2300 confocal microscope, operating in reflection mode.

Results and discussion

Recently, we have reported the synthesis and characterization of giant silicalite-1 monocrystals of different sizes and aspect ratios by single crystal X-ray diffraction (XRD).^{12, 14} The crystals were prepared applying the “bulk material dissolution” (BMD) technique.¹⁶ Cross sections of silicalite-1 monocrystals larger than 1 mm in size were obtained along the *b* axis using a diamond saw, showing minor roughness and no cracks on their surface (Fig. 1). Even though the cutting process must be optimized by a method allowing ultrathin lamellas to be obtained, the results are promising since we were able to substantially reduce the thickness of the sample from 610 to 160 µm of *L_b* (where *L_i* is the dimension along *i* axis). Moreover, our sections did not show evident cracks after the process, as can be observed from the confocal profilometry imaging (Fig. 1c). We will demonstrate that the cutting process did not affect the bulk monocristallinity of the sample.

As determined by single crystal XRD, as-synthesized silicalite-1 crystals greater than 250 µm in size tend to show a relatively high density of structural defects and fractures, especially after calcination at high temperatures.¹² The silicalite-1 crystal being the object of our study (*L_a* = 990 µm; *L_b* = 610 µm; *L_c* = 1300 µm; i.e. with a section along the (010) axis of ca 1.3 mm²) showed these features under optical microscopy also before calcination (Fig. 2a). Furthermore, single crystal XRD (Fig. 3a) revealed the presence of polycrystalline domains and microstructural defects, represented by spots (reflections) outside their expected positions from the silicalite-1 orthorhombic unit cell.¹⁷ In detail, only 47.0% of the analyzed data fitted with the orthorhombic cell calculated for this silicalite-1 crystal (Table 1). After laminating the crystal, its thickness was reduced from 610 µm to 160 µm and its section along (010) to 1.1 mm² (due to the fact that the crystal thickness was not constant) and the fraction of the as-made crystal that presented a greater amount of defects (those present in the growing external surface) was removed. In consequence, the monocristallinity of the subsequent lamella increased, the percentage of the analyzed data that fitted with the unit cell being 56.0 %.




Fig. 1.- Silicalite-1 cross section along (010) axis: a) outline of a slide along *b* axis in a typical coffin shape crystal; b) obtained slide of 160 µm in thickness; c) confocal profilometry image of b) slightly deviated from the medium *b* axis length.




Fig. 2.- a-b) Transmitted light optical microscopy images of silicalite-1 sample: a) as-synthesized crystal (*L_a* = 990 µm; *L_b* = 610 µm; *L_c* = 1300 µm); b) cross section along *b* axis (*L_a* = 990 µm; *L_b* = 160 µm; *L_c* = 1100 µm) after RTP treatment. Horizontal bars indicate 1000 µm.

Table 1.- Monocristallinity percentage of the silicalite-1 samples after different treatments (obtained by single crystal X-ray diffraction). ^a Sample treated by RTP; ^b sample treated by RTP (700 °C for 2 min) and calcined using oxygen/ozone atmosphere (350 °C for 12 h). Monocristallinity percentages were calculated comparing both the unit cell defined for silicalite-1¹⁷ and the one calculated by the software using up to 40000 spots from several image frames.

Silicalite-1 sample	Monocristallinity	Change in monocristallinity
As-made crystal	47.0 %	-

Slide	56.0 %	+9 %
RTP treated slide ^a	99.6 %	+43.6 %
RTP + O ₂ /O ₃ calcination slide ^b	89.7 %	-9.9 %

As reported by Choi et al.¹³, a sudden RTP treatment under an infrared lamp at 700 °C during 2 min diminished the formation of grain boundary defects in zeolite samples by the condensation of terminal silanol groups (Si-OH), thus preventing fracture formation. To further study the RTP treatment effect on the zeolite microstructure, this large silicalite-1 cross section along the *b* axis was analyzed again by single crystal XRD. In Figure 3b, an orthorhombic unit cell diagram is drawn over the reflections found along the *b* direction. We can observe how intense and well defined these peaks are in comparison with the intensity diagram obtained from the original crystal in Fig. 3a. In fact, after RTP treatment (700 °C, 2 min) almost all the reflections matched the calculated unit cell (99.6 %, Table 1) in comparison with the 56.0 % matching registered after the sectioning. These findings suggest that RTP treatment healed the structure of silicalite-1 crystals up to a point that samples can be considered as practically monocrystalline after being submitted to this process. Moreover, the 160 μm silicalite-1 slide showed a more transparent surface under optical microscopy,

although the superficial crack was still present from the growing step of the original crystal (Fig. 2b).

Single-step¹⁸ or two-step¹³ RTP processes have been used before to remove completely the template occluded in the zeolite pores, depending on the thickness of the sample. Using high sensitivity TGA equipment, air atmosphere and 600 °C as the maximum temperature, the weight loss of a single crystal greater than 1000 μm in size treated with RTP was registered (Fig. 4). This sample (*L*_a = 470 μm; *L*_b = 460 μm; *L*_c = 1050 μm) weighed 339.2 μg and suffered a 13.0 % weight loss at 370 °C. It should be noted that this weight loss is higher (0.8 %) than that of the as-made crystal (311.4 μg) which lost 12.2 % of its weight at 374 °C under the same experimental conditions. This data is in agreement with that already published for crystals greater than 1000 μm (12.3 %).¹² After RTP followed by conventional air calcination (RTP alone cannot completely remove the OSDA as it was already proved) at 600 °C for 8 h,¹³ the crystal integrity seemed to be better preserved in comparison with other samples calcined without previous RTP (Fig. 5a),^{12, 14} but numerous superficial cracks and carbon deposits were inferred by optical microscopy images (not shown). After the combination of both processes, single crystal XRD (Fig. 5b) showed




Fig. 3.- Orthogonal projection of the Ewald sphere of silicalite-1 samples along (010) direction: a) component 1 of the as-made crystal ($L_a = 990 \mu\text{m}$; $L_b = 610 \mu\text{m}$; $L_c = 1300 \mu\text{m}$) unit cell; b-d) silicalite-1 slide ($L_a = 990 \mu\text{m}$; $L_b = 160 \mu\text{m}$; $L_c = 1100 \mu\text{m}$): b) component 1 of the unit cell after RTP; c) component 1 of the unit cell after RTP treatment and ozone calcination; d) detail of the projection in c) with the three unit cell components drawn.

that only 36.1 % of all the measured reflections fitted the calculated orthorhombic unit cell. Minor percentages (18.8 and 14.8 %) also fitted the calculated unit cell, but corresponding to different components slightly rotated (0.07° and 2.5°) with respect to the main component (Fig. 5c). The remaining reflections measured (30.3 %) corresponded to highly defective areas inside the crystal and could not be fitted to other unit cell components. These features reveal the severe decrease in monocrystallinity in the sample after the application of drastic calcination conditions even if RTP treatment is applied in advance.




Fig. 4.- Weight loss curves under air atmosphere for silicalite-1 monocrystalline samples with $L_c > 1000 \mu\text{m}$ in size: as-made and RTP treated crystal and RTP-ozone treated slide.

Ozone, already proved as a suitable gas for removing the organic template from silicalite-1 large crystals and membranes while preserving their structure,^{14,19} was assayed as the appropriate atmosphere to calcine samples under mild temperature conditions after RTP treatment. The maximum calcination temperature was set at 350°C for 12 h with very slow heating/cooling rates ($0.2/1^\circ\text{C}\cdot\text{min}^{-1}$). Once again, high sensitivity TGA equipment was used to prove the effectiveness of ozone calcination in the removal of the organic template, in combination with RTP treatment (Fig. 4). The initial weight of the millimetric silicalite-1 cross section was $480.0 \mu\text{g}$. After an initial weight loss of around $100\text{--}150^\circ\text{C}$ (1.2 %) attributed to occluded water, the sample underwent a small weight loss (2.0 %) assigned to remaining carbon deposits, always difficult to eliminate from large silicalite-1 crystals,^{14,20} observed in the surface of the sample that shows brownish color. This weight loss value indicates that template removal was achieved in a high yield from our sample by the combination of both methodologies, which preserved the zeolite structure as the single crystal diffraction diagrams demonstrate (Fig. 3c). It should be mentioned that after a multi-stage process of microscopy characterization, slicing, RTP treatment, ozone calcination and final conventional calcination, the silicalite-1 monocrystalline slice was analyzed by single crystal XRD after each process. This fact indicates the controlled manipulation of




Fig. 5.- a) SEM image of a single silicalite-1 crystal after RTP treatment and conventional calcination; b-c) orthogonal projection of the Ewald Sphere along (100) direction of a silicalite-1 crystal RTP treated and conventionally calcined: b) reflections that do not fit with the orthorhombic unit cell of the component 1 drawn in the image; c) enlargement of the slightly rotated orthorhombic unit cell components after fitting all the spots measured.

the sample. Table 1 shows the high monocrystallinity of the silicalite-1 cross section after RTP treatment combined with ozone

calcination. A percentage of 89.7 % of all the reflections measured matched the calculated orthorhombic unit cell. The remaining reflections were attributed to two other different unit cell components, slightly rotated (0.002 and 0.007°) with respect to the majority component and with respect to each other (0.22°). These components have most of their reflections in common, being almost superimposed.

Conclusions

Calcination using ozone after rapid thermal treatment generated a minor loss of monocrystallinity (about 10 %) of giant silicalite-1 samples. However, it provoked a mild distortion in the framework during the thermal treatment to remove the OSDA. The results obtained here are in agreement with the previous research carried out by Choi et al.¹³ on the improvement of the separation performance of silicalite-1 polycrystalline membranes upon RTP activation.

Acknowledgements

This work was supported by the Spanish MINECO (MAT2010-15870), the Aragón Government, and the ESF and FPU Program fellowships (M. N.). We acknowledge the use of Laboratorio de Microscopías Avanzadas facilities at the Instituto de Nanociencia de Aragón (LMA-INA) where the electron microscopy characterization was done. Authors acknowledge the LMA-INA for offering access to their instruments and expertise. The authors would like to acknowledge the use of the Servicio General de Apoyo a la Investigación-SAI (Universidad de Zaragoza).

Notes and references

^a Chemical and Environmental Engineering Department and Nanoscience Institute of Aragón (INA), Universidad de Zaragoza, 50018 Zaragoza, Spain. * E-mail: coronas@unizar.es. Tel: +34 976 762471. Fax: +34 976 761879.

^b Department of Earth Sciences, Universidad de Zaragoza, 50009 Zaragoza, Spain.

^c Departamento de Didáctica de las Ciencias Experimentales, Universidad de Zaragoza, 50009 Zaragoza, Spain.

^d X-Ray Diffraction and Fluorescence Analysis Service, Universidad de Zaragoza, 50009 Zaragoza, Spain.

^e Department of Chemical Engineering and Materials Science, University of Minnesota, Minneapolis MN 55455, USA.

† Electronic Supplementary Information (ESI) available: [experimental details, SEM image and orthogonal projection of the Ewald sphere of a silicalite-1 crystal RTP treated and conventionally calcined]. See DOI: 10.1039/c000000x/

- G. T. Kokotailo, S. L. Lawton, D. H. Olson and W. M. Meier, *Nature*, 1978, **272**, 437.
- J. K. Reddy, K. Motokura, T.-r. Koyama, A. Miyaji and T. Baba, *J. Catal.*, 2012, **289**, 53.
- Z. Lai, G. Bonilla, I. Diaz, J. G. Nery, K. Sujaoti, M. A. Amat, E. Kokkoli, O. Terasaki, R. W. Thompson and M. Tsapatsis, *Science*, 2003, **300**, 456.
- G. Bonilla, I. Diaz, M. Tsapatsis, H. K. Jeong, Y. Lee and D. G. Vlachos, *Chem. Mater.*, 2004, **16**, 5697.
- T. Bein, *Chem. Mater.*, 1996, **8**, 1636.
- J. Gascon, F. Kapteijn, B. Zornoza, V. Sebastian, C. Casado and J. Coronas, *Chem. Mater.*, 2012, **24**, 2829.
- O. de la Iglesia, P. Hrabanek, A. Zikanova and M. Kocirik, *Mater. Lett.*, 2012, **70**, 138.

- S. B. Tantekin-Ersolmaz, C. Atalay-Orala, M. Tather, A. Erdem-Senatalar, B. Schoeman and J. Sterte, *J. Membr. Sci.*, 2000, **175**, 285.
- M. Vilaseca, J. Coronas, A. Cirera, A. Cornet, J. R. Morante and J. Santamaria, *Sens. Actuat. B-Chem.*, 2007, **124**, 99.
- C. M. Lew, R. Cai and Y. S. Yan, *Acc. Chem. Res.*, 2010, **43**, 210; M. P. Pina, R. Mallada, M. Arruebo, M. Urbiztondo, N. Navascues, O. de la Iglesia and J. Santamaria, *Microporous Mesoporous Mater.*, 2011, **144**, 19.
- H. Lee, S. I. Zones and M. E. Davis, *Nature*, 2003, **425**, 385.
- M. Navarro, E. Mateo, B. Diosdado and J. Coronas, *CrystEngComm*, 2012, **14**, 6016.
- J. Choi, H.-K. Jeong, M. A. Snyder, J. A. Stoeger, R. I. Masel and M. Tsapatsis, *Science*, 2009, **325**, 590.
- E. Mateo, A. Paniagua, C. Güell, J. Coronas and J. Santamaria, *Mater. Res. Bull.*, 2009, **44**, 1280.
- Y. Li, J. Yu, *Chem. Rev.*, 2014, **114**, 7268.
- S. Shimizu and H. Hamada, *Microporous Mesoporous Mater.*, 2001, **48**, 39.
- H. Van Koningsveld, J. C. Jansen and H. Van Bekkum, *Zeolites*, 1990, **10**, 235.
- W. C. Yoo, J. A. Stoeger, P.-S. Lee, M. Tsapatsis and A. Stein, *Angew. Chem. Int. Ed.*, 2010, **49**, 8699.
- J. Kuhn, M. Motegh, J. Gross and F. Kapteijn, *Microporous Mesoporous Mater.*, 2009, **120**, 35; I. Pellejero, M. A. Urbiztondo, M. P. Pina and J. Santamaria, *J. Membr. Sci.*, 2014, **460**, 34.
- O. Pachtova, M. Kocirik, A. Zikanova, B. Bernauer, S. Miachon and J. A. Dalmon, *Microporous Mesoporous Mater.*, 2002, **55**, 285.