

Chemical Science

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

Exploring the Ring Current of Carbon Nanotubes by First-Principles Calculations

Pengju Ren,^{†§} Anmin Zheng,^{‡§} Jianping Xiao,[†] Xiulian Pan,[†] and Xinhe Bao^{†}*

[†] State Key Laboratory of Catalysis, Dalian Institute of Chemical Physics, Chinese Academy of Sciences, Zhongshan Road 457, Dalian 116023, China.

[‡] State Key Laboratory of Magnetic Resonance and Atomic and Molecular Physics, Wuhan Center for Magnetic Resonance, Wuhan Institute of Physics and Mathematics, Chinese Academy of Sciences, Wuhan 430071, China.

Abstract

Ring current is a fundamental concept to understand the nuclear magnetic resonance (NMR) properties and aromaticity for conjugated systems, such as carbon nanotubes (CNTs). Employing the recently developed gauge including projector augmented wave (GIPAW), we studied the ring currents of CNTs systematically and visualized their distribution. The ring current patterns are determined by the semiconducting or metallic properties of CNTs. The discrepancy is mainly caused by the axial component of external magnetic fields, whereas the radial component induced ring currents are almost independent on the electronic structures of CNTs, where the intensities of ring currents are linearly related to the diameters of CNTs. Although the ring currents induced by the radial component are more intense than the ones by the axial component, only the later determines the overall NMR responses and aromaticity of CNTs as well. Furthermore, the semiconducting CNTs are more aromatic than the metallic counterparts due to the

existence of delocalized ring currents on the semiconducting CNTs. These fundamental features are of vital importance for development of CNT-based nanoelectronics and applications in magnetic fields.

1. Introduction

The physicochemical properties of molecules confined in carbon nanotubes (CNTs) have attracted great interests in diverse fields, such as in drug delivery, nanofluidics, nano-devices, and catalysis.¹⁻³ CNTs consist of sp² hybrid carbon and can be envisioned as extended conjugated systems, possessing the characteristic behaviors of ring currents, as placed in an external magnetic field.¹⁰ The magnetic properties of CNTs and the chemical shifts of CNTs-confined molecules can be significantly influenced.^{11,12} Nuclear magnetic resonance (NMR) spectroscopy is a versatile tool to investigate host-guest systems, by detecting their local electronic structures and the chemical environment of probed nuclei. For example, various molecules e.g. water, methanol and benzene, confined inside the channel of CNTs have been investigated by NMR.⁴⁻⁷ However, the experimental results revealed that the chemical shifts of the CNTs-confined molecules are quite different from those confined within other nanosized channels, such as zeolites.^{8,9} Thus, the chemical shifts of the confined molecules in CNTs remarkably decrease compared with the one in bulk, observed in a number of experimental procedures.⁴⁻⁷ The nuclei independent chemical shifts (NICS) offer a convenient route to investigate the magnetic responses shielding of molecules confined in CNT channels.¹³ With this method, Sebastiani and Kibalchenko et al. interpreted the significant changes in NMR properties of small molecules encapsulated inside CNTs.^{13,14} The NMR properties for CNTs systems are directly related with their electronic structures. The magnetic responses of metallic CNTs are paramagnetic inside the CNT channels, whereas diamagnetic responses for

semiconducting ones.^{13,14} Our previous work demonstrated that the ring currents of CNTs play a critical role in the chemical shift changes.⁹

Besides the effects on NMR response, the analysis of ring current is an efficient way to illustrate the aromaticity of conjugated systems. Aromaticity is an important property for explaining a variety of chemical behaviors, including structural features, energetic stabilities, spectroscopic properties, and reactivity.^{15,16} The aromaticity of CNTs have been investigated by various methods, but with differing conclusions. For example, Aihara et al. reported that both metallic and semiconducting CNTs have positive resonance energies, and the metallic CNTs are slightly less aromatic than semiconducting ones.^{17,18} On the other hand, by correlating the aromaticity with the chemical reactivity of CNTs, it was found that semiconducting nanotubes are analogous to aromatic $[4n+2]$ annulenes, whereas metallic nanotubes are analogous to antiaromatic $[4n]$ annulenes,¹⁹ which explained well the high reactivity of metallic nanotubes over the semiconducting ones.^{20,21} However, the adaptive natural density partitioning (AdNDP) analysis proved that graphene is locally aromatic with π electrons located over the hexagon rings and no global π delocalization presented. In addition, Ormsby and King found that only metallic CNTs can be represented by aromatic sextets and hence are more aromatic by using the Clar valence bond (VB) model.²² Their NICS calculations on a series of finite, hydrogen terminated CNTs agreed with the Clar VB model. The aromaticity of CNTs and the correlation with their reactivity is still an open issue at present.²³

Although ring current effect is important for understanding the NMR and aromaticity, it has not been systemically studied. In addition, the complicated topology of CNTs makes

the ring current to be rather intricate than simple aromatic ring. In this work, with the aid of recently developed gauge including projector augmented wave (GIPAW) method and the 3D visualization approach, we studied the ring current of CNTs by considering various diameters and electronic structures, intending to trace the origins of the magnetic behaviors of CNTs and their aromatic characters.

2. Results and discussion

According to the structural index $\lambda = \text{mod}(n - m, 3)$, where (n, m) is the rolling vector, the CNTs can be divided to two families: for CNTs with $\lambda = 0$, they are metallic; for CNTs with $\lambda \neq 0$, they are semiconducting. CNT- $(n, 0)$ with n varying between 10~17 were investigated, where CNT- $(12, 0)$ and CNT- $(15, 0)$ are metallic, others are semiconducting. Due to the tubular morphology of CNTs, their ring currents also depend on the orientation of CNTs in the magnetic field B_0 . There are two characteristic directions of B_0 relative to the nanotube axis: $B_0(R)$ in the radial direction and $B_0(A)$ in the axial direction as illustrated by Figure 1. First we focus on the ring current induced by $B_0(R)$.




Figure 1. Schematic picture of the direction of external magnetic field.




Figure 2. Ring currents $J_{\text{int}}(r=0.7)$ (a) by $B_0(R)$ and (b) by $B_0(A)$ for CNT-(n, 0), where n from 10 to 17. $J_{\text{int}}(r)$ is defined in the computational detail part.

As shown in Figure 2a, the intensities of ring currents induced by $B_0(R)$ for all CNTs are positive, which indicates that these currents flow anticlockwise and will result in diamagnetic effects. Moreover, the outer ring currents are always more intense than the inner ones. The difference between inner and outer currents by $B_0(R)$ seemingly implies the difference of the electronic states between inside and outside of CNTs. It was known

that the electron clouds of CNTs are different from a graphene layer, with more electron clouds outside than inside due to the curvature.^{24,25} However, detailed analysis reveals that it is not the intrinsic reason for the discrepancy between the inner and outer currents. As shown in Figure 2a, the fitting lines for the inner and outer current are nearly parallel indicating the differences of current intensity are independent on the diameter. Herein, we propose that the weaker inner ring currents are due to the canceling-out effect between delocalized current and the localized current illustrated in Figure 3b. Both the currents flow anticlockwise, so for the outer currents they are of the same direction while inner currents flow in opposite direction. As a result, the outer currents are enhanced whereas the inner currents are reduced (Figure 3a).




Figure 3. (a) Ring currents induced by $B_0(R)$ in the section plane along CNT axis; (b) Schematic picture for illustrating the canceling-out effect, where the red lines represent the current delocalized through the whole tube and the blue lines represent the current localized at one side of the CNTs. The ring current is in $\times 10^{-4}$ atomic unit (a.u.).

In contrast to the ring currents by $B_0(R)$ which are almost independent on their electronic structures, the currents by $B_0(A)$ typically related to the electronic structure of

CNTs: the currents of metallic CNTs are distinctive to the ones for semiconducting CNTs, as shown in Figure 2b. As the ring current reflects the orbital delocalizability which, in turn, relate to the electronic structures such as the density of states and the orbital topology. The difference of ring currents reflects the orbital topology of semiconducting and metallic CNTs, which is consistent with the band structures analysis.¹⁹

The ring currents show a counter-rotating phenomenon. In other words, the positive outer currents flow anticlockwise, while the negative inner currents flow clockwise. This is similar to the case in coronene,²⁶ which cause different magnetic effect for outer ring and inner ring. The counter-rotating currents result in opposite magnetic effects, being partially cancelled out.

Compared to the currents by $B_0(R)$, the overall currents by the $B_0(A)$ are less intense. However, the currents by the $B_0(A)$ are more sensitive to the electronic structures of CNTs. Hence, ring currents by $B_0(A)$ are responsible for the difference in the chemical shift of ^{13}C in CNTs themselves and the confined molecules between semiconducting and metallic CNTs.^{9,27,28}

To access the detail picture, we plot the vectorial map of ring currents. In the first place, we focus on the ring currents induced by $B_0(R)$. Since they do not depend on the electronic structure of CNTs, the ring currents of CNT-(11, 0) are taken as example as shown in Figure 4a and 4b. The circular ring current on the CNT surface is projected on the plane in Figure 4d. The outer ring current of CNT-(11, 0) in Figure 4a shows that the *side* currents (where $\theta > \pi/4$ or $\theta < -\pi/4$) are more intense than the currents in the *front* ($-\pi/4 < \theta < \pi/4$). The positive $J_{int}(\theta)$ indicate the overall current flows anticlockwise. From the

vectorial map, the currents on the side flow through the whole backbone of CNT. Since the periodic model used in our calculations, the currents do not circulate as a closed loop within a unit cell. In contrast, the front currents are more localized on the six-member-rings. In addition, the CNT-(11, 0) possesses the most intensive currents on the side, where the six-member-rings are parallel to B_0 . However, it is well known that a benzene molecule perpendicular to B_0 always exhibits stronger ring currents. Hence, the ring currents of CNTs cannot be intuitively predicted from simple aromatic ring.




Figure 4. Ring current vectorial maps (a) outside and (b) inside of CNT-(11, 0), where the projection plane is at distance of 0.7\AA to the CNT wall. The upper charts in (a) and (b) are integrations of the ring

currents $J_{int}(\theta)$. (c) Induced magnetic field and (d) schematic picture for projection of ring current on plane. The applied external magnetic field B_0 is in radial direction as illustrated in (d). The ring current is in $\times 10^{-4}$ atomic unit (a.u.). The unit for magnetic field is $\times 10^{-6}/B_0$.

The ring currents further induce a magnetic field, as shown in Figure 4c, resulting in a diamagnetic zone in the front and back and a paramagnetic zone in the side of the CNT. This response is qualitatively in line with the classic Ampère's circuital law, where the overall anticlockwise currents will produce a magnetic field opposite to B_0 . Interestingly, the field vectors inside the CNT are rather uniform both in direction and strength, except that the area is very close to nanotube wall. On the contrary, the field vectors outside the CNT vary with the distance to the CNT.

As the ring current induced by $B_0(A)$ depends on the electronic structures of CNTs, we take CNT-(11, 0) and CNT-(12, 0) as examples of the semiconducting and metallic CNTs and discuss them separately. Figure 5 illustrate the ring currents for semiconducting and metallic CNTs. The ring currents maps in Figure 5a and 5c clearly illustrate the counter-rotating phenomenon. Their radial integrations are shown in Figure 5b and 5d, where the currents near the CNT wall are recognized to contributed from the inner shell σ electrons (grey), while the currents in red and green are from π electrons. As the σ -currents always localize in the area near the nucleus, the delocalized π -currents are more important for the overall magnetic response of CNTs.¹³ Figure 5b and d indicate that the counter-rotating phenomenon also occurs between σ -currents and π -currents. The difference between 5b and 5d is that, for semiconducting CNT-(11, 0), the outer currents are intense than the inner ones. However, for metallic CNT-(12, 0), it is weak than the inner ones. This will result in very different magnetic response.




Figure 5. (a, c) Ring currents by $B_0(A)$ and (b, d) their radial integration $J_{int}(r)$ for (a, b) semiconducting CNT-(11, 0) and (c, d) metallic CNT-(12, 0). The ring current is in $\times 10^{-4}$ atomic unit (a.u.).

The $B_0(A)$ induced magnetic field for semiconducting and metallic CNTs are compared in Figure 6. Those counter-rotating currents result in opposite magnetic effects, being partially cancelled out. For semiconducting CNTs, as the outer ring currents are slightly intense than the inner ones, the remaining magnetic response is weak

diamagnetism (Figure 6a). On the contrary, the induced magnetic field for metallic CNTs exhibit paramagnetic effect due to more intense clockwise ring current. Furthermore, because of the larger difference between inner and outer current in CNT-(12, 0), its induced magnetic field is more intense than CNT-(11, 0). The field vectors inside CNT are also uniform both in direction and strength, which is similar to the case in Figure 4c.




Figure 6. The induced magnetic fields by $B_0(A)$ for (a) semiconducting CNT-(11, 0) and metallic CNT-(12, 0). The unit for magnetic field is $\times 10^{-6}/B_0$.

Based on the induced magnetic field, we calculated the isotropic nuclear independent chemical shift (iso-NICS). Figure 7 shows the vertical and horizontal sections of the iso-NICS distributions for CNT-(11, 0) and CNT-(12, 0). First of all, the inner iso-NICS for CNT-(12, 0) is less intense than the one of CNT-(11, 0). This is because the paramagnetic response for CNT-(12, 0) by the $B_0(A)$. Another interesting phenomenon is the inner-tube iso-NICS distributions are rather uniform both in radial and axial direction, which indicate that the magnetic shielding for confined molecules are independent with their location.⁹ In addition, the outer iso-NICS of CNT-(12, 0) is slightly intense and

dispersed than the case of CNT-(11, 0), which is due to the larger discrepancy of inner and outer ring current induced by $B_0(A)$ for CNT-(12, 0). Therefore, the magnetic responses for CNTs are mostly determined by the ring currents induced by $B_0(A)$ instead of $B_0(R)$.




Figure 7. Isotropic NICS distributions (in ppm) for (a) semiconducting CNT-(11, 0) and (b) metallic CNT-(12, 0). The insets are views in radial direction. The unit of color bars is ppm.

The ring currents patterns reflect the aromaticity of CNTs according to the original definition. The anti-clockwise flowing ring current by $B_0(R)$ indicate that all kind of CNTs are aromatic. Moreover, the coexistence of delocalized and localized ring current illustrates the competition of super-aromaticity and local aromaticity.¹⁸ The ring current by $B_0(R)$ increase with radius indicate the more aromaticity for larger CNTs. On the other hand, the ring current by $B_0(A)$ indicates that the semiconducting CNTs are more aromatic than those metallic. The isotropic NICS analysis confirms this conclusion where the more diamagnetic effect indicates more aromatic character. The conclusion derived from ring current excellently agrees with that semiconducting CNTs with larger HOMO-LUMO

gaps are always more aromatic.²⁹ The advantage of the vectorial map of ring current is that both the local and delocalized aromatic characters and their competition can be intuitively described.

The classic concept of ring current is nicely extended to CNTs, and it provides a direct and intuitive way to understand the NMR responses and aromaticity of CNTs. It is expected to be applicable for other conjugate supramolecules. The dependence of the CNTs electronic structures on the ring current and aromaticity can be used for distinguishing and separating the different type of CNTs. These fundamental insights are crucially important for applications of CNTs.

3. Conclusion

By employing the GIPAW method, the ring currents of semiconducting and metallic CNTs were investigated. The ring currents strongly depend on the specific direction of the external magnetic fields B_0 . For the ring current induced by $B_0(R)$, their flowing direction and intensities are not sensitive to the type of CNTs, and the intensities are almost linearly related with their diameters. The vectorial map illustrated that the ring current delocalized on the entire CNT rather than localized on the six-member-rings. In addition, the outer currents are more intense than the one inside the CNT channel. In comparison, the ring currents by $B_0(A)$ depend on the electronic structures (semiconducting or metallic) of CNTs and hence determine the overall magnetic responses and the aromatic characters. The semiconducting CNTs are more aromatic compared with the metallic counterparts due to the more delocalized ring currents.

Computational Details

The calculations were carried out with Quantum ESPRESSO suite,³⁰ using ultrasoft pseudopotentials with Perdew–Burke–Ernzerhof exchange-correlation functional³¹ and plane-wave basis sets. The plane-wave energy cutoff was set to 37 Ry for structures optimization, and 42 Ry for NMR calculations. The k -point grid was set to $1 \times 1 \times 4$ for structures optimization by using Monkhorst-Pack sampling method.³² Based on convergence tests, the k -point grids for semiconducting and metallic CNTs were set to $1 \times 1 \times 14$ and $1 \times 1 \times 80$ for NMR calculations, respectively. The initial geometries of CNTs were taken from the optimized structures by Zurek et al.³³

Ring currents and induced magnetic fields were calculated for each system using the state-of-the-art GIPAW approach,³⁴ which has been widely applied to investigate the NMR parameters of various condensed materials, such as zeolites and graphene-based structures.³⁵ The detail of GIPAW approach can be found in ref 34, 35. In brief, the application of external magnetic field B_0 to molecules induces an inhomogeneous electron ring current J which is evaluated from the linear response to the perturbation. In order to discuss more conveniently, the J induced by B_0 in radial direction was projected on the plane. The vectorial maps of J_{int} outside and inside of CNT with a distance of 0.7 \AA to the wall of CNT are shown in Figure 1a and 1b. The current at 0.7 \AA is considered as contributed mainly by π electrons. In order to quantitatively analyze the ring current, the current integrations $J_{int}(\theta)$ is defined by:

$$J_{int}(\theta) = \int |\mathbf{J}| \sin \varphi dz \quad (1)$$

where φ is the angle between current vector \mathbf{J} and the position vector, and θ is defined in

Figure 1d. Due to symmetry of CNTs, only the ring currents in the $-\pi/2 \leq \theta \leq \pi/2$ range are plotted. The radial integration of the current $J_{int}(r)$ is defined by:

$$J_{int}(r) = \iint |\mathbf{J}| \sin \varphi \, dz d\theta \quad (2)$$

where φ is the angle between \mathbf{J} vector and the position vector and θ is defined in Figure 2d. According to the definition of J_{int} , one can find that when the ring current \mathbf{J} flows anticlockwise ($0 < \varphi < \pi$), $|\mathbf{J}| \sin(\varphi)$ takes positive value; otherwise, the ring current \mathbf{J} flows clockwise ($\pi < \varphi < 2\pi$), it takes negative value.

The vectorial maps of J and induced magnetic field B_{in} were done by using the 3D scientific data visualization code mayavi2.³⁶ The detail of the isotropic NICS calculation can be found in our previous work.⁹

Corresponding Author

*Email: xhbao@dicp.ac.cn

Notes

§ These authors have contributed equally.

The authors declare no competing financial interests.

Acknowledgment

We acknowledge the financial support from the Natural Science Foundation of China (11079005, 21033009 and 21173215) and the Ministry of Science and Technology of China (2012CB224806 and 2011CBA00503). J. Xiao thanks the financial supports from China Postdoctoral Science Foundation and Outstanding Postdoctoral Award (DMTO Project) from Dalian Institute of Chemical Physics (DICP), Chinese Academy of Science (CAS). We also acknowledge the computational resources from Shanghai Supercomputer Center (SSC).

References

1. T. A. Hilder and J. M. Hill, *Small*, 2009, **5**, 300–308.
2. T. Zhang, S. Mubeen, N. V. Myung, and M. A. Deshusses, *Nanotechnology*, 2008, **19**, 332001.
3. X. Pan and X. Bao, *Acc. Chem. Res.*, 2011, **44**, 553–562.
4. H.-J. Wang, X.-K. Xi, A. Kleinhammes, and Y. Wu, *Science*, 2008, **322**, 80–83.
5. Q. Chen, J. L. Herberg, G. Mogilevsky, H.-J. Wang, M. Stadermann, J. K. Holt, and Y. Wu, *Nano Lett*, 2008, **8**, 1902–1905.
6. X. Liu, X. Pan, W. Shen, P. Ren, X. Han, and X. Bao, *J Phys Chem C*, 2012, **116**, 7803–7809.
7. H. Zhang, X. Pan, X. Han, X. Liu, X. Wang, W. Shen, and X. Bao, *Chem. Sci.*, 2013, **4**, 1075–1078.
8. A. Zheng, B. Han, B. Li, S.-B. Liu, and F. Deng, *Chem. Commun.*, 2012, **48**, 6936–6938.
9. P. Ren, A. Zheng, X. Pan, X. Han, and X. Bao, *J. Phys. Chem. C*, 2013, **117**, 23418–23424.
10. L. P., *Prog. Nucl. Magn. Reson. Spectrosc.*, 2000, **36**, 1–88.
11. A. C. Forse, J. M. Griffin, V. Presser, Y. Gogotsi, and C. P. Grey, *J. Phys. Chem. C*, 2014.
12. J. C. Facelli, *Magn. Reson. Chem.*, 2006, **44**, 401–408.
13. D. Sebastiani and K. N. Kudin, *ACS Nano*, 2008, **2**, 661–668.
14. M. Kibalchenko, M. C. Payne, and J. R. Yates, *ACS Nano*, 2010, **5**, 537–545.
15. R. Islas, T. Heine, and G. Merino, *Acc. Chem. Res.*, 2012, **45**, 215–228.
16. T. M. Krygowski, H. Szatyłowicz, O. A. Stasyuk, J. Dominikowska, and M. Palusiak, *Chem. Rev.*, 2014.
17. J. Aihara, T. Yamabe, and H. Hosoya, *Synth. Met.*, 1994, **64**, 309–313.
18. J. Aihara, *J. Phys. Chem.*, 1994, **98**, 9773–9776.
19. E. Joselevich, *ChemPhysChem*, 2004, **5**, 619–624.
20. M. S. Strano, C. A. Dyke, M. L. Usrey, P. W. Barone, M. J. Allen, H. Shan, C. Kittrell, R. H. Hauge, J. M. Tour, and R. E. Smalley, *Science*, 2003, **301**, 1519–1522.
21. S. Banerjee and S. S. Wong, *J. Am. Chem. Soc.*, 2004, **126**, 2073–2081.
22. J. L. Ormsby and B. T. King, *J. Org. Chem.*, 2004, **69**, 4287–4291.
23. I. A. Popov, K. V. Bozhenko, and A. I. Boldyrev, *Nano Res.*, 2012, **5**, 117–123.
24. X. Blase, L. X. Benedict, E. L. Shirley, and S. G. Louie, *Phys. Rev. Lett.*, 1994, **72**, 1878–1881.
25. L. Yu, W.-X. Li, X. Pan, and X. Bao, *J. Phys. Chem. C*, 2012, **116**, 16461–16466.
26. E. Steiner, P. W. Fowler, and L. W. Jenneskens, *Angew. Chem. Int. Ed.*, 2001, **40**, 362–366.
27. E. Zurek and J. Autschbach, *Int. J. Quantum Chem.*, 2009, **109**, 3343–3367.
28. C. Engtrakul, V. M. Irurzun, E. L. Gjersing, J. M. Holt, B. A. Larsen, D. E. Resasco, and J. L. Blackburn, *J Am Chem Soc*, 2012, **134**, 4850–4856.
29. J. Aihara, *J. Phys. Chem. A*, 1999, **103**, 7487–7495.
30. P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G. L. Chiarotti, M. Cococcioni, I. Dabo, A. Dal Corso, S. de Gironcoli, S. Fabris, G. Fratesi, R. Gebauer, U. Gerstmann, C. Gougoussis, A. Kokalj, M. Lazzeri, L. Martin-Samos, N. Marzari, F. Mauri, R. Mazzarello, S. Paolini, A. Pasquarello, L. Paulatto, C. Sbraccia, S. Scandolo, G. Sclauzero, A. P. Seitsonen, A. Smogunov, P. Umari, and R. M. Wentzcovitch, *J. Phys. Condens. Matter*, 2009, **21**, 395502.
31. J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, **77**, 3865.
32. H. J. Monkhorst and J. D. Pack, *Phys. Rev. B*, 1976, **13**, 5188–5192.
33. E. Zurek, C. J. Pickard, B. Walczak, and J. Autschbach, *J Phys Chem A*, 2006, **110**, 11995–12004.

34. F. Mauri, B. G. Pfrommer, and S. G. Louie, *Phys. Rev. Lett.*, 1996, **77**, 5300–5303.
35. C. Bonhomme, C. Gervais, F. Babonneau, C. Coelho, F. Pourpoint, T. Azaïs, S. E. Ashbrook, J. M. Griffin, J. R. Yates, F. Mauri, and C. J. Pickard, *Chem. Rev.*, 2012, **112**, 5733–5779.
36. P. Ramachandran and G. Varoquaux, *Comput. Sci. Eng.*, 2011, **13**, 40–51.