

ChemComm

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

COMMUNICATION

Cite this: DOI: 10.1039/x0xx00000x

Received 00th January 2015,
Accepted 00th February 2015DOI: 10.1039/x0xx00000x
www.rsc.org/

Photocatalytic CO₂ reduction by a mixed metal (Zr/Ti), mixed ligand metal-organic framework under visible light irradiation

Yeob Lee,^a Sangjun Kim,^b Jeung Ku Kang,^{bc*} and Seth M. Cohen^{a*}

Postsynthetic exchange (PSE) of Ti(IV) into a Zr(IV)-based MOF enabled photocatalytic CO₂ reduction to HCOOH under visible light irradiation with the aid of BNAH and TEOA. Use of a mixed-ligand strategy enhanced the photocatalytic activity of the MOF by introducing new energy levels in the band structure of the MOF.


Carbon dioxide (CO₂) produced by energy generation based on fossil fuels contributes to global warming and consequently negative effects on the environment.¹⁻³ Direct conversion of CO₂ into useful chemicals is regarded as a promising technology for addressing the CO₂ problem.⁴ Inspired by nature, systems that can photocatalytically generate hydrocarbon fuels from CO₂ have gathered substantial interests. Homogeneous systems based on transition metal centers and photosensitizers can show high efficiencies, but they are generally not reusable.⁵ On the other hand, heterogeneous photocatalysts based on semiconductors are robust, but suffer from low efficiencies because most of these systems only absorb UV light, which represents only ~4% of the solar energy spectrum.⁶ Developing new photocatalysts that can harvest more of the solar spectrum, while retaining high stability and efficiency, would be an important advancement for CO₂ utilization.

Metal-organic frameworks (MOFs) are crystalline hybrid materials for CO₂ conversion with high specific surface area, because they can be tuned by design.⁷⁻¹⁰ The use of MOFs in photocatalysis of CO₂ has been investigated.^{11,12} Fu *et al.* found that Ti-based NH₂-MIL-125(Ti) could mediate the conversion of CO₂ to HCOO⁻ in the presence of triethanolamine (TEOA). In addition, they found that visible light sensitivity could be introduced by incorporating 2-aminobenzene-1,4-dicarboxylic acid (NH₂-bdc).¹¹ Another report also used NH₂-MIL-125(Ti) to produce H₂ from a TEOA-H₂O solution with visible light irradiation.¹³

Now a well studied, robust, and highly porous MOF, UiO-66 (UiO = University of Oslo) constructed from Zr secondary-building units (SBUs) and benzene-1,4-dicarboxylic acid (H₂bdc),¹⁴⁻¹⁸ cannot catalyze the reduction of CO₂ to HCOO⁻ or the reduction of H₂O to H₂. The Zr₆ SBUs (Zr₆O₄(OH)₄) cannot accept electrons from the bdc linker under light irradiation (unlike the aforementioned Ti₈ SBUs (Ti₈O₈(OH)₄))

because the redox potential energy level of the Zr₆ SBUs in UiO-66 lie above the LUMO of the bdc ligands.^{12,13,19} Consequently, it was hypothesized that embedding Ti ions into the Zr₆ SBUs of UiO-66 might introduce catalytic activity to UiO-66 by lowering the redox potential energy of Zr₆ cluster.

Herein, we report a mixed-ligand, mixed-metal UiO-66-derivative (Zr_{4.3}Ti_{1.7}O₄(OH)₄(C₈H₇O₄N)_{5.17}(C₈H₈O₄N₂)_{0.83}, **1(Zr/Ti)**) obtained by postsynthetic exchange (PSE)²⁰⁻²⁶ as an effective photocatalyst for CO₂ reduction under visible light irradiation. The Ti(IV) ions make the SBUs capable of accepting electrons generated via light absorption by the organic linkers. Introducing a small amount of 2,5-diaminobenzene-1,4-dicarboxylic acid ((NH₂)₂-bdc) as a co-ligand provided new energy levels in the band structure of the MOF and introduced broader light absorption coverage for the MOF.



Scheme 1. Synthesis of mixed-ligand MOF **1(Zr)** via PSE to obtain mixed-metal MOFs **1(Zr/Ti)**, UiO-66(Zr/Ti)-NH₂.

Solvothermal synthesis of **1(Zr)** produced nanocrystals with excellent crystallinity (Fig. 1) and a narrow size distribution (Fig. S1). The crystal growth of **1(Zr)** gave particles with an edge length of ~70 nm, which is smaller than that obtained for UiO-66(Zr)-NH₂ at around ~200 nm. **1(Zr)** absorbed visible light as shown by two broad absorption bands in the UV-vis spectrum, while UiO-66(Zr)-NH₂ absorbs only a small portion of blue light beyond the UV spectrum

(Fig. S2). The ratio between NH_2 -bdc and $(\text{NH}_2)_2$ -bdc was calculated by dissolving the MOF under alkaline conditions and measuring the ^1H NMR spectrum in solution (see ESI). **1(Zr)** contained ~14% $(\text{NH}_2)_2$ -bdc and 86% NH_2 -bdc, which is slightly different from ligand ratio used in synthesis of the MOF (this may be due to the lower solubility of $(\text{NH}_2)_2$ -bdc in *N,N*-Dimethylformamide (DMF)). Afterwards, these Zr-based MOFs were exposed to DMF solutions of $\text{TiCl}_4(\text{THF})_2$ for 5 days at 85 °C in order to achieve PSE with Ti(IV).




Fig. 1. (a) PXRD patterns of UiO-66(Zr)-NH₂, UiO-66(Zr/Ti)-NH₂, **1(Zr)**, and **1(Zr/Ti)**. (b) Diffuse reflectance UV-visible spectra of **1(Zr)** and **1(Zr/Ti)** (normalized using the Kubelka-Munk function, F(R)). (c) ^1H NMR of dissolved **1(Zr)**.

After PSE, the crystallinity, morphology, and light absorption of the UiO-66 materials were maintained, indicating that PSE did not alter the gross physical properties of the MOFs. Introduction of Ti(IV) into the MOF was confirmed by both energy-dispersive X-ray spectroscopy (EDX) and inductively-coupled plasma mass spectrometry (ICP-MS) measurements. The ratios for Zr/Ti were 2.52 for **1(Zr/Ti)** and 3.03 for UiO-66(Zr/Ti)-NH₂ as determined by ICP-MS (Table S1). The ICP-MS data support our argument that Ti(IV) was substituted for Zr(IV) in MOF SBUs. The weight percentage of both elements in **1(Zr/Ti)** were determined to be 23.2 wt% for Zr and 4.8 wt% for Ti. If Ti was simply loaded into **1(Zr)** with no change in the SBUs, then these values should be 29.2 wt% for Zr and 6.1 wt% for Ti (Table S2). Furthermore, the surface area of **1(Zr)** was essentially unchanged after PSE (from ~930 m²/g to ~990 m²/g), indicating the added Ti is not blocking the pores of the MOF. These suggest that, on average, the Zr₆ SBUs was converted by PSE to ~Zr_{4.3}Ti_{1.7} for **1(Zr/Ti)** and ~Zr_{4.5}Ti_{1.5} for UiO-66(Zr/Ti)-NH₂.




Fig. 2. Turnover numbers of **1(Zr/Ti)** (green) and UiO-66(Zr/Ti)-NH₂ (gold) for photocatalysis of CO₂ to HCOOH over three cycles. Samples were recovered after each cycle and reused under identical reaction conditions.

Both MOFs were tested for photocatalytic CO₂ reduction under visible light irradiation. The reaction was conducted in 5 mL of a mixed solution of 4:1 (v/v) acetonitrile (MeCN)-triethanolamine (TEOA, as a sacrificial base), and 0.1 M 1-benzyl-1,4-dihydronicotinamide (BNAH, as a sacrificial reductant).²⁷⁻²⁹ The suspension, which contained 5 mg of MOF, was purged with 1 bar of CO₂ gas for 30 min followed by light irradiation by a 300 W Xe lamp. The initial pH value of the 4:1 MeCN-TEOA solution was ~11, but dropped to ~9.5 after purging with CO₂ gas. Because of the high pH, the photocatalysis products can be deprotonated; therefore, the reaction mixtures were extracted with ethyl acetate and washed with H₂SO₄ (to remove TEOA and protonated products).³⁰ The final ethyl acetate solution (1 μL) was analyzed by gas chromatograph-mass spectrometry (GC-MS) to identify the products.

The photocatalysis products were analyzed via GC-MS, the results of which are shown in Fig. 2. **1(Zr/Ti)** showed similar turnover number values over three photocatalytic cycles (6 hours each), indicating the catalytic ability of the MOF was not degraded during photocatalysis. Turnover numbers were calculated based on the Ti content determined from ICP-MS results. The average turnover number of 6.27±0.23

(31.57±1.64 μmol of HCOOH, from 3 independent samples) indicates each Ti site transferred about 13 electrons to CO₂ over the course of each catalytic run (Fig. S3). UiO-66(Zr/Ti)-NH₂ gave a lower turnover number (4.66±0.17) when compared to **1(Zr/Ti)** (Fig. 2, Fig. S4). No HCOOH was detected when using the parent **1(Zr)** and UiO-66(Zr)-NH₂ materials, indicating that Ti was essential for photocatalysis.

The MOFs were studied by photoluminescence (PL) spectroscopy to provide evidences for charge transfer in **1(Zr/Ti)**. As shown in Fig. 3a, the emission intensity of **1(Zr)** was remarkably reduced after PSE. This indicates that the recombination rate of photogenerated electron-hole pairs in the organic linkers was decreased suggesting charges were transferred to the inorganic SBUs. In addition, **1(Zr/Ti)** achieved better charge separation than UiO-66(Zr/Ti)-NH₂ because **1(Zr/Ti)** quenched a greater portion of the photogenerated charges than UiO-66(Zr/Ti)-NH₂ (Fig. S5). This indicates that **1(Zr/Ti)** accepts more electrons from the organic linkers to catalyze CO₂ than UiO-66(Zr/Ti)-NH₂, which is supported by the GC-MS results.




Fig. 3. (a) Photoluminescence spectra of both **1(Zr)** and **1(Zr/Ti)**, (b) Energy band structure of **1(Zr/Ti)** derived from UPS and F(R) results. Heterogeneous ligands formed two energy levels in MOF, which potentially catalyze CO₂.

The energy band structures of both **1(Zr/Ti)** and UiO-66(Zr/Ti)-NH₂ were investigated using UV light photo-electron spectroscopy (UPS, Fig. S6). The UPS results indicate that **1(Zr/Ti)** has two different valence bands, in contrast to UiO-66(Zr/Ti)-NH₂ that has a single valence band. This is consistent with the UV-visible spectra in Fig. 1(b) where **1(Zr/Ti)** showed two absorption bands. The maxima of the two valence bands of **1(Zr/Ti)** were calculated to be 1.62 eV and -0.44 eV (vs. SHE) from the UPS spectrum of **1(Zr/Ti)** and bandgap energies for those two levels were acquired from UV-Vis spectra as 2.46 eV and 1.66 eV, respectively. These data can be used to produce an energy band diagram of **1(Zr/Ti)** as shown in Fig. 3(b). Two conduction band minima values of -0.84 eV and -2.10 eV (vs. SHE) are suitable for electron transfer to CO₂.³¹ UiO-66(Zr/Ti)-NH₂ has a single valence band maximum of 1.88 eV and its conduction band minimum was calculated to be -0.79 eV based on the bandgap energy for UiO-66(Zr/Ti)-NH₂ of 2.67 eV (calculated from the UV-Vis spectrum, Fig. S7). Consequently, **1(Zr/Ti)** is expected to show better photocatalysis efficiency than UiO-66(Zr/Ti)-NH₂ because **1(Zr/Ti)** has two light absorption routes (both suitable for CO₂ reduction) originating from the (NH₂)₂-bdc ligand.

In order to prove that HCOOH is produced from photocatalytic reduction of CO₂, the reaction was performed using ¹³CO₂ and the products analyzed by ¹³C NMR. A solution containing CD₃CN, TEOA, BNAH, and ¹³CO₂ was subjected to similar photocatalysis conditions (see ESI). Calibration of the expected product peaks was performed

because the basic reaction conditions can perturb the chemical shifts of the products (Fig. S8).³⁰ H¹³COOH was found at 162.73 ppm in CD₃CN solution and this value was increased to 169.86 ppm due to deprotonation of H¹³COOH to H¹³COO⁻ with added TEOA.

Several products, including H¹³COO⁻, ¹³CO₂, H¹³CO₃²⁻, ¹³CO₃²⁻, residual solvent, and other small peaks were found in ¹³C NMR spectrum after photocatalysis by both **1(Zr/Ti)** after 13 hours of light irradiation (Fig. 4). ¹³CO₃²⁻ and H¹³CO₃²⁻ were produced by oxidation of ¹³CO₂ under these basic conditions.^{31,32} Other small peaks come from isotopes of BNAH as these shifts were found in a reference solution of CD₃CN-TEOA-BNAH (Fig. S8). These results indicate that the carbon source of photocatalytically produced HCOOH is CO₂ gas, and not other sources (such as MOF ligand decomposition). The ¹³C NMR spectrum of the product solution from UiO-66(Zr/Ti)-NH₂ showed additional peaks in addition to BNAH and these peaks might represent organic linkers dissociated from the MOF during photocatalysis (Fig. S9). No H¹³COO⁻ was detected in NMR spectra when using **1(Zr)** and UiO-66(Zr)-NH₂, consistent with the GC-MS results.

Durability is another important issue when considering long-term photocatalysis. The crystallinity, Zr/Ti ratio, and morphology of the UiO-66 materials were examined after three cycles of photocatalysis. Both **1(Zr/Ti)** and UiO-66(Zr/Ti)-NH₂ maintained crystallinity and morphology after three cycles of photocatalysis (Fig. S10, S11). However, UiO-66(Zr/Ti)-NH₂ showed broaden PXRD reflections, a roughened surface in SEM image, and greater leaching of Ti (as measured by ICP-MS, Table S1), compared to **1(Zr/Ti)**. Overall, **1(Zr/Ti)** was more stable than UiO-66(Zr/Ti)-NH₂ during photocatalysis.




Fig. 4. ¹³C NMR spectrum of product solution from photocatalysis of ¹³CO₂ by **1(Zr/Ti)** for 13 hours under visible light irradiation. ◆ = BNAH.

To evaluate our mixed-metal approach, the photocatalytic activity of NH₂-MIL-125(Ti) was also investigated. NH₂-MIL-125(Ti) was synthesized following a reported procedure and its structure confirmed by PXRD (Fig. S12).¹³ Photocatalysis with NH₂-MIL-125(Ti) under the same reaction conditions described above gave a turnover number of 1.52 after 6 hours. This value is much lower when compared to the MOFs described here. Therefore, it is inferred that the mixed metal SBUs described here are more efficient photocatalysts. This might be, in part, because the Ti₈ SBUs have a redox potential that is too low to provide a sufficient driving force to catalyze CO₂ reduction when compared to the mixed Zr/Ti SBUs described here.

The photocatalytic ability of **1(Zr/Ti)** was also compared to heterogeneous photocatalytic systems based on semiconductors or MOFs in units of turnover frequency (h⁻¹) (Table S3, S4).³³⁻³⁸ **1(Zr/Ti)**

prepared in this work showed a much higher photocatalytic ability, and also improved visible light sensitivity than non-MOF heterogeneous photocatalysts. In the comparison to MOF-based photocatalysts, only one MOF system we aware of shows better catalytic ability than **1(Zr/Ti)**, but this system requires Ru for both the catalytic site and an exogenous light sensitizer.³⁸ In the latter example, the reaction conditions are not identical to those reported here, which makes an absolute comparison of photoreactivity difficult.

In summary, highly efficient and robust MOF photocatalysts for CO₂ reduction to HCOOH under visible light irradiation, without the need for an exogenous light sensitizer was developed via PSE of Ti(IV) into a series of UiO-66 MOFs. UiO-66 materials were tuned to have catalytic activity by lowering the electron accepting levels of the Zr_{6-x}Ti_x (Zr_{6-x}Ti_xO₄(OH)₄) SBUs. Introduction of diamine-substituted ligands greatly enhanced the photocatalytic ability by introducing new energy levels for additional light absorption and charge transfer. This study suggests a new approach to develop MOF photocatalysts using a mixed-metal and mixed-linker approach.

The majority of the experiments described, including all of the synthetic work and MOF characterization, was supported by a grant from the Department of Energy, Office of Basic Energy Sciences, Division of Materials Science and Engineering under Award No. DE-FG02-08ER46519 (Y.L., S.M.C.). Additional support for S.K. and J.K.K. was provided by the Korea Center for Artificial Photosynthesis (KCAP) funded by the National Research Foundation of Korea (2009-0093881).

Notes and references

^a Department of Chemistry and Biochemistry, University of California, San Diego, La Jolla, California 92093, United States of America, E-mail: scohen@ucsd.edu

^b Department of Materials Science and Engineering, Korea Advanced Institute of Science and Technology (KAIST), Daejeon, 305-701, Republic of Korea, E-mail: jeung@kaist.ac.kr

^c Graduate School of EEWS, Korea Advanced Institute of Science and Technology (KAIST), Daejeon, 305-701, Republic of Korea

† Electronic Supplementary Information (ESI) available: [experimental, details of results]. See DOI: 10.1039/b000000x/

- H. D. Matthews, N. P. Gillett, P. A. Stott and K. Zickfeld, *Nature*, 2009, **459**, 829-832.
- S. J. Davis, K. Caldeira and H. D. Matthews, *Science*, 2010, **329**, 1330-1333.
- N. S. Lewis and D. G. Nocera, *Proc. Natl. Acad. Sci. USA*, 2006, **103**, 15729-15735.
- E. V. Kondratenko, G. Mul, J. Baltrusaitis, G. O. Larrazábal and J. Pérez-Ramírez, *Energy & Environ. Sci.*, 2013, **6**, 3112-3135.
- A. J. Morris, G. J. Meyer and E. Fujita, *Acc. Chem. Res.*, 2009, **42**, 1983-1994.
- Y. Qu and X. Duan, *Chem. Soc. Rev.*, 2013, **42**, 2568-2580.
- K. Sumida et al., *Chem. Rev.*, 2012, **112**, 724-781.
- J. R. Li, J. Sculley and H. C. Zhou, *Chem. Rev.*, 2012, **112**, 869-932.
- M. Yoon, R. Srirambalaji and K. Kim, *Chem. Rev.*, 2012, **112**, 1196-1231.
- J. Della Rocca, D. Liu and W. Lin, *Acc. Chem. Res.*, 2011, **44**, 957-968.
- Y. Fu et al., *Angew. Chem. Int. Ed.*, 2012, **51**, 3364-3367.
- S. Wang, W. Yao, J. Lin, Z. Ding and X. Wang, *Angew. Chem. Int. Ed.*, 2014, **53**, 1034-1038.
- Y. Horiuchi et al., *J. Phys. Chem. C*, 2012, **116**, 20848-20853.
- L. Valenzano et al., *Chem. Mater.*, 2011, **23**, 1700-1718.
- Q. Yang et al., *Chem. Commun.*, 2011, **47**, 9603-9605.
- M. Kim and S. M. Cohen, *CrystEngComm*, 2012, **14**, 4096-4106.
- M. Servalli, M. Ranocchiari and J. A. Van Bokhoven, *Chem. Commun.*, 2012, **48**, 1904-1906.
- F. Vermoortele et al., *J. Am. Chem. Soc.*, 2013, **135**, 11465-11468.
- W. Liang, R. Babarao and D. M. D'Alessandro, *Inorg. Chem.*, 2013, **52**, 12878-12880.
- M. Kim, J. F. Cahill, Y. Su, K. A. Prather and S. M. Cohen, *Chem. Sci.*, 2012, **3**, 126-130.
- O. Karagiari et al., *Chem. Sci.*, 2012, **3**, 3256-3260.
- M. Kim, J. F. Cahill, H. Fei, K. A. Prather and S. M. Cohen, *J. Am. Chem. Soc.*, 2012, **134**, 18082-18088.
- S. Takaishi, E. J. DeMarco, M. J. Pellin, O. K. Farha and J. T. Hupp, *Chem. Sci.*, 2013, **4**, 1509-1513.
- S. Pullen, H. Fei, A. Orthaber, S. M. Cohen and S. Ott, *J. Am. Chem. Soc.*, 2013, **135**, 16997-17003.
- H. Fei et al., *J. Am. Chem. Soc.*, 2014, **136**, 4965-4973.
- H. Fei, S. Pullen, A. Wagner, S. Ott and S. M. Cohen, *Chem. Commun.*, 2015, **51**, 66-69.
- Y. Tamaki, T. Morimoto, K. Koike and O. Ishitani, *Proc. Natl. Acad. Sci. USA*, 2012, **109**, 15673-15678.
- C. Pac, M. Ihama, M. Yasuda, Y. Miyauchi and H. Sakurai, *J. Am. Chem. Soc.*, 1981, **103**, 6495-6497.
- X. Q. Zhu et al., *Chem. Eur. J.*, 2003, **9**, 3937-3945.
- H. Takeda, H. Koizumi, K. Okamoto and O. Ishitani, *Chem. Commun.*, 2014, **50**, 1491-1493.
- T. Reda, C. M. Plugge, N. J. Abram and J. Hirst, *Proc. Natl. Acad. Sci. USA*, 2008, **105**, 10654-10658.
- S. Moret, P. J. Dyson and G. Laurenczy, *Dalton Trans.*, 2013, **42**, 4353-4356.
- X.-H. Xia et al., *Carbon*, 2007, **45**, 717-721.
- T. Baran, S. Wojtyła, A. Dibenedetto, M. Aresta and W. Macyk, *Appl. Catal. B*, DOI:10.1016/j.apcatb.2014.09.052.
- Q. Zhang, C.-F. Lin, Y. H. Jing and C.-T. Chang, *J. Air Waste Manag. Assoc.*, 2014, **64**, 578-585.
- G. Mele et al., *Molecules*, 2015, **20**, 396-415.
- L. Li et al., *Chem. Sci.*, 2014, **5**, 3808-3813.
- D. Sun et al., *Chem. Commun.*, 2015, **51**, 2645-2648.