

ChemComm

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

COMMUNICATION

Strong antiferromagnetic exchange between manganese phthalocyanine and ferromagnetic europium oxide[†]

Cite this: DOI: 10.1039/x0xx00000x

Received 00th January 2012,

Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

We report on the antiferromagnetic exchange coupling between a submonolayer of Mn(II)-phthalocyanine molecules and a ferromagnetic Eu(II)-oxide thin film. The exchange energy is larger by nearly two orders of magnitude compared to previous studies involving oxidic substrates.

Within the quest of organic spintronics¹ it is important to interface magnetic molecules with inorganic spin injection materials serving as electrodes.² Spin injection through the ferromagnetic (FM) semiconductor europium(II)-oxide (EuO) with spin polarization of almost 100%³ is more promising than from FM metals,⁴ in which the spin polarization is only in the order of 50%. Yet, the electronic configuration and magnetic properties of molecules adsorbed at the surface of FM semiconducting oxides remain largely unexplored despite their fundamental relevance^{1c} and in contrast to the wealth of reports focusing on the magnetic properties of paramagnetic organic semiconductors at the interface to FM metals.⁵ Only in case of a Cu(II) complex adsorbed on ferrimagnetic magnetite (Fe₃O₄) a weak exchange interaction was observed,⁶ while for the TbPc₂ single-molecule magnet deposited on the FM semiconductor La_{0.3}Sr_{0.7}MnO₃ (LSMO) the magnetic interaction was undetectably small.⁷

Here we show that Mn(II)-phthalocyanine (MnPc) couples antiferromagnetically to a thin film of the FM semiconductor Eu(II)-oxide^{4b,8} grown on highly oriented pyrolytic graphite (HOPG). Our experimental data supported by multiplet calculations reveal that the molecules adsorb with their macrocycles parallel to the surface and that the surface-adsorbed MnPc exhibits a high-spin $S = 5/2$ state.

A sketch of the sample structure and an atomic force microscope image of the bare EuO surface are shown in Figure 1a,b. The Eu(II)-oxide thin film was grown in ultra-high vacuum by reactive molecular beam epitaxy^{8c} and,

subsequently, a submonolayer amount of MnPc was deposited (*cf.* Electronic Supplementary Information (ESI)[†]).




Figure 1 (a) Structure of MnPc and sketch of the investigated sample. The magnetic field and the x-ray beam were kept parallel. (b) Atomic force microscopy (ambient conditions) image of the EuO thin film with line profile. The height difference between the brightest and darkest areas is 20 nm. (c,d) XAS and XMCD recorded in remanence at the Eu M_{4,5} (3d→4f) and Mn L_{2,3} (2p→3d) edges. The XMCD spectra are shown with an offset. The data evidence a net remanent Mn magnetic moment, revealing that MnPc couples antiferromagnetically to the ferromagnetic EuO thin film.

Grazing-incidence x-ray absorption spectra (XAS) and X-ray magnetic circular dichroism (XMCD) recorded at the Eu M_{4,5} and Mn L_{2,3} edges at 4 and 50 K in remanence are plotted in Figure 1c,d. The remanent XMCD signal at the Eu M_{4,5} edge confirms the ferromagnetism of the EuO thin film.^{8a} The Mn L_{2,3} spectra exhibit a strong XMCD signal with opposite sign demonstrating antiparallel alignment of the MnPc and EuO magnetization indicating antiferromagnetic (AFM) coupling of the MnPc molecules to the FM EuO substrate.

We have performed effective point-charge atomic multiplet calculations using the MultiX⁹ software to determine the adsorption geometry of MnPc and to shed light on the Mn and Eu electronic ground states and magnetic moments. This powerful approach is highly useful for the description of the low-symmetry ligand fields present in surface-adsorbed organometallic complexes. Least-squares fits optimizing the strengths and positions of the effective point charges to reproduce the experimental Mn circular and linear dichroism spectra allow us to extract the sought information from the experimental spectra.

Grazing-incidence x-ray spectra recorded at the Eu $M_{4,5}$ edges at 6.8 T and 4 K are shown in Figure 2a. The calculated spectra for Eu(II) considering only the first coordination sphere, that is, taking into account the closest oxygen atoms, are in excellent agreement with the experimental data. Comparison with the calculated spectra for Eu(III) and with literature spectra¹⁰ reveals that the nonmagnetic Eu_2O_3 is virtually absent.




Figure 2 XAS, XMCD (a-c) and XNLD (d) spectra recorded at the Eu $M_{4,5}$ ($3d \rightarrow 4f$) and Mn $L_{2,3}$ ($2p \rightarrow 3d$) edges at the temperatures, magnetic fields and x-ray incidence angles indicated in the plots. The experimental data are compared to calculated spectra which are obtained from multiplet calculations based on the MultiX code.⁹ Least-squares fits to all Mn x-ray spectra indicate that the MnPc molecules adsorb with their macrocycles parallel to the surface.

The Mn $L_{2,3}$ XAS and XMCD spectra recorded at 6.8 T and 4 K in grazing incidence, the x-ray natural linear dichroism (XNLD) spectra and the corresponding calculated spectra are presented in Figure 2b-d. The Mn spectra differ significantly from bulk MnPc,¹¹ e.g., the L_3 and L_2 XMCD signals are antiparallel while in the bulk they are parallel indicating a large difference in Mn electronic structure. Notably, the present spectra are also different from those of MnPc adsorbed on Co and Cu transition metal surfaces^{5e,f} and on an oxygen reconstructed Co surface.^{5h} The x-ray spectra exhibit a well resolved substructure consistent with a low molecule-substrate hybridization.^{5e} The point charges used as an input for the multiplet calculations (Table S1) were optimized in order to minimize the error calculated by the sum of squared

deviations between the calculated and experimental spectra, respectively, shown in Figure 2b-d. Details are given in the ESI†. The calculations reveal that the ground-state multiplet is characterized by a high-spin $S = 5/2$ state of the Mn ion. In contrast, the intermediate $S = 3/2$ state of Mn(II) as observed in bulk MnPc,¹¹ as well as Mn(I) and Mn(III) oxidation states can be excluded because the respective XAS calculations yield spectra which are incompatible with the experimental data (cf. Figures S1 and S2). Moreover, the flat orientation of the molecules on the EuO surface, consistent with the strong observed magnetic Mn-Eu coupling, can be directly inferred from the orientation of the point-charge ligand field (Table S1) obtained from the fits to the x-ray spectra.

The spin and orbital magnetic moments obtained from the sum rule¹² analyses of the Mn $L_{2,3}$ and Eu $M_{4,5}$ x-ray spectra are presented in Table S4. Note that the value of the effective spin projection $\langle S_{\text{eff},z} \rangle$ obtained from the sum rule analysis of the Mn spectra is lowered with respect to that of the true spin $\langle S_z \rangle$ because of mixing between $2p_{3/2}$ and $2p_{1/2}$ components.^{13a} Moreover, it can be modified by the presence of a finite dipole (T_z) term. These difficulties can be overcome by applying the sum rules to the calculated x-ray spectra for which the $\langle S_z \rangle$ value is known. This approach allows to extract the correction factors $c = \langle S_{\text{eff},z} \rangle / \langle S_z \rangle$ for Mn and Eu (Table S2 and S3), respectively. The obtained correction factor for Mn is virtually independent of the x-ray incidence angle θ . It agrees very well with the values found for high-spin $3d^5$ Fe(III)^{13b} and Mn(II).^{13a} The sum rule analysis also reveals a small orbital moment $\langle L_z \rangle$ of up to $0.3 \mu_B$ which is not reproduced in the multiplet calculations. We attribute this deviation as well as the small deviation of the calculated linear dichroism from the experimental spectra at 639 eV to subtle charge-transfer effects between the Mn(II) ion and the Pc ligand resulting in a minor contribution of the Mn(I)-Pc⁺ configuration.^{13c} This configuration which exhibits parallel alignment of spin and orbital angular momenta is neglected in our calculations. Yet, such charge-transfer effects could contribute, together with the exchange coupling to the EuO film with in-plane magnetic anisotropy, to a slight lowering of the Mn spin magnetic moment to $3.7 \pm 0.3 \mu_B$ observed in grazing incidence at 4 K, which is below the expected value of $5 \mu_B$. In view of the very short absorption length of $\sim 3 - 10 \text{ nm}^{14}$ for bulk rare earths comparable to the electron escape depth of a few nm in the corresponding x-ray range saturation effects in the used total-electron yield detection have to be considered. Saturation effects are particularly effective at the Eu M_5 edge resulting from a sizeable drop of x-ray intensity within the top surface layers owing to the strong absorption. A simple estimation yields that the Eu orbital magnetic moment extracted by the sum rule analysis vanishes, as would be expected for the $4f^7$ configuration Eu(II), when the M_5 peak of the more strongly absorbed circular polarization is scaled up by $\sim 10\%$. A further important parameter characterizing the MnPc/EuO interface is the exchange energy E_{ex} which refers to the energy needed to reverse the MnPc magnetic moment from the

antiparallel to the parallel alignment. Since the Mn magnetic moment remains antiparallel to the EuO magnetization even in the presence of an external field of 6.8 T, the exchange energy must be stronger than the corresponding Zeeman splitting of ~ 4 meV. In fact, the magnetization curves $M(H)$ obtained in grazing incidence at 4 K for both Mn and Eu show that the Mn magnetic moment saturates already for $\mu_0 H > 0.5$ T and remains saturated up to 6.8 T (Figure 3). The exchange energy can be estimated from the temperature-dependent ratio of the remanent Mn and Eu magnetization values (Table S4 and Figures S4,5) by a Brillouin function model (Figure S7),^{5c,d} yielding $E_{\text{ex}}^{\text{B}} = -14 \pm 7$ meV. Furthermore, the magnetic field dependence of the Mn magnetic moment at 4 K and the magnetic moment measured at 50 K can be calculated from the spin Hamiltonian $\hat{\mathcal{H}} = \mu_0 \mu_B \hat{S}_{\text{Mn}} g_{\text{Mn}} (H + H_{\text{ex}})$ with $H_{\text{ex}} = k_{\text{ex}} M_{\text{Eu}}$. Here, \hat{S}_{Mn} is the Mn spin operator, and $g_{\text{Mn}} = 2$ is the Mn g -factor. The coupling to the FM EuO substrate is taken into account via the effective exchange field H_{ex} which was set to be proportional to the magnetization M_{Eu} (in μ_B) of the substrate. For $S_{\text{Mn}} = 5/2$ as found from the x-ray spectra the exchange energy can be determined from a least-squares fit to be $E_{\text{ex}}^{\text{SH}} = 2 g_{\text{Mn}} S_{\text{Mn}} \mu_0 \mu_B H_{\text{ex}} = -14 \pm 4$ meV, in excellent agreement with the previous Brillouin function estimation. Magnetic anisotropies are neglected here in order to avoid overparameterization of the model, however, they may influence the shape of the Mn and Eu $M(H)$ at elevated magnetic fields.




Figure 3 Normalized magnetization $M(H)$ of the EuO thin film and of the adsorbed MnPc molecules obtained from XMCD. Experimental data and the best-fit curve obtained from the model described in the text are shown as symbols and as a solid line, respectively. Calculated Mn $M(H)$ for smaller exchange energies are shown in the inset. The dashed lines denote the field range in which the Eu magnetization is larger by more than 10% compared to the remanent magnetization, indicating the fields at which anisotropy effects may become relevant. The EuO hysteresis opening of ~ 12 mT is not resolved. Due to the interaction with the EuO substrate, the magnetization of MnPc saturates already at low magnetic fields.

This exchange energy is two orders of magnitude above the value found for Er(III) single-ion magnets on Ni,^{5k} one order of magnitude above the exchange coupling strength of Co-porphyrin on graphene on Ni^{5l} and of TbPc₂ on Ni,¹⁵ but it is up to one order of magnitude below the exchange coupling strength of 3d transition metal complexes on Co and Ni.^{5c,f} Remarkably, the Mn-Eu magnetic coupling reported here is nearly two orders of magnitude larger than that found for a Cu porphyrin derivative on magnetite.⁶ The Mn-Eu magnetic coupling is likely to be mediated via the Eu 5d bands which have been shown to be spin polarized.^{16a} Because of an AFM coupling between Mn 3d and Eu 5d electrons^{16b} and the FM coupling between the Eu 4f and 5d orbitals,^{8a,16b} the net Mn-Eu coupling is AFM with an exchange coupling strength of $j = E_{\text{ex}}/(2 S_{\text{Eu}} S_{\text{Mn}}) \cong -0.82$ meV taking into account $S_{\text{Eu}} = 7/2$. The strength of the coupling matches very well typical values for 3d-4f systems.^{16b} 3d-4f super exchange via O or N forming a 90° pathway is unlikely because it is expected to be weak and FM.^{16c} The estimated Eu-Mn dipolar coupling of $j_{\text{dipolar}} \cong -0.8$ μeV is far too small to account for the observed coupling strength.

In conclusion, we demonstrate the presence of a strong antiferromagnetic exchange interaction at the interface between the paramagnetic organic semiconductor MnPc and the ferromagnetic semiconductor Eu(II)-oxide. Moreover, the x-ray absorption spectra reveal that the MnPc molecules adsorb flat on the EuO surface. The electronic configuration of Mn(II) in MnPc is significantly modified upon adsorption on EuO compared to bulk MnPc, leading to a high-spin $S = 5/2$ state instead of intermediate spin $S = 3/2$. Our results pave the way to a new class of molecule/ferromagnetic oxide spin interfaces and hybrid molecule/inorganic tunneling spintronic devices.

The x-ray measurements were performed at the EPFL/PSI X-Treme beamline¹⁷ at the Swiss Light Source, Paul Scherrer Institut, Villigen, Switzerland. Rolf Schelldorfer and Prof. T. Jung are kindly acknowledged for the atomic force microscopy images recorded at the Scanning Probe Microscopy User Lab, Laboratory for Micro and Nanotechnology, Paul Scherrer Institut, Villigen, Switzerland. J.D. and C.W. gratefully acknowledge funding by the Swiss National Science Foundation (grant no. PZ00P2_142474). All authors thank Prof. Harald Brune for his kind support.

Notes and references

^aInstitute of Condensed Matter Physics, Ecole Polytechnique Fédérale de Lausanne, CH-1015 Lausanne, Switzerland

^bCondensed Matter Theory, Paul Scherrer Institut, CH-5232 Villigen, Switzerland

^cSwiss Light Source, Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland. Email: christian@waeckerlin.com; jan.dreiser@psi.ch.

†Electronic Supplementary Information (ESI) available: Sample preparation, experimental details of XAS, additional multiplet calculations, magnetic moments of Mn and Eu and sum-rule correction factors, X-ray spectra at 50 K, at 110 K, and on EuO_{1+x}, Brillouin function model. See DOI: 10.1039/c000000x/

- 1 (a) S. Sanvito, *Chem. Soc. Rev.*, 2011, **40**, 3336; (b) V. A. Dediu, L. E. Hueso, I. Bergenti and C. Taliani, *Nat. Mater.*, 2009, **8**, 707–716; (c) C. Barraud, P. Seneor, R. Mattana, S. Fusil, K. Bouzehouane, C. Deranlot, P. Graziosi, L. Hueso, I. Bergenti, V. Dediu, F. Petroff and A. Fert, *Nat. Phys.*, 2010, **6**, 615–620.
- 2 M. Cinchetti, K. Heimer, J.-P. Wüstenberg, O. Andreyev, M. Bauer, S. Lach, C. Ziegler, Y. Gao and M. Aeschlimann, *Nat. Mater.*, 2008, **8**, 115–119.
- 3 (a) A. Schmehl, V. Vaithyanathan, A. Herrnberger, S. Thiel, C. Richter, M. Liberati, T. Heeg, M. Röckerath, L. F. Kourkoutis, S. Mühlbauer, P. Böni, D. A. Muller, Y. Barash, J. Schubert, Y. Idzerda, J. Mannhart and D. G. Schlom, *Nat. Mater.*, 2007, **6**, 882–887; (b) A. Melville, T. Mairoser, A. Schmehl, D. E. Shai, E. J. Monkman, J. W. Harter, T. Heeg, B. Holländer, J. Schubert, K. M. Shen, J. Mannhart and D. G. Schlom, *Appl. Phys. Lett.*, 2012, **100**, 222101.
- 4 (a) N. Jutong, I. Rungger, C. Schuster, U. Eckern, S. Sanvito and U. Schwingenschlögl, *Phys. Rev. B*, 2012, **86**, 205310; (b) T. Santos and J. Moodera, *Phys. Rev. B*, 2004, **69**, 241203.
- 5 (a) A. Scheybal, T. Ramsvik, R. Bertschinger, M. Putero, F. Nolting and T. A. Jung, *Chem. Phys. Lett.*, 2005, **411**, 214–220; (b) H. Wende, M. Bernien, J. Luo, C. Sorg, N. Ponpandian, J. Kurde, J. Miguel, M. Piantek, X. Xu, P. Eckhold, W. Kuch, K. Baberschke, P. M. Panchmatia, B. Sanyal, P. M. Oppeneer and O. Eriksson, *Nat. Mater.*, 2007, **6**, 516–520; (c) M. Bernien, X. Xu, J. Miguel, M. Piantek, P. Eckhold, J. Luo, J. Kurde, W. Kuch, K. Baberschke, H. Wende and P. Srivastava, *Phys. Rev. B*, 2007, **76**, 214406; (d) M. Bernien, J. Miguel, C. Weis, M. E. Ali, J. Kurde, B. Krumme, P. M. Panchmatia, B. Sanyal, M. Piantek, P. Srivastava, K. Baberschke, P. M. Oppeneer, O. Eriksson, W. Kuch and H. Wende, *Phys. Rev. Lett.*, 2009, **102**, 047202; (e) S. Javaid, M. Bowen, S. Boukari, L. Joly, J.-B. Beaufrand, X. Chen, Y. Dappe, F. Scheurer, J.-P. Kappler, J. Arabski, W. Wulfhekkel, M. Alouani and E. Beaurepaire, *Phys. Rev. Lett.*, 2010, **105**, 077201; (f) C. Wäckerlin, K. Tarafder, D. Siewert, J. Girovsky, T. Hählen, C. Iacovita, A. Kleibert, F. Nolting, T. A. Jung, P. M. Oppeneer and N. Ballav, *Chem. Sci.*, 2012, **3**, 3154–3160; (g) J. Brede, N. Atodiresei, S. Kuck, P. Lazić, V. Caciuc, Y. Morikawa, G. Hoffmann, S. Blügel and R. Wiesendanger, *Phys. Rev. Lett.*, 2010, **105**, 047204; (h) C. Wäckerlin, J. Nowakowski, S.-X. Liu, M. Jaggi, D. Siewert, J. Girovsky, A. Shchyrba, T. Hählen, A. Kleibert, P. M. Oppeneer, F. Nolting, S. Decurtins, T. A. Jung and N. Ballav, *Adv. Mater.*, 2013, **25**, 2404–2408; (i) E. Annese, F. Casolari, J. Fujii and G. Rossi, *Phys. Rev. B*, 2013, **87**, 054420; (j) C. F. Hermanns, K. Tarafder, M. Bernien, A. Krüger, Y.-M. Chang, P. M. Oppeneer and W. Kuch, *Adv. Mater.*, 2013, **25**, 3473–3477; (k) J. Dreiser, C. Wäckerlin, M. E. Ali, C. Piamonteze, F. Donati, A. Singha, K. S. Pedersen, S. Rusponi, J. Bendix, P. M. Oppeneer, T. A. Jung and H. Brune, *ACS Nano*, 2014, **5**, 4662.
- 6 J. Klanke, E. Rentschler, K. Medjanik, D. Kutnyakhov, G. Schönhense, S. Krasnikov, I. V. Shvets, S. Schuppler, P. Nagel, M. Merz and H. J. Elmers, *Phys. Rev. Lett.*, 2013, **110**, 137202.
- 7 L. Malavolti, L. Poggini, L. Margheriti, D. Chiappe, P. Graziosi, B. Cortigiani, V. Lanzilotto, F. B. de Mongeot, P. Ohresser, E. Otero, F. Choueikani, P. Sainctavit, I. Bergenti, V. A. Dediu, M. Mannini and R. Sessoli, *Chem. Commun.*, 2013, **49**, 11506.
- 8 (a) T. Santos, J. Moodera, K. Raman, E. Negusse, J. Holroyd, J. Dvorak, M. Liberati, Y. Idzerda and E. Arenholz, *Phys. Rev. Lett.*, 2008, **101**, 147201; (b) E. Arenholz, A. Schmehl, D. G. Schlom and G. van der Laan, *J. Appl. Phys.*, 2009, **105**, 07E101; (c) A. G. Swartz, P. M. Odenthal, Y. Hao, R. S. Ruoff and R. K. Kawakami, *ACS Nano*, 2012, **6**, 10063–10069.
- 9 A. Uldry, F. Vernay and B. Delley, *Phys. Rev. B*, 2012, **85**, 125133.
- 10 E. Negusse, J. Holroyd, M. Liberati, J. Dvorak, Y. U. Idzerda, T. S. Santos, J. S. Moodera and E. Arenholz, *J. Appl. Phys.*, 2006, **99**, 08E507.
- 11 T. Kataoka, Y. Sakamoto, Y. Yamazaki, V. R. Singh, A. Fujimori, Y. Takeda, T. Ohkochi, S.-I. Fujimori, T. Okane, Y. Saitoh, H. Yamagami and A. Tanaka, *Solid State Commun.*, 2012, **152**, 806–809.
- 12 (a) B. Thole, P. Carra, F. Sette and G. van der Laan, *Phys. Rev. Lett.*, 1992, **68**, 1943–1946; (b) P. Carra, B. Thole, M. Altarelli and X. Wang, *Phys. Rev. Lett.*, 1993, **70**, 694–697; (c)
- 13 (a) Y. Teramura, A. Tanaka and T. Jo, *J. Phys. Soc. Jpn.*, 1996, **65**, 1053–1055; (b) C. Piamonteze, P. Miedema and F. M. F. de Groot, *Phys. Rev. B*, 2009, **80**, 184410; (c) S. Stepanow, P. Miedema, A. Mugarza, G. Ceballos, P. Moras, J. Cezar, C. Carbone, F. de Groot and P. Gambardella, *Phys. Rev. B*, 2011, **83**, 220401.
- 14 B. Thole, G. van der Laan, J. Fuggle, G. Sawatzky, R. Karnatak and J.-M. Esteve, *Phys. Rev. B*, 1985, **32**, 5107–5118.
- 15 A. Lodi Rizzini, C. Krull, T. Balashov, J. J. Kavich, A. Mugarza, P. S. Miedema, P. K. Thakur, V. Sessi, S. Klyatskaya, M. Ruben, S. Stepanow and P. Gambardella, *Phys. Rev. Lett.*, 2011, **107**, 177205.
- 16 (a) P. Wachter, in *Handbook on the physics and chemistry of rare earths*, eds. K. A. Gschneidner and L. Eyring, vol. 2, North-Holland, New York, USA, 1979, vol. 2, p. 507; (b) J. P. Liu, F. R. de Boer, P. F. de Châtel, R. Coehoorn and K. H. J. Buschow, *J. Magn. Magn. Mater.*, 1994, **132**, 159–179; (c) X. Wan, J. Dong and S. Y. Savrasov, *Phys. Rev. B*, 2011, **83**, 205201.
- 17 C. Piamonteze, U. Flechsig, S. Rusponi, J. Dreiser, J. Heidler, M. Schmidt, R. Wetter, M. Calvi, T. Schmidt, H. Pruchova, J. Krempasky, C. Quitmann, H. Brune and F. Nolting, *J. Synchrotron Rad.*, 2012, **19**, 661–674.