

ChemComm

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/chemcomm



Journal Name

COMMUNICATION

Substituted ferrocenes and iodine as synergistic thermoelectrochemical heat harvesting redox couples in ionic liquids

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

E.H.B. Anari,^a M. Romano,^b W.X. Teh,^a J.J. Black,^a E. Jiang,^a J. Chen,^b T.Q. To,^a J. Panchompoo^a and L. Aldous^{a*}

Combining ferrocene and iodine results in enhanced thermoelectrochemical (or thermogalvanic) waste heat harvesting abilities, for both the Seebeck coefficient and the overall power output. All systems displayed a mixture of ferrocene, ferrocenium, iodine and triiodide. The observed enhancement correlates with lower electron-density on the ferrocene; the synergistic improvement observed for mixtures of substituted ferrocenes and iodine is attributed to the formation of charge-transfer complexes. Combining dibutanoylferrocene and iodine resulted in the highest Seebeck coefficient of 1.67 mV K⁻¹

Worldwide, heat is converted into electricity on a tremendous scale. The Seebeck effect allows arguably the simplest process, whereby a difference in temperature can be converted directly into electrical power with no moving parts.¹ This simplicity has made it a hallmark energy system of unmanned space exploration.¹ The majority of thermoelectric systems are based upon solid-state semiconductor devices, typically containing rare metalloids such as Bi₂Te₃,² and which suffer from rigidity, expense and low efficiencies.¹

Thermoelectrochemical cells containing a liquid electrolyte with a suitable redox couple can also generate electrical power from a temperature difference. These systems offer many advantages such as flexibility,³ low cost⁴ and are suited to the harvesting of low-grade heat.⁵

The Seebeck coefficient (S_e , Equation 1) expresses the potential difference (ΔE) generated across two electrodes sharing a common electrolyte, as a function of their temperature difference (ΔT).⁶ Dissolved redox couples at different temperatures will have a free-energy difference proportional to the entropy difference between the redox states (ΔS). Unlike in semi-conductors, these liquid, solid or gaseous electrochemical systems give rise to significant S_e values on the order of mV K⁻¹.⁷ This is important, as the

maximum power is directly proportional to the S_e value, and the efficiency of heat conversion is proportional to the S_e squared.⁸

$$S_e = \frac{\Delta E}{\Delta T} = \frac{\Delta S}{nF} \quad (1)$$

The majority of studies into thermoelectrochemical cells have employed aqueous electrolytes containing inorganic redox couples. A prime example is aqueous potassium ferrocyanide/ferricyanide solutions, which exhibit a relatively large S_e on the order of ca. -1.4 mV K⁻¹.^{3, 4} Short-lived systems can exceed this, recently reaching +13.6 mV K⁻¹.⁹ However, the volatility of water can be a major limitation for thermoelectrochemical cells and so ionic liquids (ILs) have been proposed as non-volatile electrolytes for thermoelectrochemical cells.⁵ IL-based thermoelectrochemical cells can be operated at temperatures above 100°C with no degradation, as a result of the high thermal stability and the low (near-zero) vapour pressure of many ILs.^{5a} ILs are known to be highly structured liquids, and entropy is highly significant in many processes in ILs.¹⁰ In 2013 a Co(II)/Co(III) complex reached S_e values of 1.40 to 1.88 mV K⁻¹ in a range of ILs.^{5b}

Despite progress, relying upon the entropy change inherent in a single redox process is clearly self-limiting; to get a great an entropy change generally correlates with lower exchange current densities and necessitates an electrocatalytic material. Electrocatalysis in ILs is a relatively new and poorly understood area.¹¹ In an effort to move beyond this limiting factor, this work investigates combining two redox couples based upon ferrocene and iodine. When employed individually they represent poor thermoelectrochemical redox couples, but together they display a synergistically enhanced performance. This opens new routes to maximising performance by overcoming the limitations noted above.

Both the ferrocene|ferrocenium¹² and iodide|triiodide redox couples find extensive uses in electrochemistry, and have been (separately) well characterised in ILs. Both ferrocenium-based ILs¹⁴ and iodide/triiodide-based ILs¹³ are known. Recently, combining redox couples have been beneficially employed in IL-based dye sensitised solar cells.¹⁵

^a School of Chemistry, UNSW Australia, Sydney, NSW 2052, Australia

^b Intelligent Polymer Research Institute, Innovation Campus, University of Wollongong, Wollongong, NSW 2522, Australia

* Corresponding author; l.alldous@unsw.edu.au

Electronic Supplementary Information (ESI) available: Experimental, raw data and determination of the ferrocene/ferrocenium ratios. See DOI: 10.1039/x0xx00000x

In this work, redox couples were investigated by dissolving individual redox couples (ferrocene|ferrocenium and iodide|triiodide) and also by mixing ferrocene and iodide, which are in equilibrium with their ferrocenium triiodide salt (equation (2)). The reaction between ferrocene and iodide has been the subject of extensive fundamental research relating to equilibrium constants and kinetics,¹⁶ although not in ILs.



In addition to the ferrocenium triiodides being inherently electroactive, the overall equilibrium is also temperature-sensitive. While ferrocenium species rapidly decomposes in oxygenated organic solvents¹⁷, they were found to be stable when dissolved in the ionic liquid 1-ethyl-3-methylimidazolium bis(trifluoromethylsulfonyl)imide ([Emim][NTf₂]), hence all studies were performed in this IL.

Several substituted ferrocenes were synthesised (full details in Supplementary Information). They are ferrocene (**Fc**), acetylferrocene (**AcFc**), ethylferrocene (**EtFc**), dibutylferrocene (**DiBuFc**) and dibutanoylferrocene (**DiBoylFc**).

The Seebeck coefficients (S_e) were measured in a U-shaped assembly (U-cell, full details in the supplementary information) using platinum electrodes. Fig. 1(a) displays the potential difference of 15 mM **Fc**/15 mM **Fc**⁺ (▲), 15 mM **I**⁻/15 mM **I**₃⁻ (●) and 30 mM "[**Fc**]**I**₃" (from 30 mM **Fc** and 45 mM **I**₂, ■) in [Emim][NTf₂], measured as a function of temperature; the corresponding S_e values are summarised in Table 1.

The value measured here for **Fc**|**Fc**⁺ is essentially identical to the value reported by Migita *et al.* (+0.10 ± 0.01 mV K⁻¹).¹⁸ The measured value for **I**⁻|**I**₃⁻ is slightly lower than that reported by Abraham *et al.* (+0.154 mV K⁻¹ in [Emim][NTf₂]^{5a}) although those samples were *ca.* 30 fold more concentrated.

The [**Fc**]**I**₃ system is more complex, and interestingly displayed a non-linear potential vs temperature trend. The [**Fc**]**I**₃ also displayed consistently higher potential values that that of the individual ferrocene and iodine systems. The non-linear trend was present during heating and cooling, displaying no hysteresis, although it is important to note that it took *ca.* 1 h for these values to stabilise.

A maximum potential of *ca.* 24.4 mV was achieved by [**Fc**]**I**₃ at ΔT = 30 K, which equates to an S_e of *ca.* 0.83 mV K⁻¹. Therefore the simple expedient of mixing **Fc**⁰ with **I**₂ results in an S_e value which (at ΔT = 30 K) equates to a 14-fold increase over **I**⁻|**I**₃⁻ alone, and a 5-fold increase over the sum of the

Table 1 Seebeck coefficients for various redox couples, determined from linear ΔE vs. ΔT plots (except *, estimated from ΔE at ΔT = 30 K)

Redox couple in [Emim][NTf ₂]	Seebeck coefficient / mV K ⁻¹ (value from CR2032 casing)
15 mM Fc / 15 mM [Fc] ⁺	0.100 ± 0.002
15 mM I ⁻ / 15 mM [I ₃] ⁻	0.057 ± 0.003
30 mM [Fc] I ₃	0.813* (0.291 ± 0.002)
30 mM [EtFc] I ₃	0.106 ± 0.008
30 mM [DiBuFc] I ₃	0.279 ± 0.006
30 mM [AcFc] I ₃	0.636 ± 0.033
30 mM [DiBoylFc] I ₃	1.669 ± 0.045




Fig. 1 (a) Potential difference recorded as a function of temperature for 15 mM **Fc**/15 mM **Fc**⁺ (●), 15 mM **I**⁻/15 mM **I**₃⁻ (▲) and 30 mM of [**Fc**]**I**₃ (■ in U-tube, □ in battery casing) in [Emim][NTf₂]. Also (b) potential difference for 30 mM of [**Fc**]**I**₃ (□) 30 mM [AcFc]**I**₃ (▼), 30 mM [EtFc]**I**₃ (●), 30 mM [DiBuFc]**I**₃ (★) and 30 mM [DiBoylFc]**I**₃ (◆) in [Emim][NTf₂]. $T_{\text{cold}} = 20^\circ\text{C}$. Error bars are smaller than data points.




Fig. 2: Current-Potential discharge trends, displaying power generated by 30 mM **Fc**/**Fc**⁺ (15 mM of each) (●) and 30 mM [**Fc**]**I**₃ (■) in [Emim][NTf₂] in a Pt-coated CR2032 battery casing at ΔT = 50°C ($T_{\text{cold}} = 30^\circ\text{C}$)

individual **Fc**/**Fc**⁺ and **I**⁻|**I**₃⁻ redox couples, representing a significant synergy when the two are mixed to form [**Fc**]**I**₃. Further increases in temperature resulted in some instability, due to gradual evaporation of the volatile materials from the open U-tube, and at *ca.* 100°C [**Fc**]**I**₃ underwent irreversible decomposition to form iron iodide.

The same systems were investigated in a platinum-coated CR2032 battery casing, which provides 2 mm electrode separation (*cf.* 2 cm in the U-tube) and is more suited for power generation. The hermetically sealed casing also allowed higher temperature differences without any loss of the volatile redox compounds. In this case, the [**Fc**]**I**₃ initial trend matched that of the U-tube but deviated at higher temperatures ($S_e = 0.291 \pm 0.002 \text{ mV K}^{-1}$, hollow symbols in Fig. 1(a)). Nevertheless, the S_e value still displayed the synergy discussed above. The S_e value of **Fc**/**Fc**⁺ was also measured in the battery casing and found to be $0.081 \pm 0.001 \text{ mV K}^{-1}$ (*cf.* $0.100 \pm 0.002 \text{ mV K}^{-1}$ in the U-tube), and all systems gave *ca.*

20% lower Seebeck coefficients in the battery casing. This is predominately due to a temperature drop from the heated exterior to the interior of the cell. In the U-tube (electrodes separated by 2 cm) it took *ca.* 1 h for the potential values to stabilise, whereas in the battery casing (2 mm separation) it took only a few minutes (Figure S3). In the battery casing there is more significant thermal convection, whereas in the U-tube the temperature-induced change in the equilibrium in equation (2) appears to become more significant over time. This mirrors observations in aqueous systems where varying the electrode separation and electrode orientation to gravity can either increase or decrease power according to the precise redox couple utilised.¹⁹

The power discharge characteristics of the systems were also investigated in the battery casing. As demonstrated in Fig. 2, 30 mM $[\text{Fc}][\text{I}_3]$ generated significantly more power than 30 mM $\text{Fc}|\text{Fc}^+$, largely due to the higher S_e value of the former. The precise charge carrier(s) involved in the $[\text{Fc}][\text{I}_3]$ system is currently unknown. The power also refers to the steady-state conditions obtained after 10 min discharge. Given their differing diffusion coefficients^{12,13} and the possibility for both species to undergo Grotthuss-like conductivity, further work is required to investigate what happens to these systems under extended discharge conditions.

While the temperature-dependant equilibrium in the ferrocenium triiodide salt clearly has some influence, it does not explain the observed synergy resulting in the S_e increases. To investigate further, the ferrocene core was systematically altered by adding electron-donating (alkyl) or electron-withdrawing (alkanoyl) groups. Fig. 1(b) displays the potential differences measured for 45 mM I_2 and 30 mM of Fc (\square), AcFc (\blacktriangledown), EtFc (\bullet), DiBuFc (\star) and DiBoylFc (\blacklozenge) in $[\text{Emim}][\text{NTf}_2]$. Table 1 lists the S_e values of all redox couple species studied in this work, and it was found that 30 mM “ $[\text{DiBoylFc}][\text{I}_3]$ ” possesses the highest S_e value of $1.67 \pm 0.05 \text{ mV K}^{-1}$.

The trend in S_e values follows the order $\text{DiBoylFc} > \text{AcFc} > \text{Fc} > \text{DiBuFc} > \text{EtFc}$, which follows the anticipated electron density on the ferrocene centre from lowest to highest. The




Fig. 3: CVs recorded for 15 mM DiBoylFc , 22.5 mM I_2 , the additive sum of these two scans, and 15 mM $[\text{DiBoylFc}][\text{I}_3]$. Scans recorded at a 1.6 mm Pt electrode, 293 K, 50 mV s^{-1} , and corrected to the $\text{Fc}|\text{Fc}^+$ formal potential.

inversion of DiBuFc and EtFc is an exception to this trend, and is likely due to a subtle contribution from the alkyl chains to the overall entropy change.

In organic solvents, electron-donating groups on the ferrocene moiety (*e.g.* alkyl groups) shifts the equilibrium in equation (2) towards the right, resulting in more triiodide product formed.^{16a,16b} This was investigated in $[\text{Emim}][\text{NTf}_2]$ by cyclic voltammetry (CV), and the oxidation potentials of the substituted ferrocenes followed the expected trend in the CV (Fig. S5). Comparison of the potentials relative to those of $\text{Fc}|\text{Fc}^+ / [\text{I}_3]^-$ (Fig. S6) and use of the Nernst equation allows us to estimate (see Supplementary Information for full discussion) that a 2:3 mixture of DiBuFc and I_2 should exist as 99.9% $[\text{DiBuFc}][\text{I}_3]$ (at 298 K); for DiBoylFc only *ca.* 10% exists as $[\text{DiBoylFc}][\text{I}_3]$. However, when ferrocene and iodine were investigated in the same system the situation was more complex. Fig. 3 displays CVs of 15 mM DiBoylFc , 22.5 mM I_2 and 15 mM $[\text{DiBoylFc}][\text{I}_3]$; similar data for $[\text{Fc}][\text{I}_3]$ and $[\text{DiBuFc}][\text{I}_3]$ are included in the Supplementary Information. When mixed, the $\text{I}^- / [\text{I}_3]^-$ feature displayed a *ca.* 50 mV anodic shift, the $[\text{I}_3]^- / \text{I}_2$ process was unchanged, while the $\text{DiBoylFc}^+ / [\text{DiBoylFc}]$ peaks shifted *ca.* 50 mV cathodically. Additionally, the currents for the mixed ferrocenium triiodide systems were higher than expected, demonstrating some ‘nonadditivity’ of faradaic currents; this has been previously noted when ferrocene is mixed with cobaltocenium in ionic liquids.²⁰

Further demonstration of this non-linear behaviour was obtained by UV-Vis spectroscopy. Ferrocene-iodine charge transfer complexes are known in non-aqueous solvents,^{16a} and the extinction coefficient of I_2 and $[\text{I}_3]^-$ are extremely structure- and solvation-sensitive.²¹ Fig. 4(a) displays the titration of I_2 with I^- (introduced as $[\text{Emim}]\text{I}$), yielding the characteristic absorption bands.^{16d,22} Stoichiometric quantities of I_2 and I^- resulted in quantitative formation of $[\text{I}_3]^-$, as represented by the absorption maxima. Fig. 4(b) displays the same spectra of I_2 and I_2 / I^- , overlaid with the spectra for $\text{Fc} / [\text{Fc}][\text{PF}_6]$ and all the “ferrocenium triiodide” salts (as 3 mM ferrocene and 4.5 mM I_2). All five ferrocene/iodine mixtures should have an




Fig. 4: UV-Vis absorption spectra of (a) 3 mM I_2 in presence of various $[\text{Emim}]\text{I}$ concentrations, and (b) 3 mM I_2 , 3 mM $\text{Fc} / 3 \text{ mM } \text{Fc}^+$, 3 mM $\text{I}^- / 3 \text{ mM } [\text{I}_3]^-$ (---) as well as 3 mM of the [ferrocenium][I_3] samples. All in $[\text{Emim}][\text{NTf}_2]$. Pathlength 1 mm.

absorbance below that of 3 mM $[I_3]^-$, as they will introduce 3 mM $[I_3]^-$ or less, based upon the equilibrium in equation (2). As the absorbance of the ferrocenium triiodides exceed this in every case, the solvation environment of $[I_3]^-$ in the IL is clearly altered upon introduction of ferrocene species.

An interaction between ferrocene and iodine species will result in an additional entropic change upon a redox process occurring, relative to the individual species. These significant interactions can therefore explain the synergistic enhancement apparent in the S_e coefficient. It is logical that the electron-deficient ferrocenes would display more significant charge-transfer complexation with the electron-rich and highly polarisable iodine species. This increased interaction mirrors the observed synergistic enhancement in the S_e coefficient, with **DiBoylFc** predicted to interact with iodine the most and also displaying the highest S_e coefficient of 1.67 mV K^{-1} . This S_e coefficient compares favourably with the highest S_e value ever reported in the IL [Emim][NTf₂], which was *ca.* $1.66 \pm 0.02 \text{ mV}\cdot\text{K}^{-1}$ for 100 mM $[\text{Co}^{\text{II/III}}[\text{bpy}]_3][\text{NTf}_2]_{2/3}$.^{5b} The reported $[\text{Co}^{\text{II/III}}[\text{bpy}]_3][\text{NTf}_2]_{2/3}$ was deliberately chosen to result in the most significant entropy change upon changing oxidation state, with purely the cationic component contributing. In the case of the ferrocenium triiodides, we have demonstrated that two common, widely available, relatively poor thermoelectrochemical redox mediators (by conventional knowledge and approaches) can be combined to result in an excellent system when combined.

In conclusion, this work has investigated the thermoelectrochemistry of mixed redox couples (ferrocene and iodine) for the first time. These two couples were found to interact even in dilute solution, resulting in a synergistic thermoelectrochemical response. This likely stems from observed charge-transfer complex formation, which must introduce additional entropic changes when one component undergoes a redox process, additional to simple restructuring of the surrounding ionic liquid. This work therefore represents a new approach towards the development of thermoelectrochemical systems, with the value of 1.67 mV K^{-1} for **[DiBoylFc][I₃]** being one of the highest reported S_e value for a solute in the ionic liquid [Emim][NTf₂].

Notes and references

The Australian Research Council (ARC DECRA DE130100770) is acknowledged for funding.

- 1 C. B. Vining, *Nat. Mat.*, 2009, **8**, 83-85.
- 2 D. M. Rowe, *Thermoelectrics handbook : macro to nano*, CRC/Taylor & Francis, Boca Raton, 2006.
- 3 M. S. Romano, N. Li, D. Antiohos, J. M. Razal, A. Nattestad, S. Beirne, S. Fang, Y. Chen, R. Jalili, G. G. Wallace, R. Baughman and J. Chen, *Adv. Mat.*, 2013, **25**, 6602-6606.
- 4 R. Hu, B. A. Cola, N. Haram, J. N. Barisci, S. Lee, S. Stoughton, G. Wallace, C. Too, M. Thomas, A. Gestos, M. E. Cruz, J. P. Ferraris, A. A. Zakhidov and R. H. Baughman, *Nano Lett.*, 2010, **10**, 838-846.
- 5 For example; (a) T. J. Abraham, D. R. MacFarlane and J. M. Pringle, *Chem. Comm.*, 2011, **47**, 6260-6262; (b) T. J. Abraham, D. R. MacFarlane and J. M. Pringle, *Energy Environ. Sci.*, 2013, **6**, 2639-2645; (c) V. Vinovyeva, S. Nakamae, M. Bonetti and M.

- 6 Roger, *ChemElectroChem*, 2014, **1**, 426-430; (d) M. Bonetti, S. Nakamae, B. T. Huang, T. J. Salez, C. Wiertel-Gasquet and M. Roger, *J. Chem. Phys.*, 2015, **142**, 244708.
- 7 T. I. Quickenden and Y. Mua, *J. Electrochem. Soc.*, 1995, **142**, 3985-3994.
- 8 A. Gunawan, C. H. Lin, D. A. Buttry, V. Mujica, R. A. Taylor, R. S. Prasher and P. E. Phelan, *Nanoscale Microsc. Therm.*, 2013, **17**, 304-323.
- 9 B. Burrows, *J. Electrochem. Soc.*, 1976, **123**, 154-159.
- 10 H. A. H. Alzahrani, J. J. Black, D. Goonetilleke, J. Panchompoo and L. Aldous, *Electrochem. Comm.*, 2015, **58**, 76-79.
- 11 H. M. Yau, A. K. Croft and J. B. Harper, *Farad. Discuss.*, 2012, **154**, 365-371.
- 12 L. Aldous, A. Khan, M. M. Hossain and C. Zhao, in *Catalysis in Ionic Liquids: From Catalyst Synthesis to Application*, The Royal Society of Chemistry, 2014, 433-473.
- 13 (a) E. I. Rogers, D. S. Silvester, D. L. Poole, L. Aldous, C. Hardacre and R. G. Compton, *J. Phys. Chem. C*, 2008, **112**, 2729-2735; (b) C. P. Fu, L. Aldous, E. J. F. Dickinson, N. S. A. Manan and R. G. Compton, *ChemPhysChem*, 2011, **12**, 1708-1713; (c) C. P. Fu, L. Aldous, E. J. F. Dickinson, N. S. A. Manan and R. G. Compton, *Chem. Comm.*, 2011, **47**, 7083-7085; (d) C. P. Fu, L. Aldous, E. J. F. Dickinson, N. S. A. Manan and R. G. Compton, *New J. Chem.*, 2012, **36**, 774-780.
- 14 (a) E. I. Rogers, D. S. Silvester, L. Aldous, C. Hardacre and R. G. Compton, *J. Phys. Chem. C*, 2008, **112**, 6551-6557; (b) E. I. Rogers, I. Streeter, L. Aldous, C. Hardacre and R. G. Compton, *J. Phys. Chem. C*, 2008, **112**, 10976-10981.
- 15 For example; (a) B. Gélinas, J. C. Forgie, and D. Rochefort, *J. Electrochem. Soc.*, 2014, **161**, H161-H165; (b) B. Gélinas and D. Rochefort, *Electrochim. Acta*, 2015, **162**, 36-44; (c) Y. Funasako, T. Mochida, T. Inagaki, T. Sakurai, H. Ohta, K. Furukawa and S. Nakamura, *Chem. Comm.*, 2011, **47**, 4475-4477; (d) T. Inagaki and T. Mochida, *Chem. Lett.*, 2010, **39**, 572-573.
- 16 C.-T. Li, C.-P. Lee, C.-T. Lee, S.-R. Li, S.-S. Sun and K.-C. Ho, *ChemSusChem*, 2015, **8**, 1244-1253.
- 17 (a) H. Grimes and S. R. Logan, *Inorg. Chim. Acta*, 1980, **45**, L22-L24; (b) S. R. Logan and M. R. Welsh, *Z. Phys. Chem.*, 1986, **148**, 215-220; (c) S. R. Logan and M. R. Welsh, *J. Chem. Soc., Faraday Trans. 1*, 1988, **84**, 1259-1265; (d) H. M. A. Salman, M. K. Mahmoud, M. H. M. Abou-El-Wafa, U. M. Rabie and R. H. Crabtree, *Inorg. Chem. Comm.*, 2004, **7**, 1209-1212; (e) J. R. P. Hanna and S. R. Logan, *J. Photochem.*, 1979, **10**, 267-271; (f) W. Neuse and M. S. Loonat, *J. Organomet. Chem.*, 1985, **281**, 329-341.
- 18 J. P. Hurvois and C. Moinet, *J. Organomet. Chem.*, 2005, **691**, 1829-1839.
- 19 T. Migita, N. Tachikawa, Y. Katayama and T. Miura, *Electrochemistry*, 2009, **77**, 639-641.
- 20 A. Gunawan, H. C. Li, C. H. Lin, D. A. Buttry, V. Mujica, R. A. Taylor, R. S. Prasher and P. E. Phelan, *Int. J. Heat Mass Trans.*, 2014, **78**, 423-434.
- 21 M. J. A. Shiddiky, A. A. J. Torriero, C. Zhao, I. Burgar, G. Kennedy and A. M. Bond, *J. Am. Chem. Soc.*, 2009, **131**, 7976-7989.
- 22 K. Kaya, N. Mikami, Y. Udagawa and M. Ito, *Chem. Phys. Lett.*, 1972, **16**, 151-153.
- 23 R. E. Rundle, J. F. Foster and R. R. Baldwin, *J. Am. Chem. Soc.*, 1944, **66**, 2116-2120.