

# Green Chemistry

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

*Accepted Manuscripts* are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



## Efficient Catalytic hydrotreatment of Kraft Lignin to Alkylphenolics using Supported NiW and NiMo Catalysts in Supercritical Methanol

Received 00th January 20xx,  
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

Anand Narani<sup>a</sup>, Ramesh Kumar Chowdari<sup>b</sup>, Catia Cannilla<sup>c</sup>, Giuseppe Bonura<sup>c</sup>, Francesco Frusteri<sup>c</sup>, Hero Jan Heeres<sup>\*.b</sup> and Katalin Barta<sup>\*a</sup>

Efficient catalytic hydrotreatment of Kraft lignin to aromatic monomers was demonstrated in supercritical methanol using a variety of NiW and NiMo catalyst on acidic, basic and neutral supports. It was found that NiW catalysts on neutral or basic supports are highly suitable for depolymerization of Kraft lignin to methanol soluble organics in high yields at 320 °C and 35 bar H<sub>2</sub> pressure. Extensive analysis of the product mixtures was carried out using GC-MS-FID, GC×GC-FID, 2D HSQC NMR, GPC and elemental analysis, and several techniques were used for the characterization of the prepared catalysts in order to determine acidity and basicity of the support and morphological changes after catalytic reaction. The best results were obtained with sulphided NiW catalyst supported on activated carbon. Efficient depolymerization of Kraft lignin and a total 28 wt% monomer yield was obtained within 8 h and 76% of the products were alkylphenolics and guaiacolics. Over prolonged reaction times, the total monomer yield reached 35 wt%, containing up to 26 wt% alkylphenolics. During catalytic processing, deoxygenation was the most prevalent reaction and, importantly, no competing aromatic ring hydrogenation or undesired repolymerization to insoluble char was observed. The catalytic system described here represents a highly efficient and selective method for the production of alkylphenolics and guaiacolics from Kraft lignin.

### 1 Introduction

Kraft lignin comprises the majority of the total worldwide lignin production, which currently accounts for over 50 million tons per annum.<sup>1-3</sup> However only a very few examples exist for the use of Kraft lignin as raw material for the production of value added chemicals.<sup>4,5</sup> More than 90% of lignin is treated as a low value fuel and burned to provide heat during paper processing, because there is lack in better methods for its utilization. Therefore the development of new catalytic technologies for more efficient conversion of Kraft lignin to aromatics is of crucial importance, as it would largely contribute to the sustainable use of the sizeable amount of waste streams.<sup>6-10</sup>

Kraft lignins are obtained through the sulphide pulping process, and typically contain 1-3% sulphur in both inorganic as well as organically bound form.<sup>11,12</sup> Moreover, due to the extensive pulping, the structure of Kraft lignins is more condensed, and contains a higher amount of C-C bonds compared to other types of lignins.<sup>13-16</sup> From this follows, that Kraft lignin is a particularly challenging substrate for catalytic processing, especially with noble metal catalysts which are frequently poisoned by sulphur.<sup>3,4,7,8,17</sup>

Over the past decade, significant advances have been made in the development of new processes for the depolymerization of lignin. Most of these methods typically targeted organosolv lignins and ranged from thermal or hydrothermal depolymerization<sup>18-21</sup> to

milder oxidative or reductive methods<sup>22-24</sup> most of which have been extensively reviewed.<sup>4,7,8,17,18,25-28</sup> Among the developed methods, reductive approaches have received particular attention, since they enable the direct hydrogenolysis of the most prevalent β-O-4 lignin linkage.<sup>29-33</sup> Alternatively, protic solvents such as methanol,<sup>34</sup> ethanol,<sup>35-37</sup> isopropanol,<sup>38</sup> formic acid,<sup>39-42</sup> or water/alcohol mixtures<sup>43,44</sup> could serve as hydrogen donor for the various depolymerization and deoxygenation processes. Furthermore, water has proven as suitable reaction medium.<sup>45,46</sup>

Methods that specifically target Kraft lignin have also been described. For instance, Miller *et al.* described the efficient depolymerization of Kraft and organosolv lignin in supercritical methanol and ethanol in the presence of KOH.<sup>47</sup> In similar work, Shabtai described two step depolymerization of lignin in the presence of base.<sup>48</sup> Weckhuysen and co-workers reported a two-step process for the conversion of various lignins, including Kraft to aromatic compounds (<12 wt% yield) during which lignin was depolymerized using a Pt/γ-Al<sub>2</sub>O<sub>3</sub> catalyst in alkaline ethanol/water medium and the obtained bio-oil was subsequently deoxygenated with CoMo/Al<sub>2</sub>O<sub>3</sub> and Mo<sub>2</sub>C/CNF catalysts.<sup>49</sup> In another process, Kraft lignin was depolymerized using formic acid as a hydrogen source in water/ethanol medium without any catalyst.<sup>50</sup>

A recent work by Ma *et al.* reported that high yields (61.3 wt%) of aromatic compounds can be obtained from Kraft lignin in supercritical ethanol over MoC<sub>1-x</sub>/AC catalysts.<sup>51</sup> In this system ethanol acted as hydrogen source, but was also found to incorporate into the formed products by alkylation reactions. Side reactions of the solvent alone resulting in aliphatic products also occurred. Nonetheless this important work pointed at the suitability of molybdenum as active metal in Kraft lignin depolymerization. More recently, a one-pot complete catalytic conversion of Kraft lignin into C6-C10 chemicals, was reported in ethanol, using Mo-based catalysts.<sup>52</sup>

The depolymerization of Kraft lignin is a challenging task due to the highly condensed structure of the substrate as well as its relatively high sulphur content, which may lead to catalyst deactivation.<sup>4,12</sup> Therefore the selection of the catalyst should take

<sup>a</sup> Stratingh Institute for Chemistry, Faculty of Mathematics and Natural Science, University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands.


<sup>b</sup> Chemical Engineering Department, Faculty of Mathematics and Natural Science, University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands.

<sup>c</sup> CNR-ITAE, Istituto di Tecnologie Avanzate per l'Energia "Nicola Giordano" Via S. Lucia sopra Contesse 5, 98126 Messina, Italy. E-mail: [k.barta@rua.nl](mailto:k.barta@rua.nl), [h.j.heeres@rug.nl](mailto:h.j.heeres@rug.nl), Tel: +31(0)503634174

† Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

into account the high sulphur content of the lignin source. It is well known that NiMo and CoMo catalysts are tolerant towards sulphur and are widely used in the hydrodeoxygenation of aromatic compounds to simpler aromatics or hydrocarbons.<sup>53,54</sup> They have recently been reported as suitable catalysts for the hydrodeoxygenation of lignin model compounds,<sup>55</sup> and for lignin as discussed above.

Here we report the highly efficient catalytic hydrotreatment of Kraft lignin to value added low molecular weight aromatics, specifically alkylphenolics and guaiacolics in supercritical methanol in the presence of hydrogen. A variety of supported Mo and W, catalyst promoted by Ni and Co, on various supports have been tested and best composition identified. Under optimal reaction conditions, the main products are alkylphenolics and gratifyingly no ring hydrogenation or char formation takes place. The catalyst is thoroughly characterized before and after reaction.



**Scheme 1** Procedure developed for the fractionation of the crude product mixture obtained after catalytic treatment of Kraft lignin.

## 2 Experimental Section

### 2.1 Materials

$\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  (99%),  $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  (>99%),  $\text{Ce}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$  (99.5%), KOH (85%) were purchased from Acros Organics,  $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  (98%),  $\text{La}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$  (>99%),  $(\text{NH}_4)_6\text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$ ,  $(\text{NH}_4)_6\text{H}_2\text{W}_{12}\text{O}_{40} \cdot \text{H}_2\text{O}$  (>99%),  $\text{ZrO}(\text{NO}_3)_2 \cdot x\text{H}_2\text{O}$ , Dimethyldisulphide (DMDS),  $\text{K}_2\text{CO}_3$  (>99%), were purchased from Sigma-Aldrich. Indulin-AT (Kraft lignin) was from MWV specialty chemicals and was kindly provided by Dr. R. Gosselink from the Wageningen University and Research Centre, The Netherlands. Indulin-AT is a purified form of Kraft pine lignin, which is free of hemicellulosic material. The lignin content is 97 wt% on dry basis. Elemental analysis of this lignin is as follows: 61.1 % of carbon, 5.6 % of hydrogen, 1.6 % sulphur and 30.6 % of oxygen. Methanol (anhydrous) was purchased from Macron fine chemicals, Activated Charcoal (AC) was purchased from Merck Millipore, and Ammonium-ZSM-5 (50:1 ratio of Si/Al) was purchased from Alfa-Aesar.

### 2.2 Preparation of the catalysts

Apart from the directly purchased supports (i.e., activated charcoal and ammonium-ZSM-5), three different mixed oxides were used as catalyst supports and prepared by co-precipitation methods in accordance with literature procedures.<sup>56</sup> The support  $\text{MgO-La}_2\text{O}_3$  (ML) with an atomic ratio of Mg/La of 3 was prepared by co-precipitation method. In a typical procedure, required amounts of  $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  (0.39 mol) and  $\text{La}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$  (0.13 mol) were dissolved in 0.5 L of deionized water and precipitated with mixture of  $\text{K}_2\text{CO}_3$  (0.25M) and KOH (1M) in 0.52 L of deionized water at constant  $\text{p}^{\text{H}}$  of 10. After complete precipitation, the solid was filtered and thoroughly washed with water to reach neutral  $\text{p}^{\text{H}}$ . The resultant solid was oven dried at 120 °C for 12 h and finally calcined at 650 °C for 5 h. The  $\text{MgO-CeO}_2$  (MC) and  $\text{MgO-ZrO}_2$  (MZ) supports were prepared by similar procedures and calcined at 500 °C for 5 h ( $\text{MgO-CeO}_2$ ) and 650 °C for 4 h ( $\text{MgO-ZrO}_2$ ).

The catalysts NiO- $\text{MoO}_3/\text{AC}$  (NiMo/AC), CoO- $\text{MoO}_3/\text{AC}$  (CoMo/AC) and NiO- $\text{WO}_3/\text{AC}$  (NiW/AC) with 5 wt% of NiO or CoO and 15wt% of  $\text{WO}_3$  or  $\text{MoO}_3$  were deposited on activated carbon by impregnation of about 3-4 mL of aqueous solutions of  $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  or  $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  and  $(\text{NH}_4)_6\text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$  or  $(\text{NH}_4)_6\text{H}_2\text{W}_{12}\text{O}_{40} \cdot \text{H}_2\text{O}$  followed by evaporation to dryness at 100 °C for 12 h and calcination in  $\text{N}_2$  atmosphere at 450 °C for 5 h. In a similar method 5 wt% NiO-15 wt%  $\text{MoO}_3$ , 5 wt% CoO-15 wt%  $\text{MoO}_3$  as well as 5 wt% NiO-15 wt%  $\text{WO}_3$  on different supports were prepared.

Sulphided catalysts were generated *in-situ* by the addition of dimethyldisulphide (DMDS) to the reaction mixture at the start of the reaction.<sup>57</sup> (For the detailed pathways related to *in-situ* preparation of the catalysts see supporting information, appendix A) The sulphided NiW supported on AC, ZSM-5,  $\text{MgO-La}_2\text{O}_3$ ,  $\text{MgO-CeO}_2$ ,  $\text{MgO-ZrO}_2$  catalysts are designated as S-NiW/AC, S-NiW/ZSM-5, S-NiW/ML, S-NiW/MC, S-NiW/MZ respectively. Similarly, sulphided Ni, W, NiMo, CoMo supported on AC catalysts are abbreviated as S-Ni/AC, S-W/AC, S-NiMo/AC and S-CoMo/AC. For more detailed information of catalyst characterization techniques see Supporting Information, appendix B

### 2.3 Catalytic hydrotreatment of Kraft lignin and product analysis

The catalytic hydrotreatment of Kraft lignin was carried out in 100 ml high pressure Parr autoclave with an overhead stirrer. Typically, the autoclave was charged with 0.25 g respective catalyst, 1 g of Kraft lignin, 0.1 g of dimethyl-disulphide and 30 ml of methanol. The reactor was sealed and purged with nitrogen for several times and then pressurised with 35 bar  $\text{H}_2$  at room temperature. The reactor was heated to 320 °C for a predetermined amount of time, and stirred at 800 rpm. After reaction, the reactor was cooled to room temperature and the gas was collected in a Tedlar gas-bag. The reactor was washed with several portions of methanol to allow quantitative transfer of the reactor content, which was subjected to a general workup procedure (Scheme 1). In the first step, the solid residues were filtered and the solvent was removed by rotary evaporation. The resultant oily product (named methanol soluble oil) was further characterized. The remaining solids were washed with dichloromethane (DCM). The solids extracted in this way (DCM soluble products) were obtained after evaporation of the solvent. The remaining solid residue contained the catalyst, small amounts of unconverted lignin and char. These solids were further washed with dimethylsulfoxide (DMSO) to remove the unconverted lignin.

Methanol soluble oils were analysed by GC-MS-FID analyses using a Quadruple Hewlett Packard 6890 MSD attached to a Hewlett Packard 5890 GC equipped with a 60 m × 0.25 mm i.d. and a 0.25  $\mu\text{m}$  sol-gel capillary column. The injector temperature was set at 250 °C. The oven temperature was kept at 40 °C for 5 minutes then heated up to 250 °C at a rate of 3 °C  $\text{min}^{-1}$  and then held at 250 °C for 10 minutes.

**Table 1** Composition of the products obtained by catalytic hydrotreatment of Kraft lignin using various hydrodeoxygenation catalysts.

Entry	Catalyst	Methanol soluble oil (wt%)	DCM soluble solids (wt%)	DMSO soluble solids (wt%)	Char (wt%)	Mass balance (wt%)
1	Blank	15	8	20	30	73
2	S-NiMo/AC <sup>a</sup>	22	10	8	30	70
3	S-NiMo/AC	57	10	8	trace	75
4	S-CoMo/AC	41	6	10	9	66
5	NiWO <sub>x</sub> /AC	62	14	8	8	92
6	S-W/AC	45	2	30	5	82
7	S-Ni/AC	70	5	7	0	82
8	S-NiW/AC	82	10	trace	0	92
9	S-NiW/ZSM-5	40	3	13	30	86
10	S-NiW/ML	80	9	trace	0	89
11	S-NiW/MC	75	11	9	0	95
12	S-NiW/MZ	68	6	12	4	90
13	S-NiW/AC <sup>b</sup>	60	20	15	0	95
14	S-NiW/ML <sup>b</sup>	60	22	16	0	98

Reaction conditions: catalyst (0.25 g), Kraft lignin (1 g), methanol (30 ml), H<sub>2</sub> (35 bar), temperature (320 °C), 8 h.

<sup>a</sup> without hydrogen added, <sup>b</sup> with 2 g of Kraft lignin

GC×GC-FID analysis was performed on organic samples with a trace GC×GC from Interscience equipped with a cryogenic trap system and two columns: a 30 m × 0.25 mm i.d. and a 0.25 μm film of RTX-1701 capillary column connected by a meltfit to a 120 cm × 0.15 mm i.d. and a 0.15 μm film Rxi-5Sil MS column. An FID detector was used. A dual jet modulator was applied using carbon dioxide to trap the samples. Helium was used as the carrier gas (continuous flow 0.6 ml min<sup>-1</sup>). The injector temperature and FID temperature were set at 250 °C. The oven temperature was kept at 40 °C for 5 minutes then heated up to 250 °C at a rate of 3 °C min<sup>-1</sup>. The pressure was set at 70 kPa at 40 °C. The modulation time was 6 s.

For GC×GC-FID and GC-MS-FID analyses, the samples were diluted with tetrahydrofuran (THF) and 500 ppm di-n-butyl ether (DBE) was added as an internal standard. For more detailed information see Supporting Information, appendix C.

Gel Permeation Chromatography (GPC) analyses of the samples were performed using a HP1100 equipped with three 300 × 7.5 mm PL gel 3 μm MIXED-E columns in series using a GBC LC 1240 RI detector. Average molecular weight calculations were performed using the PSS WinGPC Unity software from Polymer Standards Service. The following conditions were used: THF as the eluent at a flow rate of 1 ml min<sup>-1</sup>; 140 bar, a column temperature of 40 °C, 20 μl injection volume and a 10 mg ml<sup>-1</sup> sample concentration. Toluene was used as a flow marker.

The gas phases were collected after reaction and stored in a gas bag (SKC Tedlar 3 L sample bag [9.5"×10"]) with a polypropylene septum fitting. GC-TCD analyses were performed using a Hewlett Packard 5890 Series II GC equipped with a Porablot Q Al<sub>2</sub>O<sub>3</sub>/Na<sub>2</sub>SO<sub>4</sub> column and a molecular sieve (5 A) column. The injector temperature was set at 150 °C and the detector temperature at 90 °C. The oven temperature was kept at 40 °C for 2 minutes then heated up to 90 °C at 20 °C min<sup>-1</sup> and kept at this temperature for 2 minutes. A reference gas was used to identify the peaks by retention time and to quantify the products (Gas product mixture: 55.19% H<sub>2</sub>,

19.70% CH<sub>4</sub>, 3.00% CO, 18.10% CO<sub>2</sub>, 0.51% ethylene, 1.49% ethane, 0.51% propylene and 1.5% propane).

NMR spectra were acquired at 25 °C using an Agilent 400 MHz spectrometer. Approximately 50 mg of methanol soluble oil was dissolved in 0.7 ml dimethylsulfoxide-d<sub>6</sub> (DMSO). For analysis of the Kraft lignin, approximately 100 mg was dissolved in 0.7 ml dimethylsulfoxide-d<sub>6</sub> (DMSO). <sup>1</sup>H-<sup>13</sup>C HSQC spectra were acquired using a standard pulse sequence HSQC programme with spectral width of 160 ppm, 16 scans, 128 increments (256 increments for Kraft lignin), on F1 dimension and data were processed using the MestReNova software.

Elemental analyses (C, H, N and S) were performed using a Euro Vector 3400 CHN-S analyzer. The oxygen content was determined by difference.

### 3 Results and discussion

Inspired by previous reports<sup>36,37,49-52</sup> as well as our own experiences regarding the catalytic conversion of various lignocellulose sources,<sup>58-60</sup> we anticipated that supercritical methanol (at 300-320 °C) in the presence of a hydrotreatment catalysts and hydrogen, would be a suitable reaction medium for the depolymerisation of Kraft lignin to aromatic monomers. These aromatic fragments would undergo further deoxygenation towards simpler aromatics, such as alkylphenolics, over the various hydrotreatment catalysts.<sup>53,55</sup> Thus, a systematic study was conducted using various hydrodeoxygenation catalysts (Ni, Co promoted with Mo or W) on various supports.

#### 3.1 Catalyst screening and fractionation of products

A series of supported NiMo, CoMo and NiW catalysts on acidic (ZSM-5), neutral (activated carbon) or basic (various MgO/lanthanide oxide combinations) supports were prepared. The nature of the acidic and basic sites was confirmed by TPD

measurements (discussed below). The corresponding BET areas as well as pore size parameters are shown in Table S1, Fig. S1 and Fig. S2.

These catalysts were tested in the depolymerization of Kraft lignin at 320 °C, 35 bar H<sub>2</sub> for 8 h in supercritical methanol and dimethylsulphide was used as a sulphur source. The reaction products were fractionated by the developed procedure (see Scheme 1 in the Experimental section). This consisted of a separate treatment of reaction solids followed by quantification of the amount of methanol soluble material, a crucial parameter and indication for the activity of the respective catalysts (for calculation of the main parameters determined, see Appendix D in Supporting Information). Gel Permeation Chromatography measurements confirmed that the methanol soluble oil mainly consists of aromatic monomers and oligomers of lower molecular weight ranges (see Supporting Information, Table S2, Fig. S3-a). The DCM soluble solids were identified as higher molecular weight materials (see Supporting Information, Table S2, Fig. S3-b). The brown DMSO soluble fraction was believed to be unreacted lignin, however due to its low solubility in THF, its molecular weight could not be determined accurately. The rest of the solids were visually assessed to be a mixture of char and catalyst.

The catalyst screening was conducted at 320 °C and 35 bar of H<sub>2</sub> using the prepared catalysts in order to determine the most suitable composition and support for maximizing the yield of methanol soluble products. First, simply heating Kraft lignin without a catalyst and hydrogen resulted in only 15 wt% of methanol soluble oil and 30 wt% of insoluble char (Table 1, entry 1). When S-NiMo on activated carbon without external hydrogen was tested, the results were comparable to a blank experiment with only 22 wt% of methanol soluble oil yields and more substantial (30 wt%) amount of char obtained (Table 1, entry 2). The same catalyst (S-NiMo/AC) with external hydrogen delivered a promising 57 wt% of methanol soluble oil yield and only traces of char (Table 1, entry 3). These findings indicate that the presence of external hydrogen is important, as it likely reduces the extent of recondensation reactions and/or enhances the rate of lignin depolymerisation reactions. In addition, unlike during our previous studies with CuPMO (Cu doped Mg-Al porous metal oxide) in supercritical methanol, where methanol reforming was the only source of hydrogen,<sup>60</sup> the NiMo catalysts required external hydrogen that played a key role in affecting lignin depolymerization, as no significant methanol reforming was observed in the present case, as expected. For a related catalyst, comprising of Co instead of Ni, (S-CoMo/AC) only 41 wt% of methanol soluble oil yield and 9 wt% of char was obtained (Table 1, entry 4). This is likely due to increase in acidity of the catalyst when Ni was replaced with Co (Table 2, entry 2). This indicates that Ni promoted Mo is more active than Co promoted Mo for lignin depolymerization. Subsequently, when Mo was replaced with W (i.e., S-NiW/AC), the acidity of the catalyst further decreased (Table 2, entry 1), which effects on the methanol soluble oil yield increased to 82 wt% without any char formation (Table 1, entry 8), representing the best product yield among the screened catalysts. As a comparison, the methanol soluble oil yields dropped to 62 wt% and 8 wt% of char (Table 1, entry 5) obtained with the non sulphided NiW/AC catalyst. Thus, the sulphided catalyst was clearly more active. Further studies confirmed that the sulphided Ni promoted W catalysts are more active than the corresponding non-sulphided NiW/AC and S-NiMo/AC catalysts or Ni/AC and S-W/AC catalysts alone (Table 1, entries 5, 1, 6, 7).


Once established that a bimetallic Ni/W catalysts is the best regarding product yield, we have subsequently investigated whether the support also plays a significant role. To this end, NiW catalysts supported on basic MgO-La<sub>2</sub>O<sub>3</sub> (ML), MgO-CeO<sub>2</sub> (MC), MgO-ZrO<sub>2</sub> (MZ) and acidic ZSM-5 catalysts (For acid and base properties, see Table 2, entries 2, 3, 4, 5) were screened and indeed the variations in product yields were significant. Using the NiW catalyst on acidic ZSM-5 support, 30 wt% of insoluble residue and

only 40 wt% of methanol soluble oil yields were observed (Table 1, entry 9), showing more pronounced recondensation processes likely due to acid catalysed side reactions leading to reactive unsaturated intermediates, such as dehydration products. The results using basic supports MgO-La<sub>2</sub>O<sub>3</sub> were not significantly different from those obtained with catalyst on neutral support. (Table 1, entries 10). When MgO-CeO<sub>2</sub> used, the methanol soluble oil yields dropped to 75 wt% and 9 wt% DMSO soluble solids obtained (Table 1, entry 10). In the case of MgO-ZrO<sub>2</sub>, the methanol soluble oil yields further dropped to 68 wt%, increase in DMSO soluble solids (12 wt%) and 4 wt% of char was observed (Table 1, entry 11). This phenomenon is likely due to decrease in basicity or increase in acidity of the catalysts when La<sub>2</sub>O<sub>3</sub> replaced in MgO-La<sub>2</sub>O<sub>3</sub> with CeO<sub>2</sub> and ZrO<sub>2</sub> (Table 2, entries 4, 5). Lastly, with increased lignin loading to 2 g, both S-NiW/AC and S-NiW/ML catalysts gave 60 wt% of methanol soluble oil yields, whereby more DCM and DMSO soluble solids were obtained with both catalysts. Char formation was not observed with both catalysts even at increased substrate loading.

### 3.2 Surface properties of the catalysts

Surface concentrations of acidic and basic sites of NiMo, CoMo and NiW catalysts were determined by temperature programmed desorption of ammonia (NH<sub>3</sub>-TPD) and carbon dioxide (CO<sub>2</sub>-TPD), respectively (Table 2).

It was found that NiW supported on ZSM-5 presents the highest number of acidic sites (507.6 μmol/g<sub>cat</sub>), while the highest basic capacity was recorded on NiW supported on MgO-La<sub>2</sub>O<sub>3</sub> (291 μmol<sub>CO2</sub>/g<sub>cat</sub>). Moreover, when La<sub>2</sub>O<sub>3</sub> was exchanged with CeO<sub>2</sub> (Table 2, entry 4) or ZrO<sub>2</sub> (Table 2, entry 5), the basicity significantly decreased, resulting in CO<sub>2</sub> uptake values of 188.3 and 104.7 μmol<sub>CO2</sub>/g<sub>cat</sub> for NiW/MgO-CeO<sub>2</sub> and NiW/MgO-ZrO<sub>2</sub>, respectively. Still, when NiW was supported on activated carbon (Table 2, entry 1), not only the NH<sub>3</sub> adsorption capacity appeared quite low (18.4 μmol/g<sub>cat</sub>), but also the basicity was practically negligible (0.6 μmol<sub>CO2</sub>/g<sub>cat</sub>), giving the sample an almost neutral character. A net increase of acidity was observed on the same support when W was exchanged with Mo (44.5 μmol<sub>NH3</sub>/g<sub>cat</sub> for NiMo/AC), likely due to an increased presence of clusters, which are able to delocalize protons among neighboring Mo<sub>x</sub> species more than in presence of isolated groups. Lastly, the substitution of NiO with CoO on activated carbon (Table 2, entry 7) also promoted a further increase of acidity (77.0 μmol<sub>NH3</sub>/g<sub>cat</sub> for CoMo/AC), while the basicity remained almost unchanged. In conclusion, it is clear that the supports play a key role in determining the acid-base behaviour, while the metal loading mainly affects the temperature of peak desorption, depending on a weak or strong metal-support interaction (see also Fig. S4 and Fig. S5 and related comments in Supporting Information). So, from these results the following scale of acidity and basicity can be drawn:




**Table 2** NH<sub>3</sub> and CO<sub>2</sub> TPD measurements of NiMo, CoMo and NiW catalysts.

Entry	Catalyst	NH <sub>3</sub> uptake (μmol/g <sub>cat</sub> )	CO <sub>2</sub> uptake (μmol/g <sub>cat</sub> )
1	NiW/AC	18.4	0.6
2	NiW/ZSM-5	507.6	-
3	NiW/MgO-La <sub>2</sub> O <sub>3</sub>	-	291.0
4	NiW/MgO-CeO <sub>2</sub>	-	188.3
5	NiW/MgO-ZrO <sub>2</sub>	-	104.7
6	NiMo/AC	44.5	0.6
7	CoMo/AC	77.0	0.7


In the attempt of confirming the sulphidation process, the spent catalyst NiW/AC, recovered after the reaction, was characterized by X-ray diffraction and in Fig. 1 the patterns of the fresh (a) and used (b) catalysts are compared. Before the reaction, typical crystalline peaks referred to the  $\langle 100 \rangle$ ,  $\langle -111 \rangle$  and  $\langle 002 \rangle$  planes of monoclinic phase of  $\text{NiWO}_4$  (JCPDS 150755) were evident, along with Ni metallic (JCPDS 040850) diffraction peaks at  $44.55^\circ$ ,  $51.91^\circ$ ,  $76.34^\circ$  and  $92.89^\circ$ , corresponding to  $\langle 111 \rangle$ ,  $\langle 200 \rangle$ ,  $\langle 220 \rangle$  and  $\langle 311 \rangle$  planes, respectively. The spent catalyst, indeed, shows the characteristic signals of tungsten sulphide ( $\text{WS}_2$ ) at  $14^\circ$ ,  $32.7^\circ$ ,  $33.4^\circ$ ,  $39.4^\circ$ ,  $43.8^\circ$ ,  $49.8^\circ$  and  $58.7^\circ$  which are referred to  $\langle 002 \rangle$ ,  $\langle 100 \rangle$ ,  $\langle 101 \rangle$ ,  $\langle 006 \rangle$ ,  $\langle 105 \rangle$  and  $\langle 110 \rangle$  planes (JCPDS 080237) and the peaks of trigonal nickel sulphide  $\text{Ni}_3\text{S}_2$  phase, observed at  $21.65^\circ$ ,  $30.9^\circ$ ,  $37.6^\circ$ ,  $44.4^\circ$ ,  $20.1^\circ$ ,  $54.9^\circ$ ,  $55.2^\circ$ , corresponding to  $\langle 101 \rangle$ ,  $\langle 012 \rangle$ ,  $\langle 003 \rangle$ ,  $\langle 021 \rangle$ ,  $\langle 202 \rangle$ ,  $\langle 211 \rangle$ ,  $\langle 104 \rangle$ ,  $\langle 122 \rangle$  planes (JCPDS 020772).

The formation of sulphided NiW/AC was further confirmed by



**Fig. 1** XRD patterns of NiW/AC catalyst: (a) sulphided (after reaction), (b) fresh (before reaction).


SEM-EDAX measurement, which showed the presence of about 2 wt% of sulphur in the used catalyst (see EDAX values reported in Table S3). Fig. 2 exhibits the micrographs of fresh and used NiW/AC catalyst, showing that the spent catalyst maintains the original structure characterized by particles in the range comprised between 10 and 100  $\mu\text{m}$ . The insert reported in Fig. 2-b is the mapping of S-NiW/AC catalyst, which shows the almost homogeneous distribution of sulphur in correspondence of Ni and W.



**Fig. 2** SEM micrographs of NiW/AC catalyst (a) fresh, and (b) used. In the insert, the mapping measurement is shown.

### 3.3 In depth analysis of the methanol soluble products by GC-MS-FID measurements

The composition of the methanol soluble products obtained in catalytic tests described in Table 1 was investigated by GC-MS-FID chromatography. A representative chromatogram of the product mixture obtained using the S-NiW/AC catalyst is shown in Fig. 3. Though the GC-MS-FID trace is complex, only around 30 main components were found in significant quantities. All of these major products were identified as shown in Fig. 3. The main groups of compounds were: a) *mono oxygenated phenolics*, such as phenol (1), anisole (4), *o*-, *p*-, *m*-cresols (3,5,6), dimethyl phenols (10,13,14,19), ethyl-phenols (13,15,16), propyl phenols (25), ethyl-methyl phenols (21,22), methylated propyl phenols (27,28), tri- and tetra-methyl phenols (12,17,23,24) and b) *guaiacolics* (2,7,8,18,20,26). Some extractives, not directly derived from lignin depolymerization were also seen (29,30)<sup>61</sup>. Interestingly, tri-oxygenated compounds, mainly expected from syringyl lignin subunits were not found. Next, this products mixture was compared to that obtained with the same catalyst (NiMo/AC) under hydrogen free conditions. The major products in this case were tri- and tetra-methylated phenols as well as 2-isopropyl-1-methoxy-4-methylbenzene (Fig. S6), a product mixture markedly different from that shown in Fig. 3, where phenolics and guaiacolics were major products. Clearly, in the absence of hydrogen, the hydrodeoxygenation processes are limited and reactions involving the solvent are predominant. Similarly, in the case of non-sulphided NiW/AC catalyst, substituted guaiacolics were prevalent over phenolics (Fig. S7) showing that sulphided form of NiW/AC catalyst enhances the deoxygenation activity of the catalyst, and further processing of the lignin derived monomers towards phenolics. All other sulphided NiMo/AC, CoMo/AC, W/AC and NiW supported on acidic ZSM-5 and basic MgO-La<sub>2</sub>O<sub>3</sub> (ML), MgO-CeO<sub>2</sub> (MC), MgO-ZrO<sub>2</sub> (MZ) catalysts gave similar product distributions.




**Fig. 3** GC-MS-FID chromatogram of methanol soluble oil obtained at  $320^\circ\text{C}$ , for 8 h with 35 bar  $\text{H}_2$  using S-NiW/AC catalyst.

### 3.4 Quantification of methanol soluble products by 2D-GC×GC measurements

In addition to identification of the components by GC-MS-FID measurements shown above, the product mixtures obtained in the catalytic runs shown in Table 1 were quantified using GC×GC-FID technique. Quantification was based on calibration of the various types of compounds present in these product mixtures and the use of di *n*-butylether (DBE) as an external standard (Fig. 4). A representative GC×GC-FID chromatogram is given in Fig. 6b and the various areas corresponding to the different types of products in the mixture are displayed (for calibration details of GC×GC-FID, see Appendix C in Supporting Information). Quantification based on

such GCxGC-FID measurements, for all product mixtures obtained with each catalyst after 8 h reaction time, are displayed in Fig. 4.

The two most important groups of products (alkylphenolics and guaiacolics) were quantified and are displayed for each run in Fig. 4. The total number of monomers is also given, which include, besides the alkylphenolics and guaiacolics, other compounds such as naphthalenes, catechols, other aromatics and linear and branched alkanes (see Supporting Information, Table S4). Similarly to the results obtained by gravimetric quantification of the various fractions (Table 1), there is a clear difference between the individual runs in terms of yields of total alkylphenolics and



**Fig. 4** Effect of catalysts on alkylphenolics, guaiacolics and monomer yields.

**Reaction conditions:** catalyst (0.25 g), Kraft lignin (1 g), methanol (30 ml), H<sub>2</sub> (35 bar), temperature (320 °C), 8 h

guaiacolics, which depend on the activity of the respective catalyst towards depolymerization. Also, the hydrodeoxygenation activity of the catalyst is correlated with the amount of alkylphenolics versus guaiacolics present.

Without hydrogen only 6.5 wt% of monomers were obtained with S-NiMo/AC and this amount increased to 14.5 wt% in the presence of hydrogen. Better results were obtained when Mo was replaced by W. With S-NiW/AC, a significantly higher (28.5 wt% monomer yield) was obtained; including 16 wt% of alkylphenolics and 5.5 wt% of guaiacolics (see also Table S4, entry 7).

Good results were obtained with the other type of catalysts as well: S-NiMo/AC (14.5 wt%), S-CoMo/AC (9 wt%) and non-sulphided NiWO<sub>x</sub>/AC (16.5 wt%). Without Ni promoter or with S-Ni/AC without W, the monomer yields decreased to 20.5 wt% and 19 wt% respectively. The acidic ZSM-5 support generally gave lower monomer yields (18%) than the basic supports. Especially MgO-La<sub>2</sub>O<sub>3</sub> (ML) gave monomer yields comparable to the activated carbon support (26.5 wt%). Thus the monomer yields depend on reaction conditions, type of metal, promoter and type of support as expected. Sulphidation and combination of Ni with W on neutral support was ideal for obtaining higher monomer yields.

### 3.5 Further improvement of monomer yields and study of reaction parameters

Next, the effect of temperature on the product yield for the catalytic hydrotreatment of Kraft lignin in methanol using the S-NiW/AC catalyst (35 bar H<sub>2</sub>, 8 h) was investigated. Table 3 shows yields of methanol soluble oil as well as monomers (see also Table S5) as a function of the temperature (entries 1-3). The runs differed in the extent of lignin conversion as well as the amount of DCM soluble product, however good product yields could even be achieved at the lowest temperature tested (280 °C). The liquid phases were also analysed by GPC, which showed the occurrence of depolymerization of the lignin at all reaction temperatures with slight variation in the average molecular weight (Fig. S8 and Table S2).

**Table 3** Effect of temperature on methanol soluble oil and monomer yields over S-NiW/AC catalyst.

Entry	Temp. (°C)	Methanol soluble oil (wt %)	DCM soluble products (wt %)	DMSO soluble solids (wt %)	Monomer yields (wt %)
1	280	60	1	35	20
2	300	65	4	28	23
3	320	82	10	trace	28.5


Reaction conditions: catalyst (0.25 g), Kraft lignin (1 g), methanol (30 ml), H<sub>2</sub> (35 bar), 8 h

Next, we have carried out experiments at standard reaction conditions (320 °C, 35 bar H<sub>2</sub> with S-NiW/AC catalyst) with different reaction times to enhance the yield of aromatic monomers and to determine the extent of possible competing ring hydrogenation reactions that may lead to alkanes. The results summarized in Table 4 indicate that 4 h of reaction time was not sufficient for full lignin conversion. In this case, the yield of the methanol soluble product fraction was 40 wt% (14.5 wt% of monomer yield), which is substantially lower than at standard reaction times (8 h, 82 wt% methanol soluble oil and 28.5 wt% of monomers). An increase in overall monomer yield to 32.5 wt% took place at 16 hours, as depolymerization of oligomeric components in the methanol soluble fraction progressed. No significant change was further observed after prolonged reaction time (24 h) and no char was formed. The slight increase in monomer yields (35 wt%) was likely due to further methylation of the formed fragments as confirmed by various techniques (GC-MS-FID, GCxGC-FID, HSQC NMR).

**Table 4** Effect of time on methanol soluble oil and monomer yields over S-NiW/AC catalyst.

Entry	Time (h)	Methanol soluble oil (wt%)	DCM soluble products (wt%)	DMSO soluble solids (wt%)	Monomer yields (wt%)
1	4	40	1	30	14.5
2	8	82	10	trace	28.5
3	16	77	4	trace	32.5
4	24	79	7	trace	35.0

Reaction conditions: catalyst (0.25 g), Kraft lignin (1 g), methanol (30 ml), H<sub>2</sub> (35 bar), temperature (320 °C)




**Fig. 5** GC-MS-FID chromatograms of methanol soluble fractions obtained at different reaction times over S-NiW/AC catalyst at 320 °C for 8 h with 35 bar H<sub>2</sub>.

The GC-MS-FID and GC×GC-FID chromatograms (Fig. 5 and Fig. 6) of the methanol soluble oils versus time show a clear change in product distribution. Guaiacol (1) and substituted guaiacols (2, 3, 4) were the major products and small amounts of alkylphenolics including phenol


were observed after 4 h. At prolonged reaction times, the amounts of guaiacols are reduced and more alkylphenolics are formed. After 24 h of reaction time almost guaiacols were absent and only alkylphenolics were observed. In addition, methylation was more extensive after 24 h, as is evident by the formation tetra alkylated phenolics (14, 15, 16). Notably, further hydrodeoxygenation or competing ring-hydrogenation did not occur even after 24 h of reaction time. Thus it can be concluded, that the catalyst (S-NiW/AC) is highly suitable, active and selective towards the formation of mono-oxygenated alkylphenolics from Kraft lignin.

In addition, the composition of the obtained product mixtures at various time points was quantified by GC×GC-FID analysis, and the results are summarized in Fig. 7. The amount of the major components (alkylphenolics and guaiacols) vs time is displayed in Fig. 8. After 4 h of reaction time, 10 wt% of guaiacols and only 2.5 wt% of alkylphenolics were present in the reaction mixture. At prolonged reaction times the amount of guaiacols decreased to about 1.5 wt%, whereas the amount of alkylphenolics increased to a maximum of 26 wt% after 24 h. The graphs convincingly show that no substantial aromatic ring hydrogenation activity was observed, even after prolonged reaction times.



**Fig. 6** GC×GC-FID chromatograms of methanol soluble fractions obtained after catalytic hydrotreatment of Kraft lignin over S-NiW/AC catalyst at 320 °C with 35 bar H<sub>2</sub> (a) 4 h, (b) 8 h, (c) 16 h, and (d) 24 h






**Fig. 7** GCxGC-FID results of product distribution with the time (a) 4 h, (b) 8 h, (c) 16 h, and (d) 24 h (Reaction conditions: catalyst (0.25 g), Kraft lignin (1 g), methanol (30 ml), H<sub>2</sub> (35 bar), temperature (320 °C))

HSQC NMR measurements confirmed the structural changes during the catalytic hydrotreatment. This NMR method was used before for the elucidation of the Kraft lignin structure.<sup>62,63</sup> The HSQC NMR spectrum of the starting lignin in DMSO is shown in Fig. 9-a. The main inter-unit linkages:  $\beta$ -O-4,  $\beta$ - $\beta$ ,  $\beta$ -5,  $\alpha$ -O-4 are clearly seen in the  $\delta$ 3-5.5 ppm (<sup>1</sup>H) and  $\delta$ 50-90 ppm (<sup>13</sup>C) region. Signals corresponding to aromatic region of the respective subunits are observed between  $\delta$ 6-8 ppm (<sup>1</sup>H),  $\delta$ 100-140 ppm (<sup>13</sup>C). The chemical shift regions corresponding to the various methoxy-groups belonging to guaiacyl or syringyl subunits are detected in the range of  $\delta$ 3.2-4.2 ppm (<sup>1</sup>H),  $\delta$ 56-58 ppm (<sup>13</sup>C), consistent with literature. The 2D-HSQC NMR spectrum of the methanol soluble oil obtained after depolymerization of Kraft lignin after 8 h of reaction time with


S-NiW/AC catalyst at 320 °C is shown in Fig. 9-b. After depolymerisation, the signals belonging to the interunit lignin linkages are lacking and new peaks arise, that are related to the main types of aromatic products confirmed by GC-MS-FID or GCxGC-FID measurements. There is also a decrease of methoxy signals belonging to lignin in region as well as a marked increase of signals in the aliphatic region, belonging to the formed alkylphenolics and guaiacolics. In addition, signals in *Area 1* of the aromatic region correspond to aromatic protons of both guaiacolics and phenolics, these being practically indistinguishable due to extensive overlap. *Area 2* of the aromatic region however, corresponds to only phenolics and alkylphenolics. These results confirm that under catalytic hydrotreatment conditions, the interunit linkages of lignin have been cleaved to produce guaiacolics, which are further demethoxylated to alkylphenolics.




**Fig. 8** Yields of alkylphenolics and guaiacolics vs batch time, in the product mixture obtained using S-NiW/AC catalyst at 320 °C with 35 bar H<sub>2</sub>

### 3.6 Catalyst characterization after reaction


In Fig. 10, TEM images of the NiW/AC catalyst, recovered after reaction, and fresh catalyst are shown. In both these catalysts, the particles were in spherical shape; this confirmed that there is no change in the morphology of the particles after the reaction, as further confirmed by N<sub>2</sub> adsorption-desorption measurements (see Table S1, Fig. S1 and Fig. S2): the fresh catalyst exhibited a surface area of 857 m<sup>2</sup>/g which decreased to 161 m<sup>2</sup>/g after reaction, along with a corresponding increase in the average pore diameter from 21 Å to 39 Å. Nonetheless, despite of particles agglomeration, the catalyst remained active even after 24 h of reaction time.



**Fig. 9**  $^1\text{H}$ - $^{13}\text{C}$  HSQC NMR spectra of Kraft lignin and methanol soluble fractions obtained after catalytic treatment using S-NiW/AC catalyst at  $320\text{ }^\circ\text{C}$  with 35 bar  $\text{H}_2$  (a) Kraft lignin (b) product mixture obtained after 8 h



**Fig. 10** TEM images of NiW/AC catalysts (a) before (b) after the reaction.



**Fig. 11** Elemental composition of Kraft lignin and derived methanol soluble fraction after reaction over S-NiW/AC catalyst at  $320\text{ }^\circ\text{C}$  with 35 bar  $\text{H}_2$  (blue line: O/C atomic ratio, black line:

Finally, Fig. 11 shows the changes in the O/C and H/C atomic ratios determined by elemental analysis in the product oils obtained at  $320\text{ }^\circ\text{C}$  with S-NiW/AC catalysts at different reaction times. The Kraft lignin used in this study contains 61.1 % of carbon, 5.6 % of hydrogen, 1.6 % sulphur and 30.6 % of oxygen. The observed continuous decrease in the O/C value from 0.375 (Kraft lignin) to 0.112 and a marked increase in the H/C value of 1.102 (Kraft lignin) to 1.298 reflects the nature of transformations expected during catalytic hydrotreatment of Kraft lignin in supercritical methanol. The decrease in O/C atomic ratio value is due to the deoxygenation reactions, and the slight increase in H/C atomic ratio is primarily due to methylation reactions and not because of ring hydrogenation, as confirmed by GC analysis.

## 4 Conclusions

This study presents a very efficient method for the catalytic conversion of Kraft lignin to aromatic monomers, in supercritical methanol. A variety of bimetallic Ni, Mo, Co and W catalysts on various supports were prepared, characterized and evaluated lead to several conclusions regarding catalyst structure-activity relationships. It was found that the activity towards lignin depolymerisation and further processing of the obtained aromatic fragments, depended on several factors: (i) Sulphided catalysts were more active than oxide catalysts. (ii) W was a more suitable metal than Mo. (iii) Ni was a more ideal promoter than Co. (iiii) The role of the support was found to be significant and activated carbon or basic  $\text{MgO-La}_2\text{O}_3$  gave highest product yields, whereas acidic supports promoted char formation.

Excellent, 35 wt% monomer yields was achieved with a sulphided S-NiW/AC catalyst and the product mixture contained up to 26 wt% alkylphenolics, moreover, competing ring hydrogenation or severe repolymerisation to insoluble char was not observed. This stands among the best result in the conversion of Kraft lignin and will lead to the development of efficient methods for the valorisation of lignin waste streams in the future.

## Acknowledgements

This research has been performed within the framework of the CatchBio program. The authors gratefully acknowledge the support of the Smart Mix Program of the Netherlands Ministry of Economic Affairs and the Netherlands Ministry of Education, Culture and

Science. The authors gratefully acknowledge Dr. Arjan Kloekhorst for his help with the GCxGC-FID measurements.

## References

- Tejado, C. Pena, J. Labidi, J. Echeverria and I. Mondragon, *Bioresour. Technol.*, 2007, **98**, 1655.
- A.J. Ragauskas, M. Nagy, D.H. Kim, C.A. Eckert, J.P. Hallett and C.L. Liotta, *Ind. Biotechnol.*, 2006, **2**, 55.
- F.G.C. Flores and J.A. Dobado, *ChemSusChem*, 2010, **3**, 1227.
- J. Zakzeski, P.C.A. Bruijninx, A.L. Jongerius and B.M. Weckhuysen, *Chem. Rev.*, 2010, **110**, 3552.
- J.E. Holladay, J.F. White, J.J. Bozell and D. Johnson, in *Top Value-Added Chemicals from Biomass. Results of Screening for Potential Candidates from Biorefinery Lignin*, vol. II, U.S. Department of Energy (DOE) by PNNL, Richland, WA, USA, 2007, PNNL-16983.
- Ch.O. Tuck, E. Perez, I.T. Horvath, R.A. Sheldon and M. Poliakoff, *Science* 2012, **337**, 695.
- S. Dutta, K.C.W. Wu and B. Saha, *Catal. Sci. Technol.*, 2014, **4**, 3785.
- C. Xu, R. Arneil, D. Arancon, J. Labidi and R. Luque, *Chem. Soc. Rev.*, 2014, **43**, 7485.
- A.J. Ragauskas, G.T. Beckham, M.J. Bidy, R. Chandra, F. Chen, M.F. Davis, B.H. Davison, R.A. Dixon, P. Gilna, M. Keller, P. Langan, A.N. Naskar, J.N. Saddler, T.J. Tschaplinski, G.A. Tuskan and C.E. Wyman, *Science*, 2014, **344**, 1246843.
- Z. Strassberger, S. Tanase and G. Rothenberg, *RSC Adv.*, 2014, **4**, 25310.
- J. Gierer, *Wood Sci. Technol.*, 1980, **14**, 241.
- W.O. Doherty, P. Mousavioun and C. M. Fellows, *Ind. Crops Prod.*, 2011, **33**, 259.
- J. Gierer, I. Noren and S. Wannstrom, *Holzforchung*, 1987, **41**, 79.
- F.S. Chakar and A.J. Ragauskas, *Industrial Crops and Products*, 2004, **20**, 131.
- J. Ralph, K. Lundquist, G. Brunow, F. Lu, H. Kim, P.F. Schatz, J.M. Marita, R.D. Hatfield, S. A. Ralph, J.H. Christensen, *Phytochem. Rev.*, 2004, **3**, 29.
- E. Adler, *Wood Sci. Technol.*, 1977, **11**, 169.
- W.J. Liu, H. Jiang and H.Q. Yu, *Green Chem.*, 2015, DOI: 10.1039/C5GC01054C
- M.P. Pandey and C. S. Kim, *Chem. Eng. Technol.*, 2011, **34**, 29.
- D. Mohan, Ch.U. Pittman and P.H. Steele, *Energy Fuels*, 2006, **20**, 848.
- G.W. Huber, S. Iborra and A. Corma, *Chem. Rev.*, 2006, **106**, 4044.
- P. Azadi, O.R. Inderwildi, R. Farnood and D.A. King, *Renew. Sustainable Energy Rev.*, 2013, **21**, 506.
- C.S. Lancefield, O.S. Ojo, F. Tran and N.J. Westwood, *Angew. Chem. Int. Ed.*, 2015, **54**, 258.
- A. Rahimi, A. Ulbrich, J. J. Coon and S. S. Stahl, *Nature*, 2014, **515**, 249.
- K. Barta, G.R. Warner, E.S. Beach and P.T. Anastas, *Green Chem.*, 2014, **16**, 191.
- P.J. Deuss and K. Barta, *Coord. Chem. Rev.*, 2015, DOI:10.1016/J.CCR.2015.02.004.
- G. Chatel and R.D. Rogers, *ACS Sustainable Chem. Eng.*, 2014, **2**, 322.
- M. Zaheer and R. Kempe, *ACS Catal.*, 2015, **5**, 1675.
- H. Kobayashi, H. Ohta and A. Fukuoka, *Catal. Sci. Technol.*, 2012, **2**, 869.
- E.E. Harris, J. D'Ianni and H. Adkins, *J. Am. Chem. Soc.*, 1938, **60**, 1467.
- K.M. Torr, D.J. van de Pas, E. Cazeils and I.D. Suckling, *Bioresour. Technol.*, 2011, **102**, 7608.
- N. Yan, C. Zhao, P.J. Dyson, C. Wang, L.t. Liu and Y. Kou, *ChemSusChem*, 2008, **1**, 626.
- C. Li, M. Zheng, A. Wang and T. Zhang, *Energy Environ. Sci.*, 2012, **5**, 6383.
- Q. Song, F. Wang, J. Cai, Y. Wang, J. Zhang, W. Yu and J. Xu, *Energy Environ. Sci.*, 2013, **6**, 994.
- K. Barta, P.C. Ford, *Acc. Chem. Res.*, 2014, **47**, 1503.
- X. Huang, T.I. Korányi, M.D. Boot and E.J. Hensen, *ChemSusChem*, 2014, **7**, 2276.
- R. Ma, W. Hao, X. Ma, Y. Tian and Y. Li, *Angew. Chem. Int. Ed.*, 2014, **126**, 7438.
- X. Huang, T.I. Korányi, M. Boot and E.J. Hensen, *Green Chem.*, DOI: 10.1039/C5GC01120E.
- X. Wang and R. Rinaldi, *Angew. Chem. Int. Ed.*, 2013, **52**, 11499.
- W. Xu, S.J. Miller, P.K. Agrawal and C.W. Jones, *ChemSusChem*, 2012, **5**, 667.
- S. Huang, N. Mahmood, M. Tymchyshyn, Z. Yuan and C. C. Xu, *Bioresour. Technol.*, 2014, **171**, 95.
- G. Gellerstedt, J. Li, I. Eide, M. Kleinert and T. Barth, *Energy Fuels*, 2008, **22**, 4240.
- A. Kloekhorst, Y. Shen, Y. Yie, M. Fang and H.J. Heeres, *Biomass Bioenergy*, 2015, **80**, 147.
- A.K. Deepa and P. L. Dhepe, *ACS Catal.*, 2014, **5**, 365.
- S.K. Singh and J.D. Ekhe, *RSC Adv.*, 2014, **4**, 53220.
- V. Roberts, V. Stein, T. Reiner, A. Lemonidou, X. Li and J. A. Lercher, *Chem. Eur. J.*, 2011, **17**, 5939.
- J.A. Onwudili and P. T. Williams, *Green Chem.*, 2014, **16**, 4740.
- J. Miller, L. Evans, A. Littlewolf and D. Trudell, *Fuel*, 1999, **78**, 1363.
- J.S. Shabtai, US pat., US5959167A, 1999.
- A.L. Jongerius, P.C. Bruijninx and B.M. Weckhuysen, *Green Chem.*, 2013, **15**, 3049.
- S. Huang, N. Mahmood, M. Tymchyshyn, Z. Yuan and C.C. Xu, *Bioresour. Technol.*, 2014, **171**, 95.
- R. Ma, W. Hao, X. Ma, Y. Tian and Y. Li, *Angew. Chem. Int. Ed.*, 2014, **126**, 7438.
- X. Ma, R. Ma, W. Hao, M. Chen, F. Yan, K. Cui, Y. Tian and Y. Li, *ACS Catal*, 2015, DOI: 10.1021/acscatal.5b01159.
- E. Furimsky, *Catal. Rev.*, 1983, **25**, 421.
- E. Furimsky and F.E. Massoth, *Catal. Rev.*, 1999, **52**, 381.
- a) S. Mukundan, M. Konarova, L. Atanda, Q. Ma and J. Beltramini, *Catal. Sci. Technol.*, 2015, DOI:10.1039/C5CY00607D.
- b) V.N. Bui, D. Laurenti, P. Delichere, and C. Geantet, *Appl. Catal. B*, 2011, **101**, 246.
- M.L. Kantam, R. Kishore, J. Yadav, M. Sudhakar and A. Venugopal, *Adv. Synth. Catal.*, 2012, **354**, 663.
- a) L. Ding and Y. Zheng, *Catal. Commun.*, 2006, **7**, 1035.
- b) F. Bataille, J.L. Lemberon, G. Perot, P. Leyrit, T. Cseri, N. Marchal and S. Kasztelan, *Appl. Catal. A: Gen.*, 2001, **220**, 191.
- W. Yin, R.H. Venderbosch, G. Bottari, K.K. Krawczyk, K. Barta and H.J. Heeres, *Appl. Catal. B*, 2015, **166-167**, 56.
- T.D. Matson, K. Barta, A.V. Iretskii and P.C Ford, *J. Am. Chem. Soc.*, 2011, **133**, 14090.
- K. Barta, T.D. Matson, M.L. Fettig, S.L. Scott, A.V. Iretskii, P.C. Ford, *Green Chem.*, 2010, **12**, 1640.
- M. Garcia-Perez, *The Formation of Polyaromatic Hydrocarbons and Dioxins During Pyrolysis: A Review of the Literature with Descriptions of Biomass Composition, Fast Pyrolysis Technologies and Thermochemical Reactions*, Washington State University, WA, USA, 2008, page 5.
- T.M. Liitiä, S.L. Maunu, B. Hortling, M. Toikka and I. Kilpeläinen, *J. Agric. Food Chem.*, 2003, **51**, 2136.
- C. Fernández-Costas, S. Gouveia, M. Sanromán and D. Moldes, *Biomass Bioenergy*, 2014, **63**, 156.