

Dalton Transactions

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

COMMUNICATION

Regulation of Cerium(IV)-driven O₂ Evolution Reaction using Composites of Liposome and Lipophilic Ruthenium Complexes

Cite this: DOI: 10.1039/x0xx00000x

Received 00th January 2012,
Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

Tomomi Koshiyama,^{*a} Nao Kanda,^a Koki Iwata,^a Masayuki Honjo,^a Sana Asada,^a Tatsuru Hatae,^a Yasuhiro Tsuji,^a Masaki Yoshida,^b Masaya Okamura,^b Reiko Kuga,^b Shigeyuki Masaoka^b and Masaaki Ohba^{*a}

A composite containing a liposome and a lipophilic ruthenium complex was synthesized to regulate an O₂ evolution reaction using cerium(IV) ammonium nitrate as an oxidizing reagent. We found that the surrounding environment of the reaction centre is an important factor controlling the O₂ evolution catalytic reaction. We successfully regulated the reaction activity using the linker length of the lipophilic ligand and the head groups of the phospholipid component.

Sophisticated design of molecular catalysts for medical and industrial applications has been a long-standing target in the field of catalyst chemistry. Molecular catalysts have high designability, and provide high activity and selectivity by the adjustment of their substituted groups of ligands, whereas the complicated organic synthesis is required. Further, the low solubility of molecular catalysts interferes with their application to “green chemistry”. Deposition of molecular catalysts in a confined environment such as a nanoreactor, which is constructed from synthetic and biological molecules, is the one of the promising methods to overcome these limitations.¹

A spherical vesicle, such as a liposome, consisting of a phospholipid bilayer has four types of region: a hydrophilic inner water phase, a hydrophobic lipid bilayer, and inner and outer surfaces in which a hierarchical incorporation of different functional molecules is expected. Such spherical composite integrated functional molecules

^a Department of Chemistry, Faculty of Science, Kyushu University, 6-10-1 Hakozaki, Higashi-ku, Fukuoka, Japan.

E-mail: ohba@chem.kyushu-univ.jp, koshi@chem.kyushu-univ.jp

Fax: +81-92-642-2570; Tel: +81-92-642-2570

^b Institute for Molecular Science, Higashiyama 5-1, Myodaiji, Okazaki 444-8787, Japan

† Electronic Supplementary Information (ESI) available: [details of synthesis of lipophilic Ru Complexes, physical measurements and additional experimental data.]. See DOI: 10.1039/c000000x/

are attractive for fabricating catalysts, sensors, drug delivery systems, and nanomaterials.^{1, 2} In addition, liposomes have advantages as “reaction spaces” because: (1) the ease of controlling their size (nm–μm scale) and their surface charge from the various types of phospholipids that can be employed, and (2) their high stability in environmentally friendly aqueous solutions. Hence, catalytic systems based on liposomes, used in organic conversion,^{3, 4} electron transfer,⁵ photocatalytic water oxidation,⁶ and hydrogen production,^{7, 8} have been reported. Previous researchers have succeeded in utilizing lipid membranes as a stage for reactions, whereas regulation of the reactions has been addressed using functional molecules themselves, and not by the environment on the membrane surface.

Here, we report on the preparation of new liposome composites with metal complexes and on a strategy for regulating their catalytic reactions (Fig. 1a). For the functionalization of the liposome surface, we designed new lipophilic metal complexes and succeeded in fixing them on liposomes. In this work, O₂ evolution from water was selected because of its potential application in artificial solar energy conversion and storage.^{9–11}

To fix the oxygen-evolving mononuclear ruthenium complex [Ru(terpy)(bpy)(OH₂)]²⁺ (Ru core unit = **cRu**) on the liposome surface,^{12, 13} two lipophilic Ru complexes having cholesterol derivatives were designed: [Ru(terpy)(L1)(sol)]²⁺ (**1**, L1 = cholesterol 2,2'-bipyridine-5-ylmethylsuccinate) and [Ru(terpy)(L2)(sol)]²⁺ (**2**, L2 = cholesterol 2,2'-bipyridine-5-carboxylate) (Fig. 1b). The high affinity of the cholesterol moiety for phospholipids allowed **1** and **2** to fix tightly on to the lipid bilayer.¹⁴ The different linker lengths between bpy and the cholesterol moieties was designed to adjust the position of the Ru cores on the liposome surface and to influence the accessibility of oxidizing reagents. Compounds **1** and **2** were synthesized as described in the Supplementary Information. The UV/vis spectra of **1** and **2** in acetonitrile were identical to that of the precursor **cRu** (Fig. S1).¹² The absorption band observed around 460 nm corresponded to the metal-to-ligand charge transfer (MLCT) band. Cyclic voltammograms of **1** and **2** in acetonitrile showed redox couples from Ru(II)/Ru(III) at $E_{1/2} = 0.91$ and 0.94 V vs. Fc/Fc⁺, respectively




Fig. 1 (a) A schematic representation of the composite of a liposome and a lipophilic Ru complex. The molecular structures of: (b) **1** and **2** and (c) the phospholipids used.




Fig. 2 (a) Cyclic voltammograms of **1**, **2** and a blank solution in aqueous 0.5 M H_2SO_4 under a N_2 atmosphere. (b) UV-visible spectra of **1**•PA (green), **1**•PC (blue), **1**•PG (red), and **2**•PG (black) in H_2O (Ru concentration = 6 μM).




Fig. 3 The crystal structure of $[\text{Ru}(\text{terpy})(\text{L}3)(\text{CH}_3\text{CN})](\text{PF}_6)_2$.

Table 1 Z_{average} diameter and zeta potential of the liposome composites.

Composite	Lipophilic Ru complex ^a	Phospholipid ^b	Z_{ave} diameter (nm)	Zeta potential (mV)	Turnover number after 12 h
1 •PA	1	DSPA	65.1	-56.5	133
1 •PC	1	DSPC	108.1	30.5	118
1 •PG	1	DSPG	41.6	-49.9	145
2 •PG	2	DSPG	56.7	-50.8	53
PA	-	DSPA	74.4	-78.5	-
PC	-	DSPC	63.3	-36.3	-
PG	-	DSPG	50.7	-70.1	N.D.

^a The concentration of the lipophilic Ru complexes was 9 mol%. Liposomes without lipophilic Ru complexes contained 9 mol% of cholesterol instead of **1** and **2**.

^b All composites contained 3.6 mol% DSPE-PEG₂₀₀₀.

(Fig. S2). In addition, cyclic voltammograms of **1** and **2** in an aqueous 0.5 M H_2SO_4 solution showed that electrocatalytic oxygen evolution from water occurred at potentials ca. 1.3 V vs. Ag/AgCl (Fig. 2a). These results show that the properties of the prepared lipophilic Ru complexes were the same as that of **cRu**.

We succeeded in crystallizing an analogue of **2**, $[\text{Ru}(\text{terpy})(\text{L}3)(\text{CH}_3\text{CN})](\text{PF}_6)_2$ ($\text{L}3 = \text{Cholesterol } 5' \text{-methyl-}2,2' \text{-bipyridine-5-carboxylate}$). The crystal structure shows that acetonitrile occupies a reaction site on the Ru core and the relative disposition of the coordinated acetonitrile and the pyridyl ring bearing the cholesterol substituent are in a trans configuration (Fig. 3). This implies that the reaction site of **1** and **2** are fixed in the lipid bilayers facing the outer water phase of the liposomes, and oxidants and water molecules can access the Ru cores easily.

The type of phospholipid used is important in the design of the reaction space surrounding the Ru cores on the liposome surface. Three phospholipids were used in this work: the negatively charged lipids 1,2-distearoyl-*sn*-glycero-3-phosphate (DSPA) and 1,2-distearoyl-*sn*-glycero-3-phospho-(1'-*rac*-glycerol) (DSPG), and the zwitterionic lipid 1,2-distearoyl-*sn*-glycero-3-phosphocholine (DSPC) (Fig. 1c). The size and charge of the phospholipid head group was expected to influence the packing and surface charge of the composites, thereby regulating the accessibility of oxidants to the Ru cores. To stabilize the liposomes under the reaction conditions used (high ionic strength and acidic solutions), phospholipids with a stearyl group were chosen. Yasuda et al. reported that liposomes containing phospholipids having saturated and relatively long fatty acid chains were stable in acidic solutions.¹⁵ In addition, 3.6 mol% of 1,2-distearoyl-*sn*-glycero-3-phosphoethanolamine-N-[methoxy(polyethylene glycol)-2000] (DSPE-PEG₂₀₀₀) was added to each composite to reduce any aggregation and fusion of the liposomes.¹⁶

Liposome composites were prepared using a lipid thin film hydration method with a 9 mol% chloroform solution of **1** or **2** followed by sonication (Table 1). Formation of the composite was confirmed directly using confocal laser scanning microscopy (CLSM), in which a giant unilamellar vesicle was used for visualization (Fig. S3), and the content of **1** and **2** was determined using inductively coupled plasma atomic emission spectroscopy. The UV-vis spectra of the samples are shown in Fig. 2b. **1**•PC and **1**•PG exhibited an absorption maximum of the MLCT at 457 nm, which is almost the same as that of **1** in acetonitrile. However, the absorption maximum of MLCT in **1**•PA and **2**•PG was red-shifted to 495 nm and 472 nm when compared with that of **1** (at 456 nm) and **2** (at 465 nm) in acetonitrile, respectively. The Ru cores of **1**•PA and **2**•PG




Fig. 4 The evolution of oxygen from an aqueous 195 mM $(\text{NH}_4)_2[\text{Ce}(\text{NO}_3)_6]$ solution in the presence of **1•PA** (green), **1•PC** (blue), **1•PG** (red), **2•PG** (black), and **PG** (orange).

could be influenced by the phosphate groups of DSPA or DSPG, because the MLCT band of **cRu** in 50 mM Na_2HPO_4 shows a similar shift to those of **1•PA** and **2•PG** (Fig. S4).

The particle size of the composites was measured using dynamic light scattering (Table 1). The Z_{ave} diameters of **1•PA**, **1•PG**, and **2•PG** were in the range 40–65 nm, and were almost the same as that of liposomes without lipophilic Ru complexes, except for **1•PC**. The particle size of **1•PC** (108 nm) was about twice as large as that of PC. Because larger liposomes commonly have a lesser degree of curvature and have a more closely packed lipid bilayer,¹⁷ the Ru complex moieties of **1** in **1•PC** could interact electrostatically with DSPC head groups. Furthermore, the fixation of the lipophilic Ru complexes on the liposome surface was confirmed from the zeta potential. The zeta potentials of all the liposome composites were more positive than those of the non-complexed liposomes (Table 1). This observation is attributed to the positive charge of the Ru core of **1** and **2**. The zeta potentials of the composites depended on the type of head group of the phospholipids. **1•PC** containing zwitterionic DSPC had a positive surface charge (30.5 mV), although other composites had a negative surface charge. This result suggests that the Ru cores are located on the liposome surface, and the charges surrounding the Ru cores were controlled by the type of phospholipid head groups.

The evolution of O_2 was examined at 20 °C under an Ar atmosphere in the presence of 195 mM $(\text{NH}_4)_2[\text{Ce}(\text{NO}_3)_6]$ as an oxidant and 0.08 mM of the liposome composites (Fig. 4). The stability of the composites under the reaction conditions was confirmed using CLSM. The reaction between **1•PG** and 40 equiv. of $(\text{NH}_4)_2[\text{Ce}(\text{NO}_3)_6]$ was monitored spectrophotometrically (Fig. S5). The spectrum of the mixture after 12 h showed the bleach of the MLCT band, corresponding to the oxidation of Ru^{II} species by Ce^{4+} .¹² After addition of an excess of ascorbic acid to the reaction mixture, the MLCT band of **1** was recovered.¹² In addition, the reaction mixture evolved negligible amount of carbon dioxide during the reaction, which was confirmed by gas chromatography. These results corroborated the robustness of **1•PG** during the O_2 evolution reaction well. **1•PG** exhibited the highest catalytic activity, which was of the same order as that of **cRu**.¹² The total amount of O_2 evolved by **1•PG** was 23.2 μmol , which was 2.7 times greater than that evolved by **2•PG**. **1•PG** and **2•PG** have mutual surface environments regarding Z_{ave} diameter and zeta potential, so that the difference in catalytic reactivity can be explained by the location of the Ru cores on the liposome surface, which was adjusted by the linker lengths of L1 and L2. The distance between the Ru and the ester oxygen atom O2 in the crystal structure of $[\text{Ru}(\text{terpy})(\text{L3})(\text{CH}_3\text{CN})](\text{PF}_6)_2$ (analogue of **2**) is ca. 5.4 Å, which is

shorter than the thickness of the PG head group (ca. 9 Å) (Fig. 3).¹⁸ Thus, the Ru core of **2•PG** would be embedded in the head group region, resulting in a reduced accessibility of Ce^{4+} ions. In addition, the O_2 evolution behaviour of these composites underwent changes depending on the types of phospholipids. The activities of **1•PG** and **1•PA**, having the negative surface charge, were significantly higher than that of **1•PC**, having the positive surface charge. In the case of **1•PA**, the O_2 evolution began without an induction period. To discuss the initial process of reaction, the reaction between composites and 40 equiv. of $(\text{NH}_4)_2[\text{Ce}(\text{NO}_3)_6]$ was monitored by UV-visible spectroscopy (Fig. S6). Soon after mixing **1•PA** with Ce^{4+} , the spectrum showed rapid bleach of the MLCT band. In contrast, the MLCT bands of **1•PC** and **1•PG** gradually decayed. This means that the relatively small and negatively charged head group of PA is effective in promoting the accessibility of Ce^{4+} ions to the Ru core. This result suggests that: (1) the location of the Ru cores is on the liposome surface, and (2) the charge of the phospholipid head group is an important consideration in the development of catalytic systems based on liposome space.

Conclusions

We fabricated O_2 evolution catalysts using liposomes and lipophilic ruthenium complexes. We found that the surrounding environment of the ruthenium reaction centre is an important factor controlling the O_2 evolution reaction. In particular, the position of the Ru cores on the liposome surface influences the accessibility of oxidizing reagents, and the reaction activity can be regulated by the linker length of the lipophilic ligand and the head group of the phospholipids. This is a new regulation method for molecular catalyst systems. Compared with the reactivity of photocatalytic water oxidation system using Ru complexes with vesicles reported by Hansen et al.,⁶ it showed higher catalytic reactivity than our system. Because the types of catalyst and reaction are completely different each other, it is not easy to clarify the reason for the different reactivity. One possible reason for it is that the lipophilic complexes were installed on the outer and inner surfaces in the current method. Because oxidants could not pass through the lipid bilayer, the complexes fixed on the inner surface do not participate in the reaction. The catalytic activity of the composites would be improved by establishing a method that selectively fixes the metal complexes on the outer surface.

Acknowledgements


This work was supported by a Grant-in-Aid for Challenging Exploratory Research (no. 26620049) from MEXT, Japan. T. K. thanks the MEXT for a Grant-in-Aid for Young Scientists (B) (no. 30467279), Kyushu University Interdisciplinary Program in Education and Projects in Research Development. This work was partly supported by Nanotechnology Platform Program (Molecule and Material Synthesis) of MEXT, Japan, and the Center of Advanced Instrumental Analysis, Kyushu University.

Notes and references

1. D. M. Vriezema, M. C. Aragoes, J. A. A. W. Elemans, J. J. L. M. Cornelissen, A. E. Rowan and R. J. M. Nolte, *Chem Rev*, 2005, **105**, 1445-1489.
2. P. Scrimin and P. Tecilla, *Curr Opin Chem Biol*, 1999, **3**, 730-735.
3. A. P. H. J. Schenning, J. H. L. Spelberg, D. H. W. Hubert, M. C. Feiters and R. J. M. Nolte, *Chem-Eur J*, 1998, **4**, 871-880.
4. P. Walde, H. Umakoshi, P. Stano and F. Mavelli, *Chem Commun*, 2014, **50**, 10177-10197.
5. J. N. Robinson and D. J. Colehamilton, *Chem Soc Rev*, 1991, **20**, 49-94.
6. M. Hansen, F. Li, L. Sun and B. Konig, *Chem Sci*, 2014, **5**, 2683-2687.
7. S. Troppmann and B. Konig, *Chem-Eur J*, 2014, **20**, 14570-+.
8. K. Watanabe, S. Takizawa and S. Murata, *Chem Lett*, 2011, **40**, 345-347.
9. J. J. Concepcion, J. W. Jurss, M. K. Brennaman, P. G. Hoertz, A. O. T. Patrocinio, N. Y. M. Iha, J. L. Templeton and T. J. Meyer, *Accounts Chem Res*, 2009, **42**, 1954-1965.
10. M. Okamura and S. Masaoka, *Chemistry, an Asian journal*, 2015, **10**, 306-315.
11. D. J. Wasylenko, R. D. Palmer and C. P. Berlinguette, *Chem Commun (Camb)*, 2013, **49**, 218-227.
12. S. Masaoka and K. Sakai, *Chem Lett*, 2009, **38**, 182-183.
13. A. Kimoto, K. Yamauchi, M. Yoshida, S. Masaoka and K. Sakai, *Chem Commun*, 2012, **48**, 239-241.
14. H. Ohvo-Rekila, B. Ramstedt, P. Leppimaki and J. P. Slotte, *Prog Lipid Res*, 2002, **41**, 66-97.
15. M. Han, S. Watarai, K. Kobayashi and T. Yasuda, *The Journal of veterinary medical science / the Japanese Society of Veterinary Science*, 1997, **59**, 1109-1114.
16. M. C. Woodle and D. D. Lasic, *Biochimica et biophysica acta*, 1992, **1113**, 171-199.
17. O. G. Mouritsen, *Eur J Lipid Sci Tech*, 2011, **113**, 1174-1187.
18. M. Alves, B. L. Bales and M. Peric, *Bba-Biomembranes*, 2008, **1778**, 414-422.

Regulation of O₂ Evolution Reaction using Composites of Liposome and Lipophilic Ruthenium Complexes

Tomomi Koshiyama, Nao Kanda, Koki Iwata, Masayuki Honjo, Sana Asada, Tatsuru Hatae, Yasuhiro Tsuji, Masaki Yoshida, Masaya Okamura, Reiko Kuga, Shigeyuki Masaoka and Masaaki Ohba**



An O₂ evolution catalyst system was fabricated using liposomes and lipophilic ruthenium complexes. The reaction activity was successfully regulated by modification of the surrounding environment of the reaction centre on the membrane surface.