Dalton Transactions

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/dalton

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

ARTICLE TYPE

Fe₃O₄@ZIF-8: Magnetically recoverable catalysts by loading Fe₃O₄ nanoparticles inside a zinc imidazolate framework

Aleksandra Schejn,^a Thomas Mazet,^b Véronique Falk,^a Lavinia Balan,^c Lionel Aranda,^b Ghouti Medjahdi^b and Raphaël Schneider*^a

s Received (in XXX, XXX) Xth XXXXXXXX 20XX, Accepted Xth XXXXXXXX 20XX DOI: 10.1039/b000000x

A simple methodology for encapsulating ca. 10 nm-sized superparamagnetic Fe₃O₄ nanoparticles in zeolitic imidazolate frameworks (ZIF-8) crystals was developed. The ¹⁰ corresponding Fe₃O₄@ZIF-8 heterostructured material exhibits bifunctional properties with both high magnetization (Fe₃O₄) and high thermal stability, large specific surface, and catalytic properties (ZIF-8). The Fe₃O₄@ZIF-8 catalyst exhibits fair separation ability and reusability, which can be ¹⁵ repeatedly applied for Knoevenagel condensations and

Huisgen cycloadditions for at least ten successive cycles.

Among metal organic frameworks (MOFs), zeolitic imidazolate frameworks (ZIFs) are microporous crystalline materials with high thermal and chemical stability which have attracted ²⁰ particular attention for gas storage and gas separation.¹⁻⁴ In ZIF-8

crystals, the network consists of Zn^{2+} atoms arranged as of [ZnN4] tetrahedrons with the N atoms of 2-methylimidazolate (mim⁻) linkers.⁵⁻⁸ ZIF-8 has a sodalite zeolite-type topology with cages of 11.6 Å and pores of 3.4 Å in diameter. The efficiency of

- ²⁵ ZIF-8 has been demonstrated in gas separation, gas storage, but also for heterogeneous catalytic transformations (Knoevenagel condensations, cycloadditions, oxidations, trans-esterification, and Friedel-Crafts alkylations).^{8,9}
- Nevertheless, one major problem with the reuse of ZIF-8 ³⁰ heterogeneous catalysts remains their separation from the reaction products. Because of the ease of magnetic separation from the reaction mixture, this strategy is more effective than nanofiltration through a membrane or centrifugation in that it allows the catalyst to be recovered.¹⁰ Superparamagnetic particles
- ³⁵ are intrinsically nonmagnetic but can be readily magnetized in the presence of an external magnetic field. This property enables trouble-free separation of the particles from the reaction medium by simply applying an external magnet, thus eliminating filtration or centrifugation operations. Additionally, magnetic particles
- ⁴⁰ exhibit high chemical stability and can be considered as inert in most chemical transformations. Finally, magnetic separation of nanoparticles is economical and promising for industrial applications.¹¹⁻¹³
- In recent years, a couple of approaches have been developed for 45 the encapsulation of small-sized functional nanoparticles like
- ⁴⁵ the encapsulation of small-sized functional hanoparticles like metal particles (Au, Ag, Pt, Pd, Ni)¹⁴⁻²⁸ or quantum dots (CdSe, ZnO, GaN)²⁹⁻³³ into MOFs to build hybrid materials for catalytic

or optical applications.³⁴ Fe₃O₄ nanoparticles capped with the $[(\eta^{5}-semiquinone)Mn(CO)_{3}]$ ligand or with polyacrylic acid have

⁵⁰ successfully been incorporated in organometallic coordination polymers involving Mn²⁺, Cd²⁺ or In^{3+, 35,36} The MIL-100 MOF (Fe³⁺ associated to 1,3,5-benzenetricarboxylate) has recently been grown onto large Fe₃O₄ or Fe₃O₄/Au particles (200-600 nm) to develop reusable catalysts for Claisen-Schmidt condensations and ⁵⁵ for the reduction of 4-nitrophenol.^{37,38} A similar approach was also used to deposit small-sized ZIF-8 crystals (70-140 nm) at the outer-surface of Fe₃O₄ crystals (380-600 nm) to prepare

core/shell Fe₃O₄/ZIF-8 particles without alteration of the properties of both materials.^{39,40} The magnetic properties of these ⁶⁰ core/shell particles were successfully used for the deposition of catalytically active ZIF-8 material in microreactors or for the development of reusable sorbent particles.

Herein, we report for the first time a simple strategy to spread ca. 10 nm-sized Fe_3O_4 nanoparticles into the cavities and/or channels

⁶⁵ of ZIF-8 crystals. The porous crystalline Fe₃O₄@ZIF-8 particles exhibit high catalytic activity in Knoevenagel condensations and present the advantage of being magnetically recoverable at the end of reactions and reuseable for up to ten cycles with no visible deterioration of their catalytic activity. The method was ⁷⁰ successfully extended to Cu²⁺-doped ZIF-8 and allowed the preparation of recyclable catalysts for Huisgen 1,3-dipolar cycloadditions.

The preparation procedure of Fe_3O_4 @ZIF-8 particles is schematically illustrated in Fig. 1.



Fig. 1 Schematic illustration of Fe₃O₄@ZIF-8 particles synthesis.

In order to fill up the ZIF-8 framework with Fe₃O₄ particles, water-dispersible Fe₃O₄ particles capped with citrate ligands were used.⁴¹ The three carboxylate groups of citrate are meant to so coordinate the Zn²⁺ ions and once these ions react with Hmim, the ZIF-8 structure will develop around the Fe₃O₄ particles. In a typical synthetic procedure, citrate-capped Fe₃O₄ nanoparticles





Fig. 2 SEM images of (a) ZIF-8 and (b) Fe₃O₄@ZIF-8 particles. TEM pictures of (b) and (e) ZIF-8, (d) and (f) Fe₃O₄@ZIF-8 particles. (g) 5 Powder XRD patterns of Fe₃O₄, ZIF-8, and Fe₃O₄@ZIF-8 crystals.

dispersed in water and the mixture stirred for 5 min under inert atmosphere. Next, an aqueous solution of $Zn(NO_3)_2$ (molar ratio Hmim/Zn(NO₃)₂ = 70/1) was added and the resulting mixture was stirred at room temperature for 10 min. Fe₃O₄@ZIF-8 crystals ¹⁰ were separated by using an external magnetic field and purified by washing with water and ethanol. The structure and morphology of Fe₃O₄@ZIF-8 particles were characterized by powder X-ray diffraction (PXRD), scanning electron microscopy (SEM), transmission electron microscopy (TEM), and N₂ ¹⁵ adsorption at 77K.

As shown by TEM and SEM experiments, ZIF-8 crystals exhibit the well-defined and thermodynamically favorable truncated rhombic dodecahedral shape and have an average diameter of ca. 430 nm (Fig. 2a,c,e). Once Fe_3O_4 nanoparticles incorporated into

 $_{\rm 20}$ the ZIF-8 framework, the morphology of ZIF-8 crystals is not markedly altered but the particle size decreases to ca. 250 nm (Fig. 2b,d,f and Fig. S1 for size distributions), indicating that Fe₃O₄ nanoparticles act as size-controlling agents for ZIF-8

crystals. It is also worth mentioning that there is no apparent ${}_{25}$ change in the diameter of Fe_3O_4 particles in Fe_3O_4@ZIF-8 compared to the



Fig. 3 (a) TGA traces of ZIF-8 and Fe₃O₄@ZIF-8 crystals. (b) N₂ adsorption/desorption curves at 77K for ZIF-8 and Fe₃O₄@ZIF-8 particles ³⁰ giving surface areas of 1856 and 871 m² g⁻¹, respectively. Black (green) and red (blue) data correspond to the adsorption and desorption branches, respectively.

native citrate-capped Fe₃O₄ particles ($9.6 \pm 1.9 \text{ nm}$) (Fig. S2). The encapsulation of Fe₃O₄ in ZIF-8 was further demonstrated by

- ³⁵ powder X-ray diffraction (PXRD) analysis (Fig. 2g). Fe₃O₄@ZIF-8 particles exhibit a similar XRD pattern compared to ZIF-8 indicating that the sodalite structure of ZIF-8 crystals remained unaffected after loading the Fe₃O₄ particles.^{5,8} Except three peaks at $2\Theta = 48.75$, 50.37, and 57.22°, which correspond
- to the (220), (311), and (400) crystal facets of magnetite (JCPDS No 19-0629), no additional peaks were detected indicating the high purity of the final $Fe_3O_4@ZIF-8$ particles.

Thermogravimetric analysis (TGA) conducted under air indicate that Fe_3O_4 @ZIF-8 particles have a slightly lower stability than

⁴⁵ ZIF-8 crystals (Fig. 3a). For ZIF-8, the sharp weight loss step of 63-64% was observed at ca. 400°C, corresponding to the decomposition of the mim⁻ linker and to the formation of ZnO crystals.⁸ The relatively lower decomposition temperature of Fe₃O₄@ZIF-8 (350°C) compared to pure ZIF-8 might be ⁵⁰ attributed to the gradual decomposition of the citrate ligand capping Fe₃O₄ nanoparticles into aconitate and citraconate between 150 and 350°C. Finally, when comparing the weight loss

of ZIF-8 and Fe₃O₄@ZIF-8 particles, the loading of Fe₃O₄ into

ZIF-8 host was estimated to be 13.3%.

Textural parameters such as surface area, pore volume and pore size of $Fe_3O_4@ZIF-8$ particles were obtained from N_2 adsorptiondesorption measurements at 77K. As shown in Fig. 3b, both ZIF-8 and $Fe_3O_4@ZIF-8$ particles display the Type I isotherms, with a



Fig. 4 (a) Magnetization at 300 K as a function of applied field. Optical images of Fe₃O₄@ZIF-8 particles dispersions (b) before and (c) after applying an external magnetic field. (d,e) Temperature dependent magnetization for citrate-capped Fe₃O₄ and Fe₃O₄@ZIF-8 particles, ¹⁰ respectively.

steep increase for the N₂ uptake at low relative pressure, which reveals the microporosity for both types of particles. The specific surface areas, determined using the Brunauer-Emmet-Teller (BET) method, were found to be 871 ± 3 and $1856 \pm 46 \text{ m}^2/\text{g}$ for 15 Fe₃O₄@ZIF-8 and ZIF-8 particles, respectively. The pore volume

- was also found to decrease from 0.71 cm³/g for ZIF-8 to 0.35 cm³/g for Fe₃O₄(a/ZIF-8. The high decrease in surface area and pore volume after loading Fe₃O₄ nanoparticles into ZIF-8 are not surprising since Fe₃O₄ particles are nonporous. These results also indicate that the available of ZIF 8 for available of headed by the
- $_{\rm 20}$ indicate that the cavities of ZIF-8 framework are blocked by the highly dispersed Fe_3O_4 nanoparticles which seem to be mainly located at the surface of ZIF-8 crystals as indicated by TEM images (Fig. 2d,f).

The temperature dependence of the magnetization recorded in FC $_{25}$ and ZFC conditions (H = 1000 Oe) exhibits characteristic

- features of superparamagnetism for both Fe_3O_4 and $Fe_3O_4@ZIF-8$ crystals (Fig. 4): (i) the ZFC curves go to a rounded maximum at the blocking temperature TB ~ 55 K and ~ 25 K for Fe₃O₄ and Fe₃O₄@ZIF-8, respectively and (ii) the room-temperature
- ³⁰ hysteresis loop points to negligible coercivity and remanence. The lower blocking temperature of Fe₃O₄@ZIF-8 compared to citrate-capped Fe₃O₄ particles originates from reduced dipolar interactions between magnetic particles encapsulated in ZIF-8 pores.^{42,43} The significantly broader peak observed for Fe₃O₄
- $_{35}$ implies a distribution of blocking temperature. Since the particle size does not significantly differ for the two materials, the distribution of TB in Fe_3O_4 is likely due to variation in interparticle interactions across the sample.

To compare the catalytic properties of Fe_3O_4 @ZIF-8 with those 40 of pure ZIF-8 crystals, we first evaluated their catalytic activity in

a Knoevenagel condensation using benzaldehyde and malononitrile as substrates and toluene as solvent (Scheme 1).⁸



Preliminary experiments showed that the reaction proceeded efficiently at room temperature using 6 equiv. malononitrile relative to benzaldehyde and only 4 mol.% of Fe₃O₄@ZIF-8 catalyst, yielding 2-(benzylidene)malononitrile in 94% yield after ⁵⁰ 3 h of reaction. Under similar experimental conditions, ZIF-8 yielded 2-(benzylidene)malononitrile in 98% yield. Fig. S3 shows the conversion of benzaldehyde when reacting with malononitrile in the presence of ZIF-8 or Fe₃O₄@ZIF-8 crystals as a function of time. As seen, the condensations proceeded very quickly at room ⁵⁵ temperature with both catalysts and the reaction is only slightly slowed down using Fe₃O₄@ZIF-8 crystals. These results demonstrate that the iron oxide nanoparticles incorporated in ZIF-8 framework do not alter the activity of ZIF-8 and that the reaction probably proceeds on the external surface of the catalyst.

- ⁶⁰ We also conducted a control experiment in which Fe₃O₄ nanoparticles were supported on the surface of ZIF-8 crystals by soaking Fe₃O₄ particles in an aqueous dispersion of ZIF-8. When benzaldehyde was reacted with malononitrile in the presence of this catalyst, the product of the Knoevenagel condensation was ⁶⁵ obtained with a yield of 73% after 3 h reaction at room temperature. We believe that the decrease in reactivity in this case may be due to the higher occupation of ZIF-8 catalytically active surface sites. Finally, catalytic cycles were run to investigate the stability of the catalytic activity and recycling. After each run, ⁷⁰ Fe₃O₄@ZIF-8 particles were separated using a magnet, washed twice with toluene and methanol, dried in air at 60°C, and reused. As shown in Fig. S4, the catalyst could be recycled at least ten times without any loss of activity for the Knoevenagel condensation between benzaldehyde and malononitrile.
- ⁷⁵ The loading of magnetite nanoparticles into ZIFs was successfully extended to Cu^{2+} -doped ZIF-8 materials developed recently.⁴⁴ Citrate-capped Fe₃O₄ were successfully immobilized in the Cu_{25%}/ZIF-8 framework and the Fe₃O₄@Cu_{25%}/ZIF-8 used for cycloaddition between benzylazide and phenylacetylene ⁸⁰ (Scheme 2).

$$Ph \land N_{3} + Ph \longrightarrow H \xrightarrow{Fe_{3}O_{4}@Cu_{25\%}/ZIF-8}{Toluene, 100°C} Ph \land Ph \land Ph \xrightarrow{N=N}{Ph} Ph$$

$$1.4-isomer/1.5-isomer > 99/1$$

Scheme 2 Synthesis of 1,2,3-triazoles using Fe_3O_4 -loaded Cu^{2+} -doped ZIF-8 particles.

The triazoles were obtained in 98% isolated yield using a sphenylacetylene/benzylazide molar ratio of 1.2 and conducting the reaction for 3 h in toluene at 100°C. Noteworthy is the improvement of regioselectivity of the cycloaddition with Fe₃O₄loaded Cu_{25%}/ZIF-8 as compared to Cu_{25%}/ZIF-8 catalyst (1,4/1,5 > 99/1 for Fe₃O₄@Cu_{25%}/ZIF-8 while 1,4/1,5 = 92/8 for 90 Cu_{25%}/ZIF-8). The Fe₃O₄@Cu_{25%}/ZIF-8 catalyst could be successfully recycled three times without any loss in activity (Fig. S5). The catalyst activity started to drop in run 4 providing triazoles in ca. 75% yield. A gradual decrease in activity was further observed and triazoles were isolated with ca. 55% yield 95 after the 10th cycle of cycloaddition. 60

65

Page 4 of 6

Blank experiments conducted in the presence of citrate-capped 55 Fe₃O₄ nanoparticles showed no detectable amounts of Knoevenagel or cycloaddition products and confirmed that both reactions were catalyzed by ZIF-8 materials associated to Fe₃O₄.

- 5 We also examined the leaching behaviour of Fe₃O₄@ZIF-8 particles in Knoevenagel and Huisgen reactions. The Fe and Zn contents were determined in the crude reaction products using Inductively Coupled Plasma-Optical Emission Spectrometry (ICP-OES). Low levels for Fe leaching (207 and 39 μ g/L in
- 10 Huisgen and Knoevenagel products, respectively) and Zn leaching (234 and 107 µg/L in Huisgen and Knoevenagel products, respectively) were obtained. These results show that ZIF-8 crystals provide enough binding sites on the surface of Fe₃O₄ particles to minimize deterioration and leaching and thus to
- 15 facilitate efficient catalyst recycling. Finally, the XRD patterns of Fe₃O₄@ZIF-8 and Fe₃O₄@Cu_{25%}/ZIF-8 catalysts exhibit no significant changes in their crystallinity after five recyclings (Fig. S6), which further confirms their high stability.

Conclusions

- 20 To sum up, we have developed an aqueous-based route for incorporating ca 10 nm-sized Fe₃O₄ nanoparticles inside ZIF-8 crystals and used Fe₃O₄@ZIF-8 particles as a heterogeneous catalyst for Knoevenagel condensations between benzaldehyde and malononitrile. The Fe₃O₄@ZIF-8 catalyst is easily
- 25 recoverable by magnetic separation and can be reused more than ten times without any loss in the catalytic activity. Using the same approach, Fe₃O₄ particles were also loaded into Cu²⁺-doped ZIF-8 crystals and the particles obtained were successfully used for Cu²⁺-catalyzed Huisgen cycloadditions. Results obtained in
- 30 this study open an avenue to the fabrication of highly efficient and easily recoverable MOFs based nanocatalysts.

Acknowledgements

This work was supported by ICCEL and MICA Carnot Institutes. We thank Kevin Mozet (LRGP, UMR CNRS 7274, Université de

35 Lorraine) and Hervé Marmier (LIEC, UMR CNRS 7360, Université de Lorraine) for BET and ICP-OES measurements, respectively.

Notes and references

^a Laboratoire Réactions et Génie des Procédés (LRGP), UMR CNRS

- 40 7274, Université de Lorraine, 1 rue Grandville 54001 Nancy, France. Email: raphael.schneider@univ-lorraine.fr
- ^b Institut Jean Lamour (IJL), Université de Lorraine, CNRS, UMR 7198, CNRS, BP 70239, 54506 Vandoeuvre-lès-Nancy Cedex, France; Tel: +33 383175053
- 45 ^c Institut de Science des Matériaux de Mulhouse (IS2M), UMR 7361, CNRS, 15 rue Jean Starcky, 68093 Mulhouse, France

† Electronic Supplementary Information (ESI) available: Synthetic procedures, size distributions, TEM images of Fe₃O₄ nanoparticles, 50 recycling performances of the catalysts, and XRD patterns of materials

- after catalytic experiments. See DOI: 10.1039/b000000x/
 - R. Morris and P. Wheatley, Angew. Chem. Int. Ed., 2008, 47, 1 4966-4981.

- 2 O. K. Farha, A. O. Yazaydin, I. Eryazici, C. D. Malliakas, B. G. Hauser, M. G. Kanatzidis, S. T. Nguyen, R. Q. Snurr and J. T. Hupp, Nat. Chem., 2010, 2, 944-948.
- 3 J. -R. Li, R. J. Kuppler and H. -C. Zhou, Chem. Soc. Rev., 2009, 38, 1477-1504.
- 4 B. Chen, C. Liang, J. Yang, D. S. Contreras, Y. L. Clancy, E. B. Lobkovsky, O. M. Yaghi and S. A. Dai, Angew. Chem. Int. Ed., 2006, 45, 1390-1393.
- 5 K. S. Park, Z. Ni, A. P. Côté, J. Y. Choi, R. D. Huang, F. J. Uribe-Romo, H. K. Chae, M. O'Keeffe and O. M. Yaghi, Proc. Natl. Acad. Sci. U.S.A., 2006, 103, 10186-10191.
- B. Wang, A. P. Côté, H. Furukawa, M. O'Keeffe and O. M. 6 Yaghi, Nature, 2008, 453, 207-211.
- 7 R. Banerjee, A. Phan, B. Wang, C. Knobler, H. Furukawa, M. O'Keeffe and O. M. Yaghi, Science, 2008, 319, 939-943.
- A. Schejn, L. Balan, V. Falk, L. Aranda, G. Medjahdi and R. 8 Schneider, CrystEngComm, 2014, 16, 4493-4500.
- 9 J. Lee, O. K. Farha, J. Roberts, K. A. Scheidt, S. T. Nguyen and J. T. Hupp, Chem. Soc. Rev., 2009, 38, 1450-1459.
- 10 D. Guin, B. Baruwati and S. V. Manorama, Org. Lett., 2007, 9. 1419-1421.
- S. Sun and H. Zeng, J. Am. Chem. Soc., 2002, 124, 8204. 11
- A. H. Latham and M. E. Williams, Acc. Chem. Res., 2008, 41, 12 411-420
- 13 S. Laurent, D. Forge, M. Port, A. Roch, C. Robic, L. Vander Elst and R. N. Muller, Chem. Res., 2008, 108, 2064-2110.
- F. Schröder, D. Esken, M. Cokoja, M. W. E. van den Berg, O. 14 I. Lebedev, G. Van Tendeloo, B. Walaszek, G. Buntkowski, H.-H. Limbach, B. Chaudret and R. A. Fischer, J. Am. Chem. Soc., 2008, 130, 6119-6130.
- 15 R. J. T. Houk, B. W. Jacobs, F. E. Gabaly, N. N. Chang, A. A. Talin, D. D. Graham, S. D. House, I. M. Robertson and M. D. Allendorf, Nano Lett., 2009, 9, 3413-3418.
- 16 H. -L. Jiang, B. Liu, T. Akita, M. Haruta, H. Sakurai and Q. Xu, J. Am. Chem. Soc., 2009, 131, 11302-11303.
- 17 H. Liu, Y. Liu, Y. Li, Z. Tang and H. Jiang, J. Phys. Chem. C, 2010, 114, 13362-13369.
- M. Meilikhov, K. Yusenko, D. Esken, S. Turner, G. Van 18 Tendeloo and R. A. Fischer, Eur. J. Inorg. Chem., 2010, 3701-3714.
- T. T. Isimjan, H. Kazemian, S. Rohani and A. K. Ray, J. 19 Mater. Chem., 2010, 20, 10241-10245.
- 20 H. -L. Jiang and Q. Xu, Chem. Commun., 2011, 47, 3351-3370.
- K. Sugikawa, Y. Furukawa and K. Sada, Chem. Mater., 2011, 21 23, 3132-3134.
- 22 C. Wang, K. E. deKrafft and W. Lin, J. Am. Chem. Soc., 2012, 134, 7211-7214.
- G. Lu, S. Li, Z. Guo, O.K. Farha, B.G. Hauser, X. Qi, Y. 23 Wang, X. Wang, S. Han, X. Liu, J. S. DuChene, H. Zhang, Q. Zhang, X. Chen, J. Ma, S. C. J. Loo, W. D. Wei, Y. Yang, J. T. Hupp and F. Huo, Nat. Chem., 2012, 4, 310-316.
- 24 Y. Pan, D. Ma, H. Liu, H. Wu, D. He and Y. Li, J. Mater. Chem., 2012, 22, 10834-10839.
- 25 Z. Li and H. C. Zeng, Chem. Mater., 2013, 25, 1761-1768.
- F. Ke, J. Zhu, L. -G. Qiu and X. Jiang, Chem. Commun., 2013, 26 49, 1267-1269.
- 27 P. Wang, J. Zhao, X. Li, Y. Yang, Q. Yang and C. Li, Chem. Commun., 2013, 49, 3330-3332.
- L. Chen, Y. Peng, H. Wang, Z. Gu and C. Duan, Chem. 28 Commun., 2014, 50, 8651-8654.
- 29 D. Esken, S. Turner, C. Wiktor, S. B. Kalidindi, G. Van Tendeloo and R. A. Fischer, J. Am. Chem. Soc., 2011, 133, 16370-16373
- D. Esken H. Noei, Y. Wang, C. Wiktor, S. Turner, G. Van 30 Tendeloo and R. A. Fischer, J. Mater. Chem., 2011, 21, 5907-5915.
- 31 D. Buso, J. Jasieniak, M. D. H. Lay, P. Schiavuta, P. Scopese, J. Laid, H. Amenitsch, A. J. Hill and P. Falcaro, Small, 2012, 8, 80-88.

95

100

105

110

115

120

5

10

15

20

- 32 B. P. Biswal, D. B. Shinde, V. K. Pillai and R. Banerjee, *Nanoscale*, 2013, **5**, 10556-10561.
- 33 T. Wakaoka, K. Hirai, K. Murayama, Y. Takano, H. Takagi, S. Furukawa and S. Kitagawa, J. Mater. Chem. C, 2014, 2, 7173-7175.
- 34 Q.-L. Zhu and Q. Xu, Chem. Soc. Rev., 2014, 43, 5468-5512.
- 35 S. B. Kim, C. Cai, S. Sun and D. A. Sweigart, *Angew. Chem. Int. Ed.*, 2009, 48, 2907-2910.
- 36 Y. Kim, Y.S. Choi, H.J. Lee, H. Yoon, Y.K. Kim and M. Oh, *Chem. Comm.* 2014, **50**, 7617-7620.
- 37 F. Ke, L. –G. Qiu and J. Zhu, Nanoscale, 2014, 6, 1596-1601.
- F. Ke, L. Wang and J. Zhu, *Nanoscale* 2015, 7, 1201-1208.
 T. Zhang, X. Zhang, X. Yan, L. Kong, G. Zhang, H. Liu, J.
- Qiu and K. L. Yeung, *Chem. Engineer. J.*, 2013, **228**, 398-404. 40 J Zheng, C. Cheng, W.-J. Fang, C. Chen, R.-W. Yan, H.-X.
- Huai and C. -C. Wang, *CrystEngComm*, 2014, **16**, 3960-3964. S. R. Ahmed, J. Dong, M. Yui, T. Kato, J. Lee and E. Y. Park,
- J. Nanobiotechnol., 2013, 11, 28 (9 pages).
 F. C. Fonseca, G. F. Goya, R. F. Jardim, R. Mucillo, N. V. L.
- Carreno, E. Longo and E. R. Leite, *Phys. Rev. B*, 2002, 66, 104406.
 - 43 S. Morup, F. Bodker, P. V. Hendriksen and S. Linderoth, *Phys. Rev. B*, 1995, **52**, 287.
- A. Schejn, A. Aboulaich, L. Balan, V. Falk, J. Lalevée, G.
 Medjahdi, L. Aranda, K. Mozet and R. Schneider, *Catal. Sci. Technol.*, 2015, 5, 1829-1839.

Table of contents entry



Synthesis and characterization of Fe_3O_4 nanoparticles encapsulated in ZIF-8 crystals along with their catalytic properties and reusability are presented.