

PCCP

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



Journal Name

ARTICLE

Global Optimization of Small Bimetallic Pd-Co Binary Nanoalloy Clusters: A Genetic Algorithm Approach at the DFT Level.

Mikail Aslan^a, Jack B. A Davis^b and Roy L. Johnston^{b*}Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

The global optimisation of small bimetallic PdCo binary nanoalloys are systematically investigated using the Birmingham Cluster Genetic Algorithm (BCGA). The effect of size and composition on the structures, stability, magnetic and electronic properties including the binding energies, second finite difference energies and mixing energies of Pd-Co binary nanoalloys are discussed. A detailed analysis of Pd-Co structural motifs and segregation effects is also presented. The maximal mixing energy corresponds to Pd atom compositions for which the number of mixed Pd-Co bonds is maximised. Global Minimum clusters are distinguished from transition states by vibrational frequency analysis. Homo-Lumo gap, electric dipole moment and vibrational frequency analyses are made to enable correlation with future experiments.

A. Introduction

The structural characterisation of clusters and nanoparticles is key in elucidating the size-dependent properties of nanoscale materials to facilitate many potential applications. Geometric structures of small nanoparticles (or subnanometre clusters) can be determined by coupling experimental measurements with theoretical calculations³. The generation of possible geometric isomers that can be used to explain experimental findings can be made by intuition⁴⁻⁶ but this becomes impossible for larger systems and will also bias results. Another approach is to utilise an algorithm that explores configurational space to determine the global minimum (GM). Several computational methods that predict the globally stable structures of subnanometre clusters are available, such as statistical mechanical methods,^{7,8} basin hopping⁹ and genetic algorithms (GA).¹⁰ The choice of technique depends on how the potential energy surface is described and how complex it is^{11,12}. After the optimisation of the cluster structure using these methods, reoptimisation at the Density Functional Theory (DFT) level can be performed in order to correlate the predicted lowest energy structure with experimental results for free or supported clusters.¹³⁻¹⁵

Experimental findings associated with theoretical investigations have revealed that the bonding situation for clusters and small nanoparticles is generally different from the

corresponding bulk material^{16,17} and can also differ for two elements of the same group.¹⁸ For these reasons, electronic structure calculations are needed to predict the correct growth characteristics of small clusters. Thus, due to growing interest in the design of novel functional nanomaterials, the DFT analysis of clusters of metals such as cobalt, platinum, palladium, silver, and gold has become a hot research field for chemists, physicists, and materials scientists.¹⁹⁻³³

Clusters become more complex when two or more metals are alloyed in order to tune the characteristics of the particles not only by size but also by composition and chemical ordering, possibly resulting in special synergistic effects for these “nanoalloys”.³⁴ In recent years, bimetallic nanoparticles have been studied using many body empirical potentials, with the GM predicted using a GA, often yielding consistent results with experiments.³⁵ However, an examination of the bonding in smaller (subnanometre) bimetallic clusters can only be achieved using electronic structure methods. For this reason, we have recently developed a program for the direct global optimisation of cluster geometries at the DFT level – the so-called GA-DFT approach.^{3,36} Another motivation is that nanoalloy particles often have superior chemical and physical properties compared to single element nanoparticles.³⁷ Thus, nanoalloys are of great interest in the chemical industry: for example, one metal may adjust the catalytic properties of the other due to structural and/or electronic effects. In many nanoalloys, the lowest energy configurations have a core of one metal surrounded by a shell of the other metal, so that smaller volumes of a catalytically active element (thereby reducing the cost) might be sufficient to achieve similar effects as those of single element catalysts.³⁸ Furthermore, in Fisher-Tropsch catalysis,³⁹⁻⁴¹ PdCo nanoparticles have been shown to display higher selectivity than pure Co particles. Synthesis of hydrocarbon fuels by reacting carbon monoxide and hydrogen

^a Department of Metallurgical and Materials Engineering, Gaziantep University, Gaziantep, Turkey

^b School of Chemistry, University of Birmingham, Birmingham, United Kingdom, * e-mail: r.l.johnston@bham.ac.uk

† Footnotes relating to the title and/or authors should appear here.

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

is appealing to many researchers in this area due to recent huge fluctuations in the prices of hydrocarbons.³⁸

In this paper, we have used the Birmingham Cluster Genetic Algorithm (BCGA) with an interface to the PWscf DFT code within the Quantum Espresso (QE) package. This provides an unbiased search starting from entirely random coordinates for the search of GM of PdCo nanoalloys. Here we conduct the first GM search for 4-7 atom PdCo bimetallic nanoalloys, over the entire composition range, using the GA-DFT approach.

B. Methods

In the present study, the putative GM isomers are generated by the Birmingham Cluster Genetic Algorithm BCGA¹⁰ within the framework of Density Functional Theory, using an interface to the PWscf code of Quantum Espresso (QE) software.⁴² BCGA is used for the structural characterisation of nanoparticles and nanoalloys. The interface with QE enables the energy landscape of a system to be searched for the GM at the DFT level.

In the first step of the GA, a set of individuals is generated randomly to form an initial population of 10 to 40 members. Real valued Cartesian coordinates are chosen and each structure is relaxed by optimising the potential energy as a function of its coordinates. The BCGA is a "Lamarckian" type GA, which combines a GA step with a subsequent local minimisation of the energy. Each structure is assigned a fitness value such that the lowest energy structures correspond to highest fitness. In the GA-DFT approach, the energy of each member of the population is obtained from a PWscf DFT calculation. The crossover process (to generate a predetermined number of offspring) uses the roulette wheel selection criterion and the Deaven-Ho cut and splice method.⁴³ Mutation is accomplished using a number of schemes in the BCGA, such as atom displacement, cluster twisting, cluster replacement, and atom permutation and is performed to improve population diversity. The process of selection, crossover, and mutation is reiterated for a predetermined maximum number of generations. However, if after a certain number of generations the lowest energy member of the population does not change, then the population is considered to have converged and the GA terminates.

Plane-wave PWscf calculations are conducted by applying ultrasoft type pseudopotentials⁴⁴ for all metallic species, including scalar relativistic effects⁴⁵. We have adopted the Perdew-Burke-Ernzerhof (PBE) GGA exchange-correlation functional⁴⁶ that has been widely used in the treatment of small, mixed clusters. For the primary screening of the structures with BCGA, the default density cutoff convergence criterion is applied with energy cutoff of 50 Ry. The Methfessel-Paxton smearing scheme⁴⁷ with a value of 0.01 Ry is applied to aid metallic convergence.

Spin-polarised reminimisations of BCGA-DFT global minima were carried out using the orbital-based DFT package

NWChem.⁴⁸ PBE exchange-correlation functionals,⁴⁶ LANL2DZ basis sets and relativistic effective core pseudopotentials (ECPs)^{49, 50} were used for Pd and Co, where only the outermost electrons are treated explicitly in the calculations. Default convergence criteria have been applied during calculations: 1×10^{-6} Hartree for energy and 5×10^{-4} Hartree/a₀ for the energy gradient. Geometry optimisations were performed without any symmetry constraints for a range of electron spin multiplicities.

DFT binding energies (E_b) are calculated from

$$E_b = \frac{nE_{Pd} + mE_{Co} - E_{Pd_nCo_m}}{n + m} \quad (1)$$

where, n is the number of Pd atoms and m is the number of Co atoms.

To further illustrate the stability of the nanoalloys and their size dependent behaviour, we have considered the second finite difference in energy, which is a sensitive quantity that is frequently used as a measure of the relative stability of a particular cluster with respect to neighbouring sizes or compositions and is often compared directly with the relative abundances determined in mass spectroscopy experiments. For a fixed size cluster, the second finite difference energy ($D_{n,m}$) of the isomer Pd_nCo_m is calculated as

$$D_{n,m} = E_{n+1,m-1} + E_{n-1,m+1} - 2E_{n,m} \quad (2)$$

where $E_{n,m}$ is the total energy of the Pd_nCo_m nanoalloy. The second finite differences in energies of the studied nanoalloys are shown in Figure 6

The mixing energies (E_m) are listed in Table I to provide a measure of the stability of the bimetallic clusters with respect to the monometallic ones or the energy associated with alloying. E_m is defined as

$$E_m = E(Pd_nCo_m) - \frac{n}{n+m} E(Pd_n) - \frac{m}{n+m} E(Co_m) \quad (3)$$

C. Results and Discussions

To check the validity of the computational method for the study of the bimetallic PdCo nanoalloys, the binding energies (BEs) of Pd and Co dimers were calculated as 0.76 and 1.03 eV per atom, respectively. The obtained results are in agreement with experimental⁵¹⁻⁵⁵ and theoretical results.^{22, 56-59} The BE of PdCo dimer (1.21 eV) does not lie between those of Pd₂ and Co₂. However, Pd_nCo_m binary nanoalloys properties are expected to lie in between those of pure palladium and cobalt clusters.




Figure 1 Global Minima for three and four atom PdCo nanoalloys. Pd and Co are shown in purple and pink, respectively.




Figure 2 Global Minima for five atom PdCo nanoalloys.




Figure 3 Global Minima for six atom PdCo nanoalloys.




Figure 4 Global Minima for seven atom PdCo nanoalloys.

The ground state structure of the Co trimer is still controversial. In our calculation, the GM structure of Co_3 has been identified as a C_{2v} isosceles triangle, as previously reported.^{57, 60, 61} Experimentally, it was reported⁶² that the electron spin resonance spectrum of the cobalt trimer in an Ar/Kr matrix shows a triangular structure with a spin moment of 5 or 7 μ_B . However, Co_3 was found to adopt a linear geometry in Refs.^{59, 63} Datta et al.⁶¹ found the BE and spin moment as 1.78 eV/atom and 5 μ_B respectively while we found corresponding values as 1.45 eV/atom and 7 μ_B respectively

(see Table 1) By introducing up to two Pd dopant atoms into the cluster, the overall structural motif is not changed significantly (see Figure 1). For the PdCo_2 cluster, an isosceles triangle with total magnetic moment 5 μ_B is found to be the GM with BE 1.62 eV/atom. The BE value is consistent with the result in Ref.³⁸. When doped with two Pd atoms, the isosceles triangle remains the GM while the pure Pd trimer has a D_{3h} equilateral triangle structure, though the calculated BE of this structure (1.37 eV/atom) is inconsistent with DFT results reported by other researchers.^{64, 65}

Table 1 Physicochemical Properties of PdCo nanoalloys ^a

| Clusters | SM | SYM | E _b | E _m | Clusters | SM | SYM | E _b | E _m |
|---------------------------------|----|-----------------|---------------------------|----------------|---------------------------------|----|-----------------|---------------------------|----------------|
| Co ₃ | 7 | C _{2v} | 1.45 | - | Co ₆ | 14 | O _h | 2.41 2.47 ^c | - |
| PdCo ₂ | 4 | C _{2v} | 1.62 | 0.60 | PdCo ₅ | 13 | C _{4v} | 2.38 | 0.16 |
| Pd ₂ Co | 3 | C _{2v} | 1.70 | 0.93 | Pd ₂ Co ₄ | 10 | C _{2v} | 2.35 | 0.32 |
| Pd ₃ | 2 | D _{3h} | 1.37 1.24 ^b | - | Pd ₃ Co ₃ | 7 | C ₁ | 2.30 | 0.38 |
| Co ₄ | 10 | C _{2v} | 1.79 | - | Pd ₄ Co ₂ | 6 | C _{2v} | 2.27 | 0.55 |
| PdCo ₃ | 7 | C _s | 1.86 | 0.29 | Pd ₅ Co | 3 | C _{4v} | 2.21 | 0.51 |
| Pd ₂ Co ₂ | 4 | C _{2v} | 1.93 | 0.57 | Pd ₆ | 2 | D _{4h} | 2.06 1.88 ^b | - |
| Pd ₃ Co | 3 | C _{3v} | 1.97 | 0.73 | Co ₇ | 15 | C ₁ | 2.51 2.45 ^c | 0.00 |
| Pd ₄ | 2 | D _{2d} | 1.78 1.63 ^b | - | Pd ₁ Co ₆ | 14 | C ₃ | 2.54 | 0.64 |
| Co ₅ | 11 | C _s | 2.10 2.29 ^c | - | Pd ₂ Co ₅ | 13 | C _s | 2.52 | 0.90 |
| PdCo ₄ | 8 | C _{3v} | 2.14 | 0.36 | Pd ₃ Co ₄ | 10 | C _{2v} | 2.50 | 1.13 |
| Pd ₂ Co ₃ | 7 | C _{2v} | 2.17 | 0.70 | Pd ₄ Co ₃ | 7 | C ₁ | 2.42 | 0.98 |
| Pd ₃ Co ₂ | 4 | C _{2v} | 2.15 | 0.82 | Pd ₅ Co ₂ | 6 | C _s | 2.36 | 1.00 |
| Pd ₄ Co | 3 | C _{2v} | 2.10 | 0.76 | Pd ₆ Co ₁ | 3 | C _s | 2.25 | 0.68 |
| Pd ₅ | 2 | C _{4v} | 1.91 1.74 ^b | - | Pd ₇ | 2 | D ₅ | 2.10 1.90 ^b | 0.00 |

^a SM, Spin Moment in μ_B ; SYM, Point Group Symmetry; E_b, Binding Energy in eV/atom; E_m, Mixing Energy in eV
^b Ref¹; ^c Ref²

The most stable isomer of Co₄ is non-planar butterfly-like structure with C_{2v} symmetry (as the two diagonals are unequal in length). It has a BE of 1.79 eV/atom and a spin moment of 10 μ_B , as reported by Sebetci,⁵⁹ Fan et al.,² and Ma et al.⁶⁶ but in contradiction to the findings of Datta et al.⁶⁷ Experimentally, Jalink et al.⁶⁸ identified Co₄ as having a planar rhombus structure based on a gas phase vibrational spectroscopy.

Replacing one of the Co atoms by Pd, results in a non-planar butterfly as the lowest energy morphology and the symmetry is reduced to C_s, which removes orbital degeneracy, increases the d electron bandwidth and reduces the local magnetic moment of Co. As Pd doping increases, the BE of Pd₂Co₂ increases to 1.93 eV per atom in the quintet magnetic state and the structure changes to a C_{2v} tetrahedron, where all faces

Table 2 Physicochemical Properties of PdCo nanoalloys ^a

| Clusters | HLG | DM | FRQ | Clusters | HLG | DM | FRQ |
|---------------------------------|------|------|---------------|---------------------------------|------|------|---------------|
| Co ₃ | 0.68 | 0.40 | 96, 231, 319 | Co ₆ | 0.32 | 0.00 | 120, 269, 344 |
| PdCo ₂ | 0.71 | 1.16 | 170, 170, 296 | PdCo ₅ | 0.29 | 0.52 | 81, 261, 318. |
| Pd ₂ Co | 0.76 | 0.75 | 148, 148, 286 | Pd ₂ Co ₄ | 0.50 | 0.25 | 78, 154, 301 |
| Pd ₃ | 0.01 | 0.13 | 159, 166, 237 | Pd ₃ Co ₃ | 0.37 | 0.72 | 66, 151, 287 |
| Co ₄ | 0.61 | 0.05 | 66, 233, 267 | Pd ₄ Co ₂ | 0.32 | 0.05 | 54, 257, 290 |
| PdCo ₃ | 0.59 | 1.32 | 46, 111, 290 | Pd ₅ Co | 0.54 | 0.74 | 83, 256, 256 |
| Pd ₂ Co ₂ | 0.51 | 1.35 | 111, 176, 289 | Pd ₆ | 0.08 | 0.00 | 99, 184, 220 |
| Pd ₃ Co | 0.48 | 0.84 | 95, 156, 285 | Co ₇ | 0.18 | 0.31 | 66, 253, 304 |
| Pd ₄ | 0.01 | 0.00 | 111, 184, 239 | Pd ₁ Co ₆ | 0.37 | 0.85 | 60, 254, 295 |
| Co ₅ | 0.52 | 0.53 | 74, 191, 327 | Pd ₂ Co ₅ | 0.33 | 0.64 | 85, 248, 299 |
| PdCo ₄ | 0.43 | 0.87 | 115, 192, 328 | Pd ₃ Co ₄ | 0.58 | 0.61 | 64, 151, 278 |
| Pd ₂ Co ₃ | 0.59 | 0.15 | 82, 256, 303 | Pd ₄ Co ₃ | 0.33 | 0.34 | 75, 257, 282 |
| Pd ₃ Co ₂ | 0.81 | 0.89 | 83, 173, 288 | Pd ₅ Co ₂ | 0.21 | 0.75 | 60, 122, 272. |
| Pd ₄ Co | 0.55 | 0.67 | 50, 238, 261 | Pd ₆ Co ₁ | 0.33 | 0.39 | 29, 226, 234 |
| Pd ₅ | 0.20 | 0.31 | 53, 195, 221 | Pd ₇ | 0.14 | 0.00 | 56, 167, 207 |

^a HLG, HOMO-LUMO Gap in eV, DM; Electric Dipole Moment in Debyes; FRQ, lowest, weighted, highest vibrational frequencies respectively in cm^{-1}




Figure 5 Binding Energies and Spin Moments of PdCo nanoalloys

are isosceles triangles. The structure of Pd₃Co is a C_{3v} tetrahedron. A triplet spin multiplicity with D_{2d} symmetry is found to be the GM structure of Pd₄, which has a D_{2d} distorted-tetrahedral structure. This agrees with the results of Zanti et al.⁶⁹ and Begum et al.⁷⁰ For the Co pentamer, a distorted trigonal bipyramidal (TBP) structure has been found as the GM energy structure with a spin magnetic moment of 11 μ_B. There is no consensus on the structure of Co₅ in the literature. Pereiro et al.,⁶⁰ Datta et al.⁶¹ and Castro et al.⁵⁸ have identified the ground state structure as the TBP configuration while the C_{4v} pyramidal structure has been proposed by Fan et al.² and Ma et al.⁶⁶

The Pd₂Co₃, Pd₃Co₂ and Pd₄Co clusters all have C_{2v} TBP geometries, with spin moments of 7, 4 and 3 μ_B, respectively, while the PdCo₄ cluster has a C_{3v} TBP structure and a spin moment of 8 μ_B. In Pd₄Co and Pd₃Co₂, Co atoms preferably occupy the higher connectivity equatorial positions in the TBP, which maximise the number of Co-Co and Co-Pd bonds (both of which are stronger than Pd-Pd bonds). The preferential doping of Pd atoms into the lower-connected apical sites in PdCo₄ and Pd₂Co₃ is consistent with this.

In the case of the pure Pd pentamer, the lowest energy morphology changes to square a pyramid with C_{4v} symmetry and a triplet magnetic state. This structure agrees with the work of Cantera and coworkers,³⁸ and Zanti and coworkers⁶⁹ while Jerzy and coworkers⁷¹ identified the GM as a TBP.

For pure Co₆ the GM structure is a regular octahedron with O_h symmetry and a magnetic moment of 14 μ_B, which is entirely consistent with previous results.^{61,66,72} On replacing one Co by Pd, the overall octahedral structure is retained. The GM structure has C_{4v} symmetry and a total magnetic moment of 13 μ_B. When Pd atom doping continues, a capped TBP (or bicapped tetrahedron) is found to be GM for Pd₂Co₄ (C_{2v}), Pd₃Co₃ (C₁) and Pd₄Co₂ (C_{2v}). As for the pentamers, the Co atoms preferentially occupy the higher coordinate sites and the Pd atoms occupy the low coordinate sites, leading to more Co-Co (and Co-Pd) and fewer Pd-Pd bonds, again correlating with bond strengths and bulk cohesive energies.⁷³ The overall effect is for core segregation of Co and surface segregation of

Pd, with this core-shell type of segregation (which is related to the lower surface energy of Pd compared to Co, since the element having smaller surface energy and cohesive energy favours occupying the surface to minimise the total energy⁷⁴) also predicted for larger PdCo clusters.⁷⁵ Jassens et al.⁷⁶ found that with fewer than 50 atoms, for Ag_nCo_m with n >> m the cobalt dopants adsorb highly coordinated sites and are strongly bound, for clusters with m >> n the silver atoms are poorly coordinated surface atoms and are loosely bound

The GM structure of Pd₅Co is an octahedron (C_{4v} symmetry) in the quartet magnetic state. The BE of Pd₅Co has been calculated as 2.21 eV/atom. It should be noted that the dominant growth patterns for the studied bimetallic nanoalloys generally keep similar frameworks to those of the pure Co clusters. Pd₆ has a D_{4h} tetragonally distorted octahedral geometry. This is consistent with previous DFT studies.^{65,77,78}

The most stable isomer of Co₇ is a capped octahedron-like structure. It has a BE of 2.51 eV/atom while Datta et al.⁶⁷ calculated the BE as 2.97 eV/atom. The structure has a spin moment of 15, which is consistent with the experimental result (2.36 ± 0.25 μ_B/atom⁷⁹). For the PdCo₆ structure, the overall capped octahedron-like structure is retained. The GM structure has C₃ symmetry and a spin moment of 14 μ_B. A low symmetry C_s isomer, with a spin moment of 13 μ_B, is found to be the GM for Pd₂Co₅. On further Pd doping, the structural motif changes to a pentagonal pyramid for Pd₃Co₄. The structure of Pd₄Co₃ has C₁ symmetry and a spin moment of 7 μ_B. The BE of Pd₄Co₃ has been calculated as 2.42 eV. For the Pd₅Co₂ structure, the structural motif is retained. The spin moment of Pd₅Co₂ is calculated as 6 μ_B and it has C_s symmetry. On further Pd doping, the structural motif changes to the pentagonal bipyramid. The pentagonal bipyramid GM structure for Pd₇ is consistent with the findings of Kalita and Deka.⁸⁰ The BE of this structure in the doublet state is calculated as 2.10 eV/atom, which is consistent with the result of Ref³⁸.

The magnetic spin moments of the GM structures of PdCo clusters within the studied size range are shown in Figure 5. The magnetic moments of bimetallic PdCo clusters exhibits a zigzag pattern upon successive addition of Pd atoms. It should be noted that all pure Pd clusters in this study have triplet magnetic ground states, which is consistent with the results of Ref.⁶⁹ since the Pd has a closed shell electronic configuration (4d¹⁰). To make a stable a metal-metal bond, some 4d electronic density needs to be promoted into the lowest unoccupied orbitals, in this case 5s. Occupying this orbital leads to triplet state. As expected, Pd atoms have a quenching effect on the magnetism of bimetallic PdCo nanoalloys, so successive Pd doping of a Co cluster leads to a decrease of the spin moment of the ground state structure. We could not find any clear size dependence, but for CoMn clusters, based on Stern–Gerlach (SG) experiments, Yin et al.⁸¹ have concluded that the magnetic enhancement of Co_nMn_n (n ≤ 60, m ≤ n/3) is independent of the cluster size and composition. However, the study conducted by Zanti and coworkers showed that clusters enriched in palladium atoms have spin multiplicities that




Figure 6 Second Finite Difference Energies and Mixing Energies of 5- and 6-atom PdCo nanoalloys.

increase with the cluster size while clusters enriched in gold atoms maintain the lowest possible spin multiplicity for the structure.⁶⁹

Nanoparticle stability can be analyzed in various ways, the most common being the computation of the energy released during the growth of metal nanoparticles starting from isolated atoms, corresponding to the BE. The dependence of the BE on the composition of PdCo nanoalloys within the studied range is shown in Figure 5. As expected, increasing nuclearity makes the BE more exothermic. This is because during the growth process the number of nearest neighbors increases, leading to a larger number of interactions per atom but the proportional gain gets smaller as the cluster gets larger, eventually approaching the bulk cohesive energy asymptotically. For bimetallic PdCo clusters, the BE is expected to lie between those of pure Pd and Co clusters. However, up to size 5, the BEs are (as seen in Table I) larger than both the pure Pd and Co clusters, while for size 6 and 7, the BE values usually lie between those of the pure Pd and Co nanoparticles, as expected. Bakken and Swang⁸² have found that for small Cobalt clusters, substituting rhenium stabilizes the clusters.

For the pentamer PdCo nanoalloys, Pd₄Co has much higher $D_{n,m}$ energy than Pd₃Co₂. This shows that it is more stable than the latter species but the result is not consistent with the mixing energy result. For the hexamer structures, the dip is seen at Pd₃Co₃ in Figure 6. This species is expected to be less abundant in mass spectra than the other corresponding clusters.

The mixing energy E_m can be used to evaluate the effect of mixing in a system. The evolution of the mixing energy with composition is shown for $n+m=5,6$ and 7 in Figure 6. The more positive values of E_m show a stronger mixing tendency. The maximum value is seen for Pd₂Co in Table I. This is consistent with the BE result. Comparing the different nuclearities, it should be noted that the mixing energy of bimetallic Pd_nCo_m nanoparticles is independent of the cluster size. However, up to 6 atoms, the values of mixing energy of the studied nanoalloys are proportional to the proportion of Pd atoms in the cluster, with the exception of Pd₄Co and Pd₅Co.

A large HOMO-LUMO gap (HLG) is generally considered as a significant requirement for chemical stability since HLG indicates the ability of electrons to bounce from HOMO to LUMO and governs a molecule to involve in chemical reactions to some degree. Pd₃Co₂ (0.81 eV) has the highest HLG among the species studied in this work. Thus, one can expect high chemical stability for this cluster. It can be noted that pure Pd clusters generally have higher chemical activity than those pure cobalt clusters. Furthermore, among the studied species, Pd-rich clusters are expected to have high chemical activity due to their low HLG values (see Table 2).

Electric dipole moment calculations have been performed to enable predictions to be made for future electron beam deflection experiments, which is one of few experimental methods for the investigation of small neutral clusters. The dipole moments are small due to the low charge distribution within the cluster with the exception of PdCo₂, PdCo₃ and Pd₂Co₂, which have clearly distinguishable dipole moments. These clusters should be easily discriminated by experiment. The vibrational frequencies lie between 29 and 344 cm⁻¹ and show no clear dependence on cluster size and composition. All vibrational frequencies, projected infra red intensities Mulliken charge analysis, electric field gradients, dipole, quadrupole and octupole moments are listed as supplementary data.

D. Conclusions

We have performed a computational study of PdCo nanoalloys ranging from 3 to 7 atoms. The structural, electronic and magnetic properties of bimetallic PdCo nanoalloys have been studied within the framework of the GA-DFT approach that performs an unbiased global optimisation search for the lowest energy isomer, for each size and composition, at the DFT level.

The calculations reveal that Pd atoms segregate to the peripheral positions of the clusters to enable maximisation of the stronger Co-Co and Co-Pd bonds and also the lower surface energy of Pd. Up to size 5, the doped nanoalloys possess higher binding energies indicating that the bimetallic species possess enhanced chemical stability than their pure counterparts. Pd atoms have a quenching effect on the magnetism of bimetallic PdCo nanoalloys, so successive Pd doping of a Co cluster leads to a decrease of the spin moment of the ground state structure. For the size dependence of magnetic moment we could not find any clear relation. It can be noted that pure Pd clusters generally have higher chemical activity than those pure cobalt clusters. Furthermore, among the studied species, Pd-rich clusters are expected to have high chemical activity due to their low HLG values. The dipole moments are small due to the low charge distribution within the cluster with the exception of PdCo₂, PdCo₃ and Pd₂Co₂, which have clearly distinguishable dipole moments.

In the future, the study we have carried out will be extended to larger bimetallic PdCo nanoalloys, where the dependence of

chemical ordering and structure on the composition will be analyzed by using the Pool-BCGA code^{83,84}, which is a new parallel implementation of the code, which reduces computational costs significantly for larger clusters.

Acknowledgements

The calculations reported here have been performed on the following HPC facilities: The University of Birmingham BlueBEAR facility (See <http://www.bear.bham.ac.uk/bluebear> for a description of the Blue-BEAR HPC facility), the MidPlus Regional Centre of Excellence for Computational Science, Engineering and Mathematics, funded under EPSRC grant EP/K000128/1 (RLJ); and via membership of the UK's HPC Materials Chemistry Consortium, which is funded by EPSRC (EP/L000202), this work made use of the facilities of ARCHER, the UK's national high-performance computing service, which is funded by the Office of Science and Technology through EPSRC's High End Computing Programme. MA acknowledges financial support by The Scientific and Technological Research Council of Turkey (TUBITAK) under the program 2214-A.

References

1. P. Nava, Density Functional Theory Calculations on Palladium Clusters and on an AgInS Semiconductor Compound, Cuvillier Verlag, 2005.
2. H.-J. Fan, C.-W. Liu and M.-S. Liao, Chemical physics letters, 1997, 273, 353-359.
3. S. Heiles, A. J. Logsdail, R. Schafer and R. L. Johnston, Nanoscale, 2012, 4, 1109-1115.
4. V. Bonačić-Koutecký, J. Burda, R. Mitrić, M. Ge, G. Zampella and P. Fantucci, The Journal of Chemical Physics, 2002, 117, 3120.
5. H. M. Lee, M. Ge, B. R. Sahu, P. Tarakeshwar and K. S. Kim, The Journal of Physical Chemistry B, 2003, 107, 9994-10005.
6. G. F. Zhao and Z. Zeng, The Journal of Chemical Physics, 2006, 125, 014303.
7. J. M. Montejano-Carrizales and J. L. Morán-López, Surface Science, 1990, 239, 169-177.
8. M. Polak and L. Rubinovich, Surface Science, 2005, 584, 41-48.
9. D. J. Wales and J. P. K. Doye, The Journal of Physical Chemistry A, 1997, 101, 5111-5116.
10. R. L. Johnston, Dalton Transactions, 2003, 4193-4207.
11. A. Sutton and J. Chen, Philosophical Magazine Letters, 1990, 61, 139-146.
12. J. N. Murrell and R. E. Mottram, Molecular physics, 1990, 69, 571-585.
13. B. C. Curley, R. L. Johnston, N. P. Young, Z. Li, M. Di Vece, R. E. Palmer and A. L. Bleloch, The Journal of Physical Chemistry C, 2007, 111, 17846-17851.
14. R. Ferrando, A. Fortunelli and R. L. Johnston, Physical Chemistry Chemical Physics, 2008, 10, 640-649.
15. O. Kostko, B. Huber, M. Moseler and B. von Issendorff, Physical review letters, 2007, 98, 043401.
16. F. Chen and R. L. Johnston, Acta Materialia, 2008, 56, 2374-2380.
17. F. Y. Chen and R. L. Johnston, Applied Physics Letters, 2007, 90, 3123.
18. J. Jellinek, Faraday Discussions, 2008, 138, 11-35.
19. L. B. Vilhelmsen and B. Hammer, The Journal of Chemical Physics, 2014, 141, 044711.
20. A. Sebetci, Computational Materials Science, 2013, 78, 9-11.
21. A. Sebetci, Computational Materials Science, 2012, 58, 77-86.
22. J. B. A. Davis, S. L. Horswell and R. L. Johnston, The Journal of Physical Chemistry A, 2013, 118, 208-214.
23. I. Demiroglu, D. Stradi, F. Illas and S. T. Bromley, Journal of Physics: Condensed Matter, 2011, 23, 334215.
24. M. Aslan, Z. Öztürk and A. Sebetci, Journal of Cluster Science, 2014, 25, 1187-1201.
25. J. B. A. Davis, R. L. Johnston, L. Rubinovich and M. Polak, The Journal of Chemical Physics, 2014, 141, 224307.
26. C. Lueng, P. J. Metaxas and M. Kostylev, 2014.
27. A. Prasad and P. J. Cascone, Journal, 2014.
28. S. Ramaprabhu, M. Baro, P. Nayak and T. Theres Baby, Journal, 2014.
29. S. Akbayrak, M. Kaya, M. Volkan and S. Özkar, Applied Catalysis B: Environmental, 2014, 147, 387-393.
30. K. Mech, G. Boczkal, P. Pařka, P. Zabiński and R. Kowalik, Journal of Solid State Electrochemistry, 2014, 18, 3121-3127.
31. B. Li, X. Liu, M. Zhu, Z. Wang, A. Adeyeye and W. Choi, Journal of Nanoscience and Nanotechnology, 2015, 15, 4332-4338.
32. H. Yildirim, A. Kara and T. S. Rahman, The Journal of Physical Chemistry C, 2012, 116, 281-291.
33. H. Arslan, International Journal of Modern Physics C, 2008, 19, 1243-1255.
34. R. Ferrando, J. Jellinek and R. L. Johnston, Chemical Reviews, 2008, 108, 845-910.
35. D. T. Tran and R. L. Johnston, Proceedings of the Royal Society A: Mathematical, Physical and Engineering Science, 2011, 467, 2004-2019.
36. S. Heiles and R. L. Johnston, International Journal of Quantum Chemistry, 2013, 113, 2091-2109.
37. F. Pittaway, L. O. Paz-Borbón, R. L. Johnston, H. Arslan, R. Ferrando, C. Mottet, G. Barcaro and A. Fortunelli, The Journal of Physical Chemistry C, 2009, 113, 9141-9152.
38. H. Cantera-López, J. M. Montejano-Carrizales, F. Aguilera-Granja and J. L. Morán-López, The European Physical Journal D, 2010, 57, 61-69.
39. S. Bischoff, A. Weigt, K. Fujimoto and B. Lücke, Journal of Molecular Catalysis A: Chemical, 1995, 95, 259-268.
40. M. Heemeier, A. F. Carlsson, M. Naschitzki, M. Schmal, M. Bäumer and H.-J. Freund, Angewandte Chemie International Edition, 2002, 41, 4073-4076.
41. F. B. Noronha, M. Schmal, C. Nicot, B. Moraweck and R. Frety, Journal of Catalysis, 1997, 168, 42-50.
42. P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G. L. Chiarotti, M. Cococcioni and I. Dabo, Journal of Physics: Condensed Matter, 2009, 21, 395502.
43. D. Deaven and K. Ho, Physical review letters, 1995, 75, 288.
44. A. M. Rappe, K. M. Rabe, E. Kaxiras and J. Joannopoulos, Physical Review B, 1990, 41, 1227.
45. P. E. Blöchl, Physical Review B, 1994, 50, 17953.
46. J. P. Perdew, K. Burke and M. Ernzerhof, Physical review letters, 1996, 77, 3865.
47. M. Methfessel and A. Paxton, Physical Review B, 1989, 40, 3616.
48. M. Valiev, E. J. Bylaska, N. Govind, K. Kowalski, T. P. Straatsma, H. J. Van Dam, D. Wang, J. Nieplocha, E. Apra and T. L. Windus, Computer Physics Communications, 2010, 181, 1477-1489.
49. P. J. Hay and W. R. Wadt, The Journal of Chemical Physics, 1985, 82, 270-283.
50. W. R. Wadt and P. J. Hay, The Journal of Chemical Physics, 1985, 82, 284-298.
51. A. Kant and B. Strauss, The Journal of Chemical Physics, 1964, 41, 3806-3808.
52. L. M. Russon, S. A. Heidecke, M. K. Birke, J. Conceicao, M. D. Morse and P. Armentrout, The Journal of chemical physics, 1994, 100, 4747-4755.
53. K. A. Gingerich, 1980.

54. S. Taylor, E. M. Spain and M. D. Morse, *The Journal of chemical physics*, 1990, 92, 2698-2709.
55. K. Koyasu, M. Mitsui, A. Nakajima and K. Kaya, *Chemical physics letters*, 2002, 358, 224-230.
56. B. Sahu, G. Maofa and L. Kleinman, *Physical Review B*, 2003, 67, 115420.
57. C. Jamorski, A. Martinez, M. Castro and D. R. Salahub, *Physical Review B*, 1997, 55, 10905.
58. M. Castro, C. Jamorski and D. R. Salahub, *Chemical physics letters*, 1997, 271, 133-142.
59. A. Sebetci, *Chemical Physics*, 2008, 354, 196-201.
60. M. Pereiro, D. Baldomir, M. Iglesias, C. Rosales and M. Castro, *International Journal of Quantum Chemistry*, 2001, 81, 422-430.
61. S. Datta, M. Kabir, S. Ganguly, B. Sanyal, T. Saha-Dasgupta and A. Mookerjee, *Physical Review B*, 2007, 76, 014429.
62. R. Van Zee, Y. Hamrick, S. Li and W. Weltner, *Chemical physics letters*, 1992, 195, 214-220.
63. Q. M. Ma, Z. Xie, J. Wang, Y. Liu and Y. C. Li, *Physics Letters, Section A: General, Atomic and Solid State Physics*, 2006, 358, 289-296.
64. G. Qiu, M. Wang, G. Wang, X. Diao, D. Zhao, Z. Du and Y. Li, *Journal of Molecular Structure: THEOCHEM*, 2008, 861, 131-136.
65. M. Moseler, H. Häkkinen, R. N. Barnett and U. Landman, *Physical Review Letters*, 2001, 86, 2545-2548.
66. Q.-M. Ma, Z. Xie, J. Wang, Y. Liu and Y.-C. Li, *Physics Letters A*, 2006, 358, 289-296.
67. S. Datta, M. Kabir, T. Saha-Dasgupta and A. Mookerjee, *Physical Review B*, 2009, 80, 085418.
68. J. Jalink, 2014.
69. G. Zanti and D. Peeters, *European Journal of Inorganic Chemistry*, 2009, 2009, 3904-3911.
70. P. Begum, D. Bhattacharjee, B. K. Mishra and R. C. Deka, *Theoretical Chemistry Accounts*, 2014, 133, 1-11.
71. J. Moc, D. G. Musaev and K. Morokuma, *The Journal of Physical Chemistry A*, 2003, 107, 4929-4939.
72. J. Rodríguez-López, F. Aguilera-Granja, K. Michaelian and A. Vega, *Physical Review B*, 2003, 67, 174413.
73. C. Kittel, *Introduction to solid state physics*, Wiley, 2005.
74. Q. L. Lu, L. Z. Zhu, L. Ma and G. H. Wang, *Physics Letters A*, 2006, 350, 258-262.
75. H. Arslan, A. K. Garip and R. L. Johnston, *Physical Chemistry Chemical Physics*, 2015, DOI: 10.1039/C5CP01029B.
76. E. Janssens, T. Van Hoof, N. Veldeman, S. Neukermans, M. Hou and P. Lievens, *International Journal of Mass Spectrometry*, 2006, 252, 38-46.
77. P. Nava, M. Sierka and R. Ahlrichs, *Physical Chemistry Chemical Physics*, 2003, 5, 3372-3381.
78. C. Luo, C. Zhou, J. Wu, T. Dhilip Kumar, N. Balakrishnan, R. C. Forrey and H. Cheng, *International Journal of Quantum Chemistry*, 2007, 107, 1632-1641.
79. M. B. Knickelbein, *The Journal of chemical physics*, 2006, 125, 44308-44308.
80. B. Kalita and R. C. Deka, *Journal of Chemical Physics*, 2007, 127, 244306-244306.
81. S. Yin, R. Moro, X. Xu and W. A. de Heer, *Physical Review Letters*, 2007, 98, 113401.
82. V. Bakken and O. Swang, *The Journal of chemical physics*, 2008, 128, 084712.
83. A. Shayeghi, D. Götz, J. Davis, R. Schaefer and R. L. Johnston, *Physical Chemistry Chemical Physics*, 2015, 17, 2104-2112.
84. J. B. Davis, A. Shayeghi, S. L. Horswell and R. L. Johnston, *Nanoscale*, 2015, 7, 14032-14038.