

PCCCP

Physical Chemistry Chemical Physics

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: A. M. Reider, M. Szalay, J. Reichegger, J. Barabás, M. Schmidt, M. Kappe, T. Höltzl, P. Scheier and O. Lushchikova, *Phys. Chem. Chem. Phys.*, 2024, DOI: 10.1039/D4CP01797H.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

The data discussed in the manuscript is available at: [10.5281/zenodo.11578007](https://zenodo.org/record/11578007). This repository contains the raw data for the spectroscopic measurements of $\text{Cu}_n[\text{CO}_2]^+$ ($n = 1-10$) and $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ ($n = 1-7$) complexes, along with laser power scans. An Excel file is included, summarizing the measurements and the most important experimental parameters. Additionally, we provide the Python script used to extract the IR spectra for the individual cluster sizes, and the Origin file containing the data after laser power corrections, averaging, and the figures used in the original manuscript and the electronic supplementary information.

View Article Online

DOI: 10.1039/D4CP01797H



ARTICLE

Spectroscopic Investigation of Size-Dependent CO₂ Binding on Cationic Copper Clusters: Analysis of the CO₂ Asymmetric Stretch

A.M. Reider¹, M. Szalay^{2,3}, J. Reichegger¹, J. Barabás^{2,4}, M. Schmidt¹, M. Kappe¹, T. Höltzl^{2,3*}, P. Scheier¹, O.V. Lushchikova^{1*}Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Photofragmentation spectroscopy, combined with quantum chemical computations, was employed to investigate the position of the asymmetric CO₂ stretch in cold, He-tagged Cu_n[CO₂]⁺ ($n = 1-10$) and Cu_n[CO₂][H₂O]⁺ ($n = 1-7$) complexes. A blue shift in the band position was observed compared to the free CO₂ molecule for Cu_n[CO₂]⁺ complexes. Furthermore, this shift was found to exhibit a notable dependence on cluster size, progressively redshifting with increasing cluster size. The computations revealed that the CO₂ binding energy is the highest for the Cu⁺ and continuously decreases with increasing cluster size. This dependency could be explained by highlighting the role of polarization in electronic structure, according to energy decomposition analysis. The introduction of water to this complex amplified the redshift of the asymmetric stretch, showing a similar dependency on the cluster size as observed for Cu_n[CO₂]⁺ complexes.

Introduction

The increasing concentration of atmospheric carbon dioxide has become a pressing global concern due to its implications for climate change and environmental sustainability. However, its conversion into valuable chemicals remains a challenging process characterized by low CO₂ conversion rates, poor selectivity, and high energy costs.^{1,2}

One of the most promising pathways for CO₂ utilization is its conversion to methanol. Behrens et al. demonstrated that Cu nanoparticles serve as the active sites in the widely used industrial Cu/ZnO/Al₂O₃ catalyst, which has been on the market for over six decades.³ Recent reviews corroborate that Cu-based catalysts continue to show the greatest promise.^{4,5} The emergence of small sub-nanometer-sized metal clusters exhibit a high potential in sustainable CO₂ conversion reactions due to their high number of uncoordinated sites and distinctive electronic and geometric properties, which can facilitate the activation and transformation of CO₂ molecules.⁶ Over the past decade, copper clusters have attracted considerable attention for their potential to convert CO₂ to methanol at lower temperatures and pressures compared to conventional catalysts.^{7,8,9,10,11,12}

It is widely acknowledged that the size of a cluster can significantly influence its catalytic properties, potentially enhancing the activity of the catalyst. The active sites of

catalysts can be imitated by gas-phase clusters to investigate the exact reaction mechanisms to obtain detailed knowledge of this phenomenon.¹³ Gas-phase studies offer the advantage of examining the interaction between CO₂ and a cluster under well-controlled conditions. Over the years, substantial knowledge has been accumulated regarding the interaction between gas-phase clusters and CO₂, as comprehensively summarized by H. Schwarz.¹⁴

Spectroscopic studies, in particular, provide detailed information about the vibrational properties of adsorbed molecules, shedding light on the nature of the adsorption process and the strength of the metal-ligand bonds. Several research groups have employed IR photodissociation spectroscopy techniques, such as eliminating one or more intact CO₂ molecules or employing Ar tagging for tightly bound complexes. Notably, Weber^{15,16,17,18,19,20,21,22,23,24,25} and his co-workers extensively explored the interaction of single metal anions with multiple CO₂ molecules, while the groups of Duncan^{26,27,28,29,30,31,32}, Mackenzie^{33,34}, and Jiang^{35,36,37,38} focused on cations and their oxides. Their works cover the interactions of CO₂ with most transition metal ions and beyond. Recently, the group of Beyer has published spectroscopic studies on the activation of CO₂ by hydrated metal cations (Mg⁺ and Co⁺)^{39,40} and anions (NbO₃)⁴¹ solvated in water, revealing that higher water load can lead to the activation of CO₂ inducing charge transfer from the metal center to CO₂.

Other spectroscopic investigations focusing mainly on the interactions of metal clusters with only a few CO₂ molecules attached employed infrared multiphoton dissociation (IRMPD) spectroscopy with the free-electron lasers (FEL) at the Fritz Haber Institute (FHI) in Berlin, Germany, and at FELIX in Nijmegen, the Netherlands. While at the FHI the focus was more on anionic clusters (Pt_n⁻ and Co_n⁻)^{42,43}, the research at FELIX was mostly leaning towards cationic clusters (Cu_n⁺ and Mg_nO_m⁺)^{44,45},

¹ Institut für Ionenphysik und Angewandte Physik, Universität Innsbruck, Technikerstraße 25, Innsbruck 6020, Austria.

² HUN-REN-BME Computation Driven Chemistry Research Group, Department of Inorganic and Analytical Chemistry, Budapest University of Technology and Economics, Muegyetem rkp. 3, Budapest 1111, Hungary

³ Furukawa Electric Institute of Technology, Késmárk Utca 28/A, Budapest 1158, Hungary

⁴ Present address: Gedeon Richter Plc., Spectroscopic Research Department, 19-21 Gyömrői út, Budapest H-1103, Hungary

*Electronic Supplementary Information (ESI) available: Laser power scan, benchmarking of different harmonic and anharmonic computational methods, correlations between binding energies and the frequencies of the CO₂ asymmetric stretch vibrations, charges of the carbon and oxygen atoms. See DOI: 10.1039/x0xx00000x



with the exception of CCu_n .⁴⁶ In addition, the activation of H_2O and CO_2 by NbO_3^- clusters was investigated at FELIX.⁴¹ Remarkably, all investigated anionic metal clusters exhibited pronounced size-dependent activation and dissociation of CO_2 .^{42, 43, 46}

While it is evident that anions exhibit greater activity in CO_2 dissociation due to their ability to donate an electron to the anti-bonding orbitals of CO_2 , surface studies highlight the crucial role of Cu particles with a positive partial charge in methanol synthesis.^{11, 47, 48} These particles stabilize reaction intermediates, promote hydrogenation reactions by facilitating the adsorption and activation of hydrogen molecules, and exhibit enhanced catalytic activity. This underscores the importance of understanding the reaction mechanism over positively charged metal particles. The research of Bakker's group, conducted at FELIX, delved into the elementary steps of methanol formation utilizing cationic Cu clusters, including hydrogenation of the clusters⁴⁹ and CO_2 and H_2 co-adsorption⁴⁴. Those studies revealed that some cluster sizes have the capability to dissociate H_2 , and the co-adsorption studies suggest the formation of intermediates leading to the subsequent formation of formate — a critical step in methanol synthesis. Intriguingly, the reaction of bare cationic Cu clusters with CO_2 revealed that clusters ranging from 7 to 25 Cu atoms physisorbed CO_2 uniformly in monodentate ($\eta^1\text{-O}$) fashion, regardless of the cluster size, as evidenced by absorption bands measured close to those of free CO_2 and calculations.⁴⁴

The measurements described above do not really capture the strongest fundamental vibration of CO_2 , the asymmetric stretch (ν_3), since they were limited by the frequency capabilities of the FEL for intracavity experiments (FELICE) used for those studies, which is 100–2100 cm^{-1} . The asymmetric stretch is only captured by the second harmonics of IR-light at 1185 cm^{-1} , halving the frequency, and consequently reducing intensity to approximately 1%.⁴⁴

In this work we employ photodissociation spectroscopy of He-tagged $\text{Cu}_n[\text{CO}_2]_m^+$ complexes, facilitated by a table-top OPO laser, to investigate the strongest vibration of CO_2 , the asymmetric stretch. He-tagged ions are generated and extracted from multiply-charged superfluid He nanodroplets (HNDs).⁵⁰ Narrower spectral bandwidth of the OPO laser compared to that of FELICE, lower dissociation energy of He compared to CO_2 (<0.04 eV vs >0.26 eV) and low temperature of the formed complexes (<1 K) contribute to the narrower bandwidth, making it possible to investigate the exact position of the ν_3 band, which is expected around 2350 cm^{-1} , according to both studies at FELIX⁴⁴ and data obtained for free CO_2 .⁵¹

Previously, HNDs were already utilized to study the reactions of neutral metal- CO_2 complexes. This method employs optically selected mass spectrometry with a narrow bandwidth laser, resulting in high-resolution IR spectra. It was observed that both studied metal atoms, Al and Mn, form two isomers with CO_2 . This conclusion was based on the presence of two bands around 2280 cm^{-1} , assigned to the different asymmetric stretches of different isomers. The CO_2 was found bound to the metal atom in either a monodentate or T-shaped configuration.⁵²

By employing IR spectroscopy of He-tagged ions coupled with theoretical calculations, we systematically investigate the influence of cluster size and hydration on the binding motifs of CO_2 characterized by the changes in the asymmetric stretch mode. This approach allows discerning size-dependent trends in CO_2 adsorption on copper clusters, the effect of the additional water attachment, and correlating these to the changes in the binding energies. It sheds light on the underlying mechanisms governing the interaction between CO_2 molecules and metal clusters.

The narrow bandwidth allows for tracking the shift of the ν_3 band as a function of cluster size, which had not been observed previously. In earlier measurements, all investigated cluster sizes ($n=4\text{--}25$) exhibited identical behavior, with all bands at the same position.⁴⁴ High-level calculations accurately predicted this red shift and found a strong correlation with the reaction energy and polarization. The current work also includes clusters ranging in size from one to three atoms and investigates the influence of hydration on the interaction with CO_2 , areas that had not been studied before. The results show that the monoatomic Cu cation has the highest reaction energy with CO_2 , which decreases with increasing cluster size in both pristine and hydrated clusters.

Methods

Experimental

This section provides an overview of the setup of ClusTOF, adapted to the presented experiment. More detailed insights into the formation, ionization and doping processes of superfluid helium droplets in the apparatus are given in the literature.^{53, 54}

The experimental process, see Figure 1, is initiated by the formation of HNDs, several 10^5 helium atoms⁵⁵, when pre-cooled (9.4 – 9.7K) and pressurized (20 – 22 bar, purity 99.9999%, Messer) helium is expanded through a pinhole nozzle, with the diameter around 5 μm , into the ultra-high vacuum. The temperature and pressure of the helium as well as the current and energy of the ionizing electron beam are finely controlled to ultimately optimize the ion yield of helium-tagged $\text{Cu}_n[\text{CO}_2]^+$ or $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ clusters. The HNDs are ionized via electron impact to create multiply-charged droplets, resulting in this experiment in a charge state around +10e.⁵⁶ In two consecutive, differentially pumped vacuum chambers, the droplets then pick up any species brought into the gas phase, explicitly copper atoms (isotopically enriched ⁶³Cu, Isotope Rosatom 99.8% purity; evaporated in a home-built, resistively heated ceramic oven), CO_2 (isotopically enriched ¹³C¹⁶O₂, Sigma Aldrich purity 99.0%) and H_2O (both introduced via separate gas inlets with needle valves). This pickup of dopants in combination with charge transfer from He_n^+ ionic cores leads to the formation of singly-charged dopant ions⁵⁷ and attachment of further dopants results in cluster ions⁵⁸ in the form of $\text{Cu}_n[\text{CO}_2]_m^+$ and $\text{Cu}_n[\text{CO}_2]_m[\text{H}_2\text{O}]_k^+$. The temperature of the oven as well as the partial pressures of water and carbon dioxide are tuned to optimize the ion yield of copper cluster ions complexed






Figure 1. Schematic sketch of the ClusTOF experiment, more details can be found in the text. HNDs are produced by the cluster source (CS). After multiply charging the droplets via electron impact (EI), they are doped with evaporated copper in the pick-up chamber (PU), followed by the pick-up of CO₂ and, if desired, H₂O. After cluster formation, the HNDs collide with a surface (SC), liberating He-tagged dopants feasible for analysis and detection with the time-of-flight (ToF) mass spectrometer. Action spectroscopy is achieved by irradiating the extracted cluster ions with an IR laser before entering the ToF.

with one CO₂ or one CO₂ and one H₂O molecule. The charged droplets then collide with a surface⁵⁹, liberating cold, helium-tagged ions, which are analyzed using a time-of-flight mass spectrometer combined with infrared IR photon absorption from a tunable OPO laser (EKSPLA NT277, linewidth ~8 cm⁻¹). In this form of action spectroscopy, the absorption of a photon leads to the loss of He atoms and enables the determination of absorption spectra via the increase of the photoproducts.⁵⁰ The mass spectrometer runs at a 10 kHz extraction rate, while the laser operates at 1 kHz. This ensures that every tenth extraction pulse coincides with laser illumination, facilitating side-by-side comparison of mass spectra with and without laser interaction. Absorption of a resonant photon leads to evaporation of the weakly bound He tags, observed in the mass spectrum as a depletion of the Cu_n[CO₂]_m[He]_x⁺ ion signal and the simultaneous increase of the photoproduct, the bare Cu_n[CO₂]_m⁺ ion. The resulting ion yield is then defined as the ratio of the signal of the bare ion with and without laser exposure. All spectral results are corrected for background noise by subtracting the signal of IR-inactive ions from the IR-active ions at each ToF extraction. No power correction has been employed since it remains flat in the region where complexes absorb the radiation. The laser power at each

scanned wavelength can be found in Figure S1 in the Electronic Supplementary Information (ESI). DOI: 10.1039/D4CP01797H

Computational

Density functional computations were carried out using the Q-Chem 6.1 program package⁶⁰ to recompute previously reported most stable Cu_n⁺ (*n* = 1-14) cluster geometries.^{61, 62} Here the pre-screened possible reaction products, both with intact CO₂ (Cu_n[CO₂]⁺); with intact CO₂ and intact H₂O (Cu_n[CO₂][H₂O]⁺); and with intact CO₂ and H₂O, dissociated to H and OH (Cu_n[CO₂][H][OH]⁺) are reported using the PBE/LANL2DZ level of theory.

The in-house code is utilized to systematically generate the initial geometries for different binding modes, similar to that in our previous works.^{46, 63, 64} The CO₂ is bound to the Cu_n⁺ (*n* = 1-14) clusters in mono- (*η*¹-O) or bidentate (*η*²-C, O) modes. H₂O is bound to the most stable Cu_n[CO₂]⁺ structures for *n* = 1-10. The monodentate mode (*η*¹-H) was selected for intact H₂O, while H was bound in bridge mode over adjacent coppers, or over a three-membered copper ring, and OH was bound in bridge mode over adjacent copper atoms or was bound to a single copper, as the water molecule may dissociate on copper clusters.^{65, 66} Please note that the goal is not to locate the global minimum structures, but rather to locate the possible products, accessible by the addition of the reactants to the cluster. All isomers are relaxed and calculated with the lowest spin state (i.e. singlet or doublet for structures having an even or odd number of electrons, respectively).

Final geometry optimizations and vibrational frequency computations are performed using the (U)TPSSH/def2-TZVP + D3 level of theory. This method has been used previously for similar systems and yielded accurate results compared both to computational benchmarks (up to CCSD(T)/def2-QZVPPD) and to experimental results.^{44, 46, 67} After the final optimization, the energetic order of the different isomers remained the same as in the pre-screening. The harmonic frequency computations reported in the main text were completed using isotopically pure ¹³C.

The impact of the correlation, basis sets, dispersion correction, relativity and anharmonicity on the computed vibrational spectrum is carefully benchmarked to ensure the most accurate results. The results of benchmarking are shown in Figure S2 of the ESI. Anharmonicity calculations shown in Tables S1 and S2 for Cu_n[CO₂]⁺, with *n* = 0, suggest a scaling factor of 0.98, which is subsequently applied to the results presented in the text. It is worth noting, however, that benchmarking is done for CO₂ with the ¹²C isotope, while frequencies used for the comparison with the experimental data were corrected for the ¹³C isotope. Binding energies are determined by calculating the difference between the total energy of the complex and the sum of the individual gas phase reactants namely Cu_n⁺, CO₂, and intact H₂O.

Results and Discussion

Spectroscopic investigation

In this study, we investigate He-tagged Cu_n[CO₂]⁺ complexes (*n* = 1-10) formed within helium nanodroplets (HNDs) using






Figure 2: a. The average of experimental photodissociation spectra of the $\text{Cu}_n[\text{CO}_2]^+$ complexes, covering the range of $n = 1-10$, within the vibration spectrum of the CO_2 asymmetric stretch, is showcased in grey. b. The same spectral range investigated for $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ complexes, $n = 1-7$. On both graphs, the Lorentzian-fitted bands are highlighted in red. Additionally, the position of the band determined for free CO_2 is indicated with a dashed line.

photodissociation spectroscopy. Upon photon absorption, the weakly bound helium atoms evaporate, leading to an increase in the ion intensity of the naked complex. To ensure sufficient helium attachment, over 50 helium atoms were attached to each complex, subsequently decaying into the naked complex. The resulting spectra are presented in Figure 2.a.

Based on previous measurements, it is anticipated that CO_2 will be physisorbed onto the cationic Cu cluster ions.⁴⁴ Consequently, the asymmetric stretch vibration is expected to closely mirror that of free $^{13}\text{CO}_2$, which has been determined via IR spectroscopy in a gaseous phase at 2283.48 cm^{-1} , a reference point we will utilize throughout this text.⁵¹ It is important to note that this experiment was conducted using isotopically enriched CO_2 , with ^{13}C , rather than the naturally more abundant one with ^{12}C , which would exhibit asymmetric stretch at 2349.16 cm^{-1} .⁵¹ This isotope was chosen to eliminate possible overlapping of the He-tagging series with the $\text{Cu}_n[\text{CO}_2]^+$ series in the mass spectrum. The current experiment on the complexes with $n = 1-10$ exhibits a blue shift of at least 15 cm^{-1} compared to the vibration of free CO_2 , falling within the range of $2290-2330\text{ cm}^{-1}$ with an average full width at half maximum (FWHM) of 9 cm^{-1} . The signal-to-noise ratio (S/N) decreases with increasing cluster size due to reduced helium attachment for

larger clusters, as illustrated in the mass spectrum shown in Figure S3.

When comparing the interaction of the Cu^+ monomer with CO_2 (with the ν_3 band at 2316 cm^{-1}) to monomers of other previously studied metals, first a correction for the heavier isotope of CO_2 must be made. The reduced mass for naturally abundant $^{12}\text{CO}_2$ and ^{63}Cu is 25.9 , while for the heavier $^{13}\text{CO}_2$ isotope, it is 26.25 . Therefore, to compare the results with other experiments, the experimentally obtained frequency is multiplied by a factor of 1.014 , resulting in a frequency of 2347 cm^{-1} .

Most metal and metal oxide ions investigated to date (including Ni, Si, Ti, Fe, Mg, Co, Rh, Ir, Al, NbO, and TaO) exhibit a band between 2265 and 2385 cm^{-1} , which is blue-shifted relative to the asymmetric stretch of free CO_2 , similarly to the one found in the current experiment.^{27, 28, 29, 30, 31, 33, 34, 68} When these ions are further solvated with CO_2 molecules, this band generally shifts further towards the red, closer to the vibrational frequency of free CO_2 , indicating a lower binding energy of subsequent CO_2 molecules. It's noteworthy that for most of these metals, no data on complexes with only one CO_2 molecule is reported, hence the band position of two CO_2 is utilized. Additionally, Ar is used as a tag, as the dissociation of CO_2 requires higher energy, leading to significant band broadening.²⁷



Other metals such as Ca, Sr, Ba exhibit a band around 2245 cm^{-1} .⁶⁹ For all these alkaline earth metals, it has been observed that the first CO_2 molecule is weakly bound in an η^1 configuration dominated by charge-quadrupole interaction. However, further solvation leads to the blue shift of ν_3 by at least 10 cm^{-1} . From the calculations it becomes evident that the second CO_2 binds in a bidentate manner due to the transfer of positive charge to the metal core, rendering CO_2 electronegative and stimulating its activation. A similar effect has also been noted for the solvation of metal- CO_2 complexes in water.^{40, 41}

In the current study, the primary focus lies on cluster size rather than solvation effects. The position of the ν_3 band exhibits a correlation with cluster size, progressively approaching that of free CO_2 as the cluster size increases, which was not observed before. Drawing an analogy with previous experiments involving ion solvation in multiple CO_2 molecules, a similar trend is observed, indicating a decrease in reaction energy.

A similar behavior of the CO_2 asymmetric stretch is observed when H_2O is co-adsorbed on the cluster. However, it is further

A triple band is observed for $n = 1$, which might result from the low S/N. However, based on the width of the peaks and their height, it is highly unlikely that they originate from a single band, as this feature would be much broader than the corresponding bands in the other cluster sizes. Similarly, the spectra for $n = 2$ and $n = 3$ exhibit two bands.

Computational results

For a comprehensive understanding of the investigated complexes, the lowest energy isomers of bare Cu_n^+ were explored computationally, along with the corresponding lowest energy $\text{Cu}_n[\text{CO}_2]^+$, $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ and $\text{Cu}_n[\text{CO}_2][\text{H}][\text{OH}]^+$ adducts. The resulting structures are depicted in Figure 3.

In all $\text{Cu}_n[\text{CO}_2]^+$ adducts, the CO_2 molecule binds in an η^1 configuration with one oxygen to one of the copper atoms at the cluster edge. This binding mode, together with the previous results^{44, 46, 67}, suggests a barrierless reaction of CO_2 with the cluster. Upon addition of water, cluster backbone rearrangement was observed only in the case of $n = 9$. However, following H_2O dissociation, significant cluster geometry changes were observed in almost all cases (except for $n = 2, 4, 6$), indicating a multi-step reaction mechanism. Notably, for $n = 1$, no structure with dissociated H_2O was found among the selected binding modes.

Figure 4.a illustrates the binding energies of the aforementioned structures. In all cases, both CO_2 and subsequent water adsorption are thermodynamically favorable. However, during the water dissociation, significant stabilization was observed only in the case of $n = 5, 9$ and 10, suggesting that water dissociation is less probable for other cluster sizes.

For both, the CO_2 adsorption and its co-adsorption with water, the CO_2 binding becomes less favored with increasing cluster size. This trend is also reflected in the frequencies of the asymmetric stretching vibrational mode of adsorbed CO_2 , which converge toward that of free CO_2 , as shown in Figure 4.b.

The overall trend is in good agreement with the calculations, as evidenced by recognizable dips at $n = 1, 4$, and 7 for both experimental data and theoretical predictions for $\text{Cu}_n[\text{CO}_2]^+$ in the top of Figure 4.b. However, discrepancies arise when comparing co-adsorption with water in the bottom of Figure 4b: while the calculations suggest no double or triple peaks, they are experimentally observed for $n = 1-3$. Notably, the peak with the highest measured frequency for $n = 1$ is almost 40 cm^{-1} lower, than what was calculated for $\text{Cu}[\text{CO}_2][\text{H}_2\text{O}]^+$. For $n = 2$, the calculated asymmetric CO_2 stretching frequency in $\text{Cu}_2[\text{CO}_2][\text{H}_2\text{O}]^+$ and $\text{Cu}_2[\text{CO}_2][\text{H}][\text{OH}]^+$ are remarkably similar to each other as well as to the average of the two measured peaks. In contrast, for $n = 3$, the calculated frequencies for intact and dissociated water are 20 cm^{-1} apart, with the frequency of




Figure 3: Lowest energy isomers for Cu_n^+ , $\text{Cu}_n[\text{CO}_2]^+$, $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$, and $\text{Cu}_n[\text{CO}_2][\text{H}][\text{OH}]^+$ in the studied binding modes.

redshifted compared to the ν_3 band of $\text{Cu}_n[\text{CO}_2]^+$ complexes, as can be seen in Figure 2.b.






Figure 4: a. Binding energies of the cluster adducts depicted on Figure 3. b. Top: Frequencies of the asymmetric stretching vibrational mode of the bound CO_2 on corresponding adducts are depicted. Bottom: The frequency of the same vibration, when water is co-adsorbed. The diamonds denote the experimental results, which include error bars. Note that the error bars are often smaller than the symbols; therefore, a black color is used to represent them. Additionally, for $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$, for $n = 1-3$ the symbols are not connected, since it is not clear which of them might originate from the ν_3 vibration. The dashed grey line represents the vibration of free CO_2 .

$\text{Cu}_3[\text{CO}_2][\text{H}_2\text{O}]^+$ falling between the experimentally determined peaks. All following cluster sizes exhibit only one band, which is in good agreement with the calculations.

According to the computations, the shift in the asymmetric stretch vibrational frequency of the bound CO_2 due to the H_2O adsorption is generally low, although somewhat larger in smaller sizes ($n = 1-4$), since CO_2 and H_2O are bound to the same ($n = 1$) or adjacent copper atoms ($n = 2-4$). A good correlation between the vibrational frequencies and the binding energies for $\text{Cu}_n[\text{CO}_2]^+$ ($R^2 = 0.743$) and $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ ($R^2 = 0.963$) is observed as evident from Figure S4. However, it is much lower for $\text{Cu}_n[\text{CO}_2][\text{H}][\text{OH}]^+$, with $R^2 = 0.141$. Accordingly, in the case of $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ the binding energy is significantly more negative for $n = 1$, thus the CO_2 asymmetric stretching vibrational frequency is considerably increased in the next largest cluster.

Energy decomposition analysis (EDA) was performed for several cluster sizes to gain a better understanding of the molecular

interactions and rationalize the reactivity of the clusters. The aim of the EDA is to decompose the interaction energy between two fragments (in this case, the Cu_n^+ clusters and CO_2) with an adduct into chemically meaningful terms. The EDA based on Absolutely Localized Molecular Orbitals (ALMO-EDA) is employed, where ALMOs are localized on each fragment facilitating a detailed analysis of intermolecular interactions.⁷⁰ ALMO-EDA decomposes the total interaction energy (here, binding energy) into frozen terms encompassing electrostatic interaction, Pauli repulsion, and dispersion interaction between the fragments, along with polarization, charge transfer and relaxation terms. The charge transfer energy can be further decomposed exactly to contributions from complementary occupied-virtual pairs (COVPs), wherein each orbital pair member resides on one of the fragments. Consequently, COVPs visually highlight the most significant orbitals involved in charge transfer. These analyses are illustrated in Figure 5. Figure 5.a shows the EDA, without the relaxation energies, because these values are practically zero (around 0.01 eV), as expected since no significant geometry changes occur in the fragments due to the CO_2 adsorption on the clusters. Polarization in the




Figure 5: a. Energy decomposition analysis for $\text{Cu}_n[\text{CO}_2]^+$ adducts ($n = 1, 4, 7, 10$). b. Major complementary occupied-virtual pairs (COVP) and their contribution to the charge transfer energy changes (above the arrow in kJ/mol) and transferred charge (under the arrow in me^-) (D = donor, A = acceptor).



fragments is the main term in the binding energies, which is strongly decreasing with the cluster size. Charge transfer (CT) follows the same trend, although with a significantly lower magnitude. Figure 5.b shows the main complementary occupied-virtual pairs (COVP) based on the values of the energy transfer. Donation from the clusters' σ and π orbitals to the LUMO of CO_2 weakens the carbon-oxygen bond. Additionally, back donation occurs, where the lone electron pair of the oxygen atom in CO_2 donates electron density to the formally unoccupied $4p$ orbital of the copper atoms, albeit with a somewhat lesser contribution. However, it's crucial to note that low values of both donation and back-donation indicate a lesser significance of the charge transfer process compared to the polarization. The approximately equal values of charge transfer contribute to the charge neutrality of the bound CO_2 , with a total charge of around ~ 0.02 . On the contrary, polarization exerts a more noticeable effect. Figures 6.a and 6.b show the natural charges of the connected Cu and O atoms, while 6.c shows the total charge of the remaining copper atoms in the cluster. Additionally, charges of C and outside O can be found in Figure S5. The two fragments, namely the CO_2 molecule and the Cu_n^+ cluster, exert a mutual polarization effect. This results in the connecting oxygen atom of the CO_2 molecule accumulating a more negative charge (by the electron transfer from the other oxygen

atom), while the connecting copper atom in the cluster experiences a corresponding increase in positive charge compared to the other copper atoms in the cluster. This effect diminishes with increasing cluster size, as can be seen from Figures 6.a and 6.b, as charges can be more readily redistributed across larger clusters (see Figure 6.c). Consequently, a less pronounced positive charge can be attained on the copper atom connected to the CO_2 . While bond indices (Figure 7) between the C and inner O are increasing with the cluster size, those between the C and the outer O are decreasing almost to the same extent. The increased $\text{O}^{\text{inner}}\text{-C}$ and the decreased $\text{O}^{\text{outer}}\text{-C}$ bond orders are in line with the polarization effects, shown already by the energy decomposition analysis, while the slightly decreased average O-C bond orders suggest the effect of a small charge transfer. Interestingly, the cluster size-dependent asymmetric stretch vibrational frequency correlates with both the increased and the decreased C-O bond indices, and also with their average, as can be seen in Figure S6. As the asymmetric stretch involves both C-O bonds and the distance between the inner oxygen and the connecting copper atom also changes, all these together determine the corresponding vibrational frequency. According to our computations, the asymmetric vibrational stretch frequency correlates with the CO_2 binding energy, which according to the EDA is determined mainly by polarization.




Figure 6: a. Charges of the Cu atom which is connected to the CO_2 in $\text{Cu}_n[\text{CO}_2]^+$. b. Charges of the O atom in $\text{Cu}_n[\text{CO}_2]^+$ which is connected to the cluster. c. Cumulated charges of the copper atoms except the Cu atom which is connected to the CO_2 in $\text{Cu}_n[\text{CO}_2]^+$ (copper atoms not bound to CO_2).




Figure 7: Wiberg bond indices of a. the C-O bond (where oxygen is connected to the cluster, i.e. inner oxygen); b. the C-O bond (where oxygen is not connected to the cluster, i.e. outer oxygen); c. both C-O bonds (inner and outer) with respect to the cluster size.



Conclusion

In conclusion, our spectroscopic investigation of He-tagged $\text{Cu}_n[\text{CO}_2]^+$ and $\text{Cu}_n[\text{CO}_2][\text{H}_2\text{O}]^+$ complexes within helium nanodroplets has provided valuable insights into the interaction between metal clusters and CO_2 molecules. Through photodissociation spectroscopy, we observed a blue shift in the asymmetric stretch vibration of CO_2 compared to gas phase CO_2 , with this shift diminishing as cluster size increases. This trend indicates a reduction in binding energy with increasing cluster size, a result supported by a computational analysis. Further computational examinations provided detailed insights into the binding energies and structural alterations upon the adsorption of CO_2 and water. The energy decomposition analysis underscored the significance of polarization over charge transfer in cluster- CO_2 interactions. Collectively, our findings highlight the intricate interplay among cluster size, molecular structure, and reactivity, offering promising avenues for the rational design of catalytic systems centered around metal clusters.

Author Contributions

A.M. Reider: Investigation, Visualization, Writing – Original Draft Preparation **M. Szalay:** Investigation, Formal Analysis, Writing – Original Draft Preparation, Visualization **J. Reichegger:** Investigation, Formal Analysis, Visualization, Writing – Review & Editing **J. Barabas:** Investigation, Formal Analysis **M. Schmidt:** Investigation **M. Kappe:** Investigation, Methodology **P. Scheier:** Conceptualization, Funding Acquisition, Resources, Methodology, Conceptualization, Software, Writing – Review & Editing **T. Höltzl:** Conceptualization, Investigation, Formal Analysis, Visualization, Writing – Original Draft Preparation, Review & Editing **O.V. Lushchikova:** Conceptualization, Data Curation, Funding Acquisition, Investigation, Project Administration, Supervision, Visualization, Writing – Original Draft Preparation.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

We are grateful to the Austrian Science Fund, FWF (grant number P34563, W1259 DK-ALM, and M3229-N) for funding the experimental part of this research and providing open access funding.

The computational part of the project was supported by the European Union's Horizon 2020 research and innovation programme under the Marie Skłodowska-Curie grant agreement no. 955650 (CatChy). T. Höltzl is grateful for the János Bolyai Research Scholarship of the Hungarian Academy of Sciences (grant number BO/00642/21/7). Project No. KDP-IKT-2023-900-I1-00000957/0000003 has been implemented with the support provided by the Ministry of Culture and Innovation

of Hungary from the National Research, Development and Innovation Fund, financed under the KDP-2023 funding scheme. This article is based upon work from the COST Actions CA21101 – Confined Molecular Systems: From a New Generation of Materials to the Stars (COSY), supported by COST (European Cooperation in Science and Technology).

References

1. P. Friedlingstein, *et al.*, *Earth System Science Data*, 2022, **14**, 1917-2005.
2. S. De, A. Dokania, A. Ramirez and J. Gascon, *Acs Catalysis*, 2020, **10**, 14147-14185.
3. M. Behrens, *et al.*, *Science*, 2012, **336**, 893-897.
4. J. Zhao, S. Xue, J. Barber, Y. W. Zhou, J. Meng and X. B. Ke, *Journal of Materials Chemistry A*, 2020, **8**, 4700-4734.
5. J. T. Niu, H. Y. Liu, Y. Jin, B. G. Fan, W. J. Qi and J. Y. Ran, *International Journal of Hydrogen Energy*, 2022, **47**, 9183-9200.
6. A. Halder, L. A. Curtiss, A. Fortunelli and S. Vajda, *The Journal of Chemical Physics*, 2018, **148**, 110901.
7. Q. Y. Fan, Y. Wang and J. Cheng, *Journal of Physical Chemistry Letters*, 2021, **12**, 3891-3897.
8. S. K. Iyemperumal and N. A. Deskins, *Physical Chemistry Chemical Physics*, 2017, **19**, 28788-28807.
9. C. Liu, B. Yang, E. Tyo, S. Seifert, J. DeBartolo, B. von Issendorff, P. Zapol, S. Vajda and L. A. Curtiss, *Journal of the American Chemical Society*, 2015, **137**, 8676-8679.
10. Y. Yang, J. Evans, J. A. Rodriguez, M. G. White and P. Liu, *Physical Chemistry Chemical Physics*, 2010, **12**, 9909-9917.
11. B. Yang, C. Liu, A. Halder, E. C. Tyo, A. B. F. Martinson, S. Seifer, P. Zapol, L. A. Curtiss and S. Vajda, *Journal of Physical Chemistry C*, 2017, **121**, 10406-10412.
12. X. Zhang, J. X. Liu, B. Zijlstra, I. A. W. Filot, Z. Y. Zhou, S. G. Sun and E. J. M. Hensen, *Nano Energy*, 2018, **43**, 200-209.
13. S. M. Lang and T. M. Bernhardt, *Physical Chemistry Chemical Physics*, 2012, **14**, 9255-9269.
14. H. Schwarz, *Coordination Chemistry Reviews*, 2017, **334**, 112-123.
15. J. M. Weber, *International Reviews in Physical Chemistry*, 2014, **33**, 489-519.
16. L. G. Dodson, M. C. Thompson and J. M. Weber, *Annual Review of Physical Chemistry*, 2018, **69**, 231-252.
17. B. J. Knurr and J. M. Weber, *Journal of the American Chemical Society*, 2012, **134**, 18804-18808.
18. B. J. Knurr and J. M. Weber, *The Journal of Physical Chemistry A*, 2013, **117**, 10764-10771.
19. B. J. Knurr and J. M. Weber, *The Journal of Physical Chemistry A*, 2014, **118**, 10246-10251.
20. B. J. Knurr and J. M. Weber, *The Journal of Physical Chemistry A*, 2014, **118**, 4056-4062.
21. B. J. Knurr and J. M. Weber, *The Journal of Physical Chemistry A*, 2014, **118**, 8753-8757.
22. M. C. Thompson, J. Ramsay and J. M. Weber, *Angewandte Chemie International Edition*, 2016, **55**, 15171-15174.
23. M. C. Thompson, L. G. Dodson and J. M. Weber, *The Journal of Physical Chemistry A*, 2017, **121**, 4132-4138.
24. M. C. Thompson, J. Ramsay and J. M. Weber, *The Journal of Physical Chemistry A*, 2017, **121**, 7534-7542.
25. L. G. Dodson, M. C. Thompson and J. M. Weber, *The Journal of Physical Chemistry A*, 2018, **122**, 2983-2991.



26. N. R. Walker, R. S. Walters and M. A. Duncan, *New Journal of Chemistry*, 2005, **29**, 1495-1503.
27. G. Gregoire and M. Duncan, *The Journal of Chemical Physics*, 2002, **117**, 2120-2130.
28. R. Walters, N. Brinkmann, H. Schaefer and M. Duncan, *The Journal of Physical Chemistry A*, 2003, **107**, 7396-7405.
29. G. Gregoire, N. Brinkmann, D. Van Heijnsbergen, H. Schaefer and M. Duncan, *The Journal of Physical Chemistry A*, 2003, **107**, 218-227.
30. N. Walker, R. Walters, G. Grieves and M. Duncan, *The Journal of Chemical Physics*, 2004, **121**, 10498-10507.
31. J. Jaeger, T. Jaeger, N. Brinkmann, H. Schaefer and M. Duncan, *Canadian Journal of Chemistry*, 2004, **82**, 934-946.
32. A. M. Ricks, A. D. Brathwaite and M. A. Duncan, *The Journal of Physical Chemistry A*, 2013, **117**, 11490-11498.
33. A. Iskra, A. S. Gentleman, A. Kartouzian, M. J. Kent, A. P. Sharp and S. R. Mackenzie, *The Journal of Physical Chemistry A*, 2017, **121**, 133-140.
34. A. Iskra, A. S. Gentleman, E. M. Cunningham and S. R. Mackenzie, *International Journal of Mass Spectrometry*, 2019, **435**, 93-100.
35. Z. Zhao, X. Kong, D. Yang, Q. Yuan, H. Xie, H. Fan, J. Zhao and L. Jiang, *The Journal of Physical Chemistry A*, 2017, **121**, 3220-3226.
36. D. Yang, *et al.*, *Chinese Journal of Chemical Physics*, 2020, **33**, 160-166.
37. Z. Zhao, X. Kong, Q. Yuan, H. Xie, D. Yang, J. Zhao, H. Fan and L. Jiang, *Physical Chemistry Chemical Physics*, 2018, **20**, 19314-19320.
38. H. Zheng, *et al.*, *The Journal of Physical Chemistry Letters*, 2021, **12**, 472-477.
39. E. Barwa, T. F. Pascher, M. Ončák, C. van der Linde and M. K. Beyer, *Angewandte Chemie International Edition*, 2020, **59**, 7467-7471.
40. E. Barwa, M. Ončák, T. F. Pascher, A. Herburger, C. van der Linde and M. K. Beyer, *Chemistry – A European Journal*, 2020, **26**, 1074-1081.
41. M. Salzburger, R. T. Saragi, F. J. Wensink, E. M. Cunningham, M. K. Beyer, J. M. Bakker, M. Ončák and C. van der Linde, *The Journal of Physical Chemistry A*, 2023, **127**, 3402-3411.
42. A. E. Green, J. Justen, W. Schöllkopf, A. S. Gentleman, A. Fielicke and S. R. Mackenzie, *Angewandte Chemie*, 2018, **130**, 15038-15042.
43. A. Yanagimachi, K. Koyasu, D. Y. Valdivielso, S. Gewinner, W. Schöllkopf, A. Fielicke and T. Tsukuda, *The Journal of Physical Chemistry C*, 2016, **120**, 14209-14215.
44. O. V. Lushchikova, M. Szalay, H. Tahmasbi, L. B. F. Juurlink, J. Meyer, T. Holtz and J. M. Bakker, *Physical Chemistry Chemical Physics*, 2021, **23**, 26661-26673.
45. N. Zimmermann, T. M. Bernhardt, J. M. Bakker, R. N. Barnett, U. Landman and S. M. Lang, *The Journal of Physical Chemistry A*, 2020, **124**, 1561-1566.
46. O. V. Lushchikova, M. Szalay, T. Holtz and J. M. Bakker, *Faraday Discussions*, 2022, **242**, 252-268.
47. T. Kakumoto, *Energy Conversion and Management*, 1995, **36**, 661-664.
48. S. K. Iyemperumal and N. A. Deskins, *Physical Chemistry Chemical Physics*, 2017, **19**, 28788-28807.
49. O. V. Lushchikova, H. Tahmasbi, S. Reijmer, R. Platte, J. Meyer and J. M. Bakker, *The Journal of Physical Chemistry A* 2021, **125**, 2836-2848.
50. M. Kappe, A. Schiller, F. Zappa, S. A. Krasnokutski, M. S. Wagner, H. F. Bettinger and P. Scheier, *Astronomy & Astrophysics*, 2023, **672**.
51. T. Shimanouchi, *Tables of molecular vibrational frequencies*, National Bureau of Standards Washington, DC, 1972.
52. B. J. Thomas, B. A. Harruff-Miller, C. E. Bunker and W. K. Lewis, *The Journal of Chemical Physics*, 2015, **142**, 174310.
53. M. Kappe, B. Rasul, M. Mahmoodi-Darian, A. Schiller, F. Zappa, S. A. Krasnokutski and P. Scheier, *Molecular Physics*, 2024, **122**, e2202271.
54. M. Meyer, P. Martini, A. Schiller, F. Zappa, S. A. Krasnokutski and P. Scheier, *The Astrophysical Journal*, 2021, **913**, 136.
55. L. F. Gomez, E. Loginov, R. Sliter and A. F. Vilesov, *The Journal of Chemical Physics*, 2011, **135**, 154201.
56. F. Laimer, L. Kranabetter, L. Tiefenthaler, S. Albertini, F. Zappa, A. M. Ellis, M. Gatchell and P. Scheier, *Physical Review Letters*, 2019, **123**, 165301.
57. A. J. Feinberg, *et al.*, *Physical Review Research*, 2022, **4**, L022063.
58. S. Albertini, E. Gruber, F. Zappa, S. Krasnokutski, F. Laimer and P. Scheier, *Mass Spectrometry Reviews*, 2022, **41**, 529-567.
59. P. Martini, S. Albertini, F. Laimer, M. Meyer, M. Gatchell, O. Echt, F. Zappa and P. Scheier, *Physical Review Letters*, 2021, **127**, 263401.
60. E. Epifanovsky, *et al.*, *The Journal of Chemical Physics*, 2021, **155**, 84801.
61. O. V. Lushchikova, D. M. M. Huitema, P. Lopez-Tarifa, L. Visscher, Z. Jamshidi and J. M. Bakker, *The Journal of Physical Chemistry Letters*, 2019, **10**, 2151-2155.
62. E. M. Fernandez, J. M. Soler, I. L. Garzon and L. C. Balbas, *Physical Review B*, 2004, **70**, 165403.
63. M. Szalay, D. Buzsáki, J. Barabás, E. Faragó, E. Janssens, L. Nyulászi and T. Höltzl, *Physical Chemistry Chemical Physics*, 2021, **23**, 21738-21747.
64. B. Zamora, L. Nyulászi and T. Höltzl, *Chem Phys Chem*, 2024, **25**, e202300409.
65. L. Chen, *et al.*, *Physical Chemistry Chemical Physics*, 2010, **12**, 9845-9851.
66. J. H. Stenlid, A. J. Johansson, L. Kloos and T. Brinck, *The Journal of Physical Chemistry C*, 2016, **120**, 1977-1988.
67. M. Szalay, D. Buzsaki, J. Barabas, E. Farago, E. Janssens, L. Nyulaszi and T. Holtz, *Physical Chemistry Chemical Physics*, 2021, **23**, 21738-21747.
68. X. p. Xing, G. j. Wang, C. x. Wang and M. f. Zhou, *Chinese Journal of Chemical Physics*, 2013, **26**, 687-687.
69. Y. Yang, G. Wang and M. Zhou, *The Journal of Physical Chemistry A*, 2024, **128**, 618-625.
70. P. R. Horn, Y. Mao and M. Head-Gordon, *Physical Chemistry Chemical Physics*, 2016, **18**, 23067-23079.

