## Journal of Materials Chemistry A



## CORRECTION

View Article Online
View Journal | View Issue



Cite this: J. Mater. Chem. A, 2015, 3, 9317

DOI: 10.1039/c5ta90073e

www.rsc.org/MaterialsA

## Correction: Structure and function relationships in alkylammonium lead(||) iodide solar cells

Majid Safdari, <sup>a</sup> Andreas Fischer, <sup>a</sup> Bo Xu, <sup>b</sup> Lars Kloo <sup>a</sup> and James M. Gardner \*a

Correction for 'Structure and function relationships in alkylammonium lead(II) iodide solar cells' by Majid Safdari et al., J. Mater. Chem. A, 2015, DOI: 10.1039/c4ta06174h.

A row from Table 3, and a phrase from the caption, were not included in the manuscript. The correct Table 3 is shown below. **Table 3** Photovoltaic parameters (average values of 5 devices) of the MAPbI<sub>3</sub>, EAPbI<sub>3</sub> and PAPbI<sub>3</sub> devices. 600 nm thick TiO<sub>2</sub> films were used as substrate, and Spiro-OMeTAD was used as the HTM. A 200 nm layer of silver was used as back contact. Conductivity data collected as described in the text.

	$MAPbI_3$	$EAPbI_3$	$PAPbI_3$
$J_{ m sc}$ mA cm $^{-2}$	$16.29\pm1.69$	$0.77\pm0.14$	$0.075 \pm 0.021$
$V_{\rm oc}$ (V)	$0.784 \pm 0.026$	$0.662 \pm 0.040$	$0.564 \pm 0.034$
FF	$0.580 \pm 0.011$	$0.521 \pm 0.051$	$0.372 \pm 0.034$
$\eta$ (%)	$7.4 \pm 0.59$	$0.26 \pm 0.025$	$0.016 \pm 0.004$
APCE	78.35	2.83	0.18
Band gap (eV)	1.6	2.2	2.4
Conductivity (S cm <sup>-1</sup> )	$1.1\times10^{-4}$	$1.3\times10^{-6}$	$9.4\times10^{-7}$

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

<sup>&</sup>lt;sup>a</sup>Division of Applied Physical Chemistry, Department of Chemistry, KTH Royal Institute of Technology, SE-100 44, Stockholm, Sweden. E-mail: jgardner@kth.se <sup>b</sup>Organic Chemistry, Center of Molecular Devices, Department of Chemistry, KTH Chemical Science and Engineering, 10044, Stockholm, Sweden