

Cite this: *Nanoscale Adv.*, 2019, 1, 4246

# The molecular mechanisms underlying mussel adhesion

Yiran Li <sup>ab</sup> and Yi Cao <sup>\*abc</sup>

Marine mussels are able to firmly affix on various wet surfaces by the overproduction of special mussel foot proteins (mfps). Abundant fundamental studies have been conducted to understand the molecular basis of mussel adhesion, where the catecholic amino acid, L-3,4-dihydroxyphenylalanine (DOPA) has been found to play the major role. These studies continue to inspire the engineering of novel adhesives and coatings with improved underwater performances. Despite the fact that the recent advances of adhesives and coatings inspired by mussel adhesive proteins have been intensively reviewed in literature, the fundamental biochemical and biophysical studies on the origin of the strong and versatile wet adhesion have not been fully covered. In this review, we show how the force measurements at the molecular level by surface force apparatus (SFA) and single molecule atomic force microscopy (AFM) can be used to reveal the direct link between DOPA and the wet adhesion strength of mussel proteins. We highlight a few important technical details that are critical to the successful experimental design. We also summarize many new insights going beyond DOPA adhesion, such as the surface environment and protein sequence dependent synergistic and cooperative binding. We also provide a perspective on a few uncharted but outstanding questions for future studies. A comprehensive understanding on mussel adhesion will be beneficial to the design of novel synthetic wet adhesives for various biomedical applications.

Received 15th September 2019  
Accepted 9th October 2019

DOI: 10.1039/c9na00582j

rsc.li/nanoscale-advances

<sup>a</sup>Shenzhen Research Institute of Nanjing University, Shenzhen, 518057, China. E-mail: Caoyi@nju.edu.cn<sup>b</sup>Department of Physics, Collaborative Innovation Center of Advanced Microstructures, National Laboratory of Solid State Microstructure, Nanjing University, Nanjing, 210093, China<sup>c</sup>Chemistry and Biomedicine Innovation Center, Nanjing University, Nanjing, 210093, China

## Introduction

Bioinspired design has enjoyed great success in materials science for the production of novel materials with functions similar or even superior to naturally occurring ones.<sup>1–3</sup> The heart of bioinspired design is to understand the structure–function relationship of natural biomaterials.<sup>4–6</sup> In the past few decades, considerable efforts have been devoted to the



Yiran Li received his Ph.D. degree from the Physics department of Nanjing University. He joined the University of California, Berkeley as a post-doctoral fellow and then the Nanjing University as a research associate. His research focuses on AFM based single-molecule force spectroscopy and nanoscale mechanical measurement.



Yi Cao received his bachelor's degree in 2001 and Master's degree in 2004 from Nanjing University. He then obtained his Ph.D. in 2009 from the University of British Columbia. He started his independent career at the Department of Physics, Nanjing University as a full professor in 2010. He was the recipient of the 2014 IUPAP Young Scientist Prize in Biological Physics and the 2018 Young

Innovator Award by Nano Research. His current research combines single molecule force spectroscopy with synthetic biology and polymer chemistry to address fundamental questions as well as applied challenges in soft materials.



fabrication of mussel-inspired underwater adhesives and surface coating technologies,<sup>7–10</sup> owing to the great advances in the understanding of mussel adhesion mechanism. Marine mussels produce a bundle of byssus to firmly fix themselves on a wet rocky seashore to avoid being taken by fierce sea waves. Biochemical studies have revealed that the mussel secretes special proteins to form the major adhesion apparatus, byssus.<sup>11</sup> These mussel foot proteins, particularly the ones at the very tip of the byssus typically contain a high percentage of a post-translationally modified amino acid, L-3,4-dihydroxyphenylalanine (DOPA).<sup>11</sup> Biophysical characterizations by surface force apparatus (SFA) and atomic force microscopy (AFM)-based single-molecule force spectroscopy (SMFS) has uncovered the direct correlation of the adhesion strength with the contents of DOPA.<sup>12–14</sup> Moreover, it was discovered that DOPA can adaptively bind to different surfaces using different binding modes.<sup>13,15</sup> The surface chemical properties can greatly modulate the DOPA adhesion.<sup>16</sup> It was also revealed that the proximate lysine residues can promote DOPA binding in a sequence dependent manner.<sup>17,18</sup> In this perspective, we have first summarized the sequence and biochemical properties of different mussel foot proteins. Then, we have briefly introduced the SFA studies of mussel foot proteins and the synthetic mimetics. Next, we have mainly focused on the AFM-based single molecule force spectroscopy studies of DOPA adhesion, from the basic experimental design to data interpretation and the major scientific discoveries. Furthermore, we have also introduced the recent applications of SMFS in the study of DOPA-Fe<sup>3+</sup> coordination bonds and the real-time polydopamine polymerization. Finally, we have provided our perspective on the potential challenges and opportunities in SMFS studies of DOPA adhesion.

## Biochemical properties of mussel foot proteins

Mussel byssus consists of a bundle of collagenous threads and a flattened adhesive plaque at the end (Fig. 1). The threads can be extended to more than 30% and dissipate a considerable mechanical energy upon stretching through the rupture of reversible metal chelation bonds (*i.e.* DOPA-Fe<sup>3+</sup> and histidine-Zn<sup>2+</sup> bonds) and function as shock-absorbers.<sup>11,19</sup> The plaques provide strong adhesion strength to various wet substrates. A set of sticky and highly basic proteins were extracted and purified from the phenol gland of mussel byssus.<sup>20–22</sup> Further analysis




Fig. 1 Mussel adhesion and schematic structure of mussel byssus.

showed that this protein contains large amounts of DOPA, lysine and 3- and 4-hydroxyproline, and is considered to be responsible for the wet adhesion. Later, at least 15 different proteins were characterized from mussel byssus. Eight of these proteins are only present in the adhesive plaques and the rest are also found in other parts of the byssus.<sup>20,22,23</sup> For example, collagens dominate the fibrous core of each thread and extend to the plaque. Mfp-1, a major constituent of the protective cuticle, was found covering all the exposed byssus, including the plaque.<sup>12,22</sup> Mfp-2 is a cysteine-rich structural element of the plaque matrix, which is in the shape of a structural foam.<sup>21,24</sup> Mfp-3 and mfp-5 are found in plaques with the lowest mass and the highest DOPA contents among all the mussel foot proteins.<sup>12,23</sup> Mfp-6 is also located at the plaque but surprisingly contains low levels of DOPA and high levels of cysteine.<sup>25</sup> It forms cysteinyl-DOPA cross-links with other proteins to stabilize the structure of the plaque and maintains a reducing environment to prevent the oxidation of DOPA.<sup>26,27</sup> Mfp-4 is found in the plaque-thread junction and mediates the contact between the fibrous collagen and the foam protein. It has a mass of 93 kDa and has an abundance of histidine, lysine, arginine and aspartate.<sup>25</sup> Given that all these proteins contain considerable amounts of DOPA, and the DOPA levels are the highest in the proteins at the adhesive plaque, it is natural to attribute the adhesion properties to DOPA. It was proposed that DOPA can form bidentate H-bonding,<sup>28–30</sup> metal coordination<sup>14,28</sup> or covalent oxidative cross-linking,<sup>31</sup> hydrophobic,  $\pi$ - $\pi$  and cation- $\pi$  interactions with different surfaces.<sup>13,32</sup> Later on, the hypothesis was confirmed by various biophysical studies, including SFA and AFM.

The mechanical properties of mfp adhesion can be measured by different techniques, including optical tweezers, bio-membrane force probe, AFM-based SMFS, and bulk tensile test. The ranges of loading rates and forces of these methods are summarized in Fig. 2. As SFA and AFM-based SMFS are two major methods used to study the binding mechanism of mfps,




Fig. 2 Force and loading rate ranges of different force measurement approaches. OT represents optical tweezers and its range is estimated from ref. 42–44. Bio-membrane force probe (BFP) is estimated from ref. 45. AFM-based SMFS data are from ref. 46–48 and are estimated by general AFM technical details and typical cantilever mechanical properties. SFA data are from ref. 33, 49 and 50. Tensile stretching data are estimated from ref. 47 and 51–54.



the technical details and the major findings by these methods are summarized below.

## SFA studies

SFA is a precise and powerful tool to measure the interactions between two surfaces. It uses multiple beam interferometry to monitor surface separation and the deformation of the contact area. Owing to the sensitive elements, the device can resolve to within 0.1 nm in the  $z$  direction and a force to  $10^{-8}$  N.<sup>33</sup> One of the two surfaces of SFA is held by the cantilevered spring, and it measures the normal forces. The other is linked to a piezoelectric positioner to accurately control the separation of the two surfaces. Usually, in the SFA measurement, two orthogonal cylinders coated with atomically smoothed mica are made to approach each other in a direction normal to the axes. The samples are placed between two cylinders. In a typical experiment, a large compressive load force ( $\sim 1$ – $10$  MPa) is applied to make the formation of sample-surface interaction. Then, the two surfaces are separated, and the separation force is calculated by a spring system based on Hooke's law (Fig. 3a). SFA can measure varieties of interactions, such as van der Waals forces, electrostatic forces and even hydrogen bonding.

Using SFA, Jacob N. Israelachvili *et al.* have greatly advanced our understanding of mussel adhesion in the past decades. They have directly quantified the surface binding strength of various mfps with diverse DOPA contents under different environmental conditions. It was found that mfp-3 and mfp-5, the two major adhesive proteins at the plaque, could achieve  $\sim 3 \times 10^{-4}$  and  $\sim 1.4 \times 10^{-3}$  J m $^{-2}$  adhesion energies to the mica

surfaces, respectively.<sup>12,15</sup> The adhesion strength of mfp-5 is even higher than that of a highly oriented biotin and streptavidin monolayer.<sup>34</sup> Their adhesion energies are directly correlated with their DOPA contents. Interestingly, despite the fact that mfp-1 has a similar DOPA content as mfp-3, its adhesion performance is distinct.<sup>12</sup> No adhesion was ever observed for mfp-1 coated single layers in SFA experiments presumably due to the absence of long-range bridging forces. However, a subsequent shearing-separation test observed a finite adhesion between mica and mfp-1. A possible explanation is that most of the binding sites of the mfp-1 were initially attached to a one surface only and were rearranged to the opposite surface upon shearing.<sup>12</sup> This case indicated that in a SFA measurement, successful adhesion on both surfaces is the prerequisite for detecting interactions. Therefore, both adhesion between surfaces and the cohesion among the proteins are important for the strong surface adhesion energies measured in SFA.

The effect of the oxidation of DOPA on the adhesion properties of mfps was studied. Oxidation could abolish many important types of interactions between DOPA and the surfaces (*e.g.* hydrogen bonding and metal chelation). Oxidizing DOPA to dopaquinone by periodate led to the abolition of the adhesion between both asymmetrically and symmetrically deposited mfp-5 films.<sup>35</sup> Mussels have evolved an intriguing mechanism to limit DOPA oxidation by secreting an acidic and thiol-rich foot protein, mfp-6, which can revert the oxidized dopaquinone to DOPA using thiol as the reductant.<sup>36</sup> Furthermore, the oxidation of DOPA can also promote cohesion if the oxidized surface could bind strongly to the unoxidized surface due to the strong hydrogen bonding between DOPA and dopaquinone.<sup>37</sup>




Fig. 3 Illustrative scheme of SFA (a) and two types of SMFS (c) and (e) measurements. (b) is the representative force–distance relationship of SFA measurement, (d) is the representative force–extension curve of single-ligand recognition and (f) is the polymer-based fishing measurement.



Moreover, as oxidized DOPA can crosslink with thiol or amino group *via* Michael addition,<sup>38</sup> some reports also utilized the periodate treatment to enhance DOPA adhesion or cohesion.<sup>39–41</sup>

The interactions among the adhesive mfp family (mfp-1, mfp-3 and mfp-5) and other surfaces with different chemical properties have also been studied by SFA.<sup>15</sup> The results showed that all three mfps could adhere to the four tested substrates (mica, TiO<sub>2</sub>, silica and polystyrene), yet the adhesion strength was exquisitely dependent on the mfp species, the substrate surface chemistry and the contact time. It was proposed that several different binding mechanisms are involved in the binding, including electrostatic, hydrogen bonding, hydrophobic interactions, cation- $\pi$  interactions and  $\pi$ - $\pi$  stacking.<sup>15</sup>

The contribution of other residues in mfps to the adhesion energies was also explored. Using cyclic model compounds as an example, Butler, Israelachvili, and Waite *et al.* showed that lysine and DOPA can synergistically enhance the binding strength.<sup>18,55</sup> The synergy was interpreted as that the positively charged amine could help break the hydrated salt layer on the mineral surface and serve as vanguards to keep a stable bidentate catechol-surface interaction.<sup>18</sup> It remains elusive whether other mechanisms may also contribute to their cooperative surface binding. Moreover, lysine and DOPA interactions can also enhance the intermolecular cohesion of mfp mimicking peptides. Based on the solid state NMR spectroscopy characterization, cation- $\pi$  interaction was clearly observed.<sup>32,56</sup> However, it was quite surprising to discover that the peptides containing lysine-phenylalanine showed a much stronger adhesion energy than those containing lysine-DOPA. It is plausible that lysine-phenylalanine has stronger cation- $\pi$  interactions. However, it cannot be fully excluded that the formation of certain molecular structures of the peptides may also significantly enhance the cohesion strength. It was noticed that the peptides being studied contained a diphenylalanine motif, which showed a strong self-assembling tendency.<sup>57,58</sup>

Although SFA has been widely used to measure the adhesion of mfps to different surfaces, we should be aware that these measurements are done at the ensemble level. The adhesion energy does not necessarily correlate with the surface binding strength of individual mfps as the cohesive interactions of proteins and the cooperativity of different molecules also play significant roles. Moreover, it is difficult to prepare a single protein layer for the SFA test in real experiments, even though most SFA measurements declared that single layer adhesives were tested. Besides, adhesion strength is not only determined by the individual bond strength but also by the bond density, which is difficult to control. In general, the bond density can vary dramatically when different proteins or synthetic adhesives are used. Recent studies showed that the distribution of proteins on the two surfaces can greatly affect the SFA observation.<sup>35</sup>

## Single-molecule force spectroscopy experiments by AFM

AFM-based SMFS has been widely used to study the mechanical strength of chemical bonds, ligand-receptor interactions,

protein-protein interactions and adhesive molecule-surface interactions.<sup>59–74</sup> AFM measurement is complementary to SFA measurement and can directly quantify the strength of single adhesion bonds with an extremely high resolution of 10<sup>-9</sup> N on force and 10<sup>-10</sup> m on separation. Representative interaction strengths measured by SMFS are summarized in Table 1.

Using AFM-based SMFS, the adhesion of mfps has been widely studied. In early AFM experiments, mfps were directly placed between the cantilever tip and the substrate, similar to the design of SFA experiments.<sup>75,76</sup> Therefore, it remained difficult to identify the single molecule pulling events. Later on, experiments were carefully designed to minimize the nonspecific interactions and the elastic properties of the polymer were used as the fingerprint of single molecule pulling events. To minimize the interference from other amino acids, SMFS studies mainly focused on DOPA instead of the whole natural mfps. In general, there are two ways to unambiguously study the DOPA adhesion *via* SMFS (Fig. 3b and c). The first one is to covalently connect DOPA to the AFM cantilever *via* a bifunctional polymer linker and directly measure DOPA-surface interactions.<sup>77–82</sup> In this strategy, inert polyethylene glycol (PEG) is usually used as the linker to minimize nonspecific interactions between the cantilever and the substrates. The other method is to incorporate DOPA into a polymer. By stretching the surface-immobilized polymer chain, DOPA-surface interactions are ruptured one by one. Both methods are widely used and each has its own advantages and disadvantages. The former one allows the direct observation of DOPA-surface interactions without the interference from other components. However, it is not applicable if the interactions involve more than two ligands (*e.g.* the tris-complex formed between Fe<sup>3+</sup> and DOPA). The latter approach is a high-volume method, which is akin to the unfolding of polyproteins.<sup>81,83–85</sup> Since it relies on nonspecific interactions to pick up the polymers, it is important to make sure that the sawtooth-like peaks are indeed from the rupture of individual DOPA adhesion bonds. A common criterion is that the persistence length of the force-extension relationship of each rupture event is consistent and matches that of the polymer backbone. The last peak can either be the rupture of a surface adhesion bond or the detachment of the polymer from the cantilever tip, and therefore should be excluded in data analysis. The nonspecific adhesion of the polymer to the cantilever tip is not always high enough to ensure the rupture events in all force regions to be unbiasedly sampled. Nevertheless, with carefully designed experiments and data analysis procedures, this high-volume method can readily probe the rupture of single adhesion bonds. Another aspect that should be emphasized is that SMFS experiments are typically performed at a non-equilibrium condition. The rupture forces largely depend on the force loading rates (Fig. 4). The faster the loading rate is, the higher the rupture forces are. As such, it is not meaningful to compare the binding forces measured at different loading rates. The force-loading rate relationship can be understood by adding a force-dependent term to the Arrhenius model as first introduced by Bell and later by Evans.<sup>108–110</sup> The force-dependent term is directly determined by the height of the activation barrier and the width of the potential at the



Table 1 Typical interaction strengths measured by SMFS

Interaction type	Bond carrier	Bond strength [pN] (at loading rate [nN s <sup>-1</sup> ])	Dissociation rate [s <sup>-1</sup> ]	Distance to transition state [nm]	Ref.
Hydrogen bonding	DOPA-Ti [aqueous]	77 (50)	20.02	0.13	13
	UPy tandem [toluene]	~120 (30)	0.88	0.20	86
	P(BTA) stacking [mesitylene]	~70 (6.7)	0.30	0.45	87
Hydrophobic interaction	DOPA-PS [aqueous]	78 (50)	14.94	0.17	13
	Hexadecane-hexadecane [aqueous]	~75 (5.0)	1.1	0.24	88
	Unravel PS [aqueous]	~70 (—)	—	—	89
	Unravel PS [aqueous]	~80 (—)	—	—	90
	Hydrophobin	~110 (20)	0.59	0.35	91
Covalent bond	SiO <sub>x</sub> -amylose-SiO <sub>x</sub> [aqueous]	2000 (10)	—	—	92
	Cycloreversion of cyclobutene [DMSO]	>1700 (100–500)	—	—	93
	Thiol-maleimide adduct	900 (30)	3.5 × 10 <sup>-4</sup> (open ring)	0.05	94
	Thioester [in protein]	~100 (6)	—	—	95
	Au-S	600–1000 (30)	—	—	112
Charge interaction	Histidine-histidine	115 (16)	0.12 (pH7)	0.23 (simulated fitting)	96
	Polyanion and positively charged surface [aqueous]	120 (60)	—	—	97
	Polyvinylamine-SiO <sub>2</sub> [aqueous]	45–81 (—)	—	—	98
Coordinate bonding	His tag/NTA-CO <sup>2+</sup> , Cu <sup>2+</sup> , Ni <sup>2+</sup> , Zn <sup>2+</sup> [aqueous]	22–58 (30)	—	—	99
	Catechol-Fe <sup>3+</sup> [aqueous]	100–200 (50)	—	0.14 (bis), 0.27 (tris)	100
	Fe <sup>2+</sup> -S bond [aqueous]	146–242 (16)	3 × 10 <sup>-6</sup> to 0.7	0.11–0.30 (pulling direction dependent)	101
	Au-S interaction	500–2900 (30–50)	—	—	92 and 102–104
	Cu-S [in protein]	147 (40)	—	—	105
	Zn-S [in protein]	90–170 (—)	—	—	106 and 107




Fig. 4 Schematic figures of energy landscape (a) and force–loading rate dependency (b). Applied force can tilt the energy landscape and lower the energy barrier. By fitting force–loading rate relationship, dissociation rate and distance to transition state can be extracted.

pulling direction. Therefore, based on the force–loading rate relationships, one can extract the kinetic parameters underlying the free energy landscape of the bond dissociation. The measurement of rupture forces at different loading rates is typically named as dynamic force spectroscopy, which provides a unique way to understand the molecular mechanism of the adhesion bonds. In these experiments, the cantilevers were moved away from the substrates at different separation speeds. The force loading rates depend on both the separation speeds and the spring constants of the cantilevers, which can be experimentally determined from the force–time relationships.

For some interactions, loading rate-independent rupture forces were also observed at the low loading rate region. This can be attributed to the high rebinding rates of the system and the binding and rebinding were in equilibrium.<sup>111</sup>

In 2006, Messersmith *et al.* used AFM-based SMFS to study the interactions between individual DOPA and titanium surfaces, which shed new light on the DOPA adhesion mechanism.<sup>14</sup> Without the interference from the other components in mfps, the contribution of DOPA to the wet adhesion was first studied. In this test, *N*-(*tert*-butoxycarbonyl)-DOPA (*N*-Boc-DOPA) was end-tethered to a functional PEG linker and the Boc group prevented potential interference from the N-terminal positive charge. Their results showed that the adhesion force is ~800 pN for the DOPA-Ti surface in deionized water at a loading rate of 60.0 nN s<sup>-1</sup>, which is a strong noncovalent interaction (Fig. 5a and b). They also performed dynamic force spectroscopy and found that the rupture forces depend on the logarithm of loading rates. Then, they studied the effect of DOPA oxidation to the adhesion strength. At a basic pH of 8.3 or 9.7, they observed a bimodal distribution with a lower value peak located at ~150 pN and a higher value at 800 pN. The lower value peak was attributed to the detachment of oxidized DOPA from the surface. They also analyzed the relationship between rupture forces and the experimental duration. The results showed that the events of large rupture force values occurred







binding is sensitive to the structures of the compounds, and the synergy could be observed only when the external force is evenly distributed to lysine and DOPA. Therefore, the neighboring positive charge can not only displace the hydration layer as well as the surface salt to facilitate DOPA adhesion but can also directly participate in surface binding by forming ionic bonds with the surfaces. Apart from DOPA, hydrophobic amino acid (for example Phe, Leu and Orn) was also found to contribute to wet adhesion. Recently, Leader *et al.* used SMFS to measure the interactions between various amino acids and the TiO<sub>2</sub> surface.<sup>56</sup> Their results showed that aromatic interactions dominate over aliphatic interactions. In addition, the affinity of positively charged amino acids to the titanium dioxide surface is higher than that of uncharged, and can be further increased at elevated pH above the pK<sub>a</sub> of basic residues.<sup>56</sup>

## Mechanics of DOPA–Fe<sup>3+</sup> coordination bonds

A large amount of DOPA–Fe<sup>3+</sup> coordination moieties are found in mfp-1. These coordination bonds act as sacrificial bonds to dissipate shock energy and protect the collagen core in the thread from rupture.<sup>19</sup> In 2010, Zeng *et al.* used SFA to study the DOPA–Fe<sup>3+</sup> interactions.<sup>118</sup> They added a Fe<sup>3+</sup> solution between two mfp-1 coated surfaces and tested the cohesion strength bridged by Fe<sup>3+</sup>. Their results showed that this Fe<sup>3+</sup> mediated cohesion is fully reversible in the presence of 10 μM Fe<sup>3+</sup>. However, when the Fe<sup>3+</sup> concentration was increased to 100 μM,




Fig. 8 Schematics of SMFS study on catechol–Fe<sup>3+</sup> complex (a) and force spectroscopy (b). Reprinted with permission from ref. 100. Copyright (2017) American Chemical Society.

the cohesion abolished. They proposed a stoichiometric change in the catechol–Fe<sup>3+</sup> complex from a triple complex at a low Fe<sup>3+</sup> : catechol ratio to a mono complex at a high Fe<sup>3+</sup> : catechol ratio. The subsequent SMFS study by Li *et al.* focused on DOPA–Fe<sup>3+</sup> interactions on a single molecule level (Fig. 8).<sup>100</sup> They conjugated DOPA to HA to form the HA–DOPA polymer, and then mixed the polymer with Fe<sup>3+</sup> to form single-polymer micelles.<sup>100</sup> The experiments were performed in different solution pH and Fe<sup>3+</sup> concentrations to tune the stoichiometry of catechol–Fe<sup>3+</sup> complexes. In some conditions, the bis-catechol–Fe<sup>3+</sup> complexes were dominant and in the others, the tris-complexes were favored.

In this experiment, the single molecule micelles cross-linked by DOPA–Fe<sup>3+</sup> complexes were deposited on the glass substrates and they were picked up by non-specific interactions between the polymer with the cantilever and the surface to rupture catechol–Fe<sup>3+</sup> bonds. The force–extension curves showed sawtooth-like patterns, and each peak corresponded to a rupture of catechol–Fe<sup>3+</sup> interaction. They found that tris- and bis-DOPA–Fe<sup>3+</sup> complexes had different mechanical strengths. The averaged rupture force of bis-complex was ~200 pN, whereas the rupture force of tris-complex was ~100 pN at a pulling speed of 1000 nm s<sup>-1</sup>. By further performing dynamic force spectroscopy and fitting with Bell–Evans model, they extracted kinetic parameters for the rupture of tris- and bis-catechol–Fe<sup>3+</sup> bonds. Combining with first principle calculations, they found that the different mechanical strengths of catechol–Fe<sup>3+</sup> bonds originated from their different mechanical rupture pathways. The thermodynamically more stable tris-complexes exhibited lower mechanical stability because of the relatively larger deformation of the complexes at the transition state. They also revealed the fast rebinding kinetics of catechol–Fe<sup>3+</sup> complexes. The single-molecule results provided a nanoscale mechanical understanding of cohesive interactions in mfps mediated *via* DOPA–Fe<sup>3+</sup> coordination.




Fig. 7 Force distribution of lysine–DOPA and DOPA lysine dipeptides and the TiO<sub>2</sub> surface (a), and the schematic of the unbinding process of Dopa containing dipeptides (b). Reproduced from ref. 17 with permission from the Royal Society of Chemistry.

## From DOPA to poly-dopamine

SMFS was also applied to study the *in situ* polymerization of poly-dopamine (pDA).<sup>119</sup> Dopamine could auto-oxidize giving rise to *o*-dopamine-quinone, which cyclized to form a precursor





of polydopamine, dihydroxyindole. Although the preparation of pDA coatings is simple and easy, and the pDA coating has been widely employed in surface functionalization, some fundamental facts of pDA remain elusive. This experiment provided the first evidence that pDA is a complex polymer. They performed SMFS experiments on pDA films directly deposited on silicon nitride AFM cantilevers. Plateau pattern force–extension curves with  $\sim 200$  nm of contour length in the traces were constantly observed in their experiments, which might have resulted from the sequential desorbing of catechol containing polymers from the surface. The plateau forces were  $\sim 90$  pN. Time-dependent force spectroscopy during the early stages of pDA formation revealed that the pDA chain growth occurred at the solid–liquid interface. The formation of films likely started with the adsorption of small oligomeric species, which then underwent further polymerization and maturation to form higher-molecular-weight pDA chains. Their findings clarified that pDA is indeed a polymer instead of the aggregates of oligomers. This study may also inspire the use of SMFS to resolve complex molecule forms in surface coatings and adhesives.<sup>120</sup>

## Outlook

Despite the fact that great advances have been made towards the understanding of molecular mechanism of mussel adhesion using SFA and single molecule AFM, there are still many uncharted outstanding questions deserving further efforts. First, it remains unknown whether the other residues in mfps also contribute significantly to mussel adhesion. It was found that the foot protein, pvfp-1 from Asian green mussels, *Perna viridis*, does not contain DOPA residues but another type of unusual amino acid, C(2)-mannosyl-7-hydroxytryptophan (Man7-OHTrp).<sup>121</sup> Halogenated DOPA (2-chloro-DOPA) was also found in a large quantity in the adhesive proteins from the sandcastle worm *Phragmatopoma californica*.<sup>122</sup> It would be interesting to reveal the roles of these special residues in underwater adhesion. Second, the components of hydrophobic and charged residues vary dramatically among different mussel foot proteins and even in the same protein from different species. Even though the effects of redox potential,<sup>36</sup> hydrophobic environment,<sup>123</sup> charge–charge interactions,<sup>124</sup> and cation– $\pi$  interactions on the adhesion have been revealed,<sup>55</sup> these effects have not been quantitatively evaluated using single molecule AFM. Third, most adhesive proteins form coacervates *via* liquid–liquid phase separation. Although this phenomenon is now well appreciated in biological systems,<sup>125–127</sup> the mechanism underlying the coacervation of mussel proteins is less explored. Obviously, SFA and single-molecule AFM provide unique platforms to study liquid–liquid phase separation at the molecular level. Fourth, mussel foot proteins are not just random coiled structures and may exhibit unique secondary structures. For example, pvfp-1 from Asian green mussels shows a trimeric structure through the formation of coiled-coil structure of the C-terminus collagen sequence.<sup>121</sup> Molecular dynamics simulations revealed that Pvfp-5 $\beta$  adopts a conformation with the aromatic rings of peripheral tyrosine residues facing the solvent.<sup>128</sup> How these special conformations affect surface adhesion is eluded in the current

studies. Fifth, it was also found that mussel foot proteins rapidly self-assembled into complex architectures during the bio-fabrication of byssus.<sup>25</sup> The barnacle adhesive proteins could preassemble at a low pH value before being secreted out to enhance their underwater adhesion in basic sea water.<sup>46</sup> It will also be interesting to study how the special processing and also the surface-induced conformational change affect the adhesion behaviors. Some strong adhesion behaviors were observed in DOPA and TiO<sub>2</sub> or silica surface interactions. A reversible dynamic covalent bond could be formed in such a process, particularly in the presence of a large pressure. It would be interesting to figure out the effect of the applied pressure on DOPA adhesion. Last but not the least, how different mussel foot proteins synergistically enhance underwater adhesion by forming protein complexes also remains uncharted but is definitely critical for the understanding of the full picture of mussel adhesion mechanisms. We anticipate that these important aspects will be studied in the near future. These studies are extremely helpful for the design of mussel mimicking peptides and proteins with similar adhesion strengths but with much simplified sequences. These studies can also inspire the rational design of chemically synthesized underwater adhesives.<sup>18,129,130</sup>

## Conclusion

Mussel adhesion is a very important, yet complicated system. Despite numerous studies and applications on mussel-inspired adhesion, some of the fundamental mechanisms still remain elusive. In this article, we emphasize the importance of the biophysical studies of mussel adhesion using SFA and AFM-based single-molecule force spectroscopy to reveal the molecular mechanism underlying mussel adhesion. We show that these two methods are complementary, yet different. We explain why some seemingly conflicting results may just originate from a slightly different experimental design. As DOPA-mediated adhesion is versatile and adaptive, it will be extremely important to precisely control the surface chemistry in these measurements. It will be helpful to combine these measurements with *in situ* chemical characterization techniques, such as infrared spectroscopy and Raman spectroscopy, in the future to provide a more comprehensive understanding of mussel adhesion. We believe that with the advances of the characterization techniques, more complicated molecular mechanisms about mussel adhesion will be revealed. Such information is invaluable for the design of the next generation underwater adhesives and surface coating techniques.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This research work is financially supported by the National Natural Science Foundation of China (11674153), the Basic Research Project of Science and Technology Plan of Shenzhen



(JCYJ20170818110643669) and Natural Science Foundation of Jiangsu Province (BK20180335).

## Notes and references

- B. D. B. Tiu, P. Delparastan, M. R. Ney, M. Gerst and P. B. Messersmith, *ACS Appl. Mater. Interfaces*, 2019, **11**, 28296–28306.
- C. J. Higginson, K. G. Malollari, Y. Xu, A. V. Kelleghan, N. G. Ricipito and P. B. Messersmith, *Angew. Chem., Int. Ed.*, 2019, **58**, 12271–12279.
- G. M. Whitesides, *Interface Focus*, 2015, **5**, 20150031.
- J. H. Waite and C. C. Broomell, *J. Exp. Biol.*, 2012, **215**, 873.
- H. Li and Y. Cao, *Acc. Chem. Res.*, 2010, **43**, 1331–1341.
- S. Lv, D. M. Dudek, Y. Cao, M. M. Balamurali, J. Gosline and H. Li, *Nature*, 2010, **465**, 69–73.
- H. Lee, S. M. Dellatore, W. M. Miller and P. B. Messersmith, *Science*, 2007, **318**, 426.
- H. Lee, B. P. Lee and P. B. Messersmith, *Nature*, 2007, **448**, 338.
- Z. Huang, P. Delparastan, P. Burch, J. Cheng, Y. Cao and P. B. Messersmith, *Biomater. Sci.*, 2018, **6**, 2487–2495.
- Y. Li, C. Liang, L. Gao, S. Li, Y. Zhang, J. Zhang and Y. Cao, *Mater. Chem. Front.*, 2017, **1**, 2664–2668.
- H. G. Silverman and F. F. Roberto, *Mar. Biotechnol.*, 2007, **9**, 661–681.
- Q. Lin, D. Gourdon, C. Sun, N. Holten-Andersen, T. H. Anderson, J. H. Waite and J. N. Israelachvili, *Proc. Natl. Acad. Sci. U. S. A.*, 2007, **104**, 3782.
- Y. Li, M. Qin, Y. Li, Y. Cao and W. Wang, *Langmuir*, 2014, **30**, 4358–4366.
- H. Lee, N. F. Scherer and P. B. Messersmith, *Proc. Natl. Acad. Sci. U. S. A.*, 2006, **103**, 12999.
- Q. Lu, E. Danner, J. H. Waite, N. Israelachvili Jacob, H. Zeng and S. Hwang Dong, *J. R. Soc., Interface*, 2013, **10**, 20120759.
- Y. Li, H. Liu, T. Wang, M. Qin, Y. Cao and W. Wang, *ChemPhysChem*, 2017, **18**, 1466–1469.
- Y. Li, T. Wang, L. Xia, L. Wang, M. Qin, Y. Li, W. Wang and Y. Cao, *J. Mater. Chem. B*, 2017, **5**, 4416–4420.
- G. P. Maier, M. V. Rapp, J. H. Waite, J. N. Israelachvili and A. Butler, *Science*, 2015, **349**, 628.
- N. Holten-Andersen, M. J. Harrington, H. Birkedal, B. P. Lee, P. B. Messersmith, K. Y. C. Lee and J. H. Waite, *Proc. Natl. Acad. Sci. U. S. A.*, 2011, **108**, 2651.
- J. H. Waite and M. L. Tanzer, *Science*, 1981, **212**, 1038.
- B. P. Lee, P. B. Messersmith, J. N. Israelachvili and J. H. Waite, *Annu. Rev. Mater. Res.*, 2011, **41**, 99–132.
- J. H. Waite, T. J. Housley and M. L. Tanzer, *Biochemistry*, 1985, **24**, 5010–5014.
- V. V. Papov, T. V. Diamond, K. Biemann and J. H. Waite, *J. Biol. Chem.*, 1995, **270**, 20183–20192.
- L. M. Rzepecki, K. M. Hansen and J. H. Waite, *Biol. Bull.*, 1992, **183**, 123–137.
- H. Zhao and J. H. Waite, *Biochemistry*, 2006, **45**, 14223–14231.
- J. Yu, in *Adhesive Interactions of Mussel Foot Proteins*, ed. J. Yu, Springer International Publishing, Cham, 2014, DOI: 10.1007/978-3-319-06031-6\_4, pp. 31–41.
- H. Zhao and J. H. Waite, *J. Biol. Chem.*, 2006, **281**, 26150–26158.
- T. H. Anderson, J. Yu, A. Estrada, M. U. Hammer, J. H. Waite and J. N. Israelachvili, *Adv. Funct. Mater.*, 2010, **20**, 4196–4205.
- J. Yu, W. Wei, E. Danner, J. N. Israelachvili and J. H. Waite, *Adv. Mater.*, 2011, **23**, 2362–2366.
- S. Bahri, C. M. Jonsson, C. L. Jonsson, D. Azzolini, D. A. Sverjensky and R. M. Hazen, *Environ. Sci. Technol.*, 2011, **45**, 3959–3966.
- J. J. Wilker, *Angew. Chem., Int. Ed.*, 2010, **49**, 8076–8078.
- M. A. Gebbie, W. Wei, A. M. Schrader, T. R. Cristiani, H. A. Dobbs, M. Idso, B. F. Chmelka, J. H. Waite and J. N. Israelachvili, *Nat. Chem.*, 2017, **9**, 473.
- J. Israelachvili, Y. Min, M. Akbulut, A. Alig, G. Carver, W. Greene, K. Kristiansen, E. Meyer, N. Pesika, K. Rosenberg and H. Zeng, *Rep. Prog. Phys.*, 2010, **73**, 036601.
- R. Blankenburg, P. Meller, H. Ringsdorf and C. Saless, *Biochemistry*, 1989, **28**, 8214–8221.
- E. W. Danner, Y. Kan, M. U. Hammer, J. N. Israelachvili and J. H. Waite, *Biochemistry*, 2012, **51**, 6511–6518.
- J. Yu, W. Wei, E. Danner, R. K. Ashley, J. N. Israelachvili and J. H. Waite, *Nat. Chem. Biol.*, 2011, **7**, 588.
- B. K. Ahn, D. W. Lee, J. N. Israelachvili and J. H. Waite, *Nat. Mater.*, 2014, **13**, 867.
- Y. Cao, X. Zhang, L. Tao, K. Li, Z. Xue, L. Feng and Y. Wei, *ACS Appl. Mater. Interfaces*, 2013, **5**, 4438–4442.
- L. Burdine, T. G. Gillette, H.-J. Lin and T. Kodadek, *J. Am. Chem. Soc.*, 2004, **126**, 11442–11443.
- B. Liu, L. Burdine and T. Kodadek, *J. Am. Chem. Soc.*, 2006, **128**, 15228–15235.
- L. A. Burzio and J. H. Waite, *Biochemistry*, 2000, **39**, 11147–11153.
- L. P. Ghislain and W. W. Webb, *Opt. Lett.*, 1993, **18**, 1678–1680.
- C. Bradac, *Adv. Opt. Mater.*, 2018, **6**, 1800005.
- M. D. Newton, B. J. Taylor, R. P. C. Driessen, L. Roos, N. Cveticic, S. Allyjaun, B. Lenhard, M. E. Cuomo and D. S. Rueda, *Nat. Struct. Mol. Biol.*, 2019, **26**, 185–192.
- C. Gourier, A. Jegou, J. Husson and F. Pincet, *Cell. Mol. Bieng.*, 2008, **1**, 263.
- C. Liang, Z. Ye, B. Xue, L. Zeng, W. Wu, C. Zhong, Y. Cao, B. Hu and P. B. Messersmith, *ACS Appl. Mater. Interfaces*, 2018, **10**, 25017–25025.
- J. Wu, P. Li, C. Dong, H. Jiang, X. Bin, X. Gao, M. Qin, W. Wang, C. Bin and Y. Cao, *Nat. Commun.*, 2018, **9**, 620.
- Y. Sun, W. Di, Y. Li, W. Huang, X. Wang, M. Qin, W. Wang and Y. Cao, *Angew. Chem., Int. Ed.*, 2017, **56**, 9376–9380.
- A. M. Schrader, J. I. Monroe, R. Sheil, H. A. Dobbs, T. J. Keller, Y. Li, S. Jain, M. S. Shell, J. N. Israelachvili and S. Han, *Proc. Natl. Acad. Sci. U. S. A.*, 2018, **115**, 2890.
- J. Yu, N. E. Jackson, X. Xu, B. K. Brettmann, M. Ruths, J. J. de Pablo and M. Tirrell, *Sci. Adv.*, 2017, **3**, ea01497.
- K. K. Mahato, M. Biswal, D. K. Rathore, R. K. Prusty, K. Dutta and B. C. Ray, *IOP Conf. Ser.: Mater. Sci. Eng.*, 2016, **115**, 012017.



- 52 W. Sun, H. Jiang, X. Wu, Z. Xu, C. Yao, J. Wang, M. Qin, Q. Jiang, W. Wang, D. Shi and Y. Cao, *Nano Res.*, 2019, **12**, 115–119.
- 53 L. Zeng, M. Song, J. Gu, Z. Xu, B. Xue, Y. Li and Y. Cao, *Biomimetics*, 2019, **4**, 36.
- 54 Q. Fan, B. Chen and Y. Cao, *J. Mech. Phys. Solids*, 2019, **125**, 653–665.
- 55 M. V. Rapp, G. P. Maier, H. A. Dobbs, N. J. Higdon, J. H. Waite, A. Butler and J. N. Israelachvili, *J. Am. Chem. Soc.*, 2016, **138**, 9013–9016.
- 56 A. Leader, D. Mandler and M. Reches, *Phys. Chem. Chem. Phys.*, 2018, **20**, 29811–29816.
- 57 M. Reches and E. Gazit, *Science*, 2003, **300**, 625.
- 58 Y. Li and Y. Cao, *Chin. J. Polym. Sci.*, 2018, **36**, 366–378.
- 59 M. Mathelié-Guinlet, F. Viela, A. Vijloen, J. Dehullu and Y. F. Dufrène, *Curr. Opin. Biomed. Eng.*, 2019, **12**, 1–7.
- 60 M. Krieg, G. Fläschner, D. Alsteens, B. M. Gaub, W. H. Roos, G. J. L. Wuite, H. E. Gaub, C. Gerber, Y. F. Dufrène and D. J. Müller, *Nat. Rev. Phys.*, 2019, **1**, 41–57.
- 61 C. Feuillie, C. Formosa-Dague, L. M. C. Hays, O. Vervaek, S. Derclaye, M. P. Brennan, T. J. Foster, J. A. Geoghegan and Y. F. Dufrène, *Proc. Natl. Acad. Sci. U. S. A.*, 2017, **114**, 3738.
- 62 T. M. Kennelly, Y. Li, Y. Cao, E. E. Qwarnstrom and M. Geoghegan, *Biophys. J.*, 2019, **117**, 688–695.
- 63 Y. Deng, T. Wu, M. Wang, S. Shi, G. Yuan, X. Li, H. Chong, B. Wu and P. Zheng, *Nat. Commun.*, 2019, **10**, 2775.
- 64 W. Cai, D. Xu, L. Qian, J. Wei, C. Xiao, L. Qian, Z.-y. Lu and S. Cui, *J. Am. Chem. Soc.*, 2019, **141**, 9500–9503.
- 65 D. T. Edwards, J. K. Faulk, M.-A. LeBlanc and T. T. Perkins, *Biophys. J.*, 2017, **113**, 2595–2600.
- 66 J. Li and H. Li, *J. Phys. Chem. B*, 2018, **122**, 9340–9349.
- 67 B. Li, T. Wang, X. Wang, X. Wu, C. Wang, F. Miao, M. Qin, W. Wang and Y. Cao, *Chem.–Eur. J.*, 2019, **25**, 7991–7997.
- 68 W. Ott, M. A. Jobst, M. S. Bauer, E. Durner, L. F. Milles, M. A. Nash and H. E. Gaub, *ACS Nano*, 2017, **11**, 6346–6354.
- 69 X. Wang, B. Li, M. Qin, Y. Cao and W. Wang, *J. Biomed. Nanotechnol.*, 2018, **14**, 344–353.
- 70 S. Zhang, H.-j. Qian, Z. Liu, H. Ju, Z.-y. Lu, H. Zhang, L. Chi and S. Cui, *Angew. Chem., Int. Ed.*, 2019, **58**, 1659–1663.
- 71 P. Yang, Y. Song, W. Feng and W. Zhang, *Macromolecules*, 2018, **51**, 7052–7060.
- 72 X. Lyu, Y. Song, W. Feng and W. Zhang, *ACS Macro Lett.*, 2018, **7**, 762–766.
- 73 N. O. Alieva, A. K. Efremov, S. Hu, D. Oh, Z. Chen, M. Natarajan, H. T. Ong, A. Jégou, G. Romet-Lemonne, J. T. Groves, M. P. Sheetz, J. Yan and A. D. Bershadsky, *Nat. Commun.*, 2019, **10**, 3593.
- 74 C. Liu, J. Xia, S. Ji, Z. Fan and H. Xu, *Chem. Commun.*, 2019, **55**, 2813–2816.
- 75 B. P. Frank and G. Belfort, *Biotechnol. Prog.*, 2002, **18**, 580–586.
- 76 D. S. Hwang, H. J. Yoo, J. H. Jun, W. K. Moon and H. J. Cha, *Appl. Environ. Microbiol.*, 2004, **70**, 3352–3359.
- 77 P. Hinterdorfer, W. Baumgartner, H. J. Gruber, K. Schilcher and H. Schindler, *Proc. Natl. Acad. Sci. U. S. A.*, 1996, **93**, 3477.
- 78 S. M. Sedlak, L. C. Schendel, M. C. R. Melo, D. A. Pippig, Z. Luthey-Schulten, H. E. Gaub and R. C. Bernardi, *Nano Lett.*, 2019, **19**, 3415–3421.
- 79 M. Goktas, C. Luo, R. M. A. Sullan, A. E. Bergues-Pupo, R. Lipowsky, A. Vila Verde and K. G. Blank, *Chem. Sci.*, 2018, **9**, 4610–4621.
- 80 J. L. Zimmermann, T. Nicolaus, G. Neuert and K. Blank, *Nat. Protoc.*, 2010, **5**, 975.
- 81 R. C. Bernardi, E. Durner, C. Schoeler, K. H. Malinowska, B. G. Carvalho, E. A. Bayer, Z. Luthey-Schulten, H. E. Gaub and M. A. Nash, *J. Am. Chem. Soc.*, 2019, **37**, 14752–14763.
- 82 R. Tapia-Rojo, E. C. Eckels and J. M. Fernández, *Proc. Natl. Acad. Sci. U. S. A.*, 2019, **116**, 7873.
- 83 J. Valle-Orero, J. A. Rivas-Pardo and I. Popa, *Nanotechnology*, 2017, **28**, 174003.
- 84 A. Duran, F. J. González-Sánchez, M. J. Fernández, R. Sirera, Í. Navarro-Blasco and I. J. Alvarez, *Polymers*, 2018, **10**, 824.
- 85 E. Infante, A. Stannard, S. J. Board, P. Rico-Lastres, E. Rostkova, A. E. M. Beedle, A. Lezamiz, Y. J. Wang, S. Gulaidi Breen, F. Panagaki, V. Sundar Rajan, C. Shanahan, P. Roca-Cusachs and S. Garcia-Manyes, *Nat. Phys.*, 2019, **15**, 973–981.
- 86 J. Chung, A. M. Kushner, A. C. Weisman and Z. Guan, *Nat. Mater.*, 2014, **13**, 1055.
- 87 N. Hosono, A. M. Kushner, J. Chung, A. R. A. Palmans, Z. Guan and E. W. Meijer, *J. Am. Chem. Soc.*, 2015, **137**, 6880–6888.
- 88 C. Ray, J. R. Brown and B. B. Akhremitchev, *J. Phys. Chem. B*, 2006, **110**, 17578–17583.
- 89 I. T. S. Li and G. C. Walker, *Proc. Natl. Acad. Sci. U. S. A.*, 2011, **108**, 16527.
- 90 W. Di, X. Gao, W. Huang, Y. Sun, H. Lei, Y. Liu, W. Li, Y. Li, X. Wang, M. Qin, Z. Zhu, Y. Cao and W. Wang, *Phys. Rev. Lett.*, 2019, **122**, 047801.
- 91 B. Li, X. Wang, Y. Li, A. Paananen, G. R. Szilvay, M. Qin, W. Wang and Y. Cao, *Chem.–Eur. J.*, 2018, **24**, 9224–9228.
- 92 M. Grandbois, M. Beyer, M. Rief, H. Clausen-Schaumann and H. E. Gaub, *Science*, 1999, **283**, 1727.
- 93 M. F. Pill, K. Holz, N. Preußke, F. Berger, H. Clausen-Schaumann, U. Lüning and M. K. Beyer, *Chem.–Eur. J.*, 2016, **22**, 12034–12039.
- 94 W. Huang, X. Wu, X. Gao, Y. Yu, H. Lei, Z. Zhu, Y. Shi, Y. Chen, M. Qin, W. Wang and Y. Cao, *Nat. Chem.*, 2019, **11**, 310–319.
- 95 D. J. Echelman, A. Q. Lee and J. M. Fernández, *J. Biol. Chem.*, 2017, **292**, 8988–8997.
- 96 P. Zheng, Y. Cao, T. Bu, S. K. Straus and H. Li, *Biophys. J.*, 2011, **100**, 1534–1541.
- 97 S. Cui, C. Liu, Z. Wang, X. Zhang, S. Strandman and H. Tenhu, *Macromolecules*, 2004, **37**, 946–953.
- 98 T. Hugel, M. Grosholz, H. Clausen-Schaumann, A. Pfau, H. Gaub and M. Seitz, *Macromolecules*, 2001, **34**, 1039–1047.
- 99 L. Schmitt, M. Ludwig, H. E. Gaub and R. Tampé, *Biophys. J.*, 2000, **78**, 3275–3285.
- 100 Y. Li, J. Wen, M. Qin, Y. Cao, H. Ma and W. Wang, *ACS Biomater. Sci. Eng.*, 2017, **3**, 979–989.



- 101 P. Zheng, C.-C. Chou, Y. Guo, Y. Wang and H. Li, *J. Am. Chem. Soc.*, 2013, **135**, 17783–17792.
- 102 Y. Xue, X. Li, H. Li and W. Zhang, *Nat. Commun.*, 2014, **5**, 4348.
- 103 M. A. Hollinger, *Crit. Rev. Toxicol.*, 1996, **26**, 255–260.
- 104 W. Xiang, Z. Li, C.-Q. Xu, J. Li, W. Zhang and H. Xu, *Chem. – Asian J.*, 2019, **14**, 1481–1486.
- 105 W. Wei, Y. Sun, M. Zhu, X. Liu, P. Sun, F. Wang, Q. Gui, W. Meng, Y. Cao and J. Zhao, *J. Am. Chem. Soc.*, 2015, **137**, 15358–15361.
- 106 C. F. Shaw, *Chem. Rev.*, 1999, **99**, 2589–2600.
- 107 S. R. K. Ainarapu, J. Brujić, H. H. Huang, A. P. Wiita, H. Lu, L. Li, K. A. Walther, M. Carrion-Vazquez, H. Li and J. M. Fernandez, *Biophys. J.*, 2007, **92**, 225–233.
- 108 G. I. Bell, *Science*, 1978, **200**, 618.
- 109 E. Evans and K. Ritchie, *Biophys. J.*, 1999, **76**, 2439–2447.
- 110 Y. Wang, J. Yan and B. T. Goult, *Biochemistry*, 2019, DOI: 10.1021/acs.biochem.9b00453.
- 111 R. W. Friddle, A. Noy and J. J. De Yoreo, *Proc. Natl. Acad. Sci. U. S. A.*, 2012, **109**, 13573.
- 112 J. Wang, M. N. Tahir, M. Kappl, W. Tremel, N. Metz, M. Barz, P. Theato and H.-J. Butt, *Adv. Mater.*, 2008, **20**, 3872–3876.
- 113 T. Utzig, P. Stock and M. Valtiner, *Angew. Chem., Int. Ed.*, 2016, **55**, 9524–9528.
- 114 S. Kinugawa, S. Wang, S. Taira, A. Tsuge and D. Kaneko, *Polym. J.*, 2016, **48**, 715.
- 115 P. Das and M. Reches, *Nanoscale*, 2016, **8**, 15309–15316.
- 116 S.-C. Li, L.-N. Chu, X.-Q. Gong and U. Diebold, *Science*, 2010, **328**, 882.
- 117 S. A. Mian and Y. Khan, *Am. J. Chem.*, 2017, **2017**, 6.
- 118 H. Zeng, D. S. Hwang, J. N. Israelachvili and J. H. Waite, *Proc. Natl. Acad. Sci. U. S. A.*, 2010, **107**, 12850.
- 119 P. Delparastan, K. G. Malollari, H. Lee and P. B. Messersmith, *Angew. Chem., Int. Ed.*, 2019, **58**, 1077–1082.
- 120 X. Kang, W. Cai, S. Zhang and S. Cui, *Polym. Chem.*, 2017, **8**, 860–864.
- 121 D. S. Hwang, H. Zeng, Q. Lu, J. Israelachvili and J. H. Waite, *Soft Matter*, 2012, **8**, 5640–5648.
- 122 C. J. Sun, A. Srivastava, J. R. Reifert and J. H. Waite, *J. Adhes.*, 2009, **85**, 126.
- 123 W. Wei, J. Yu, C. Broomell, J. N. Israelachvili and J. H. Waite, *J. Am. Chem. Soc.*, 2013, **135**, 377–383.
- 124 J. Yu, Y. Kan, M. Rapp, E. Danner, W. Wei, S. Das, D. R. Miller, Y. Chen, J. H. Waite and J. N. Israelachvili, *Proc. Natl. Acad. Sci. U. S. A.*, 2013, **110**, 15680.
- 125 S. F. Banani, H. O. Lee, A. A. Hyman and M. K. Rosen, *Nat. Rev. Mol. Cell Biol.*, 2017, **18**, 285.
- 126 J. B. Woodruff, A. A. Hyman and E. Boke, *Trends Biochem. Sci.*, 2018, **43**, 81–94.
- 127 Y. Shin and C. P. Brangwynne, *Science*, 2017, **357**, eaaf4382.
- 128 L. Petrone, A. Kumar, C. N. Sutanto, N. J. Patil, S. Kannan, A. Palaniappan, S. Amini, B. Zappone, C. Verma and A. Miserez, *Nat. Commun.*, 2015, **6**, 8737.
- 129 B. K. Ahn, S. Das, R. Linstadt, Y. Kaufman, N. R. Martinez-Rodriguez, R. Mirshafian, E. Kesselman, Y. Talmon, B. H. Lipshutz, J. N. Israelachvili and J. H. Waite, *Nat. Commun.*, 2015, **6**, 8663.
- 130 R. Santonocito, F. Venturella, F. Dal Piaz, M. A. Morando, A. Provenzano, E. Rao, M. A. Costa, D. Bulone, P. L. San Biagio, D. Giacomazza, A. Sicorello, C. Alfano, R. Passantino and A. Pastore, *J. Biol. Chem.*, 2019, **34**, 12826–12835.

