

Cite this: *Chem. Sci.*, 2019, 10, 257

All publication charges for this article have been paid for by the Royal Society of Chemistry

Hybrid CuCoO–GO enables ultrasensitive detection of antibiotics with enhanced laser desorption/ionization at nano-interfaces†

Enhui Wu,^{‡a} Kun Feng,^{‡a} Rui Shi,^{‡a} Rui Lv,^a Fuzhong Ouyang,^a Shawn S. C. Li,^b Jun Zhong^{ID}*^a and Jian Liu^{ID}*^a

The soaring concerns globally on antibiotic overuse have made calls for the development of rapid and sensitive detection methods urgent. Here we report that the hybrid CuCoO–GO matrix allows for sensitive detection of various antibiotics in combination with MALDI TOF MS. The new matrix is composed of few-layered GO nanosheets decorated with CuCoO nanoparticles with an average size of 10 nm, and exhibits excellent aqueous suspensibility. Accurate quantitation of the sulfonamide antibiotics in milk samples have been demonstrated using a CuCoO–GO matrix and a stable isotope (C^{13})-labeled analyte as the internal standard. Our experiments have achieved lower limits of detection (LOD) by several hundred fold for the detection of a panel of representative antibiotics, in comparison with the literature reports. Both intrabacterial and extrabacterial residual antibiotics can be sensitively detected with our method. We have further investigated the molecular mechanism of the enhanced desorption/ionization efficiency by the CuCoO–GO matrix with synchrotron radiation techniques for the first time. This work provides a sensitive matrix enabling MALDI-TOF MS to be applied in small molecular analysis, but also presents a distinct perspective on the mechanism behind the material functions.

Received 18th August 2018
Accepted 5th October 2018

DOI: 10.1039/c8sc03692f

rsc.li/chemical-science

Introduction

There are growing concerns globally over the inappropriate use of antibiotics which are polluting the environment, contributing to food contamination, and threatening the medical practice of public health.^{1–5} A report in the literature reveals that early exposure to antibiotics may lead to potentially long-term harmful impacts by changing gut microbiota, brain cytokines and behavior.¹ It has become a more serious danger to human healthcare with the emergence of “superbugs” induced by the overuse of antibiotics.³ Increasing needs demand the development of rapid and sensitive techniques to detect various antibiotics in trace amounts. The traditional methods include microbial growth inhibition assays,⁶ chromatography,^{7–9} immunochemical detection,^{10–12} as well as receptor- or enzyme-based tests.¹³ However, they are subject to several critical limitations. Assays of microbial growth inhibition suffer from low sensitivity and many factors interfere in signal reading.⁶

Chromatographic methods require lengthy procedures for sample-pretreatment.^{7,9} Receptor-based screening methods, such as radio-receptor assay, enzyme-labelling receptor assay, colloidal gold-labelling receptor assay and enzyme colorimetry are limited by enzymatic activity fluctuations and labelling-reagent contamination.^{12,13}

Matrix-assisted laser desorption/ionization time-of-flight mass spectrometry (MALDI-TOF MS) is an indispensable tool for the analysis of biomolecules, with the advantages of high sensitivity, high throughput, and a fast procedure to obtain results.^{14–21} However, the conventional organic matrices (CHCA, DHB, SA, *etc.*) widely used in MALDI-TOF MS are subject to their own structural fragmentation by lasers, which generates intensive background noise below m/z 700 intrinsically. This overwhelms the true signals of small molecular analytes, thus severely limiting the applications of MALDI-TOF MS in the (m/z < 700) molecular range.^{22,23} Researchers have attempted to synthesize different types of organic molecules as replaceable matrix candidates to suppress background noise.^{24,25} Alternatively, various inorganic nanomaterials and nanostructures have been proposed as MALDI matrices to increase the signal to noise ratio in the detection of small molecules, including silicon, metal, metallic oxide and carbon-based nanomaterials.^{26–34} Among them, graphene oxide (GO) is attractive due to its large surface area, good light absorption, and excellent optoelectric properties.³² It has been suggested that graphene oxide/multi-walled carbon nanotube composites can

^aInstitute of Functional Nano and Soft Materials (FUNSOM), Jiangsu Key Laboratory for Carbon-based Functional Materials and Devices, Joint International Research Laboratory of Carbon-based Functional Materials and Devices, Soochow University, Suzhou, Jiangsu Province 215123, China. E-mail: jliu@suda.edu.cn; jzhong@suda.edu.cn

^bDepartment of Biochemistry, Western University, London, Ontario N6A 5C1, Canada

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c8sc03692f

‡ These authors contributed equally to this work.



promote small molecule detection by MALDI MS because of the improved wettability in water and enlarged surface area.³² However, many nanomaterial-based matrices still suffer from drawbacks such as the background noise generated by their inherent structural defects, or the relatively lower efficiency in assisting molecular ionization.^{34–36}

Herein, we report an important discovery and mechanism revelation for the sensitive detection of various antibiotics using hybrid CuCoO–GO as the MALDI matrix. Previously we reported that tuning the ratio of copper and cobalt atoms in their metal oxide–graphene composite could maximize the electron transfer properties for a synergistic catalytic performance in the hydrolysis of ammonia borane.³⁷ In this work, we hypothesize that the electron transfer properties of hybrid CuCoO–GO could promote the ionization of small molecules under laser irradiation, with significant improvement in the signal to noise ratios in MS spectral analysis. We have demonstrated that the CuCoO–GO matrix enables the detection of 7 representative antibiotics with lower limits of detection (LOD) by several hundred fold. Accurate results with absolute quantitation of the antibiotic in milk samples have been demonstrated using our approach integrated with a stable isotope-labelled analyte as the internal standard. Intrabacterial and extrabacterial antibiotic residues can be sensitively detected using our method. For the first time, we have revealed the mechanism of molecular deprotonation assisted by a CuCoO–GO matrix for its high performance in MALDI-TOF MS with synchrotron radiation techniques. This work provides a sensitive and robust matrix enabling MALDI-TOF MS applications in small molecule analysis, but also offers a distinctly important perspective on the molecular mechanism behind the material functions.

Experimental

Chemicals

All of the chemicals were purchased from Sigma Aldrich, Aladdin Industrial Corporation, or Shanghai Macklin Biochemical Co., Ltd. Sulfapyridine-¹³C was bought from WITEGA Laboratorien Berlin-Adlershof GmbH (Germany). The milk samples were purchased from a local grocery store. Deionized water (18 MΩ cm⁻¹) was used in the experiments.

Preparation of CuCoO–GO

A modified Hummers' method was used to prepare graphene oxide (GO) from natural graphite. A GO solution was prepared by re-suspending 80 mg GO in 80 mL isopropanol, followed by sonication for 20 min. 38.3 mg (0.192 mmol) Cu(CH₃COO)₂·H₂O and 12 mg (0.048 mmol) Co(CH₃COO)₂·4H₂O were mixed with the GO isopropanol solution. The mixture was heated to 80 °C for 1 h with a reflux set-up. After 80 mL of deionized water was added into the reaction, the mixture was kept at 80 °C for 30 min. The product was cooled to room temperature, then collected by centrifugation at 8000 rpm for 3 min with an ethanol rinse. This was dried in an oven at 70 °C for 12 h. The samples of CuCoO–GO with different Cu/Co atom ratios (including CuO–GO) were prepared similarly by referring to this procedure.³⁷

Characterization

High-resolution transmission electron microscopy (HRTEM) images were acquired with a FEI Tecnai G2 F20 S-TWIN TEM. Atomic force microscopy (AFM) images were obtained by using a Veeco Multimode V atomic force microscope. Raman spectra were collected using a HR 800 Raman spectroscope (J Y, France). The Fourier Transform Infrared (FT-IR) spectrum was obtained using a Bruker Fourier Transform Infrared Spectrometer (Hyperion). X-ray photoelectron spectroscopy (XPS) characterization was performed with a KRATOS Axis ultra DLD X-ray photoelectron spectroscope. X-ray diffraction (XRD) data were collected by a PANalytical B.V. Empyrean powder diffractometer equipped with a PIXcel3D detector. Scanning electron microscope (SEM) images of samples were acquired by an S-4700 SEM (Hitachi, Japan).

Sample preparation for MALDI-TOF MS analysis

The conventional organic matrices of α -cyano-4-hydroxycinnamic acid (CHCA) and 3,5-dimethoxy 4-hydroxycinnamic acid (SA) were individually prepared by a standard method.^{38,39} Graphene oxide, CuO–GO, CuO, CuCoO, CuCoO–GO were all dispersed in water at a concentration of 1 mg mL⁻¹. The analytes of 7 different antibiotics and 3 additional chemical analogs, including sulfadiazine (SDZ), sulfamethoxazole (SMX), norfloxacin, ampicillin, benzylpenicillin, streptomycin, tetracycline, sulfapyridine, sulfonamide and pyrimethanil, were dissolved in water or ethyl alcohol as the standard mother solutions. They were subsequently diluted to a series of different concentrations as specified in the experiments. The sample spots on the MALDI plate were prepared by a standard method of sandwiching the matrix and analyte solutions. The liquid volume in each pipetting step for one sample spot was 1 μ L. The milk samples were mixed with different concentrations of the antibiotic solutions for the tests. They were defatted by mixing with 20% TFA and citrate buffer (0.4 M, pH = 4), followed by centrifugation (4000 rpm for 20 min) to collect the supernatants for MALDI-TOF MS analysis.⁴⁰

Mass Spectrometry

The MALDI-TOF MS data were acquired using a MALDI TOF/TOF Ultraflex extreme mass spectrometer equipped with a Smart-Beam II Nd:YAG/355 nm laser operating at 2000 kHz (Bruker Daltonics, Inc., Billerica, MA), either in the reflective positive-ion or negative-ion mode. The laser energy was optimized at 30% corresponding to 57 μ J per pulse (laser pulse duration: 3 ns). The laser spot size was approximately 50–100 μ m. Each sample was tested with a repetition of $n = 4$. An accumulation of 3000 laser shots was applied for each spectrum.

For the comparison of different matrices, the negative ion mode was carried out using CuCoO–GO, GO, CuO–GO, and CuCoO as nano-matrices for detection of SDZ and SMX. In addition, the noise baselines of traditional matrices of CHCA and SA were also included in the measurements under identical instrumental conditions.





Fig. 1 Characterization of CuCoO-GO (CuO-GO and GO as the control samples). (a) TEM image; (a1) dark-field TEM image; (a2) zoomed-in view of the dark-field in the red box; (a3 and a4) corresponding elemental mapping in the red box: Cu (green) and Co (brown). Sample: CuCoO-GO; scale bars as specified. (b) AFM image of CuCoO-GO in the larger field of view; (b1) AFM of a single nanosheet of CuCoO-GO; (b2) height profile along the corresponding blue line of (b1). Scale bars: 5 μm . (c and d) Raman spectra and X-ray diffraction (XRD) patterns of GO, CuO-GO and CuCoO-GO.

CuCoO-GO matrix in the ionization of small molecular antibiotics for detection (Fig. S4[†]).

We performed quantitative analysis on SDZ by including an isotope labelled analog of the analyte with reference to the standard method. Stable isotope labelled sulfapyridine-¹³C was selected as the internal standard due to its great similarity in chemical structure to SDZ. It was further validated for being a good choice by the linear calibration curves in the titration of SDZ concentrations in MALDI MS. As shown in Fig. 2c, the characteristic peaks for SDZ (m/z 249) and sulfapyridine-¹³C (m/z 254) are presented in the mass spectra. The intensities of these peaks are consistent with their spiking ratios in the water or the milk samples. There is excellent linearity for the calibration curve in the aqueous solution prepared with either water ($R^2 = 0.983$) or milk ($R^2 = 0.982$) between the MS signal intensity ratios (SDZ: sulfapyridine-¹³C) and the concentrations of SDZ (10–1000 $\mu\text{g L}^{-1}$). In addition, the MS spectrum of the blank milk without any antibiotic addition is available in the ESI (Fig. S5[†]) as the negative control. It verifies that the characteristic peaks of the antibiotic analytes are not contaminated. These results provide good evidence to demonstrate the usefulness of our approach with the CuCoO-GO matrix for residual antibiotic quantification in milk samples.

The limit of detection (LOD) using our approach was determined by titrating the analytes and linear extrapolation of the signal-to-noise ratio ($S/N = 3$), according to the standard method.⁴² As previously demonstrated in Fig. 2, the CuCoO-GO

matrix is featured with a clean baseline in MALDI MS, which is important for improved LOD in the detection of antibiotics. The detailed values of LOD are summarized in Table S1 and Fig. S6 in the ESI,[†] including SDZ, SMX, and the other five representative antibiotics. For instance, the LOD for SDZ antibiotic is 0.5 $\mu\text{g L}^{-1}$ by our approach, which is nearly 500 fold lower than the previously reported results in the literature. This value is also far lower than the maximum residue limit (MRL, 250 $\mu\text{g L}^{-1}$ for SDZ) in the milk regulated by the China National Standards. The superior performance of the CuCoO-GO matrix was validated by testing the other antibiotics in the list (Table S1[†]), and comparing with the results using different matrices (including graphene, graphene oxide, and other common matrices) in the literature.^{15,40,43–45} This suggests that our approach of using the CuCoO-GO matrix can sufficiently meet the technical requirement for the sensitive detection of antibiotics.

Antibiotic susceptibility testing (AST) has been widely used in clinical microbiology labs to determine sensitiveness or the resistance of individual bacterial isolates to any specific antimicrobial agents. The methods for AST include broth dilution test, antimicrobial gradient method, disk diffusion test, or AST stripes, which typically rely on optical measurements or empirical naked-eye observations.⁴¹ Recently an important advance of TiO₂-assisted MALDI TOF MS was developed to detect antimicrobial resistance-relevant proteins while minimizing sample preparation steps, which promotes simultaneous species identification and antimicrobial resistance





Fig. 2 High performance of the CuCoO-GO matrix in MALDI mass spectrometry for antibiotic analysis. (a) The background noise of the CuCoO-GO matrix in comparison with traditional organic matrices of CHCA and SA, in the negative-ion mode. (b) The mass spectra of SDZ and SMX in the positive-ion and negative-ion modes using the CuCoO-GO matrix. (c) Mass spectra of SDZ and sulfapyridine- ^{13}C (internal standard) in water solution or the milk sample, and the calibration curves for absolute quantitation of SDZ in the negative-ion mode ($n = 4$). Error bars: standard deviation.

analysis.⁴⁶ Inspired by this work, we attempted to explore the utility of the CuCoO-GO matrix for the application of antimicrobial resistance analysis by measuring both the intrabacterial and extrabacterial antibiotic residues (Fig. 3a). We performed AST experiments to test the antibiotic SDS on *E. coli* and *S. aureus*, using a standard microdilution assay (Fig. S7†). The morphological changes of *E. coli* and *S. aureus* induced by the antibiotic treatments were characterized by scanning electron microscopy (SEM, Fig. S8†). The bacterial samples treated with different concentrations of SDS were centrifuged to separate the supernatants and bacterial pellets, which were subsequently processed to analyze the antibiotic residues inside or outside the bacteria by CuCoO-GO assisted MALDI MS. As shown in Fig. 3b and c, in the mass spectra of *E. coli* and *S. aureus* lysates, the characteristic peaks of SDS (m/z 273), sulfapyridine- ^{13}C (m/z 278), and a potential metabolite (4-OH-SDS, m/z 289) can be clearly identified. The calibration curve in the plot (Fig. 3d) according to the standard isotope internal control method exhibits a good linearity ($R^2 = 0.982$), indicating a reliable performance of our approach for the antibiotic quantification using the samples of bacterial cultivation. As shown in Fig. 3e and f, the residual SDS outside and inside the *E. coli* or *S. aureus*

after antibiotic treatment can be quantitatively analyzed. It suggests a trend that the proportion of SDS penetrating and leftover inside the bacteria increases, driven by the increase of the initial antibiotic dosages. Aligned to the standard AST experiments, our method can provide more detailed information on the uptake and potential metabolic changes of antibiotics, which are essential for the understanding of bacterial resistance mechanisms.^{28,47}

Our design of hybridizing CuCoO nanoparticles on GO nanosheets is critical for the development of a high performance matrix. Indeed, GO plays an important role in this hybrid nanomaterial. GO nanosheets contain aromatic structures and chemical groups such as hydroxyl, epoxy, and carboxyl groups, enhancing molecular interactions with analytes and serving as a matrix choice.^{32,48} We designed experiments to compare the performance of CuO or CuCoO nanoparticles without GO, and the CuCoO-GO hybrid matrix in the detection of SDZ and SMX molecules. In contrast to the high efficiency of CuCoO-GO in the ionization of small molecules, CuO or CuCoO nanoparticles as the matrix can only produce very low signals for the detection of SDZ or SMZ. The difference in the signal intensity is nearly two orders of magnitude (Fig. S9†). This suggests that bare CuO





Fig. 3 (a) Schematic diagram of antibiotic detection comparing our method to standard antibiotic susceptibility testing (AST). (b) Mass spectrometry data of *E. coli* lysates. (c) Mass spectrometry data of *S. aureus* lysates. O, Δ and # represent peaks of SDS, sulfapyridine-¹³C and a potential SDS metabolite in (b) and (c). (d) The calibration curves for absolute quantitation of sulfadiazine sodium using sulfapyridine-¹³C as the internal standard ($n = 4$). (e) Extrabacterial and (f) intrabacterial SDS residue detected by our method, after the treatment of bacteria for 20 h with different antibiotic dosages: 2 mg mL⁻¹, 1 mg mL⁻¹, 0.5 mg mL⁻¹ light blue: *E. coli*; green: *S. aureus*. Data points were collected from 2 separate batches. Each of the batches contained a repetition of 4 in parallel. Error bar: standard deviation.

or CuCoO nanoparticles without GO as the matrix are limited when promoting small molecule ionization. In addition, we compared the efficiency in laser desorption ionization (LDI) of the analytes using different types of graphene oxide-based

matrices including GO, CuO-GO, CuCoO-GO under identical conditions. As shown in Fig. 4, both SDZ and SMX can be detected by using any of the above matrices. However, there appears to be prominent differences among these GO-based



matrices in terms of the signal-to-noise (S/N) ratios for the detection of the antibiotic analytes. The CuCoO-GO matrix allows for the detection of either SDZ or SMX with the highest S/N ratio, which is approximately 2 fold higher than the CuO-GO matrix, or 8 fold higher than the bare GO matrix. The significantly enhanced S/N ratio by the CuCoO-GO matrix suggests a synergistic effect on LDI of the analytes, contributed to by the hybrid nanosystem of metal oxides and GO.

Mechanistic studies by synchrotron radiation-based techniques

Synchrotron radiation-based X-ray absorption spectroscopy (XAS) has been widely used to reveal the chemical state information of elements in various materials.^{37,49,50} Here we employed this technique to explore the absorption changes of the specific elements in the CuCoO-GO matrix with/without small molecule analytes for mechanistic studies. The C K-edge XAS spectra (Fig. S10†) validate the interactions between SDZ molecules and CuCoO-GO nanosheets accompanying adsorption. The pristine sample of CuCoO-GO exhibits a XAS spectrum similar to typical GO-based materials as reported in the literature.³⁷ The sample CuCoO-GO after addition of SDZ presents clear signals for its adsorption with the evidence the shifted peak A and the intensity increase in peak B. After the addition of the analyte (SDZ), there is no significant shift in the absorption peak of the Cu L-edge in CuO-GO (black, red curves in Fig. 5a and b). In contrast, the absorption peak of the Cu L-edge in CuCoO-GO is shifted to a higher energy level

($\Delta E \approx 0.3$ eV), suggesting a change for the higher chemical state of the Cu element (blue, purple curves in Fig. 5a and b). This change can be attributed to the interactions between SDZ and the Cu element, which induce an effect of partial electron shift from Cu to O in SDZ. Compared to CuO-GO, CuCoO-GO with Co doping may facilitate a delocalized electron effect by promoting interactions between CuCoO and GO. Furthermore, in the *in situ* Cu K-edge XAS experiments (Fig. 5c and d and S11†), addition of SDZ results in an intensity increase for the absorption peak of CuCoO-GO, corresponding to a chemical state change of Cu due to a partial electron shift to atoms with higher electronegativity such as the oxygen atom. These results are consistent with the previous measurements of Cu L-edge absorption in Fig. 5a and b. Interestingly, there is an inverse change for the absorption peak intensity at the Cu K-edge when the sample mixture of CuCoO-GO and SDZ is illuminated *in situ* by UV light. This suggests recovery of the chemical state of copper, accompanying the removal of SDZ and a drop in the interactions between SDZ and Cu due to UV irradiation.

We propose a mechanism for the ionization of small molecules with the CuCoO-GO matrix, based on the above experimental evidence collectively (Fig. 6). The hybrid nanomaterial CuCoO-GO is able to ionize the small molecular analyte (SDZ) with high efficiency assisted by clustered Cu, Co, O atoms on the GO nanosheets. SDZ molecules can be adsorbed on the surface of CuCoO-GO by hydrogen bonds and van der Waals forces. The Cu and O sites on the matrix can respectively interact with the S=O bond and the -NH- group in the SDZ molecule. The



Fig. 4 Comparison of performance of GO, CuO-GO and CuCoO-GO matrices in the MALDI-TOF MS detection of antibiotics. (a–c) SDZ; (d–f) SMX, under identical conditions (in the negative-ion mode, accumulated to 3000 shots, concentration: SDZ with $0.05 \mu\text{g mL}^{-1}$, SMX with $1 \mu\text{g mL}^{-1}$).





Fig. 5 Investigation on the interactions between SDZ and CuCoO-GO by synchrotron radiation-based techniques. (a) Hard X-ray XAS spectra of CuO-GO and CuCoO-GO with and without addition of SDZ. (b) Zoomed-in view of the peaks highlighted in the blue circles of (a). (c) *In situ* hard X-ray XAS spectra of CuCoO-GO at the Cu K-edge (d) Zoomed-in view of the peaks highlighted in the blue circle of (c).

presence of Co as the doping element in the matrix enables enhanced interactions between the atom clusters and GO, which could promote charge transfer between the CuCoO-GO matrix and SDZ in the ionization process. The energy input by laser may facilitate the deprotonation of SDZ, allowing for the ionized small molecule (SDZ) to be detected by the mass analyzer in the MALDI-TOF MS instrument. The hybrid CuCoO-GO nanomaterial tends to exhibit a high proton affinity due to

the delocalized pi-electron system across the GO surface. Due to the synergistic effect of the Co and Cu bimetallic oxides on the GO nanosheets, this hybrid matrix turns out to improve the ionization efficiency of small molecules, thus promoting their MS signal-to-noise ratios in detection.

The proposed mechanism is suitable for the negative-ion mode in MALDI MS, by taking advantage of the enhanced interactions between small molecules and the CuCoO-GO



Fig. 6 Schematic diagram of the mechanism of SDZ ionization using the CuCoO-GO matrix for MALDI TOF mass spectrometry.



