


 Cite this: *Chem. Commun.*, 2023, 59, 944

 Received 30th August 2022,
 Accepted 19th December 2022

DOI: 10.1039/d2cc04810h

rsc.li/chemcomm

Hybrid photocathode based on a Ni molecular catalyst and Sb₂Se₃ for solar H₂ production†

 D. Alicia Garcia-Osorio,^a Thomas P. Shalvey,^a Liam Banerji,^a Khezar Saeed,^{id} ^{ab}
 Gaia Neri,^{‡a} Laurie J. Phillips,^a Oliver S. Hutter,^{id} ^{ac} Carla Casadevall,^{id} ^d
 Daniel Antón-García,^{id} ^d Erwin Reisner,^{id} ^d Jonathan D Major^{*a} and
 Alexander J Cowan^{id} ^{*a}

We report a H₂ evolving hybrid photocathode based on Sb₂Se₃ and a precious metal free molecular catalyst. Through the use of a high surface area TiO₂ scaffold, we successfully increased the Ni molecular catalyst loading from 7.08 ± 0.43 to 45.76 ± 0.81 nmol cm⁻², achieving photocurrents of 1.3 mA cm⁻² at 0 V vs. RHE, which is 81-fold higher than the device without the TiO₂ mesoporous layer.

Photoelectrodes for the production of solar fuels, for example by splitting water to generate H₂ and O₂,¹ have the potential to play a key role in future energy systems. However, advances in both photoanodes for water oxidation² and photocathodes for hydrogen evolution (HER) are needed to improve the stability and to lower the cost for industrial scaling, since most long-lasting devices rely on precious metals.^{3–5} Sb₂Se₃ has recently gained interest from the photovoltaic (PV) community due to its near-direct band gap of 1.18 eV, a high absorption coefficient across the visible region,⁶ and an unusual 1D nanoribbon structure that enables effective charge transport.⁷ These properties, combined with improvements in material processability and the use of earth-abundant elements, have led to the suggestion that Sb₂Se₃ could be a viable thin film PV material for use on a global scale.⁸ Sb₂Se₃ has also been studied as a photocathode for HER, the conduction band minimum at –0.5 V vs. RHE provides enough driving force for producing H₂,⁹ and its band gap (*E_g*) is very close to the optimal calculated for the bottom electrode in dual absorber standalone device for water splitting.¹⁰ Reported solar to hydrogen efficiencies, using state-of-the-art Sb₂Se₃ photocathodes, have now exceeded 10%.^{11,12} These photocathodes consist of a Sb₂Se₃/CdS buried

junction that is coated with a protective TiO₂ capping layer. The planar TiO₂ is then modified with a HER catalyst like Pt,^{13,14} RuO₂,^{12,15} and MoS_x.¹⁶ Notably, even with state-of-the-art devices, reductive dissolution of TiO₂ caused by photoelectron accumulation can occur.^{11,13} C₆₀ between TiO₂ and the H₂-evolution catalyst can alleviate charge accumulation promoting the photoelectron transfer at the TiO₂/Pt interface, but device stabilities are still low.^{11,13} Therefore, a need still exists to identify new active photoelectrode/catalysts systems that are able to keep up with the rate of photoelectron generation and to explore how the catalyst/TiO₂ interface can be modified to prevent the generation of high-electron densities. Earth abundant molecular electrocatalysts have not previously been explored on Sb₂Se₃ photocathodes, even though they are an alternative to precious metal electrocatalysts and could potentially offer improved rates of charge transfer at the semiconductor/molecular catalyst interface.^{17,18} Here, **NiP** with a [Ni(P₂^RN₂^{R'})₂]²⁺ core (P₂^RN₂^{R'} = bis(1,5-R'-diphospha-3,7-R''-diazacyclooctane)), shown in Fig. 1b, was chosen as model molecular catalyst.¹⁹ The **NiP** catalyst mimics the hydrogenase intramolecular proton transfer to the Ni centre through the pendant amine groups in the second coordination sphere.²⁰ Furthermore, it can be covalently anchored to TiO₂ by the phosphonic acid groups in the outer coordination sphere, Fig. 1b.²¹

The complete device FTO/Au/Sb₂Se₃/CdS/TiO₂/TiO₂-*meso*/NiP is shown in Fig. 1a. Sb₂Se₃ (1.5 μm) was deposited on Au (70 nm) coated fluorine-doped SnO₂-glass (FTO) by a two-step fast-cooling close space sublimation process, which generates a compact preferentially orientated nanoribbon crystal structure that facilitates rapid hole transfer to the Au contact.^{7,11,12} Then, a thin sputtered CdS buffer layer (20 nm) was added which forms a Sb₂Se₃ heterojunction with a negligible conduction band offset, thereby allowing efficient charge separation and electron transfer towards TiO₂ (Fig. 1c).⁶ In this way, the onset potential and fill factor of the Sb₂Se₃ photocathodes are improved despite the parasitic absorption of photons below λ < 500 nm in the CdS causing a decrease in the photocurrent.^{11,12} After, TiO₂ (100 nm) was sputtered to provide a physical barrier preventing contact between the light absorber

^a Stephenson Institute for Renewable Energy, University of Liverpool, L69 7ZF, UK.
 E-mail: acowan@liverpool.ac.uk

^b Department of Chemistry, Aarhus University, Aarhus C 8000, Denmark

^c Department of Mathematics, Physics and Electrical Engineering,

Northumbria University, NE1 8ST, UK

^d Yusuf Hamied Department of Chemistry, University of Cambridge, CB2 1EW, UK

 † Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d2cc04810h>

‡ Current address: Enapter S.R.L, via di Lavoria 56/g, 56040 Pisa.





Fig. 3 (a) Cross-sectional SEM image of $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}/\text{NiP}$. (b–d) XPS spectra of **NiP** molecular catalyst (blue trace) after it is immobilized on TiO_2 (pre-CPP, black trace), and after 5 h of CPP test at 0 V vs. NHE (post-CPP, red trace) with light intensity of 100 mW cm^{-2} and $\lambda > 340 \text{ nm}$ in $0.1 \text{ M Na}_2\text{SO}_4$ at pH 3. (b–d) XPS spectra showing Ni 2p, P 2p and N 1s regions respectively.

provides the state-of-the-art hybrid photocathodes for H_2 production. **NiP** has been previously used with a $\text{Si}/\text{TiO}_2\text{-meso}$ photocathode to achieve a photocurrent of -0.3 mA cm^{-2} at 0 V vs. RHE²⁴ and -0.6 mA cm^{-2} at 0 V vs. RHE for a $\text{La}_5\text{Ti}_2\text{Cu}_{0.9}\text{Ag}_{0.1}\text{S}_5\text{O}_7/\text{TiO}_2$ photocathode.²³ A control experiment without the catalyst ($\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}$, Fig. S2.4, ESI[†]) demonstrates the importance of the **NiP** catalyst, it showed a photocurrent of only -0.12 mA cm^{-2} at 0 V vs. RHE. Incident photon to current efficiency (IPCE, Fig. S2.12, ESI[†]) demonstrates the device is active at wavelengths up to 900 nm (at 0 V vs. RHE), in-line with the E_g of Sb_2Se_3 .^{6,7}

Controlled potential photoelectrolysis (CPP) carried out at 0 V vs. RHE assessed the stability of the $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}/\text{NiP}$ electrode, results shown in Fig. 4. The H_2 faradaic efficiency after 1 h was $77.5 \pm 9.1\%$, giving a TON_{NiP} of 12.8 ± 2.8 . However, the photocurrent decreased significantly in the first hour reaching $-40 \mu\text{A cm}^{-2}$ and by 5 hours, it decreased to only $-15 \mu\text{A cm}^{-2}$ (Fig. S2.13, ESI[†]). The loss of photoactivity of **NiP** photoelectrodes has previously been attributed to the hydrolysis of the phosphonic anchoring group from the TiO_2 .^{23,24} XPS analysis of the hybrid photocathode post CPP shows the loss of the Ni^{2+} bands (red trace, Fig. 3b). However, it is clear that both the N 1s and P 2p signals are still present, although significantly shifted. A broadening of the N 1s band has previously been assigned to protonation of the amine in the acidic electrolyte²³ and the shifting of the P band is due to the loss of the metal centre.²⁸ The XPS results suggest the phosphonate linkage has been retained but the Ni is no longer coordinated to the ligand, in-line with the stability of the phosphonate linkage at pH < 7.²⁹ Past studies have shown that **NiP** degradation occurs on photocathodes but with a slower decay rate.^{23,24}



Fig. 4 CPP at 0 V vs. RHE of the hybrid photocathodes $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2/\text{NiP}$ (a) and $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}/\text{NiP}$ (b) in $0.1 \text{ M Na}_2\text{SO}_4$ pH 3 at 100 mW cm^{-2} and $\lambda > 340 \text{ nm}$.

To explore the mechanism of the hybrid photocathode decay here, we examined the $\text{TiO}_2\text{-meso}/\text{NiP}$ interface (without $\text{Sb}_2\text{Se}_3/\text{CdS}$). CPE at -0.24 V vs. RHE (Fig. S2.7b, ESI[†]), shows that following an initial drop in the current in the first 600 s, the electrode maintains a stable current of -0.24 mA cm^{-2} for 1 h suggesting that the $\text{TiO}_2\text{-meso}/\text{NiP}$ interface is stable at this potential and capable of dealing with low current density. However, the current spikes observed with $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}/\text{NiP}$ when the light is turned off in Fig. 2 are typical features of electron accumulation in the TiO_2 , suggesting that the **NiP** catalyst was unable to turnover at the rate of photoelectron generation under 100 mW cm^{-2} illumination. Based on the concentration of immobilised **NiP** ($45.76 \pm 0.81 \text{ nmol cm}^{-2}$), and the highest reported turnover frequency of **NiP** ($460 \pm 5 \text{ h}^{-1}$),²¹ we calculate that the **NiP** on the surface could support a photocurrent of -1.15 mA cm^{-2} . This magnitude of photocurrent is achieved briefly in the LSV, but CPP shows the photocurrent decreases rapidly as the **NiP** catalyst degrades. To assess the photoelectron generation of $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}$, we used Pt as co-catalyst (see ESI[†] for synthetic details, Fig. S2.14). The $\text{Sb}_2\text{Se}_3/\text{CdS}/\text{TiO}_2\text{-meso}/\text{Pt}$ electrode achieved a stable photocurrent of -3 mA cm^{-2} at 0 V vs. RHE for 5 hours. It is clear that the rate of photoelectron generation at the $\text{Sb}_2\text{Se}_3/\text{CdS}$ interface greatly exceeds the maximum current density that **NiP** can sustain. The catalytic mechanism of **NiP** is shown in Fig. S2.15 (ESI[†]),²⁰ H_2 production occurs following the $\text{Ni}^{\text{III/I}}$ reduction. Further reduction from Ni^{I} to Ni^0 can also potentially occur deactivating the catalyst if the rate of photoelectron generation is too high.³⁰ To explore if limiting the photoelectron generation on the Sb_2Se_3 would be beneficial, experiments at 20 mW cm^{-2} (Fig. S2.16 and S17, ESI[†]) were carried out. Notably, only a small decrease in photocurrent was observed from 1.30 to 0.81 mA cm^{-2} at 0 V vs. RHE, and 20% of photocurrent was retained after 1800 s compared with the 11% at 100 mW cm^{-2} .

Past studies using precious metal HER catalysts like Pt on planar TiO_2 coated Sb_2Se_3 photocathodes have noted that



dissolution of TiO₂ can also occur due to photoelectron accumulation.^{11,13} The SEM images post-CPP Sb₂Se₃/CdS/TiO₂-*meso*/NiP electrodes (tested at 100 mW cm⁻²) did not show significant change in the morphology of the device (Fig. S2.18, ESI†) despite the demonstration of electron accumulation in the device. XRD analysis of a post-CPP sample only showed the typical peaks of Sb₂Se₃ and TiO₂ (Fig. S2.19, ESI†) and no indication of Sb₂O₃ formation, which has been associated with the deactivation of the Sb₂Se₃ photoelectrodes (Fig. S2.20, ESI†).^{12,13} However experiments where Sb₂Se₃/CdS/TiO₂-*meso*/NiP underwent (i) LSV and CPP at 0 V vs. RHE for 1 h, (ii) removal of any remaining NiP by NaOH stripping, and (iii) Pt addition and photoelectrochemical testing showed evidence of partial failure of the sputtered TiO₂ layer due to photoelectron accumulation. Significantly higher dark currents (< -5 mA cm⁻², Fig. S2.21, ESI†) and decreased photocurrents were measured compared to a pristine platinized photoelectrode, reinforcing the importance of preventing photoelectron accumulation in the Sb₂Se₃/CdS/TiO₂-*meso*/NiP photocathode.

Emergent chalcogenide semiconductors such as Sb₂Se₃ are promising photocathodes due to their ability to achieve a high rate of photoelectron generation but they suffer from thermal instability limiting processing opportunities. Furthermore, Sb₂Se₃ interfaces need to be protected by metal oxide capping layers where corrosion could occur due to photoelectron accumulation. To prevent electron accumulation research has focused on the use of these absorbers with precious metal HER catalysts. Here we present an alternative approach using a Sb₂Se₃/CdS/TiO₂-*meso* photocathode. The high surface area TiO₂ support, prepared by a UV and low temperature N₂ annealing process that is compatible with Sb₂Se₃, enables a high loading of an earth abundant molecular HER catalyst, NiP. An 81-fold increase in the photocurrent was achieved when compared to a similar device without the mesoporous TiO₂. Despite the high catalyst loading, stability and activity under 100 mW cm⁻² is still limited by the turnover frequency of the HER catalyst. However, initial experiments under low light intensities indicate that improved stability is achievable with further advances in the catalytic turnover frequency.

We thank the studentship financial support from CONACYT-SENER (556479, DAGO), EPSRC (DTA, DAG), the UKRI Cambridge Creative Circular Plastics Centre (EP/S025308, ER, CC), and the European Commission for Horizon 2020 Marie Skłodowska-Curie Individual Fellowships (890745-SmArtC, CC). EPSRC is acknowledged for funding through EP/P034497/1, EP/N014057/1 and EP/V011863/1. Prof L. Hardwick and Facility for XPS ("HarwellXPS") are thanked for the Raman spectroscopy access and the XPS data collection (Contract No. PR16195).

Conflicts of interest

There are no conflicts to declare.

Notes and references

- S. Ye, C. Ding, R. Chen, F. Fan, P. Fu, H. Yin, X. Wang, Z. Wang, P. Du and C. Li, *J. Am. Chem. Soc.*, 2018, **140**, 3250–3256.
- S. Ye, C. Ding, M. Liu, A. Wang, Q. Huang and C. Li, *Adv. Mater.*, 2019, **31**, 1902069.
- H. Song, S. Luo, H. Huang, B. Deng and J. Ye, *ACS Energy Lett.*, 2022, **7**, 1043–1065.
- R. M. Irfan, D. Jiang, Z. Sun, L. Zhang, S. Cui and P. Du, *J. Catal.*, 2017, **353**, 274–285.
- S. Ye, W. Shi, Y. Liu, D. Li, H. Yin, H. Chi, Y. Luo, N. Ta, F. Fan, X. Wang and C. Li, *J. Am. Chem. Soc.*, 2021, **143**, 12499–12508.
- H. Shiel, O. S. Hutter, L. J. Phillips, J. E. N. Swallow, L. A. H. Jones, T. J. Featherstone, M. J. Smiles, P. K. Thakur, T. L. Lee, V. R. Dhanak, J. D. Major and T. D. Veal, *ACS Appl. Energy Mater.*, 2020, **3**, 11617–11626.
- O. S. Hutter, L. J. Phillips, K. Durose and J. D. Major, *Sol. Energy Mater. Sol. Cells*, 2018, **188**, 177–181.
- A. Mavlonov, T. Razykov, F. Raziq, J. Gan, J. Chantana, Y. Kawano, T. Nishimura, H. Wei, A. Zakutayev, T. Minemoto, X. Zu, S. Li and L. Qiao, *Sol. Energy*, 2020, **201**, 227–246.
- S. Chen, T. Liu, Z. Zheng, M. Ishaq, G. Liang, P. Fan, T. Chen and J. Tang, *J. Energy Chem.*, 2022, **67**, 508–523.
- B. A. Pinaud, J. D. Benck, L. C. Seitz, A. J. Forman, Z. Chen, T. G. Deutsch, B. D. James, K. N. Baum, G. N. Baum, S. Ardo, H. Wang, E. Miller and T. F. Jaramillo, *Energy Environ. Sci.*, 2013, **6**, 1983–2002.
- W. Yang, J. Park, H.-C. C. Kwon, O. S. Hutter, L. J. Phillips, J. Tan, H. Lee, J. Lee, S. D. Tilley, J. D. Major and J. Moon, *Energy Environ. Sci.*, 2020, **13**, 4362–4370.
- W. Yang, J. H. Kim, O. S. Hutter, L. J. Phillips, J. Tan, J. Park, H. Lee, J. D. Major, J. S. Lee and J. Moon, *Nat. Commun.*, 2020, **11**, 1–10.
- J. Tan, W. Yang, Y. Oh, H. Lee, J. Park, R. Boppella, J. Kim and J. Moon, *Adv. Energy Mater.*, 2019, 1900179.
- J. Park, W. Yang, J. Tan, H. Lee, J. W. Yun, S. G. Shim, Y. S. Park and J. Moon, *ACS Energy Lett.*, 2020, **5**, 136–145.
- W. Yang, S. Lee, H.-C. Kwon, J. Tan, H. Lee, J. Park, Y. Oh, H. Choi and J. Moon, *ACS Nano*, 2018, **12**, 11088–11097.
- R. R. Prabhakar, W. Septina, S. Siol, T. Moehl, R. Wick-Joliat and S. D. Tilley, *J. Mater. Chem. A*, 2017, **5**, 23139–23145.
- F. Niu, D. Wang, F. Li, Y. Liu, S. Shen and T. J. Meyer, *Adv. Energy Mater.*, 2019, 1900399.
- W. Jiang, X. Yang, F. Li, Q. Zhang, S. Li, H. Tong, Y. Jiang and L. Xia, *Chem. Commun.*, 2019, **55**, 1414–1417.
- M. L. Helm, M. P. Stewart, R. M. Bullock, M. R. DuBois and D. L. DuBois, *Science*, 2011, **333**, 863–866.
- W. J. Shaw, M. L. Helm and D. L. du Bois, *Biochim. Biophys. Acta, Bioenerg.*, 2013, **1827**, 1123–1139.
- M. A. Gross, A. Reynal, J. R. Durrant and E. Reisner, *J. Am. Chem. Soc.*, 2014, **136**, 356–366.
- A. Paracchino, V. Laporte, K. Sivula, M. Grätzel and E. Thimsen, *Nat. Mater.*, 2011, **10**, 456–461.
- T. E. Rosser, T. Hisatomi, S. Sun, D. Antón-García, T. Minegishi, E. Reisner and K. Domen, *Chem. – Eur. J.*, 2018, **24**, 18393–18397.
- J. J. Leung, J. Warnan, D. H. Nam, J. Z. Zhang, J. Willkomm and E. Reisner, *Chem. Sci.*, 2017, **8**, 5172–5180.
- T. E. Rosser, M. A. Gross, Y. H. Lai and E. Reisner, *Chem. Sci.*, 2016, **7**, 4024–4035.
- T. Berger, D. Monllor-Satoca, M. Jankulovska, T. Lana-Villarreal and R. Gomez, *ChemPhysChem*, 2012, **13**, 2824–2875.
- M. Schreier, J. Luo, P. Gao, T. Moehl, M. T. Mayer and M. Grätzel, *J. Am. Chem. Soc.*, 2016, **138**, 1938–1946.
- NIST X-ray Photoelectron Spectroscopy (XPS) Database, Version 3.5, <https://srdata.nist.gov/xps/>, accessed 26 July 2022.
- K. L. Materna, R. H. Crabtree and G. W. Brudvig, *Chem. Soc. Rev.*, 2017, **46**, 6099–6110.
- A. Ruff, S. Janke, J. Szczesny, S. Alsaoub, I. Ruff, W. Lubitz and W. Schuhmann, *ACS Appl. Energy Mater.*, 2019, **2**, 2921–2929.

