

Cite this: *Chem. Sci.*, 2019, 10, 564

All publication charges for this article have been paid for by the Royal Society of Chemistry

## Unusual fcc-structured Ag<sub>10</sub> kernels trapped in Ag<sub>70</sub> nanoclusters†

Yan-Min Su,<sup>‡a</sup> Zhi Wang,<sup>‡a</sup> Gui-Lin Zhuang,<sup>Ⓜb</sup> Quan-Qin Zhao,<sup>a</sup> Xing-Po Wang,<sup>a</sup> Chen-Ho Tung<sup>a</sup> and Di Sun<sup>Ⓜ\*a</sup>

Controlled trapping atom-precise ultrasmall silver nanoparticles into silver nanoclusters is challenging; thus only limited progress has been made in this area. We are therefore inspired to isolate two novel silver nanoclusters, Ag<sub>10</sub>@Ag<sub>70</sub> (SD/Ag80a and SD/Ag80b; SD = SunDi), where a novel fcc-structured Ag<sub>10</sub> kernel built from two single-edge opened Ag<sub>6</sub> octahedra by sharing one edge is trapped. The biocuboctahedral Ag<sub>10</sub> kernel is locked by a pair of Mo<sub>7</sub>O<sub>26</sub><sup>10-</sup> anions to form an inner Ag<sub>10</sub>@(Mo<sub>7</sub>O<sub>26</sub>)<sub>2</sub> core which is further encapsulated by an outer Ag<sub>70</sub> shell to form three-shell Ag<sub>10</sub>@(Mo<sub>7</sub>O<sub>26</sub>)<sub>2</sub>@Ag<sub>70</sub> nanoclusters. Notably, the biocuboctahedral Ag<sub>10</sub> kernel has not been observed in silver nanoclusters ever before, thus representing a new embryo state of silver nanoparticles. SD/Ag80a emits in the near infrared (NIR) region (λ<sub>em</sub> = 730 nm) at low temperature. This work will deepen our understanding on the atomic-level growth of silver nanoparticles and complicated three-shell self-assembly involving polyoxometalate (POM) and two different silver nanoclusters.

Received 31st July 2018

Accepted 13th October 2018

DOI: 10.1039/c8sc03396j

rsc.li/chemical-science

## Introduction

Ultrasmall silver nanoparticles (*e.g.*, few-atom clusters, <1 nm) represent the embryo states of larger silver nanoparticles (typically >2 nm) to some extent, which have defined molecular structures and compositions and thus can deepen the understanding on the size evolution of silver nanoparticles.<sup>1</sup> Given this, X-ray single crystal structures become a prerequisite to get atomic-level information including the surface ligands, inorganic-organic interfaces and silver atoms packed in silver nanoparticles.<sup>2</sup> While chasing large silver nanoclusters such as Ag<sub>14</sub>, Ag<sub>21</sub>, Ag<sub>23</sub>, Ag<sub>44</sub>, Ag<sub>50</sub>, Ag<sub>62</sub>, Ag<sub>67</sub>, Ag<sub>74</sub>, and Ag<sub>141</sub> and even the largest known Ag<sub>374</sub>,<sup>3</sup> chemists almost neglect the significance of the embryo states of silver nanoparticles that however are quite difficult to be captured due to their typical kinetics-controlled growth course.<sup>4</sup> Therefore, controlling the reductive transformation from Ag(I) to Ag<sup>0</sup> and then trapping the transient Ag aggregates into the thermodynamically stable crystalline product during the self-assembly is an urgent need and thus a major challenge.

Learning from the solvent-controlled synthesis of multiple-twin decahedral and icosahedral silver nanoparticles with special favourable [111] facets,<sup>5</sup> we found that DMF (*N,N*-dimethylformamide), compared to widely used NaBH<sub>4</sub>, is a much more mild reductive agent which facilitates the formation of Ag<sub>6</sub> octahedral kernels during the slow reduction process as seen in Ag<sub>34</sub> and Ag<sub>62</sub> nanoclusters.<sup>6</sup> Such Ag<sub>6</sub> octahedra can be seen as the smallest fragment cut from the unit cell of face-centered cubic (fcc) bulk silver metal, whereas other silver nanoclusters smaller than the most common icosahedral Ag<sub>13</sub> are still not directly observed in any reported silver nanoclusters.<sup>7</sup> Thus, the species in the early evolution from discrete Ag atoms to the metallic state are still largely vague and the exploration of a suitable synthesis strategy to trap them is scientifically desired.

With these considerations in mind, we used a DMF-containing mixed solvent system to isolate two novel silver nanoclusters [Ag<sub>10</sub>@(Mo<sub>7</sub>O<sub>26</sub>)<sub>2</sub>@Ag<sub>70</sub>(MoO<sub>4</sub>)<sub>2</sub>(CyhS)<sub>36</sub>(CF<sub>3</sub>SO<sub>3</sub>)<sub>16</sub>·(DMF)<sub>6</sub>]·2DMF·4<sup>n</sup>PrOH (SD/Ag80a; SD = SunDi; CyhSH = cyclohexanethiol) and [Ag<sub>10</sub>@(Mo<sub>7</sub>O<sub>26</sub>)<sub>2</sub>@Ag<sub>70</sub>(MoO<sub>4</sub>)<sub>2</sub>(<sup>i</sup>PrS)<sub>36</sub>·(CF<sub>3</sub>SO<sub>3</sub>)<sub>16</sub>(DMF)<sub>6</sub>] (SD/Ag80b). Two silver nanoclusters have the same metallic core but different organic coatings. In the innermost of cluster, an unusual fcc-structured Ag<sub>10</sub> nanocluster constructed from two single-edge opened Ag<sub>6</sub> octahedra by sharing one edge is locked by a pair of Mo<sub>7</sub>O<sub>26</sub><sup>10-</sup> anions to form an inner Ag<sub>10</sub>@(Mo<sub>7</sub>O<sub>26</sub>)<sub>2</sub> core which acts as a template to support the outer Ag<sub>70</sub> nanocluster to form a final three-shell Ag<sub>10</sub>@(Mo<sub>7</sub>O<sub>26</sub>)<sub>2</sub>@Ag<sub>70</sub> nanocluster. This unprecedented biocuboctahedral Ag<sub>10</sub> nanocrystal can be deemed as a new nanofragment cut from fcc silver metal and represents a possible transient species in the growth of large silver nanoparticles.

<sup>a</sup>Key Lab for Colloid and Interface Chemistry of Education Ministry, School of Chemistry and Chemical Engineering, Shandong University, Jinan, 250100, People's Republic of China. E-mail: dsun@sdu.edu.cn

<sup>b</sup>College of Chemical Engineering and Materials Science, Zhejiang University of Technology, Hangzhou, 310032, People's Republic of China

† Electronic supplementary information (ESI) available: IR, <sup>13</sup>C NMR, CV, UV, EDS, PXRD and luminescence decay curve, and details of the data collection and structure refinements, and crystal data. CCDC 1850394 and 1850395 for SD/Ag80a and SD/Ag80b. For ESI and crystallographic data in CIF or other electronic format see DOI: 10.1039/c8sc03396j

‡ These authors contributed equally.



## Results and discussion

## X-ray structures of SD/Ag80a and SD/Ag80b

SD/Ag80a and SD/Ag80b were synthesized through a facile one-pot solvothermal reaction of silver-thiolate polymeric precursors,  $\text{CF}_3\text{SO}_3\text{Ag}$  and molybdates in different DMF-containing mixed solvent systems (Scheme 1). In spite of several attempts, we still couldn't isolate SD/Ag80a and SD/Ag80b using the same Mo sources. Their samples were collected as brown-yellow and red crystals, respectively, after evaporation of solvents at room temperature for 1–2 weeks. Several synthetic parameters were optimized and are listed in Tables S1 and S2 (ESI)<sup>†</sup> for details. Details of the synthesis and some basic characterization are shown in the ESI.<sup>†</sup>

The molecular structures of SD/Ag80a and SD/Ag80b were revealed by single-crystal X-ray diffraction (SCXRD) analysis. They crystallize in monoclinic  $P2_1/n$  and triclinic  $P\bar{1}$  space groups, respectively. In each asymmetric unit only half of the corresponding clusters were resolved. Due to the structural similarities, only that of SD/Ag80a is described in detail here. The structural diagrams of SD/Ag80b are shown in Fig. S1.<sup>†</sup> Selected details of the data collection and structure refinements are listed in Table S3.<sup>†</sup>

SD/Ag80a is an elongated spheroid ( $1.0 \times 1.4 \times 2.1$  nm) that sits on the crystallographic inversion center (*i*). The  $\text{Ag}_{80}$  nanocluster is composed of a  $\text{Ag}_{70}$  shell and a  $\text{Ag}_{10}$  kernel. The  $\text{Ag}_{70}$  shell is capped by 36  $\text{CyhS}^-$ , 16  $\text{CF}_3\text{SO}_3^-$ , 2  $\text{MoO}_4^{2-}$  and 6 DMF (Fig. 1a and b). All cyclohexyl groups of 36  $\text{CyhS}^-$  ligands show a unified chair configuration. Two different coordination modes ( $\mu_3$  and  $\mu_4$ ) are found in 36  $\text{CyhS}^-$  ligands capped on the silver trigons or tetragons ( $\text{Ag-S}$  distances: 2.389(5)–2.722(5) Å). The 16  $\text{CF}_3\text{SO}_3^-$  anions exhibit three different coordination fashions including  $\mu_3\text{-}\eta^1\text{:}\eta^2\text{:}\eta^0$ ,  $\mu_3\text{-}\eta^1\text{:}\eta^1\text{:}\eta^1$ , and  $\mu_2\text{-}\eta^1\text{:}\eta^1\text{:}\eta^0$ . Two  $\text{MoO}_4^{2-}$  anions (yellow tetrahedra in Fig. 1) adopt a  $\mu_8\text{-}\eta^2\text{:}\eta^3\text{:}\eta^3$  mode to bind in the equatorial region of the  $\text{Ag}_{70}$  shell. Six DMF molecules as terminal ligands finished the organic ligand coverage on the surface of the  $\text{Ag}_{70}$  shell. Three different O donor ligands ( $\text{CF}_3\text{SO}_3^-$ ,  $\text{MoO}_4^{2-}$ , and DMF) interact with Ag atoms with the bonding distances in the ranges of 2.406(15)–2.789(17), 2.251(11)–2.568(11) and 2.390(13)–2.458(14) Å, respectively. The  $\text{Ag}_{70}$  shell was further consolidated by the argentophilic interaction<sup>8</sup> ranging from 2.833(2) to 3.4394(16) Å. The surface of the  $\text{Ag}_{70}$  shell consists silver trigons, tetragons, pentagons and heptagons (Fig. 1c). The silver trigons, tetragons,



Fig. 1 (a) and (b) The X-ray crystal structure of  $\text{Ag}_{10}@\text{(Mo}_7\text{O}_{26})_2@\text{Ag}_{70}$  nanoclusters viewed along two orthogonal directions. The inner silver atoms of the  $\text{Ag}_{10}$  kernel are highlighted in black.  $\text{Mo}_7\text{O}_{26}^{10-}$  and  $\text{MoO}_4^{2-}$  are represented by green and yellow polyhedra, respectively. (c) The  $\text{Ag}_{70}\text{S}_{36}$  shell with silver heptagons highlighted in green.

and pentagons are capped by  $\text{CyhS}^-$  or  $\text{CF}_3\text{SO}_3^-$ , whereas  $\text{MoO}_4^{2-}$  shapes the large silver heptagons (green rings in Fig. 1c).

There are two crescent-like  $\text{Mo}_7\text{O}_{26}^{10-}$  anions under the  $\text{Ag}_{70}$  shell (Fig. 2a). During the synthesis of SD/Ag80a and SD/Ag80b, although different Mo sources,  $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$  and  $[^n\text{Bu}_4\text{N}]_2\text{Mo}_6\text{O}_{19}$ , were used, respectively, the same  $\text{Mo}_7\text{O}_{26}^{10-}$  anion was trapped as the template in the final silver nanoclusters. Thus, the novel  $\text{Mo}_7\text{O}_{26}^{10-}$  anions should be *in situ* transformed from  $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$  or  $[^n\text{Bu}_4\text{N}]_2(\text{Mo}_6\text{O}_{19})$  in different solvent environments. We used Bond-Valence Sum (BVS) calculations for seven Mo atoms of  $\text{Mo}_7\text{O}_{26}^{10-}$ , which confirmed that all of them are in the +6 oxidation state (Table S5<sup>†</sup>).<sup>9</sup> The  $\text{Mo}_7\text{O}_{26}^{10-}$  is constructed from seven edge-shared  $\text{MoO}_6$  octahedra. The total 26 O atoms are divided into four kinds based on their binding fashion to Ag atoms, 2  $\mu_0$ , 4  $\mu_1$ , 16  $\mu_2$ , and 4  $\mu_3$ . Such highly negative-charged  $\text{Mo}_7\text{O}_{26}^{10-}$  totally binds 35 silver atoms. Among them, 7 are from the inner  $\text{Ag}_{10}$  kernel and the remaining 28 are from the  $\text{Ag}_{70}$  shell (Fig. 2b). Notably, this novel molybdate has neither been observed in classic POM chemistry nor in silver nanoclusters. More importantly, this molybdate carries the second highest negative charges<sup>10</sup> which effectively enhanced its template effect by binding more Ag atoms (Table S6<sup>†</sup>).

The most interesting feature in SD/Ag80a is the unusual  $\text{Ag}_{10}$  kernel underlying the equatorial region of the  $\text{Ag}_{70}$  shell which is built from two single-edge opened  $\text{Ag}_6$  octahedra by sharing one edge (Fig. 2c). The shared edge is the longest  $\text{Ag}\cdots\text{Ag}$  edge ( $\text{Ag}38\cdots\text{Ag}38^i = 3.457(1)$  Å, symmetry code *i*:  $-x + 1, -y + 1, -z + 1$ ) within the  $\text{Ag}_{10}$  kernel, which is out of the normal  $\text{Ag}\cdots\text{Ag}$  interaction range. All other eleven  $\text{Ag}\cdots\text{Ag}$  edges are



Scheme 1 Synthetic routes for SD/Ag80a and SD/Ag80b.





Fig. 2 (a) Two  $\text{Mo}_7\text{O}_{26}^{10-}$  anions in *SD/Ag80a* shown in polyhedral (left) and ball-and-stick modes (right). (b) Binding fashion of  $\text{Mo}_7\text{O}_{26}^{10-}$  toward 35 Ag atoms (black: Ag from the  $\text{Ag}_{10}$  kernel; purple: Ag from the  $\text{Ag}_{70}$  shell). (c) Animation showing the formation of a  $\text{Ag}_{10}$  bioctahedron from two single-edge opened  $\text{Ag}_6$  octahedra by fusing one Ag–Ag edge. (d) The  $\text{Ag}_{10}$  bioctahedron locked by a pair of  $\text{Mo}_7\text{O}_{26}^{10-}$  anions. (e) The  $\text{Ag}_{10}$  bioctahedron (claybank space-filling balls) residing in the  $\text{Ag}_{70}$  shell.

distributed in the range of 2.659(2)–2.980(1) Å (Fig. S2†) and the average  $\text{Ag}\cdots\text{Ag}$  distance is 2.814 Å, which is 2.5% shorter than the  $\text{Ag}\cdots\text{Ag}$  distance in metallic silver (2.886 Å),<sup>11</sup> indicating strong argentophilic interactions as in bulk silver metal. All exposed trigons of the  $\text{Ag}_{10}$  bioctahedral kernel are [111] facets which are capped by  $\text{Mo}_7\text{O}_{26}^{10-}$  anions through Ag–O bonding (Ag–O distances: 2.284(10)–2.433(10) Å; Fig. 2d). As such, the  $\text{Ag}_{10}$  bioctahedron is doubly clamped by a pair of  $\text{Mo}_7\text{O}_{26}^{10-}$  anions to form an inner  $\text{Ag}_{10}@(\text{Mo}_7\text{O}_{26})_2$  core, which was enwrapped by an outer  $\text{Ag}_{70}$  shell to form a three-shell  $\text{Ag}_{10}@(\text{Mo}_7\text{O}_{26})_2@ \text{Ag}_{70}$  nanocluster. The two polar sites of the  $\text{Ag}_{10}$  bioctahedron are also linked with the outer  $\text{Ag}_{70}$  shell through argentophilic interactions ( $\text{Ag}\cdots\text{Ag}$ : 2.8523(19)–3.3621(18) Å; Fig. S3†).

Although the single  $\text{Ag}_6$  octahedron has been observed in several inorganic compounds<sup>12</sup> and a few silver nanoclusters,<sup>13</sup> its dimer,  $\text{Ag}_{10}$  bioctahedron, has never been observed before in silver nanoclusters. Such a  $\text{Ag}_{10}$  bioctahedron can be seen as a bigger nanofragment than a  $\text{Ag}_6$  octahedron. An important driven force for its formation should be the suitable reducibility of DMF.<sup>6</sup> The oxidation product of DMF in the assembly process is  $\text{Me}_2\text{NCOOH}$ <sup>14</sup> which can be recognized from the <sup>13</sup>C NMR (nuclear magnetic resonance) of HCl digested reaction mother solution (Fig. S4†). In the chemical shift scale corresponding to aldehydes and carboxylates ( $\delta = 150$ –200 ppm), two peaks appeared at  $\delta = 164.64$  and 162.92 ppm, which are assigned to the carbon resonances of DMF and  $\text{Me}_2\text{NCOOH}$ , respectively.

We didn't observe any peaks in <sup>13</sup>C NMR corresponding to the oxidation product of <sup>n</sup>PrOH, which clearly excluded the possible reductive effect of <sup>n</sup>PrOH in this assembly system. These results clearly evidenced the redox reaction between Ag(I) and DMF occurred during the self-assembly process. The emergence of a fcc-structured  $\text{Ag}_{10}$  nanocluster, on the other hand, answered an important question, which is how the common observed smaller  $\text{Ag}_6$  kernel grew up to larger structures. Based on the above structural information, we can tentatively assign a new edge-fusion mode to its growth mechanism, although several other growth modes for noble metal nanoparticles have been proposed such as face-fusion, interpenetration, shell-by-shell, layer-by-layer, and tetrahedron-based vertex-sharing growth modes.<sup>2</sup> Based on the formulae and charge neutrality considerations, we can determine that the valence of the  $\text{Ag}_{10}$  kernel is +6, which means such a kernel carries four free electrons, belonging to a 4e superatom network. We also performed DFT calculations at the B3LYP/SDD theoretical level to study the free electron distributions on the frontier orbitals of the  $\text{Ag}_{10}$  kernel (see details in the ESI†). According to the results identified experimentally, the inner  $\text{Ag}_{10}$  kernel features  $C_i$  symmetry with +6 valence and four free electrons. Thus, frontier molecular orbital analysis (Fig. S5†) reveals that four free electrons occupy two  $A_u$ -symmetry HOMO-1 and HOMO. HOMO-1 and HOMO exhibit different components. HOMO involves in the 5s orbitals of two ends of  $\text{Ag}_{10}$ , while HOMO-1 concentrates on the 4d orbitals of two ends of  $\text{Ag}_{10}$ . Moreover, HOMO-2 features  $A_g$  symmetry with similar components to HOMO-1, and LUMO consists of 5s orbitals in the centre of  $\text{Ag}_{10}$ .

Combining the structural analysis and DMF-involved reductive process, we tentatively proposed a total shell-by-shell formation mechanism for such new silver nanoclusters. Weakly reductive DMF firstly induced the formation of an inner  $\text{Ag}_{10}$  kernel (1st shell), which exposes highly active [111] facets that are quickly passivated by the formation of Ag–O interaction with  $\text{Mo}_7\text{O}_{26}^{10-}$  (2nd shell). The inner  $[\text{Ag}_{10}@(\text{Mo}_7\text{O}_{26})_2]$  core acts as the authentic template to support an outer  $\text{Ag}_{70}$  shell, forming the final core–shell type silver nanoclusters. Such a formation route resembled the mechanism revealed in the  $[\text{Ag}_6@(\text{MoO}_4)_7@ \text{Ag}_{56}]$  family by electrospray ionization mass spectrometry.<sup>6b</sup>

We also noted that the  $\text{Au}_{21}(\text{S-Adm})_{15}$  nanocluster has been reported by the Zhu group,<sup>15</sup> who firstly found the bioctahedral  $\text{Au}_{10}$  kernel formed by edge-sharing of two single-edge opened  $\text{Au}_6$  octahedra. However, the shared edge is not the longest one (opened edge) and the overall  $\text{Au}_6$  octahedral framework is severely disordered. Anyhow, as a counterpart of this  $\text{Au}_{10}$  kernel, the bioctahedral  $\text{Ag}_{10}$  kernel has not been reported before in silver nanoclusters.

### The optical properties of *SD/Ag80a*

The UV/Vis spectrum of *SD/Ag80a* was measured in the solid state using diffuse reflectance mode. As shown in Fig. 3, *SD/Ag80a* showed an absorption maximum at 344 nm and a shoulder peak in the visible region (~490 nm), which should be ascribed to ligand-based absorption and the charge transfer





- 54, 3702–3706; (c) C. Liu, T. Li, H. Abroshan, Z. M. Li, C. Zhang, H. J. Kim, G. Li and R. C. Jin, *Nat. Commun.*, 2018, **9**, 744; (d) A. Desireddy, B. E. Conn, J. Guo, B. Yoon, R. N. Barnett, B. M. Monahan, K. Kirschbaum, W. P. Griffith, R. L. Whetten, U. Landman and T. P. Bigioni, *Nature*, 2013, **501**, 399–402; (e) W. J. Du, S. Jin, L. Xiong, M. Chen, J. Zhang, X. J. Zou, Y. Pei, S. X. Wang and M. Z. Zhu, *J. Am. Chem. Soc.*, 2017, **139**, 1618–1624; (f) S. Jin, S. X. Wang, Y. B. Song, M. Zhou, J. Zhong, J. Zhang, A. D. Xia, Y. Pei, M. Chen, P. Li and M. Z. Zhu, *J. Am. Chem. Soc.*, 2014, **136**, 15559–15565; (g) M. J. Alhilaly, M. S. Bootharaju, C. P. Joshi, T. M. Besong, A.-H. Emwas, R. Juarez-Mosqueda, S. Kaappa, S. Malola, K. Adil, A. Shkurenko, H. Hakkinen, M. Eddaoudi and O. M. Bakr, *J. Am. Chem. Soc.*, 2016, **138**, 14727–14732; (h) M. Qu, H. Li, L. H. Xie, S. T. Yan, J. R. Li, J. H. Wang, C. Y. Wei, Y. W. Wu and X. M. Zhang, *J. Am. Chem. Soc.*, 2017, **139**, 12346–12349; (i) L. Ren, P. Yuan, H. Su, S. Malola, S. Lin, Z. Tang, B. K. Teo, H. Hakkinen, L. Zheng and N. Zheng, *J. Am. Chem. Soc.*, 2017, **139**, 13288–13291; (j) H. Y. Yang, Y. Wang, X. Chen, X. J. Zhao, L. Gu, H. Q. Huang, J. Z. Yan, C. F. Xu, G. Li, J. C. Wu, A. J. Edwards, B. Dittrich, Z. C. Tang, D. D. Wang, L. Lehtovaara, H. Hakkinen and N. F. Zheng, *Nat. Commun.*, 2016, **7**, 12809.
- 4 (a) Y. Wang, Y. Q. Zheng, C. Z. Huang and Y. N. Xia, *J. Am. Chem. Soc.*, 2013, **135**, 1941–1951; (b) M. Zhu, P. Wang, N. Yan, X. Q. Chai, L. Z. He, Y. Zhao, N. Xia, C. H. Yao, J. Li, H. T. Deng, Y. Zhu, Y. Pei and Z. K. Wu, *Angew. Chem., Int. Ed.*, 2018, **57**, 4500–4504; (c) L. Z. He, J. Y. Yuan, N. Xia, L. W. Liao, X. Liu, Z. B. Gan, C. M. Wang, J. L. Yang and Z. K. Wu, *J. Am. Chem. Soc.*, 2018, **140**, 3487–3490.
- 5 (a) A. Tao, P. Sinsermsuksakul and P. D. Yang, *Angew. Chem., Int. Ed.*, 2006, **45**, 4597–4601; (b) M. Tsuji, Y. Maeda, S. Hikino, H. Kumagae, M. Matsunaga, X. L. Tang, R. Matsuo, M. Ogino and P. Jiang, *Cryst. Growth Des.*, 2009, **9**, 4700–4705; (c) M. Tsuji, M. Ogino, R. Matsuo, H. Kumagae, S. Hikino, T. Kim and S. H. Yoon, *Cryst. Growth Des.*, 2010, **10**, 296–301; (d) M. Tsuji, X. L. Tang, M. Matsunaga, Y. Maeda and M. Watanabe, *Cryst. Growth Des.*, 2010, **10**, 5238–5243.
- 6 (a) D. Sun, G.-G. Luo, N. Zhang, R.-B. Huang and L.-S. Zheng, *Chem. Commun.*, 2011, **47**, 1461–1463; (b) Z. Wang, H. F. Su, M. Kurmoo, C. H. Tung, D. Sun and L.-S. Zheng, *Nat. Commun.*, 2018, **9**, 2094.
- 7 R. S. Dhayal, Y.-R. Lin, J.-H. Liao, Y.-J. Chen, Y.-C. Liu, M.-H. Chiang, S. Kahlal, J.-Y. Saillard and C. W. Liu, *Chem.–Eur. J.*, 2016, **22**, 9943–9947.
- 8 (a) H. Schmidbaur and A. Schier, *Angew. Chem., Int. Ed.*, 2015, **54**, 746–784; (b) H. Liu, C.-Y. Song, R.-W. Huang, Y. Zhang, H. Xu, M.-J. Li, S.-Q. Zang and G.-G. Gao, *Angew. Chem., Int. Ed.*, 2016, **55**, 3699–3703; (c) S. Li, X.-S. Du, B. Li, J.-Y. Wang, G.-P. Li, G.-G. Gao and S.-Q. Zang, *J. Am. Chem. Soc.*, 2018, **140**, 594–597; (d) R.-W. Huang, Y.-S. Wei, X.-Y. Dong, X.-H. Wu, C.-X. Du, S.-Q. Zang and T. C. W. Mak, *Nat. Chem.*, 2017, **9**, 689–697.
- 9 W. Liu and H. H. Thorp, *Inorg. Chem.*, 1992, **31**, 1585–1588.
- 10 R.-W. Huang, Q.-Q. Xu, H.-L. Lu, X.-K. Guo, S.-Q. Zang, G.-G. Gao, M.-S. Tang and T. C. W. Mak, *Nanoscale*, 2015, **7**, 7151–7154.
- 11 P. Pykkö, *Chem. Rev.*, 1997, **97**, 597–636.
- 12 (a) H. G. V. Schnering and K. G. Hausler, *Rev. Chim. Miner.*, 1976, **13**, 71–81; (b) W. Beesk, P. G. Jones, H. Rumpel, E. Schwarzmann and G. M. Sheldrick, *J. Chem. Soc., Chem. Commun.*, 1981, 664–665; (c) C. Linke and M. Jansen, *Inorg. Chem.*, 1994, **33**, 2614–2616; (d) M. Jansen and C. Linke, *Angew. Chem., Int. Ed. Engl.*, 1992, **31**, 653–654.
- 13 (a) Y. Kikukawa, Y. Kuroda, K. Suzuki, M. Hibino, K. Yamaguchi and N. Mizuno, *Chem. Commun.*, 2013, **49**, 376–378; (b) Z.-Y. Wang, M.-Q. Wang, Y.-L. Li, P. Luo, T.-T. Jia, R.-W. Huang, S.-Q. Zang and T. C. W. Mak, *J. Am. Chem. Soc.*, 2018, **140**, 1069–1076.
- 14 I. Pastoriza-Santos and L. M. Liz-Marzan, *Pure Appl. Chem.*, 2000, **72**, 83–90.
- 15 S. Chen, L. Xiong, S. X. Wang, Z. Y. Ma, S. Jin, H. T. Sheng, Y. Pei and M. Z. Zhu, *J. Am. Chem. Soc.*, 2016, **136**, 10754–10757.
- 16 G. Li, Z. Lei and Q. M. Wang, *J. Am. Chem. Soc.*, 2010, **132**, 17678–17679.
- 17 (a) C. Yang, O. Elbjeirami, C. S. P. Gamage, H. V. R. Dias and M. A. Omary, *Chem. Commun.*, 2011, **47**, 7434–7436; (b) C.-M. Che, M.-C. Tse, M. C. W. Chan, K.-K. Cheung, D. L. Phillips and K.-H. Leung, *J. Am. Chem. Soc.*, 2000, **122**, 2464–2468; (c) D. Sun, L. L. Zhang, H. F. Lu, S. Y. Feng and D. F. Sun, *Dalton Trans.*, 2013, **42**, 3528–3532; (d) J. Jin, W.-Y. Wang, Y.-H. Liu, H.-W. Hou and Y.-T. Fan, *Chem. Commun.*, 2011, **47**, 7461–7463.
- 18 V. W.-W. Yam, V. K.-M. Au and S. Y.-L. Leung, *Chem. Rev.*, 2015, **115**, 7589–7728.

