

Cite this: *Dalton Trans.*, 2021, **50**, 1465

# Utilization of a Pt(II) di-yne chromophore incorporating a 2,2'-bipyridine-5,5'-diyl spacer as a chelate to synthesize a green and red emitting d–f–d heterotrinnuclear complex†

Idris Juma Al-Busaidi,<sup>a</sup> Rashid Ilmi,<sup>a</sup> José D. L. Dutra,<sup>b</sup> Willyan F. Oliveira,<sup>b</sup> Ashanul Haque,<sup>a,c</sup> Nawal K. Al Rasbi,<sup>a</sup> Frank Marken,<sup>d</sup> Paul R. Raithby<sup>d</sup> and Muhammad S. Khan<sup>\*a</sup>

A new heterotrinnuclear (d–f–d) complex **[Eu(btfa)<sub>3</sub>1c]** (btfa = 4,4,4-trifluoro-1-phenyl-1,3-butanedione and **1c** = [(Ph)(Et<sub>3</sub>P)<sub>2</sub>Pt–C≡C–R–C≡C–Pt(Et<sub>3</sub>P)<sub>2</sub>(Ph)] (R = 2,2'-bipyridine-5,5'-diyl) has been synthesized by utilizing the N,N-donor sites of the organometallic chromophore. The complex was characterized by analytical and spectroscopic methods. Photophysical properties of the complex were analysed in detail using both steady-state and time-resolved emission and excitation spectroscopy. The optical absorption spectrum of the complex is dominated by the spin allowed  $\pi-\pi^*$  transitions of the btfa and **1c** units in the UV–visible region (200–418 nm) and thus is excitable over a wide range of wavelengths across the UV into the visible region of the electromagnetic spectrum. The complex displays typical red Eu(III) emission when excited at 345 nm. However, it also shows green emission when excited at 464 nm and, thus could be an interesting candidate for full colour display applications. The change in the colour could be a result of the high value of the energy back-transfer rate ( $6.73 \times 10^5 \text{ s}^{-1}$ ) from the triplet state of the organometallic chromophore to the <sup>5</sup>D<sub>1</sub> state of Eu(III). Judd–Ofelt (J–O) intensity parameters ( $\Omega_2$  and  $\Omega_4$ ), radiative ( $A_R$ ), non-radiative ( $A_{NR}$ ) decay rates and intrinsic quantum yield ( $Q_{Eu}^{int}$ ) have been calculated.

Received 9th December 2020,  
Accepted 23rd December 2020

DOI: 10.1039/d0dt04198j

rsc.li/dalton

## 1. Introduction

Organo-transition metal complexes with triplet (T) and singlet (S) harvesting features have emerged as attractive materials for efficient optoelectronic (O–E) applications.<sup>1</sup> The introduction of heavy transition metals such as rhenium (Re), ruthenium (Ru), osmium (Os) and platinum (Pt) into these systems, with their associated high spin–orbit coupling (SOC), facilitates intersystem-crossing (ISC) of the excited singlet state S<sub>1</sub> to the lower-lying triplet state T<sub>1</sub>.<sup>2</sup> As a result, highly efficient photoluminescence quantum yields (PLQY) approaching 100% efficiency at ambient temperature are achievable. Hence, in the electroluminescence experiments, Pt(II) complexes can

exploit both the singlet and triplet excitons and produce light.<sup>1,3</sup> Additionally, trivalent lanthanide [Ln(III)] ions provide a fascinating platform because of their atom-like emission spectra with very sharp emission bands (full width at half maxima (FWHM) less than 10 nm), long luminescence lifetimes and ion-specific emissions.<sup>4</sup> Coordinating Ln(III) complex ions to organo-transition metal complexes could endow the resultant complexes with enhanced PL properties for many potential applications.<sup>5</sup> The unique optical properties of the Ln(III) ions render them useful in a range of applications such as in lasers,<sup>5h,6</sup> light-emitting sensors for hetero- and homogeneous fluoroimmunoassays,<sup>7</sup> organic light-emitting diodes (OLEDs) used in display devices,<sup>5c,e,8</sup> and biological imaging.<sup>9</sup> Hetero-multimetallic d–f complexes have shown enhanced PL properties *via* energy transfer from the transition metals acting as an antenna triplet state for the Ln(III) ions.<sup>10</sup> Compared to organic sensitizer chromophores, the metal-based chromophores possess both a low energy singlet state and a low triplet excited state and thus can be used to extend the excitation window of the luminescent lanthanide complexes.<sup>11</sup> Hence, optimized and tuned photophysical properties of luminescent lanthanide complexes such as narrow emission bands, large Stokes' shifts and long-lived excited

<sup>a</sup>Department of Chemistry, Sultan Qaboos University, P.O. Box 36, Al Khoud 123, Oman. E-mail: rashidilmi@gmail.com, msk@squ.edu.om

<sup>b</sup>Pople Computational Chemistry Laboratory, Department of Chemistry, UFS, 49100-000 São Cristóvão, Sergipe, Brazil

<sup>c</sup>Department of Chemistry, College of Science, University of Hail, Ha'il 81451, Kingdom of Saudi Arabia

<sup>d</sup>Department of Chemistry, University of Bath, Claverton Down, Bath BA2 7AY, UK. E-mail: p.r.raithby@bath.ac.uk

†Electronic supplementary information (ESI) available. See DOI: 10.1039/d0dt04198j



state lifetimes can be easily enhanced. Moreover, 3d/5d coordination complexes can facilitate highly efficient Electronic Energy Transfer (EET) to the excited states of chelated 4f<sup>n</sup> cations.<sup>12</sup> The latter process can be performed *via* two possible pathways: (a) <sup>1</sup>MLCT–<sup>3</sup>MLCT intersystem crossing arising from the heavy-atom effect of the transition metals upon coordination to the lanthanide unit, (b) efficient <sup>3</sup>MLCT–Ln\* process that can compete with bimolecular quenching of the <sup>3</sup>MLCT state by triplet oxygen.<sup>13</sup> The coordination of 3d/5d metals containing appropriate ligands allows the excitation in the visible region.<sup>14</sup> In addition, the inclusion of acetylide-functionalized chelating ligands allows light emission from the triplet excited state of the conjugated ligand.<sup>15</sup> Moreover, introducing the acetylide unit may endow the complex with intriguing photophysical properties by additional intra-ligand and/or inter-ligand charge-transfer excited states (ILCT). Therefore, a strong sensitization of Eu(III) in the visible domain (up to 460 nm) by the use of a phosphorescent Pt(II) complex raises the overall luminescence QY of the complexes.<sup>12,13</sup> We have recently<sup>4c</sup> reported a heterotrinnuclear ‘Pt–Eu–Pt’ complex of a sterically hindered kinked/V-shaped Pt(II) di-yne antenna chromophore of the type *trans*-[(Ph)(Et<sub>3</sub>P)<sub>2</sub>Pt–C≡C–R–C≡C–Pt(Et<sub>3</sub>P)<sub>2</sub>(Ph)] (R = 2,2'-bipyridine-6,6'-diyl) (**1d**) as shown in Chart 1 and described its photophysical properties. The complex displayed typical red emission of the Eu(III) centre; however, the excitation window was confined to the UV region. This can be attributed to conjugation interruption in the system due to ligand topology (presence of the ethynyl groups at 6,6'-positions of 2,2'-Bipy).<sup>16</sup> A general strategy to shift the excitation window of a complex is to design and engineer the molecule(s) with extended/uninterrupted π-conjugation. We have previously reported that Pt(II) di-yne and poly-yne incorporating a variety of carbocyclic,<sup>15a,17</sup> heterocyclic<sup>15a,18</sup> and mixed heterocyclic<sup>15a,19</sup> spacers with extended conjugation exhibit improved photophysical properties for various opto-electronic applications. We noted that 5,5'-bis(ethynyl)-2,2'-bipyridine is

fully conjugated while its 6,6'-bis(ethynyl) counterpart has broken conjugation and that 2,2'-bipyridine-5,5'-diyl spacer imparts more desirable optical properties to the Pt(II) di-yne and poly-yne complexes.<sup>20</sup> Based on this idea, in the present work, we have utilized the ‘rigid-rod’ Pt(II) di-yne chromophore incorporating 2,2'-bipyridine-5,5'-diyl chelating spacer to synthesize a new heterotrinnuclear Pt–Eu–Pt complex (Chart 1). The photophysical properties of the heterotrinnuclear complex have been investigated. The optical absorption spectrum of the present heterotrinnuclear complex [Eu(btfa)<sub>3</sub>**1c**] displays a red shift compared to its kinked counterpart [Eu(btfa)<sub>3</sub>**1d**] [**1d**] = [(Ph)(Et<sub>3</sub>P)<sub>2</sub>Pt–C≡C–R–C≡C–Pt(Et<sub>3</sub>P)<sub>2</sub>(Ph)] (R = 2,2'-bipyridine-6,6'-diyl) because of the uninterrupted conjugation present in the former complex. Moreover, the newly synthesized heterotrinnuclear complex displays fascinating dual emissions *i.e.*, typical red emission due to the Eu(III) ion occurs when excited at 345 nm while a strong green emission is observed when the complex is excited at 464 nm. Finally, DFT calculations have been carried out to understand the photophysical properties and the nature of the excited state. Furthermore, the results of the DFT in conjunction with the observed photophysical data were utilized to gain an insight into the IET processes with the help of the LUMPAC<sup>21</sup> software package.

## 2. Experimental

### 2.1. General

All reactions were performed under a dry Argon (Ar) atmosphere using standard Schlenk line techniques. Solvents were pre-dried and distilled before use according to standard procedures. Europium chloride and gadolinium nitrate were purchased from Strem, USA. All other chemicals were obtained from Sigma Aldrich except 5,5'-dibromo-2,2'-bipyridine which was obtained from Tokyo Chemical Industry (TCI) and all were used as received. The compound *trans*-[Ph(Et<sub>3</sub>P)<sub>2</sub>PtCl] was prepared according to reported procedures.<sup>4c</sup> Column chromatography was performed either with Kieselgel 60 (230–400 mesh) silica gel or alumina (Brockman Grade I). Elemental analysis was performed in the Department of Chemistry, Sultan Qaboos University. Attenuated total-reflectance (ATR) infrared (IR) spectra were recorded on pure samples on diamond using a Cary 630 FT-IR spectrometer. Mass spectra were obtained using the Agilent 6530 Accurate-Mass Quadruple Time-of-Flight (Q-TOF) LC/MS.

### 2.2. Synthesis of hetero-trinnuclear complex [Eu(btfa)<sub>3</sub>**1c**]

5,5'-Bis(trimethylsilylethynyl)-2,2'-bipyridine (**1a**), 5,5'-bis(ethynyl)-2,2'-bipyridine (**1b**) and *trans*-[(Ph)(Et<sub>3</sub>P)<sub>2</sub>Pt–C≡C–R–C≡C–Pt(Et<sub>3</sub>P)<sub>2</sub>(Ph)] (R = 2,2'-bipyridine-5,5'-diyl (**1c**)) (Scheme 1) were synthesized as reported by us previously.<sup>16</sup> A solution of **1c** (0.073 g, 0.06 mmol) in MeOH/DCM (10 mL) was added to a solution of [Eu(btfa)<sub>3</sub>(H<sub>2</sub>O)<sub>2</sub>] (0.050 g, 0.06 mmol) in MeOH/DCM (10 mL). The reaction mixture was left overnight with stirring at RT. The solution was left for slow



**Chart 1** Structure of the present and previously<sup>4c</sup> designed Pt(II) di-yne organometallic chromophore and their heterotrinnuclear (d–f–d) complex.





viously by us.<sup>5c</sup> This was utilized to aid the drawing of the starting geometry of the hetero-trinuclear complex [Eu(btfa)<sub>3</sub>1c] and was first optimized with the semiempirical quantum mechanical Sparkle/PM6 model<sup>24</sup> implemented in the MOPAC2016 software,<sup>25</sup> without imposing any symmetry restrictions. The optimized Sparkle/PM6 geometry was used to finally elucidate the structure of [Eu(btfa)<sub>3</sub>1c] by the DFT approach at the B3LYP level of theory with the help of the ORCA 4.2.1 software package.<sup>26</sup> The SVP basis set<sup>27</sup> was used to represent the electronic structure of the hydrogen (H) atom as (4s1p)/[2s1p], while the carbon (C), nitrogen (N), oxygen (O) and fluorine (F) atoms are treated as (7s4p1d)/[3s2p1d] by SVP. The electronic structure of the Eu and Pt atoms were represented by the MWB(52) and LANL(68)<sup>28</sup> effective core potentials (ECP),<sup>28</sup> respectively, which considered 52 and 68 electrons in each of the respective cores. For Eu and Pt atoms the remaining electrons were treated as (7s6p5d)/[5s4p3d] and (7s6p5d1f)/[6s3p2d1f], respectively. Finally, the phosphorus (P) atom was represented by the LANL(10)<sup>28</sup> ECP with the remaining electrons being treated as (10s7p1d)/[4s3p1d].

Using the B3LYP geometry the singlet and triplet states of the coordinated ligands were determined with the time-dependent density functional theory (TD-DFT) approach, applying the CAM-B3LYP functional.<sup>28</sup> The elements were represented by the same basis set and ECPs specified for the procedure of geometry optimization. As in a previous study<sup>5a</sup> the effect of the dichloromethane solvent was implicitly considered and did not promote change in the excited states energies, therefore such effect was not considered in the current work. The corresponding absorption spectrum was obtained from fitting to a Lorentzian function with a half-width at half maximum (HWHM) arbitrarily attributed as 10 nm.

**2.5.2. Intermolecular energy transfer (IET) rate.** The most recent Malta's model<sup>29</sup> implemented into LUMPAC 1.4.1<sup>21</sup> was employed in the ET rates calculation involving the main ET channels for [Eu(btfa)<sub>3</sub>1c]. Such a model considers the contribution from two mechanisms, being the ligand–metal ET in view only of the direct coulombic interaction calculated by:

$$W_{\text{ET}}^{\text{C}} = \frac{2\pi}{\hbar} \frac{e^2 S_{\text{L}} F}{G(2J+1)} \sum_{\lambda=2,4,6} \Lambda_{\lambda} \langle \psi' J' \| U^{(\lambda)} \| \psi J \rangle^2 \quad (7)$$

$$\Lambda_{\lambda} = 2\Omega_{\lambda}^{\text{FED}} (1 - \sigma_1)^2 \left( \frac{1}{R_{\text{L}}^6} \right) + \langle r^{\lambda} \rangle^2 \langle 3 \| C^{(\lambda)} \| 3 \rangle^2 (1 - \sigma_{\lambda})^2 \times \left( \frac{\lambda + 1}{(R_{\text{L}}^{\lambda+2})^2} \right) \quad (8)$$

The ligand–metal ET rates considering only the exchange mechanism is given by:

$$W_{\text{ET}}^{\text{EX}} = \frac{8\pi e^2 (1 - \sigma_0)^2 F}{3\hbar R_{\text{L}}^4 G(2J+1)} \langle \psi' J' \| S \| \psi J \rangle^2 \sum_m \left\langle \Psi_{N-1} \Pi \left| \sum_j r_j C_0^{(1)}(j) s_{-m}(j) \right| \Psi_{N-1} \Pi^* \right\rangle^2 \quad (9)$$

The  $\langle \psi' J' \| U^{(\lambda)} \| \psi J \rangle^2$  and  $\langle \psi' J' \| S \| \psi J \rangle^2$  reduced matrix elements provide the selection rules for the direct coulombic interaction

(CI) and exchange (Ex) mechanisms, respectively. As a consequence, the electronic excitation of the states  ${}^5\text{D}_4 \leftarrow {}^7\text{F}_0$ ,  ${}^5\text{G}_6 \leftarrow {}^7\text{F}_0$ , and  ${}^5\text{L}_6 \leftarrow {}^7\text{F}_0$  for the Eu(III) ion are governed by the multipolar mechanism, while the exchange mechanism dominates the  ${}^5\text{D}_1 \leftarrow {}^7\text{F}_0$  and  ${}^5\text{D}_0 \leftarrow {}^7\text{F}_1$  excitations. Reference<sup>21</sup> presents the details of all terms contained in the eqn (7)–(9).

The  $(1 - \sigma_0)$  shielding factor, from eqn (9), deserves particular mention and is estimated as a function of the distance from the Ln(III) ion nucleus to the electronic barycentre of the ligand donor (or acceptor) state,<sup>29</sup> such distance is known as  $R_{\text{L}}$  (eqn (11)).

$$(1 - \sigma_0) = \rho \left( \frac{R_{\text{min}}}{R_{\text{L}}} \right)^{7/2} \quad (10)$$

$$R_{\text{L}} = \frac{\sum_i c_i^2 R_{\text{L},i}}{\sum_i c_i^2} \quad (11)$$

where  $c_i$  is a given molecular orbital coefficient of the  $i$  atom that contributes to the ligand state,  $R_{\text{L},i}$  is the distance from  $i$  atom to the Ln(III) ion, and  $R_{\text{min}}$  is the smallest distance between the atoms coordinated directly and the Ln(III) ion. The  $\rho$  overlap integral between the valence shells of the Ln(III) ion and the ligating atom usually assumes a value equal to 0.05.

The  $F$  term, from eqn (7) and (9), corresponds to the energy mismatch spectral overlap and is approximately calculated by:

$$F = \frac{1}{\hbar \gamma_{\text{L}}} \sqrt{\frac{\ln 2}{\pi}} e^{-\left(\frac{\Delta}{\hbar \gamma_{\text{L}}}\right)^2 \ln 2} \quad (12)$$

where the ligand bandwidth at half-height,  $\gamma_{\text{L}}$  (in  $\text{s}^{-1}$ ) is considered as being much larger than the widths of the 4f–4f transitions of Ln(III) ions ( $\gamma_{\text{Ln}}$ ). The  $\Delta$  quantity (in erg) is the energy difference between donor and acceptor energy states involved in the ligand–metal ET. Back ET rate is calculated multiplying the corresponding direct ET rate by the Boltzmann factor  $e^{-|\Delta|/k_{\text{B}}T}$ , where  $k_{\text{B}}$  stands for the Boltzmann constant and  $T$  is assumed as being the environment temperature.

The  $\Omega_{\lambda}^{\text{FED}}$  corresponds to the forced electric dipole (FED) intensity parameters, which is derived from the Judd–Ofelt theory (eqn (13)), and is taken from the eqn (14) neglecting the contribution from the dynamic coupling (DC). The FED and DC contributions depend on the so-called odd-rank ligand field parameter ( $\gamma_{\text{p}}^t$ ) and  $\Gamma_{\text{p}}^t$ , respectively.

$$\Omega_{\lambda}^{\text{calc}} = (2\lambda + 1) \sum_t^{\lambda-1, \lambda+1(\text{odd})} \sum_{p=-t}^{t(\text{all})} \frac{|B_{\lambda tp}|^2}{(2t + 1)} \quad (13)$$

$$B_{\lambda tp} = \frac{2}{\Delta E} \langle r^{t+1} \rangle \theta(t, \lambda) \gamma_{\text{p}}^t - \left[ \frac{(\lambda + 1)(2\lambda + 3)}{2\lambda + 1} \right]^{1/2} \langle r^{\lambda} \rangle (1 - \sigma_{\lambda}) \langle f \| C^{(\lambda)} \| f \rangle \Gamma_{\text{p}}^t \delta_{t, \lambda+1} \quad (14)$$

$$\gamma_{\text{p}}^t = \left( \frac{4\pi}{2t + 1} \right)^{1/2} e^2 \sum_j \rho_j (2\beta_j)^{t+1} \frac{g_j}{R_j^{t+1}} Y_{\text{p}}^{t*}(\theta_j, \phi_j) \quad (15)$$



$$I_p^t = \left( \frac{4\pi}{2t+1} \right)^{1/2} \sum_j \frac{\alpha_j}{R_j^{t+1}} Y_p^{t*}(\theta_j, \phi_j) \quad (16)$$

The  $j$  index runs over the atoms coordinated directly to the lanthanide ion,  $R_j$  corresponds to the distance between a given  $j$  atom and the lanthanide ion,  $\theta_j$  and  $\phi_j$  are the corresponding angular coordinates. The charge factors ( $g_j$ ) and polarizabilities ( $\alpha_j$ ), present in eqn (15) and (16), respectively, were adjusted using the QDC model<sup>30</sup> to reproduce the experimental values of  $\Omega_\lambda$ . QDC model is implemented into LUMPAC<sup>21</sup> and postulates that the  $g_j$  are obtained from the product between an adjustable parameter ( $Q$ ) and each ZDO (Zero Differential Overlap) electronic density ( $q_j$ ) of each  $j$  atom (eqn (17)). As shown in eqn (18), the  $\alpha_j$  quantities are calculated by using the  $D$  and  $C$  adjustable parameters together with the electrophilic superdelocalizabilities (SE). The reference<sup>21</sup> details all terms present in eqn (13)–(18).

$$g_j = Q \times q_j \quad (17)$$

$$\alpha_j = SE_j \times D + C \quad (18)$$

From the energy of the occupied molecular orbital and the corresponding linear coefficients calculated with Sparkle/PM6, considering the B3LYP geometry of **[Eu(btfa)<sub>3</sub>1c]**, the  $q_j$  and  $SE_j$  quantities were obtained using LUMPAC.

**2.5.3. Theoretical quantum yield.** The PLQY ( $q$ ) is an important spectroscopic parameter and is defined as the ratio of the number of emitted photons by the lanthanide ion to the number of absorbed photons by the ligand. For the Eu(III) ion,  $q$  is calculated using the following equation:

$$q = \frac{A_{\text{rad}} \eta_{5D_0}}{\varphi \eta_{S_0}} \quad (19)$$

where  $\varphi$  is the absorption rate ( $s^{-1}$ ) from the fundamental singlet to the excited singlet of the ligand.  $\eta_{S_0}$  and  $\eta_{5D_0}$  are the energetic population of the  $S_0$  fundamental state of the ligand and the  $5D_0$  emitting state of the  $\text{Eu}^{3+}$ , respectively.

The radiative emission rate ( $A_{\text{rad}}$ ) depends on the theoretical intensity parameters (eqn (13)) and for the europium ion is calculated by:

$$A_{\text{rad}} = \frac{32e^2\pi^3\chi}{3\hbar(2J+1)} \sum_{\lambda=2,4,6} \nu[5D_0 \rightarrow 7F_{J-\lambda}]^3 \Omega_\lambda \times \left| \langle 5D_0 \| U^{(\lambda)} \| 7F_{J-\lambda} \rangle \right|^2 + \frac{32\pi^3 n^3 \nu[5D_0 \rightarrow 7F_1]^3}{3\hbar} S_{\text{md}} \quad (20)$$

where  $e$  is the elementary charge;  $2J+1$  is the degeneracy of the initial state, for  $\text{Eu}^{3+}$  the  $5D_0$  emitting is considered ( $J=0$ ). The energies of the barycentres of the respective transitions are represented by the  $\nu[5D_0 \rightarrow 7F_J]$  quantities.  $\chi$  is the Lorentz local-field correction term, and is given by  $\chi = n(n^2+2)^2/9$ , where the  $n$  refractive index was considered as equal to 1.424, regarding the DCM solvent. The magnetic dipole strength ( $S_{\text{md}}$ ) of the  $5D_0 \rightarrow 7F_1$  transition is theoretically equals  $9.6 \times 10^{-42} \text{ esu}^2 \text{ cm}^2$ .<sup>30</sup>

From a system of equations in the steady-state condition the normalized population of a given  $a$  level considered in the ET modelling ( $\eta_j$ ) is calculated analytically by:

$$\frac{d\eta_a}{dt} = - \sum_{a \neq b} W_{ba} \eta_b + \sum_{a \neq b} W_{ab} \eta_a = 0 \quad (21)$$

where  $W_{ab}$  is the transfer rate from level  $a$  to level  $b$ , and if  $a=b$ ,  $W_{ab}=0$ .

## 3. Results and discussion

### 3.1. Synthesis, characterization and elucidation of the ground state geometry

In this work, we have synthesized a new hetero-trinuclear complex (Scheme 1) bearing a rigid dinuclear Pt(II) di-yne chromophore. The chemical structure of the Pt(II) di-yne chromophore, heterotrinnuclear (d–f–d) complex and their step-wise synthesis is depicted in Scheme 1. *Trans*-[(Ph)(Et<sub>3</sub>P)<sub>2</sub>Pt–C≡C–R–C≡C–Pt(PET<sub>3</sub>)<sub>2</sub>(Ph)] (R = 2,2'-bipyridine-5,5'-diyl) was synthesized following our previously reported method.<sup>16</sup> Briefly, 5,5'-dibromo-2,2'-bipyridine was protected with trimethylsilyl ethyne yielding **1a** (Scheme 1) by a Sonogashira cross-coupling reaction.<sup>31</sup> Smooth removal of trimethylsilyl groups with KOH/MeOH (Scheme 1) followed by dehydrohalogenation reaction of the diterminal alkyne **1b** with *trans*-[Ph(Et<sub>3</sub>P)<sub>2</sub>PtCl] yielded the Pt(II) di-yne **1c** (Scheme 1) as a yellow solid. The heterotrinnuclear complex **[Eu(btfa)<sub>3</sub>1c]** (Scheme 1) was synthesized in 74.0% yield by reacting **[Eu(btfa)<sub>3</sub>(H<sub>2</sub>O)<sub>2</sub>]** and Pt(II) di-yne (**1c**) in 1:1 ratio. The formulation of **[Eu(btfa)<sub>3</sub>1c]** was confirmed by elemental analysis, ESI-MS and IR spectroscopy. The elemental analysis shows satisfactory results and confirms the proposed formulation for the newly synthesized complex. The result of the elemental analysis was further confirmed by the ESI-MS. The spectrum of **[Eu(btfa)<sub>3</sub>1c]** in positive ion mode was recorded in MeOH. The complex displayed a molecular ion peak at 2016.59  $m/z$  [ $\text{M}^+$ ] (Fig. S2, ESI†) and thus confirms the proposed stoichiometry shown in Chart 1. The spectrum also displayed various peaks which could be due to fragmentation of the fluorinated  $\beta$ -diketonate ligands.<sup>32</sup> The results of the elemental analysis and ESI† were further confirmed by IR spectroscopy. The IR spectra of **[Eu(btfa)<sub>3</sub>1c]** together with those of **[Eu(btfa)<sub>3</sub>(H<sub>2</sub>O)<sub>2</sub>]** and **1c** are shown in Fig. S1, ESI.† The spectrum of **[Eu(btfa)<sub>3</sub>1c]** displayed a single, sharp –C≡C– stretch at 2087  $\text{cm}^{-1}$ , consistent with a *trans* configuration of the ethynyl units around the Pt(II) centres.<sup>15b</sup> The presence of this stretching absorption clearly supports the formation of the hetero-trinuclear complex. Moreover, the IR spectra of the complex exhibits C=O and C=C stretching vibrations at 1610 and 1571  $\text{cm}^{-1}$ , respectively, characteristics of the lanthanide chelate complexes containing  $\beta$ -diketone ligand.<sup>4c</sup> The appearance of (PCH<sub>2</sub>CH<sub>3</sub>)<sub>3</sub> twisting and bending vibration bands in the spectrum also provide additional evidence of complex formation; however, the position of the peaks remain unaltered appearing at 3041, 2961 and 2871  $\text{cm}^{-1}$  as observed in the Pt





Fig. 1 Ground state geometry of the heterotrinnuclear complex optimized at the B3LYP level of theory.

(ii) di-yne chromophore. The results clearly provide unambiguous support for the formation of the heterotrinnuclear complex  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$ .

Repeated attempts to obtain single crystals of the complex suitable for X-ray analysis failed. In fact, for predicting the photophysical properties of the given Eu complex, one needs to have the theoretical structure of the complex, even though the experimental structure is available.<sup>5a</sup> Given this fact, the ground state geometry of the present hetero-trinnuclear complex was elucidated by the DFT method shown in Fig. 1, and the coordination geometry of  $\text{EuN}_2\text{O}_6$  polyhedron is highlighted. The crystallographic structure of the  $\mathbf{1c}$  [EWOQEM Cambridge Structural Database (CSD) code]<sup>16</sup> shows a linear orientation around the  $-\text{C}\equiv\text{C}-$  triple bond. However, in the present case, we noted distortion when  $\mathbf{1c}$  is coordinated to the Eu(III) ion. Such a structural modification is observed in the literature when ligands comparable to  $\mathbf{1c}$  are coordinated to a given metal centre (*e.g.*, ASUVER and KIRSOU CSD refcodes),<sup>33</sup> and could be due to the interactions involving the peripheral substituents in the different ligands of  $\mathbf{1c}$  with the

$\beta$ -diketonate ligands. Spherical coordinates of coordination polyhedron are gathered in Table S1, ESI,<sup>†</sup> and, as can be seen, the Eu–N bonds predicted by the applied DFT approach are 2.684 and 2.647 Å, in line with literature values.<sup>34</sup> On the other hand, the Eu–O bonds are in the ranges of 2.399–2.422 Å and plainly the coordination polyhedron is of low symmetry.

### 3.2. Optical absorption spectroscopy

Fig. 2 shows the optical absorption spectra of the Pt(II) di-yne chromophore ( $\mathbf{1c}$ ) and of  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$ . The spectrum of the Pt(II) chromophore displays a strong split peak at 382 nm due to the  $\pi-\pi^*$  transitions. It is important to emphasize that in the spectrum of  $\mathbf{1c}$  with the ethynyl groups at the 5,5'-positions there is a 50 nm red shift compared to 6,6'-ethynyl based Pt(II) chromophore. This shift is a result of uninterrupted conjugation along the chromophore and attests to our assumption as stated in the introduction. The absorption spectrum of  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$  is dominated by spin allowed  $\pi-\pi^*$  transitions of the  $\beta$ -diketonate ligand and  $\mathbf{1c}$  in the UV-visible region (200–418 nm) with three major absorption peaks at 331 nm,



Fig. 2 (a) Optical absorption spectra of  $\mathbf{1c}$  and  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$  at RT. (b) Theoretical electronic spectrum calculated at the CAM-B3LYP level of theory using the B3LYP geometry for  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$ .



389 nm and 416 nm. As noted in the organometallic chromophore **1c**, the spectrum of the present heterotrinnuclear complex displays a red shift and this extends into the visible region of the spectrum compared to previously reported [Eu(btfa)<sub>3</sub>**1d**] [**1d**] = [(Ph)(Et<sub>3</sub>P)<sub>2</sub>Pt-C≡C-R-C≡C-Pt(Et<sub>3</sub>P)<sub>2</sub>(Ph)] (R = 2,2'-bipyridine-6,6'-diyl)<sup>4c</sup> (Fig S4, ESI†). It is thus excitable across a wide range of wavelengths from UV to the visible. The spectral differences of the two systems encouraged us to study the photoluminescence (PL) of the new system further.

To underpin the optical absorption spectroscopy result and to clearly understand the origin of transition, we obtained the theoretical absorption spectrum of the present complex (Fig. 2b). As shown in Fig. 2b, the theoretical absorption spectrum is in qualitative agreement with the experimental spectrum. The aforementioned assigned electronic transition is further supported by the molecular orbital (MO) analysis. Table 1 shows that the electronic transition highest occupied molecule orbital (HOMO) → lowest unoccupied molecular orbital (LUMO) dominates the band located at the highest wavelengths, and such MOs are centred in the molecular fragment present in the **1c** complex (Fig. 3). On the other hand, the band corresponding to the lowest wavelengths is domi-

nated by electronic transitions involving MOs centred on the β-diketonate ligands.

### 3.3. PL properties

The PL and excitation spectrum of [Eu(btfa)<sub>3</sub>**1c**] recorded in DCM at RT is shown in Fig. 4a. The excitation spectrum of the complex was recorded by monitoring the most intense emission transition <sup>5</sup>D<sub>0</sub> → <sup>7</sup>F<sub>2</sub> at 616 nm. The excitation spectrum contains a broad band in the region between 270–400 nm. Apart from this, the spectrum exhibits Eu(III) excitation transitions assigned to <sup>7</sup>F<sub>0</sub> → <sup>5</sup>D<sub>2</sub> (21 551 cm<sup>-1</sup>; 464 nm) and <sup>7</sup>F<sub>0</sub> → <sup>5</sup>D<sub>1</sub> (18 657 cm<sup>-1</sup>; 536 nm). The intensity of the excitation transition is higher than the broad band suggesting that the heterotrinnuclear complex could be excitable at the blue 464 nm wavelength.

The emission spectrum of [Eu(btfa)<sub>3</sub>**1c**] at RT was obtained by exciting it at λ<sub>max</sub> 345 nm (Fig. 4a). The spectrum displays typical well resolved sharp Eu(III) emission transitions at 579 nm, 594 nm, 616 nm, 653 nm and 701 nm, which corresponds to D<sub>0</sub> → <sup>7</sup>F<sub>0</sub>, <sup>5</sup>D<sub>0</sub> → <sup>7</sup>F<sub>1</sub>, <sup>5</sup>D<sub>0</sub> → <sup>7</sup>F<sub>2</sub>, <sup>5</sup>D<sub>0</sub> → <sup>7</sup>F<sub>3</sub> and <sup>5</sup>D<sub>0</sub> → <sup>7</sup>F<sub>4</sub>, respectively. The spectrum is dominated by the narrow hypersensitive electric dipole <sup>5</sup>D<sub>0</sub> → <sup>7</sup>F<sub>2</sub> transitions (FWHM = 12.57 nm, Table 2). Moreover, the spectrum does show some residual ligand fluorescence in the region between 425–531 nm, suggesting less efficient energy transfer (ET) from the newly synthesized organometallic chromophore compared to [Eu(btfa)<sub>3</sub>**1d**]. The 1931 CIE (*Commission internationale de l'éclairage*) colour coordinate of the heterotrinnuclear complex calculated from the PL spectrum shows a typical red emission with colour coordinates (x = 0.6358; y = 0.3381, Table 2), which is very close to National Television System Committee (NTSC) and, thus, could be beneficial for the design of monochromatic red emitter for full colour displays.<sup>5a</sup> Moreover, as mentioned previously, we excited the complex at 464 nm.

**Table 1** Electron transition configurations calculated at the TD-DFT CAM-B3LYP level of theory for the most relevant singlet states of [Eu(btfa)<sub>3</sub>**1c**]

Wavelength	Ligand	Oscillator strength	Major contribution	Total
338.09 nm	<b>1c</b>	1.79	HOMO → LUMO	87.30%
263.82 nm	<b>1c</b> /btfa	1.44	HOMO-2 → LUMO+3 (25.15%) HOMO-5 → LUMO+1 (22.94%) HOMO-8 → LUMO+2 (12.81%)	60.91%
277.85 nm	<b>1c</b> /btfa	0.34	HOMO → LUMO+1 (41.21%) HOMO → LUMO+4 (30.33%)	71.54%



**Fig. 3** Most relevant MOs calculated at the TD-DFT CAM-BLYP level of theory that explain the main electronic transitions.







Fig. 5 (a) Emission spectrum in DCM at RT at 464 nm, (b) CIE-1931 chromaticity diagram demonstrating the calculated color coordinate ( $x$ ,  $y$ ) values for  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$ .

**Table 3** Energy of the singlet and triplet excited states most relevant, distance from energy donor to acceptor centre ( $R_L$ ), and electronic transition configurations calculated at the TD-DFT CAM-B3LYP level of theory for the corresponding triplet state of  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$

State	Energy	$R_L$	Major contribution	Total
$S_1$	$29\,577.5\text{ cm}^{-1}$	$5.49\text{ \AA}$	HOMO $\rightarrow$ LUMO	87.30%
$T_1$	$20\,442.2\text{ cm}^{-1}$	$4.98\text{ \AA}$	HOMO $\rightarrow$ LUMO (79.55%)	79.55%
$T_2$	$22\,664.2\text{ cm}^{-1}$	$4.35\text{ \AA}$	HOMO-2 $\rightarrow$ LUMO+2 (26.69%) HOMO-2 $\rightarrow$ LUMO+3 (19.00%) HOMO-8 $\rightarrow$ LUMO+3 (16.34%)	62.03%

unit is more symmetrical than the 2,2'-bipyridine-6,6'-diyl unit ( $\Omega_2 = 29.45 \times 10^{-20}\text{ cm}^2$ )<sup>4c</sup> and results in less hypersensitivity of the ED  $^5D_0 \rightarrow ^7F_2$  transition. This is further supported by the observed lower  $R_{21} = 11.65$  value compared to that in the 2,2'-bipyridine-6,6'-diyl based complex ( $R_{21} = 16.60$ ).<sup>4c</sup> The intrinsic quantum yield ( $Q_{\text{Eu}}^{\text{Eu}}$ ) is calculated by utilizing eqn (6) and the data is summarized in Table 3. The complex  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$  displayed high  $Q_{\text{Eu}}^{\text{Eu}} = 38.45\%$ , however, it is lower than  $[\text{Eu}(\text{btfa})_3\mathbf{1d}]$   $Q_{\text{Eu}}^{\text{Eu}} = 53.95\%$ ,<sup>4c</sup> which is due to the increased  $A_{\text{NR}}$  value of the present complex.

The fitted  $\Omega_2$  and  $\Omega_4$  values using the QDC model are in perfect agreement with the corresponding experimental values. This procedure is important to obtain the forced electric dipole contribution for the intensity parameters, which are presented in Table S2, ESI† and are used to evaluate the energy transfer rates *via* the direct coulombic interaction mechanism.

### 3.4. Intermolecular energy transfer (IET) process

The energy of the most relevant triplet excited states, as well as the respective distance between donor and acceptor centre ( $R_L$ ), calculated at the TD-DFT CAM-B3LYP level of theory are shown in Table 3. In addition, the table presents the electronic transition configurations for each of the relevant triplet states

of  $[\text{Eu}(\text{btfa})_3\mathbf{1c}]$ . The HOMO  $\rightarrow$  LUMO transition is the one responsible for the lowest triplet state and as pictured in Fig. 4, such orbitals are centred on the ligands present in  $\mathbf{1c}$ . In this manner, the lowest triplet state ( $T_1 = 20\,442.2\text{ cm}^{-1}$ ) calculated at the CAM-B3LYP level of theory using the B3LYP geometry is characterized as involving MOs centred on the ligands present in the  $\mathbf{1c}$  molecular fragment. The energy of the next lowest triplet state ( $T_2$ ) is equal to  $22\,664\text{ cm}^{-1}$  and the most relevant electronic transitions involve MOs centred mainly on the btfa ligands.  $R_L$  values present in Table 3 show that the donor centre is more distant from the Eu(III) centre for  $T_2$  in comparison with  $T_1$  due to the contribution of the btfa ligands in  $T_2$ .

In order to take account the effect of the distinct molecular groups (Table 3) in the modelling of the ligand – Eu(III) energy transfer, the diagram pictured in Fig. 6 was proposed, in which the ET rates were calculated applying the LUMPAC program. In the ET modelling, for Eu(III) only three states were considered, namely,  $^5D_4$  (*ca.*  $27\,586\text{ cm}^{-1}$ ),  $^5D_1$  (*ca.*  $19\,027\text{ cm}^{-1}$ ), and  $^5D_0$  (*ca.*  $17\,293\text{ cm}^{-1}$ ), with the energy values obtained from Carnall *et al.*<sup>36</sup> To calculate the energetic population involving the states shown in Fig. 6, typical experimental values for the non-radiative rates in coordination compounds were considered.<sup>36</sup>

For complexes containing  $\beta$ -diketonate ligands it is known that the ET channel is the one dominated by the exchange mechanism (Dexter mechanism), and the ET value the order of  $10^8\text{ s}^{-1}$  (Table 4) calculated with the exchange mechanism confirms this. The triplet  $\rightarrow$  ( $^5D_0$ ,  $^5D_1$ ) channels are related to the  $^5D_1 \leftarrow ^7F_0$  and  $^5D_0 \leftarrow ^7F_1$  excitations, respectively, where the  $^7F_1$  state is considered as being thermally populated.<sup>5c</sup> By considering the schematic energy-level diagram postulated in Fig. 6 together the ET rates presented in Table 4, the populations of the  $S_0$  and  $^5D_0$  states were calculated ( $\eta_{S_0} = 0.28$  and  $\eta_{^5D_0} = 0.52$ ), which provided a theoretical PLQY of 19.8% that is close to experimentally determined value 15.10%.





Fig. 6 Schematic energy-level diagram showing the most important ET channels for  $[\text{Eu}(\text{btfa})_3]1\text{c}$ . Please see Table 5 for the corresponding values of ET rates.

Table 4 Energy transfer rates calculated by the Malta's model using LUMPAC for the  $[\text{Eu}(\text{btfa})_3]1\text{c}$  complexes with the ligand state energies calculated at the TD-DFT CAM-B3LYP level of theory

Ligand state ( $\text{cm}^{-1}$ )	4f state ( $\text{cm}^{-1}$ )	ET rate ( $\text{s}^{-1}$ )	Energy back-transfer rate ( $\text{s}^{-1}$ )
$S_1$ (29 577.5)	${}^5D_4$ (27 586)	$1.60 \times 10^4$	$1.14 \times 10^1$
$T_2$ (22 664.2)	${}^5D_1$ (19 027)	$1.27 \times 10^9$	$3.36 \times 10^1$
$T_2$ (22 664.2)	${}^5D_0$ (17 293)	$8.72 \times 10^8$	$5.66 \times 10^{-3}$
$T_1$ (20 442.2)	${}^5D_1$ (19 027)	$5.96 \times 10^8$	$6.73 \times 10^5$
$T_1$ (20 442.2)	${}^5D_1$ (19 027)	$6.81 \times 10^8$	$1.88 \times 10^2$

### 3.5. Electrochemical properties

Preliminary CV experiments were conducted with a glassy carbon disk, Pt wire, and Ag/AgCl electrode as the working electrode, counter electrode, and reference electrode, respectively, in deaerated DCM solution containing 0.1 M tetrabutyl-

ammonium hexafluorophosphate ( $\text{Bu}_4\text{NPF}_6$ ) as the electrolyte and approx. 1 mM metal complex. The CV experiment was performed to investigate the electrochemical behaviour of  $[\text{Eu}(\text{btfa})_3]1\text{c}$  and the related  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  in the  $-2.0$  to  $2.0$  V range. Table 5 contains all the electrochemical parameters and data obtained. The protonated btfa ligand showed two reductions peaks with an initial broad shoulder in the region of  $-2.0$  to  $0.0$  V and there was no oxidation peak in the positive potential region. Both  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  and  $[\text{Eu}(\text{btfa})_3]1\text{c}$  show an oxidation signal and a complex sequence of reduction signals. We noted a considerable difference in reduction peaks between  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  and  $[\text{Eu}(\text{btfa})_3]1\text{c}$ . New chemically irreversible oxidation peaks appear in positive region at  $1.74$  V and  $1.57$  V for  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  and for  $[\text{Eu}(\text{btfa})_3]1\text{c}$  respectively. The latter complex shows a reduction peak at  $-0.77$  V (Fig. 7), which we tentatively assign to the reduction peak of the  $\text{Eu}(\text{III})$ .<sup>37</sup> The reduction peak of  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  was ca.  $0.49$  V less negative compared to  $[\text{Eu}(\text{btfa})_3]1\text{c}$ . This observation

Table 5 Cyclic voltammetry data of btfa,  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  and  $[\text{Eu}(\text{btfa})_3]1\text{c}$

Compound	$E_{\text{Ox}}^{\text{onset}}$ (V)	$E_{\text{red}}^{\text{onset}}$ (V)	$E_{\text{p}}^{\text{Ox}}$ (V)	$E_{\text{p}}^{\text{RE}}$ (V)	HOMO (eV)	LUMO (eV)	$E_{\text{g}}^{\text{ele}}$ (eV)	$E_{\text{g}}^{\text{opt}}$ (eV)
btfa	$-0.82^a$	$-0.67^a$	$-0.53^b, -1.13^b$	$-0.86^c, -1.22^c$	—	—	—	—
$[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$	$1.44^a$	$-0.06^a$	$1.74^b$	$-0.28^c, -1.20^c, -1.63^c$	$-5.85^d$	$-2.49^e (-4.35)^e$	$1.6^f$	3.36
$[\text{Eu}(\text{btfa})_3]1\text{c}$	$1.19^a$	$-0.41^a$	$1.57^b$	$-0.77^c, -1.22^c, -1.36^c, -1.77^c$	$-5.60^d$	$-3.03^e (-4.00)^e$	$1.5^f$	2.57
Theoretical (B3LYP)	—	—	—	—	$-5.40$	$-2.18$	—	3.19

<sup>a</sup>  $E_{\text{Ox}}^{\text{onset}}$  = the onset oxidation potentials;  $E_{\text{Re}}^{\text{onset}}$  = the onset reduction potentials. <sup>b</sup> Anodic peak potential. <sup>c</sup> Cathodic peak potential. <sup>d</sup> HOMO energy level. <sup>e</sup> LUMO energy level. <sup>f</sup> Energy gap measured from electrochemical data according to the  $E_{\text{onset}}$ ,  $E_{\text{g}}^{\text{ele}} = E_{\text{Ox}}^{\text{onset}} - E_{\text{red}}^{\text{onset}}$  eV. The energy LUMO values were calculated by cyclic voltammogram and are displayed in parentheses.





Fig. 7 Cyclic voltammograms of btfa (red),  $[\text{Eu}(\text{btfa})_3(\text{H}_2\text{O})_2]$  (black) and  $[\text{Eu}(\text{btfa})_3]1\text{c}$  (blue) in the region between  $-2.0$  to  $2.0$  V on glassy carbon electrode in  $0.1$  M  $\text{Bu}_4\text{NPF}_6$  solution in DCM at a scan rate of  $100$   $\text{mV s}^{-1}$ .

suggests that primary ligands play a significant role in changing the electrochemical behaviour of  $\text{Eu}(\text{III})$  complexes and the shift of reduction peak of  $\text{Eu}(\text{III})$ .<sup>38</sup> The other peaks could correspond to the reduction/oxidation of the electrochemically active  $\beta$ -diketonate groups<sup>39</sup> or further fragmentation products.

For calibration, the redox potential of ferrocene/ferrocenium ( $\text{Fc}/\text{Fc}^+$ ) was measured under the same experimental conditions, and it is located at  $0.39$  V vs. the  $\text{Ag}/\text{AgCl}$  electrode (Fig. S7, ESI<sup>†</sup>). HOMO energy values were calculated based on the value of  $-4.8$  eV for  $\text{Fc}$  with respect to a zero vacuum level.<sup>40</sup> The energy levels of the HOMO was estimated according to the following equation:<sup>41</sup>  $E_{\text{HOMO}} = -(E_{\text{Ox}}^{\text{onset}} + 4.41)$  eV where  $E_{\text{Ox}}^{\text{onset}}$  is the onset oxidation potential vs.  $\text{Ag}/\text{AgCl}$ . The energy band gap ( $E_{\text{g}}^{\text{ele}}$ ) was calculated from the onset wavelength of the UV absorption ( $E_{\text{g}}^{\text{ele}} = 1240/\lambda$ ).<sup>42</sup> The LUMO energy level was obtained from the HOMO energy and the energy bandgap ( $E_{\text{g}}^{\text{ele}} = \text{LUMO} - \text{HOMO}$ ) and  $E_{\text{LUMO}} = -(E_{\text{Red}}^{\text{onset}} + 4.41)$  eV where  $E_{\text{Red}}^{\text{onset}}$  = onset reduction potential vs.  $\text{Ag}/\text{AgCl}$ . An important disparity was ascertained between the measured optical and electrochemical energy bandgap values. However, there is no contradiction between these values, since they refer to different processes. The optical absorption data provides an estimation of the energy difference of the HOMO–LUMO orbitals, while the electrochemical band gap is consistent with the energy required to form a tightly bound exciton with additional contributions from charging.<sup>43</sup> The redox potentials measured by CV afford the absolute energetic positions of the HOMO and LUMO levels (assuming insignificant effects from charging), and the electrochemical or transport bandgap depicts the energy required to form free charge carriers.<sup>43,44</sup> Moreover, the theoretically estimated HOMO and LUMO values are almost similar to the experimentally determined value (HOMO  $\approx -5.60$  eV, Table 5) especially at the **B3LYP** level (HOMO  $\approx -5.40$  eV, Table S3, ESI<sup>†</sup>).

## 4. Conclusion

In summary, we have utilized a  $\text{Pt}(\text{II})$  di-yne chromophore incorporating a bipyridine-5,5'-diyl spacer (**1c**) as a chelate to syn-

thesize a novel hetero-trinuclear (d–f–d) complex  $[\text{Eu}(\text{btfa})_3]1\text{c}$ . The structure of the complex was elucidated using DFT methods. The optical absorption spectrum of the complex exhibited transitions in the  $200$ – $418$  nm range. Interestingly, the complex displayed a red shift compared to the analogous kinked hetero-trinuclear complex reported earlier by us.<sup>4c</sup> This shift is due to uninterrupted conjugation in the present complex (Chart 1). The PL studies revealed dual emissions, with a typical red emission (CIE;  $x = 0.6358$ ;  $y = 0.3381$ ) when excited at  $345$  nm and a green emission (CIE<sub>*x,y*</sub> =  $0.3011$ ,  $0.5726$  at  $464$  nm excitation. The dual emission could be due to two different triplet states centred at: (a) btfa  $22\,664.2$   $\text{cm}^{-1}$  with the ET rate  $1.27 \times 10^9$   $\text{s}^{-1}$  with the negligible energy back-transfer rate (Table 4) and (b) organometallic chromophore ( $20\,442.2$   $\text{cm}^{-1}$ ) with an ET rate  $5.96 \times 10^8$   $\text{s}^{-1}$  with the energy back-transfer rate of  $6.73 \times 10^5$   $\text{s}^{-1}$  for the  $\text{T}_1 \rightarrow {}^5\text{D}_1$ . The excited state lifetime of the present complex is in microsecond range typical for europium  $\beta$ -diketonate complexes. The intermolecular energy transfer in the complex on the basis of experimental results and DFT calculations is discussed in detail. Moreover, the calculated photophysical parameters are in excellent agreement with the experimentally observed results.

## Conflicts of interest

The authors declare no conflicts of interest.

## Acknowledgements

M. S. K. acknowledges the Research Council (TRC), Oman (Grant: RC/RG-SCI/CHEM/20/01) for funding. I. J. A. B. acknowledges the Ministry of Education, Oman for a Ph.D. scholarship. R. I. thanks HM's Trust Fund (Grant No. SR/SQU/SCI/CHEM/16/02) for a postdoctoral fellowship. W. F. O. thanks PIBIC/CNPq/UFS (02/2019 COPES/POSGRAP/UFS) for a scientific initiation fellowship. P. R. R. is grateful to the Engineering and Physical Sciences Research Council (EPSRC) for continued funding (Grant EP/K004956/1).



## References

- 1 A. Haque, R. A. Al-Balushi, I. J. Al-Busaidi, M. S. Khan and P. R. Raithby, *Chem. Rev.*, 2018, **118**, 8474–8597.
- 2 (a) A. F. Rausch, H. H. H. Homeier and H. Yersin, in *Photophysics of Organometallics*, ed. A. J. Lees, Springer Berlin Heidelberg, Berlin, Heidelberg, 2010, pp. 193–235; (b) I. J. Al-Busaidi, A. Haque, N. K. Al Rasbi and M. S. Khan, *Synth. Met.*, 2019, **257**, 116189; (c) C.-L. Ho, Z.-Q. Yu and W.-Y. Wong, *Chem. Soc. Rev.*, 2016, **45**, 5264–5295; (d) W.-Y. Wong, *Dalton Trans.*, 2007, 4495–4510; (e) J. Zhang, L. Xu, C.-L. Ho and W.-Y. Wong, in *Polymer Synthesis Based on Triple-Bond Building Blocks*, ed. B. Z. Tang and R. Hu, Springer International Publishing, Cham, 2018, pp. 157–189; (f) L. Xu, C.-L. Ho, L. Liu and W.-Y. Wong, *Coord. Chem. Rev.*, 2018, **373**, 233–257; (g) C.-L. Ho and W.-Y. Wong, *Coord. Chem. Rev.*, 2013, **257**, 1614–1649.
- 3 (a) H. Yersin, *Highly Efficient Oleds with Phosphorescent Materials*, John Wiley & Sons, 2008; (b) S. Wang, H. Zhang, B. Zhang, Z. Xie and W.-Y. Wong, *Mater. Sci. Eng., R*, 2020, **140**, 100547; (c) Z. Chen, C.-L. Ho, L. Wang and W.-Y. Wong, *Adv. Mater.*, 2020, **32**, 1903269; (d) G. Zhou, W.-Y. Wong and X. Yang, *Chem. – Asian J.*, 2011, **6**, 1706–1727; (e) X. Yang, G. Zhou and W.-Y. Wong, *Chem. Soc. Rev.*, 2015, **44**, 8484–8575.
- 4 (a) A. N. Al-Khalili, I. J. Al-Busaidi, R. Ilmi, M. Al-Mandhary, M. S. Khan and N. K. Al-Rasbi, *Inorg. Chim. Acta*, 2020, **501**, 119226; (b) K. Binnemans, *Coord. Chem. Rev.*, 2015, **295**, 1–45; (c) R. Ilmi, A. Haque, I. J. Al-Busaidi, N. K. Al Rasbi and M. S. Khan, *Dyes Pigm.*, 2019, **162**, 59–66.
- 5 (a) M. S. Khan, R. Ilmi, W. Sun, J. D. L. Dutra, W. F. Oliveira, L. Zhou, W.-Y. Wong and P. R. Raithby, *J. Mater. Chem. C*, 2020, **8**, 5600–5612; (b) R. Ilmi, W. Sun, J. D. L. Dutra, N. K. Al-Rasbi, L. Zhou, P.-C. Qian, W.-Y. Wong, P. R. Raithby and M. S. Khan, *J. Mater. Chem. C*, 2020, **8**, 9816–9827; (c) R. Ilmi, M. S. Khan, Z. Li, L. Zhou, W.-Y. Wong, F. Marken and P. R. Raithby, *Inorg. Chem.*, 2019, **58**, 8316–8331; (d) R. Ilmi, S. Kansız, N. K. Al-Rasbi, N. Dege, P. R. Raithby and M. S. Khan, *New J. Chem.*, 2020, **44**, 5673–5683; (e) R. Ilmi, M. S. Khan, W. Sun, L. Zhou, W.-Y. Wong and P. R. Raithby, *J. Mater. Chem. C*, 2019, **7**, 13966–13975; (f) J. Li, J.-Y. Wang and Z.-N. Chen, *J. Mater. Chem. C*, 2013, **1**, 3661–3668; (g) M. D. Ward, *Coord. Chem. Rev.*, 2007, **251**, 1663–1677; (h) H.-B. Xu, L.-X. Shi, E. Ma, L.-Y. Zhang, Q.-H. Wei and Z.-N. Chen, *Chem. Commun.*, 2006, 1601–1603.
- 6 R. Ilmi, S. Anjum, A. Haque and M. S. Khan, *J. Photochem. Photobiol., A*, 2019, **383**, 111968.
- 7 E. G. Moore, A. P. S. Samuel and K. N. Raymond, *Acc. Chem. Res.*, 2009, **42**, 542–552.
- 8 J. Kido and Y. Okamoto, *Chem. Rev.*, 2002, **102**, 2357–2368.
- 9 (a) S. Zhu and Z. Gu, in *Lanthanide-Based Multifunctional Materials*, ed. P. Martín-Ramos and M. Ramos Silva, Elsevier, 2018, pp. 381–410; (b) K. Y. Zhang, Q. Yu, H. Wei, S. Liu, Q. Zhao and W. Huang, *Chem. Rev.*, 2018, **118**, 1770–1839.
- 10 (a) S. I. Klink, H. Keizer and F. C. van Veggel, *Angew. Chem.*, 2000, **112**, 4489–4491; (b) T. J. Sørensen and S. Faulkner, *Acc. Chem. Res.*, 2018, **51**, 2493–2501; (c) M. Pan, W.-M. Liao, S.-Y. Yin, S.-S. Sun and C.-Y. Su, *Chem. Rev.*, 2018, **118**, 8889–8935.
- 11 (a) K.-J. Chen, H.-B. Xu, L.-Y. Zhang and Z.-N. Chen, *Inorg. Chem. Commun.*, 2009, **12**, 744–746; (b) O. J. Stacey, A. J. Amoroso, J. A. Platts, P. N. Horton, S. J. Coles, D. Lloyd, C. F. Williams, A. J. Hayes, J. J. Dunsford and S. J. A. Pope, *Chem. Commun.*, 2015, **51**, 12305–12308.
- 12 I. M. Etchells, M. C. Pfrunder, J. A. G. Williams and E. G. Moore, *Dalton Trans.*, 2019, **48**, 2142–2149.
- 13 R. Ziessel, S. Diring, P. Kadjane, L. Charbonnière, P. Retailleau and C. Philouze, *Chem. – Asian J.*, 2007, **2**, 975–982.
- 14 M. D. Ward, *Coord. Chem. Rev.*, 2007, **251**, 1663–1677.
- 15 (a) J. S. Wilson, N. Chawdhury, M. R. A. Al-Mandhary, M. Younus, M. S. Khan, P. R. Raithby, A. Köhler and R. H. Friend, *J. Am. Chem. Soc.*, 2001, **123**, 9412–9417; (b) M. Jayapal, A. Haque, I. J. Al-Busaidi, R. Al-Balushi, M. K. Al-Suti, S. M. Islam and M. S. Khan, *J. Organomet. Chem.*, 2017, **842**, 32–38.
- 16 M. S. Khan, M. R. A. Al-Mandhary, M. K. Al-Suti, A. K. Hisahm, P. R. Raithby, B. Ahrens, M. F. Mahon, L. Male, E. A. Marseglia, E. Tedesco, R. H. Friend, A. Kohler, N. Feeder and S. J. Teat, *J. Chem. Soc., Dalton Trans.*, 2002, 1358–1368.
- 17 (a) M. S. Khan, M. R. A. Al-Mandhary, M. K. Al-Suti, F. R. Al-Battashi, S. Al-Saadi, B. Ahrens, J. K. Bjernemose, M. F. Mahon, P. R. Raithby, M. Younus, N. Chawdhury, A. Köhler, E. A. Marseglia, E. Tedesco, N. Feeder and S. J. Teat, *Dalton Trans.*, 2004, 2377–2385; (b) R. A. Al-Balushi, A. Haque, M. Jayapal, M. K. Al-Suti, J. Husband, M. S. Khan, J. M. Skelton, K. C. Molloy and P. R. Raithby, *Inorg. Chem.*, 2016, **55**, 10955–10967; (c) M. S. Khan, M. R. A. Al-Mandhary, M. K. Al-Suti, T. C. Corcoran, Y. Al-Mahrooqi, J. P. Atfield, N. Feeder, W. I. F. David, K. Shankland, R. H. Friend, A. Köhler, E. A. Marseglia, E. Tedesco, C. C. Tang, P. R. Raithby, J. C. Collings, K. P. Roscoe, A. S. Batsanov, L. M. Stimson and T. B. Marder, *New J. Chem.*, 2003, **27**, 140–149; (d) M. S. Khan, A. K. Kakkar, N. J. Long, J. Lewis, P. Raithby, P. Nguyen, T. B. Marder, F. Wittmann and R. H. Friend, *J. Mater. Chem.*, 1994, **4**, 1227–1232; (e) M. S. Khan, M. K. Al-Suti, M. R. A. Al-Mandhary, B. Ahrens, J. K. Bjernemose, M. F. Mahon, L. Male, P. R. Raithby, R. H. Friend, A. Köhler and J. S. Wilson, *Dalton Trans.*, 2003, 65–73.
- 18 (a) N. Chawdhury, A. Köhler, R. H. Friend, W. Y. Wong, J. Lewis, M. Younus, P. R. Raithby, T. C. Corcoran, M. R. A. Al-Mandhary and M. S. Khan, *J. Chem. Phys.*, 1999, **110**, 4963–4970; (b) L. Sudha Devi, M. K. Al-Suti, N. Zhang, S. J. Teat, L. Male, H. A. Sparkes, P. R. Raithby, M. S. Khan and A. Köhler, *Macromolecules*, 2009, **42**, 1131–1141;



- (c) R. A. Al-Balushi, A. Haque, M. Jayapal, M. K. Al-Suti, J. Husband, M. S. Khan, O. F. Koentjoro, K. C. Molloy, J. M. Skelton and P. R. Raithby, *Inorg. Chem.*, 2016, **55**, 6465–6480; (d) J. S. Wilson, A. S. Dhoot, A. J. A. B. Seeley, M. S. Khan, A. Köhler and R. H. Friend, *Nature*, 2001, **413**, 828–831; (e) M. Younus, A. Köhler, S. Cron, N. Chawdhury, M. R. A. Al-Mandhary, M. S. Khan, J. Lewis, N. J. Long, R. H. Friend and P. R. Raithby, *Angew. Chem., Int. Ed.*, 1998, **37**, 3036–3039; (f) P. Li, B. Ahrens, K.-H. Choi, M. S. Khan, P. R. Raithby, P. J. Wilson and W.-Y. Wong, *CrystEngComm*, 2002, **4**, 405–412.
- 19 M. S. Khan, M. R. A. Al-Mandhary, M. K. Al-Suti, N. Feeder, S. Nahar, A. Köhler, R. H. Friend, P. J. Wilson and P. R. Raithby, *J. Chem. Soc., Dalton Trans.*, 2002, 2441–2448.
- 20 M. S. Khan, M. R. A. Al-Mandhary, M. K. Al-Suti, A. K. Hisahm, P. R. Raithby, B. Ahrens, M. F. Mahon, L. Male, E. A. Marseglia, E. Tedesco, R. H. Friend, A. Köhler, N. Feeder and S. J. Teat, *J. Chem. Soc., Dalton Trans.*, 2002, 1358–1368.
- 21 J. D. Dutra, T. D. Bispo and R. O. Freire, *J. Comput. Chem.*, 2014, **35**, 772–775.
- 22 D. F. Eaton, *J. Photochem. Photobiol., B*, 1988, **2**, 523–531.
- 23 N. B. Lima, S. M. Goncalves, S. A. Junior and A. M. Simas, *Sci. Rep.*, 2013, **3**, 2395.
- 24 M. S. Khan, M. K. Al-Suti, B. Ahrens, P. R. Raithby and S. J. Teat, *Acta Crystallogr., Sect. E: Struct. Rep. Online*, 2004, **60**, m735–m737.
- 25 R. O. Freire and A. M. Simas, *J. Chem. Theory Comput.*, 2010, **6**, 2019–2023.
- 26 F. Neese, *Wiley Interdiscip. Rev.: Comput. Mol. Sci.*, 2018, **8**, e1327.
- 27 F. Weigend and R. Ahlrichs, *Phys. Chem. Chem. Phys.*, 2005, **7**, 3297–3305.
- 28 P. J. Hay and W. R. Wadt, *J. Chem. Phys.*, 1985, **82**, 270–283.
- 29 A. N. Carneiro Neto, E. E. S. Teotonio, G. F. de Sá, H. F. Brito, J. Legendziewicz, L. D. Carlos, M. C. F. C. Felinto, P. Gawryszewska, R. T. Moura, R. L. Longo, W. M. Faustino and O. L. Malta, in *Handbook on the Physics and Chemistry of Rare Earths*, ed. J.-C. G. Bünzli and V. K. Pecharsky, Elsevier, 2019, vol. 56, pp. 55–162.
- 30 J. D. L. Dutra, N. B. D. Lima, R. O. Freire and A. M. Simas, *Sci. Rep.*, 2015, **5**, 13695.
- 31 K. Sonogashira, Y. Tohda and N. Hagihara, *Tetrahedron Lett.*, 1975, **16**, 4467–4470.
- 32 S. V. Eliseeva, O. V. Kotova, F. Gumy, S. N. Semenov, V. G. Kessler, L. S. Lepnev, J.-C. G. Bünzli and N. P. Kuzmina, *J. Phys. Chem. A*, 2008, **112**, 3614–3626.
- 33 (a) J. E. Barnsley, S. Ø. Scottwell, A. B. S. Elliott, K. C. Gordon and J. D. Crowley, *Inorg. Chem.*, 2016, **55**, 8184–8192; (b) F. Paul, S. Goeb, F. Justaud, G. Argouarch, L. Toupet, R. F. Ziesel and C. Lapinte, *Inorg. Chem.*, 2007, **46**, 9036–9038.
- 34 S. A. Cotton and P. R. Raithby, *Coord. Chem. Rev.*, 2017, **340**, 220–231.
- 35 (a) F. Wu, H. Tong, Z. Li, W. Lei, L. Liu, W.-Y. Wong, W.-K. Wong and X. Zhu, *Dalton Trans.*, 2014, **43**, 12463–12466; (b) X. Yang, G. Zhou and W.-Y. Wong, *J. Mater. Chem. C*, 2014, **2**, 1760–1778.
- 36 W. T. Carnall, H. Crosswhite and H. M. Crosswhite, *Energy Level Structure and Transition Probabilities in the Spectra of the Trivalent Lanthanides in LaF<sub>3</sub>*, United States, 1978.
- 37 M. Gál, F. Kielar, R. Sokolová, Š. Ramešová and V. Kolivoška, *Eur. J. Inorg. Chem.*, 2013, **2013**, 3217–3223.
- 38 (a) E. L. Yee, R. J. Cave, K. L. Guyer, P. D. Tyma and M. J. Weaver, *J. Am. Chem. Soc.*, 1979, **101**, 1131–1137; (b) F. Muraier, L. Kišová, J. Komenda and G. Gritzner, *J. Electroanal. Chem.*, 1999, **470**, 1–8.
- 39 M. M. Richter and A. J. Bard, *Anal. Chem.*, 1996, **68**, 2641–2650.
- 40 (a) M. Thelakkat and H.-W. Schmidt, *Adv. Mater.*, 1998, **10**, 219–223; (b) L. Dou, J. Gao, E. Richard, J. You, C.-C. Chen, K. C. Cha, Y. He, G. Li and Y. Yang, *J. Am. Chem. Soc.*, 2012, **134**, 10071–10079.
- 41 J. Yu, M. Xiao, H. Tan and W. Zhu, *Thin Solid Films*, 2016, **619**, 1–9.
- 42 X. Zhang, Z. Chi, H. Li, B. Xu, X. Li, S. Liu, Y. Zhang and J. Xu, *J. Mater. Chem.*, 2011, **21**, 1788–1796.
- 43 A. Bejan, S. Shova, M.-D. Damaceanu, B. C. Simionescu and L. Marin, *Cryst. Growth Des.*, 2016, **16**, 3716–3730.
- 44 Y. Takeda, T. L. Andrew, J. M. Lobe, A. J. Mork and T. M. Swager, *Angew. Chem., Int. Ed.*, 2012, **51**, 9042–9046.

