Chemical Science

EDGE ARTICLE

CrossMark

Cite this: Chem. Sci., 2016, 7, 5537

Received 16th February 2016 Accepted 7th May 2016 DOI: 10.1039/c6sc00715e

www.rsc.org/chemicalscience

Introduction

Photovoltaic technology, such as dye-sensitised solar cells, enables the conversion of solar energy into electricity and is commercially available.1 Solar fuel devices allow for the storage of solar energy in a chemical energy carrier, but are only in an early stage of development and have not yet reached the required efficiencies and stabilities at low cost suitable for application.² Splitting of water into its elements in a photoelectrochemical (PEC) cell is a potentially sustainable means of generating renewable H₂.³ However, a lack of novel strategies to electronically couple a light-harvesting unit to a stable proton reduction catalyst is currently holding back advances in the development of high-performance PEC devices.⁴ Molecular dyes and catalysts offer several advantages over heterogeneous alternatives as their composition and activity can be more easily synthetically controlled and fine-tuned.⁵ They provide an excellent platform to develop rational strategies such as layerby-layer deposition⁶ to integrate dyes and catalysts on electrode materials and enable detailed mechanistic studies to improve

Photoelectrochemical hydrogen production in water using a layer-by-layer assembly of a Ru dye and Ni catalyst on NiO⁺

Manuela A. Gross, Charles E. Creissen, Katherine L. Orchard and Erwin Reisner*

Capture and conversion of sunlight into the storable energy carrier H₂ can be achieved through photoelectrochemical water splitting using light-absorbing cathodes and anodes bearing H₂ and O₂ evolving catalysts. Here, we report on the development of a dye-sensitised p-type nickel oxide (NiO) photocathode with a hexaphosphonated Ru(2,2'-bipyridine)₃ based dye (**RuP3**) and a tetraphosphonated molecular [Ni(P₂N₂)₂]²⁺ type proton reduction catalyst (NiP) for the photoreduction of aqueous protons to H₂. A layer-by-layer deposition approach was employed, using Zr⁴⁺ ions to link the phosphonate units in **RuP3** and **NiP** in a supramolecular assembly on the NiO photocathode. This approach keeps the dye in close proximity to the catalyst and semiconductor surface, but spatially separates **NiP** from NiO for advantageous electron transfer dynamics. The NiO|**RuP3**–Zr⁴⁺–**NiP** electrodes generate higher photocurrents and are more stable than photocathodes with **RuP3** and **NiP** co-immobilised on the NiO surface in the absence of Zr⁴⁺ cations linking dye and catalyst. The generation of H₂ with the NiO|**RuP3**–Zr⁴⁺–**NiP** hybrid electrode in pH 3 aqueous electrolyte solution during irradiation with a UV-filtered solar light simulator ($\lambda > 400$ nm, 100 mW cm⁻², AM1.5G) has been confirmed by gas chromatography at an underpotential of 300 mV ($E_{appl} = +0.3$ V vs. RHE), demonstrating the potential of these electrodes to store solar energy in the chemical bond of H₂.

our understanding of photoelectrode assemblies.⁷ Ultimately, these insights may contribute to the establishment of advanced approaches to fabricate electrodes in PEC water splitting cells.

We have previously reported on several suspension-based photocatalytic H2-generation systems with molecular catalysts attached to light-absorbing nanoparticles to advance our understanding of efficient combination of dyes and catalysts on semiconducting surfaces.8 However, all of these systems relied on the use of a sacrificial electron donor (SED) to provide the reducing equivalents for fuel formation. SEDs are chemicals of relatively high value and are consumed stoichiometrically during the H₂ generation process. They are disadvantageous as half-reaction promoting agents as they often form unknown decomposition products via highly reactive intermediates, which can interfere with the catalytic system, and should ultimately be avoided. One approach to bypass the need for a SED in a H₂ evolution system is to immobilise the catalyst onto a photocathode material that can be incorporated into a PEC cell. The redox cycle can then be closed by use of a suitable (photo)anode for water/substrate oxidation.3b,c One of the main challenges for the assembly of molecule-based PEC devices is the design and effective integration of H₂ evolving electrocatalysts and dyes onto the electrodes, which should ultimately allow for efficient solar light absorption, charge separation and chemical catalysis.



View Article Online

View Journal | View Issue

Christian Doppler Laboratory for Sustainable SynGas Chemistry, Lensfield Road, CB2 1EW Cambridge, UK. E-mail: reisner@ch.cam.ac.uk

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/c6sc00715e. Additional data related to this publication are available at the University of Cambridge data repository (https://www.repository.cam.ac.uk/handle/1810/255990).

Photocathode materials that have been studied for solar H₂ generation include p-silicon,9 p-GaP10 and p-NiO.11 Of these, p-type NiO offers the possibility to produce nanostructured high-surface area electrodes without the need for specialised techniques. High roughness is a prerequisite for maximising dye and catalyst loading on a given geometric surface area. Dye-sensitised NiO photocathodes in organic or aqueous electrolyte solution have been studied with sacrificial electron acceptors (SEAs),¹² [FeFe]-hydrogenase mimics,¹³ and rhodium and cobaloxime catalysts.11b-e,14 While charge transfer and recombination kinetics of NiO|dye15 and NiO|dye-catalyst13 assemblies have been studied in detail with time-resolved spectroscopy, light-driven H₂ production with dye-sensitised NiO photocathodes remains challenging and only cobaloximebased catalysts have been reported to generate H₂ with NiO.^{11b,d,e} The binding of the cobaloxime catalyst in these cases was achieved through a linker tethered to NiO bearing a free pyridine



Fig. 1 Structures of the dyes (RuP and RuP3) and proton reduction catalyst (NiP) used in this study. Chloride (RuP3) and bromide (RuP, NiP) counter-ions are omitted for clarity.



Fig. 2 (a) Supramolecular dye-catalyst assembly on photocathode: layer-by-layer deposition of RuP3, Zr^{4+} and NiP on p-type NiO photocathode (see text for details). (b) Energy diagram of the NiO photocathode assembly showing the proposed electron transfer mechanisms (reductive quenching) as black solid arrows and possible recombination pathways as grey dashed arrows between p-NiO, RuP3 and NiP.

moiety, which coordinates to the axial coordination sphere of the cobaloxime.^{11c-e} Axial pyridine units coordinated to cobaloximes have been shown to be inherently labile during catalytic turnover,^{5b,10b,16} and therefore H_2 evolution catalysts with a stable ligand framework are needed.

Nickel bis(diphosphine) type catalysts, $[Ni(P_2N_2)_2]^{2+}$, are attractive proton reduction catalysts as they operate in water,86,17 and display higher activity than cobaloximes in photocatalytic H_2 production.^{17*a*,18} The $[Ni(P_2N_2)_2]^{2+}$ complex also provides a stable ligand framework with no coordinating moieties becoming labile during the catalytic cycle,19 and is therefore less susceptible to catalyst dissociation from a surface due to ligand dissociation.20 [Ni(P2N2)2]2+ catalysts have previously been shown to retain high electrocatalytic activity for H₂ generation from water when immobilised on multi-walled carbon nanotubes (CNTs) via covalent linking²⁰ or π - π interactions of pyrene moieties,²¹ and when immobilised via phosphonate groups on mesostructured TiO₂ electrodes.²² The phosphonated catalyst, NiP (Fig. 1), was also used as catalyst on TiO₂ nanoparticles sensitised with a phosphonated ruthenium-based dye (RuP, Fig. 1) in photocatalytic H₂ generation with a SED.^{17a} A $[Ni(P_2N_2)_2]^{2+}$ and a $[Ni(PNP)_2]^{2+}$ type catalyst have previously been immobilised on p-Si,9c,23 but photocatalytic H2 generation was only shown for the latter assembly in acetonitrile with trifluoroacetic acid as proton source. Thus, previous work on H₂ generation with $[Ni(P_2N_2)_2]^{2+}$ catalysts relied on the use of a SED, an applied electrochemical overpotential or nonaqueous conditions to generate H₂.

In this study, PEC H₂ evolution was investigated on a p-type NiO photocathode sensitised with a hexaphosphonated ruthenium tris(bipyridine) based dye (RuP3, Fig. 1)24 and NiP. A rational and simple procedure of sequential immersion of NiO films into solutions of RuP3, ZrOCl₂ and NiP was employed to produce electrodes of the type NiO|RuP3-Zr⁴⁺-NiP (Fig. 2),²⁵ where the catalyst is spatially separated from the semiconductor electrode to reduce inefficiencies from charge-recombination.13 Our study shows that increasing the distance of the catalyst from the NiO surface results in substantially enhanced PEC performance in terms of photocurrent and stability when compared to NiO|RuP3-NiP, where the dye and catalyst are coimmobilised on NiO. We demonstrate a dye-sensitised NiO hybrid electrode with an adsorbed Ni catalyst, which has the potential to store solar energy in the bond of H₂ without the decomposition of valuable sacrificial agents or an applied overpotential. Rational layer-by-layer assembly of dye and catalyst on a semiconductor electrode is therefore established as a route to produce functional PEC H₂ production systems.

Results and discussion

Assembly and pre-catalysis characterisation

Mesoporous NiO was grown on tin-doped indium oxide (ITO)coated glass electrodes by a previously reported hydrothermal method²⁶ from a solution containing Ni(NO₃)₂·6H₂O and hexamethylenetetramine (0.25 M each). NiO electrodes were sensitised by immersion in a **RuP3** solution (1 mM in H₂O) overnight to give NiO|**RuP3** for PEC experiments.

View Article Online Chemical Science

Immobilisation of monolayers of molecular compounds via phosphonic acids on metal oxide surfaces is a well-established tool for surface modification.25a NiP was immobilised on the NiO **RuP3** photocathodes in a layered assembly using Zr⁴⁺ to link the phosphonates of dye and catalyst (Fig. 2; see below for more details). Zr⁴⁺ ions bind strongly to phosphonic acid moieties and were previously used for creating multi-layered Zr⁴⁺-phosphonate structures.^{25,27} Zr⁴⁺ was bound by dipping NiO|RuP3 electrodes into a solution of ZrOCl₂ (5 mM in EtOH/ H_2O , 60/40 v/v) for 2 h, rinsing with H_2O and EtOH and drying under a stream of N₂. The NiO|RuP3-Zr⁴⁺ electrodes were subsequently submerged in a solution of NiP (0.5 mM in MeOH) for at least 2 h to obtain the supramolecular NiO|RuP3-Zr⁴⁺-NiP electrode assembly with one layer of dye and one layer of catalyst linked by Zr⁴⁺. All immobilisation steps were carried out at room temperature.

In previously reported homogeneous, SED-promoted photocatalytic H₂ generation systems, the ratio between the dye and the catalyst was found to strongly influence the overall performance.17a,28 We have therefore varied the ratio of co-immobilised RuP3 and NiP on the p-NiO photocathodes. The layer-bylayer deposition approach allowed the RuP3 and NiP loading on the metal oxide surface to be controlled more precisely, creating Zr⁴⁺-linked dye/catalyst layers by repeated immobilisation cycles.^{25c} Repeated deposition of Zr⁴⁺ and either RuP3 dye or NiP catalyst gave electrodes of the structure NiO|(RuP3-Zr⁴⁺)₂-NiP (containing two layers of RuP3-Zr⁴⁺) or NiO|RuP3-(Zr⁴⁺-NiP)₂ (containing two layers of Zr⁴⁺-NiP). For control experiments, NiO|RuP3 electrodes were submerged directly in NiP solution without prior immobilisation of Zr⁴⁺ ions, and the so-obtained NiO RuP3-NiP electrodes were also studied. Additionally, RuP3 was replaced with the diphosphonated dye RuP (Fig. 1), which only allows binding to NiO and does not offer any phosphonic acid moieties to generate Zr⁴⁺-linked phosphonate networks.

The photocurrent response of NiO|RuP3 electrodes with different NiO film thickness was recorded in a PEC experiment in aqueous electrolyte solution (0.1 M Na₂SO₄, pH 3) in the presence of the SEA 4,4'-dithiodipyridine (DTDP, 1 mM; Fig. 3 and S1[†]) at room temperature. DTDP is reduced in two irreversible steps, with the first reduction occurring at $E_{\rm p} = -0.06$ V vs. the reversible hydrogen electrode (RHE). Thickness, morphology and crystallinity of the NiO films was studied by varying the reaction conditions (see Table S1 and Fig. S2 and S3† for powder X-ray diffraction pattern and scanning electron microscopy images). The optimised films have an average pore size (measured as distance between sheets) of 290 \pm 81 nm and a film thickness of 2 μ m (Fig. 3). The flatband potential of this NiO electrode was determined via electrochemical impedance spectroscopy at 0.75 V vs. RHE from Mott-Schottky analysis (Fig. S4[†]) and shows Nernstian pH dependence (one electron/ one proton couple) in aqueous electrolyte solution, which is in agreement with previous reports on NiO electrodes.29

The photocurrent response of NiO|**RuP3** and the loading capacity for **RuP3** on NiO films with different film thickness was studied by PEC methods and desorption of the attached dye with 0.1 M NaOH and monitoring the UV-vis absorption at λ = 295 nm in solution (Table S1†). The dye loading capacity

increased as expected with increasing film thickness, but the highest photocurrent density was achieved with a 2 μ m thick NiO film, despite the higher dye loadings for thicker films (Fig. 3, Table S1†). This observation is consistent with the known limitation of hole mobility and lifetime in NiO,³⁰ which suggests that the photocurrent generated with **RuP3**-sensitised NiO photocathodes is a balance between limiting charge transport in thick films and dye loading on thin films.

We subsequently investigated the interface between molecular components and the p-type NiO surface of the NiO|**RuP3**– Zr⁴⁺–**NiP** electrodes by UV-vis (Fig. S5†), attenuated total reflection infrared (ATR-IR; Fig. S6†), X-ray photoelectron (XPS; Fig. S7†) and inductively coupled plasma-optical emission spectroscopies (ICP-OES). The UV-vis spectrum of a bare NiO thin film shows the typical strong absorption at $\lambda < 380$ nm, and also a broad indirect transition at $\lambda < 550$ nm.²⁹ All **RuP3**-sensitised NiO electrodes exhibit the typical MLCT absorption band for Ru(bpy)₃-based dyes around $\lambda = 465$ nm and strong π - π * absorption in the UV region.²⁴ When **NiP** is present on the electrodes a small shoulder at $\lambda = 520$ nm could be observed, which is typical for the d–d transition in **NiP** as also observed in solution spectra (Fig. S5†).

The ATR-IR spectra of the NiO|**RuP3** electrodes at $\nu = 800$ to 1250 cm⁻¹ in the presence and absence of Zr⁴⁺ and **NiP** are shown in Fig. S6.† This region is characteristic for P=O and P–O–R vibrations, which are also observed in the spectra of powdered **RuP3**, **RuP** and **NiP**.³¹ NiO|**RuP3** electrodes show a broad band at $\nu \sim 1100$ cm⁻¹ attributed to P=O vibrations in **RuP3**, which is absent in a bare NiO film. In a NiO|**RuP3**–Zr⁴⁺ electrode, a small additional IR band at $\nu \sim 983$ cm⁻¹ appears when compared to NiO|**RuP3**, and the signal increases and shifts to slightly higher wavenumbers for NiO|**RuP3**–Zr⁴⁺–**NiP** ($\nu \sim 986$ cm⁻¹) and NiO|**RuP3**–(Zr⁴⁺–**NiP**)₂ ($\nu \sim 992$ cm⁻¹). This shift is in good accordance with previously reported values for Zr⁴⁺ bound to phosphonic acid groups.^{25b}



Fig. 3 Photocurrent response of NiO|RuP3 under visible light irradiation ($\lambda > 400$ nm, AM1.5G filter, 100 mW cm⁻²) after 100 s at $E_{appl} =$ 0.3 V vs. RHE in Na₂SO₄ (0.1 M, pH 3) in the presence of 4,4'-dithiodipyridine (DTDP, 1 mM) as SEA and dye loading (no applied potential; cm⁻² refers to the geometrical surface area of the NiO electrode) with varying thicknesses of the NiO films. Inset: SEM image of optimised p-type NiO electrode (2 µm film thickness).

XPS analysis was used to further characterise the modified NiO surface, and the presence of Ru and Zr on NiO after each layering step was confirmed (Fig. S7[†]). The signal for NiP could not be distinguished from the NiO background signal. Instead, mesoporous indium-tin oxide (ITO, 3.3 µm thickness) electrodes were prepared according to a previously reported procedure³² and used here as a scaffold. The XPS signals of ITO RuP3-NiP, ITO|RuP3-Zr⁴⁺ and ITO|RuP3-Zr⁴⁺-NiP electrodes (prepared analogously to the related NiO hybrids) were analysed. In the presence of NiP, peaks at 855.0 and 872.5 eV were observed and were assigned to the Ni $2p_{3/2}$ and Ni $2p_{1/2}$ of the molecular NiP, respectively.^{17c,33} The P 2p signal for ITO|RuP3-NiP and ITO|RuP3-Zr⁴⁺-NiP electrodes is broad (133.0-131.0 eV) and consists of signals for the phosphonic acid bound to ITO³⁴ and for the phosphine ligand.³³ In contrast, ITO|RuP3-Zr⁴⁺ showed only a sharp XPS peak at 133.5 eV, which is assigned to the -PO(OH)₂ groups.³⁴ As the **RuP3**-Zr⁴⁺-NiP was assembled in identical manner on ITO and NiO, the presence of intact NiP on ITO supports its integrity on NiO prior to catalysis.

Finally, we quantified the immobilised dye and catalyst on NiO by UV-vis spectroscopy and ICP-OES analysis after desorption in aqueous NaOH (0.1 M). The overlap of RuP3 and NiP in the electronic absorption spectra prevented the simultaneous determination of dye and catalyst loading on the electrodes and ICP-OES measurements were used instead. Quantification of NiP on NiO was challenging due to the high nickel background from the electrode. Mesoporous ITO electrodes were used again as a scaffold and analysis of ITO|RuP3, ITO|RuP3-NiP, ITO| RuP3-Zr⁴⁺ and ITO|RuP3-Zr⁴⁺-NiP electrodes was carried out. The quantity of NiP on NiO was estimated from the Ru : Ni ratio found on the ITO electrodes (Table 1). The ICP-OES data for the amount of RuP3 immobilised on bare NiO (10.7 \pm 0.3 nmol cm^{-2}) correlates well with quantification by UV-vis spectroscopy after dye desorption (10.8 \pm 0.8 nmol cm⁻²). Analysis of ITO **RuP3–NiP** electrodes revealed a Ru : Ni ratio of 2.6 ± 0.04 : 1 and this ratio decreases only slightly to $\sim 2.2 \pm 1.5$: 1 on ITO RuP3-Zr⁴⁺-NiP, indicating that a similar amount of NiP is immobilised in the presence and absence of Zr⁴⁺. This ratio allows us to estimate a NiP loading of 4.98 ± 3.54 nmol cm⁻² for NiO|**RuP3**-Zr⁴⁺-**NiP**, which is comparable to the loading of a cobaloxime catalyst on CdSe-sensitised NiO (${\sim}3$ nmol cm $^{-2}$ for a 5.6 μm thick NiO film).11b

Photoelectrochemical experiments

The photocathodes were studied in PEC experiments in aqueous electrolyte solution (0.1 M Na₂SO₄, pH 3) in a threeelectrode setup with a Ag/AgCl reference and a Pt counter electrode at room temperature. Linear sweep voltammetry (LSV) scans were recorded between E = +0.6 V and -0.15 V vs. RHE at a scan rate of 5 mV s⁻¹ in the dark and under chopped and UV filtered irradiation with simulated solar light ($\lambda > 400$ nm, 100 mW cm⁻², AM1.5G; Fig. 4a). All NiO electrodes (irrespective of being loaded with molecules or not) displayed a partially reversible oxidation wave between E = 0.42 and 0.48 V vs. RHE, which is assigned to the Ni³⁺/Ni²⁺ redox couple (Fig. S8⁺).^{29,30b} In the absence of dye, only marginal photocurrent densities (reported per geometrical surface area) were observed in the studied potential range. Transient and small cathodic photocurrents were observed upon irradiating NiO|**RuP3** ($|j| \sim 1.4 \mu$ A cm⁻² at 0.5 V vs. RHE) and NiO|**RuP3–**Zr⁴⁺ ($|j| \sim 1.2 \mu A \text{ cm}^{-2}$ at 0.5 V vs. RHE) electrodes, indicating hole injection of the excited dye, RuP3*, into the valence band of NiO (Fig. 2, for details see Mechanistic interpretation below). Quenching of RuP3* by NiO results in the formation of a reduced dye, RuP3⁻, which is then likely to undergo rapid charge recombination with the holes generated in NiO in absence of a suitable electron acceptor.13,15b A comparable photoresponse was observed between NiO|RuP3 and NiO|RuP3-NiP, indicating that direct binding of the NiP to NiO results in an unproductive assembly with negligible electron accumulation at NiP. When a NiO|RuP3-Zr⁴⁺-NiP electrode was used, however, an initial photocurrent density up to $|j| \sim 5.56 \ \mu A \ cm^{-2}$ was achieved under the same experimental conditions (Fig. 4a).

Subsequently, the importance of the phosphonic acid moieties in the assembly of functional electrodes was investigated (Fig. S9†). When the diphosphonated dye **RuP** (Fig. 1)³⁵ is immobilised on NiO instead of **RuP3**, no phosphonic acid binding sites are available for Zr⁴⁺. A comparable photocurrent was observed for a NiO|**RuP**–Zr⁴⁺–**NiP** and NiO|**RuP–NiP**

Louding concernations are reported for the geometrical burner area of the clock odes				
Composition	RuP3 /nmol cm ^{-2}	NiP /nmol cm ⁻²	$ j /\mu A \text{ cm}^{-2(a)}$	$ j /\mu A \text{ cm}^{-2(b)}$
NiO RuP3	10.7 ± 0.3	_	0.51	3.0
NiO RuP3-NiP	9.4 ± 1.6	$3.57\pm0.61^{(\mathrm{c})}$	0.94	n.d. ^(d)
NiO RuP3 -Zr ⁴⁺	6.3 ± 2.2	—	0.76	7.62
NiO RuP3-Zr ⁴⁺ -NiP	6.3 ± 3.1	$4.98 \pm 3.54^{\rm (c)}$	6.40	14.0
$NiO RuP3-(Zr^{4+}-NiP)_2$	n.d.	n.d.	8.82	n.d.
NiO (RuP3 -Zr ⁴⁺) ₂ -NiP	n.d.	n.d.	2.18	n.d.
ITO RuP3-NiP	37.6 ± 0.2	14.3 ± 0.2	_	—
ITO RuP3-Zr ⁴⁺	53.2 ± 20.5	_	_	—
ITO RuP3-Zr ⁴⁺ -NiP	41.3 ± 20.3	19.2 ± 9.9	—	—

Table 1 Quantification of **RuP3** and **NiP** on the NiO electrodes (determined by ICP-OES) and photocurrents (AM1.5G filter, 100 mW cm⁻² and λ > 400 nm) of the respective electrodes after 100 s CPPE at $E_{appl} = 0.3$ V vs. RHE at room temperature. **RuP3** and **NiP** loading on ITO is also shown. Loading concentrations are reported for the geometrical surface area of the electrodes^a

^a Measured in ^(a)the absence and ^(b)presence of DTDP as SEA. ^(c)Calculated value from RuP3 : NiP ratio on ITO. ^(d)Not determined.



Fig. 4 (a) LSV scans of NiO electrodes at a scan rate of 5 mV s⁻¹ under chopped light irradiation (λ > 400 nm, AM1.5G filter, 100 mW cm⁻²). (b) Chronoamperometry of NiO working electrodes under chopped light irradiation (10 s on/off cycles) at $E_{appl} = 0.3$ V vs. RHE. All experiments were performed in a 3-electrode setup with a Ag/AgCl/KCl_(sat.) reference and a Pt mesh counter electrode under N₂ in a custom-made one-compartment PEC cell at room temperature.

electrode, which confirms that Zr^{4+} binding to the electrode assembly occurs *via* the free phosphonic acid groups of **RuP3** and not *via* intercalation in the mesoporous NiO scaffold or precipitation as ZrO_2 during the deposition procedure. The results from LSV confirm that the presence of **RuP3**, **NiP** and Zr^{4+} in the layered assembly is essential for the functional hybrid photoelectrode.

Chronoamperograms for all photoelectrodes were recorded at an applied potential, E_{appl} , of 0.3 V vs. RHE (Table 1 and Fig. 4b) and at $E_{appl} = 0.5$ V vs. RHE (Fig. S10†) under chopped light irradiation and confirmed the trends observed by LSV. Cathodic photocurrents for NiO|**RuP3** ($|j| \sim 0.5 \ \mu A \ cm^{-2}$) and for NiO|**RuP3**-Zr⁴⁺ ($|j| \sim 0.76 \ \mu A \ cm^{-2}$) were small at $E_{appl} = 0.3$ V vs. RHE. The photocurrent of a NiO|**RuP3**-NiP electrode (|j| =0.94 $\mu A \ cm^{-2}$) at $E_{appl} = 0.3$ V vs. RHE was more than six times smaller than the photocurrent achieved with a NiO|**RuP3**-Zr⁴⁺-**NiP** electrode (initial photocurrent $|j| = 9.97 \ \mu A \ cm^{-2}$ stabilised to 6.40 $\mu A \ cm^{-2}$ after 100 s).

The photoelectrodes were also investigated in the presence of DTDP as SEA. A UV-vis spectrum of **NiP** in solution in the presence and absence of DTDP (1 mM) shows no differences, confirming the stability of the catalyst in the presence of DTDP (Fig. S11†). As expected, the presence of a soluble SEA in the electrolyte solution enhanced the photocurrents observed for the NiO|**RuP3** ($|j| = 3.0 \ \mu A \ cm^{-2}$) and NiO|**RuP3**-Zr⁴⁺ electrodes ($|j| = 7.6 \ \mu A \ cm^{-2}$) at $E_{appl} = 0.3 \ V \ \nu s$. RHE (Fig. S12†). A significant increase in photocurrent was also found for a NiO|**RuP3**-Zr⁴⁺-**NiP** electrode in the presence of DTDP in solution ($|j| = 14.0 \ \mu A \ cm^{-2}$) compared to a SEA-free system ($|j| = 6.4 \ \mu A \ cm^{-2}$). This suggests that surface-bound **NiP** is efficiently reduced by the generated photoelectrons and electron transfer from the reduced catalyst to the dissolved SEA in the electrolyte solution is faster than competing charge recombination. An increased photocurrent in the presence of DTDP suggests that the reduction of the SEA is faster than **NiP**-promoted catalysis.

The effect of the ratio of dye and catalyst was also studied by preparing electrodes with either two layers of dye, NiO|(RuP3- $Zr^{4+})_2$ -NiP, or two layers of catalyst, NiO|RuP3-(Zr^{4+} -NiP)₂. The photocurrent generated by a NiO|(RuP3-Zr⁴⁺)₂-NiP electrode after 100 s chronoamperometry at $E_{appl} = 0.3$ V vs. RHE (|j| =2.18 μ A cm⁻²) was almost three times lower than the photocurrent of a NiO|**RuP3**–Zr⁴⁺–**NiP** electrode (Table 1). In contrast, approximately 40% increase in photocurrent was observed for a NiO|**RuP3**–(Zr⁴⁺–**NiP**)₂ electrode ($|j| = 8.82 \mu \text{A cm}^{-2}$). These experiments confirmed that there is a significant dependence of the number of layers on the photocurrent response and show that transient photocurrents generated by dye-sensitised NiO electrodes are dependent on the strategy used to co-immobilise dye and catalyst on the surface. This layer-by-layer approach has previously been successful for dye-sensitised photoanodes for water oxidation,36 but has not yet been explored for fuel-forming photocathodes.

The formation of H₂ at the NiO |RuP3-Zr⁴⁺-NiP electrode was then studied by controlled potential photoelectrolysis (CPPE; Fig. 5). Irradiation of the NiO|RuP3-Zr⁴⁺-NiP and NiO|RuP3- $(Zr^{4+}-NiP)_2$ electrodes at $E_{appl} = 0.3$ V vs. RHE in a twocompartment PEC cell generated 6.11 \pm 0.68 and 6.8 \pm 0.9 nmol H_2 in the headspace (analysed by gas chromatography with N_2 carrier gas) with a faradaic efficiency of 8.6 \pm 2.3% and 10.1 \pm 1.8%, respectively (Table S2[†]). Increasing the light intensity to 200 mW cm⁻² or using an $E_{appl} = 0.5$ V vs. RHE did not alter the H₂ production rate nor improve the faradaic efficiency for NiO **RuP3–Zr⁴⁺–NiP.** In the absence of **NiP** or in the dark, no H_2 generation was observed. NiO|RuP3-NiP and NiO|(RuP3- $Zr^{4+})_2$ -NiP electrodes produced only traces of H₂ below the limit of quantification (LOQ) of the thermal conductivity detector. The low activity of the NiO|RuP3-Zr⁴⁺-NiP electrode is likely due to inefficient charge transfer dynamics at the NiO|RuP3 interface and between reduced NiP and oxidised RuP3 or NiO (Fig. 2b). Nevertheless, confirmation of H_2 evolution at the photocathode is an important step towards the goal of implementing dye-sensitised NiO photocathodes in full water splitting PEC cells.11c,13

Post-catalysis characterisation

The electrode stability was further examined by ICP-OES analysis of the Ru content in both electrolyte solution and on the electrodes following 2 h CPPE at $E_{appl} = 0.3 \text{ V} vs.$ RHE. For NiO| **RuP3**-Zr⁴⁺-**NiP** a substantial amount of the initially loaded Ru ($6.3 \pm 3.1 \text{ nmol cm}^{-2}$) was recovered from the used electrodes (3.4-7.4 nmol Ru cm⁻²) upon desorption in aqueous NaOH (0.1M). Almost no Ru leaked into the electrolyte solution of the

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.



Fig. 5 CPPE of a NiO|RuP3-Zr⁴⁺-NiP photoelectrode (1 cm²) at E_{appl} = 0.3 V vs. RHE in Na₂SO₄ (0.5 M, pH 3) at room temperature. Electrolysis was performed in a 2-compartment PEC cell with the working and counter compartment separated by a Nafion membrane. The working electrode was held in the dark for 1 h, followed by irradiation for 2 h using a solar light simulator (100 mW cm⁻², AM1.5G filter, $\lambda >$ 400 nm).

working or counter compartments (<0.2 nmol total Ru content). The opposite was observed for the NiO|**RuP3-NiP** electrodes after 2 h CPPE and 4.9–5.3 nmol total Ru content were found in the electrolyte solution of the working compartment and very little Ru (0.39–0.74 nmol cm⁻²) was recovered from the used working electrode. The Zr^{4+} interlayer might contribute to stabilising **RuP3** on the surface of NiO electrodes under CPPE conditions. The stability of the NiO|**RuP3**– Zr^{4+} –**NiP** working electrodes against material degradation was also confirmed by the lack of observable changes in the cyclic voltammograms before and after CPPE (Fig. S13†) and a significant alteration for NiO|**RuP3**– Zr^{4+} electrodes after CPPE at 0 V *vs.* RHE (Fig. S14†), indicating material instability of the latter.

The XPS spectra of a NiO|**RuP3**–Zr⁴⁺–**NiP** electrode were recorded and confirmed the presence of both **RuP3** (281 eV, Ru $3d_{5/2}$) and Zr⁴⁺ (182.6 and 185 eV for Zr $3d_{5/2}$ and Zr $3d_{3/2}$, respectively) before and after 2 h CPPE at $E_{appl} = 0.3$ V νs . RHE (Fig. S7†). No new peaks in the Ru $3d_{5/2}$ region were observed after CPPE to indicate formation of Ru/RuO_x particles. The presence and integrity of **NiP** on the NiO|**RuP3**–Zr⁴⁺–**NiP** electrode after CPPE could not unambiguously be confirmed by XPS due to the presence of the NiO. However, the stability of **NiP** on the electrode surface of a mesostructured TiO₂ electrode under reducing conditions ($E_{appl} = -0.25$ V νs . RHE) in the dark in otherwise identical aqueous electrolyte solution (0.1 M Na₂SO₄, pH 3) has previously been confirmed.²²

Mechanistic interpretation

Visible light irradiation of **RuP3** generates **RuP3***, which can in principle be quenched by two different mechanisms in the NiO| **RuP3**-Zr⁴⁺-**NiP** assembly: (a) oxidative quenching of **RuP3*** (*E*(**RuP3**⁺/**RuP3***) ~ -0.78 V *vs.* the normal hydrogen electrode (NHE), HOMO-LUMO gap *E*_{H-L}(**RuP3**) = 2.19 eV, $\lambda_{em} = 567$ nm, Fig. S15[†])³⁷ by **NiP**, followed by hole injection from the oxidised **RuP3*** (*E*(**RuP3**⁺/**RuP3**) ~ 1.41 V *vs.* NHE, Fig. S16[†]) into NiO

 $(E_{\rm VB}(\rm NiO) = 0.57 V \nu s. \text{ NHE at pH 3});^{38} \text{ or (b) reductive quenching}$ of RuP3* by fast electron transfer from NiO into the HOMO of the dye to form the reduced species $RuP3^{-}$ ($E(RuP3^{*}/RuP3^{-}) \sim$ 0.80 V vs. NHE, Fig. 2b).39 RuP3⁻ has a sufficiently negative ground state reduction potential ($E(RuP3/RuP3^{-}) \sim -1.29 \text{ V} \nu s.$ NHE)³⁹ to provide driving force for reduction of **NiP** ($E(Ni^{II/I}) =$ -0.35 V vs. NHE at pH 4.5).17a The reductive quenching mechanism for the NiO|**RuP3**–Zr⁴⁺–**NiP** assembly is much more likely since hole injection from a dye into NiO happens on very fast timescales of hundreds of femto- to picoseconds.13,15a Additionally, spectroscopic studies of a homogenous RuP-NiP system for photocatalytic H₂ generation have shown previously that RuP* does not directly inject electrons into NiP in solution or when both molecules are anchored on ZrO2 as a non-injecting matrix. Reductive quenching by a SED or p-NiO yields RuP-, which was shown to efficiently reduce NiP.17a Reductive quenching of the NiO|**RuP3**-Zr⁴⁺-**NiP** system would provide the catalyst with an overpotential of \sim 0.9 V (Fig. 2b).

Our results also suggest an important contribution of the Zr⁴⁺ interlayer to the efficiency of electron transfer away from the electrode surface to the associated catalyst. As Zr⁴⁺ is inert against reduction, it is unlikely that the Zr⁴⁺ coordinated to **RuP3** and **NiP** is acting as an electron relay similar to TiO_2 in H_2 evolving dye-TiO2-catalyst suspension systems.18 It is more likely that the Zr⁴⁺ layer prevents **NiP** from binding directly on the NiO surface in close proximity to NiO|RuP3, and that spatial separation of the reduced catalyst from the generated holes in NiO is beneficial to avoid charge recombination which is fast when dye and catalyst are in close proximity.13 Reports on the catalytic activity of photoanodes for water oxidation showed that stability was enhanced when the catalyst was spatially separated from the dye-sensitised electrode.25d,36a,40 Spectroscopic studies of a TiO₂|**RuP3**–Zr⁴⁺–catalyst photoanode demonstrated that electron back transfer was slowed down significantly compared to a TiO2 catalyst electrode,25b which was assigned to increased spatial separation. Similar effects were also found for electron transfer between photoexcited TiO2 and cobaloxime catalysts with different linker lengths.41 These experiments show the high potential of using rationally designed dye-catalyst assemblies on photocathodes.

Conclusions

A dye-sensitised photocathode with a co-immobilised nickel catalyst for light driven H_2 generation in water has been reported. Co-deposition of the Ru dye **RuP3** and Ni catalyst **NiP** on the p-type semiconductor NiO in a supramolecular assembly of Zr^{4+} -phosphonates provided us with a tool to control spatial arrangement of individual species without the need for elaborate chemical synthesis of dye–linker–catalyst dyads. This layer-by-layer approach keeps the catalyst in close proximity to the dye, but increases the distance to the semiconductor electrode. Our PEC experiments confirm that directed forward electron transfer from the excited dye to the catalyst is efficient and recombination kinetics are slowed down. The catalyst was therefore able to turn over and the hybrid electrode able to photo-generate H_2 at an electrochemical underpotential,

thereby demonstrating the potential of this system to store light in the chemical bonds of H_2 . Layer-by-layer assembly of dye and catalyst is therefore established as a novel strategy to produce molecule-based photocathodes for H_2 evolution.

The efficiency of the presented system can be improved in the future by optimising the NiO|dye interface such as developing phosphonated push-pull dyes optimised for p-NiO,¹² and fine-tuning of the H₂ evolution catalyst. Further work will also include the synthesis and investigation of dyes, which are better suited to inject holes into the NiO valence band. Optimised molecule-containing photocathodes might ultimately become an attractive component for use in PEC cells for full water splitting.^{114,22}

Experimental section

Materials and methods

NiP,^{17a} RuP,³⁵ and RuP3 ²⁴ (Fig. 1) were synthesised and characterised as previously reported. Chemicals for analytical measurements were purchased in the highest available purity and used without further purification. Ni(NO₃)₂·6H₂O (Fisher Scientific, extra pure, 250 g) and hexamethylenetetramine (Sigma Aldrich, ReagentPlus, 99%) were used for the preparation of NiO electrodes. ITO nanopowder (Sigma Aldrich, particle size below 50 nm) was used for the preparation of mesostructured ITO electrodes. All electrochemical and analytical measurements were performed using Milli-Q[®] H₂O ($R > 18 \text{ M}\Omega$ cm). ITO-covered glass sheets (Vision Tek Systems Ltd., $R = 12 \Omega$ cm⁻², thickness 1.1 mm) were cut into 3 × 1 cm² slides for preparation of working electrodes.

Physical characterisation

An FEI Phillips XL30 SFEG SEM was used in the Electron Microscopy Suite in the Cavendish Laboratory, University of Cambridge. Powder X-ray diffraction (XRD) analysis was performed using a PANalytical BV X'Pert Pro X-ray diffractometer in the Department of Chemistry, University of Cambridge. XPS analysis was performed at the NEXUS XPS facility at Newcastle University. XPS spectra were calibrated to the C 1s signal at 284.8 eV. Quantification of Ni and Ru on the electrodes via ICP-OES (PerkinElmer Optima 2100 DV spectrometer) was carried out at the Department of Geography, University of Cambridge. High-resolution ATR-IR spectra were recorded on a Thermo Scientific Nicolet iS 50 FT-IR spectrometer with an ATR unit. UVvis absorption spectra of electrodes were recorded in transmission mode in air, and UV-vis solution spectra were recorded in a quartz glass cuvette (1 cm path length) with a Varian Cary 50 UV-vis spectrophotometer. Fluorescence emission spectra of RuP3 in Na₂SO₄ (0.1 M, pH 3) were measured with an Edinburgh Instruments FS5 spectrofluorometer.

Electrochemical impedance spectroscopy

Electrochemical impedance spectroscopy (EIS) was performed on an IviumStat potentiostat in the frequency range of 100 kHz to 0.1 Hz in aqueous Na_2SO_4 solution (0.1 M, pH 3, 5 and 7). An equivalent circuit (inset Fig. S4[†]) consisting of electrolyte

solution resistance (R_s) , constant phase element (CPE), and interfacial charge transfer resistance (R_{CT}) was fitted to Nyquist plots obtained at different potentials in ZView® (Scribner Associates Inc.) to retrieve Csc values required to form a Mott-Mott-Schottky Schottky plot. The equation, $\frac{1}{C_{\rm SC}}^2 = \frac{2}{\varepsilon \varepsilon_0 A^2 e N} \left(V - V_{\rm fb} - \frac{k_{\rm B} T}{e} \right), \text{ where } C_{\rm SC} \text{ is the interfacial}$ capacitance, A is the interfacial area, N the density of acceptors, V the applied potential, $V_{\rm fb}$ the flatband potential, $k_{\rm B}$ the Boltzmann constant, T the absolute temperature, and e the electronic charge, was used to calculate the flatband potential of NiO. $1/C_{SC}^{2}$ plotted against applied potential results in a straight line with the intercept being equal to $V_{\rm fb} + k_{\rm B}T/e$. The negative slope is indicative of the p-type character of the NiO

Preparation of nanostructured NiO electrodes^{26b}

electrodes.

ITO covered glass slides $(3 \times 1 \text{ cm}^2)$ were cleaned by successive sonication in ethanol and acetone for 10 min, respectively. After drying in air, the conductive surface was confined to *ca.* $1 \times$ 1.5 cm² with electrical tape. The ITO glass slides were placed at approximately 45° with the conductive side facing down into separate vials and a solution of Ni(NiO₃)₂·6H₂O and hexamethylenetetramine (250 mM each, 6 mL) was added to each vial. For hydrothermal growth of the films, the vials were placed into an oven (Thermo Scientific Heratherm) for 15, 30, 45 or 60 min at 90 °C and the reaction was stopped by the immediate addition of distilled water. The slides were rinsed with water, dried in air and the tape removed before the slides were annealed in a furnace (Carbolite) at 450 °C in air for 30 min (heating rate 20 °C min⁻¹), and left to cool to room temperature in the furnace chamber.

Preparation of mesostructured ITO electrodes³²

ITO covered glass slides $(3 \times 1 \text{ cm}^2)$ were cleaned by heating them in a mixture of NH_{3(conc.)}/H₂O/H₂O_{2(30%)} (1 : 5 : 1) at 70 °C for 30 min. The slides were rinsed with distilled water and dried in an oven at 180 °C for 1 h. The surface of the conductive side was confined with Scotch tape to circular 0.28 cm². ITO nanopowder (20% w/w) was sonicated in EtOH (5 M acetic acid) for 1 hour and then doctor bladed on the ITO support. After drying in air, the tape was removed and the electrodes were annealed in a furnace (Carbolite) at 400 °C in air for 1 h (4 °C min⁻¹ heating rate) and left to cool to room temperature in the oven chamber.

Assembly of molecular photocathodes

The layer-by-layer deposition of dye (**RuP3** or **RuP**) and catalyst (**NiP**) was achieved by sequential immersion of the electrodes in solutions containing the molecular compounds at room temperature. NiO electrodes were submerged in solutions of **RuP3** or **RuP** (1 mM in H₂O, overnight, washed with H₂O and EtOH), $ZrOCl_2$ (5 mM in EtOH (60% v/v in H₂O), 2 h, washed with H₂O and EtOH) and **NiP** (0.5 mM in MeOH, 2–3 h, washed with MeOH) to build up the supramolecular layered assemblies.

Chemical Science

The electrodes were dried in a stream of N_2 after each immobilisation step. Multiple (*n*) catalyst and dye layers were assembled by repeating the immobilisation cycles *n* times. **RuP3** sensitised mesostructured ITO electrodes (ITO|**RuP3**) for controls were prepared according to the same procedure. The electrodes were stored in the dark prior use.

Quantification of immobilised compounds on NiO

(A) Quantification of RuP3 by UV-vis spectrophotometry. A NiO|RuP3 electrode was immersed in aqueous NaOH (0.1 M, 1.0 mL) for 5 min to desorb the phosphonated species. The absorbance of the resulting solution at $\lambda = 467$ and 297 nm was used to determine the amount of **RuP3** detached from the surface (assuming quantitative detachment of phosphonic acids in pH 13 solution).

(B) Quantification of Ru, and Ni *via* ICP-OES. Surfacebound species were detached by immersing the electrodes in aqueous NaOH (0.1 M, 1.0 mL) for 5 min. The electrodes were rinsed with 10 mL H₂O and then HNO₃ (2% v/v) was added to a final volume of 25 mL. Samples were prepared and analysed from at least two individual electrodes for each condition and the averages are reported. Errors are given as maximum deviation from the average.

Determination of RuP3 oxidation potential

 $E(\mathbf{RuP3}^+/\mathbf{RuP3})$ was determined by recording a CV of **RuP3** in Na₂SO₄ (0.1 M, pH 3) with a boron doped diamond working, Ag/AgCl/KCl_(sat.) reference and Pt mesh counter electrode. The HOMO-LUMO gap $E_{\mathrm{H-L}}(\mathbf{RuP3})$ was determined as the intersection of the normalised absorption and emission spectra of **RuP3** in Na₂SO₄ (0.1 M, pH 3).²⁴ $E(\mathbf{RuP3}^+/\mathbf{RuP3}^*)$ was estimated by $E(\mathbf{RuP3}^+/\mathbf{RuP3}^*) = E(\mathbf{RuP3}^+/\mathbf{RuP3}) - E_{\mathrm{H-L}}(\mathbf{RuP3}).$

Photoelectrochemistry

Electrochemical measurements were performed on an Ivium CompactStat potentiostat using a three-electrode configuration in a custom-made cell with a flat borosilicate window for PEC experiments. The prepared dye-sensitised NiO slides (1 cm² geometrical surface area confined with electrical tape) were studied as working electrodes. A Pt mesh counter electrode, and a Ag/AgCl/KCl_(sat.) reference electrode were used in aqueous electrolyte solution (0.1 M Na₂SO₄, pH 3). Prior to any measurements, all solutions were purged for at least 10 min with N₂ to remove O₂. PEC experiments were performed under irradiation from the back-side of the electrodes with visible light ($\lambda > 400$ nm, UQG Optics filter) using a solar light simulator (Newport Oriel, 150 W, 100 mW cm⁻²) equipped with an AM1.5G and IR water filter.

CPPE was carried out in a custom-made 2-compartment PEC cell separated by a Nafion membrane (quartz glass window, 1.5 cm diameter). In the working compartment, 14.5 mL of electrolyte solution were used, leaving a gas headspace of 4.9 mL. In the counter compartment, 4.5 mL of electrolyte solution were used, leaving a gas headspace of 3.1 mL. Both compartments were purged prior to electrolysis with N₂ containing CH₄ (2%) as internal standard for gas chromatography

measurements. The electrolyte solution (0.5 M Na₂SO₄, pH 3) in both compartments was stirred during the experiments. The amount of H₂ in the headspace of the electrolysis cell was quantified by an Agilent 7890A Series gas chromatograph equipped with a 5 Å molecular sieve column. The GC oven temperature was kept constant at 45 °C, N₂ was used as a carrier gas at an approximate flow rate of 3 mL min⁻¹ and a thermal conductivity detector was used. In a standard experiment, the working electrode was held at the respective potential (E_{appl}) in the dark for the first h, and after confirming the absence of headspace H₂, it was exposed to visible light ($\lambda > 400$ nm, 100 or 200 mW cm⁻²) for 2 h at E_{appl} . All CPPE experiments were carried out at least three times, unless noted otherwise. The mean values of the measurements are reported along with their standard errors.^{17a}

Acknowledgements

We gratefully acknowledge financial support by the Christian Doppler Research Association (Austrian Federal Ministry of Science, Research, and Economy and the National Foundation for Research, Technology, and Development), the OMV Group (E.R. and M.A.G.), the EPSRC NanoDTC in Cambridge (EP/ L015978/1; E.R. and C.E.C.), and the World Premier International Research Center Initiative (WPI), MEXT, Japan (K.L.O.). XPS spectra were measured at the National EPSRC XPS User's Service (NEXUS) research facility at Newcastle University, UK. Thanks also to Mr Benjamin Martindale for help with the XPS data analysis and helpful discussions and Mr Chris Rolfe at the Department of Geography at the University of Cambridge for help with the ICP measurements. We appreciate the help of Ms Janina Willkomm in optimising the synthesis of NiO electrodes and Dr Julien Warnan for helpful suggestions and comments on the manuscript.

References

- S. Mathew, A. Yella, P. Gao, R. Humphry-Baker, B. F. E. Curchod, N. Ashari-Astani, I. Tavernelli, U. Rothlisberger, M. K. Nazeeruddin and M. Grätzel, *Nat. Chem.*, 2014, 6, 242–247.
- 2 (a) C.-Y. Lin, Y.-H. Lai, D. Mersch and E. Reisner, *Chem. Sci.*, 2012, 3, 3482–3487; (b) M. S. Prévot and K. Sivula, *J. Phys. Chem. C*, 2013, 117, 17879–17893.
- 3 (a) T. R. Cook, D. K. Dogutan, S. Y. Reece, Y. Surendranath, T. S. Teets and D. G. Nocera, *Chem. Rev.*, 2010, **110**, 6474– 6502; (b) M. G. Walter, E. L. Warren, J. R. McKone, S. W. Boettcher, Q. Mi, E. A. Santori and N. S. Lewis, *Chem. Rev.*, 2010, **110**, 6446–6473; (c) Y.-H. Lai, D. W. Palm and E. Reisner, *Adv. Energy Mater.*, 2015, **5**, 1501668; (d) F. F. Abdi, L. Han, A. H. M. Smets, M. Zeman, B. Dam and R. van de Krol, *Nat. Commun.*, 2013, **4**, 2195.
- 4 Z. Yu, F. Li and L. Sun, Energy Environ. Sci., 2015, 8, 760–775.
- 5 (a) M. P. Stewart, M.-H. Ho, S. Wiese, M. L. Lindstrom, C. E. Thogerson, S. Raugei, R. M. Bullock and M. L. Helm,
 - J. Am. Chem. Soc., 2013, 135, 6033–6046; (b) J. Willkomm,

N. M. Muresan and E. Reisner, *Chem. Sci.*, 2015, 6, 2727–2736.

- 6 R. Bhosale, J. Mišek, N. Sakai and S. Matile, *Chem. Soc. Rev.*, 2010, **39**, 138–149.
- 7 A. Reynal, F. Lakadamyali, M. A. Gross, E. Reisner and J. R. Durrant, *Energy Environ. Sci.*, 2013, **6**, 3291–3300.
- 8 (a) F. Lakadamyali and E. Reisner, Chem. Commun., 2011, 47, 1695–1697; (b) C. A. Caputo, M. A. Gross, V. W. Lau, C. Cavazza, B. V. Lotsch and E. Reisner, Angew. Chem., Int. Ed., 2014, 53, 11538–11542; (c) B. C. M. Martindale, G. A. M. Hutton, C. A. Caputo and E. Reisner, J. Am. Chem. Soc., 2015, 137, 6018–6025; (d) J. Willkomm, K. L. Orchard, A. Reynal, E. Pastor, J. R. Durrant and E. Reisner, Chem. Soc. Rev., 2016, 45, 9–23.
- 9 (a) B. Kumar, M. Beyler, C. P. Kubiak and S. Ott, Chem.-Eur. J., 2012, 18, 1295-1298; (b) R. N. Dominey, N. S. Lewis, J. A. Bruce, D. C. Bookbinder and M. S. Wrighton, J. Am. Chem. Soc., 1982, 104, 467-482; (c) J. Seo, R. T. Pekarek and M. J. Rose, Chem. Commun., 2015, 51, 13264-13267; (d) J. R. McKone, E. L. Warren, M. J. Bierman, S. W. Boettcher, B. S. Brunschwig, N. S. Lewis and H. B. Gray, Energy Environ. Sci., 2011, 4, 3573-3583; (e) Y.-H. Lai, H. S. Park, J. Z. Zhang, P. D. Matthews, D. S. Wright and E. Reisner, Chem.-Eur. J., 2015, 21, 3919-3923.
- 10 (a) D. Cedeno, A. Krawicz, P. Doak, M. Yu, J. B. Neaton and G. F. Moore, *J. Phys. Chem. Lett.*, 2014, 5, 3222–3226; (b) A. Krawicz, J. Yang, E. Anzenberg, J. Yano, I. D. Sharp and G. F. Moore, *J. Am. Chem. Soc.*, 2013, 135, 11861–11868.
- 11 (a) C. E. Castillo, M. Gennari, T. Stoll, J. Fortage, A. Deronzier, M.-N. Collomb, M. Sandroni, F. Légalité, E. Blart, Y. Pellegrin, C. Delacote, M. Boujtita, F. Odobel, P. Rannou and S. Sadki, *J. Phys. Chem. C*, 2015, **119**, 5806– 5818; (b) P. Meng, M. Wang, Y. Yang, S. Zhang and L. Sun, *J. Mater. Chem. A*, 2015, **3**, 18852–18859; (c) K. Fan, F. Li, L. Wang, Q. Daniel, E. Gabrielsson and L. Sun, *Phys. Chem. Chem. Phys.*, 2014, **16**, 25234–25240; (d) F. Li, K. Fan, B. Xu, E. Gabrielsson, Q. Daniel, L. Li and L. Sun, *J. Am. Chem. Soc.*, 2015, **137**, 9153–9159; (e) Z. Ji, M. He, Z. Huang, U. Ozkan and Y. Wu, *J. Am. Chem. Soc.*, 2013, **135**, 11696–11699; (f) K. A. Click, D. R. Beauchamp, Z. Huang, W. Chen and Y. Wu, *J. Am. Chem. Soc.*, 2016, **138**, 1174–1179.
- J. Massin, M. Bräutigam, N. Kaeffer, N. Queyriaux, M. J. Field, F. H. Schacher, J. Popp, M. Chavarot-Kerlidou, B. Dietzek and V. Artero, *Interface Focus*, 2015, 5, 20140083.
- 13 J. M. Gardner, M. Beyler, M. Karnahl, S. Tschierlei, S. Ott and L. Hammarström, *J. Am. Chem. Soc.*, 2012, **134**, 19322–19325.
- 14 L. Li, L. Duan, F. Wen, C. Li, M. Wang, A. Hagfeldt and L. Sun, *Chem. Commun.*, 2012, **48**, 988–990.
- 15 (a) A. Morandeira, G. Boschloo, A. Hagfeldt and L. Hammarström, J. Phys. Chem. C, 2008, 112, 9530–9537;
 (b) A. Morandeira, G. Boschloo, A. Hagfeldt and L. Hammarström, J. Phys. Chem. B, 2005, 109, 19403– 19410; (c) E. A. Gibson, A. L. Smeigh, L. Le Pleux, J. Fortage, G. Boschloo, E. Blart, Y. Pellegrin, F. Odobel, A. Hagfeldt and L. Hammarström, Angew. Chem., Int. Ed., 2009, 48, 4402–4405.

- 16 (a) T. M. McCormick, Z. Han, D. J. Weinberg, W. W. Brennessel, P. L. Holland and R. Eisenberg, *Inorg. Chem.*, 2011, 50, 10660–10666; (b) B. S. Veldkamp, W.-S. Han, S. M. Dyar, S. W. Eaton, M. A. Ratner and M. R. Wasielewski, *Energy Environ. Sci.*, 2013, 6, 1917–1928.
- 17 (a) M. A. Gross, A. Reynal, J. R. Durrant and E. Reisner, J. Am. Chem. Soc., 2014, 136, 356–366; (b) D. W. Wakerley, M. A. Gross and E. Reisner, Chem. Commun., 2014, 50, 15995–15998; (c) P. Rodriguez-Maciá, A. Dutta, W. Lubitz, W. J. Shaw and O. Rüdiger, Angew. Chem., Int. Ed., 2015, 54, 12303–12307; (d) A. Dutta, S. Lense, J. Hou, M. H. Engelhard, J. A. S. Roberts and W. J. Shaw, J. Am. Chem. Soc., 2013, 135, 18490–18496.
- 18 F. Lakadamyali, A. Reynal, M. Kato, J. R. Durrant and E. Reisner, *Chem.-Eur. J.*, 2012, **18**, 15464–15475.
- 19 S. Horvath, L. E. Fernandez, A. V. Soudackov and S. Hammes-Schiffer, *Proc. Natl. Acad. Sci. U. S. A.*, 2012, 109, 15663–15998.
- 20 A. Le Goff, V. Artero, B. Jousselme, P. D. Tran, N. Guillet, R. Métayé, A. Fihri, S. Palacin and M. Fontecave, *Science*, 2009, **326**, 1384–1387.
- 21 P. D. Tran, A. Le Goff, J. Heidkamp, B. Jousselme, N. Guillet,
 S. Palacin, H. Dau, M. Fontecave and V. Artero, *Angew. Chem., Int. Ed.*, 2011, 50, 1371–1374.
- 22 T. E. Rosser, M. A. Gross, Y.-H. Lai and E. Reisner, *Chem. Sci.*, 2016, DOI: 10.1039/c1035sc04863j, in press.
- 23 G. F. Moore and I. D. Sharp, *J. Phys. Chem. Lett.*, 2013, 4, 568–572.
- 24 H. Park, E. Bae, J.-J. Lee, J. Park and W. Choi, *J. Phys. Chem. B*, 2006, **110**, 8740–8749.
- 25 (a) C. Queffélec, M. Petit, P. Janvier, D. A. Knight and B. Bujoli, *Chem. Rev.*, 2012, **112**, 3777–3807; (b) K. Hanson, D. A. Torelli, A. K. Vannucci, M. K. Brennaman, H. Luo, L. Alibabaei, W. Song, D. L. Ashford, M. R. Norris, C. R. K. Glasson, J. J. Concepcion and T. J. Meyer, *Angew. Chem., Int. Ed.*, 2012, **51**, 12782–12785; (c) K. Kanaizuka, S. Kato, H. Moriyama and C. Pac, *Res. Chem. Intermed.*, 2007, **33**, 91–100; (d) X. Ding, Y. Gao, L. Zhang, Z. Yu, J. Liu and L. Sun, *ACS Catal.*, 2014, **4**, 2347–2350.
- 26 (a) A. Xiao, S. Zhou, C. Zuo, Y. Zhuan and X. Ding, *Mater. Res.* Bull., 2015, 61, 54–57; (b) Y. Y. Xi, D. Li, A. B. Djurišić, M. H. Xie, K. Y. K. Man and W. K. Chan, *Electrochem.* Solid-State Lett., 2008, 11, D56–D59; (c) L. Lepleux, B. Chavillon, Y. Pellegrin, E. Blart, L. Cario, S. Jobic and F. Odobel, *Inorg. Chem.*, 2009, 48, 8245–8250.
- 27 A. Clearfield and K. Demadis, *Metal Phosphonate Chemistry: From Synthesis to Applications*, RSC, Cambridge, 2011.
- 28 (a) M. Natali, A. Luisa, E. Iengo and F. Scandola, *Chem. Commun.*, 2014, 50, 1842–1844; (b) Y. Sun, J. Sun, J. R. Long, P. Yang and C. J. Chang, *Chem. Sci.*, 2013, 4, 118–124; (c) M. P. McLaughlin, T. M. McCormick, R. Eisenberg and P. L. Holland, *Chem. Commun.*, 2011, 47, 7989–7991; (d) P. Du, J. Schneider, G. Luo, W. W. Brennessel and R. Eisenberg, *Inorg. Chem.*, 2009, 48, 4952–4962.
- 29 G. Boschloo and A. Hagfeldt, *J. Phys. Chem. B*, 2001, **105**, 3039–3044.

- 30 (a) F. Odobel, Y. Pellegrin, E. A. Gibson, A. Hagfeldt,
 A. L. Smeigh and L. Hammarström, *Coord. Chem. Rev.*,
 2012, 256, 2414–2423; (b) D. Dini, Y. Halpin, J. G. Vos and
 E. A. Gibson, *Coord. Chem. Rev.*, 2015, 304–305, 179–201;
 (c) G. Natu, Z. Huang, Z. Ji and Y. Wu, *Langmuir*, 2012, 28, 950–956.
- 31 (a) F. Odobel, B. Bujoli and D. Massiot, *Chem. Mater.*, 2001,
 13, 163–173; (b) J. D. Wang, A. Clearfield and G.-Z. Peng, *Mater. Chem. Phys.*, 1993, 35, 208–216.
- 32 N. M. Muresan, J. Willkomm, D. Mersch, Y. Vaynzof and E. Reisner, *Angew. Chem., Int. Ed.*, 2012, **51**, 12749–12753.
- 33 A. K. Das, M. H. Engelhard, R. M. Bullock and J. A. S. Roberts, *Inorg. Chem.*, 2014, 53, 6875–6885.
- 34 S. A. Paniagua, P. J. Hotchkiss, S. C. Jones, S. R. Marder, A. Mudalige, F. S. Marrikar, J. E. Pemberton and N. R. Armstrong, J. Phys. Chem. C, 2008, 112, 7809–7817.
- 35 I. Gillaizeau-Gauthier, F. Odobel, M. Alebbi, R. Argazzi,
 E. Costa, C. A. Bignozzi, P. Qu and G. J. Meyer, *Inorg. Chem.*, 2001, 40, 6073–6079.
- 36 (a) A. M. Lapides, B. D. Sherman, M. K. Brennaman, C. J. Dares, K. R. Skinner, J. L. Templeton and T. J. Meyer,

Chem. Sci., 2015, **6**, 6398–6406; (*b*) X. Ding, Y. Gao, L. Ye, L. Zhang and L. Sun, *ChemSusChem*, 2015, **8**, 3992–3995.

- 37 This work, estimated by the intersection point of the normalised absorption and emission spectra of RuP3 in Na_2SO_4 (0.1 M, pH 3).
- 38 This work, measured by electrochemical impedance spectroscopy of optimised NiO films in aqueous electrolyte solution.
- 39 D. L. Ashford, M. K. Brennaman, R. J. Brown, S. Keinan, J. J. Concepcion, J. M. Papanikolas, J. L. Templeton and T. J. Meyer, *Inorg. Chem.*, 2015, 54, 460–469.
- 40 (a) H.-J. Son, C. Prasittichai, J. E. Mondloch, L. Luo, J. Wu,
 D. W. Kim, O. K. Farha and J. T. Hupp, *J. Am. Chem. Soc.*,
 2013, 135, 11529–11532; (b) K.-R. Wee, M. K. Brennaman,
 L. Alibabaei, B. H. Farnum, B. Sherman, A. M. Lapides and
 T. J. Meyer, *J. Am. Chem. Soc.*, 2014, 136, 13514–13517.
- 41 A. Reynal, J. Willkomm, N. M. Muresan, F. Lakadamyali, M. Planells, E. Reisner and J. R. Durrant, *Chem. Commun.*, 2014, 50, 12768–12771.