



Cite this: *RSC Adv.*, 2018, 8, 20543

# Improving the photocatalytic reduction of CO<sub>2</sub> to CO for TiO<sub>2</sub> hollow spheres through hybridization with a cobalt complex†

Jinliang Lin, \*<sup>a</sup> Xiaoxiang Sun,<sup>b</sup> Biao Qin<sup>a</sup> and Ting Yu<sup>a</sup>

A chemical system with enhanced efficiency for electron generation and transfer was constructed by the integration of TiO<sub>2</sub> hollow spheres with [Co(bipy)<sub>3</sub>]<sup>2+</sup>. The introduction of [Co(bipy)<sub>3</sub>]<sup>2+</sup> remarkably enhances the photocatalytic activity of pristine semiconductor photocatalysts for heterogeneous CO<sub>2</sub> conversion, which is attributable to the acceleration of charge separation. Of particular interest is that the excellent photocatalytic activity of the heterogeneous catalysts can be utilised for a universal photocatalytic CO<sub>2</sub> reduction system. Yields of 16.8 μmol CO and 6.6 μmol H<sub>2</sub> can be obtained after 2 h of the photoredox reaction, and the apparent overall quantum yield was estimated to be 0.66% under irradiation at λ = 365 nm. The present findings clearly demonstrate that the integration of electron mediators with semiconductors is a feasible process for the design and development of efficient photochemical systems for CO<sub>2</sub> conversion.

Received 14th April 2018

Accepted 23rd May 2018

DOI: 10.1039/c8ra03211d

[rsc.li/rsc-advances](http://rsc.li/rsc-advances)

## 1 Introduction

The photochemical reduction of CO<sub>2</sub>, as a model reaction of artificial photosynthesis, has obtained much attention because it may provide solutions for overcoming both the problem of global warming and the shortage of fossil resources.<sup>1</sup> Of particular interest is the conversion of CO<sub>2</sub> into the energy carrier CO, which is an important chemical feedstock used to form syngas in combination with H<sub>2</sub>, and can be used to replace the steam reforming of fossil fuels in the petrochemical industry.<sup>2</sup>

Photoelectrocatalytic CO<sub>2</sub> reduction has been achieved on various kinds of material, including inorganic semiconductors, carbon based semiconductors, metal complexes, supermolecules, and their derivatives.<sup>3</sup> Of these, TiO<sub>2</sub> is one of the most well-known and widely used materials due to its prominent properties, namely that it is non-toxic, low cost, chemically stable, and exhibits good radiosity.<sup>4</sup> In order to improve optical performance, it has been combined with various metals or other semiconductors to form hybridized composites in an attempt to reduce the band gap or suppress the recombination of photogenerated charge carriers.<sup>5</sup> Another way to achieve desirable photocatalytic behavior is by preparing catalytic

materials that possess special structures. Hierarchical structured TiO<sub>2</sub> with high surface areas such as hollow spheres has been designed for the purpose of increasing active site exposure. The beneficial effects of particle morphology on photochemistry have also been proven, with previous examples investigating geometric effects and electronic nature.<sup>6</sup> Additionally, previous works have proven that spherical morphology endowed Ti-base materials exhibit improved photocatalytic performances.<sup>7</sup>

Furthermore, hollow sphere structured TiO<sub>2</sub> can be further modified through hybridization or ion-doping strategies, and exhibits an enhanced photocatalytic performance for CO<sub>2</sub> activation. Fang *et al.* has presented novel Ti-based spherical photocatalysts with a large mesoporous volume and hierarchical porosity.<sup>8</sup> These exhibited an improvement in photocatalytic activity and an enhancement in the efficiency for the solar reduction of CO<sub>2</sub>. Additionally, a one-pot template-free method has been reported for the preparation of Cu(II) incorporated TiO<sub>2</sub> hollow microspheres for photo-driven CO<sub>2</sub> reduction. The effect of metal vacancies on the physicochemical properties has been proven to be critically important for metal oxides.<sup>9</sup> Hollow spheres consisting of alternating titania nanosheets (Ti<sub>0.91</sub>O<sub>2</sub>) and graphene nanosheets have been prepared by Zou's group.<sup>10</sup> There was a nine-fold enhancement of the photocatalytic activity on such hollow spherical materials compared to commercial P25 for photocatalytic CO<sub>2</sub> conversion. They have also reported a Au–TiO<sub>2</sub> nanocomposite with bifunctional linker molecules which was applied for the photocatalytic reduction of CO<sub>2</sub> into hydrocarbon fuels.<sup>11</sup> Several carbon fuels were produced over the Au–TiO<sub>2</sub> nanocomposite, including CO, CH<sub>4</sub>, CH<sub>3</sub>OH and CH<sub>3</sub>CH<sub>2</sub>OH, under different forms of light

<sup>a</sup>Department of Chemical and Engineering, Zunyi Normal College, 563000, Zunyi, P. R. China. E-mail: jinliang\_lin@163.com; Fax: +86-851-28927159; Tel: +86-851-28927159

<sup>b</sup>Department of Chemical and Engineering, Qiannan Normal University for Nationalities, 558000, Duyun, P. R. China

† Electronic supplementary information (ESI) available: Details of element analysis are listed. See DOI: 10.1039/c8ra03211d



irradiation and in different reaction systems. A Cu<sub>2</sub>O/TiO<sub>2</sub> composite exhibited higher efficiency in the photocatalytic reduction of CO<sub>2</sub> into CH<sub>4</sub> under visible-light irradiation ( $\lambda \geq 420$  nm).<sup>12</sup> This is because of the formation of a p–n heterojunction in the composites, resulting in the efficient suppression of the recombination of the photogenerated electrons and holes as well as an improved stability of the catalyst and, accordingly, an improved visible-light photocatalytic activity. Additionally, Jiang *et al.* found that a significantly improved photocatalytic activity obtained by hybrid carbon@TiO<sub>2</sub> hollow spheres was mainly due to the increased specific surface area, CO<sub>2</sub> uptake, local photothermal effect, enhancement of light absorption and charge transfer efficiency.<sup>5b</sup> A comprehensive review on surface and interface design in cocatalysts concerning CO<sub>2</sub> reduction has been presented by Bai *et al.*<sup>13</sup> As discussed, the rational material design of cocatalysts would be an effective route for pursuing their maximum contribution to the performance of photocatalysts.

The strategy of hybrid photocatalysts is a promising approach for the rational design of efficient and stable artificial photosynthetic systems. This is because homogeneous processes exhibit high quantum efficiencies, while heterogeneous processes possess desirable stabilities. Z-scheme water splitting systems, redox couples (*e.g.*, Fe<sup>3+</sup>/Fe<sup>2+</sup>, IO<sub>3</sub><sup>−</sup>/I<sup>−</sup>, [Co(bipy)<sub>3</sub>]<sup>3+/2+</sup> and [Co(phen)<sub>3</sub>]<sup>3+/2+</sup>) and reduced graphene oxides have been revealed to act as electron mediators to deliver photogenerated electrons from the O<sub>2</sub>-evolving catalyst to the H<sub>2</sub>-evolving catalyst in the two-photon type photocatalytic system.<sup>14</sup> Also, various metal complexes, which mostly can facilitate charge separation and lower the energy barrier, are usually employed as co-catalysts for CO<sub>2</sub> conversion. In earlier years, a high-efficiency photocatalytic CO<sub>2</sub> reduction system consisting of semiconductor powders and a Ru-based complex was reported by Bhatt and coworkers.<sup>15</sup> Xu *et al.* have developed an efficient hybrid CO<sub>2</sub> photoreduction system by mixing CdS nanoparticles and CoCl<sub>2</sub>/bipy in an acetonitrile solution, which affords a high apparent quantum yield of 1.0% for CO formation under monochromatic irradiation ( $\lambda = 470$  nm).<sup>16</sup> Our previous work revealed that a similar reaction mechanism can be further extended to both heterogeneous and homogeneous photocatalytic CO<sub>2</sub> reduction systems in acetonitrile solution.<sup>17</sup> More recently, Kuriki *et al.* has successfully developed several types of hybrid photocatalyst consisting of semiconductors and metal complexes, which have both the efficient CO<sub>2</sub> reduction abilities supplied by the metal-complex unit and the strong oxidation power of semiconductors.<sup>18</sup>

Complex/semiconductor hybrid photocatalysts represent a feasible approach to achieving high efficiency semiconductors for solar fuel production. However, the research in this direction is still in an early stage and therefore leaves much room for further development. In this paper we present the synthesis of spherical TiO<sub>2</sub> (denoted as “sTiO<sub>2</sub>”), and then employ it as photocatalyst for CO<sub>2</sub> reduction under UV-light irradiation. Based on the analysis, it is reasonable to think that the hybrid of TiO<sub>2</sub> hollow sphere and homogeneous methods may be an ideal pathway towards high efficiency. The spherical TiO<sub>2</sub> with higher surface area exhibits a superior photocatalytic performance to

bulk TiO<sub>2</sub> (denoted as “bTiO<sub>2</sub>”). More importantly, this study also shows that the combination of the sTiO<sub>2</sub> catalyzed photo-system with [Co(bipy)<sub>3</sub>]<sup>2+</sup> as a cobalt complex redox shuttle induces a highly efficient and selective electron transfer for the reduction of CO<sub>2</sub>. The reaction activity in the presence/absence of cobalt complex shows that this is a feasible way to obtain high efficiency photocatalytic CO<sub>2</sub> conversion.

## 2 Experimental

### 2.1 Chemicals

All reagents were commercially provided and used without further purification. Diethylenetriamine (DETA, 97%), titanium(IV) isopropoxide (TIP, 97%) and 2,2-bipyridine (bipy, 98%) were purchased from Alfa. Isopropyl alcohol (IPA, 98%), acetonitrile (MeCN, AR), triethanolamine (TEOA, AR) and cobalt chloride hexahydrate (CoCl<sub>2</sub>·6H<sub>2</sub>O, 99.9%) were purchased from China Sinopharm Chemical Reagent Co. Ltd.

### 2.2 Preparation of TiO<sub>2</sub> samples

The TiO<sub>2</sub> spheres were prepared using a hydrothermal method as described in previous reports:<sup>19</sup> 0.05 mL of DETA was added to 75 mL of isopropyl alcohol, and the mixture was stirred for 5 minutes. Then, 2.5 mL of titanium(IV) isopropoxide was added. The reaction solution was then transferred to a 100 mL Teflon-lined stainless steel autoclave and the temperature was maintained at 180 °C for 24 h. The autoclave was then taken out of the oven and left to cool naturally to room temperature. The pure products were isolated *via* centrifugation, cleaned with four cycles of centrifugation and washing in ethanol and water respectively, and dried at 60 °C overnight. All of the products were calcined at 450 °C for 2 h with a heating rate of 1 °C min<sup>−1</sup> to obtain a highly crystalline anatase phase. The bulk TiO<sub>2</sub> was directly obtained through hydrolysis: 5 mL of titanium(IV) isopropoxide was added to 95 mL of water, and the mixture was stirred for 10 minutes. The following processes, including isolation and calcination, were the same as those for the TiO<sub>2</sub> sphere.

### 2.3 Characterization

X-ray diffraction (XRD) patterns were collected using a Bruker D8 Advance X-ray diffractometer (Cu K $\alpha$  irradiation,  $\lambda = 1.5406$  Å), irradiating with a scanning rate of 0.02 deg s<sup>−1</sup>. A transmission electron microscope (TEM, JEOL-200CX) was used to observe the morphology of the particles. The scanning electron microscope (SEM, FEI-Philips CM-20) images were obtained with an electron microscope coupled to an energy-dispersive X-ray spectrometer (EDS) with an accelerating voltage of 200 kV. The Brunauer–Emmett–Teller (BET) specific surface areas of initially treated samples at 453 K for 8 h were calculated from the nitrogen adsorption–desorption isotherms obtained at 77 K with the Micromeritics ASAP 2020 system. Ultraviolet and visible absorption spectra were recorded at room temperature with a UV-vis (Varian Cary 5000) spectrophotometer. The detection of the Co<sup>I</sup> transition was conducted in a sealed container adapted to accommodate the recording equipment,



and the sample was exposed to light irradiation for 10 min before the test. Photoluminescence (PL) spectra were observed with a spectrophotometer (Hitachi, F-4600), with an excitation wavelength of 400 nm. The electrochemical behavior was tested on a CHI660E workstation (Shanghai Chenhua Instruments, China) using a three-electrode electrochemical cell with a working electrode, a platinum counter electrode and a saturated calomel electrode (SCE) as a reference electrode in a 0.1 M KCl aqueous solution. The working electrode was made of indium-tin oxide (ITO) glass.

#### 2.4 Photocatalysis test

All experiments were performed in a Schlenk flask (80 mL) under an atmospheric pressure of CO<sub>2</sub> (1 atm).<sup>20</sup> In the Schlenk flask, TiO<sub>2</sub> (50 mg), bipy (15 mg) and CoCl<sub>2</sub> (50 μmol) were added to a mixture of solvent (5 mL) and TEOA (1 mL). The system was subjected to vacuum degassing and backfilling with pure CO<sub>2</sub> gas. This process was repeated three times and after the last cycle the flask was back filled with CO<sub>2</sub>. Then the system was irradiated with five non-focused 6 W UV lights (Hitachi F6T5, 365 nm) with vigorous stirring at 20 °C controlled by a water-cooling system. The produced gases (CO, H<sub>2</sub>) were detected by a gas chromatograph (Agilent 7890B, Agilent Technologies) equipped with a packed column (TDX-1 mesh 42/10). Ar was used as the carrier gas. The apparent quantum yield (AQY) for CO/H<sub>2</sub> generation was measured using the same photochemical experimental setup. The intensity of light irradiation was measured as 2.6 mW cm<sup>-2</sup> (CEAulight, AULTT-P4000) and the irradiated area was 1.0 cm<sup>2</sup>.

### 3 Results and discussion

The high crystallinity and phase purity of the spherical resultant material (sTiO<sub>2</sub>) were confirmed *via* XRD (Fig. 1). The diffraction peaks of TiO<sub>2</sub> were observed at  $2\theta = 25.1^\circ$  (101),  $37.6^\circ$  (004),  $47.9^\circ$  (200),  $53.7^\circ$  (105),  $54.5^\circ$  (211) and  $62.7^\circ$  (204), which agrees with the corresponding crystal planes of anatase TiO<sub>2</sub> (JCPDS file no. 21-1272). Additionally, the TiO<sub>2</sub> directly obtained *via* hydrolysis and then calcination at 450 °C that was used as a reference sample (bTiO<sub>2</sub>) exhibited a pattern corresponding to the anatase phase, which is the same as the spherical sample.




Fig. 1 XRD spectra of the as-prepared sTiO<sub>2</sub> and bTiO<sub>2</sub>.

The morphology of the TiO<sub>2</sub> sphere was verified *via* SEM and TEM. As shown in Fig. 2a, the SEM images display that the as-synthesized TiO<sub>2</sub> structures are typically spherical in shape. Fig. 2b indicates that the units of the spheres are constructed with nanosheets. These plates with interlaced structure are also revealed in the SEM image. The superstructure was further confirmed *via* TEM (Fig. 2c), and is in accord with previous reports.<sup>19</sup> These results indicate that the three-dimensional structure with pieces supporting each other greatly contributes to the high surface area and the stability of the catalytic material during the photochemical reaction.

The self-assembly of the hollow structured TiO<sub>2</sub> produces a nanoporous structure, as confirmed by the N<sub>2</sub> adsorption/desorption isotherm shown in Fig. 3. It gives a type-IV isotherm with a type H<sub>3</sub> hysteresis loop, which is indicative of a mesoporous structure.<sup>21</sup> The relatively narrow pore size distribution of sTiO<sub>2</sub> (Fig. 3, inset) calculated using the Barrett-Joyner-Halenda (BJH) method from the two branches of the isotherm signifies that most of the pores have sizes in the range 5–15 nm. Such a porous structure gives rise to a surface area of 136 m<sup>2</sup> g<sup>-1</sup>, as calculated *via* the Brunauer-Emmett-Teller (BET) method. Obviously, as demonstrated in Fig. 3, the surface area of sTiO<sub>2</sub> is much higher than that of bTiO<sub>2</sub> (*ca.* 14 m<sup>2</sup> g<sup>-1</sup>).

As shown in Fig. 4, only a trace amount of CO (<1 μmol) was detected in the current system, and the yield of H<sub>2</sub> was also moderate (3 μmol). When Co(bipy)<sub>3</sub><sup>2+</sup> was present as an effective electron transport carrier, as expected, the reaction was promoted dramatically, yielding nearly a 20-fold increase in CO (16.8 μmol) and twice the amount of H<sub>2</sub> (6.6 μmol). The apparent overall quantum yield of this CO<sub>2</sub> photoreduction system was estimated to be 0.66% under irradiation at  $\lambda = 365$  nm. The production of CO and H<sub>2</sub> on bTiO<sub>2</sub> was 9.4 μmol and 3.2 μmol respectively, in spite of this system also containing [Co(bipy)<sub>3</sub>]Cl<sub>2</sub>. We have also tested the photocatalytic performance on P25 (Degussa) as a standard reference, which leads to the formation of CO (19.3 μmol) and H<sub>2</sub> (8.9 μmol) in the current system. This is mainly attributable to its intrinsic structure being a 70% rutile phase and 30% anatase phase titanium mixture. CO production on sTiO<sub>2</sub> is 2.5 μmol less than that on P25. When CO<sub>2</sub> was replaced by N<sub>2</sub> in the system, evidence was observed that confirmed the participation of CO<sub>2</sub>




Fig. 2 SEM (a and b) and TEM (c) images of the TiO<sub>2</sub> spheres.






Fig. 3  $N_2$  adsorption/desorption isotherm of the as-prepared spherical  $TiO_2$  (●) and bulk  $TiO_2$  (■). The inset shows the pore size distributions calculated using the BJH method.




Fig. 4 The photocatalytic performance of (a)  $sTiO_2$ , (b)  $sTiO_2$  +  $Co(bipy)_3Cl_2$ , (c)  $bTiO_2$  +  $Co(bipy)_3Cl_2$  and (d)  $sTiO_2$  +  $Co(bipy)_3Cl_2$  under an  $N_2$  atmosphere.

in the reaction, because only  $H_2$  gas ( $3.9 \mu mol$ ) was detected under these reaction conditions, and no CO was detected. This result confirmed that the carbon source of CO production is  $CO_2$ , and not other organic ingredients. Additionally, control experiments showed that there was no CO generation in the absence of light or  $TiO_2$ . In addition, energy-dispersive X-ray spectroscopy (EDS) analysis and elemental mapping are shown in Fig. S1 to S6<sup>†</sup>, and were used to determine the Co content in  $bTiO_2$ ,  $sTiO_2$  and  $sTiO_2$  samples after reaction. There was no change detected in the Co content in  $sTiO_2$  after the reaction, compared with the samples before the reaction. The results indicate the existence of the Co-complex in this system throughout the studied process.

To identify the formation of cobalt species, the optical absorption spectra of several solutions including  $Co^{2+}$ ,  $[Co^{II}(bipy)_3]Cl_2$ , and  $[Co^I(bipy)_3]Cl$  are presented in Fig. 5. The solution containing  $Co^{2+}$  exhibited an absorption band positioned at 550–720 nm (red line), which is due to the d-d transition in  $CoL_4$  tetrahedral complexes.<sup>22</sup> After the introduction of bipy, a new absorption peak at 400–570 nm was observed in the UV-vis spectrum (blue line), which was in accord with results for  $Co(bipy)_3Cl_2$  in previous literature.<sup>23</sup> These results are due to the formation of a new photo-responsive compound  $[Co(bipy)_3]^{2+}$




Fig. 5 Absorption spectra of acetonitrile solutions in the forms of  $[Co^I(bipy)_3]Cl$  (green line, containing  $TiO_2$  spheres),  $[Co^{II}(bipy)_3]Cl_2$  (blue line) and  $CoCl_2$  (red line).

when  $Co^{2+}$  and bipy were combined. To investigate the effect upon  $Co^{II}$  when catalyzed by  $sTiO_2$ , the reaction solution was measured *via* UV-Vis absorption spectroscopy after 10 min of light irradiation (green line). The formation of a new absorption band (ca. 450–720 nm) was observed in the UV-Vis absorption spectrum. The broad absorption band is attributed to the intramolecular charge-transfer from the metal center to the pyridinium moiety. This change is mainly due to the generation of a reducing  $Co^I$ -complex during the photocatalytic  $CO_2$  reduction reaction.

To determine whether the cobalt complex accelerates charge carrier transfer, we used a PL technique to investigate the fluorescence, and the results are shown in Fig. 6. The  $sTiO_2$  exhibited a strong PL band that was assigned to the inherent recombination of photogenerated electrons and holes.<sup>24</sup> In the presence of  $[Co(bipy)_3]^{2+}$ , there is a significant decrease in the PL intensity. A weaker intensity of the PL peak represents a lower recombination probability of photogenerated charge carriers. Therefore, the integration of cobalt redox mediators with  $sTiO_2$  could effectively inhibit the recombination of photogenerated charge carriers and accelerate electron migration.

The process of cobalt complex transformation during  $CO_2$  reduction can be inspected *via* cyclic voltammetry (CV). In




Fig. 6 Photoluminescence spectra of semiconductor photocatalysts without (dashed line) and with (solid line)  $[Co(bipy)_3]^{2+}$ .






electrochemical tests, the transition state of the cobalt species can be monitored indirectly, which involves the initial reduction of Co<sup>II</sup> complexes and their subsequent reaction with CO<sub>2</sub> to form Co–CO<sub>2</sub> intermediates.<sup>25</sup> In the absence of CO<sub>2</sub>, the obtained redox potential ( $E_0 = -0.8$  V) in MeCN solution is attributed to the conversion of the Co<sup>II</sup> complex to Co<sup>I</sup> species.<sup>26</sup> When CO<sub>2</sub> is introduced (Fig. 7), the intensity of the peak observed in N<sub>2</sub> is enhanced considerably. The markedly increased current densities reveal that the reaction system undergoes the electrocatalytic CO<sub>2</sub> reduction reaction with high efficiency.



The advantage of hollow spherical TiO<sub>2</sub> has been demonstrated in the photocatalytic performance of CO<sub>2</sub> reduction (Fig. 4). We suggest that the hierarchical structure plays a important role in the current reaction. As revealed in Fig. 2, the ultrathin nature of the TiO<sub>2</sub> nanosheets allows charge carriers to move rapidly onto the surface. In addition, the sufficient separation of the ultrathin TiO<sub>2</sub> nanosheets enables photogenerated electrons to quickly transfer from the TiO<sub>2</sub> nanosheets to the cobalt complex to enhance utilization of the charge carriers. With respect to the photoresponse, the hollow structure potentially acts as a photon trap well to allow the multiscattering of incident light for the enhancement of light absorption.

Upon irradiation, the excited TiO<sub>2</sub> liberates the electrons from the valence band to the conduction band.<sup>27</sup> CO<sub>2</sub> activation happens in the absence of [Co(bipy)<sub>3</sub>]<sup>2+</sup> through charge transfer from the semiconductor to the CO<sub>2</sub> molecule adsorbed on the TiO<sub>2</sub> surface. While the presence of massive photogenerated electron–hole pairs is in vain because of the fast recombination, especially in the heterogeneous photocatalytic system, as expected, there is a dominant pathway that is designed for electron transfer towards the CO<sub>2</sub> molecule *via* the cobalt complex.<sup>28</sup> After Co<sup>II</sup> gains an electron, the low valent Co intermediates are stabilized by pyridine ligands through weak coordination,<sup>29</sup> promoting the activation of the CO<sub>2</sub> molecules *via* nucleophilic attack. The thus formed Co<sup>I</sup> complexes are important redox active catalysts.<sup>16</sup> In our previous work, evidence of the generation of Co<sup>I</sup> through light excitation was observed *via* UV-vis spectroscopy.<sup>30</sup> Such intermediates may also result in the




protonation of the Co<sup>I</sup>–H complex when hydron is present, subsequently yielding H<sub>2</sub>.<sup>31</sup> It should be noted that the activity of the CO<sub>2</sub> conversion reaction is determined not only by the rate of formation of the photogenerated charge carrier, but also the energy barrier to formation of the relevant CO<sub>2</sub> intermediates. The activation energy of molecular CO<sub>2</sub> is lowered after the combination of CO<sub>2</sub> with cobalt species. Thus, CO<sub>2</sub> reduction exhibits superior competitiveness towards H<sub>2</sub> generation. As discussed, the following processes are revealed by the electrochemical performance, and are described in eqn (1)–(7).



In N<sub>2</sub>-saturated solution



In CO<sub>2</sub>-saturated solution



## 4 Conclusions

In summary, we have explored improving the efficiency of photocatalytic CO<sub>2</sub> reduction with TiO<sub>2</sub> hollow spheres as photocatalysts in synergetic combination with [Co(bipy)<sub>3</sub>]Cl<sub>2</sub>. This hybrid system exhibits high photocatalytic reactivity towards CO<sub>2</sub>-to-CO conversion due to the addition of [Co(bipy)<sub>3</sub>]<sup>2+</sup> as a promoter for charge-carrier separation, transfer kinetics, and interface interaction. This result provides insight to the construction of efficient heterogeneous photochemical CO<sub>2</sub> reduction systems under mild conditions. This finding has the potential to open up new opportunities in artificial photosynthesis, catalytic chemistry, and energy conversion with excellent morphology catalytic materials.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was sponsored by the Natural Science Foundation of Guizhou Province ([2017]1198 & [2017]7089 & [2016]7010) and Construction Projects of Undergraduate Course Teaching of the Guizhou Province Education Department ([2015]337 & [2017]352).




Fig. 7 Cyclic voltammograms in N<sub>2</sub> (black) and CO<sub>2</sub> (red) saturated solutions.



## Notes and references

- 1 (a) X. Z. Zheng, Y. Yang, S. F. Chen and L. W. Zhang, *Chin. J. Catal.*, 2018, **39**, 379–389; (b) T. Gasser, C. Guivarch, K. Tachiiri, C. D. Jones and P. Ciais, *Nat. Commun.*, 2015, **6**, 7958.
- 2 J. M. Spurgeon and B. Kumar, *Energy Environ. Sci.*, 2018, DOI: 10.1039/c8ee00097b.
- 3 (a) B. Wang, C. Li, H. Cui, J. Zhang, J. P. Zhai and Q. Li, *J. Mater. Sci.*, 2014, **49**, 1336–1344; (b) Z. M. Li, P. Y. Zhang, T. Shao and X. Y. Li, *Appl. Catal., B*, 2012, **125**, 350–357; (c) J. Zhu and X. F. Qian, *J. Solid State Chem.*, 2010, **183**, 1632–1639; (d) C. Q. Zhu, B. G. Lu, Q. Su, E. Q. Xie and W. Lan, *Nanoscale*, 2012, **4**, 3060–3064; (e) G. F. Lin, J. W. Zheng and R. Xu, *J. Phys. Chem. C*, 2008, **112**, 7363–7370; (f) A. Nikokavoura and C. Trapalis, *Appl. Surf. Sci.*, 2017, **391**, 149–174; (g) J. M. Lehn and R. Ziessel, *Proc. Natl. Acad. Sci. U. S. A.*, 1982, **79**, 701–704.
- 4 (a) M. R. Hoffmann, S. T. Martin, W. Y. Choi and D. W. Bahnemann, *Chem. Rev.*, 1995, **95**, 69–96; (b) D. R. Fattakhova, A. Zaleska and T. Bein, *Chem. Rev.*, 2014, **114**, 9487–9558.
- 5 (a) L. Pan, S. Wang, J. Xie, L. Wang, X. Zhang and J. J. Zou, *Nano Energy*, 2016, **28**, 296–303; (b) W. K. Wang, D. Xu, B. Cheng, J. G. Yu and C. J. Jiang, *J. Mater. Chem. A*, 2017, **5**, 5020–5029.
- 6 (a) G. Liu, J. C. Yu, G. Q. Lu and H. M. Cheng, *Chem. Commun.*, 2011, **47**, 6763–6783; (b) M. A. Butler and D. S. Ginley, *J. Electrochem. Soc.*, 1978, **125**, 228–232.
- 7 D. Zhang, J. Y. Zhu, N. Zhang, T. Liu, L. M. Chen, X. H. Liu, R. Z. Ma, H. T. Zhang and G. Z. Qiu, *Sci. Rep.*, 2015, **5**, 8737.
- 8 B. Fang, A. Bonakdarpour, K. Reilly, Y. Xing, F. Taghipour and D. P. Wilkinson, *ACS Appl. Mater. Interfaces*, 2014, **6**, 15488–15498.
- 9 S. B. Wang, L. Pan, J. J. Song, W. B. Mi, J. J. Zou, L. Wang and X. W. Zhang, *J. Am. Chem. Soc.*, 2015, **137**, 2975–2983.
- 10 W. Tu, Z. Tian, J. Gao, Y. Zhou, Q. Liu, X. Y. Chen, H. T. Zhang, J. G. Liu and Z. G. Zou, *Adv. Funct. Mater.*, 2012, **22**, 1215–1221.
- 11 M. Wang, Q. T. Han, Y. Zhou, P. Li, W. G. Tu, L. Q. Tang and Z. G. Zou, *RSC Adv.*, 2016, **6**, 81510–81516.
- 12 F. Bi, M. N. Ashiq, M. F. Ehsan, W. Liu and T. He, *Chin. J. Chem.*, 2015, **33**, 112–118.
- 13 S. Bai, W. J. Yin, L. L. Wang, Z. Q. Li and Y. J. Xiong, *RSC Adv.*, 2016, **6**, 57446–57463.
- 14 (a) Y. Sasaki, H. Kato and A. Kudo, *J. Am. Chem. Soc.*, 2013, **135**, 5441–5449; (b) A. Iwase, Y. H. Ng, Y. Ishiguro, A. Kudo and R. Amal, *J. Am. Chem. Soc.*, 2011, **133**, 11054–11057; (c) R. Abe, T. Takata, H. Sugihara and K. Domen, *Chem. Commun.*, 2005, 3829–3831.
- 15 M. M. T. Khan, D. Chatterjee and J. Bhatt, *J. Chem. Sci.*, 1992, **104**, 747–752.
- 16 Z. G. Chai, Q. Li and D. S. Xu, *RSC Adv.*, 2014, **4**, 44991–44995.
- 17 J. L. Lin, Y. D. Hou, Y. Zheng and X. C. Wang, *Chem.–Asian J.*, 2014, **9**, 2468–2474.
- 18 R. Kuriki, H. Kumagai, K. Maeda and O. Ishitani, *Hyomen Kagaku*, 2017, **38**, 291–296.
- 19 J. S. Chen, Y. L. Tan, C. M. Li, Y. L. Cheah and D. Luan, *J. Am. Chem. Soc.*, 2010, **132**, 6124–6130.
- 20 J. L. Lin, Z. X. Ding, Y. D. Hou and X. C. Wang, *Sci. Rep.*, 2013, **3**, 1056.
- 21 K. S. W. Sing, D. H. Everett, R. A. W. Haul, L. Moscou, R. A. Pierotti, J. Rouquerol and T. Siemieniowska, *Pure Appl. Chem.*, 1985, **57**, 603.
- 22 K. Sivaraj and K. P. Elango, *J. Solution Chem.*, 2010, **39**, 1681–1697.
- 23 H. A. Schwarz, C. Creutz and N. Sutin, *Inorg. Chem.*, 1985, **24**, 433–439.
- 24 (a) R. R. Prabhu and M. A. Khadar, *J. Phys. D: Appl. Phys.*, 2005, **65**, 801–807; (b) J. Zhou, M. Takeuchi, A. K. Ray, M. Anpo and X. S. Zhao, *J. Colloid Interface Sci.*, 2007, **311**, 497–501; (c) X. Wang, K. Maeda, A. Thomas, K. Takanabe, G. Xin, J. M. Carlsson, K. Domen and M. Antonietti, *Nat. Mater.*, 2009, **8**, 76–80.
- 25 J. D. Froehlich and C. P. Kubiak, *J. Am. Chem. Soc.*, 2015, **137**, 3565–3573.
- 26 H. Fillon, E. L. Gall, C. Gosmini and J. Périchon, *Tetrahedron Lett.*, 2002, **43**, 5941–5944.
- 27 F. Wenand and C. Li, *Acc. Chem. Res.*, 2013, **46**, 2355–2364.
- 28 A. L. Linsebigler, G. Q. Lu and J. T. Yates, *Chem. Rev.*, 1995, **95**, 735–758.
- 29 Y. G. Budnikova, A. Kafiyatullina, Y. M. Kargin and O. Sinyashin, *Russ. Chem. Bull.*, 2003, **52**, 1504–1511.
- 30 J. L. Lin, B. Qin and G. L. Zhao, *J. Photochem. Photobiol., A*, 2018, **354**, 181–186.
- 31 S. C. Marinescu, J. R. Winkler and H. B. Gray, *Proc. Natl. Acad. Sci. U. S. A.*, 2012, **109**, 15127–15131.

