INORGANIC CHEMISTRY

FRONTIERS

RESEARCH ARTICLE

Check for updates

Cite this: Inorg. Chem. Front., 2022, 9, 2462

$KNa_{0.78}Eu_{0.27}In_{3.80}B_{12}S_{12}$: a novel hexanary thioborate featuring a $B_{12}S_{12}$ cluster and diverse InS_x (x = 4, 5, 6) units[†]

Shan-Shan Han, Su-Xin Yu, Wenlong Liu 🕩 and Sheng-Ping Guo 🕩 *

Thioborates combine the advantages of sulfides and borates, and are a new type of multifunctional inorganic material with versatile structural features. Here, a thioborate $KNa_{0.78}Eu_{0.27}In_{3.80}B_{12}S_{12}$ crystallizing with a new type of compound was synthesized by a high-temperature flux method. Its structure features a rarely discovered $B_{12}S_{12}$ cluster and diverse InS_x (x = 4, 5, 6) units built in a three-dimensional $\{[In_{3.80}B_{12}S_{12}]^{2.6-}\}_{\infty}$ polyanionic framework. The structural complexity and novelty are well elaborated. Its optical band gap was determined to be 2.28 eV, and a theoretical calculation of its electronic structure was also performed. This work not only enriches the structural chemistry of chalcogenoborates but also provides a new potential RE-B-Q family (RE = rare-earth metal; Q = S, Se). The latter may produce some interesting functionals.

Received 9th March 2022, Accepted 13th April 2022 DOI: 10.1039/d2qi00520d

rsc.li/frontiers-inorganic

1. Introduction

The boron element features structural complexity, electron deficiency, unusual bonding situations, and builds a rich boron chemistry.1 Boron and boron-based materials have important applications in modern industry, agriculture, biology, medicine and national defense.²⁻⁸ There are many variants of crystalline elemental boron, and all of them are built by the basic building unit B_{12} icosahedron. Each B_{12} icosahedron has three B-B σ single bonds and ten three-center twoelectron (3c-2e) bonds.9 This specific bonding style yields a rich boron chemistry, in which the closo-polyhedral borane anions have drawn attention to these species as precursors of a new and rapidly expanding field of chemistry enriched with novel applications in contemporary materials research.¹⁰⁻¹² *closo*-borane $[B_{12}H_{12}]^{2-}$ is a cluster exhibiting a three-dimensional (3D) aromatic electron delocalization and a remarkable chemical stability.¹³⁻¹⁵ In contrast to the highly reactive borane with a small molecular weight, $[B_{12}H_{12}]^{2-}$ -based salts are the most stable molecules; this anion survives extended heating in strongly acidic or alkaline solutions.^{16,17}

Attracted by the specialty of B₁₂, many efforts have been made to enrich this special entity.¹⁸ Completely saturated with hydrogen, halogens, or even hydroxyl groups, the boron icosahedra can be obtained in solution.^{10,19-24} All of these bond with B₁₂ to form an anion cluster. Different from this style, B₁₂ icosahedron can also connect with twelve Q (Q = S, Se) atoms to form a unique $[B_{12}Q_{12}]^{14-}$ cluster.²⁵⁻³² To date, around thirty chalcogenoborates containing B₁₂Q₁₂ cluster have been discovered. In their structures, there are two types of coordination environments around each B_{12} icosahedron. One is B_{12} saturated with six BQ₃ units to form the $[B_{12}(BQ_3)_6]^{8-}$ anion,²⁵ and the other is B12 connected with six MQ4 and two M'Q6 units to build a $[MB_{12}(M'Q_4)_3]^{x-}$ (x = 0, 2; M = Sm, Gd, Ga, In, Sn, Cr; M' = Ga, In, Sn, Si) open framework.^{31,33–37} Specifically, the noncentrosymmetric (NCS) ones of the latter show Kleinman-forbidden second-harmonic generation activity.^{33–36}

Chalcogenoborates containing $B_{12}Q_{12}$ clusters are very rare when compared with those containing $B_{12}X_{12}$, $B_{12}(OH)_{12}$ or $B_{12}H_{12}$ clusters.³⁸⁻⁴² Encouraged by the structural diversity for these, it is necessary to explore more $B_{12}Q_{12}$ -based ones to enrich their structural chemistry and explore their application potentials. Based on this consideration, our continuous investigation of the $[B_{12}Q_{12}]^{14-}$ -based system has led to the discovery of a novel hexanary thioborate, $KNa_{0.78}Eu_{0.27}In_{3.80}B_{12}S_{12}$ (1). Its 3D structure features two types of B_{12} icosahedron and diverse InS_x (x = 4, 5, 6) units, and B_{12} icosahedra are consolidated by eight or four InS_x units, representing a new type of chalcogenoborate. Here, the synthesis, crystal structure, and diverse characterizations are reported.



View Article Online

View Journal | View Issue

School of Chemistry and Chemical Engineering, Yangzhou University, Yangzhou, Jiangsu 225002, P. R. China. E-mail: spguo@yzu.edu.cn

[†]Electronic supplementary information (ESI) available: Crystal data tables, crystal photographs, EDS and other tables. CCDC 2086848. For ESI and crystallographic data in CIF or other electronic format see DOI: https://doi.org/10.1039/ d2qi00520d

2. Experimental section

2.1. Synthesis and analyses

A high-temperature solid-state method was used to synthesize the crystals of $KNa_{0.78}Eu_{0.27}In_{3.80}B_{12}S_{12}$ (1). All the starting materials were used as received without further purification. Considerable efforts were devoted to synthesize 1, and eventually an optimized routine with a high yield was found. For the optimized synthetic route, a 500 mg mixture of Eu₂O₃ (99.9%), In₂O₃ (99.9%), S (99.95%) and B (99%) with 1:3:16:12 of Eu: In: B: S, and an additional 400 mg of NaI and 200 mg of KI (99%) as flux, were used as the starting materials, which were hand-ground in an agate mortar for 30 minutes. The obtained mixture was pressed into a pellet and then loaded into an evacuated quartz ampoule with a vacuum degree of 1×10^{-4} Torr. The quartz tube was put in a muffle furnace and heated to 950 °C in 25 h and kept for 7 days, and then cooled down to 300 °C in 5 days. The dark-red crystals of 1 are stable without any change after exposure to air for a few months at room temperature.

A semiquantitative microscopic elemental analysis on the as-prepared single-crystals of **1** was performed on a field-emission scanning electron microscope (FESEM, Zeiss-Supra55) equipped with an energy dispersive X-ray spectroscope (EDS, Bruker, Quantax), which confirmed the presence of K, Na, Eu, In and S. Specifically, the average ratio of In and Eu is 13, close to that of the single-crystal structure analysis, determined as 14.07. The B element could not be detected in view of its light mass (Table S1 and Fig. S1†).

The inductively coupled plasma (ICP) spectroscopy of **1** was measured on an Optima 7300 DV spectrometer. Polytetrafluoroethylene(PTFE) beakers were used to dissolve the powder of **1** and blank samples were also measured to eliminate background effects. The results show that the mass ratios of Eu/In (14.67) and K/Na (1.26) are close to the theoretical values (Eu/In = 14.07 and K/Na = 1.33).

The powder X-ray diffraction measurement of **1** was carried out with a Bruker D8 Advance diffractometer at 40 kV and 100 mA for Cu-K α radiation (λ = 1.5406 Å) at room temperature. The 2 θ range was 10–60° with a scan step width of 2°. The calculated pattern was generated using the Mercury program with its single-crystal structure data. JANA2006 software was employed to perform the Rietveld refinement (Table S2† and Fig. 1).

2.2. Crystal data

Several suitable single crystals of **1** were selected using an optical microscope for the single-crystal X-ray diffraction analysis. The diffraction data were collected by using a graphite-monochromated Mo-K α radiation ($\lambda = 0.71073$ Å) at room temperature on a Bruker D8 QUEST X-ray diffractometer. The structure was solved by direct methods and refined on F² by full-matrix least-squares methods using the Shelxtl2014 crystal-lographic software package.⁴³ The crystallographic data are listed in Table 1, and the atom positions and anisotropic displacement parameters (ADP), and bond distances are listed in



Fig. 1 Rietveld refinement for the powder X-ray diffraction pattern of 1.

Table 1 Crystal data and structure refinement parameters for 1

Chemical formula	KNa _{0.78} Eu _{0.27} In _{3.80} B ₁₂ S ₁₂
FW	1048.21
$T(\mathbf{K})$	296
Crystal system	Monoclinic
Space group	C2/m
Z	4
a (Å)	15.2538(12)
b (Å)	10.4468(7)
c (Å)	14.6131(10)
$\beta(\circ)$	105.036(3)
$V(Å^3)$	2248.9(3)
$D_{\text{calcd}} (\text{g cm}^{-3})$	3.096
$\mu (\text{mm}^{-1})$	5.888
F(000)	1930.0
Crystal size/mm ³	0.136 imes 0.12 imes 0.05
2θ range (°)	4.78 to 50.942
Indep. reflns./R _{int}	2108/0.0245
Data/restraints/parameters	2108/0/164
GOF on F^2	1.097
$R1^{a} (I > 2\sigma(I))$	0.0306
$wR2^{b}$ (all data)	0.0701
${}^{a}R1 = F_{o} - F_{c} / F_{o} $. ${}^{b}wR2 = [w(F_{o})]$	$(F_{\rm o}^2)^2 - (F_{\rm o}^2)^2 [w(F_{\rm o}^2)^2]^{1/2}$.

Tables S3 and S4,† respectively. The CIF document has also been deposited with the CCDC 2086848.†

Considering that the structure of **1** is heavily disordered, involving partial occupation and spilt sites, it is necessary to make a detailed description about the structure solution process, which can be described as below. First, the EDS analysis result indicates that K, Na, Eu, In and S are the compositional elements in crystals of **1**, and all these elements have nonnegligible contents according to the EDS analysis of more than 30 single-crystals. Second, all the B, S, and K sites are fully occupied with reasonable anisotropic displacement factors (ADPs). Third, two of the three In sites are fully occupied, while the third one (In(1)) is partially occupied, and the occupancy was freely refined to 0.80. Fourth, the occupancy of Eu(1) was freely refined to 0.27. Compared with the refinement results for the model with a full occupation of In(1) and Eu(1) atoms, the *R*1 value reduced from 0.1153 to 0.0492. Fifth, the Na(1) site was split over two neighboring sites, namely, Na(1A) on Wyckoff site *m* and Na(1B) on Wyckoff site 2/*m*. The occupancies for these two sites were refined to 0.56 for Na(1A) and 0.44 for Na(1B). The incomplete occupations of Eu and In atoms in other works were also discovered (Table S5†). Combining the above considerations together, the chemical formula of **1** is given as KNa_{0.78}Eu_{0.27}In_{3.80}B₁₂S₁₂.

2.3. UV-vis-NIR diffuse reflectance spectroscopy

The UV-vis-NIR diffuse reflection spectrum was recorded at room temperature using a powder $BaSO_4$ sample as a standard on a computer-controlled Cary 5000 UV-vis-NIR spectrometer equipped with a diffuse reflectance accessory at 200–2500 nm. The spectrum was calculated from the reflection spectrum by the Kubelka–Munk function:⁴⁴

$$F(R) = (1 - R)^2 / (2R) = K/S$$

where *R* is the reflectance, *K* is the absorption, and *S* is the scattering. In the (K/S) versus *E* plot, extrapolating the linear portion of the rising curve to zero gives rise to the onset of absorption.

2.4. Thermal analysis

Differential scanning calorimetry (DSC) analysis on 1 was performed by using a Mettler Toledo thermal analyzer under N_2 atmosphere. The powder sample of 1 was put into a crucible and heated to 1000 °C and cooled back to room temperature at a rate of 10 °C min⁻¹.

2.5. Calculation details

The electronic structure calculation, including band structure and density of states (DOS), was performed using the CASTEP module in Material Studio.⁴⁵ A generalized gradient approximation (GGA) by PBE was adopted to describe the exchangecorrelation energy. The electronic configurations for In, B, S, Na, K, and Eu were 5s and 5p, 2s and 2p, 3s and 3p, 3s, 4s, 5s/ 6s and 4f, respectively, and a cutoff energy of 700 eV was set. The numerical integration of the Brillouin zone was implemented by employing $2 \times 2 \times 4$ Monkhorst–Pack *k*-point sampling. The Fermi level at 0 eV was chosen as the reference.

3. Results and discussion

3.1. Crystal structure

1 adopts a new monoclinic structure type with the space group C2/m (Pearson code mC119.4). There are three In, eight S, eight B, one K, one Na and one Eu sites in the crystallographically independent unit in the structure of **1** (Fig. 2a). Eight kinds of B atoms comprise two types of B₁₂ icosahedra. For the sake of clarity, each B₁₂ icosahedron is dummied into one sphere. Two B(2), two B(3), four B(4) and four B(7) link together to form a B₁₂ icosahedron (type-I) with the B–B dis-



Fig. 2 Crystal structure of **1**: (a) Coordination geometry; (b) $\{[\ln_{3.80}S_{12}]^{12.6-}\}_{\infty}$ polyanionic ribbons along the *b* axis; (C) 3*D* view of the crystal structure along the *b* direction.

tances in the range 1.768(9)–1.806(8) Å. Meanwhile, two B(1), two B(5), four B(6) and four B(8) build a B_{12} (type-II) icosahedron, in which the B–B bond lengths are 1.764(8)–1.805(8) Å. In both cases, there are nine types of B–B distances, showing the B–B bond distance dispersity.

Na, K, and Eu metal elements are surrounded with five, eight, and six S atoms to form a NaS₅ trigonal bipyramid, KS₈ cuboctahedron, and EuS₆ octahedron, respectively. Each B₁₂ icosahedron has twelve nearest S atoms to form the B₁₂S₁₂ cluster, in which each type-I B₁₂ icosahedron is surrounded by two InS₄ tetrahedra and four InS₅ trigonal bipyramids by sharing edges. Whereas each type-II B₁₂ icosahedron is surrounded by four InS₆ octahedra through sharing faces, two InS₄ tetrahedra and four InS₅ trigonal bipyramids by sharing edges. Both types of B₁₂S₁₂ cluster are isolated, and they only connect with InS_x polyhedra. The In(1)S₆ octahedra and In(3) S₅ trigonal bipyramids build two types of *zig-zag* chains and then connect with In(2)S₄ tetrahedra to form {[In_{3.80}S₁₂]^{12.6–}}_∞ polyanionic ribbons extending along the *b* direction (Fig. 2b), which further connect with two types of B₁₂ to build a 3*D* structure (Fig. 2c).

The simplified 3*D* structure graph of **1** viewing along the *b* and *c* directions is depicted in Fig. 3, where K, Na and Eu atoms are omitted for the sake of clarity, and the B_{12} icosahedron, $In(1)S_6$ octahedra, $In(2)S_4$ tetrahedra and $In(3)S_5$ trigonal bipyramid are dummied to one atom, namely *I*-B₁₂, *O*-In(1)S₆, *T*-In(2)S₄, *TP*-In(3)S₅. The connections between the diverse polyhedra can be clearly observed. There are two-types of connections around *I*-B₁₂, one with four *O*-In(1)S₆, four *TP*-In(3)S₅ and two *T*-In(2)S₄, and the other with four *TP*-In(3)S₅ and two *T*-In(2)S₄. The *I*-B₁₂ are isolated from each other, and they are connected by InS_x polyhedra. Each *O*-In(1)S₆ is surrounded by two *I*-B₁₂, two *T*-In(2)S₄, and two *TP*-In(3)S₅, while each *T*-In(2)S₄, and each *TP*-In(3)S₅ is surrounded by two *I*-B₁₂, one *T*-In(2)S₄, and one *O*-In(1)S₆.

Specifically, the coordination diversity of In atoms is fully exhibited in this structure. In(1), In(2) and In(3) atoms coordinate with six, four and five S atoms to form octahedral $In(1)S_6$, tetrahedral $In(2)S_4$ and trigonal bipyramidal $In(3)S_5$ units. The distances from In to the three equatorial and one of the apical S atoms are short (2.4596(14)-2.5778(9) Å); while the distance to the other apical S atom is considerably longer (2.9409(8) Å)(Fig. S2[†]). This longer In-S distance is comparable with those in NaIn₃S₅, Ba₁₈F₁₈In₈S₂₁, Fe_{1.5}Pb_{5.5}In₁₀S₂₂, Ca_{0.76}In_{2.84}S₅ and La4Ag2In4S13 (Table S6[†]). In other In-containing chalcogenides, tetrahedral and octahedral coordination geometries are normally found for the In atom; in contrast, examples of trigonal bipyramidal geometry are very few, including but not limited to γ -In₂Se₃,⁴⁶ Ga_xIn_{2-x}Se₃,⁴⁷ BaRE₂In₂Q₇ (Q = S, Se)⁴⁸ and $K_5In_3P_6Se_{19}$.⁴⁹ In general, a structure containing three In coordination geometries simultaneously is very rare. At present, it's only discovered in K₅In₃P₆Se₁₉.⁴⁹ Hence, 1 is the first chalcogenoborate and the second chalcogenide containing three InS_x coordination geometries.

(b)

When referring to the different In–S polyhedra, the connection between In and S atoms can be described as a highly distorted In(3)S₅ trigonal bipyramid, slightly distorted In(2)S₄ tetrahedron and normal In(1)S₆ octahedron with gradually reduced calculated dipole moments of 18.8529, 9.2955, and 3.9815 D, respectively. They connect with each other to form $\{[In_{3.80}S_{12}]^{12.6-}\}_{\infty}$ polyanionic ribbons (Fig. 2b), which represent a new In–S slab. Differently, the three InSe_x coordination geometries in K₅In₃P₆Se₁₉ are connected with each other by Se(1) atoms to form the $[In_3Se_{13}]^{17-}$ anion (Fig. S2†).⁴⁹

Differently from the arrangement of other $B_{12}Q_{12}$ compounds,^{25,34} the $B_{12}S_{12}$ clusters in **1** are arranged in a cubic closest-packed manner with the center to center distance within 8.987 to 11.857 Å (Fig. S3†).⁵⁰ The cluster anions exhibit their centers of gravity at the Wyckoff positions 2*a* (for type-I B_{12}) and 2*d* (for type-II B_{12}), with distances of almost 1.7 Å to the twelve boron atoms, providing them an inner diameter of 3.4 Å, which is close to that of other inorganic compounds containing B_{12} clusters (Table 2) and indicates the high stability of B_{12} clusters.

As far as we know, there are two-types of connection around B_{12} icosahedra: one is surrounded by six BS₃ units to form $[B_{12}(BS_3)_6]^{8-}$ polyanion (Fig. 4a), while the other one is connected with two InS₆ and six InS₄ units to construct the $[In_8B_{12}S_{30}]^{26-}$ polyanion (Fig. 4b).^{26,35} Different from these two styles, the B_{12} icosahedron in this work adopts a new connection mode with diverse InS_x units to form the $[In_{7.1}B_{12}S_{29}]^{26.7-}$ anion in 1 (Fig. 4c). Among the two known structure types, a family of multinary (A₃X)[MB₁₂(M'Q₄)₃] (A = alkali metal; X = halogen element; M = Ga, In, rare-earth metal; M' = Ga, In) compounds have the maximum relevance to the structure of

Table 2 Different B₁₂ clusters in known chalcogenoborates

Compound	\overline{d} (B–B)/Å	\overline{d} (C–B)/Å	ID	The CE of B ₁₂
$K_{3}Cl[InB_{12}(InSe_{4})_{3}]^{36}$	1.79	1.70	3.40	6[InSe ₄], 4[InSe ₆]
$Ag_2B_{12}Cl_{12}^{50}$	1.78	1.70	3.40	6[AgCl ₆]
Sn ₄ B ₁₂ Se ₁₅ ³¹	1.79	1.70	3.40	$6[SnSe_4], 2[SnSe_6]$
$Cs_8B_{12}(BSe_3)_6^{25}$	1.78	1.70	3.39	6[BSe ₃]
1 (type-I B ₁₂)	1.79	1.71	3.41	$4[InS_5], 2[InS_4]$
1 (type-II B ₁₂)	1.79	1.70	3.40	$4[InS_6], 2[InS_4], 4[InS_5]$

Note: \vec{d} (C–B), ID and CE represent the average values of the B₁₂ gravity's center to B atoms, inner diameter of B₁₂, and chemical environments of B₁₂, respectively.



1.^{33–36} (K₃I)[InB₁₂(InS₄)₃] crystalizes in the NCS hexagonal space group $P6_322$ featuring a 3D honeycomb-like open-framework, providing channels occupied by face-sharing IK₆ octahedral chains.³⁵ Accordingly, 1 features { $[In_{3.80}S_{12}]^{12.6-}$ } polyanionic ribbons constructed by diverse InS_x units, which further connect with two types of B₁₂ icosahedra to form the 3D structure (Fig. 4c). Unlike 1 with two types of B₁₂ icosahedron with two unique B atoms, and each B₁₂ icosahedron is surrounded by two In(1)S₆ octahedra *via* sharing faces and six In (2)S₄ tetrahedra *via* sharing edges (Fig. 4b and c).

The In(1)–S bond distances in the InS₆ unit are 2.680(6) Å and the In(2)-S bond distances in the InS₄ unit are 2.399(6)-2.492(7) Å in $(K_3I)[InB_{12}(InS_4)_3]$, indicating that $In(1)S_6$ octahedra are normal and centrosymmetric (CS). In(1)S₆ octahedra arrange in a parallel manner and $In(2)S_4$ tetrahedra settle orderly at a certain angle. Although all the coordination polyhedra in 1 are distorted, it crystallizes in the CS structure, since all the InS_x units in its structure stack in a back-to-back style, which cancels out their hyperpolarizabilities.^{51,52} Their NCS/CS structures can also be explained by analyzing their structural symmetry. Considering their unit-cell centers, the In atom coordinates with four S atoms to form a highly distorted InS_4 tetrahedron in $(K_3I)[InB_{12}(InS_4)_3]$ with side lengths of 3.854-4.181 Å, whereas in the symmetric center of 1, Na and S atoms connect with each other to form two parallelograms with Na-S distances of 3.261(6) and 3.007(5) Å (Fig. 5).

3.2. Optical properties

The optical band gap of **1** was determined to be approximately 2.26 eV from the result of UV-vis-NIR diffuse-reflectance spectroscopy (Fig. 6), which is consistent with its dark-red color.

3.3. Thermal behavior

The differential scanning calorimetry (DSC) result shows that it undergoes melting upon heating and crystallization upon cooling events (Fig. 7).^{53,54} The inherently high kinetic stability of the B_{12} icosahedron makes it resistant to decomposition reactions at elevated temperatures, and it is thermally stable up to 739 °C.



Fig. 5 The center of the unit cell: (a) parallelograms formed by Na and S in 1; (b) highly distorted InS_4 tetrahedron in $(K_3I)[InB_{12}(InS_4)_3]$.



Fig. 6 UV-vis-NIR diffuse reflectance spectrum of 1.



Fig. 7 DSC curve for 1 measured from room temperature to 1000 $^\circ\text{C}$ under a N_2 atmosphere.

3.4. Theoretical calculations

To better understand its structure, an electronic structure calculation for **1** was performed. The calculated band gap of **1** is 1.08 eV (Fig. 8a). Usually, the calculated band gap is underestimated compared with its experimental one. The density of



Fig. 8 Calculated electronic structure, including band structure (a) and DOS (b). 0 eV is selected as the Fermi level.

Inorganic Chemistry Frontiers

states (DOS) calculation was carried out to observe the orbitals' contribution near the Fermi level (Fig. 8b). Total and Partial DOS show that the top of the valence band is mainly composed of S-3p and minor B-2p orbitals, while the bottom of the conduction band is primarily constituted of In-5s and S-3p orbitals, suggesting that charge transfer between the frontier orbitals is primarily from S 3p to In 5s orbitals. Recalling the case for $(K_3I)[InB_{12}(InS_4)_3]$,³⁴ similar calculation results are available and also verify that these calculations are reliable.

4. Conclusion

In summary, а novel hexanary thioborate KNa_{0.78}Eu_{0.27}In_{3.80}B₁₂S₁₂ (1) was obtained and systematically studied. Its structure features an unprecedented $\{[In_{3.80}S_{12}]^{12.6-}\}_{\infty}$ polyanionic ribbon, two types of B_{12} icosahedra, and diverse InS_x units. 1 is the first thioborate and the second chalcogenide to include InS₄, InS₅ and InS₆ polyhedra in one structure. This work not only provides a novel type of thioborate with a special structure, but also enriches both B and In chemistry. Next, it is proposed to explore its potential structural tolerance for diverse derivatives and physical properties. We hope this work can evoke increasing interest on chalcogenoborates, which really represents an amazing while insufficiently explored material system.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors would like to acknowledge the financial support by the national natural science foundation of China (21771159, 22071212), and the Qinglan project from Yangzhou University.

References

- 1 B. Albert and H. Hillebrecht, Boron: Elementary Challenge for Experimenters and Theoreticians, *Angew. Chem., Int. Ed.*, 2009, **48**, 8640–8668.
- 2 Y. Chi, J. Xu, H. G. Xue, Y. P. Zhang, X. L. Chen, M. H. Whangbo, S. P. Guo and S. Q. Deng, Triple-Kagome-Layer Slabs of Mixed-Valence Rare-Earth Ions Exhibiting Quantum Spin Liquid Behaviors: Synthesis and Characterization of Eu₉MgS₂B₂₀O₄₁, *J. Am. Chem. Soc.*, 2019, **141**, 9533–9536.
- 3 N. S. Hosmane, *Boron Science: New Technologies and Applications*, CRC Press, 2011.
- 4 Y. Chi, H. G. Xue and S. P. Guo, Designing Sulfide Borate as a Novel Type of Second-Order Nonlinear-Optical Material, *Inorg. Chem.*, 2020, **59**, 1547–1555.

- 5 Z. H. Zhang, E. S. Penev and B. I. Yakobson, Two-Dimensional Boron: Structures, Properties and Applications, *Chem. Soc. Rev.*, 2017, **46**, 6746–6763.
- 6 F. Ali, N. S. Hosmane and Y. Zhu, Boron Chemistry for Medical Applications, *Molecules*, 2020, **25**, 828–852.
- 7 Y. Zhu and N. S. Hosmane, Recent Advances and Applications in Boron Chemistry, *Coord. Chem. Rev.*, 2015, **293**, 357–367.
- 8 Z. H. Shi, Y. Chi, M. Yang, W. L. Liu and S. P. Guo, A Series of Chalcogenide Borates $RE_6Ta_2MgQB_8O_{26}$ (RE = Sm, Eu, Gd; Q = S, Se) Featuring a B_4O_{10} Cluster, *Inorg. Chem.*, 2020, **59**, 3532–3536.
- 9 M. Fujimori, T. Nakata, T. Nakayama, E. Nishibori, K. Kimura, M. Takata and M. Sakata, Peculiar Covalent Bonds in α-Rhombohedral Boron, *Phys. Rev. Lett.*, 1999, 82, 4452–4455.
- 10 T. Peymann, C. B. Knobler, S. I. Khan and M. F. Hawthorne, Dodecahydroxy-closo-Dodecaborate(2–), J. Am. Chem. Soc., 2001, 123, 2182–2185.
- 11 O. Conrad, C. Jansen and B. Krebs, Boron-Sulfur and Boron-Selenium Compounds-From Unique Molecular Structural Principles to Novel Polymeric Materials, *Angew. Chem., Int. Ed.*, 1998, **37**, 3208–3218.
- 12 W. L. Li, X. Chen, T. Jian, T. T. Chen, J. Li and L. S. Wang, From Planar Boron Clusters to Borophenes and Metalloborophenes, *Nat. Rev. Chem.*, 2017, **1**, 0071–0080.
- 13 M. F. Hawthorne, *Advances in Boron Chemistry: Special Publication No. 201*, Royal Society of Chemistry, London, 1997.
- 14 J. J. Aihara, Three-Dimensional Aromaticity of Polyhedral Boranes, *J. Am. Chem. Soc.*, 1878, **100**, 3339–3342.
- 15 R. B. King, Three-Dimensional Aromaticity in Polyhedral Boranes and Related Molecules, *Chem. Rev.*, 2001, 101, 1119–1152.
- 16 E. L. Muetterties, J. H. Balthis, Y. T. Chia, W. H. Knoth and H. C. Miller, Chemistry of Boranes. VIII. Salts and Acids of $B_{10}H_{10}^{2-}$ and $B_{12}H_{12}^{2-}$, *Inorg. Chem.*, 1964, 3, 444–451.
- A. A. Kamin and M. A. Juhasz, Exhaustive Cyanation of the Dodecaborate Dianion: Synthesis, Characterization, and X-ray Crystal Structure of [B₁₂(CN)₁₂]²⁻, *Inorg. Chem.*, 2020, 59, 189–192.
- I. B. Sivaev, V. I. Bregadze and S. Sjöberg, Chemistry of closo-Dodecaborate Anion [B₁₂H₁₂]²⁻: A Review, Collect. Czech. Chem. Commun., 2002, 67, 679–727.
- 19 T. Peymann, A. Herzog, C. B. Knobler and M. F. Hawthorne, Aromatic Polyhedral Hydroxyborates: Briding Boron Oxides and Boron Hydrides, *Angew. Chem.*, *Int. Ed.*, 1999, **38**, 1061–1064.
- 20 I. Tiritiris and T. Schleid, Single Crystals of the Dodecaiodo-*closo*-Dodecaborate Cs₂[B₁₂I₁₂]·2CH₃CN (≡Cs-(NCCH₃)₂[B₁₂I₁₂]) from Acetonitrile, *Z. Anorg. Allg. Chem.*, 2001, **627**, 2568–2570.
- 21 E. V. Bukovsky, D. V. Peryshkov, H. Wu, W. Zhou, W. S. Tang, W. M. Jones, V. Stavila, T. J. Udovic and S. H. Strauss, Comparison of the Coordination of $B_{12}F_{12}^{2-}$, $B_{12}Cl_{12}^{2-}$, and $B_{12}H_{12}^{2-}$ to Na⁺ in the Solid State: Crystal

Research Article

- 22 M. Mayer, M. Rohdenburg, V. van Lessen, M. C. Nierstenhöfer, E. Aprà, S. Grabowsky, K. R. Asmis, C. Jenne and J. Warneke, First Steps Towards a Stable Neon Compound: Observation and Bonding Analysis of [B₁₂(CN)₁₁Ne]⁻, *Chem. Commun.*, 2020, **56**, 4591–4594.
- 23 R. T. Boeré, J. Derendorf, C. Jenne, S. Kacprzak, M. Keßler, R. Riebau, S. Riedel, T. L. Roemmele, M. Rühle, H. Scherer, T. Vent-Schmidt, J. Warneke and S. Weber, On the Oxidation of the Three-Dimensional Aromatics [B₁₂X₁₂]²⁻ (X=F, Cl, Br, I), *Chem. Eur. J.*, 2014, **20**, 4447–4459.
- 24 H. F. T. Klare and M. Oestreich, Silylium Ions in Catalysis, *Dalton Trans.*, 2010, **39**, 9176–9184.
- 25 J. Küper, O. Conrad and B. Krebs, Selenoboratoborates [B₁₂(BSe₃)₆]⁸⁻: A New Class of Chalcogen-Substituted Icosahedral Boron Clusters, *Angew. Chem., Int. Ed. Engl.*, 1997, 36, 1903–1904.
- 26 J. Kuchinke, A. Hammerschmidt and B. Krebs, Rb₈[B₁₂(BS₃)₆] and Cs₈[B₁₂(BS₃)₆]: The First Thioboratocloso-Dodecaborates, Solid State Sci., 2003, 5, 189–196.
- 27 A. Hammerschmidt, A. Lindemann, C. Köster and B. Krebs, Na₆[B₁₈Se₁₇]: The First Selenoborato-*closo*-Dodecaborate with a Polymeric Chain Anion, *Z. Anorg. Allg. Chem.*, 2001, 627, 2121–2126.
- 28 A. Hammerschmidt, A. Lindemann, M. Döch and B. Krebs, A Novel Selenoborato-*closo*-Dodecaborate with Different Anion Substitution Patterns, *Z. Anorg. Allg. Chem.*, 2003, 629, 1249–1255.
- 29 A. Hammerschmidt, M. Döch, S. Pütz and B. Krebs, Na₈[B₁₂(BSe₃)₆]: A Novel Selenoborato-*closo*-Dodecaborate, *Z. Anorg. Allg. Chem.*, 2004, 630, 2299–2303.
- 30 A. Hammerschmidt, M. Döch, S. Pütz and B. Krebs, Na₂[B₁₈Se₁₆]: The First 3D Polymeric Selenoborato-*closo*-Dodecaborate, *Z. Anorg. Allg. Chem.*, 2005, 631, 1125–1128.
- 31 D. G. Chica, I. Spanopoulos, S. Hao, C. Wolverton and M. G. Kanatzidis, $Sn_{4-\delta}$, $B_{12}Se_{12}[Q_x]$, Q = Se, Te, a B_{12} Cluster Tunnel Framework Hosting Neutral Chalcogen Chains, *Chem. Mater.*, 2021, 33, 1723–1730.
- 32 A. Hammerschmidt, M. Döch, A. Lindemann, S. Pütz and B. Krebs, Sodium Selenoborato-*closo*-Dodecaborates: Structures and Properties, *Phys. Chem. Glasses: Eur. J. Glass Sci. Technol., Part B*, 2006, 47, 377–380.
- 33 S. P. Guo, G. C. Guo, M. S. Wang, J. P. Zou, H. Y. Zeng, L. Z. Cai and J. S. Huang, A Facile Approach to Hexanary Chalcogenoborate Featuring a 3-D Chiral Honeycomb-Like Open-framework Constructed from Rare-Earth Consolidating Thiogallate-*closo*-Dodecaborate, *Chem. Commun.*, 2009, 4366–4368.
- 34 S. P. Guo, Y. Chi, B. W. Liu and G. C. Guo, Synthesis, Crystal Structure and Second-Order Nonlinear Optical Property of a Novel Pentanary Selenide (K₃I)[InB₁₂(InSe₄)]₃, *Dalton Trans.*, 2016, 45, 10459–10465.
- 35 Z. D. Sun, Y. Chi, H. G. Xue and S. P. Guo, A Series of Pentanary Inorganic Supramolecular Sulfides (A₃X)

 $[MB_{12}(MS_4)_3]$ (A = K, Cs; X = Cl, Br, I; M = Ga, In, Gd) Featuring $B_{12}S_{12}$ Clusters, *Inorg. Chem. Front.*, 2017, 4, 1841–1847.

- 36 S. S. Han, W. D. Yao, S. X. Yu, Y. Sun, A. Gong and S. P. Guo, Salt-Inclusion Chalcogenoborates Containing a $B_{12}Q_{12}$ (Q = S, Se) Cluster Exhibiting a Kleinman-Forbidden Frequency-Doubling Effect, *Inorg. Chem.*, 2021, **60**, 3375–3383.
- 37 M. Sugimori, H. Fukuoka, H. Imoto and T. Saito, Preparation and Crystal Structure of Chromium Silicon Selenide Containing a B_{12} Icosahedron with a Tunnel Structure, *J. Organomet. Chem.*, 2000, **611**, 547–550.
- 38 H. Lin, W. B. Wei, H. Chen, X. T. Wu and Q. L. Zhu, Ration Design of Infrared Nonlinear Optical Chalcogenides by Chemical Substitution, *Coord. Chem. Rev.*, 2020, 406, 213150–213173.
- 39 M. Y. Ran, Z. J. Ma, H. Chen, B. X. Li, X. T. Wu, H. Lin and Q. L. Zhu, Partial Isovalent Anion Substitution to Access Remarkable Second-Harmonic Generation Response: a Generic and Effective Strategy for Design of Infrared Nonlinear Optical Materials, *Chem. Mater.*, 2020, **32**, 5890– 5896.
- 40 M. M. Chen, Z. Ma, B. X. Li, W. B. Wei, X. T. Wu, H. Lin and Q. L. Zhu, $M_2As_2Q_5$ (M = Ba, Pb; Q = S, Se): A Source of Infrared Nonlinear Optical Materials with Excellent Overall Performance Activated by Multiple Discrete Arsenate Anions, *J. Mater. Chem. C*, 2021, **9**, 1156–1163.
- 41 H. Chen, W. B. Wei, H. Lin and X. T. Wu, Transition-metalbased chalcogenides: A rich source of infrared nonlinear optical materials, *Coord. Chem. Rev.*, 2021, **448**, 214154– 214192.
- 42 M. M. Chen, S. H. Zhou, W. B. Wei, X. T. Wu and Q. L. Zhu, Phase Matchability Transformation in the Infrared Nonlinear Optical Materials with Diamond-Like Frameworks, *Adv. Opt. Mater.*, 2021, **10**, 2102123–2102131.
- 43 O. V. Dolomanov, L. J. Bourhis, R. J. Gildea, J. A. K. Howard and H. Puschmann, OLEX2: A Complete Structure Solution, Refinement and Analysis Program, *J. Appl. Crystallogr.*, 2009, **42**, 339–341.
- 44 (a) W. W. Wendlandt and H. G. Hecht, *Reflectance pectroscopy*, Interscience Publishers, New York, 1966;
 (b) G. Kortüm, *Reflectance Spectroscopy*, Springer, 1969.
- 45 S. J. Clark, M. D. Segall, C. J. Pickard, P. J. Hasnip, M. I. Probert, K. Refson and M. C. Payne, First Principles Methods Using CASTEP, *Z. Kristallogr. – Cryst. Mater.*, 2005, 220, 567–570.
- 46 Y. Chi, Z. D. Sun, Q. T. Xu, H. G. Xue and S. P. Guo, Hexagonal In_2Se_3 : A Defect Wurtzite-Type Infrared Nonlinear Optical Material with Moderate Birefringence Contributed by Unique $InSe_5$ Unit, *ACS Appl. Mater. Interfaces*, 2020, **12**, 17711–17717.
- 47 Q. T. Xu, Y. Chi, X. H. Li, W. L. Liu and S. P. Guo, Structural Chemistry and Excellent Nonlinear Optical Properties of a Series of Ternary Selenides Ga_x,In_{2-x}Se₃, *Inorg. Chem.*, 2021, **61**, 431–438.
- 48 W. L. Yin, A. K. Iyer, X. Lin, C. Li, J. Y. Yao and A. Mar, A. Quaternary Chalcogenides BaRE₂In₂Ch₇ (RE = La-Nd; Ch =

S, Se) Containing $InCh_5$ Trigonal Bipyramids, *Dalton Trans.*, 2016, 45, 12329–12337.

- 49 A. Rothenberger, H. H. Wang, D. Chung and M. G. Kanatzidis, Structural Diversity by Mixing Chalcogen Atoms in the Chalcophosphate System K/In/P/Q (Q = S, Se), *Inorg. Chem.*, 2010, **49**, 1144–1151.
- 50 I. Tiritiris and T. Schleid, The Crystal Structure of Solvent-Free Silver Dodecachloro-*closo*-Dodecaborate Ag₂[B₁₂Cl₁₂] from Aqueous Solution, *Z. Anorg. Allg. Chem.*, 2003, 629, 581–583.
- 51 B. W. Liu, X. M. Jiang, H. Y. Zeng and G. C. Guo, [ABa₂Cl][Ga₄S₈] (A = Rb, Cs): Wide-Spectrum Nonlinear Optical Materials Obtained by Polycation-Substitution-Induced Nonlinear Optical (NLO)-Functional Motif Ordering, *J. Am. Chem. Soc.*, 2020, **142**, 10641–10645.
- 52 Z. T. Lu, Z. D. Sun, Y. Chi, H. G. Xue and S. P. Guo, Balanced Second-Order Nonlinear Optical Properties of Adducts CHI₃·(S₈)₃ and AsI₃·(S₈)₃: A Systematic Survey, *Inorg. Chem.*, 2019, 58, 4619–4625.
- 53 B. W. Liu, H. Y. Zeng, X. M. Jiang, G. E. Wang, S. F. Li, L. Xu and G. C. Guo, [A₃X][Ga₃PS₈] (A = K, Rb; X = Cl, Br): Promising IR Non-Linear Optical Materials Exhibiting Concurrently Strong Second-Harmonic Generation and High Laser Induced Damage Thresholds, *Chem. Sci.*, 2016, 7, 6273–6277.
- 54 J. N. Li, W. D. Yao, X. H. Li, W. L. Liu, H. G. Xue and S. P. Guo, A Novel Promising Infrared Nonlinear Optical Selenide KAg₃Ga₈Se₁₄ Designed from Benchmark AgGaQ₂ (Q = S, Se), *Chem. Commun.*, 2021, 57, 1109–1112.